Graphene Oxide as High-Efficient Separation Membrane

Materials: Role of Electrostatic Interaction

Gonggang Liu^a, Hongqi Ye^a, Antai Li^a, Chenyuan Zhu^a, Heng Jiang^a, Yong Liu^{b,c}, Kai Han^{b,c*}, Yonghua Zhou^{a*}

^a. School of Chemistry and Chemical Engineering, Central South University, Changsha 410083, China.

^b. State Key Laboratory of Powder Metallurgy, Central South University, Changsha 410083, China

^c. Powder Metallurgy Research Institute, Central South University, Changsha 410083, China

Abstract: Graphene oxide (GO) membranes represent a next generation of high-flux, ultra-lightweight and energy-efficient membranes for molecular and ionic separation in aqueous solution. In this work, we fabricate free-standing GO membranes with tunable thickness via facile vacuum filtration process. The effect of electrostatic interaction on the separation performance of GO membrane for organic dyes was demonstrated. It is observed that GO is negatively charged in a wide pH range of 1-12 and its surface charge density significantly varied with pH of aqueous solution. The electronegative GO membrane exhibits much higher rejection rate for electronegative organic dyes than that for electropositive molecules. Furthermore, the rejection rate and the strength of electrostatic interaction are directly related. In addition, the rejection behaviors of GO membranes for inorganic salts with different charge or ionic strength are explored as well. The experimental data are fitted well with the theoretical model based on Donnan equilibrium. Our results indicate that GO membranes could be promising candidate for water treatment and desalination application. And adjusting the surface charge density of GO and filtrated molecules is an effective way to achieve high separation performance (e.g. rejection rate).

Corresponding author: Kai Han, Yonghua Zhou

Fax: +86-731-88879616; Tel: +86-731-88879616;

E-mail: hankai@csu.edu.cn (Kai Han); zhouyonghua@csu.edu.cn (Yonghua Zhou)

1. Introduction

Strong, lightweight graphene oxide (GO) membranes have been extensively investigated in separation related applications, such as desalination, water treatment and energy production [1-5]. Due to the excellent characteristics including good hydrophilism, outstanding mechanical strength, ultrathin lamellar structure and superior flexibility [6-9], GO and GO-based functional materials are considered to be an ideal candidate for nanoscale filtration and molecule/ionic sieving [10-14]. As for nanofiltration membranes, physical sieving (size exclusion) and electrostatic interaction (charge effect) are two main separation mechanisms [15-17]. To date, there already have many reports about the physical sieving effect of GO and GO-based functional membranes on separation performance [18-20]. However, the thoroughly understand of the work principles for GO membranes in aqueous solution is in urgent need to demonstrate. Other potential separation mechanism (e.g., electrostatic interaction) is still needed to be fundamentally elucidated.

Herein, we firstly investigated the effect of electrostatic interaction on GO membrane for rejecting electric organic dyes. It is found that the electronegative GO membrane exhibits much higher rejection rate for electronegative organic dyes than that for electropositive molecules. Moreover, the rejection performance of GO membranes for inorganic ions with different valence and concentration was explored and the results fitted well to Donnan equilibrium model. Both the results of dyes and ions reveal that GO membrane is a typical nanofiltration membrane, and the electrostatic interaction shows a significant influence on the separation performance.

The results indicate that GO membranes could be promising alternative separation materials for water treatment and desalination application. And adjusting the surface charge density of GO and filtrated molecules is an effective way to achieve high separation performance, especially for the rejection rate.

2. Experimental

2.1 GO and GO membrane preparation

GO was prepared following the modified Hummers method, as shown in our previous work [21]. The as-prepared GO was stored as aqueous suspension of 0.4 mg/mL. GO membranes were fabricated by vacuum filtration of the as-prepared GO suspension through a porous cellulose membrane (47 mm in diameter, 0.45 μm pore size). Typically, 2 ml of GO dispersion was filtrated to fabricate GO membranes, and it was stabilized for 30min under a pressure of 0.3 MPa by nitrogen filling.

2.2 Membrane flux and rejection rate tests

Water flux and rejection performance of the GO membrane were investigated using a dead end membrane filtration system as shown in Fig. S1. It consists of a feed tank pressurized with a nitrogen cylinder. The pressure can be adjusted by nitrogen filling. The pH of GO suspension and filtrate was adjusted from 1 to 11 using HCl and NaOH solutions. To characterize membrane rejection performance, GO membrane (2 ml of 0.2 mg/mL GO suspension) for various concentrations of electric organic dyes feed solutions were tested. The tested dyes include Congon red, Indigo carmine, Rhodamine B and Methylene Blue. In addition, GO membrane (2 ml of 0.4 mg/mL

GO suspension) for various concentrations of NaCl, Na₂SO₄ and Na₃PO₄ were tested. The dye concentration of the feed was determined by a UV-spectrometer (UV-752N). And the ion concentrations were tested by a conductivity meter (DDS-11A). The rejection rate was calculated through the definition in reference [11] using the following equation:

$$R = \left(1 - \frac{C_p}{C_0}\right) \times 100\%$$

Where R is rejection rate, C_p and C_0 are the concentration of the molecules or ions in the permeates and their concentrations in the original solutions, respectively. The water flux was determined by the volume gained from the permeation test.

2.3 Materials characterization

The charge properties of GO suspension at different pH were analyzed using Zeta potentials measurement (Zetaplus, Brookhaven, USA). Morphology of the membranes was observed by a scanning electronic microscope (Nova, Nano SEM230, USA). Transmission electron microscopy (TEM) was carried out on JEM-2100F. X-ray photoelectron spectroscopy (XPS) analysis was conducted on Thermo Scientific ESCALAB 250Xi equipped with an electron flood gun and a scanning ion gun, using the Al K α radiation (1486.6 eV) as the excitation source.

3. Results and discussion

Fig. 1 shows the morphologies of the as-prepared GO sheets and the stacked GO membrane. As shown in Fig. 1(a, b), GO sheet is obviously flaky and wrinkle-like. When they are assembled to membrane, GO sheets ripple a little. And the formed

rippled sheets are the filtering channel for organic molecule and inorganic ions as shown in Fig. 1c. The GO membrane formed using 2 ml of GO suspension (0.2 mg/mL) has a typical thickness of about 200 nm as shown in Fig. 1d. The XRD result of as-prepared GO membrane was as shown in Fig. S2. The characteristic peak of GO membrane was observed at 9.86° , and its d-spacing was 0.896 nm according Bragg formula.

Fig. 1. The morphologies of the as-prepared GO sheets (a, b) and the corresponding GO membranes (c, d)

The Zeta potentials of GO suspension at pH values ranged from 1 to 11 are shown in Fig. 2. It reveals that the surface charge density of GO strongly depends on pH value. This can be ascribed to the protonation and deprotonation process of carboxyl groups on GO sheets. It is found that GO is able to maintain negatively charged over a wide pH range of 1-11, while the surface charge density varies. At pH 8, GO sheets

exhibit the highest negative charge density. However, when pH value exceeds 8, the value of Zeta potential increased, which means the decrease of the surface negative charge density. It is probably caused by the ionic screening effect. With the increasing pH, the content of ion is increased and part of these ions could enter into GO layers. The counter ion was absorbed in GO surface, and the charge on GO surface was neutralized.

Fig. 2. Zeta potentials of GO at different pH in aqueous solution.

The GO membrane separation performance was evaluated by rejecting electronegative Congon red at varied pH condition as shown in Fig. 3a. It is shown that pH value has a significant impact on the rejection and permeation of Congon Red through GO membrane. It is known that as for nanofiltration, the electrostatic interaction always play an important role as well as the physical sieving. When pH value increases from 1 to 6, the negative charge density on GO sheets is increased as shown in Fig. 2. Both the repulsion forces between GO sheets and the repulsion force between Congon Red molecule and GO sheets are enhanced. The former leads to the

increase of the inter-spacing which is beneficial to permeation, while the latter results in the rejection of Congon Red molecule. With the increase of the charge density of GO sheets, the expanded inter-spacing between GO sheets overlap the electrostatic repulsion between Congon Red molecule and GO sheets. Therefore, a decreased rejection and an increased flux are observed in Fig. 3a. When pH value increases further from 6 to 8, the inter-spacing of GO sheets reach the maximum at pH 6 and it does not increase anymore. However, the repulsion action between GO sheets and Congon Red molecule are increased because of the constantly increased negative charge density on GO sheets. As a result, an increased rejection and decreased flux are observed in the range of pH value 6 to 8. As pH value exceeds 8, the charge density of GO is decreased due to ionic screening effect [6]. As a result, a shrank inter-spacing of GO membrane leads to the decrease of rejection and increase of flux. To further understand the effect of pH value on inter-spacing of GO, XRD was performed and the interlayer spacing was calculated by Bragg equation, as shown in Fig. S3. It's obvious the interlayer spacing of GO membranes has a minute fluctuation from 0.861 to 0.896 nm with different pH values. The XRD results were basically consistent with supposition in the above analysis.

In addition, we also investigated the effect of GO membrane thickness on the rejection rate and flux for Congon Red, as shown in Fig. 3b. Since the thickness of the GO membranes can be tuned by just controlling the content of the filtrated GO aqueous suspension, we directly studied the effect of GO content in the membrane. It is obvious with the increasing content of GO, the rejection rate was increased and the

flux decreased, respectively. And the results are consistent with the previous reported work [10].

Fig. 3 (a) GO membrane separation performance for Congon Red at varied pH condition; (b) Flux and rejection rates for separating a Congon Red solution by GO films fabricated with different content at pH of 6.

In order to understand the electrostatic interaction effect of GO membrane in

separation process, UV radiation treatment is used to remove the majority of oxygenic groups on GO membrane to obtain reduced GO (RGO) membrane. As shown in Fig. S4 and Fig. S5, most of the oxygen-containing groups of the treated GO membrane are successfully removed with the color from brown to black. The RGO membrane separation performance for Congon Red is shown in Fig. S6. Compared with GO membrane, the rejection rate and flux of RGO membrane are almost constant at various pH value, due to the elimination of electrostatic interaction effect.

Since electrostatic interaction is depending on the charge density of GO surface and organic molecules, the separation performance of GO membrane can be affected not only by modulating the surface charge density of GO membrane, but also by changing the charge density of filter materials. For comparison, the charge properties of dyes Congon Red and Rhodamine B are illustrated in Fig. S7. As expected, GO membrane exhibits completely different performance for the electronegative dyes (Congon Red and Indigo Carmine) and electropositive dyes (Rhodamine B and Methylene Blue) as shown in Fig. 4. The rejection rate of GO membrane for electronegative dyes is much higher than that for electropositive ones at the same pH of 7. Though their molecular weight is not far off, ranging from 466 to 696 Da, the rejection rates are largely different. This can mainly be ascribed to the electrostatic interactions between membranes and the dye molecules. Therefore, the charge property of the filter material also greatly affects the separation performance of GO membrane.

Fig. 4. GO membrane separation performance for various dyes with different valance.

As for organic dyes, it is not easy to exactly determine the charge density difference between those with the same charge property. To illustrate the electrostatic effect caused by the charge density difference of the filter materials, the GO membrane separation performance for inorganic salts (NaCl , Na_2SO_4 , Na_3PO_4) were investigated. Here, the high ion valence can be viewed as high charge density. As shown in Fig. 5a, GO membrane exhibits a higher rejection for the higher valence ion than for the lower one ($\text{PO}_4^{3-} > \text{SO}_4^{2-} > \text{Cl}^-$). It is worthy to point out here is that as the size of inorganic ion is much smaller than the d-spacing of GO layers, the effect doesn't play a leading role. And the ionic radius of Cl^- , SO_4^{2-} and PO_4^{3-} were 0.181, 0.215 and 0.223nm, respectively, which show not obvious difference. Hence, the size effect of inorganic ion was not considered when discussing the electrostatic effect of ion with different charge densities.

Fig. 5 (a) The rejection performance of GO membrane for NaCl, Na₂SO₄, and Na₃PO₄ with different concentrations; (b) Rejection rates for separating inorganic salts by GO films fabricated with different content

Donnan equilibrium is a common model for predicting process performance of charge mosaic membrane [22]. In terms of Donnan equilibrium model of single salt solution, the relationship between the ion concentration on the GO membrane and that in the GO membrane can be expressed by simplified formula (1-a) as follows [23].

$$\frac{C_B^m}{C_B} = \left(\frac{|Z_B|C_B}{|Z_B|C_B^m + \Delta C_X^m} \right)^{|Z_B||Z_A|} \quad (1-a)$$

Where C_B^m and C_B represent the negative ion concentration in the GO membrane and the negative ion concentration on the surface of GO membrane, respectively. Z_A and Z_B represent the valence of positive ion and the valence of negative ion, respectively. ΔC_X^m is a constant value, which is fixed charge on GO membrane. In terms of NaCl, Na₂SO₄, Na₃PO₄ solutions, equation (1-a) can be simplified to (1-b), (1-c), and (1-d), respectively.

$$\frac{C_B^m}{C_B} = \frac{C_B}{C_B^m + \Delta C_X^m} \quad (1-b)$$

$$\frac{C_B^m}{C_B} = \left(\frac{2C_B}{2C_B^m + \Delta C_X^m} \right)^2 = \frac{C_B}{C_B^m + \frac{\Delta C_X^m}{2}} \cdot \frac{C_B}{C_B^m + \frac{\Delta C_X^m}{2}} \quad (1-c)$$

$$\frac{C_B^m}{C_B} = \left(\frac{3C_B}{3C_B^m + \Delta C_X^m} \right)^3 = \frac{C_B}{C_B^m + \frac{\Delta C_X^m}{3}} \cdot \frac{C_B}{C_B^m + \frac{\Delta C_X^m}{3}} \cdot \frac{C_B}{C_B^m + \frac{\Delta C_X^m}{3}} \quad (1-d)$$

For electronegative GO membrane, ΔC_X^m is a positive number. C_B^m/C_B reflects the permeating ability of ion through GO membrane. Higher value of C_B^m/C_B indicates lower rejection. Comparing the three formula (1-b), (1-c) and (1-d), we can found that C_B^m/C_B (NaCl) > C_B^m/C_B (Na₂SO₄) > C_B^m/C_B (Na₃PO₄). That is to say, GO would deliver higher rejection for the ion with higher valence.

Besides, it is also noted that the rejection rate decreased with the increase of salt concentration as shown in Fig. 5a. The charge density of GO membrane surface is

getting higher with the increasing concentration of salt ion. Then it attracts more counter-ions into the solution inside the membrane pores. As such, the presence of more ions of similar charges around the target ion lowers its interaction energy with its image charge on the membrane surface [24]. It weakens concentration gradient of GO membranes. The lessened Donnan charge effect finally caused the decreased rejection. It could be also interpreted by the model. If the ion concentration is increased and the concentration gradient in and on the GO membrane are assumed to be ΔC_B^m and ΔC_B , formula (1-b) will be turned to formula (1-e). As ΔC_B^m is much smaller than ΔC_B due to the physical sieving and electrostatic interaction effects, the value of $C_B^{m'}/C_B'$ will be larger than C_B^m/C_B . For formula (1-c) and formula (1-d), the same results could be obtained. That means increased ion concentration will lead to the decrease of rejection rate. Therefore, considering the effect of ion valence and concentration on GO membrane, Donnan equilibrium model is fitted well with the experimental results as shown in Fig. 5a.

$$\frac{C_B^{m'}}{C_B'} = \frac{C_B + \Delta C_B}{C_B^m + \Delta C_B^m + \Delta C_X^m} \quad (1-e)$$

In addition, GO membranes thickness also has a notable influence on its rejection rate for inorganic salts, and the result was as shown in Fig. 5b. With increasing GO membranes thickness, the rejection rates were increased. And the rejection rates were hard to improve a lot when the GO membranes thickness was increased in some degree. We also studied on the separation performance for inorganic salts at different pH values (from pH 4-11), as shown in Fig. 6. The rejection rate of salts have similar trends as that of organic dyes, but the trends is not so obvious as that of organic dyes,

especially for NaCl. In our opinion, it is mainly because the size of salts is much smaller than that of dye molecules, and the effect of the GO interlayer spacing resulting from pH was less.

Fig. 6 the rejection rate of salts at different pH values (from pH 4-11)

All the results illustrated that GO membrane is a typical nanofiltration membrane considering its obvious charge-dependent property. Both the electrostatic interaction inner GO sheets and the electrostatic interaction between GO membrane and the filter materials, play important roles for the separation performance of GO membrane. The transport model of organic dye molecule or inorganic ions in GO membranes is finally proposed to simply understand the separation mechanism based on charge effects, as shown in Fig. 7. As the presence of carboxyl groups on GO sheets, there are negative charges distributed among GO sheets which block organic dye molecule or inorganic ions through pores of GO membrane due to electrostatic repulsion.

Fig. 7. The scheme of the separation mechanism of electronegative material by GO membrane.

4. Conclusions

The electrostatic interaction effect on the separation performance of GO membrane was investigated in this study. The surface negative charge density of GO membrane can be modulated by changing the pH condition. And the electronegative GO membrane exhibits a higher rejection for electronegative organic dyes than for those electropositive. In addition, the rejection increases with the increased charge density on GO membrane and the filter materials. All the results illustrated that GO membrane is a typical nanofiltration membrane. Both the electrostatic interaction inner GO sheets and the electrostatic interaction between GO membrane and the filter material, are important for the separation performance of GO membrane, which can be adjusted not only by modulating the surface charge density of GO membrane, but

also by changing the charge density of filter materials. Therefore, besides controlling pore size, this study also provides us one strategy to design efficiency GO membranes via electronic effect for separation application, such as water treatment and desalination.

Acknowledgements

The project was supported by State Key Laboratory of Powder Metallurgy (Central South University, Changsha, China). Materials characterization was financially supported by the Open-End Fund of the Valuable and Precision Instruments of Central South University. Kai Han is funded by China Postdoctoral Science Foundation (2015M582343) and Postdoctoral Foundation from Central South University. Hongqi Ye and Yonghua Zhou thank the financial support from the National Science Foundation of China (No. 21276284), the Research Foundation for CSU Teachers (2014JSJJ020). Gonggang Liu acknowledges the Fundamental Research Funds for the Central Universities of Central South University (No. 2015zzts019).

References

- [1] Joshi RK, Carbone P, Wang FC, Kravets VG, Su Y, Grigorieva IV, et al. Precise and ultrafast molecular sieving through graphene oxide membranes. *Science* 2014; 343(6172): 752-754.
- [2] Mahmoud KA, Mansoor B, Mansour A, Khraisheh M. Functional graphene nanosheets: The next generation membranes for water desalination. *Desalination* 2015;

356: 208-225.

[3] Abo NFD, Chong JY, Wang B, Mattevi C, Li K. Graphene oxide membranes on ceramic hollow fibers-microstructural stability and nanofiltration performance. *J. Membr. Sci.* 2015; 484: 87-94.

[4] Huang Y, Li H, Wang L, Qiao Y, Tang C, Jung C, et al. Ultrafiltration membranes with structure-optimized graphene-oxide coatings for antifouling oil/water separation. *Adv. Mater. Interfaces* 2014; 2(2): 1400433-1400440.

[5] Sun P, Zheng F, Zhu M, Wang K, Zhong M, Wu D, et al. Realizing synchronous energy harvesting and ion separation with graphene oxide membranes. *Sci. Rep.* 2014; 4: 5528-5532.

[6] Yu PT, Paul DR, Tai SC. Free-standing graphene oxide thin films assembled by a pressurized ultrafiltration method for dehydration of ethanol. *J. Membr. Sci.* 2014; 458(9): 199-208.

[7] Vadukumpully S, Paul J, Mahanta N, Valiyaveetil S. Flexible conductive graphene/poly(vinyl chloride) composite thin films with high mechanical strength and thermal stability. *Carbon* 2011; 49(1): 198-205.

[8] Suk ME, Aluru NR. Water transport through ultrathin graphene. *J. Phys. Chem. C* 2010; 114(10): 1590-1594.

[9] Paliotta L, Bellis GD, Tamburrano A, Marra F, Rinaldi A, Balijepalli SK, et al. Highly conductive multilayer-graphene paper as a flexible lightweight electromagnetic shield. *Carbon* 2015; 89: 260-271.

[10] Huang H, Mao Y, Ying Y, Liu Y, Sun L, Peng X. Salt concentration, pH and

pressure controlled separation of small molecules through lamellar graphene oxide membranes. *Chem Commun* 2013; 49(53): 5963-5965.

[11] Gao SJ, Qin H, Liu P, Jin J. SWCNT-intercalated GO ultrathin films for ultrafast separation of molecules. *J. Mater. Chem. A* 2015; 3: 6649-6654.

[12] Huang H, Song Z, Wei N, Shi L, Mao Y, Ying Y, et al. Ultrafast viscous water flow through nanostrand-channelled graphene oxide membranes. *Nature Commun.* 2013; 4(4): 345-350.

[13] Han Y, Xu Z, Gao C. Ultrathin Graphene Nanofiltration Membrane for Water Purification. *Adv. Funct. Mater.* 2013; 23(29): 3693-3700.

[14] Tsetseris L, Pantelides ST. Graphene: an impermeable or selectively permeable membrane for atomic species. *Carbon* 2014; 67(1): 58-63.

[15] Gilron J, Gara N, Kedem O. Experimental analysis of negative salt rejection in nanofiltration membranes. *J. Membr. Sci.* 2001; 185: 223-236.

[16] Artug G, Hapke J. Characterization of nanofiltration membranes by their morphology, charge and filtration performance parameters. *Desalination* 2006; 200(1): 178-180.

[17] Wang XL, Shang WJ, Wang DX, Ling W, Tu CH. Characterization and applications of nanofiltration membranes: state of the art. *Desalination* 2009; 236: 316-326.

[18] Cohentanugi D, Grossman JC. Water desalination across nanoporous graphene. *Nano Letters* 2012; 12(7): 3602-3608.

[19] Cohen-Tanugi D, Grossman JC. Nanoporous graphene as a reverse osmosis

membrane: recent insights from theory and simulation. *Desalination* 2015; 366: 59-70.

[20] O'Hern SC, Boutilier MSH, Idrobo JC, Song Y, Kong J, Laoui T, et al. Selective Ionic Transport through Tunable Subnanometer Pores in Single-Layer Graphene Membranes. *Nano Letters* 2014; 14(3): 1234-1241.

[21] Han K, Liu Z, Shen JM, Lin YY, Dai F, Ye HQ. A free-standing and ultralong-life lithium-selenium battery cathode enabled by 3D mesoporous carbon/graphene hierarchical architecture. *Adv. Funct. Mater.* 2015; 25: 455-463.

[22] Vezzani D, Bandini S. Donnan equilibrium and dielectric exclusion for characterization of nanofiltration membranes . *Desalination* 2002; 149: 477-483.

[23] Fan GD, He QC, Liu JD, Zhang HQ, Wan YZ. Study on Donnan Equilibrium Model of Charge-mosaic membrane. *Chinese Journal of Zhengzhou University* 2002; 23(4): 98-101.

[24] Fadaei F, Hoshyargar V, Shirazian S, Ashrafizadeh SN. Mass transfer simulation of ion separation by nanofiltration considering electrical and dielectrical effects. *Desalination* 2012; 284(2): 316-323.