**A Mechanistic Basis for the Effects of Mn Loading on C₂₊ Oxygenates
Synthesis Directly from Syngas over Rh-MnO_x/SiO₂ Catalysts**

Wei Mao, Junjie Su, Zhengpai Zhang, Xin-Chao Xu, Donglong Fu, Weiwei Dai, Jing
Xu*, Xinggui Zhou and Yi-Fan Han*

*State Key Laboratory of Chemical Engineering, East China University of Science and
Technology, Shanghai 200237, China*

*E-mail: yifanhan@ecust.edu.cn; xujing@ecust.edu.cn

Tel: +86-21-64251928. Fax: +86-21-64251928

Abstract

Kinetics of the synthesis of C_{2+} oxygenates directly from syngas was investigated over a series of Rh-MnO_x/SiO₂ catalysts (atomic ratio of Mn/Rh = 0, 0.5 and 5.0). It was evidenced that the activation energies for C_{2+} oxygenates changed little when introducing MnO_x, while the apparent activation energies for hydrocarbons, especially methane, increased remarkably. Kinetic parameters indicate that the formation of hydrocarbons can be suppressed in the presence of MnO_x. In the meantime, the reaction orders with respect to different products were also altered with the variation of MnO_x loadings. In accordance with in situ DRIFTS, we found that two new active sites on Rh surfaces resulting from the Rh-MnO_x interaction might be responsible for the enhancement of reaction rates and the selectivity to C_{2+} oxygenates. However, the over-loading of MnO_x leads to a decrease in the number of active sites.

Key words: *Rhodium, CO hydrogenation, C_{2+} oxygenates, intrinsic kinetics, syngas, MnO_x promotional effect, mechanism*

1. INTRODUCTION

The synthesis of liquid fuels based on non-oil fossil resources (coal, biomass and natural (shale & tight) gas) from CO hydrogenation has been attracting to industry since 1920s. But it was not until 1970s since Bhasin and Ellgen (Bhasin et al., 1978) reported that C_{2+} oxygenates (ethanol, acetaldehyde and acetic acid) could be produced through this process over particular supported metal catalysts under well-controlled conditions. Among those products, acetaldehyde and acetic acid can be transferred into ethanol through a sequential catalytic hydrogenation. Since ethanol can be used as a fuel additive or a fuel alternative due to its high octane number, such a process has been regarded as an effective pathway for the clean utilization of non-oil fossil fuels.

Recent reviews show that several types of catalysts have been investigated for this process, including rhodium (Rh)-based catalysts, molybdenum sulfide-based catalysts, modified Fischer-Tropsch (F-T) catalysts and modified methanol synthesis catalysts (Farrell et al., 2006; Spivey and Egbebi, 2007; Subramani and Gangwal, 2008; Zaman and Smith, 2012). Among those catalysts, supported Rh catalysts (usually ca. 5.0 wt% Rh) exhibited higher selectivity, especially to alcohols; however, they are still unfeasible for practical applications because of the high cost of Rh and relatively low catalytic efficiency.

In order to reduce the consumption of Rh and maximize the catalytic efficiency over the catalyst, various electronic promoters, such as Li (Schwartz et al., 2011), V (Gao et al., 2009a; Gao et al., 2009b), La (Subramanian et al., 2010), Fe (Chen et al., 2011), and Mn (Yin et al., 2003) were investigated. Previous studies have demonstrated that the performance of Rh catalysts could be enhanced significantly with the modification of MnO_x . Lisitsyn (Lisitsyn et al., 1990) and Sachtler (Sachtler

and Ichikawa, 1986) proposed that MnO_x might boost CO dissociation through the formation of tilted CO adsorbed at the interface of Rh- MnO_x . van den Berg (van den Berg et al., 1985) and Ojeda (Ojeda et al., 2004) suggested that the MnO_x might act as an electron-withdrawing promoter, which partially oxidizes the Rh atoms at the interface of Rh- MnO_x to enhance the CO insertion in the aim reaction.

The Goodman group (McClure et al., 2011) has demonstrated that the optimum size of Rh particles was ~2.5 nm for CO hydrogenation over a model Rh/ SiO_2 catalyst. By DFT calculations, Choi et al. (Choi and Liu, 2009) demonstrated that CO hydrogenation was impeded due to the strong Rh-CO bond on Rh(111), which depressed the formation of ethanol. More recently, Ma et al. (Ma et al., 2011) proved that MnO_x could stabilize both intermediates and reaction products. However, due to the so-called “material gap” from model to technical catalysts, those assertions are hard to be a guidance for the design of industrial or technical catalysts. Furthermore, despite the intensive kinetic studies of F-T synthesis, the intrinsic kinetics of C_{2+} oxygenates synthesis from syngas over Rh based catalysts under real reaction conditions (250-300°C, 2.0-5.0MPa) have still been rarely reported.

In the present study, as a part of the efforts to the mechanistic investigation of the aiming reaction system, the intrinsic kinetics for C_{2+} oxygenates synthesis directly from syngas was studied using a series of Rh- $\text{MnO}_x/\text{SiO}_2$ catalysts with a fixed Rh loading and different MnO_x loadings. We aim to reveal the effects of different MnO_x loadings on the performance of Rh catalysts. The kinetic measurements of CO hydrogenation in the temperature range 230-290°C were carried out under real reaction conditions. Finally, with the combination of catalyst structures and kinetic parameters, the structure-performance relationship, in particular, the Rh catalytic property promoted by MnO_x , was discussed.

2. EXPERIMENTAL SECTION

2.1 .Catalyst preparation

For the catalyst preparation, aqueous solutions of $\text{Rh}(\text{NO}_3)_3$ (Heraeus) and $\text{Mn}(\text{NO}_3)_2$ (Sinopharm Group) were used as precursors while silica gel (Qingdao Makall Group, BET surface area of $300 \text{ m}^2/\text{g}$) were used as a support. Generally, silica gel was first washed by 1.0 mol/L nitric acid, and then ground and sieved to desired granularity (20-40, 40-60, 60-80, 80-100 mesh) followed by washing with the ultra-pure water until neutral to remove any metal impurities. Finally, the silica gel was dried and calcined in an oven at 400°C for 3 h before used as the catalyst support. Catalysts were prepared by co-impregnation to incipient wetness of the purified silica gel with the aqueous solution of $\text{Rh}(\text{NO}_3)_3$ and $\text{Mn}(\text{NO}_3)_2$ according to the calculated atomic ratios (1 ml solution per gram of silica gel). After the impregnation, mixtures were dried overnight at 100°C and then calcined in an oven at 400°C for 4 h with a ramping rate of $2^\circ\text{C}/\text{min}$. All the catalysts were denoted as xRh-yMn, where x and y represent the weight fraction of each Rh and Mn, respectively. The loading amount of Rh was set at 1.5 wt% for comparison with the literatures. (Gao et al., 2009a; Mo et al., 2009; Yu et al., 2012, 2013). The actual metal loading was measured by ICP-MS (Perkin-Elmer NexION 300).

2.2. Catalyst characterization

2.2.1. H_2 Chemisorption

The dispersion of Rh particles was determined by H_2 chemisorption using a Micromeritics AutoChem II 2920 catalyst characterization system (USA). Prior to the measurement, ca. 0.1g catalyst was degassed in an Ar flow (30 mL/min) at 120°C for 2h and then reduced at 350°C in a H_2 flow (30 mL/min) for 2 h, followed by flushing with Ar (30 mL/min) at 380°C for 2 h to remove any physically or chemically

adsorbed impurities. After cooling down to 40°C in the same Ar flow, H₂ uptake was measured by introducing pulses of H₂ with a quantitative loop into the Ar flow by a six-way valve. The pulses were continued until no further uptake of H₂ was detected. The amount of chemisorbed H₂ was obtained by extrapolating the total adsorption isotherm to zero pressure, and Rh dispersion (Rh_s/Rh_{total}) was calculated subsequently with assuming $H/Rh_s = 1$.

2.2.2 *In situ Diffuse Reflectance Infrared Fourier Transform Spectroscopy (DRIFTS)*

A Perkin Elmer Spectrum 100 FTIR spectrometer equipped with a Harrick Praying Mantis cell was employed for the IR study. About 50 mg catalyst was ground and placed into the sample cup. Ultrahigh purity Ar, H₂ and CO (99.999%, Shanghai WOG Gas Equipment Co., Ltd.) used in the DRIFTS study was purified by a de-oxygen trap and the flow rate were controlled by mass flow controllers. Prior to the experiment, the sample was reduced online at 350 °C under pure H₂ (30 mL/min) for 2 h, followed by Ar (30 mL/min) flushing at 350 °C for 1 h. Then, the background spectrum was taken at 270 °C. Afterwards CO/H₂/Ar flow was introduced into the cell and the infrared spectra were taken at 4 cm⁻¹ resolution at 270 °C. The flow rate and composition of the gas mixtures for CO/H₂ co-adsorption were 30 mL/min of 3.3%CO/6.6%H₂/Ar.

2.3. *Kinetic measurement*

Kinetic measurements were carried out in a continuous stainless steel fixed-bed micro-reactor with a length of 450 mm and an inner diameter of 5 mm, respectively. Three mass flow controllers were used to adjust automatically the flow rate of the inlet gases (H₂ (99.999%), N₂ (99.999%), and syngas with different CO/H₂ ratios, Shanghai WOG Gas Equipment Co., Ltd.). After reaching the specified temperature through a preheater, the gas was introduced into the reactor, which was placed inside a

tubular furnace. The reaction temperature was monitored by a K-type thermocouple inserted into the catalyst bed, which located in the middle of the reactor. A back pressure regulator was placed at the end of the pipeline to control the reaction pressure in the range 0.1-10.0 MPa. The conversion of CO was kept below 10.0% in order to ensure a differential condition. The external/internal diffusion effects were ruled out following the procedures introduced by previous studies (Madon and Boudart, 1982).

Prior to the reaction, the catalyst was first reduced in pure H₂ at 0.5 MPa, 350°C for 2 h. Then, the catalyst was cooled down to the reaction temperature (270°C) in the H₂ flow. The reaction was run in the mixed gas of H₂/CO/N₂ at a total pressure of 3.0 MPa with different CO, H₂ and N₂ partial pressures: 0.9 MPa H₂, 0.23-1.8 MPa CO, rest N₂; 0.54 MPa CO, 0.27-2.16 MPa H₂, rest N₂.

Before kinetic measurements, a blank test was done with 0.2 g purified SiO₂ sample. It could be inferred that less than 0.1% conversion of CO was detected over SiO₂ (diluter) under reaction conditions (30% CO, 60% H₂ and 10% N₂, 3.0MPa, GHSV of 3500 h⁻¹, 290 °C), indicating that the potential effects from the reactor wall and SiO₂ were excluded. In the meantime, the catalytic test for 1.0Mn/SiO₂ was also performed under the same reaction conditions. The result showed that 1.0Mn/SiO₂ was not active for CO hydrogenation, indicating that Mn only acted as a promoter in the catalysts.

All the components in the effluent gas, including syngas, paraffins, olefins, carbon dioxide and oxygenated compounds (alcohols, acetaldehydes and acetic acid), were analyzed with an online gas chromatograph (Shanghai Ruimin GC2060) equipped with one thermal conductivity detector (TCD) and two flame ionization detectors (FID) using Ar as the carrier gas. A capillary column (HP-PLOT-Q)

connected to one FID was used to analyze hydrocarbon products and oxygenated compounds. CO₂ was separated by a 6-foot long TDX-01 packed column and detected by the other FID through a methanation furnace at 360 °C. The unreacted syngas was determined using a 6-foot long 5A Molecular Sieve packed column connected to TCD. The oven temperature was held at 60 °C for 5 min and then ramped up to 220 °C at 10 °C/min, for 5 min. All the experimental data were obtained after reaction 16 h.

2.4. Calculations

The absolute reaction rate of CO hydrogenation (r_{CO}) is expressed as eq 2.

$$r_{CO} = \frac{v_{CO,in} \cdot X_{CO} \cdot Q_{in}}{m_{Rh}} \quad [mol \ s^{-1} \ g_{Rh}^{-1}] \quad (2)$$

m_{Rh} - Mass of Rh in the reactor bed.

Q_{in} - Total molar flow rate.

X_{CO} - CO conversion based on the products formation.

v_{CO} - Fraction of CO in the gas mixture, equal to p_i/p_0 , p_i : partial pressures of reactants, p_0 : total pressure in the system.

Carbon monoxide conversion (X_{CO}) was determined from the summation of carbon numbers in all products (eq.3).

$$X_{CO} = \frac{\sum n_i C_i}{n_{CO}} \times 100\% \quad (3)$$

The selectivity for each product was obtained by eq. 4.

$$S_i = \frac{n_i C_i}{\sum n_i C_i} \times 100\% \quad (4)$$

Here, CO conversion was kept less than ca. 10% to assure the differential condition. n_i and C_i are the carbon number and mole fraction of i component, respectively. n_{CO} is the mole fraction of CO in inlet gases.

Space time yield (STY) of C₂ oxygenates were calculated through eq 5.

$$STY(\mu g \cdot g_{cat}^{-1} \cdot s^{-1}) = \frac{\sum_{j=1}^{20} C_{ij} \cdot n_{total,j} \cdot M_i}{m_{cat} t} \quad (5)$$

All data points were collected at each hour. C_{ij} is the mole fraction of the i component at the j hour. $n_{total,j}$ is the total mole of the effluent gas at the j hour. M_i is the molar mass of i component. m_{cat} is the mass of the catalyst sample and t is the total reaction time (20 h).

The rate in TOF (r_{TOF} , s^{-1}) was calculated following eq. 6

$$r_{TOF} = \frac{r_{CO} M_{Rh}}{d_{Rh}} \times 100\% \quad [s^{-1}] \quad (6)$$

where M_{Rh} : atomic weight of Rh, d_{Rh} : dispersion of Rh. Here, we assume the surface Rh atoms to be main active sites. Dispersion of Rh atoms was calculated on the basis of a ball model.

3. Results and Discussion

3.1. H_2 -chemisorption

A series of Rh (1.5 wt%)- MnO_x catalysts were prepared with Mn contents of 0, 0.4 wt% and 4.0 wt%, corresponding to Mn/Rh atomic ratios of 0, 0.5 and 5.0, respectively. The dispersion of Rh atoms (Table 1) changed little according to the H_2 chemisorption, increasing slightly from 64.2% (1.5Rh) to 74.3% (1.5Rh-0.4Mn), but dropping to 65.8% for 4.0wt% Mn.

Table 1. Rh and Mn compositions and morphologies of fresh reduced catalysts.

Catalysts	Rh (wt%) ^a	Mn (wt%) ^a	Atomic ratio of Mn/Rh ^a	Dispersion (%) ^b	Calculated particle size (nm) ^c
1.5Rh	1.4	0	0	64.2	1.8
1.5Rh-0.4Mn	1.5	0.4	0.5	74.3	1.5

1.5Rh-4.0Mn	1.5	3.9	5.0	65.8	1.7
-------------	-----	-----	-----	------	-----

^aBased on ICP-Mass analysis

^b Based on the irreversible chemisorption and assuming a stoichiometry of H/Rh_s = 1.

^c Calculated from H₂-chemisorption

3.2 DRIFTS studies for Surface structure of Rh at 270 °C

DRIFT spectra at 270 °C in CO/H₂/Ar are presented in Fig. 1. There are two types of adsorbed CO on the Rh/SiO₂ catalysts which centered at 2051 cm⁻¹ and 1910 cm⁻¹, respectively. The band centered at 2051 cm⁻¹, which was 10 cm⁻¹ lower than linear CO adsorption on Rh⁰ under CO streams (Mo et al., 2009; Schwartz et al., 2011), might be ascribed to a carbonyl hydride species [H-Rh-CO] on Rh⁰ (Solymosi et al., 1980; Yu et al., 2012). The electron donating from chemisorbed H to Rh and the increase in the π -donation from Rh to π anti-bonding orbital of CO leads to a decrease in CO stretching frequencies (Solymosi et al., 1980). On the other hand, the band at 1910 cm⁻¹ might be ascribed to bridged CO adsorption on Rh⁰ (Schwartz et al., 2011). These results indicate that both chain growth and CO insertion are preceded on both active sites. With the addition of MnO_x, three new bands appear at 2110, 1714 and 1586 cm⁻¹, respectively (Spectrum B and C in Fig. 1). The 2110 cm⁻¹ band is ascribed to the linearly adsorbed CO on Rh ^{δ +} sites, which plays an important role in the CO insertion step to produce oxygenates. Watson and Somorjai (Watson and Somorjai, 1981) proposed that the CO insertion takes place on Rh oxide surfaces which could be important for the formation of ethanol and other oxygenates. The 1714 cm⁻¹ band can be assigned to the tilted CO species on Rh-Mn interfaces, which can be ascribed to C bonded with Rh and O bonded Mn. It is generally accepted that this kind of CO species favors CO dissociation to form CH_x intermediates (Fukushima et al., 1985; Lisitsyn et al., 1990; Sachtler and Ichikawa, 1986). However, some studies indicated

that tilted adsorbed CO species were inactive for the CO insertion during the reaction of C_2H_4/H_2 with pre-adsorbed CO on Rh-Ce/SiO₂ (Chuang et al., 1996) or Rh-Mn/SiO₂ (Chuang et al., 1997). Thus, those results indicate that the active sites on Rh surfaces altered indeed by MnO_x. The band at 1586 cm⁻¹ might be ascribed to the surface formate species (HCOO⁻), which agreed well with a stretching vibration at 1585 cm⁻¹ detected after introducing HCOOH into Rh/Al₂O₃ catalysts (Solymosi et al. 1980). The surface formate species might be the intermediate for the formation of C₂₊ oxygenates, indicating that Mn-promoted Rh catalysts are more favorable for the formation of C₂₊ oxygenates than non-promoted Rh catalysts.

Fig. 1. DRIFTS spectra of CO/H₂ co-adsorption on Rh catalysts with different Mn loadings at 270 °C, 30ml/min of CO/H₂/Ar. (A) 1.5Rh, (B) 1.5Rh-0.4Mn and (C) 1.5Rh-4.0Mn.

3.3 Kinetics of CO hydrogenation

3.3.1 Exclusion of the internal diffusion effects

Catalysts with different sizes were used to investigate the influence of the internal mass diffusion (Madon and Boudart, 1982). Fig. 2a showed the conversion of CO

changed little with the variation of catalyst sizes below 0.3 mm. Therefore, the catalyst with an average size of 0.18 mm (80 mesh) was employed in the whole experiments to eliminate the influence of the internal mass diffusion.

3.3.2. Exclusion of the external diffusion effects

The catalyst with an average size of 0.15 mm was used to study the influence of the external mass diffusion. The amount of the catalyst sample and flow rate of the gas stream were varied to change the gas linear velocity through the catalyst bed with a GHSV of 15000 h⁻¹ (Madon and Boudart, 1982). Fig. 2b shows the changes in CO conversions with different gas velocities at the steady state. CO conversion reached a constant at the gas velocity through the bed above 0.086 m/s, which means that the external mass diffusion can be excluded.

Fig. 2. (a) Dependence of CO conversion on different catalysts with a size of 0.42, 0.25, 0.18, and 0.15 mm, respectively, at 270 °C, 3.0 MPa, H₂:CO:N₂=6:3:1, GHSV: 15000 h⁻¹. (-■-1.5 Rh, -●-1.5 Rh-0.4Mn, -▲- 1.5Rh-4.0Mn) and (b) Dependence of CO conversion on gas velocity of syngas over different catalysts (0.15 mm) at 270 °C, 3.0 MPa, H₂:CO:N₂=6:3:1. (-■-1.5 Rh, -●-1.5 Rh-0.4Mn, -▲- 1.5Rh-4.0Mn)

The Frossling correlation is generally used to evaluate the external mass diffusion in catalysis, especially in flow around spherical particles to obtain the relations among the particle size (d_p) of the catalyst, mass-transfer coefficient (k_c) and boundary layer thickness (δ). The mass-transfer correlation is given as eq.7:

$$Sh = 2 + 0.6Re^{1/2} Sc^{1/3}, Sh = \frac{k_c d_p}{D_e}, Re = \frac{\rho u d_p}{\mu}, \text{ and } Sc = \frac{\mu}{\rho D_e} \quad (7)$$

Here, k_c is the average mass-transfer coefficient of a reactant from the bulk flow to catalyst surface (m/s), d_p is the average diameter of the catalyst particle (m), D_e is the effective diffusivity for a binary gas mixture (m²/s), u is the free stream velocity of fluid (m/s), ρ is the gas density (kg/m³), and μ is the gas dynamic viscosity (kg·m⁻¹·s⁻¹). The average mass-transfer coefficient k_c corresponding to the linear velocity is listed in Table 2. The results show that the external mass diffusion could be ruled out at the linear velocity above 0.086m/s, which coincides with the experimental results.

Table 2. Effect of gas linear velocity on the external mass diffusion over Rh-MnO_x/SiO₂ catalysts

flow rate (ml/min)	linear velocity (m/s)	k_c (m /s)
21.8	2.8×10^{-2}	3.3×10^{-2}
43.4	5.8×10^{-2}	3.4×10^{-2}
65.4	8.6×10^{-2}	3.5×10^{-2}
86.7	11.5×10^{-2}	3.5×10^{-2}

3.3.3. Catalyst stability and catalytic performance

All catalysts (1.5Rh, 1.5Rh-0.4Mn, 1.5Rh-4.0Mn) showed good stabilities after 20 h time-on-stream under 270°C, 3.0 MPa (Fig. 3). The results indicate that the structure of active sites for the formation of C₂₊ oxygenates was unlikely altered during the reaction.

Fig. 3. Time-dependent reaction over Rh catalysts with different Mn loadings. Pretreatment: H₂ reduction for 2h at 350°C, 0.6MPa; Reaction condition: H₂/CO=2, 270°C, 3.0MPa, GHSV=15000h⁻¹. (■-1.5 Rh, ●-1.5 Rh-0.4Mn, ▲- 1.5Rh-4.0Mn)

The catalytic performance of CO hydrogenation over Rh-MnO_x catalysts with different Mn loadings after eliminating internal and external diffusion at the typical reaction conditions (270 °C, 3.0 MPa) is listed in Table 3. It can be seen that the conversion of CO and selectivity of C₂₊ oxygenates were enhanced by the addition of MnO_x while the formation of methane was suppressed.

Table 3 Catalytic performance of Rh catalysts with different Mn loadings.^a

Catalyst ^a	CO	Selectivity (%) ^b								
	conv. (%)	CH ₄	C ₂₊ HCs ^c	MeOH	EtOH	PrOH	BuOH	AcH	AcOH	Total oxy. ^d
1.5Rh	0.8	64.1	11.7	6.8	8.5	1.1	0.5	3.6	2.7	16.4
1.5Rh-0.4Mn	1.6	39.8	12.5	7.9	19.9	1.1	0.6	9.6	5.0	38.2
1.5Rh-4.0Mn	1.2	44.7	12.6	6.4	19.7	1.2	0.6	7.3	3.9	34.7

^a Catalyst: 0.1 g; pretreatment: 350°C in H₂ flow at 0.5MPa; reaction conditions: T = 270 °C, P = 3.0MPa, GHSV= 15000h⁻¹ (30% CO, 60% H₂, 10% N₂). Data was recorded after reaching steady state. Error of ±10% of all the values measured.

^b Carbon selectivity = $n_i C_i / \sum n_i C_i$.

^c Hydrocarbons with two or more carbons.

^d Including all C₂₊ oxygenates (alcohols, aldehyde, carboxylic acid and esters)

3.4. Effect of MnO_x on kinetics

By kinetic measurements, the power-law function was employed for fitting the kinetic data (eq. 8). The parameters include apparent activation energies (E_a) and reaction orders with respect to CO (x) and H_2 (y), which can reflect the effects of reaction temperature and reactant partial pressures directly on the rate. In addition, the simple model also has an important guiding significance for the scaling-up of reactor.

$$r_A = k \cdot p_{CO}^x \cdot p_{H_2}^y \quad (8)$$

Where the rate constant k can be expressed as eq. 9:

$$k = k_0 \cdot e^{-\frac{E_a}{RT}} \quad (9)$$

The dependence of reaction rates with respect to H_2 partial pressure ($p_{CO}=0.54$ MPa, $p_{H_2}=0.27-2.16$ MPa) and CO partial pressure ($p_{H_2}=0.9$ MPa, $p_{CO}=0.23-1.8$ MPa) of main products (methane, ethanol, acetaldehyde and acetic acid) and by products (methanol, C_{2+} hydrocarbons and oxygenates) at 270°C are depicted in Figs. 4-5 and S1-S2, respectively. All the reaction orders with respect to CO and H_2 over Rh catalysts with different Mn loadings and E_a were calculated on the basis of yields for different products after linear fittings of the data (Table 4 and Table 5). The dependence of reaction rates based on the formation of main products and by products on the reciprocal of the reaction temperature at 230-290 °C (the Arrhenius plots) is presented in Figs. 6 and S3, respectively.

Fig. 4. Dependence of reaction rate of main products on partial pressure of CO over Rh catalysts with different Mn loadings. (■-1.5 Rh, ●-1.5 Rh-0.4Mn, ▲-1.5Rh-4.0Mn). (a) CH₄, (b) ethanol, (c) acetaldehyde and (d) acetic acid.

Fig. 5. Dependence of reaction rate of main products on partial pressure of H₂ over Rh catalysts with different Mn loadings. (-■-1.5 Rh, -●-1.5 Rh-0.4Mn, -▲- 1.5Rh-4.0Mn). (a) CH₄, (b) ethanol, (c) acetaldehyde and (d) acetic acid.

Fig. 6. Arrhenius plots of main products over Rh catalysts with different Mn loadings. (-■-1.5 Rh, -●-1.5 Rh-0.4Mn, -▲- 1.5Rh-4.0Mn). (a) methane, (b) ethanol, (c) acetaldehyde and (d) acetic acid.

Table 4. Apparent kinetic parameters^{a,b} of hydrocarbons on Rh based catalysts with different Mn loadings at 270°C and 3.0 MPa

Product	1.5Rh			1.5Rh-0.4Mn			1.5Rh-4.0Mn		
	Ea (kJ/mol)	x	y	Ea (kJ/mol)	x	y	Ea (kJ/mol)	X	y
CH ₄	87.2±1.1	-0.8±0.01	0.9±0.07	121.9±7.7	-0.8±0.02	1.0±0.09	119.6±5.5	-0.8±0.04	1.0±0.09
C ₂ H ₄	71.5±4.1	1.1±0.04	-0.5±0.02	90.4±2.2	1.1±0.07	-0.5±0.03	84.3±4.8	1.1±0.04	-0.5±0.02
C ₂ H ₆	84.4±2.2	-0.5±0.03	0.9±0.08	108.8±3.4	-0.2±0.01	1.0±0.07	113.0±2.4	-0.3±0.03	1.0±0.07
C ₃ H ₆	64.6±4.2	0.7±0.06	-0.6±0.03	74.6±4.3	0.4±0.06	-0.5±0.14	72.5±2.6	0.3±0.04	-0.5±0.01
C ₃ H ₈	82.6±4.4	-0.6±0.02	1.0±0.04	96.1±5.0	-0.5±0.02	1.0±0.02	94.1±4.1	-0.5±0.06	1.0±0.04
C ₄ H ₈	36.4±6.2	0.9±0.09	-0.5±0.04	52.7±7.7	0.9±0.07	-0.5±0.05	52.2±7.3	0.8±0.06	-0.5±0.05
C ₄ H ₁₀	53.6±2.1	-0.3±0.02	1.0±0.03	73.3±2.8	-0.2±0.02	1.0±0.04	71.8±2.2	-0.3±0.02	1.1±0.03

^a The reaction orders of CO and H₂ were determined by fitting a power-law rate expression as eq. 8.

^b Apparent activation energies (E_a) of reactant CO and products were determined by Arrhenius equation as eq. 9.

Table 5. Apparent kinetic parameters^{a,b} of oxygenates and CO₂ calculated on the basis of the transformation of CO on Rh based catalysts with different Mn loadings at 270°C and 3.0 MPa

Product	1.5Rh			1.5Rh-0.4Mn			1.5Rh-4.0Mn		
	Ea (kJ/mol)	x	y	Ea (kJ/mol)	x	y	Ea (kJ/mol)	x	y
MeOH	52.5±3.3	0.1±0.01	2.0±0.12	57.0±2.7	-0.1±0.01	1.9±0.16	55.6±2.0	-0.1±0.02	1.9±0.10
EtOH	84.3±3.7	-0.3±0.02	0.8±0.07	91.0±3.0	-0.7±0.04	1.1±0.08	89.9±3.7	-0.7±0.01	1.1±0.10
AcH	85.2±5.0	0.2±0.05	-0.1±0.02	89.6±3.5	-0.1±0.04	-0.1±0.01	88.1±2.8	-0.1±0.01	-0.1±0.01
AcOH	74.2±4.7	-0.5±0.04	-0.6±0.05	75.6±2.7	-0.6±0.08	-0.9±0.09	76.7±2.3	-0.5±0.07	-0.9±0.09
PrOH	76.8±3.5	0.4±0.02	0.6±0.06	79.1±2.4	0.1±0.03	0.7±0.05	79.4±3.1	0.1±0.01	0.7±0.07
BuOH	87.0±6.0	0.5±0.04	0.7±0.11	94.5±5.9	0.4±0.03	0.8±0.06	94.3±5.6	0.4±0.02	0.7±0.08
CO ₂	93.3±9.0	0.1±0.02	/	91.9±7.7	-0.3±0.02	/	95.3±7.5	-0.1±0.01	/

^a The reaction orders of CO and H₂ were determined by fitting a power-law rate expression as eq. 8.

^b Apparent activation energies (E_a) of reactant CO and products determined by Arrhenius equation as eq. 9.

3.4.1 Effect of MnO_x on E_a

From Table 4 and Table 5, the E_a for the formation of hydrocarbons differs slightly with that of oxygenates over Rh/SiO₂. However, after loading 0.4 wt% Mn, the E_a of hydrocarbons increases significantly (e.g. 87.2 kJ/mol to 121.9 kJ/mol for methane, and 84.4 kJ/mol to 108.8 kJ/mol for ethane) while the E_a for oxygenates increases slightly (e.g. 84.3 kJ/mol to 91.0 kJ/mol for EtOH, and 85.2 kJ/mol to 89.6 kJ/mol for AcH). The fact demonstrates that the formation of hydrocarbons could be kinetically suppressed by MnO_x , which was similar to that reported by Choi and Liu *via* micro-kinetic modeling (Choi and Liu, 2009). They have evidenced that the addition of Fe promoter could dramatically increase the barrier of methane formation. Moreover, those reaction orders calculated on the same product varied little with an increase in the Mn content, indicating that the active sites for C₂₊ oxygenates were kept constant regardless of excessive addition of Mn.

3.4.2 Effect of MnO_x on reaction orders of products

The power-law rate functions in the form of $r = Ae^{-\frac{E_a}{RT}} p_{CO}^x p_{H_2}^y$ for the synthesis of hydrocarbons and oxygenates (alcohols, aldehydes, carboxylic acids) are summarized in Tables 4-5. Since the formation of different products from CO hydrogenation follows somewhat different pathways, it is more meaningful to examine the power-law rate parameters for the individual product rather than the rate parameters for the overall reaction of CO. The low standard deviations for E_a and reaction order measurements along with their correlation coefficients (>0.95) indicate that these parameters represent the data well. In this study, the effects of MnO_x on kinetics over Rh catalysts are mainly discussed. Compared with the pure Rh catalyst, CO and H₂ orders of all hydrocarbons remained unchanged with the addition of MnO_x , indicating that the formation mechanism of hydrocarbons was little affected. However,

with the addition of MnO_x , CO order dropped to about -0.68 from -0.25 while H_2 order increased to about 1.14 from 0.78. That means the coverage of surface C^* intermediates or non-dissociatively adsorbed CO on Rh sites can be enhanced. In accordance to the mechanism as proposed in our previous work, CO orders of hydrocarbons would be reduced with an increase in the coverage of C^* species; however, this phenomenon was not observed in Table 4. In other words, the addition of MnO_x enhanced the coverage of non-dissociatively adsorbed CO, which was partially proved by CO-DRIFTS, thus CO orders decreased with the rise of the amount of CH_3CO^* species. Similarly, the enhancement of H_2 coverage improved the yield of EtOH via hydrogenation of CH_3CO^* species. But the H_2 orders of AcOH dropped to -0.92 from -0.57, caused by the competition among hydrogenation of CH_3CO^* , hydrogenation of OH^* and OH^* insertion to CH_3CO^* species.

3.5 ASF distribution

Chain growth is a key step in C_{2+} oxygenates synthesis, and the distribution of oxygenates could be described by Anderson–Schulz–Flory distribution (Eq. 10) as it is widely used in F-T synthesis.

$$\ln\left(\frac{W_n}{n}\right) = n \cdot \ln \alpha + 2 \ln\left(\frac{1-\alpha}{\sqrt{\alpha}}\right) \quad (10)$$

The ASF product distribution for the formation of oxygenates and hydrocarbons at different temperatures are shown in Fig. 7 and Fig. 8. It is noted that C_1 products such as methanol and methane were plotted but not included in the chain growth probability calculations because Rh catalysts are not typical Fischer-Tropsch catalysts as Fe or Co based catalysts. That is to say, C_1 products are not generated from chain growth steps but only hydrogenation of dissociated C^* species or non-dissociated CO^* species. The oxygenate distribution shows less C_1 (methanol) than would be

expected by extrapolation of the ASF distribution for C_{2+} oxygenates according to the distribution of oxygenates, suggesting that the pathway for methanol formation is different from that for ethanol and other higher oxygenates. As mentioned above, methanol is presumably formed by direct hydrogenation of non-dissociated CO^* rather than chain growth after CO dissociation as C_{2+} oxygenates. Thus the formation of methanol does not follow the chain growth mechanism. On the contrary, the hydrocarbon distribution shows that the amount of methane is more than expected based on the distribution of C_{2+} hydrocarbons. This suggests that only a part of the surface hydrocarbon species, $(CH_x)_{ads}$, resulting from the hydrogenation of the surface carbon formed in CO dissociation, participates in the ASF chain growth mechanism to form C_{2+} hydrocarbons. Most of CH_x species undergo further hydrogenation to form methane. In other words, methane is also formed by a mechanism without chain growth. Furthermore, the distributions for C_{2+} hydrocarbon and oxygenate products comply with the ASF distribution, but the chain growth probabilities vary with different Mn loadings (Table 6).

For Rh/SiO₂, the chain growth probabilities for hydrocarbons and oxygenates are very close, indicating those products are formed over the same active sites. With the addition of MnO_x, the chain growth probability of hydrocarbons changed little, in contrast, the chain growth probability of oxygenates decreased dramatically. Those results suggest that the reactions leading to these products may either proceed by diverse mechanisms or on different active sites. For Rh/SiO₂, both chain growth and CO insertion steps occur on Rh⁰ active sites (linear or bridged CO), resulting in similar chain growth probabilities of hydrocarbons and oxygenates. The surface of Rh-MnO_x is much more complex than the Rh alone. Chain growth and CO insertion steps may take place on different active sites, which are responsible for the variation

of chain growth probabilities for hydrocarbons and oxygenates.

Fig. 7. ASF fitting for hydrocarbons over Rh catalysts with different Mn loadings at (a) 230°C, (b) 250°C, (c) 270°C and (d) 290°C. Reaction conditions: 3.0 MPa, $\text{H}_2:\text{CO}:\text{N}_2=6:3:1$ and $\text{GHSV}=15000 \text{ h}^{-1}$. ($\blacksquare$ -1.5 Rh, $\bullet$ -1.5 Rh-0.4Mn, $\blacktriangle$ -1.5Rh-4.0Mn)

Fig. 8. ASF fitting for oxygenates over Rh catalysts with different Mn loadings at (a) 230°C, (b) 250°C, (c) 270°C and (d) 290°C. Reaction conditions: 3.0 MPa, $\text{H}_2\text{:CO:N}_2=6\text{:}3\text{:}1$ and $\text{GHSV}=15000 \text{ h}^{-1}$. (- ■ - 1.5 Rh, - ● - 1.5 Rh-0.4Mn, - ▲ - 1.5Rh-4.0Mn)

Table 6. Chain growth probability of Rh catalyst with different Mn loadings

	230°C		250°C		270°C		290°C	
Sample	HCs	oxy	HCs	oxy	HCs	oxy	HCs	oxy
1.5Rh	0.41	0.33	0.21	0.20	0.18	0.17	0.14	0.16
1.5Rh-0.4Mn	0.36	0.29	0.26	0.10	0.24	0.10	0.20	0.10
1.5Rh-4.0Mn	0.40	0.35	0.27	0.12	0.23	0.13	0.21	0.13

3.6. Promotional effects of MnO_x

The catalytic performance of Rh/SiO_2 was greatly enhanced with the addition of MnO_x . Kinetic behaviors and product distributions have been investigated on Rh-MnO_x catalysts with different compositions. Therefore, in this section, the

discussion is focused on two aspects: (i) the MnO_x structural modification by the interaction with Rh, and its effects on the catalyst performance; (ii) the plausible mechanism for CO hydrogenation on the basis of kinetics. It is noted that Rh is regarded as the primary active metal in this system. However, the conversion of syngas over the Rh alone will not be mentioned in detail here, because it has already been studied widely.

The mechanism for the formation of methane addressed here will enlighten us to understand the effect of promoters on CO hydrogenation. However, even for methane formation, there are disagreements in the literature about whether C–O bond cleavage occurs in CO hydrogenation via direct dissociation (carbide models) or via a hydrogen-enhanced process. There has been an increasing focus more recently on the latter mechanism because several studies have provided strong evidences supporting this mechanism over Rh catalysts (Davis, 2001; Fisher and Bell, 1996; Storsæter et al., 2006; Su et al., 2014).

It is well known that Rh catalysts have been attracting to industry in selective CO hydrogenation, which is a surface-catalyzed polymerization process. CH_x monomers, yielded by the hydrogen-assisted activation of adsorbed CO, are the building blocks for the subsequent chain growth reactions to produce paraffins, olefins, alcohols and oxygenates. The well-accepted pathway for syngas conversion was illustrated in Scheme 1 (Chuang et al., 2005), which includes several primary steps, such as CO dissociation, $^*\text{C}$ hydrogenation and CO insertion into $^*\text{CH}_x$.

The reaction rate and selectivity to C_{2+} oxygenates over Rh catalysts were affected by several factors, such as the size of Rh crystallites (Arakawa et al., 1984; Kapur et al., 2010), the support property (Sachtler and Ichikawa, 1986), the Rh- RhO_x assemble and the second metal (Ojeda et al., 2004). In this study, we only discuss the

production of C_{2+} oxygenates affected by MnO_x and the role of $Rh^{\delta+}$ because the particle size of Rh changed slightly in the range of 1.5-1.8 nm after the addition of Mn. Hence, we proposed the enhancement of selectivity to C_{2+} oxygenates may be caused by the modification of Rh electronic structure rather than the particle size of Rh after addition of Mn. With the combination of the DRIFTS spectra (Fig. 1) and kinetic parameters (Table 3-5), it can be seen that CO conversion and selectivities of C_{2+} oxygenates were greatly enhanced by linearly adsorbed CO species on $Rh^{\delta+}$ sites and tilted species on Rh- MnO_x sites.

The reaction pathways over Rh and Rh- MnO_x were illustrated in Scheme 1. The reaction pathway for the former is marked as the straight line while both straight line and dashed line are marked for the latter. For Rh catalysts, all the elementary steps (CO dissociation, chain growth, hydrogenation and CO insertion) take place on metallic Rh^0 surfaces (Chuang et al., 2005; Egbebi and Spivey, 2008). For Rh- MnO_x catalysts, CO dissociation and chain growth steps take place on metallic Rh^0 and the presence of MnO_x could enhance CO dissociation through the production of a titled CO adsorbed at the Rh- MnO_x interface (Sachtler and Ichikawa, 1986; Wang et al., 2000). On the other hand, CO insertion, the key step for the formation of oxygenates, is highly active on $Rh^{\delta+}$ sites after the addition of MnO_x . Watson and Somorjai (Watson and Somorjai, 1981) also proposed that RhO_x played an important role in the formation of C_{2+} oxygenates from CO hydrogenation over Rh catalysts. In the meantime, the ASF distribution in Table 6 shows the chain growth probability for C_{2+} oxygenates decreased rapidly in the presence of MnO_x . This fact indicates that CH_2CO^* species on $Rh^{\delta+}$ sites selectively favor the formation of oxygenates after hydrogenation rather than chain growth to form $C_2H_4CO^*$. On the contrary, CH_2CO^* on Rh^0 sites can either go through hydrogenation to form oxygenates or chain growth

to yield long chain oxygenates. Thus, it can be concluded that MnO_x in Rh-MnO_x can enhance CO insertion pathways that form oxygenates while the hydrogenation of $^*\text{CH}_x$ and chain growth reaction by inserting $^*\text{CH}_x$ are significantly depressed (Scheme 1).

Scheme 1. Pathways for the formation of methane, methanol and C_{2+} oxygenates from CO hydrogenation over $\text{Rh-MnO}_x/\text{SiO}_2$ catalysts. (Reactions of dashed arrows took place only over Mn promoted Rh/SiO_2 catalysts)

As a summary, we have demonstrated that the structure of Rh particles could be modified upon interacting with MnO_x and varied with the change in Mn loadings. Consequently, the activity and selectivity to C_{2+} oxygenates over Rh-MnO_x catalysts were improved significantly. In the studied system, the morphology and size of Rh particles play trivial roles in this reaction. Nevertheless, the fine structure of the surface species, such as Rh-MnO_x , Rh-O-Mn or Rh-RhO_x , which may impact on selective hydrogenation of C_{2+} oxygenates, need to be further identified for both understanding the mechanisms and redesigning catalysts with higher efficiencies.

4. Conclusions

The mechanistic basis of the effects of MnO_x loading on syngas to C_{2+} oxygenates were studied over $\text{Rh-MnO}_x/\text{SiO}_2$ catalysts with different Mn/Rh molar

ratios (0, 0.5 and 5). The kinetic parameters of CO hydrogenation over the three catalysts at 270°C, 3.0 MPa were obtained using a power law model. It was found that apparent activation energies changed slightly for the formation of oxygenates but increased rapidly for the formation of hydrocarbons when promoted by MnO_x. DRIFTS study at 270°C under CO/H₂/Ar flow indicates that there appear two new active sites over Rh-MnO_x/SiO₂ catalysts, which may play an important role in CO dissociation and CO insertion. The reaction orders with respect to CO are negative and positive value to H₂ orders for all paraffins; totally opposite results were obtained for all olefins. C₂₊ oxygenates have been assumed to be formed via non-dissociated CO insertion and further hydrogenation of CH₂CO* species.

Acknowledgment

The authors are grateful to the support from the National Science Foundation (21176071, 21106041, 21273070), the Program for New Century Excellent Talents in university (NCET-12-0852), Science and Technology Commission of Shanghai Municipality (11JC1402700), International Cooperation Project of Shanghai Ministry of Science and Technology (14230710700) and the Chinese Education Ministry 111 project (B08021).

References

- Arakawa, H., Takeuchi, K., Matsuzaki, T., Sugi, Y., 1984. Effect of metal dispersion on the activity and selectivity of Rh/SiO₂ catalyst for high pressure CO hydrogenation. *Chemistry Letters* 13, 1607-1610.
- Bhasin, M.M., Bartley, W.J., Ellgen, P.C., Wilson, T.P., 1978. Synthesis gas conversion over supported rhodium and rhodium-iron catalysts. *Journal of Catalysis* 54, 120-128.
- Chen, W., Ding, Y., Song, X., Wang, T., Luo, H., 2011. Promotion effect of support calcination on ethanol production from CO hydrogenation over Rh/Fe/Al₂O₃ catalysts. *Applied Catalysis A: General* 407, 231-237.
- Choi, Y., Liu, P., 2009. Mechanism of Ethanol Synthesis from Syngas on Rh(111). *Journal of the American Chemical Society* 131, 13054-13061.
- Chuang, S.S.C., Brundage, M.A., Balakos, M.W., 1997. Mechanistic study in catalysis using dynamic and isotopic transient infrared spectroscopy: CO/H₂/C₂H₄ reaction on MnRh/SiO₂. *Applied Catalysis A: General* 151, 333-354.
- Chuang, S.S.C., Srinivas, G., Brundage, M.A., 1996. Role of Tilted CO in Dynamics of CO Insertion on Ce-Rh/SiO₂. *Energy & Fuels* 10, 524-530.
- Chuang, S.S.C., Stevens, R.W., Khatri, R., 2005. Mechanism of C₂₊ oxygenate synthesis on Rh catalysts. *Topics in Catalysis* 32, 225-232.
- Davis, B.H., 2001. Fischer–Tropsch synthesis: current mechanism and futuristic needs. *Fuel Processing Technology* 71, 157-166.
- Egbebi, A., Spivey, J.J., 2008. Effect of H₂/CO ratio and temperature on methane selectivity in the synthesis of ethanol on Rh-based catalysts. *Catalysis Communications* 9, 2308-2311.
- Farrell, A.E., Plevin, R.J., Turner, B.T., Jones, A.D., O'Hare, M., Kammen, D.M.,

2006. Ethanol can contribute to energy and environmental goals. *Science* 311, 506-508.
- Fisher, I.A., Bell, A.T., 1996. A comparative study of CO and CO₂ hydrogenation over Rh/SiO₂. *Journal of Catalysis* 162, 54-65.
- Fukushima, T., Arakawa, H., Ichikawa, M., 1985. High-pressure I.R. spectroscopic evidence of acetyl and acetate species directly formed in CO-H₂ conversion on SiO₂-supported Rh and Rh-Mn catalysts. *Journal of the Chemical Society, Chemical Communications*, 729-731.
- Gao, J., Mo, X., Chien, A.C.-Y., Torres, W., Goodwin Jr, J.G., 2009a. CO hydrogenation on lanthana and vanadia doubly promoted Rh/SiO₂ catalysts. *Journal of Catalysis* 262, 119-126.
- Gao, J., Mo, X., Goodwin Jr, J.G., 2009b. La, V, and Fe promotion of Rh/SiO₂ for CO hydrogenation: Detailed analysis of kinetics and mechanism. *Journal of Catalysis* 268, 142-149.
- Kapur, N., Hyun, J., Shan, B., Nicholas, J.B., Cho, K., 2010. Ab Initio Study of CO Hydrogenation to Oxygenates on Reduced Rh Terraces and Stepped Surfaces. *The Journal of Physical Chemistry C* 114, 10171-10182.
- Lisitsyn, A.S., Stevenson, S.A., Knözinger, H., 1990. Carbon monoxide hydrogenation on supported Rh-Mn catalysts. *Journal of Molecular Catalysis* 63, 201-211.
- Liu, J., Guo, Z., Childers, D., Schweitzer, N., Marshall, C.L., Klie, R.F., Miller, J.T., Meyer, R.J., 2014. Correlating the degree of metal-promoter interaction to ethanol selectivity over MnRh/CNTs CO hydrogenation catalysts. *Journal of Catalysis* 313, 149-158.
- Liu, J., Tao, R., Guo, Z., Regalbuto, J.R., Marshall, C.L., Klie, R.F., Miller, J.T.,

- Meyer, R.J., 2013. Selective Adsorption of Manganese onto Rhodium for Optimized Mn/Rh/SiO₂ Alcohol Synthesis Catalysts. *ChemCatChem* 5, 3665-3672.
- Ma, X.F., Su, H.Y., Deng, H.Q., Li, W.X., 2011. Carbon monoxide adsorption and dissociation on Mn-decorated Rh(111) and Rh(553) surfaces: A first-principles study. *Catalysis Today* 160, 228-233.
- Madon, R.J., Boudart, M., 1982. Experimental criterion for the absence of artifacts in the measurement of rates of heterogeneous catalytic reactions. *Industrial & Engineering Chemistry Fundamentals* 21, 438-447.
- McClure, S.M., Lundwall, M.J., Goodman, D.W., 2011. Planar oxide supported rhodium nanoparticles as model catalysts. *Proceedings of the National Academy of Sciences of the United States of America* 108, 931-936.
- Mo, X., Gao, J., Goodwin Jr, J.G., 2009. Role of promoters on Rh/SiO₂ in CO hydrogenation: A comparison using DRIFTS. *Catalysis Today* 147, 139-149.
- Ojeda, M., Granados, M.L., Rojas, S., Terreros, P., Garcia-Garcia, F.J., Fierro, J.L.G., 2004. Manganese-promoted Rh/Al₂O₃ for C₂-oxygenates synthesis from syngas - Effect of manganese loading. *Applied Catalysis a-General* 261, 47-55.
- Sachtler, W.M.H., Ichikawa, M., 1986. Catalytic site requirements for elementary steps in syngas conversion to oxygenates over promoted rhodium. *The Journal of Physical Chemistry* 90, 4752-4758.
- Schwartz, V., Campos, A., Egbibi, A., Spivey, J.J., Overbury, S.H., 2011. EXAFS and FT-IR Characterization of Mn and Li Promoted Titania-Supported Rh Catalysts for CO Hydrogenation. *ACS Catalysis* 1, 1298-1306.
- Solymosi, F., Erdöhelyi, A., Kocsis, M., 1980. Surface interaction between H₂ and CO₂ on Rh/Al₂O₃, studied by adsorption and infrared spectroscopic

- measurements. *Journal of Catalysis* 65, 428-436.
- Spivey, J.J., Egbebi, A., 2007. Heterogeneous catalytic synthesis of ethanol from biomass-derived syngas. *Chemical Society Reviews* 36, 1514.
- Storsæter, S., Chen, D., Holmen, A., 2006. Microkinetic modelling of the formation of C₁ and C₂ products in the Fischer–Tropsch synthesis over cobalt catalysts. *Surface Science* 600, 2051-2063.
- Su, J., Mao, W., Xu, X.-C., Yang, Z., Li, H., Xu, J., Han, Y.-F., 2014. Kinetic study of higher alcohol synthesis directly from syngas over CoCu/SiO₂ catalysts. *AIChE Journal* 60, 1797-1809.
- Subramani, V., Gangwal, S.K., 2008. A Review of Recent Literature to Search for an Efficient Catalytic Process for the Conversion of Syngas to Ethanol. *Energy & Fuels* 22, 814-839.
- Subramanian, N.D., Gao, J., Mo, X., Goodwin Jr, J.G., Torres, W., Spivey, J.J., 2010. La and/or V oxide promoted Rh/SiO₂ catalysts: Effect of temperature, H₂/CO ratio, space velocity, and pressure on ethanol selectivity from syngas. *Journal of Catalysis* 272, 204-209.
- van den Berg, F.G.A., Glezer, J.H.E., Sachtler, W.M.H., 1985. The role of promoters in CO/H₂ reactions: Effects of MnO and MoO₂ in silica-supported rhodium catalysts. *Journal of Catalysis* 93, 340-352.
- Wang, Y., Luo, H., Liang, D., Bao, X., 2000. Different Mechanisms for the Formation of Acetaldehyde and Ethanol on the Rh–Based Catalysts. *Journal of Catalysis* 196, 46-55.
- Watson, P.R., Somorjai, G.A., 1981. The hydrogenation of carbon monoxide over rhodium oxide surfaces. *Journal of Catalysis* 72, 347-363.
- Yin, H., Ding, Y., Luo, H., Yan, L., Wang, T., Lin, L., 2003. The performance of C₂

- oxygenates synthesis from syngas over Rh-Mn-Li-Fe/SiO₂ catalysts with various Rh loadings. *Energy & Fuels* 17, 1401-1406.
- Yu, J., Mao, D., Han, L., Guo, Q., Lu, G., 2012. The effect of Fe on the catalytic performance of Rh-Mn-Li/SiO₂ catalyst: A DRIFTS study. *Catalysis Communications* 27, 1-4.
- Yu, J., Mao, D., Han, L., Guo, Q., Lu, G., 2013. Catalytic conversion of syngas into C₂₊ oxygenates over Rh/SiO₂-based catalysts: The remarkable effect of hydroxyls on the SiO₂. *Journal of Molecular Catalysis A: Chemical* 367, 38-45.
- Zaman, S., Smith, K.J., 2012. A Review of Molybdenum Catalysts for Synthesis Gas Conversion to Alcohols: Catalysts, Mechanisms and Kinetics. *Catalysis Reviews-Science and Engineering* 54, 41-132.