Graphic abstract

Generalized correlation between the damage ratio (D_m) and fractal dimension (D_f)

(γ : surface energy, U : Impact velocity, We : Weber number, B and α are fitting parameters)

Manuscript submitted to

Chemical Engineering Science

Breakage of fractal agglomerates

Xiaoliang Deng, Rajesh N. Dave*

New Jersey Institute of Technology, Newark, NJ 07102, USA

Author to whom the correspondence should be addressed to:

*Rajesh N. Dave

Abstract

Breakage behavior of fractal agglomerates as a function of impact velocity and surface energy was investigated using discrete element method (DEM). Agglomerates with fractal dimensions (D_f) ranging from about 2.0 to 2.8 were produced by letting primary particles having random initial velocities agglomerate under a centripetal force. The simulation results show that the damage ratio (D_m), defined as the ratio of broken interparticle contacts to the initial total contacts, decreases with increasing fractal dimension in the range between 2.0 to 2.6, which can be explained by the increased mechanical strength with increasing fractal dimension. Previously introduced Weber number (W_e) based correlation for damage ratio is generalized by incorporating the fractal dimension: $D_m = B \left(\frac{W_e}{D_f^2} \right)^\alpha$, where B and α depend exponentially and linearly on Weber number, respectively. Visualization of impact process illustrates the feature of ductile fracture of fractal agglomerates irrespective of fractal dimensions.

Key words: *agglomerate, fractal dimension, impact, breakage, discrete element method (DEM), Weber number*

1. Introduction

Fine particles have a strong tendency to agglomerate due to the relatively strong interparticle cohesive forces compared with their gravitational forces. In a variety of engineering processes, it is highly desirable to break those agglomerates in order to achieve required properties and improve product performance. For instance, in pharmaceutical industry it is critical to break the irregular agglomerates during the mixing process in order to achieve homogeneity of the mixture at sub-agglomerate scale (Ammendola et al., 2011; Deng et al., 2013). Therefore, breakage of agglomerates is one of the fundamental issues commonly encountered in many industrial processes and has attracted a great deal of research interest (Antonyuk et al., 2006; Golchert et al., 2004; Liu et al., 2016; Moreno et al., 2003; Ning et al., 1997; Spetl et al., 2015; Thornton and Liu, 2004; Thornton et al., 1996; Zheng et al., 2015).

Discrete element method (DEM) simulations have access to particle scale information on the coordinates and velocities of all the constituted primary particles within agglomerates, which is crucial for better mechanistic understanding of agglomerate breakage dynamics. As a consequence, DEM simulations have been widely used to investigate the breakage of agglomerates, particularly in identifying broken interparticle contacts induced by impact (Kafui and Thornton, 2000; Liu et al., 2010; Liu et al., 2016; Moreno-Atanasio, 2012; Moreno-Atanasio and Ghadiri, 2006; Moreno et al., 2003; Thornton et al., 1999; Thornton and Liu, 2004; Thornton et al., 1996). In previous literature, the breakage behavior of agglomerates resulting from impact has been comprehensively investigated with the focus on the effect of impact velocity, impact angle, and surface energy (Kafui and Thornton, 2000; Mishra and Thornton, 2001; Moreno-Atanasio and Ghadiri, 2006; Samimi et al., 2004; Thornton et al., 1999; Thornton et al., 1996). To quantify the extent of breakage suffered by agglomerate under impact, the concept of damage ratio has been introduced by Thornton (Thornton et al., 1996). It is a dimensionless number of broken contacts divided by the initial number of contacts within the agglomerate. The damage ratio has been correlated with the Weber number $W_e = \frac{\rho D U^2}{\Gamma}$, where ρ , D , U , and Γ are the particle density, particle diameter,

impact velocity, and work of adhesion, respectively (Kafui and Thornton, 2000; Moreno-Atanasio and Ghadiri, 2006; Subero et al., 1999). Later, Thornton et al. modified the Weber number by introducing a critical impact velocity (Thornton et al., 1996).

An important point to note is that the agglomerate models used in previous research are characterized by generally round, regular shape and compact structure, perhaps stemming from particular interest in the granulation process (Kafui and Thornton, 2000; Liu et al., 2010; Reynolds et al., 2005). However, some other applications such as mixing and fluidization of nanoparticles (Chen et al., 2008; Deng et al., 2013; Scicolone et al., 2011) and dry coating (Pfeffer et al., 2001; Yang et al., 2005) require handling and processing the agglomerates formed by dry fine particles, characterized by irregular shapes and more open structures (Froeschke et al., 2003; Kanniah et al., 2012). Therefore, the crucial missing information is the detailed understanding of how the morphological features of agglomerates impact their breakage behavior. There has been several recent DEM simulation studies intended to help better understand the effect of not only the shape but also morphological properties of agglomerates on breakage behavior. For instance, DEM simulation results have shown that the breakage behaviors of spherical, cuboidal, and cylindrical agglomerates differ from each other, depending on impact orientations (Liu et al., 2010). The effect of the internal microstructure of agglomerates on their breakage characteristics has been examined as well, focusing on the role of primary particle size distribution (Spetl et al., 2015). Some experimental results also have shown that the local structure can impact the pattern of agglomerate breakage due to its effect on stress transmission during the impact process (Subero and Ghadiri, 2001). Overall, such results have indicated that the morphological parameters of agglomerates may play a significant role in their breakage behavior, together with other parameters, such as impact velocity and surface energy.

In order to fully characterize the breakage behavior of agglomerates, it is therefore necessary to elucidate the role of agglomerate morphology during the process of breakage. Fractal dimension, an exponent that relates the mass of an agglomerate to its length scale, is an important parameter characterizing the morphological features of agglomerates (Meakin, 1987). However, the effect of fractal dimension on

breakage behavior of agglomerates under impact loading has not been well explored. At present, to the best of our knowledge, there is no empirical or theoretical model that is able to assess, even at a qualitative level, how the fractal dimension affects the breakage behavior of agglomerates.

In this paper, first, the original method to form spherical agglomerates is extended to achieve agglomerates of different fractal dimensions. Such agglomerates are used in DEM simulations to examine the effect of fractal dimension on the breakage behavior of agglomerates composed of uniform-sized spheres. Statistical analysis is used to determine the damage ratio as a function of fractal dimension for various impact velocities and surface energies. The goal of the present work is to provide the foundation for the development of a fundamental agglomerate breakage model incorporating realistic morphological information.

2. Simulation Model

2.1 Discrete element method

DEM is a commonly used computational tool for simulating the properties of particle assembly. It is able to describe complex temporal evolution of particle system using basic input parameters representing physical properties of particle material without making oversimplifying assumptions. In this method, each particle interacts with its neighbors through contacts which can be dynamically formed or broken during simulations. The coordinates and velocities of individual particles are updated at each time-step for the duration of the simulation time according to Newton's second law of motion, for instance (Cundall and Strack, 1979). Every particle can not only experience translational but also rotational motion due to the collisions with other particles or geometries. The equations governing translational and rotational motions can be expressed as $m_i \frac{d\vec{v}_i}{dt} = m_i \vec{g} + \vec{F}_i$ and $I_i \frac{d\vec{\omega}_i}{dt} = \vec{T}_i$, where m_i , $\vec{v}_i$, t , $\vec{g}$, and $\vec{F}_i$ represent the mass, translational velocity vector of particle i , time, gravitational acceleration, and contact forces resulting from the particle-particle and particle-geometry interactions, respectively, and I_i is the moment of inertia,

$\vec{\omega}_i$ the angular velocity and $\vec{T}_i$ the torque acting on particle i induced by tangential contact force and rolling friction.

In DEM, the physics of the model is captured by the contact model from which individual force equations for each particle are derived. The contact model defines the interactions between particles, and particle and geometries. A contact is established if the distance between the centers of particles is less than sum of their radii. In this work, Johnson-Kendall-Roberts (JKR) model is used to describe the normal interparticle interaction, where the total normal contact force is the superposition of elastic Hertzian contact force and attractive force induced by the surface energy (Johnson et al., 1971). Mindlin-Deresiewicz model is used for the tangential interactions and the maximum tangential force is subject to the Coulomb's friction (Mindlin and Deresiewicz, 1953). It is noted that the combination of JKR normal contact force model and Mindlin-Deresiewicz tangential contact force model is frequently used (Nan et al., 2015; Subero et al., 1999). In addition, the energy dissipation during collisions is taken into consideration by introducing a velocity-dependent damping force. Complete details of contact model are not reproduced in this paper but additional information on the implementation of the contact model can be found in (Deng et al., 2013; Johnson et al., 1971).

In this study, the radius of primary particles is equal to 5 micrometers, Poisson's ratio is 0.3, Young's modulus of 0.13 GPa, and particle density is 2,000 kg/m³. The breakage of irregular agglomerates is more complicated than the breakage of regular agglomerate. The simulation is also more time consuming because of the use of very fine primary particles. Therefore, the Young's modulus in this research is selected to be lower than the value used in some other published literature in order to keep computation time reasonable. Use of lower Young's modulus is relevant for the agglomerates formed by soft materials, such as rubber, polymers and pharmaceutical excipients, including cellulosic derivatives, starches, etc. As an example, to simulate the breakage of agglomerates formed by lactose powder even lower Young's modulus was used (Tong et al., 2009), and it was shown that similar breakage behavior was obtained as compared with the experimental results. Therefore, the use of a low Young's modulus may be justified

and our DEM simulation results and model generalizations are expected to be valid. Clearly, there will be an effect of the elastic properties of primary particle on the agglomerate breakage, such as higher Young's modulus would lead to higher breakage and hence larger damage ratio at the same velocity. That means, the actual damage ratio for a material with higher Young's modulus would be higher unless the impact velocity was relatively scaled down. Detailed investigation of the scaling relationship between the impact velocity and Young's modulus with respect to the damage ratio could be a subject of future research. The impact boundaries along z axis share same material properties with primary particles and the periodic boundary conditions are applied in x, and y boundaries. The coefficient of static friction is 0.3 and the coefficient of rolling friction is 0.01. There are totally 1,000 primary particles involved in all the simulations. The simulation domain is cubic with each edge having dimension 760 micrometers. The time step is fixed at 2.0×10^{-8} s throughout all simulations. The total simulation steps can vary for each specific case because agglomeration processes differ depending on initial particle velocity and amplitude of the centripetal force. In this study, the number of simulation steps range from 4.50×10^5 (0.009 s) to 9.05×10^6 (0.181 s). The criteria for stopping simulations is that the total simulations time should be long enough to make sure the agglomerates have completed their impact with the wall; i.e., all particles have completely rebounded away from the wall.

2.2. Determination of fractal dimension of individual agglomerate

The concept of fractal dimension has been frequently used to characterize the morphological features of agglomerates formed by fine cohesive particles (Froeschke et al., 2003; Kanniah et al., 2012). For fractal agglomerates, there is a power law between the number of primary particles within an agglomerate and its size, represented by the radius of gyration (Meakin, 1987):

$$N = k \left(\frac{2R_g}{D} \right)^{D_f} \quad (1)$$

where N , k , R_g , and D_f are the number of primary particles, the scaling pre-factor, the radius of gyration of agglomerate, and the fractal dimension, respectively. The fractal dimension can vary from 1 to 3,

corresponding respectively to a chain-like structure and spherical agglomerate. Mean value of fractal dimension of large amount of agglomerates are usually determined by least square regression fitting to power law relationship between N and Rg/a (Koeylu et al., 1995).

However, usually only a single, typical agglomerate is used in DEM simulations to investigate the breakage of agglomerate due to the intensive computational challenge (Moreno et al., 2003; Thornton and Liu, 2004). As a consequence, the fractal dimension cannot be determined by linear regression due to the lack of statistical information. Here, a method proposed by Lapuerta has been applied to determine the fractal dimension of an individual agglomerate (Lapueta et al., 2006). In this method, an empirical equation has been proposed to describe the dependence of pre-factor on fractal dimension. When the number of primary particle is large enough, this relationship can be expressed as

$$k = 0.732 + 0.861^{((D_f-1)/2)^n} \quad (2)$$

where n is a shape parameter and the mean value can be taken as 1.95 (Lapueta et al., 2006). The radius of gyration can be calculated using the following equation

$$R_g = \left[\frac{1}{2N^2} \sum_{i=0}^N \sum_{j=0}^N (\vec{r}_i - \vec{r}_j)^2 \right]^{0.5} \quad (3)$$

where $\vec{r}_i$ and $\vec{r}_j$ are position vectors of the i th and j th constituent primary particles, respectively. Eqs. (1)-(3) can be solved simultaneously and the fractal dimension of individual agglomerate can be therefore determined.

2.3. Formation of fractal agglomerates

In order to produce the agglomerates with various fractal dimensions, the original protocol to generate spherical agglomerates has been modified (Thornton et al., 1996). In previous work, the protocol to form agglomerate is to initiate the motion of randomly generated primary particles with zero initial velocities towards the center by an external centripetal force. The packing density of agglomerate can be modified

by adjusting the duration of imposition of the centripetal force. Figs. 1(a)-(c) display the agglomeration process using this protocol and the centripetal force is equal to twenty times the weight of the individual constituent particle. This protocol is convenient and efficient to produce spherical or other regular shaped agglomerates (Liu et al., 2010; Subero et al., 1999; Tong et al., 2009). However, it is difficult to obtain the agglomerates with more complicated irregular shape and open structures.

Therefore, the protocol described above has been modified in order to produce desired irregular structures. Instead of using motionless primary particles, individual primary particles are assigned nonzero initial velocities with random directions but fixed magnitudes at the beginning of agglomeration process. Figs. 1 (d)-(f) show the agglomeration process using this modified method. The centripetal force is twenty times the weight of the individual constituent particle as in previous models but the magnitude of initial velocities for each primary particle is equal to 2.5 m/s. It can be seen that the primary particles can collide with each other due to their random components of velocities and first form some small agglomerates (Fig. 1(e)). At the same time, those small agglomerates and other individual primary particles always have a trend to move towards the center of simulation system since the external centripetal force is applied to all the particles. Finally, single agglomerate with irregular shape can be formed (Fig. 1(f)). The number of agglomerates is monitored dynamically. Agglomeration process is regarded to be complete after the system relaxes extra 3×10^5 time step after the single agglomerate is achieved.

There are two competitive mechanisms involved in this process: random particle motion versus particle motion under the given centripetal force. Generally speaking, strong random motions of primary particles lead to form more irregular agglomerate; in contrast, strong centripetal force favors the formation of spherical agglomerate. Consequently, the agglomerate structure can be modified by manipulating magnitudes of the centripetal force and random initial velocity. Figure 2 presents four agglomerates with various fractal dimensions. The centripetal forces applied during the agglomeration processes are all equal to twenty times the weight of the individual constituent particle. However, the magnitudes of random

initial velocities are equal to 2.5 m/s, 1.0 m/s, 0.08 m/s, and 0.01 m/s corresponding to Fig. 2(a), (b), (c), and (d), respectively. As expected, the larger the magnitude of random initial velocity, the higher the fractal dimension.

Numerous simulations were run and it was found that in order to prepare agglomerates with lower fractal dimensions very small centripetal force needs to be applied, which greatly increases the computation time demand. Therefore, the fractal dimensions used in this work range from about 2.0 to 2.8, in contrast to the previous spherical agglomerates with fractal dimension of about 3.0.

3. Results and Discussion

3.1. Effect of fractal dimension on damage ratio

The fractal agglomerates may exhibit more complicated breakage behavior compared with spherical agglomerates. For example, two identical fractal agglomerates but rotating at different angles with respect to the impact orientation may lead to different damage ratios even at fixed impact velocity. The previous DEM simulation results also indicate that the impact orientation can affect the breakage of spherical, cuboidal, and cylindrical agglomerates (Liu et al., 2010). In order to take this factor into consideration, total 9 identical agglomerates are generated for a fixed fractal dimension and each of them rotates at different angle (increment of 40° from 0° to 360°) around the x axis before they impact with the wall along the z axis at a prescribed impact velocity. Subsequently, the average damage ratio and standard deviation over 9 agglomerates can be computed and are presented here.

Figure 3(a) illustrates the relationship between damage ratios and fractal dimensions under various impact velocities and fixed surface energy of 0.10 J/m^2 . For a fixed impact velocity, 13 different values of fractal dimension are simulated and each one includes 9 samples as mentioned before. Therefore, each point in the figure represents an average of nine values and total 117 numerical simulations have been performed at each one of four different fixed impact velocities. It can be seen that damage ratio decreases with

increasing fraction dimension over a range of 2.0 to 2.6. In contrast, as fractal dimension increases beyond 2.6, the damage ratio starts approaching an asymptotic value. The surface energy has also been varied to further investigate the effect of fractal dimension on damage ratio. Fig. 3(b) displays the simulation results for various surface energies at fixed impact velocity of 7.0 m/s. The results indicate that the damage ratio decreases with increasing fractal dimensions, which is consistent with fixed surface energy and various impact velocities (Fig. 3(a)). Therefore, it can be concluded that the damage ratio decreases with increasing fractal dimension over a range of 2.0 to 2.6, regardless of impact velocity and surface energy.

3.2. Relationship between mechanical properties and damage ratio

The behavior of agglomerate breakage is related to the mechanical strength of agglomerate. Kendall et al. proposed a model to evaluate the strength of agglomerate (σ) based on the porosity (ε), work of adhesion (Γ), and the diameter of primary particles (D) (Kendall and Stainton, 2001). The strength of agglomerate can be expressed as

$$\sigma = \frac{15.6(1-\varepsilon)^4 \Gamma}{D} \quad (4)$$

The work of adhesion is the energy required to separate unit areas of two surfaces from contact to infinity in a vacuum, which is defined by the Dupré equation (Israelachvili, 2010):

$$\Gamma = \gamma_1 + \gamma_2 - \gamma_{12} \quad (5)$$

where γ_1, γ_2 are surface energies of two particles in contact with each other and γ_{12} is the interfacial energy between particles 1 and 2. For the surfaces of same material γ_{12} is zero and therefore $\Gamma = 2\gamma$, which is the case for our simulations.

The porosity of agglomerate can be expressed by

$$\varepsilon = 1 - \sum_{i=1}^N V_i / V_a \quad (6)$$

$$V_a = \frac{4}{3}\pi R_e^3 \quad (7)$$

$$R_e = \sqrt{\frac{5}{3}}R_g \quad (8)$$

where V_i , V_a , and R_e are the volume of i th primary particle, volume of agglomerate, and equivalent radius of agglomerate, respectively.

The mechanical strength of an agglomerate can be computed using Eqs. (4)-(8). In addition, the fractal dimension of an agglomerate can be determined using Eqs. (1)-(3). Hence, the relationship between mechanical strength and fractal dimension can be obtained, which is shown in Fig. 4(a). It can be seen that the mechanical strength greatly increases with increasing fractal dimension. Higher mechanical strength indicates the more work needs to be done in order to break the agglomerate, hence the damage ratio decreases with increasing mechanical strength at fixed impact velocity (Fig. 4(b)). Therefore, the knowledge of mechanical strength of fractal agglomerates can assist in better understanding of relationship between damage ratio and fractal dimension. Fig. 4(c) depicts the relationship between mechanical strength and fractal dimensions for various surface energies. The mechanical strength increases with increasing surface energy at fixed fractal dimension, in agreement with increasing damage ratio with decreasing surface energy at fixed fractal dimension (Fig. 3(b)).

However, it can be noted that the mechanical strength monotonically increases with increasing fractal dimension over the whole simulated range. In contrast, the damage ratio shows an asymptotic behavior for the range of fractal dimension larger than about 2.6. This interesting phenomenon indicates that the damage ratio is not related to fractal dimension anymore if the mechanical strength of agglomerates reaches a threshold value. Overall, the mechanical strength increases with increasing fractal dimension, leading to decreasing damage ratio with increasing fractal dimension. However, the damage ratio shows an asymptotic behavior for the fractal dimension greater than 2.6 (or mechanical strength greater than 10^3 Pa). This asymptotic behavior is understandable because damage ratio is independent of the mechanical

strength once the mechanical strength is sufficiently large. It should be also noted that the rate of increase of mechanical strength as a function of fractal dimension decreases with increasing fractal dimension, indicating mechanical strength may also have asymptotic behavior for the fractal dimension greater than 2.8.

3.3. Generalized correlation between damage ratio and Weber number

As previous research has shown, damage ratio of agglomerate induced by impact is related to the Weber number (Ghadiri et al., 2007; Subero et al., 1999; Thornton et al., 1996). However, Weber number is independent of fractal dimension. Therefore, it cannot be directly used to explain our current simulation results, which indicates that the damage ratio is a function of fractal dimension as well, regardless of impact velocity and surface energy.

The current simulation results have shown that the damage ratio is inversely proportional to the fractal dimension for the fractal dimension lower than about 2.6. Therefore, the following equation is proposed to express the dependence of damage ratio on the fractal dimension and Weber number:

$$D_m = B \left(\frac{W_e}{D_f^2} \right)^\alpha \quad (9)$$

Here B and α are constants and they represent the intercept and slop in the log-log coordinates (Fig. 5(a)), respectively. It should be pointed out that the simulation data corresponding to the fractal dimensions above 2.6 have been excluded from Fig. 5(a) since their damage ratios do not show obvious dependence on the fractal dimension. The most important feature shown in Fig. 5(a) is that α and B generally decrease with increasing Weber number. The relationship between α and B and Weber number has been plotted in Fig. 5(b) and (c). It can be seen that there is an approximate linear dependence of α on Weber number, which can be expressed by

$$\alpha = 0.82 - 0.06W_e \quad (10)$$

In contrast, the B depends exponentially on Weber number:

$$B = 0.78 + 2.12 \exp(-We) \quad (11)$$

After substituting Eqs. (10) and (11) into Eq. (9), the relationship between D_m , We , and D_f can be obtained, which is shown in Fig. 5(d). It can be seen that now all the simulation data collapse into a single line as compared to Fig. 5(a).

3.4. Breakage pattern of fractal agglomerate

Damage ratio only accounts for the total number of broken interparticle contacts upon impact. However, it does not reveal how the agglomerates break and, hence, provides an incomplete picture of breakage dynamics. To obtain a more complete picture of the breakage behavior of agglomerates, the breakage pattern is also investigated. Figs. 6 (a)-(c) illustrate the impact process for the agglomerate with fractal dimension of 2.8 at impact velocity of 3.0 m/s and impact orientation of 0 degree. Similarly, Figs. 6(d)-(f) correspond to the fractal dimension of 2.0 at the impact velocity of 3.0 m/s and impact orientation of 0 degree. Figs. 6(g)-(i) are for fractal dimension of 2.0 at the impact velocity of 3.0 m/s and impact orientation of 240 degree. First of all, for the fractal dimension of 2.8, only very small percentage of particles detached from the parent agglomerate after impact. In contrast, for the fractal dimension of 2.0, there are more particles separated from the agglomerate, although the impact velocity is fixed as 3.0 m/s for fractal dimension of 2.8 and 2.0. Therefore, the amount of particles separated from the parent agglomerate increases with decreasing fractal dimension at fixed impact velocity. In addition, the debris created during impact consists mainly of singlets and small fragments of a few primary particles, irrespective of fractal dimensions. Second, both agglomerates experience considerable plastic deformation during impact, exhibiting ductile failure mode. This characteristic is in good agreement with previously published DEM simulations (Subero et al., 1999; Tong et al., 2009) and experimental results using lactose agglomerates (Boerefijn et al., 1998; Ning et al., 1997). It should be noted that brittle or semi-brittle failure modes, characterized by the initialization and propagation of cracks, have also been observed in

other DEM simulations (Thornton et al., 1996) and experiments (Salman et al., 2004; Samimi et al., 2003). The failure mode of agglomerate can be influenced by both agglomerate structure and external loading conditions (Reynolds et al., 2005; Salman et al., 2004; Samimi et al., 2003; Subero and Ghadiri, 2001).

Breakage pattern has also been quantitatively examined by measuring the size of the residual fragments. The fragment size is represented by the number of primary particles forming the fragment normalized by the number of primary particles of the whole agglomerate (Moreno et al., 2003). Figs. 7 (a) and (b) show the dimensionless sizes of the biggest and the second biggest residual fragments as a function of fractal dimension for impact velocities of 3.0 m/s and 5.0 m/s, respectively. First, it can be seen that the sizes of the biggest fragment increase with increasing fractal dimension, while the sizes of the second biggest fragment exhibit the opposite trend. Moreover, Fig. 7(a) shows that the biggest fragment is larger than 90% over a range of fractal dimension larger than 2.4 and the second largest fragment is smaller than 1.2% for the same range of fractal dimension. Those results are also consistent with Fig. 6(c), which indicates that there is a relatively large survived fragment, and fewer singlets and agglomerates consisting of a few primary particles are separated from parent agglomerate upon impact.

Figure 7(b) displays the sizes of the two biggest survived fragments as a function of fractal dimension at the impact velocity of 5.0 m/s. It can be seen that the sizes of the biggest fragment decrease with decreasing fractal dimension, which is consistent with the impact velocity of 3.0 m/s. The difference is that the sizes of the biggest fragment for the impact velocity of 5.0 m/s is smaller than that of 3.0 m/s at fixed fractal dimension, which is understandable because higher impact velocity indicates more energy available to break interparticle contacts. In terms of the second biggest fragments, they usually consist of a few primary particles and do not vary appreciably with fractal dimension over the whole simulated range.

4. Conclusions

DEM simulations were conducted to investigate the breakage behavior of fractal agglomerates as a function of various impact velocities and surface energies. The previous protocol to generate spherical agglomerates was modified by introducing non-zero initial velocities for primary particles in order to produce the agglomerates with various fractal dimensions. Simulation results show that the damage ratio decreases with increasing fractal dimension in the range between 2.0 and 2.6, irrespective of the impact velocity and surface energy. With the further increase of fractal dimension, the damage ratio shows the asymptotic behavior. The mechanical properties of agglomerate such as porosity and strength have been analyzed and the results indicate the low fractal dimension corresponds to the high porosity and low mechanical strength. The higher mechanical strength indicates that more work needs to be done before breaking the agglomerates, which explains the damage ratio decreases with increasing fractal dimension. The relationship among damage ratio (D_m), Weber number (We), and fractal dimension (D_f) can be expressed as $D_m = B \left(\frac{We}{D_f^2} \right)^\alpha$. The power exponent α depends linearly on We and the coefficient of B depends exponentially on We . The breakage pattern of agglomerate upon impact has also been examined by visualizing simulation results, as well as computing the dimensionless size of the biggest and the second biggest residual fragments. The results indicate ductile fracture characteristic, regardless of the fractal dimension. The current research reveals the significant effect of fractal dimension on the breakage behavior of agglomerate and provides fundamental information for developing more accurate and sophisticated breakage models of agglomerates.

Acknowledgements

The authors gratefully acknowledge partial financial support from the National Science Foundation (NSF) through grants EEC-0540855 and EEC-0951845.

Notation

Roman

B = fitting parameter

D = diameter of particle, m

D_f = fractal dimension of agglomerate

D_m = damage ratio

F = force, N

g = gravitational acceleration, m/s²

I = moment of inertia, kg·m²

k = pre-factor

m = mass of particle, kg

n = shape parameter

N = number of primary particles

r = particle position, m

R_e = equivalent radius of agglomerate, m

R_g = radius of gyration of agglomerate, m

T = torque, N·m

U = impact velocity, m/s

v = linear velocity of particle, m/s

V = volume of primary particle, m³

V_a = volume of agglomerate, m³

We = Weber number

Greek letters

ρ = density, kg/m³

ω = rotational velocity of particle, rad/s

γ = surface energy, J/m²

ε = porosity

σ = strength of agglomerate, Pa

α = fitting parameter

Γ = work of adhesion, J/m²

Subscripts

i = particle index

References

- Ammendola, P., Chirone, R., Raganati, F., 2011. Effect of mixture composition, nanoparticle density and sound intensity on mixing quality of nanopowders. *Chemical Engineering and Processing: Process Intensification* 50, 885-891.
- Antonyuk, S., Khanal, M., Tomas, J., Heinrich, S., Mörl, L., 2006. Impact breakage of spherical granules: Experimental study and DEM simulation. *Chemical Engineering and Processing: Process Intensification* 45, 838-856.
- Boerefijn, R., Ning, Z., Ghadiri, M., 1998. Disintegration of weak lactose agglomerates for inhalation applications. *International Journal of Pharmaceutics* 172, 199-209.
- Chen, Y., Yang, J., Dave, R.N., Pfeffer, R., 2008. Fluidization of coated group C powders. *AIChE Journal* 54, 104-121.
- Cundall, P.A., Strack, O.D.L., 1979. A discrete numerical model for granular assemblies. *Géotechnique* 29, 47-65.
- Deng, X., Scicolone, J.V., Davé, R.N., 2013. Discrete element method simulation of cohesive particles mixing under magnetically assisted impaction. *Powder Technology* 243, 96-109.
- Froeschke, S., Kohler, S., P. Weber, A., Kasper, G., 2003. Impact fragmentation of nanoparticle agglomerates. *Journal of Aerosol Science* 34, 275-287.
- Ghadiri, M., Moreno-Atanasio, R., Hassanpour, A., Antony, S.J., 2007. Chapter 19 Analysis of Agglomerate Breakage, in: Agba D. Salman, M.G., Michael, J.H. (Eds.), *Handbook of Powder Technology*. Elsevier Science B.V., pp. 837-872.
- Golchert, D.J., Moreno, R., Ghadiri, M., Litster, J., Williams, R., 2004. Application of X-ray microtomography to numerical simulations of agglomerate breakage by distinct element method. *Advanced Powder Technology* 15, 447-457.
- Israelachvili, J.N., 2010. *Intermolecular and Surface Forces*. Elsevier Science.
- Johnson, K.L., Kendall, K., Roberts, A.D., 1971. Surface Energy and the Contact of Elastic Solids. *Proceedings of the Royal Society of London A: Mathematical, Physical and Engineering Sciences* 324, 301-313.
- Kafui, K.D., Thornton, C., 2000. Numerical simulations of impact breakage of a spherical crystalline agglomerate. *Powder Technology* 109, 113-132.
- Kanniah, V., Wu, P., Mandzy, N., Grulke, E.A., 2012. Fractal analysis as a complimentary technique for characterizing nanoparticle size distributions. *Powder Technology* 226, 189-198.
- Kendall, K., Stainton, C., 2001. Adhesion and aggregation of fine particles. *Powder Technology* 121, 223-229.
- Koeylue, U., Xing, Y., Rosner, D.E., 1995. Fractal Morphology Analysis of Combustion-Generated Aggregates Using Angular Light Scattering and Electron Microscope Images. *Langmuir* 11, 4848-4854.
- Lapuerta, M., Ballesteros, R., Martos, F.J., 2006. A method to determine the fractal dimension of diesel soot agglomerates. *Journal of Colloid and Interface Science* 303, 149-158.
- Liu, L., Kafui, K.D., Thornton, C., 2010. Impact breakage of spherical, cuboidal and cylindrical agglomerates. *Powder Technology* 199, 189-196.
- Liu, L., Thornton, C., Shaw, S.J., Tadjouddine, E.M., 2016. Discrete element modelling of agglomerate impact using autoadhesive elastic-plastic particles. *Powder Technology* 297, 81-88.
- Meakin, P., 1987. Fractal aggregates. *Advances in Colloid and Interface Science* 28, 249-331.
- Mindlin, R.D., Deresiewicz, H., 1953. Elastic spheres in contact under varying oblique forces. *Journal of applied mechanics* 20, 327-344.
- Mishra, B.K., Thornton, C., 2001. Impact breakage of particle agglomerates. *International Journal of Mineral Processing* 61, 225-239.

Moreno-Atanasio, R., 2012. Energy dissipation in agglomerates during normal impact. *Powder Technology* 223, 12-18.

Moreno-Atanasio, R., Ghadiri, M., 2006. Mechanistic analysis and computer simulation of impact breakage of agglomerates: Effect of surface energy. *Chemical Engineering Science* 61, 2476-2481.

Moreno, R., Ghadiri, M., Antony, S.J., 2003. Effect of the impact angle on the breakage of agglomerates: a numerical study using DEM. *Powder Technology* 130, 132-137.

Nan, W., Wang, Y., Liu, Y., Tang, H., 2015. DEM simulation of the packing of rodlike particles. *Advanced Powder Technology* 26, 527-536.

Ning, Z., Boerefijn, R., Ghadiri, M., Thornton, C., 1997. Distinct element simulation of impact breakage of lactose agglomerates. *Advanced Powder Technology* 8, 15-37.

Pfeffer, R., Dave, R.N., Wei, D., Ramlakhan, M., 2001. Synthesis of engineered particulates with tailored properties using dry particle coating. *Powder Technology* 117, 40-67.

Reynolds, G.K., Fu, J.S., Cheong, Y.S., Hounslow, M.J., Salman, A.D., 2005. Breakage in granulation: A review. *Chemical Engineering Science* 60, 3969-3992.

Salman, A.D., Reynolds, G.K., Fu, J.S., Cheong, Y.S., Biggs, C.A., Adams, M.J., Gorham, D.A., Lukenics, J., Hounslow, M.J., 2004. Descriptive classification of the impact failure modes of spherical particles. *Powder Technology* 143-144, 19-30.

Samimi, A., Ghadiri, M., Boerefijn, R., Groot, A., Kohlus, R., 2003. Effect of structural characteristics on impact breakage of agglomerates. *Powder Technology* 130, 428-435.

Samimi, A., Moreno, R., Ghadiri, M., 2004. Analysis of impact damage of agglomerates: effect of impact angle. *Powder Technology* 143-144, 97-109.

Scicolone, J., Mujumdar, A., Sundaresan, S., Davé, R.N., 2011. Environmentally benign dry mechanical mixing of nano-particles using magnetically assisted impact mixing process. *Powder Technology* 209, 138-146.

Spettl, A., Dosta, M., Antonyuk, S., Heinrich, S., Schmidt, V., 2015. Statistical investigation of agglomerate breakage based on combined stochastic microstructure modeling and DEM simulations. *Advanced Powder Technology* 26, 1021-1030.

Subero, J., Ghadiri, M., 2001. Breakage patterns of agglomerates. *Powder Technology* 120, 232-243.

Subero, J., Ning, Z., Ghadiri, M., Thornton, C., 1999. Effect of interface energy on the impact strength of agglomerates. *Powder Technology* 105, 66-73.

Thornton, C., Ciomocos, M.T., Adams, M.J., 1999. Numerical simulations of agglomerate impact breakage. *Powder Technology* 105, 74-82.

Thornton, C., Liu, L., 2004. How do agglomerates break? *Powder Technology* 143-144, 110-116.

Thornton, C., Yin, K.K., Adams, M.J., 1996. Numerical simulation of the impact fracture and fragmentation of agglomerates. *Journal of Physics D: Applied Physics* 29, 424.

Tong, Z.B., Yang, R.Y., Yu, A.B., Adi, S., Chan, H.K., 2009. Numerical modelling of the breakage of loose agglomerates of fine particles. *Powder Technology* 196, 213-221.

Yang, J., Sliva, A., Banerjee, A., Dave, R.N., Pfeffer, R., 2005. Dry particle coating for improving the flowability of cohesive powders. *Powder Technology* 158, 21-33.

Zheng, K., Du, C., Li, J., Qiu, B., Fu, L., Dong, J., 2015. Numerical simulation of the impact-breakage behavior of non-spherical agglomerates. *Powder Technology* 286, 582-591.

List of figures

Fig. 1 Snapshots for the agglomeration process at centripetal force of 20. (a)-(c) correspond simulation time of 0, 0.0012, and 0.002 seconds, respectively, for initial velocity of 0 m/s, (d)-(f) correspond simulation time of 0, 0.016, and 0.04 seconds, respectively, for initial velocity of 2.5 m/s. Colors indicate the coordination numbers of primary particles.

Fig. 2 Schematics of agglomerates with various fractal dimensions. (a) $D_f = 2.13$, (b) $D_f = 2.33$, (c) $D_f = 2.55$, (d) $D_f = 2.80$. Particles are colored according to their coordination number. Centripetal force used is 20 times gravitational force of individual particles. The magnitudes of random initial velocity are equal to 2.5 m/s, 1.0 m/s, 0.08 m/s, and 0.01 m/s for (a), (b), (c), and (d), respectively.

Fig. 3. (a) Damage ratio (D_m) as a function of fractal dimension (D_f) for various impact velocities at surface energy of 0.10 J/m^2 ; (b) Damage ratio as a function of fractal dimension for various surface energies at impact velocity of 7 m/s.

Fig. 4. (a) Relationship between mechanical strength and fractal dimension, (b) relationship between damage ratio and mechanical strength. Surface energy is equal to 0.10 J/m^2 . (c) relationship between mechanical strength and fractal dimension for various surface energies.

Fig. 5. (a) Relationship between D_m and W_e/D_f^2 for various impact velocities and surface energies. (b) relationship between α and Weber number. (c) relationship between B and Weber number. (d) relationship between D_m and $B \left(\frac{W_e}{D_f^2} \right)^\alpha$.

Fig. 6. Snapshots of simulation for agglomerate with different fractal dimensions at impact velocity of 3.0m/s and impact orientation of 0 degree. (a)-(c) correspond to before, during, and after impact, respectively, for $D_f = 2.8$, (d)-(f) correspond to before, during, and after impact, respectively, for $D_f = 2.0$ and impact orientation of 0 degree; (g)-(i) correspond to before, during , and after impact, respectively, for $D_f = 2.0$ and impact orientation of 240 degree.

Fig. 7. The size of two biggest daughter fragments as a function of fractal dimension. (a) impact velocity = 3.0 m/s, (b) impact velocity = 5.0 m/s.

Fig. 1. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

Snapshots for the agglomeration process at centripetal force of 20. (a)-(c) correspond simulation time of 0, 0.0012, and 0.002 seconds, respectively, for initial velocity of 0 m/s, (d)-(f) correspond simulation time of 0, 0.016, and 0.04 seconds, respectively, for initial velocity of 2.5 m/s. Colors indicate the coordination numbers of primary particles.

Fig. 2. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

Schematics of agglomerates with various fractal dimensions. (a) $D_f = 2.13$, (b) $D_f = 2.33$, (c) $D_f = 2.55$, (d) $D_f = 2.80$. Particles are colored according to their coordination number. Centripetal force used is 20 times gravitational force of individual particles. The magnitudes of random initial velocity are equal to 2.5 m/s, 1.0 m/s, 0.08 m/s, and 0.01 m/s for (a), (b), (c), and (d), respectively.

Fig. 3. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

(a) Damage ratio (D_m) as a function of fractal dimension (D_f) for various impact velocities at surface energy of 0.10 J/m^2 ; (b) Damage ratio as a function of fractal dimension for various surface energies at impact velocity of 7 m/s .

Fig. 4. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

(a) Relationship between mechanical strength and fractal dimension, (b) relationship between damage ratio and mechanical strength. Surface energy is equal to 0.10 J/m². (c) relationship between mechanical strength and fractal dimension for various surface energies.

Fig. 5. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

(a) Relationship between D_m and We/D_f^2 for various impact velocities and surface energies. (b) relationship between α and Weber number. (c) relationship between B and Weber number. (d) relationship between D_m and $B \left(\frac{We}{D_f^2} \right)^\alpha$.

Fig. 6. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

Snapshots of simulation for agglomerate with different fractal dimensions at impact velocity of 3.0m/s and impact orientation of 0 degree. (a)-(c) correspond to before, during, and after impact, respectively, for $D_f = 2.8$, (d)-(f) correspond to before, during, and after impact, respectively, for $D_f = 2.0$ and impact orientation of 0 degree; (g)-(i) correspond to before, during, and after impact, respectively, for $D_f = 2.0$ and impact orientation of 240 degree.

Fig. 7. Xiaoliang Deng et al. (2016) intended for *Chemical Engineering Science*.

The size of two biggest daughter fragments as a function of fractal dimension. (a) impact velocity = 3.0 m/s,
 (b) impact velocity = 5.0 m/s.