Optimization of Lead-free Organic–inorganic Tin(II) Halide Perovskite Semiconductors by Scanning Electrochemical Microscopy

Hsien-Yi Hsu^{†§}, Li Ji^{†‡§}, Minshu Du[†], Ji Zhao[†], Edward T. Yu[‡] and Allen J. Bard^{*†}

[†]*Center for Electrochemistry, Department of Chemistry, The University of Texas at Austin, Austin, Texas 78712, United States*

[‡]*Microelectronics Research Center, Department of Electrical and Computer Engineering, University of Texas at Austin, Austin, Texas 78712, United States*

RECEIVED DATE (to be automatically inserted after your manuscript is accepted if required according to the journal that you are submitting your paper to)

ABSTRACT

Lead-free organic-inorganic tin halide perovskites were prepared and investigated by a rapid screening technique utilizing a modified scanning electrochemical microscope (SECM). We studied liquid junction photoelectrochemical (PEC) solar cells based on p-type methylammonium tin halide ($\text{MASnI}_{3-x}\text{Br}_x$) perovskites employing the benzoquinone (BQ) redox couple, $\text{BQ}/\text{BQ}^{\bullet-}$, in dichloromethane (CH_2Cl_2). We found that the optimized Sn-based mixed halide perovskite, $\text{MASnI}_{0.5}\text{Br}_{2.5}$, exhibits enhanced performance and stability in liquid-junction PEC solar cells, with a power conversion efficiency of 1.51% (an increase of 20.8%) and a photovoltaic lifetime of 175 min (an increase of 75.0%), in comparison to MASnI_3 perovskites.

Keywords: non-toxic, lead-free, tin, perovskite, semiconductor, photoelectrochemistry, liquid junction, solar cell, scanning electrochemical microscopy.

INTRODUCTION

Hybrid organic-inorganic perovskite materials have emerged as a new category of direct-bandgap semiconductors for solar energy applications. The impressive properties of perovskite materials, e.g., MAPbX_3 ($\text{Me}=\text{CH}_3$; $\text{X}=\text{I}, \text{Br}, \text{or Cl}$) for photovoltaic (PV) devices include very strong light absorption, excellent ambipolar charge mobility, small exciton binding energy, and apparent tolerance to defects.^[1-6] The remarkably high power conversion efficiency (PCE) of 22.1% reported for hybrid Pb-based perovskite solar cells was achieved by optimizing both series resistance and band positions.^[7] However, the most extensively explored hybrid perovskite materials contain the toxic metal lead, raising concerns about their environmental impacts. To replace Pb with a less toxic metal, Sn-containing compounds such as MASnI_3 or $\text{MASnI}_{3-x}\text{Br}_x$ has been of considerable interest. Unfortunately, the Sn-containing materials are typically air and moisture sensitive, and their oxidation behavior can be detected in the evolution of powder diffraction patterns over time. The patterns show the appearance of extra Bragg diffraction peaks that belong to the oxidized Sn^{4+} species $(\text{MA})_2\text{SnI}_6$, as determined by comparing the diffraction pattern of the unindexed peaks with those of Cs_2SnI_6 .^[8] This process will destroy the charge neutrality of the perovskite structure and give rise to the formation of oxides/hydroxides of Sn and MAI. For solid-state lead free perovskite cells, the PCE of MASnI_3 can be further improved by partly substituting I with Br,^[9] although the solar energy efficiency of non-toxic tin-based perovskite photovoltaics is still low in comparison with lead-based perovskite solar cells. The photoluminescence decay lifetime and charge diffusion length for MASnI_3 solar cells were measured to be ~ 200 ps and 30 nm, respectively.^[10] If the background doping level of MASnI_3 was controlled to be 10^{15} cm^{-3} , however, the diffusion length would increase to $1 \mu\text{m}$.^[10] Given these developments, the determination of tin-based mixed halide perovskite compositions optimized for photovoltaic performance is of outstanding interest.

In a previous paper, we described liquid-junction PEC solar cells involving MAPbI_3 perovskites.^[5] The MAPbI_3 perovskites are extremely sensitive to moisture^[11] and unstable in polar

solvents. We found that dichloromethane (CH_2Cl_2) can be used for liquid-junction PEC solar cells with reasonable stability because of its relatively higher dielectric constant.^[5] Because the use of liquid electrolytes allows easy combinatorial synthesis and screening of new perovskite materials in arrays as well as testing of the effects of various dopants, we apply this solvent system with benzoquinone redox couples ($\text{BQ}/\text{BQ}^{\bullet-}$) to investigate tin-based mixed halide perovskites $\text{MASnI}_{3-x}\text{Br}_x$ using robotic synthesis and rapid screening based on scanning electrochemical microscopy, and to optimize compositions for photovoltaic performance.

1. EXPERIMENTAL SECTION

1.1 Materials. Methylamine (MA, 2M in methanol, Alfa Aesar), hydroiodic acid (HI, 57 wt.% in water, Alfa Aesar), methylammonium bromide tin iodide (MABr, 98%, Sigma-Aldrich), (SnI_2 , 99.9985% metals basis, Alfa Aesar), tin bromide (SnBr_2 , 99% metals basis, Alfa Aesar), N,N-Dimethylformamide (DMF, $\geq 99.9\%$, Sigma-Aldrich), Methylene chloride (CH_2Cl_2 , anhydrous, $\geq 99.9\%$, Sigma-Aldrich), Tetrahydrofuran (THF, anhydrous, $\geq 99.9\%$, Sigma-Aldrich), Ethyl acetate (EA, anhydrous, $\geq 99.8\%$, Sigma-Aldrich), *p*-Benzoquinone (BQ, $\geq 99.5\%$, Sigma-Aldrich), Tetrabutylammonium hexafluorophosphate (TBAPF_6 , $\geq 99.9\%$, Sigma-Aldrich). FTO-coated glass was obtained from Pilkington (Toledo, OH) as a substrate of the electrodes. The 15×15 mm FTO-coated glass squares were cleaned by successive sonication in ethanol and 2-propanol and rinsed with deionized water.

1.2 Preparation of Perovskite Film. $\text{MASnI}_{3-x}\text{Br}_x$ was spin-cast on fluorine-doped tin oxide (FTO) glass substrates from N,N-dimethylformamide (DMF) (Alfa Aesar) solution with the mixture of MAI, MABr, PbI_2 and PbBr_2 . MAI was synthesized by stirring 27.86 mL methylamine (2M in methanol, Alfa Aesar) and 30 mL of hydroiodic acid (57 wt.% in water, Alfa Aesar) in a 250 mL round bottomed flask in an ice bath under an argon atmosphere for 3 hours. After the reaction, the solvent was

evaporated using a rotary evaporator. A white powder, methyl ammonium iodide (MAI), was washed with diethyl ether by stirring the solution for 30 min, which was repeated three times, and then finally dried at 60 °C in vacuum oven for 24 h.^[12] The synthesized MAI white powder was mixed with PbI₂ (Alfa Aesar) in DMF at 125 °C for one hour.^[13]

1.3 Preparation of Photocatalyst Spot Array Electrodes. Spot array electrodes (an electrode composed of spots with each spot having a different composition) were fabricated by a previously reported method^[14, 15] using a CH Instruments dispenser. The precursor solutions (0.518 M in DMF) were dispensed on the FTO substrate to create the spot array electrode. To accomplish this the piezo-dispensing tip was moved to a programmed position over the FTO substrate, and dispensing drops (~ 100 pL/drop) of the precursor solution. The tin halide precursor solution, SnI₂ and SnBr₂, was dispensed first in a preprogrammed pattern onto the FTO substrate, followed by the second precursor solution, MAI and MABr, dispensed onto the FTO in an overlay pattern. The distance between photocatalyst spots on the array was about 150 μm with a spot diameter of approximately 350 μm. Each spot had a total of 25 drops, and the spot composition is reported as the relative number of drops of each precursor solution. In all cases, the composition of MASnI_{3-x}Br_x perovskites was controlled from the ratio of precursors. The prepared arrays were annealed at 125 °C for 1 h in air to form the MASnI_{3-x}Br_x perovskites.

1.4 Screening of Spot Array Electrodes. A schematic SECM setup has been described previously.^[14, 15] Briefly, a 400 μm diameter optical fiber was connected to a 150 W xenon lamp (Oriel) and was attached to the tip holder of a CHI 900B SECM. A 420 nm long-pass filter (removing the UV portion of the spectrum) was used for visible light only illumination in rapid screening experiments. The perovskite array was used as the working electrode and was placed in the bottom of a custom designed Teflon SECM cell with an O-ring (exposed area: 1.0 cm²). A Pt wire was used as the counter electrode, and a saturated Ag/AgNO₃ electrode was used as the reference electrode. The electrolyte consisted of 2

mM BQ and 0.1M TBAPF₆ (supporting electrolyte). Light from the xenon lamp was passed through the optical fiber, positioned perpendicular to the working electrode ~ 200 μm above the surface, to illuminate one spot on the working electrode at a time. The optical fiber tip was scanned across the spot array electrode with a scan rate of 500 μm/s, while a potential of – 0.6 V vs Ag/AgNO₃ was applied to the working electrode through the SECM potentiostat. Scanning over the spot arrays revealed two-dimensional images indicative of the generation of photocurrent on each spot.

1.5 Photoelectrochemical Measurements. The results on array electrodes were confirmed by PEC of perovskite films. The photoactivity of MASnI_{3-x}Br_x was measured in a photoelectrochemical cell. The films were used as working electrodes (0.27cm²) exposed to electrolyte solution and irradiation. All measurements were carried out in a borosilicate glass cell with a carbon counter electrode and Ag/AgNO₃ reference electrode (a silver wire immersed in 0.01 M silver nitrate in MeCN connected to the cell via a 0.10 M TBAPF₆ in deaerated CH₂Cl₂ salt bridge).^[5] All potentials are reported vs. Fc/Fc⁺ in deaerated CH₂Cl₂. The light source was irradiated through the electrolyte solution using full output of the Xe lamp with an incident light intensity of about 100 mW/cm². The supporting electrolyte was 0.1 M TBAPF₆ in deaerated CH₂Cl₂.

1.6 Instruments. A CH Instruments Model 760E electrochemical analyzer (Austin, TX) was used as a potentiostat for the experiments with the thin film electrodes. Illumination was with a Xenon lamp (XBO 150 W, Osram) at full output for UV–visible irradiation. Glancing incidence angle X-ray diffraction (XRD) measurements were performed by using D8 ADVANCE (Bruker, Fitchburg, WI) equipped with a Cu Kα radiation source where the incident angle was 0.4°. The film thickness was measured by scanning electron microscopy (SEM, Quanta 650 FEG, FEI Company, Inc., Hillsboro, OR). In the solar cell measurements, current (I) and voltage (V) readings were taken between the working electrode and the carbon counter electrode without external power source using a Keithley Model 2400 electrometer and a Xenon lamp solar simulator (Newport) equipped with an AM1.5G filter. For precursor dispensing, a CH Instruments model 1550 dispenser (Austin, TX) with a piezoelectric dispensing tip (Micro Jet AB-01-

60, MicroFab, Plano, TX) connected to an XYZ stage driven by a computer-controlled stepper-motor system (Newport) was used.

2. RESULTS AND DISCUSSION

2.1 Current-Potential Behavior. Cyclic voltammograms (CVs) were measured for 2 mM BQ, 2 mM BQ $\cdot^-$ in 0.1M TBAPF $_6$ at a glassy carbon electrode (diameter = 3 mm), displayed in Figure 1a. This wave shows peak splitting with the first wave at -0.90 V and the second at -0.70 V (formal potential = -0.80 vs. Fc/Fc $^+$). Under chopped illumination, a typical linear sweep voltammogram (LSV), as shown in Figure 1b exhibits demonstrates that a significant cathodic current flows with the onset at potentials negative by about 0.05 V vs. Fc/Fc $^+$, which should be near the perovskite valence band edge and correspond approximately to the flat band potential (E_{fb}). The photocurrent at potentials more positive than those for reduction at C electrode (Figure 1a) represents conversion of radiant to electrical energy. The photocurrent density of p-MASnI $_3$ perovskite materials at -0.70 vs. Fc/Fc $^+$ is 0.9 mA/cm 2 with the fill factor of ~ 0.55 . In comparison to tin-based perovskites, the photocurrent density and fill factor of MAPbI $_3$ perovskites are approximately 4.2 mA/cm 2 and 0.60, respectively. Figure 1 shows that the difference, ΔE , between the onset potential for the photocurrent, E_{on} , and the standard potential of the redox couple, E^0 , is 0.85 V. The individual current – potential behaviors of other MASnI $_{3-x}$ Br $_x$ perovskites in a 2mM BQ $\cdot^-$ /BQ solution were also investigated, and onset potentials of their photocurrents are listed in Table 1.

2.2 Characterization of MASnI $_{3-x}$ Br $_x$ Perovskites. The MASnI $_{3-x}$ Br $_x$ perovskite films were prepared by a one-step deposition and annealing process in a nitrogen glovebox. MASnI $_{3-x}$ Br $_x$ was tuned by varying the content of bromide in the precursor solution. The compositions of MASnI $_{3-x}$ Br $_x$ perovskite films were then characterized by X-ray diffraction (XRD) patterns. In Figure 3, the diffraction pattern of MASnI $_3$ is seen to correspond well to simulated and literature data^[8] and represents the tetragonal conformation of the perovskite structure^[8] Without doping any bromide, the

structure of MASnI_3 is the same with that of methylammonium lead halide perovskites, MAPbI_3 .^[5, 16] In this case, the diffraction patterns demonstrate that the replacement of the central metal atom does not have an influence on the overall crystal structure of the material (Figure 2). Because this series of $\text{MASnI}_{3-x}\text{Br}_x$ perovskites does not show any structural transitions at room temperature, they maintain the crystal structure of both end members, as given in Figure 2.

2.3 SECM Scanning of Perovskite Arrays. A method for rapid screening of semiconductor materials by utilizing a form of the modified SECM has been reported previously.^[17] Briefly, arrays composed of $\sim 350\text{-}\mu\text{m}$ diameter semiconductor spots with different compositions were deposited by a piezoelectric dispenser onto a conductive fluorine-doped tin oxide (FTO) substrate. The scanning tip of the modified SECM was replaced by a $300\text{ }\mu\text{m}$ fiber optic connected to a xenon lamp and was rapidly scanned over the array. This combinatorial screening technique can reduce the effort and material expended in the optimization process,^[18, 19] and offers rapid, automated evaluation of the photocurrent response at the substrate of different elements in the semiconductor array.^[15, 20] In this study, we performed a rapid screening analysis on $\text{MASnI}_{3-x}\text{Br}_x$ perovskite semiconductors with a modified SECM. The arrays contained three rows and seven columns of spots. To test the reproducibility, the first and second seven-spot rows are pristine MASnI_3 perovskites. The photocurrents of all 14 spots are nearly identical ($\sim 0.95 \pm 0.2\text{ }\mu\text{A}$). The third seven-spot row we analyzed is spot arrays of $\text{MASnI}_{3-x}\text{Br}_x$ perovskite materials with the value of x from 0 to 3. We observe that the photocurrent density of $\text{MASnI}_{3-x}\text{Br}_x$ perovskite materials decreases with increasing bromide content, consistent with previously reported results.^[9]

While it has been established that the maximum power conversion efficiency (PCE) of photovoltaic devices may be increased by introduction of bromide in MASnI_3 due to the larger open-circuit voltage,^[21] SECM rapid screening of $\text{MASnI}_{3-x}\text{Br}_x$ materials enables determination of the

optimum amount of bromide in the $\text{MASnI}_{3-x}\text{Br}_x$ perovskite. Employing the SECM technique, we screened spot array electrodes to determine the dependence of photocurrent response on $\text{MASnI}_{3-x}\text{Br}_x$ perovskites with bromide content ranging from $x=0$ to $x=3$. The rapid screening results showed that MASnI_3 gave rise to the highest photocurrent ($\sim 0.95 \mu\text{A}$) under irradiation. The photocurrent density decreases with increasing the content of bromide, as presented in Figure 3, which shows a representative example of the SECM result of a $\text{MASnI}_{3-x}\text{Br}_x$ spot array electrode under irradiation. The colors in Figure 2 represent the photocurrent for BQ reduction at an applied potential of $-0.6 \text{ V vs Fc/Fc}^+$ with browns representing higher currents and greens representing lower currents. The leftmost spot on third seven-spot row of the spot array represents pure MASnI_3 , and then moving right, each spot has an increased bromide content in $\text{MASnI}_{3-x}\text{Br}_x$ perovskites, as shown by the schematic below the SECM image.

2.4 Capacitance Measurements. Determination of the energy levels of the semiconductor electrode with reference to the solution energy level is beneficial for maximizing the performance of a PEC solar cell. The valence band edge, E_v , and flat band potential, E_{fb} , can be determined by capacitance measurements (Mott-Schottky plots), i.e. capacitance of the semiconductor/electrolyte interface as a function of the applied potential. This capacitance is assumed to be the semiconductor space-charge capacitance, where E_{fb} can be estimated from the potential-axis intercept.^[22] MS analysis of p- MASnI_3 electrode in $\text{CH}_2\text{Cl}_2/0.1 \text{ M TBAPF}_6$ for frequencies of 500 Hz, 2 kHz, and 5 kHz are shown in Figure 4. The x-intercepts of the solid lines indicate that E_{fb} appears to be $\sim 0.06 \pm 0.01 \text{ V vs Fc/Fc}^+$, which is close to the onset photopotential of p- MASnI_3 in a $\text{BQ}^{\bullet-}/\text{BQ}$ system (onset potential = 0.05 vs. Fc/Fc^+). The MS plots for other $\text{MASnI}_{3-x}\text{Br}_x$ perovskite materials were also measured and their flatband potentials are displayed in Table 1. Clearly, E_{fb} is dependent on the content of bromide, and ΔE increases with increasing bromide content.

2.5 PEC solar cells. The LSV behavior can be used as a guide for the construction of PEC photovoltaic cells, where the open-circuit potential of the semiconductor ideally (in the absence of recombination) approaches ΔE . The photocurrent responses found in the LSV experiments with $\text{MASnI}_{3-x}\text{Br}_x$ were recognizable, clearly indicating that the responses are not caused by conductivity changes under illumination. Thus, the experimental results between actual two-electrode photovoltaic cells are also of interest. The PEC behavior of these electrodes was investigated in a cell. The following cells were prepared: $\text{p-MASnI}_{3-x}\text{Br}_x / \text{CH}_2\text{Cl}_2$, TBAPF_6 (0.1M), $\text{BQ}^{\bullet-}$ (2 mM), BQ (2 mM)/C ($x = 0$ to 3). The $\text{p-MASnI}_{3-x}\text{Br}_x$ photocathode and the reticulated vitreous carbon counter electrode were spaced apart with a Teflon gasket about 0.30 mm, with the $\text{p-MASnI}_{3-x}\text{Br}_x$ electrode about < 1 mm away from the cell window. To decrease the light adsorption by the intensely colored redox species, the $\text{BQ}^{\bullet-}/\text{BQ}$ solutions were kept at a low concentration. The overall optical-to-electrical energy conversion efficiencies for $\text{p-MASnI}_{3-x}\text{Br}_x$ perovskite liquid-junction solar cells are summarized in Figure 5. It is obvious that the $\text{MASnI}_{0.5}\text{Br}_{2.5}$ based PEC solar cell exhibits the highest efficiency. In figure 6, PEC photovoltaic cells, with configurations of $\text{p-MASnI}_{0.5}\text{Br}_{2.5} / \text{CH}_2\text{Cl}_2$, BQ (2 mM), $\text{BQ}^{\bullet-}$ (2 mM)/carbon and $\text{p-MASnI}_3 / \text{CH}_2\text{Cl}_2$, BQ (2 mM), $\text{BQ}^{\bullet-}$ (2 mM)/carbon, show open-circuit photovoltages of 0.8 V and 0.7V, as well as short-circuit current densities of 3.15 mA/cm^2 and 3.40 mA/cm^2 under 100 mW/cm^2 irradiation. The overall optical-to-electrical energy conversion efficiencies are 1.51% and 1.25%, respectively.

In addition, the photocurrent responses for the $\text{MASnI}_{0.5}\text{Br}_{2.5}$ and MASnI_3 in 2 mM $\text{BQ}^{\bullet-}/\text{BQ}$ system were measured as a function of wavelength over the range 350 to 980 nm using a Xe lamp. The incident photon-to-electron conversion efficiencies (IPCEs) were calculated and are plotted in Figure 7. For $\text{MASnI}_{0.5}\text{Br}_{2.5}$, it reaches a maximum of 39% at 445 nm and sharply declined at around 710 nm. The IPCEs of MASnI_3 perovskites moderately increased to 33% at 790 nm and then decreased at longer wavelength. Integration of the IPCE spectra for $\text{MASnI}_{0.5}\text{Br}_{2.5}$ and MASnI_3 perovskites gives current densities of 3.0 mA/cm^2 and 3.5 mA/cm^2 , in good agreement with the current densities measured using

the solar simulator. The stability was monitored for unencapsulated p-MASnI_{0.5}Br_{2.5} and p-MASnI₃ perovskite PEC solar cells in ambient atmosphere under irradiation at higher power intensity (150 mW/cm²), as shown in Figure 8. The normalized efficiency for p-MASnI_{0.5}Br_{2.5} perovskites is reduced by 70% for 120 min. However, p-MASnI₃-based PEC solar cells degraded completely within 100 min. We thus demonstrate that the MASnI_{0.5}Br_{2.5} based solar cell shows improved stability compared to that for p-MASnI₃ perovskites.

3. SUMMARY AND CONCLUSION

We have optimized p-type methylammonium tin halide (MASnI_{3-x}Br_x)-based liquid junction PEC solar cells by using a modified SECM imaging apparatus equipped with an optical fiber as a screening tip. We demonstrate that MASnI_{0.5}Br_{2.5} shows higher solar cell efficiency and longer stability in a photoelectrode array system containing a series of MASnI_{3-x}Br_x perovskite semiconductors on the FTO substrate. The PCE of liquid-junction solar cells is increased to the 1.51% as a result of the introduction of bromine. With regards to MASnI_{0.5}Br_{2.5} perovskites, their lifetime is prolonged compared to that of MASnI₃-based devices.

AUTHOR INFORMATION

Corresponding Author

ajbard@mail.utexas.edu

Author Contributions

[§]These authors contributed equally

Acknowledgements

The authors gratefully acknowledge the U.S. Department of Energy SISGR (DE-FG02-09ER16119) and the Robert A. Welch Foundation (F-0021).

Figure 1

Figure 1. Voltammetric curves of p-MASnI₃ and C in CH₂Cl₂ containing 2 mM BQ, 2 mM BQ^{•-} and 0.1M TBAPF₆ (supporting electrolyte). Light source, 100 mW/cm² xenon lamp. Scan rate = 50 mV/sec. (a) cyclic voltammogram at C electrodes (b) LSV characteristics under chopped illumination on p-MASnI₃ (b).

Figure 2

Figure 2. X-ray diffraction patterns of MASnI_{3-x}Br_x perovskite films with increasing content of bromide.

Figure 3

Figure 3. SECM images for the absolute photocurrent of MASnI_{3-x}Br_x perovskites under irradiation.

The color represents the measured photocurrent shown in the scale bar below the SECM image. The

first and second seven-spot rows are pure MASnI_3 perovskites. The third seven-spot row represents $\text{MASnI}_{3-x}\text{Br}_x$ perovskite materials in each spot in the array electrode. The photocurrent shown is for 2 mM BQ reduction with 0.1M TBAPF_6 supporting electrolytes in CH_2Cl_2 measured at an applied potential of -0.6 V vs Fc/Fc^+ .

Figure 4

Figure 4. Mott-Schottky plot of p-MASnI₃ in CH_2Cl_2 containing 0.1 M TBAPF_6 supporting electrolyte at 500 Hz, 2000 Hz, and 5000 Hz. The solid lines are linear fits to the experimental data.

Table 1

Table 1. Flatband potential and onset Potential of Photocurrent^a

MASnI _{3-x} Br _x	E_{fb} , V	E_{on} , V vs. Fc/Fc ⁺	$\Delta E = E_{on} - E^0 = E_{on} - (-0.8)$, V ^b
x = 0.0	0.06 ± 0.01	0.05	0.85
x = 0.5	0.09 ± 0.01	0.10	0.90
x = 1.0	0.13 ± 0.01	0.15	0.95
x = 1.5	0.21 ± 0.01	0.20	1.00
x = 2.0	0.25 ± 0.01	0.25	1.05
x = 2.5	0.28 ± 0.01	0.30	1.10
x = 3.0	0.33 ± 0.01	0.35	1.15

^aThe onset potential of photocurrent V_{on} here is defined as the potential at which 1% of the limiting or maximal photocurrent is observed. ^b ΔE is the difference between the onset potential for the photocurrent, E_{on} , and the formal potential of the BQ^{•-}/BQ redox couple, E^0 , which is -0.8 V vs Fc/Fc⁺.

Figure 5

Figure 5. Efficiencies of MASnI_{3-x}Br_x-based PEC solar cells under irradiation with a 100 mW/cm² xenon lamp focused onto the photoelectrode. The optical path through the solution was about 0.3 mm.

Figure 6

Figure 6. Steady-state current density – voltage relation for p-MASnI_{0.5}Br_{2.5} / CH₂Cl₂, BQ (2 mM), BQ •– (2 mM)/C and p-MASnI₃ / CH₂Cl₂, BQ (2 mM), BQ •– (2 mM)/C PEC solar cells under irradiation with a 100 mW/cm² xenon lamp focused onto the photoelectrode. The optical path through the solution was about 0.3 mm.

Figure 7

Figure 7. IPCE spectra for p-MASnI_{0.5}Br_{2.5} and p-MASnI₃ perovskite PEC solar cells.

Figure 8

Figure 8. Normalized efficiency of unencapsulated p-MASnI_{0.5}Br_{2.5} and p-MASnI₃ perovskite PEC solar cells in ambient atmosphere. The MASnI_{0.5}Br_{2.5} and p-MASnI₃ photoelectrodes was irradiated by a 150 mW/cm² Xe lamp. The optical path through the solution was about 0.3 mm.

References

- [1] Etgar L, Gao P, Xue Z, Peng Q, Chandiran AK, Liu B, et al. Mesoscopic $\text{CH}_3\text{NH}_3\text{PbI}_3/\text{TiO}_2$ Heterojunction Solar Cells. *Journal of the American Chemical Society* 2012;134:17396-9.
- [2] Kagan C, Mitzi D, Dimitrakopoulos C. Organic-inorganic hybrid materials as semiconducting channels in thin-film field-effect transistors. *Science* 1999;286:945-7.
- [3] Kojima A, Ikegami M, Teshima K, Miyasaka T. Highly luminescent lead bromide perovskite nanoparticles synthesized with porous alumina media. *Chemistry Letters* 2012;41:397-9.
- [4] Gao P, Gratzel M, Nazeeruddin MK. Organohalide lead perovskites for photovoltaic applications. *Energy & Environmental Science* 2014;7:2448-63.
- [5] Hsu H-Y, Ji L, Ahn HS, Zhao J, Yu ET, Bard AJ. A Liquid Junction Photoelectrochemical Solar Cell Based on p-Type $\text{MeNH}_3\text{PbI}_3$ Perovskite with 1.05 V Open-Circuit Photovoltage. *Journal of the American Chemical Society* 2015;137:14758-64.
- [6] Hsu H-Y, Vella JH, Myers JD, Xue J, Schanze KS. Triplet Exciton Diffusion in Platinum Polyyne Films. *The Journal of Physical Chemistry C* 2014;118:24282-9.
- [7] Zhou Y, Zhu K. Perovskite Solar Cells Shine in the “Valley of the Sun”. *ACS Energy Letters* 2016;1:64-7.
- [8] Stoumpos CC, Malliakas CD, Kanatzidis MG. Semiconducting tin and lead iodide perovskites with organic cations: phase transitions, high mobilities, and near-infrared photoluminescent properties. *Inorganic chemistry* 2013;52:9019-38.
- [9] Hao F, Stoumpos CC, Cao DH, Chang RP, Kanatzidis MG. Lead-free solid-state organic-inorganic halide perovskite solar cells. *Nature Photonics* 2014;8:489-94.
- [10] Noel NK, Stranks SD, Abate A, Wehrenfennig C, Guarnera S, Haghighirad A-A, et al. Lead-free organic-inorganic tin halide perovskites for photovoltaic applications. *Energy & Environmental Science* 2014;7:3061-8.
- [11] Niu G, Guo X, Wang L. Review of recent progress in chemical stability of perovskite solar cells. *Journal of Materials Chemistry A* 2015;3:8970-80.
- [12] Im J-H, Lee C-R, Lee J-W, Park S-W, Park N-G. 6.5% efficient perovskite quantum-dot-sensitized solar cell. *Nanoscale* 2011;3:4088-93.
- [13] Zhao Y, Zhu K. $\text{CH}_3\text{NH}_3\text{Cl}$ -Assisted One-Step Solution Growth of $\text{CH}_3\text{NH}_3\text{PbI}_3$: Structure, Charge-Carrier Dynamics, and Photovoltaic Properties of Perovskite Solar Cells. *The Journal of Physical Chemistry C* 2014;118:9412-8.
- [14] Lee J, Ye H, Pan S, Bard AJ. Screening of photocatalysts by scanning electrochemical microscopy. *Analytical chemistry* 2008;80:7445-50.
- [15] Hsu H-Y, Ji L, Du M, Zhao J, Yu ET, Bard AJ. Optimization of $\text{PbI}_2/\text{MAPbI}_3$ Perovskite Composites by Scanning Electrochemical Microscopy. *The Journal of Physical Chemistry C* 2016;120:19890-5.
- [16] Lee MM, Teuscher J, Miyasaka T, Murakami TN, Snaith HJ. Efficient hybrid solar cells based on meso-superstructured organometal halide perovskites. *Science* 2012;338:643-7.
- [17] Fernández JL, Mano N, Heller A, Bard AJ. Optimization Of “Wired” Enzyme O_2 -Electroreduction Catalyst Compositions by Scanning Electrochemical Microscopy. *Angewandte Chemie* 2004;116:6515-7.
- [18] Fernández JL, Mano N, Heller A, Bard AJ. Optimization Of “Wired” Enzyme O_2 -Electroreduction Catalyst Compositions by Scanning Electrochemical Microscopy. *Angewandte Chemie International Edition* 2004;43:6355-7.

- [19] Mano N, Kim H-H, Heller A. On the relationship between the characteristics of bilirubin oxidases and O₂ cathodes based on their “wiring”. *The Journal of Physical Chemistry B* 2002;106:8842-8.
- [20] Hao F, Stoumpos CC, Chang RP, Kanatzidis MG. Anomalous band gap behavior in mixed Sn and Pb perovskites enables broadening of absorption spectrum in solar cells. *Journal of the American Chemical Society* 2014;136:8094-9.
- [21] Wang L, McCleese C, Kovalsky A, Zhao Y, Burda C. Femtosecond Time-Resolved Transient Absorption Spectroscopy of CH₃NH₃PbI₃ Perovskite Films: Evidence for Passivation Effect of PbI₂. *Journal of the American Chemical Society* 2014;136:12205-8.
- [22] Nagasubramanian G, Gioda AS, Bard AJ. Semiconductor Electrodes XXXVII. Photoelectrochemical Behavior of p-Type in Acetonitrile Solutions. *Journal of the Electrochemical Society* 1981;128:2158-64.