**Electrochromic polymers electrochemically polymerized from 2, 5
–dithienylpyrrole (DTP) with different triarylamine units: Synthesis,
characterization and optoelectrochemical properties**

Shuwei Cai^a, Hailin Wen^a, Shuzhong Wang^a, Haijun Niu^a, Cheng Wang^a, Xiankai
Jiang^a, Xuduo Bai^a, Wen Wang^b

Abstract

A series of polymers, consisting both 2, 5-dithienylpyrrole (DTP) and different triarylamine units were synthesized by electrochemical oxidative polymerization. The structures of the monomers, including N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)-N-Phenyl Naphthalene-2-amine (DTP-PNA), 4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N,N-diphenylaniline (DTP-DPA), 4-(tert-butyl)-N-(4-(tert-butyl)phenyl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl) aniline (DTP-TBPA), 4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)-N-(p-tolyl)aniline (DTP-PTA-DTP), and N-(4-(9H-carbazol-9-yl)phenyl

1)-4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-
2
3 yl)phenyl)aniline (DTP-CPA-DTP) were elucidated by FT-IR, ¹H NMR, ¹³C NMR,
4
5
6 Mass spectra (MS) and the performance and morphology of resulting polymers
7
8
9 (P(DTP-PNA), P(DTP-DPA), P(DTP-TBPA), P(DTP-PTA-DTP), and
10
11 P(DTP-CPA-DTP)) were determined by cyclic voltammetry (CV), ultra-visible-near
12
13 infrared (UV–Vis–NIR) spectrophotometer, and scanning electron microscopy
14
15 (SEM), respectively. The polymers exhibit good reversible multicolor in the visible
16
17 and NIR region (original yellowish to dusty blue until violet occurred), with better
18
19 coloration efficiency (CE), fast response time.
20
21
22
23
24
25
26
27

28 Key words

29
30
31 2, 5-dithienylpyrrole; triarylamine; electrochemical oxidative polymerization;
32
33
34 optoelectronic functional material; electrochromic.
35
36
37
38

39 1. Introduction

40
41
42 At present, electrochromic (EC) polymers, which exhibit reversible absorption
43
44 spectral changes by changing the applied potentials, have attained much
45
46 prominence[1-8]. They are used widely in our daily life, such as smart windows,
47
48 optical displays and e-paper due to their high optical contrast, stable oxidation states,
49
50 excellent switching reproducibility and flexibility[9]. Organic conjugated polymers
51
52
53 have been generally considered as one of the most prospective intelligent materials,
54
55
56 such as polythiophene, polypyrrole, polyaniline and polycarbazole, owing to their
57
58
59
60
61
62
63
64
65

1 good conductivity, photochemical and electrochromic properties compared with
2
3 inorganic and small organic compounds[10].
4
5

6 As has been stated earlier, polythiophene and polypyrrole derivatives have the
7
8 great optoelectrochemical performance[11,12]. The advantages of them are the lower
9
10 energy gap, better conductivity, good stability, photochemical properties,
11
12 electrochromic properties and film-forming properties, which make them suitable to
13
14 design the electrochromic devices, sensors and solar cells[13]. The polythiophene
15
16 and polypyrrole can be obtained chemically or electrochemically, however, the
17
18 potential which is used to oxidize the thiophene monomer, meanwhile, often leads to
19
20 overoxidation of the polymer itself, because the oxidation potential is a little higher
21
22 and reaches the potentials of the polythiophene selfoxidation. This is known as the
23
24 “polythiophene paradox”[14]. Similar problem occurred with polypyrrole. Although
25
26 we can prevent the paradox from reducing the oxidation potentials, the performances
27
28 will degrade at the same time. In order to avoid this phenomenon and improve the
29
30 performances of the polymer, the dimers and trimers with two or more
31
32 heteroaromatic rings, such as dithiophene, trithiophene and thienylpyrrole, having
33
34 lower oxidized potential without destroying their optical and mechanical
35
36 performance, have been selected as monomers for electropolymerization [15].
37
38
39
40
41
42
43
44
45
46
47
48
49

50 From previous article, Ferraris and Skiles [16] obtained the
51
52 2,5-bis(2-thienyl)-1H-pyrrole polymer (PSNS) by the direct polymerization of
53
54 thiophene and pyrrole derivative (SNS) in 1987 firstly. From that moment on, many
55
56 researchers have synthesized a series of different polymer of
57
58
59
60
61
62
63
64
65

1 2,5-bis(2-thienyl)-1H-pyrrole, and discussed their physical and chemical
2
3 properties[17-20]. And furthermore, from beginning of 2000, Enric Brillas has begun
4
5 to study their electrochemical performance. Later on, Chane Ching [21], L. Toppare
6
7 [22,23] and A. Cihaner [24-27] synthesized a large number of polymers and studied
8
9 their photoelectrochemical properties in detail. For example, Toppare proved that the
10
11 new conducting polymers of 1-(4-nitrophenyl)-2,5-di (2-thienyl) -1H-pyrrole can be
12
13 used as the immobilization matrices for invertase. In A. Cihaner's research, a series
14
15 of polymers of 1-(1-naphthyl)-2,5-di(thiophen-2-yl)-1H-pyrrole, 1-(2-naphthyl)-2,5-d
16
17 i(thiophen-2-yl)-1H-pyrrole, 1-(9H-fluoren-2-yl) -2,5-di(thiophen-2-yl)-1H-pyrrole
18
19 and 1-(benzo-15-crown-5)-2,5-di(thiophen-2-yl)- 1H-pyrrole were synthesized by
20
21 electrochemical polymerization, which exhibited multielectrochromic behavior
22
23 (yellow, green, blue and violet).
24
25
26
27
28
29
30
31
32

33
34 On the other hand, Liou and Hsiao's groups have been making efforts on the
35
36 triarylamine compounds[28], which attracted much interest as EC materials because
37
38 of their relative high mobilities and low ionization potentials[29]. Especially, Hsiao's
39
40 group has done some electropolymerization of poly(amide-triarylamine)s containing
41
42 triptycene units, which exhibit reversible electrochemical oxidation process, higher
43
44 coloration efficiency and stronger color changes[30]. In addition, You's group
45
46 synthesized poly-DTP-Ph-TPA by electropolymerization, which proved the polymer
47
48 has the high contrast and a very short response time[31]. In J. S. Zhao's group, they
49
50 obtained a kind of polymer based on 4,4'-di(N-carbazoyl)biphenyl and 2,
51
52 2'-bithiophene units by electropolymerization in 2011[32]. What's more, J. K. Xu's et.
53
54
55
56
57
58
59
60
61
62
63
64
65

al designed and synthesized the various length polyether chains bridged thiophene (T-E-T) and 2,2-bithiophene (BT-E-BT) groups [33].

Compared with the traditional method, named chemical routes to obtain the electrochromic (EC) polymer, electrochemical polymerization has several advantages, such as it saves the time for coating the film [34], requires only a small quantity of monomer to synthesize the polymer [35], can control the thickness of the films [36] and provides mild experimental conditions at room temperature [37].

However, up to now, there is not intensive and systematical research on the effect of different triarylamine substituted group on the photoelectrochemical properties. Thus, in this study, we synthesized successfully five new monomers, which containing 2, 5-dithienylpyrrole (DTP) and different aromatic amines groups. Then, the polymer films were prepared on the conductive substrates directly by electrochemical oxidative polymerization. Finally, we researched the properties of the different triarylamine substituted group on 2,5-bis(2-thienyl)-1H-pyrrole based polymer and discussed the performance effect of different triarylamine units. These polymers have the both advantages of the monomers. Meanwhile, 2, 5-dithienylpyrrole derivatives could be widely used in the optoelectronic field due to their good environmental stability and electrical chemical properties [38].

2. Experimental

2.1 Materials

Thiophene, succinyl chloride, aluminum chloride and p-toluenesulfonic acid

(PTSA) were supplied from TCI Co. The starting material, 1, 4-di(thiophen-2-yl)butane-1,4-dione was prepared from Paal-Knorr reaction by the method proposed in the literature [39,40] ([Scheme1](#)), and N-(naphthalen-2-yl)-N-phenylbenzene-1,4-diamine (TPA-1), N,N-diphenyl benzene-1,4-diamine (TPA-2), N,N-bis(4-(tert-butyl)phenyl)benzene-1,4-diamine (TPA-3), N-(4-aminophenyl)-N-(p-tolyl)benzene-1,4-diamine (TPA-4) and N-(4-(9H-carbazol-9-yl)phenyl)-N-(4-aminophenyl)benzene-1,4-diamine (TPA-5) were synthesized according to the method similarly described in the literature [41]. Dichloromethane, toluene, and dimethyl sulfoxide (DMSO) were purified by distillation over calcium hydride. All the other reagents and solvents were analytical grade and without further purification. Flash column chromatography purification was carried out on silica gel (200-300 mesh).

2.2 Synthesis of N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)-N-Phenyl Naphthalene-2-amine (DTP-PNA)

A three-neck round-bottomed flask equipped with a Dean-stark trap, a nitrogen inlet and a reflux condenser was charged with 0.25g (1.00mmol) compound 1, 0.3105g (1.00mmol) TPA-1, 0.0264g (0.14mmol) PTSA, and 80ml toluene. The reaction mixture was stirred and refluxed for 3 days under N₂ atmosphere. After cooling to room temperature, evaporation of the toluene, adding enough CH₂Cl₂ to dissolve solid, then **undissolved** solid was separated under reduced pressure, evaporation of the filtrate, followed by flash column chromatography (SiO₂ column,

elution with dichloromethane) afforded the crude compound. Finally, the desired product was obtained as yellow solid followed by flash column chromatography (SiO₂ column, elution with dichloromethane and petroleum ether). Other compounds 4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N,N-diphenylaniline (DTP-DPA), 4-(tert-butyl)-N-(4-(tert-butyl)phenyl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)aniline (DTP-TBPA), 4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)-N-(p-tolyl)aniline (DTP-PTA-DTP), N-(4-(9H-carbazol-9-yl)phenyl)-4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)-N-(4-(2,5-di(thiophen-2-yl)-1H-pyrrol-1-yl)phenyl)aniline (DTP-CPA-DTP) were prepared by an analogous procedure. The synthetic route of the monomers and polymers are shown in [Scheme 2](#).

[Scheme 2](#)

DTP-PNA: FTIR: (KBr, ν/cm^{-1}): 3044, 844, 820, 760, 694; ¹H NMR: (DMSO-d₆, 400MHz): 7.90 (d, 1 H), 7.85 (d, 1 H), 7.71 (d, 1 H), 7.49 (m, 2 H), 7.45 (m, 1 H), 7.43 (m, 1 H), 7.40 (m, 2 H), 7.36 (s, 2 H), 7.30 (d, 1 H), 7.23 (d, 1 H), 7.16 (d, 1 H), 7.08 (d, 2 H), 6.96 (m, 1 H), 6.82 (d, 2 H), 6.17 (d, 2 H); ¹³C-NMR (DMSO-d₆, 100MHz): 145.7, 143.3, 142.7, 140.5, 139.9, 138.6, 138.1, 135.9, 134.8, 134.6, 133.7, 132.1, 130.8, 129.8, 129.3, 128.4, 127.8, 127.1, 126.7, 126.6, 125.3, 125.2, 124.7; MS (EI) (m/z): [M]⁺ calcd for C₃₄H₂₄N₂S₂, 524.0; found, 524.07.

DTP-DPA: FTIR: (KBr, ν/cm^{-1}): 3050, 841, 826, 760, 732, 694; ¹H NMR: (DMSO-d₆, 400MHz): 7.34 (d, 2 H), 7.21 (d, 2 H), 7.11 (m, 2 H), 7.09 (m, 2 H), 7.01 (t, 2 H), 6.93 (d, 2 H), 6.80 (d, 4 H), 6.56 (d, 2 H); ¹³C-NMR (DMSO-d₆, 100MHz):

1 148.7, 147.6, 135.4, 131.9, 131.1, 130.5, 129.7, 127.1, 125.3, 124.3, 124.0, 123.7,
2
3 122.9; MS (EI) (m/z): $[M]^+$ calcd for $C_{30}H_{22}N_2S_2$, 474.0; found, 474.08.
4
5

6 **DTP-TBPA:** FTIR: (KBr, ν/cm^{-1}): 3051, 844, 830, 755, 730; 1H NMR: (DMSO- d_6 ,
7
8 400MHz): 7.38 (d, 2 H), 7.33 (d, 2 H), 7.18 (d, 2 H), 7.04 (m, 2 H), 6.95 (d, 4 H),
9
10 6.93 (d, 2H), 6.80 (m, 4H), 6.56 (d, 2H), 1.27(s, 18H); ^{13}C -NMR (DMSO- d_6 ,
11
12 100MHz): 148.9, 146.5, 144.5, 135.3, 131.1, 130.5, 127.2, 126.3, 124.5, 123.9,
13
14 121.9, 109.2, 34.4, 31.5; MS (EI) (m/z): $[M]^+$ calcd for $C_{38}H_{38}N_2S_2$, 586.0; found,
15
16 586.2.
17
18
19
20
21

22 **DTP-PTA-DTP:** FTIR: (KBr, ν/cm^{-1}): 3101, 859, 787, 631; 1H NMR:
23
24 (DMSO- d_6 , 400MHz): 7.33(d, 4H), 7.30(q, 4H), 7.28(d, 4H), 7.25(d, 4H), 7.12(d,
25
26 4H), 6.93(q, 2H), 6.80(d, 4H), 6.57 (d, 4H), 2.30(s, 3H); ^{13}C -NMR (DMSO- d_6 ,
27
28 100MHz): 148.1, 143.7, 134.5, 132.6, 131.8, 131.1, 130.4, 127.7, 126.9, 125.2,
29
30 124.4, 123.6, 122.5, 109.5, 20.9; MS (EI) (m/z): $[M]^+$ calcd for $C_{43}H_{31}N_3S_4$, 717.0;
31
32 found, 717.2.
33
34
35
36
37
38

39 **DTP-CPA-DTP:** FTIR: (KBr, ν/cm^{-1}): 2963, 1505, 802, 750, 688; 1H NMR:
40
41 (DMSO- d_6 , 400MHz): 8.27(d, 4H), 7.76(d, 2H), 7.64(d, 4H), 7.48(d, 4H) 7.42(d, 2H),
42
43 7.40(s, 2H), 7.38(d, 4H), 7.32(s, 2H), 6.96(t, 2H), 6.86(d, 4H), 6.64 (d, 4H);
44
45 ^{13}C -NMR (DMSO- d_6 , 100MHz): 140.6, 138.4, 137.3, 135.0, 131.7, 130.4, 127.6,
46
47 127.0, 126.2, 124.7, 124.4, 123.8, 120.4, 110.3, 109.6; MS (EI) (m/z): $[M]^+$ calcd for
48
49 $C_{54}H_{36}N_4S_4$, 868.0, found, 868.1.
50
51
52
53
54
55
56
57
58

59 2.3 Electrochemical polymerization

60
61
62
63
64
65

Electrochemical polymerization of the DTP-TPAs were accomplished via potential dynamic method in a compartment cell furnished with Pt electrode, ITO working electrode, reference electrode, in the presence of 0.10mol/L TBAP (tetrabutylammonium perchlorate) of the CH_2Cl_2 , 2×10^{-3} mol/L monomer of the CH_2Cl_2 . The electrodes coated with the polymer were rinsed with CH_2Cl_2 in order to get rid of the salts and unreacted monomer.

2.4 Instrument

The obtained compounds were characterized by the following techniques: FT-IR spectra were recorded on a PerkinElmer Spectrum 100 Model FT-IR spectrometer. ^1H NMR and ^{13}C NMR spectra were measured on a Bruker AC-400 MHz and AC-100 MHz spectrometer using DMSO-d_6 as solvent. Mass Spectra (MS) was performed on a Finnigan LC-MS/MS system (Thermo Electron, San Jose, CA, USA).

The cyclic voltammogram (CV) was conducted on a CH Instruments 660A electrochemical analyzer with the use of a three-electrode cell at the different scan rate with a 0.1mol/L LiClO_4 as the supporting electrolyte under nitrogen atmosphere in dried acetonitrile (CH_3CN). Geometry optimizations were carried out using the B3LYP functional as implemented in Gaussian 98 program.

For the electrochromic investigations, the films were deposited on an ITO-coated glass substrate by electrochemical polymerization, and a home-made electrochemical cell was built from a commercial UV-vis cuvette. The cell was

placed in the optical path of the sample light beam in a UV-vis spectrophotometer, which allowed us to acquire electronic absorption spectra under potential control in a 0.1 mol/L LiClO₄/CH₃CN.

Colorimetry measurements were performed by using Conica Minolta CS-200 chromameter with viewing geometry as recommended by Commission Internationale de l'Eclairage (CIE). According to the CIE system, the color is made up of three aspects: luminance (L), hue (a), and saturation (b). These values (L; a; b) were measured at the neural, intermediate and fully oxidized state of the electrochromic polymer on the ITO/glass surface.

SEM measurement was carried out on a S4800 instrument with accelerating potentials of 2 kV, and the samples were sputtered with Pt prior to observation.

3. Results and Discussion

3.1 Synthesis and Characterization

In this study, we devoted our efforts to synthesize a series of 2, 5-dithienylpyrrole derivative monomers and obtain polymer films by electrochemical polymerization. The monomers were prepared in two steps mainly (Scheme 1). The starting reagent 1, 4-di(2-thienyl)-1, 4-butanedione and five kinds of TPAs compounds were synthesized according to the previously reported work. Then the monomers were prepared by the condensation reaction, Knorr-Paal reaction, between compound 1 (1, 4-di(2-thienyl)-1, 4-butanedione) and TPAs in presence of PTSA enough as the catalyst in toluene, and yellow crude products were obtained.

1 Finally, the polymer films were fabricated via electrochemical polymerization. And
2
3 structural identification of these compounds was elucidated by using FT-IR, ^1H
4
5 NMR, ^{13}C NMR, MS techniques after each reaction.
6
7

8
9 After condensation reaction, molecular structures of the monomers (DTP-TPAs)
10
11 were also identified by FT-IR, ^1H NMR spectra, ^{13}C NMR spectra and MS (Seen in
12
13 Supporting Information [Fig.S1-S5](#)). On the one hand, in the FT-IR of DTP-PNA, we
14
15 can observe three peaks at 820cm^{-1} , 760cm^{-1} and 621cm^{-1} , which attribute to β/β'
16
17 -hydrogens of thiophene rings, β -hydrogens of pyrrole ring and α -hydrogens of
18
19 thiophene rings respectively[42]. Compared with DTP-PNA, the P(DTP-TPA)'s peak
20
21 at 621cm^{-1} disappears but the other peaks still exist. On the other hand, in the ^1H
22
23 NMR spectra, the characteristic amine band which was attributed to TPA
24
25 disappeared by the accomplishment of the synthesis of DTP-TPAs. The tall singlet
26
27 signal at 6.58 ppm belongs to the protons (H-4) on the pyrrole unit of these
28
29 DTP-TPAs monomers. Taking DTP-DPA for example, the integrals of the proton
30
31 (H-4) and the other protons are 0.10 and 1.00, respectively, which are consistent with
32
33 the theoretical values. In conclusion, these results indicate that the presence of
34
35 thiophene and pyrrole rings in the polymer structure.
36
37
38
39
40
41
42
43
44
45
46
47
48
49

50 3.2 Electrochemical polymerization of the DTP-TPAs 51

52
53 The P(DTP-TPA)s coated on ITO electrodes were obtained by the
54
55 electrochemical polymerization of DTP-TPA in 0.1mol/L TBAP dissolved in CH_2Cl_2
56
57 solutions at the room temperature. The scan potentials were added between 0.0V and
58
59
60
61
62
63
64
65

1 1.5V at the rate of 50mV/s. As seen in the first cycle ([Fig.1](#) and [Fig.S6](#)), the
2
3 monomer oxidation peak appeared at 1.10V, 1.12V, 1.05V, 0.86V and
4
5 0.94V, respectively, which resulted from 2, 5-dithienylpyrrole (DTP) group[43].
6
7 However, it was a little different from the previous report, perhaps due to the TPA
8
9 unit inserting the monomer, which influencing the potential. During the second scan,
10
11 a couple of new reversible redoxidation peaks were observed for different monomers
12
13 at 0.72V/0.82V 、 0.87V/0.70V, 0.90V/0.84V, 1.01V/0.62V, and 0.77V/0.46V
14
15 respectively, which contribute to the oxidation of the monomers gradually.
16
17 Meanwhile, the current intensity of this reversible peak became higher and higher
18
19 after each successive cycle, which clearly indicated the electroactive polymer was
20
21 deposited on the ITO/glass surface successfully. After the polymerization, the
22
23 deposited films were washed with CH₂Cl₂ for several times to wash off the inorganic
24
25 salts and the unreacted monomers.
26
27
28
29
30
31
32
33
34
35

36 [Fig.1](#)

37 3.3 Electrochemical properties of the P(DTP-TPA)s

38
39 Electrochemical properties of P(DTP-TPA)s were investigated via cyclic
40
41 voltammetry (CV) ([Fig.2](#)). In the cyclic voltammetry of P(DTP-PNA), peaks at
42
43 0.91V and 1.36V were observed as the oxidation process while 0.85V and 1.22V
44
45 were the reduction peaks. As shown in the inset of Fig.2, a linear relationship was
46
47 showed between the peak current and the scan rate, signifying this polymerization
48
49 was a reversible and non-diffusional redox process and the electroactive polymer
50
51 films were well-adhered, which was proving that the process of the
52
53
54
55
56
57
58
59
60
61
62
63
64
65

oxidation-reduction reaction was due to the electronic gain and loss. Other polymer's cyclic voltammetry at different scan rate were given in Supporting Information Fig.S7. The cyclic voltammetrys curves of the monomers were given in Supporting Information Fig.S8 and the Fig.3 showed the CV of the polymers. During the scan, we can see the polymers exhibit different oxidation peaks compared with the monomers. The first oxidation peaks of the polymer P(DTP-TPA)s are at 0.91V, 0.85V, 0.65V, 0.67V, 0.62V respectively, which are ascribed to the radical cation (TPA⁺) formation which are similar to the reported TPA derivatives[44]. The peak appeared at 1.36V, 1.34V, 1.20, 0.97V, 1.00V respectively, maybe occur from DTP unit [31]. All these observation are proved that the polymers are synthesized successfully.

[Fig.2](#)

[Fig.3](#)

3.4 Geometry and electronic structure of P(DTP-TPA)s

In order to obtain deeper insight into the polymer structure-property relationships, the ground-state geometry optimizations and the energy levels of P(DTP-TPA)s were carried out by using density functional theory at the B3LYP/6-31G level.

The average C=N bond lengths between the pyrrole ring and phenylene ring in P(DTP-PNA), P(DTP-DPA), P(DTP-TBPA), P(DTP-PTA-DTP) and P(DTP-CPA-DTP) are 1.412nm, 1.414nm, 1.415nm, 1.414nm and 1.413nm (1.414nm), respectively, and the torsional angles (Φ) between the C=N linkage and

adjacent phenylene or pyrrole ring are in the range of 178° - 180° ([Fig.4](#) and [Table S1](#)), which suggest that they are nearly in one planar conformation.

To better understand the evolution of the oxidation and reduction potentials, we studied the highest occupied molecular orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) energy levels of the polymers via cyclic voltammetry (CV) method. The E_{HOMO} and the optical band gap (E_g) were calculated from E_{onset} and λ_{onset} ([Table 1](#)) [45]. In order to obtain the accurate redox potential, we use $E_{\text{Fc/Fc}^+} = -4.80\text{eV}$ as reference electrode, which has been calibrated already. We know the $E_{1/2}(\text{Fc/Fc}^+ \text{ vs Ag/AgCl}) = 0.37\text{V}$ via cyclic voltammetry of (Fc/Fc^+) . Then the E_{HOMO} , E_{LUMO} and E_g were summarized in Table 1. The results showed that the TPA derivatives had an important influence on regulating the electronic structure of the 2, 5 -dithienylpyrrole derivatives. The lower potentials they are, the easier electron goes into the polymer films from ITO.

[Fig.4](#)

[Table 1](#)

On the other hand, E_{HOMO} represents the supply electronic capability while E_{LUMO} is relating to acceptance electronic power. In HOMO state, the electron cloud is completely distributed in 2, 5 -dithienylpyrrole part, which in favor of higher hole mobility ([Fig. 5](#)). However, in LUMO state, electron cloud is mainly distributed in TPA unit which can reduce E_g effectively. The lone pair electron of N in the TPA core unit would couple with π electron strongly, resulting effective density distribution in the molecule during the charge transfer. From Table 1, we can know

the theoretical data are basically consistent with the experimental data. In experimental data, $E_{(P(DTP-DPA))} > E_{(P(DTP-PNA))} > E_{(P(DTP-TBPA))} > E_{(P(DTP-PTA-DTP))} > E_{(P(DTP-CPA-DTP))}$. However, in theoretical data, $E_{(P(DTP-TBPA))} > E_{(P(DTP-DPA))} > E_{(P(DTP-PNA))} > E_{(P(DTP-CPA-DTP))} > E_{(P(DTP-PTA-DTP))}$. The slight deviation may be owing to the influence of the adjacent benzene ring. Moreover, theoretical data only resulted from the monomer, not long polymer chain. In fact, the solvent and electrolyte also play an important effect on the result.

[Fig.5](#)

3.5 Spectroelectrochemical properties

Spectroelectrochemical measurements were conducted by UV–Vis–NIR spectrophotometer upon incrementally changing the applied potential (from 0.0 V to 1.5 V) of the polymer films. The optical behavior as well as electronic structure of the polymers can be explained. Taking P(DTP-PNA) for example ([Fig.6](#)), the polymer film is yellow at neutral state in the visible region and transparent in the NIR regions, which has a strong band at 321nm and 397nm. The absorptions were accounted for the $\pi - \pi^*$ and $n - \pi^*$ transitions of the DTP backbones and the TPA subunits[46]. But the absorption of 321nm intensity decreased sharply when the potentials grew up, meanwhile, the absorption at 397 nm gradually increased. Also, the absorption at 816nm and 1313nm gradually increased with the potentials growing up, and the color of the film became from yellow (L:65; a:-5; b:23) to dusty blue (L:61; a:-22; b:-16) to violet (L:65; a:-4; b:-9), which is according with the view that conjugated polymers are promising materials for electrochromic applications

1 However, the absorption of P(DTP-PTA-DTP) at 453nm decreased gradually when
2
3 the applied potentials increased, and two new bands which appeared at 755nm and
4
5 1181nm increased. Other electronic absorption spectra changing process are given in
6
7 Supporting Information Fig. S9. From the Fig.7, we can know the mechanism of the
8
9 **electron** transfer of the P(DTP-TPA)s.
10
11
12
13

14 [Fig.6](#)

15 [Fig.7](#)

16
17
18
19
20 Colorimetric analysis is used to evaluate the color changes of electrochromic
21
22 material. The measurements were performed by Commission Internationale de
23
24 L'Eclairage (CIE) system. According to CIE system, the color is made up of three
25
26 aspects: luminance (L), hue (a), saturation (b)[47], which representing the brightness
27
28 of the materials, how red versus green and how yellow versus blue, respectively. In
29
30 other words, this means the higher of the L, a, b, the brighter of the materials, the
31
32 redder of the materials and the more yellow of the materials. These color and
33
34 corresponding L, a, b values are shown in Table S2 in Supporting Information.
35
36
37
38
39
40
41

42 Response time, one of the most important characteristics of electrochromic
43
44 materials, is the time needed to perform a switching between the neutral and
45
46 oxidized states of the materials[48], which was measured by UV–Vis–NIR
47
48 spectroscopy at fixed wavelength from 0.0V to 1.0V. The response is found to be 2.9
49
50 s from the neutral to the oxidized state and 2.8 s from the oxidized to the reduced
51
52 state of P(DTP-PNA) in 816nm at Fig.8 (a). The coloration time is different from
53
54 fading time, which may be owing to dispersion dynamics of ionic resulting from the
55
56
57
58
59
60
61
62
63
64
65

different surface images of the oxidation-reduction process. At [Fig.8 \(b\)](#), we find that the current density of PDTP-PNA keeps stable in 100s from 0.0V to 1.0V, which indicating that P(DTP-PNA) has stable electrochromic properties. P(DTP-PNA), P(DTP-DPA), P(DTP-TBPA), P(DTP-PTA-DTP) and P(DTP-CPA-DTP) films have a high optical contrast, which are attributed to the introduction of triarylamine units into the polymer backbone, but the P(DTP-PNA), P(DTP-DPA) and P(DTP-TBPA) are more faster than P(DTP-PTA-DTP) and P(DTP-CPA-DTP), which may be attribute to their more smaller steric hindrance. Other P(DTP-TPA)s have a similar explanation.

[Fig. 8](#)

The coloration efficiency (CE) is another important characteristic for the electrochromic materials. CE can be calculated using the equations given below[49]

$$\delta_{OD} = \lg(T_b/T_c) \quad (1)$$

$$\eta = \delta_{OD}/Q \quad (2)$$

where T_b and T_c denote the transmittances of the film before and after colorations, respectively. δ_{OD} is the change of the optical density, which is proportional to the amount of created color centers. η denotes the coloration efficiency (CE). Q (mC/cm^2) is the amount of injected charge per unit sample area. $\Delta T(\%)$ is the percentage transmittance change. As a result, the calculating data shows the CEs of the P(DTP-TPA)s are $75.72 \text{ cm}^2/\text{C}$, $90.06 \text{ cm}^2/\text{C}$, $102.4 \text{ cm}^2/\text{C}$, $83.55 \text{ cm}^2/\text{C}$, $94.69 \text{ cm}^2/\text{C}$, respectively ([Table 2](#)). At the same time, the $\Delta T(\%)$ of the polymers are 23%, 24%, 13%, 19% and 17%, respectively. It indicates that the materials have not relative

high CEs but have a relative high color changing velocity.

[Table 2](#)

3.6 Surface Morphology

The morphology and stacking mode of the polymer have a very important influence on their properties, such as electron transfer speed, stability and so on. So the morphologies of film surface of the P(DTP-TPA)s were investigated specially by SEM. The surface morphologies of the polymer films were shown in [Fig.9](#), which were deposited on ITO electrodes via electrochemical polymerization. The closer the distance of movement of ion is, the faster of the ion transfers, and the more efficiency of electrochromic gets. From [Fig.9](#), we can see the polymer films are composed of many well-distributed microspheres. When the images are enlarged, as the inset in [Fig.9](#), the particles diameter is estimated as approximately 300-1000 nm. The larger surface area of the particles is in favor of increasing the area of the electrolyte solution contacting to the polymers surface, then facilitating the ion carriers transferring freely passing in out the films.

[Fig.9](#)

4. Conclusions

In summary, a series of polymers based on 2,5 - dithienylpyrrole (DTP) and triarylamine units (TPA) with excellent optical transmittance change were successfully designed and synthesized. Spectroelectrochemical as well as electrochemical properties were used for the structural characterization. The polymers P(DTP-PNA), P(DTP-DPA) and P(DTP-TBPA) with single branched DTP

unit have a better performance than P(DTP-PTA-DTP), P(DTP-CPA-DTP) containing double branched DTP unit, which may be due to the steric hindrance of the latter two is larger than the first three, so the properties of the P(DTP-PTA-DTP) and P(DTP-CPA-DTP) need further improvement. Meanwhile by SEM, we can see all films surface are regular, which are in favor of the carrier's input and output in polymer structure, and have a potential application on the device. Also, an obvious color change was observed from a yellow neutral to dusty blue and violet. These prominent features make P(DTP-TPA)s have many applications in the future, such as light-emitting, hole-transporting materials, electrochromic materials and memory device application.

Acknowledgements

The authors are grateful to National Science Foundation of China (Grant No.51373049, 51372055, 51303045, 51273056, 21372067, 51527804), Reserve Talented Person of Harbin (2015RAXXJ015) and Doctoral Fund of Ministry of Education of China (20132301120004, 20132301110001) for the financial support.

Reference

- [1] A. A. Argun, P. H. Aubert, B. C. Thompson, I. Schwendeman, C. L. Gaupp, J. Hwang, N. J. Pinto, D. B. Tanner, A. G. MacDiarmid and J. R. Reynolds, Multicolored electrochromism in polymers: structures and devices, Chem. Mater. 16 (2004) 4401–4412.
- [2] P. M. Monk, R. J. Mortimer and D. R. Rosseinsky, Electrochromism and electrochromic devices, Cambridge University Press, Cambridge, UK, 2007.

- [3] P. M. Beaujuge, S. Ellinger and J. R. Reynolds, The donor–acceptor approach allows a black-to-transmissive switching polymeric electrochrome, *Nat. Mater.* 7 (2008) 795–799.
- [4] P. M. Beaujuge and J. R. Reynolds, Color control in π -conjugated organic polymers for use in electrochromic devices, *Chem. Rev.* 110 (2010) 268–320.
- [5] R. J. Mortimer, Electrochromic materials, *Annu. Rev. Mater. Res.* 41 (2011) 241–268.
- [6] Y. Zhong, C. Yao and H. Nie, Electropolymerized films of vinyl-substituted polypyridine complexes: synthesis, characterization, and applications, *Coord. Chem. Rev.* 257 (2013) 1357–1372.
- [7] L. Beverina, G. A. Pagani and M. Sassi, Multichromophoric electrochromic polymers: colour tuning of conjugated polymers through the side chain functionalization approach, *Chem. Commun.* 50 (2014) 5413–5430.
- [8] X. You, *Molecular-Based Materials opto-electronic functional compounds*, Science Press, Beijing, China, 2014.
- [9] R. J. Mortimer, A. L. Dyer and J. R. Reynolds, Electrochromic organic and polymeric materials for display applications, *Displays* 27 (2006) 2–18.
- [10] A. Cihaner and F. Algi, A processable rainbow mimic fluorescent polymer and its unprecedented coloration efficiency in electrochromic device, *Electrochim. Acta* 53 (2008) 2574–2578.
- [11] F. Tavoli and N. Alizadeh, In situ UV–vis spectroelectrochemical study of dye doped nanostructure polypyrrole as electrochromic film, *J. Electroanal Chem.* 720 (2014) 128–133.
- [12] F. Tavoli and N. Alizadeh, Enhancement effect of transition metal cations on the electrochromic properties of nanostructure tiron doped polypyrrole film, *J. Electroanal Chem.* 746 (2015) 39–44.
- [13] U. Mehmood, A. Al-Ahmed and I. A. Hussein, Review on recent advances in polythiophene based photovoltaic devices, *Renew. Sust. Energ. Rev.* 57 (2016) 550–561.
- [14] S. Jin, S. Cong, G. Xue, H. Xiong, B. Mansdorf and S. Z. D. Cheng, Anisotropic Polythiophene Films with High Conductivity and Good Mechanical Properties via a New Electrochemical Synthesis, *Adv. Mater.* 14 (2002) 1492.

- [15] G. G. McLeod, M. G. B. Mahboubian-Jones, R. A. Pethrick, S. D. Watson, N. D. Truong and J. C. Galin, Synthesis, electrochemical polymerization and properties of poly(2,5-di-(2-thienyl)-pyrrole), *Polymer* 27(1986) 455-458.
- [16] J. P. Ferraris and T. R. Hanlon, Optical, electrical and electrochemical properties of heteroaromatic copolymers, *Polymer* 30 (1989) 1319-1327.
- [17] S. T arkus, E. Sahmetlioglu, C. Tanyel, I. M. Akhmedov and L. Toppare, Electrochromic properties of a soluble conducting polymer of 1-benzyl-2,5-di(thiophene-2-yl)-1H-pyrrole, *Sens. Actuators* 121(2007) 622-628.
- [18] S. Varis, M. Ak, I. M. Akhmedov, C. Tanyeli and L. Toppare, Electrochromic properties of a novel low band gap conductive copolymer, *Electrochim. Acta* 52 (2007) 6561-6568.
- [19] S. Varis, M. Ak, I. M. Akhmediv, C. Tanyeli and L. Toppare, A novel multielectrochromic copolymer based on 1-(4-nitrophenyl)-2,5-di(2-thienyl)-1H-pyrrole and EDOT, *J. Electroanal Chem* 603 (2007) 8-14.
- [20] A. Arslan, Ö. Türkarslan, C.Tanyeli, İ. Akhmedov and L. Toppare, Electrochromic properties of a soluble conducting polymer: Poly(1-(4-fluorophenyl)-2,5-di(thiophen-2-yl)-1H-pyrrole), *Mater. Chem. Phys.* 104 (2007) 410-416.
- [21] P. Audebert, S. Sadki F. Miomandre, P. Hapiot and K. Chane-Ching, New conjugated polymerizable pyrrole and 2,5-dithienylpyrrole azobenzene dyes: synthesis and spectroelectrochemical properties, *New J. Chem.* 27 (2003) 798-804.
- [22] S. Varis, M. Ak, C. Tanyeli, I. M. Akhmedov and L. Toppare, A soluble and multichromic conducting polythiophene derivative, *Eur. Polym. J.* 42 (2006) 2352–2360.
- [23] S. Tuncagil, S. Kiralp, S. Vans and L. Toppare, Immobilization of invertase on a conducting polymer of 1-(4-nitrophenyl)-2, 5-di (2-thienyl)-1H-pyrrole, *React. Funct. Polym.* 68 (2008) 710-717.
- [24] A. Cihaner, F. Algi, Processable electrochromic and fluorescent polymers based on N-substituted thienylpyrrole, *Electrochim. Acta* 54 (2008) 665-670.
- [25] F. Algi and A. Cihaner, An electroactive polymeric material and its voltammetric response towards alkali metal cations in meat water, *Tetrahadron Lett.* 49 (2008) 3530-3533.

- [26] A. Cihaner and F. Algi, An electrochromic and fluorescent polymer based on 1-(1-naphthyl)-2,5-di-2-thienyl-1H-pyrrole, *Electroanal. Chem.* 614 (2008) 101-106.
- [27] A. Cihaner and F. Algi, Electrochemical and optical properties of new soluble dithienylpyrroles based on azo dyes, *Electrochim. Acta* 54 (2009) 1702-1709.
- [28] (a) Y. W. Chuang, H. J. Yen, J. H. Wu and G. S. Liou, Colorless triphenylamine-based aliphatic thermoset epoxy for multicolored and near-Infrared electrochromic applications, *ACS Appl. Mater. Interfaces* 6 (2014) 3594–3599; (b) S. H. Cheng, S. H. Hsiao, T. H. Su and G. S. Liou, Novel aromatic poly (amine-imide)s bearing a pendent triphenylamine group: synthesis, thermal, photophysical, electrochemical, and electrochromic characteristics, *Macromolecules* 38 (2005) 307–316; (c) H. J. Yen, H. Y. Lin and G. S. Liou, Novel starburst triarylamine-containing electroactive aramids with highly stable electrochromism in near-infrared and visible light regions, *Chem. Mater.* 23 (2011) 1874–1882; (d) H. M. Wang and S. H. Hsiao, Substituent effects on electrochemical and electrochromic properties of aromatic polyimides with 4-(Carbazol-9-yl)triphenylamine Moieties, *J. Polym. Sci., Part A: Polym. Chem.* 52 (2014) 1172–1184; (e) S. H. Hsiao, P. C. Chang, H. M. Wang, Y. R. Kung and T. M. Lee, Synthesis of a new class of triphenylamine - containing poly (ether - imide) s for electrochromic applications, *J. Polym. Sci., Part A: Polym. Chem.* 52 (2014) 825–838; (f) S. H. Hsiao, G. S. Liou, Y. C. Kung and T. J. Hsiung, Synthesis and properties of new aromatic polyamides with redox-Active 2,4-dimethoxytriphenylamine moieties, *J. Polym. Sci., Part A: Polym. Chem.* 48 (2010) 3392-3401.
- [29] (a) C. W. Tang and S. A. VanSlyke, Organic electroluminescent diodes, *Appl. Phys. Lett.* 51(1987) 913; (b) C. W. Tang, S. A. VanSlyke and C. H. Chen, Electroluminescence of doped organic thin films, *J. Appl. Phys.* 65 (1989) 3610; (c) C. Adachi, K. Nagai, N. Tamoto, Molecular design of hole transport materials for obtaining high durability in organic electroluminescent diodes, *Appl. Phys. Lett.* 66 (1995) 2679; (d) Y. Shirota, Molecular design of hole transport materials for obtaining high durability in organic electroluminescent diodes, *J. Mater. Chem.* 10 (2000) 1-25; (e) Y. Shirota, Photo-and

- electroactive amorphous molecular materials—molecular design, syntheses, reactions, properties, and applications, *J. Mater. Chem.* 15 (2005) 75-93.
- [30] S. H. Hsiao and Y. T. Chiu, Electrosynthesis and electrochromic properties of poly (amide-triarylamine) s containing triptycene units, *RSC Advances* 5 (2015) 90941-90951.
- [31] J. Lai, X. Lu, B. Qu, F. Liu, C. Li and X. You, A new multicolored and near-infrared electrochromic material based on triphenylamine-containing poly (3, 4-dithienylpyrrole), *Org. Electron* 15 (2014) 3735-3745.
- [32] B. Wang, J. Zhao and R. Liu, Electrosyntheses, characterizations and electrochromic properties of a copolymer based on 4, 4' -di (N-carbazoyl) biphenyl and 2, 2' -bithiophene, *Sol. Energy Mater. Sol. Cells* 95 (2011) 1867-1874.
- [33] Y. Hu, D. Hu, S. Ming, X. Duan, F. Zhao, J. Hou, J. Xun and F. Jiang, Synthesis of polyether-bridged bithiophenes and their electrochemical polymerization to electrochromic property, *Electrochim. Acta* 189 (2016) 64-73.
- [34] S. Inaoka, D. B. Roitman and R. C. Advincula, Cross-linked polyfluorene polymer precursors: electrodeposition, PLED device characterization, and two-site co-deposition with poly (vinylcarbazole), *Chem. Mater.* 17 (2005) 6781–6789.
- [35] C. R. Siju, K. N. Rao and S. Sindhu, Enhanced performance characteristics of electropolymerized poly (3, 4 ethylenedioxythiophene) films on ITO by one step cyclic voltammetry, *J. Opt.* 42 (2013) 67–72.
- [36] S. Jamadade, S. V. Jadhav and V. Puri, Electromagnetic reflection, shielding and conductivity of polypyrrole thin film electropolymerized in P-Toluenesulfonic acid, *J Non Cryst Solids* 357 (2011) 1177–1181.
- [37] Torres S, Neculqueo G and Martinez F. Preparation and characterization of polypyrrole/graphene nanocomposite films and their electrochemical performance, *J Chil Chem Soc.* 52 (2007) 1235–1236.
- [38] J. Deng, X. Fu, G. Wang, J. Huang, L. Wu and X. Zou, Progress in synthesis and application of 2,5-dithienylpyrrole derivatives, *Chin. J. Org. Chem.* 32 (2012) 1051-1059.
- [39] A. Merz and F. Ellinger, Convenient synthesis of α -terthienyl and α -quinquethienyl via a

- Friedel-Crafts route, *Synthesis* 6 (1991) 462-464.
- [40] J. Nakazaki, I. Chung, M. M. Matsushita, T. Sugawara, R. Watanabe, A. Izuoka and Y. J. Kawada, Design and preparation of pyrrole-based spin-polarized donors, *Mater. Chem.* 13 (2003) 1011-1022.
- [41] J. Cai, H. Niu, C. Wang, L. Ma, X. Bai and W. Wang, Tuning the bandgaps of polyazomethines containing triphenylamine by different linkage sites of dialdehyde monomers, *Electrochim. Acta* 76 (2012) 229–241.
- [42] A. Cihaner and F. Algi, A processable rainbow mimic fluorescent polymer and its unprecedented coloration efficiency in electrochromic device, *Electrochim. Acta* 53 (2008) 2574-2578
- [43] J. P. Ferraris, T. R. Hanlon, Optical, electrical and electrochemical properties of heteroaromatic copolymers, *Polymer* 30 (1989) 1319-1327.
- [44] W. Chen, K. Wang, W. Hung, J. Jiang, D. Liaw, K. Lee, J. Lai and C. Chen, Novel triarylamine - based alternating conjugated polymer with high hole mobility: Synthesis, electro - optical, and electronic properties, *J. Polym. Sci.Part A: Polym. Chem.* 48 (2010) 4654 - 4667.
- [45] K. Zhang, H. Niu, C. Wang, X. Bai, Y. Lian and W. Wang, Novel aromatic polyimides with pendent triphenylamine units: Synthesis, photophysical, electrochromic properties, *J. Electroanal. Chem.* 682 (2012) 101–109.
- [46] S. Tarkuc, E. Sahmetlioglu, C. Tanyeli, I. M. Akhmedov and L. Toppare, A soluble conducting polymer: 1-Phenyl-2, 5-di (2-thienyl)-1H-pyrrole and its electrochromic application, *Electrochim. Acta* 51 (2006) 5412-5419.
- [47] B. C. Thompson, P. Schottland, G. Sonmez and J. R. Reynolds, In situ colorimetric analysis of electrochromic polymer films and devices, *Synth. Met.* 119 (2001) 333-334.
- [48] G. M. Nie, L. J. Zhou, Q. F. Guo and S. S. Zhang, A new electrochromic material from an indole derivative and its application in high-quality electrochromic devices, *Electrochem. Commun.* 12 (2010) 160-163.
- [49] S. J. Yoo, J. H. Cho, J. W. Lim, S. H. Park, J. Jang and Y. E. Sung, High contrast ratio and

fast switching polymeric electrochromic films based on water-dispersible polyaniline-poly
(4-styrenesulfonate) nanoparticles, *Electrochem. Commun.* 12 (2010) 164-167.

Fig.1 Electrochemical polymerization of DTP-PNA and DTP-PTA-DTP in 0.1mol/L TBAP/ CH_2Cl_2 via repetitive cycling at a scan rate 50mV/s

Fig.2 (a) Electrochemical oxidation process behavior of P(DTP-PNA) and P(DTP-PTA-DTP) film at different scan rates (b) anodic and cathodic current peaks as a function of scan rate in 0.1mol/L $\text{LiClO}_4/\text{CH}_3\text{CN}$

Fig.3 Cyclic voltammetry curves for P(DTP-TPA)s in 0.1mol/L LiClO₄/CH₃CN at a scan rate of 50 mV/ s

Fig.4 Optimized geometries of the DTP-TPAs

Fig.5 Pictorial representations of the electron density in the frontier molecular orbitals of repetition units.

Fig.6 Electronic absorption spectra changing process for P(DTP-PNA) and P(DTP-PTA-DTP) in 0.1mol/L

LiClO₄/CH₃CN solution (insets are the photos of changing color)

Fig.7 The proposed electrochromism mechanization of P(DTP-PNA) and P(DTP-PTA-DTP)

Fig.8 Optical switching procedures: (a) potential step transmittance of P(DTP-TPA)s by applying a potential step (0.0-1.0 V); (b) Current consumption of P(DTP-TPA)s.

Fig.9 SEM image of P(DTP-TPA)s deposited on ITO electrodes via electrochemical polymerization method

Table 1 Optical and electrochemical properties of the polymers

Polymers	$\lambda_{\max}$ nm	$\lambda_{\text{onset}}^{\text{a}}$ nm	$E_{\text{onset}}^{\text{ox} \text{ b}}$ eV	$E_{\text{HOMO}}^{\text{c}}$ eV	$E_{\text{LUMO}}^{\text{d}}$ eV	E_{g}^{e} eV	$E_{\text{g}}^{\text{quantum} \text{ f}}$ eV
P(DTP-PNA)	328	477	0.67	-6.10	-3.50	2.60	3.64
P(DTP-DPA)	326	476	0.62	-5.05	-2.44	2.61	3.67
P(DTP-TBAP)	325	484	0.45	-4.88	-2.32	2.56	3.96
P(DTP-PTA-DTP)	453	545	0.50	-4.93	-2.66	2.27	2.41
P(DTP-CPA-DTP)	448	560	0.46	-4.89	-2.68	2.21	2.67

a λ_{onset} : the absorption starting wavelength.

b $E_{\text{ox/onset}}$ (Fc/Fc+ vs Ag/AgCl) = 0.37V

c based on formula (1) $E_{\text{HOMO}} = -e(E_{\text{onset}}^{\text{ox}}$ vs Ag/AgCl+4.43)eV

d based on formula (2) $E_{\text{LUMO}} = E_{\text{HOMO}} + E_{\text{g}}$

e based on formula (3) $E_{\text{g}} = 1240/\lambda_{\text{onset}}$

f E_{quantum} : values of theoretical calculation

Table 2 Optical and Electrochemical Data Collected for Coloration Efficiency Measurements of P(DTP-TPA)s

Polymers	$\lambda_{(\text{nm})}^{\text{a}}$	$\delta_{\text{OD}}^{\text{b}}$	$Q(\text{mC}/\text{cm}^2)^{\text{c}}$	$\eta (\text{cm}^2/\text{C})^{\text{d}}$	$\Delta T(\%)^{\text{e}}$
P(DTP-PNA)	816	0.1310	1.730	75.72	23
P(DTP-DPA)	830	0.1450	1.610	90.06	24
P(DTP-TBAP)	828	0.1280	1.250	102.4	13
P(DTP-PTA-DTP)	765	0.0715	0.8558	83.55	19
P(DTP-CPA-DTP)	800	0.1641	1.733	94.69	17

^a The given wavelength where the data were determined;

^b Optical density change at the given wavelength;

^c Injected charge, determined from the in situ experiments;

^d Coloration efficiency is derived from the equation (2).

^e The percentage transmittance changes.