Prevalent role of porosity and osteonal area over mineralization heterogeneity in the fracture toughness of human cortical bone

Mathilde Granke^{1,2,3}, Alexander J Makowski^{1,2,3,4}, Sasidhar Uppuganti^{1,2}, Jeffry S Nyman^{1,2,3,4}

¹Department of Orthopaedics Surgery & Rehabilitation, Vanderbilt University Medical Center, Nashville, TN 37232

²Center for Bone Biology, Vanderbilt University Medical Center, Nashville, TN 37232

³Department of Veterans Affairs, Tennessee Valley Healthcare System, Nashville, TN 37212

⁴Department of Biomedical Engineering, Vanderbilt University, Nashville, TN 37232

Contact: Jeffry S. Nyman
Medical Center East
South Tower, Suite 4200
Nashville, TN 37232

jeffry.s.nyman@vanderbilt.edu

office: (615) 936-6296

fax: (615) 936-0117

Word count: 3893

Key Words: fracture toughness, heterogeneity, mineralization, porosity, microstructure

Abstract

Changes in the distribution of bone mineralization occurring with aging, disease, or treatment have prompted concerns that alterations in mineralization heterogeneity may affect the fracture resistance of bone. Yet, so far, studies assessing bone from hip fracture cases and fracture-free women have not reached a consensus on how heterogeneity in tissue mineralization relates to skeletal fragility. Owing to the multifactorial nature of toughening mechanisms occurring in bone, we assessed the relative contribution of heterogeneity in mineralization to fracture resistance with respect to age, porosity, and area fraction of osteonal tissue. The latter parameters were extracted from quantitative backscattered electron imaging of human cortical bone sections following R-curve tests of single-edge notched beam specimens to determine fracture toughness properties. Microstructural heterogeneity was determined as the width of the mineral distribution (bulk) and as the sill of the variogram (local). In univariate analyses of measures from 62 human donors (21 to 101 years), local but not bulk heterogeneity as well as pore clustering negatively correlated with fracture toughness properties. With age as covariate, heterogeneity was a significant predictor of crack initiation, though local had a stronger negative contribution than bulk. When considering all potential covariates, age, cortical porosity and area fraction of osteons explained up to 50% of the variance in bone's crack initiation toughness. However, including heterogeneity in mineralization did not improve upon this prediction. The findings of the present work stress the necessity to account for porosity and microstructure when evaluating the potential of matrix-related features to affect skeletal fragility.

1. Introduction

The fracture resistance of bone does not solely depend on the quantity of bone, or bone mineral density, but also on the integrity of the bone tissue (Donnelly et al., 2014). In particular, owing to

its hierarchical organization, bone is able to resist fracture through the combination of multiple toughening mechanisms that interact at several length scales. For example, interfibrillar sliding at the nanoscale allows the mineralized collagen fibrils to deform without failing, while osteons on the order of hundreds of microns create natural barriers to the propagation of cracks through bone tissue (O'Brien et al., 2003; Ural and Vashishth, 2014). With aging and disease progression, changes can occur at any of the hierarchical levels of organization, thereby lowering the fracture resistance of bone (e.g., accumulation of non-enzymatic collagen crosslinks impeding interfibrillar sliding). Complicating the clinical assessment of fracture resistance or fracture risk, heterogeneity exists at the multiple length scales of organization, but not all heterogeneity may significantly contribute to the age-related loss of fracture resistance.

Investigations of fracture processes in material science indicate that microstructural heterogeneity (i.e., the spatial variation of compositional properties in a material) improves resistance to fracture: crack propagation is straight in a homogenous material with less energy dissipation while it is tortuous deflecting at interfaces in a heterogeneous material, thereby requiring more energy to grow (Dimas et al., 2014; Hossain et al., 2014). Changes in bone metabolism associated with diseases or drug treatment are known to significantly affect the distribution of bone mineralization at the micron length scale (Roschger et al., 2008). In this context, a loss in heterogeneity in mineralization has been posited as a possible factor contributing to an increase in fracture risk (Ettinger et al., 2013). However, in the current literature, there is a lack of consensus on how heterogeneity in tissue mineralization relates to skeletal fragility. Indeed, heterogeneity in mineralization at the micro-structural level was found either to be greater (Bousson et al., 2011) or lower (Gourion-Arsiquaud et al., 2013; Milovanovic et al., 2014) in treatment naïve, hip fracture cases compared to fracture-free women. The

inconsistency of these results highlights the need to account for other contributing factors to conclusively state that bone fragility is directly related to the distribution of tissue mineralization.

Among the factors that contribute to skeletal fragility, vascular porosity is greater in patients with a history of fracture compared to non-fracture controls (Ahmed et al., 2015; Bala et al., 2014; Bell et al., 1999; Milovanovic et al., 2014; Shigdel et al., 2015) or in bone specimens with lower fracture toughness properties, as determined from mechanical tests of cadaveric tissue (Granke et al., 2015; Yeni et al., 1997). Moreover, image analysis of bone cross-sections of the femoral neck suggests that greater cortical porosity in fragile bone may result from the merging of spatially clustered remodeling osteons (Bell et al., 2000; Jordan et al., 2000). Therefore, not only the extent but also the spatial distribution of porosity may decrease the fracture resistance of bone, a phenomenon described for porous media (Bilger et al., 2005).

To date, the question of whether heterogeneity mineralization affects bone's resistance to fracture remains undetermined for two reasons. First, published data is confined to comparing tissue composition between fracture and control cases, but to date, no studies have attempted to relate heterogeneity in mineralization and the mechanical properties of cortical bone. Second, most studies investigating associations between tissue composition and fracture status or risk do not adjust for other microstructural features (i.e., porosity or bone volume fraction). Given the possible contribution of age, porosity, and tissue microstructure to skeletal fragility, we aimed to determine whether microstructural heterogeneity in mineralization significantly explains bone's ability to resist fracture after adjusting for these factors. To address this, we analyzed cross-sections of human cortical bone specimens for which fracture toughness properties had been previously determined (Granke et al., 2015). Upon imaging these cross-sections by quantitative backscattered electron imaging (qBEI), image processing techniques quantified lacunar and

vascular porosities, pore clustering, population and local heterogeneity in mineralization, as well as area fraction of osteonal tissue.

2. Material and methods

The preparation of the mechanical specimens and measurement methods are extensively described in Granke et al. (2015) and briefly summarized herein. Femurs from sixty-two human donors (30 male, age = 63.5 ± 23.7 [21 -98] years and 32 female, age = 64.4 ± 21.3 [23-101] years) were obtained from the Musculoskeletal Transplant Foundation (Edison, NJ), the Vanderbilt Donor Program (Nashville, TN), and the National Disease Research Interchange (Philadelphia, PA) and stored fresh-frozen. Single-sedge notched beam (SENB) specimens (span x thickness x width $\sim 20 \times 2.5 \times 5.0 \text{ mm}^3$) were machined from the lateral quadrant of each femoral mid-shaft (N=62). After imaging the notched region with micro-computed tomography (μ CT) at a 5 μm voxel size (Granke et al., 2015) to determine vascular porosity, a progressive, loading/partial unloading/reloading scheme in a three-point bending configuration was used to initiate and propagate a crack from the micro-notch through the cortical bone such that crack extension was perpendicular to the osteonal direction. A non-linear fracture mechanics approach based on the analysis of the resulting R-curve (J-integral vs. crack length) provided the resistance (elastic plus plastic contributions) to initiate (K_{init}) and propagate (K_{grow}) a crack from the notch as well as the energy dissipated during fracture (J) (ASTM Standard E1820-15a, 2015). K_{grow} could not be calculated for specimens that exhibit highly brittle behavior, which was the case for 11 specimens out of 62. Following mechanical testing, the specimens were stored in phosphate-buffered saline at -20°C until the next phase of the experimental protocol.

2.1 Quantitative backscattered electron imaging (qBEI)

2.1.1 Specimens preparation and image acquisition

A cross-section (~2.5 mm x 4.5 mm) was cut adjacent to the fracture line (Fig.1), ground on successive grits (1200 to 4000) of wet silicon carbide paper, and polished on synthetic cloth with 0.05 μm aluminum oxide suspension (MasterPrep, Buehler, Lake Bluff, IL). Upon drying for several days in a vacuum desiccator at room temperature, the samples were mounted on aluminum stubs with double-sided carbon tape together with pure aluminum and carbon standards for calibration (EMS, Hatfield PA) (Fig.1). The surface of the specimen was imaged by qBEI using a Quanta FEG 250 ESEM (FEI Company, Hillsboro, Oregon, USA) equipped with a low-voltage, high-contrast backscattered electron detector. Digital images from the bone cross-section and calibration materials were acquired using the same settings (high vacuum mode, acceleration voltage of 20kV, working distance of 15 mm, scan speed of 100 sec/frame). Contrast and brightness were adjusted so that the mean grey levels of the backscattered signals from carbon and aluminum reached 25 and 225, respectively. In order to cover the entire surface of the cross-section, four to six images ($2 \times 2.5 \text{ mm}^2$) were collected at 50x magnification with a 1.2 μm pixel resolution, merged to a single image using Photoshop[®] CS6 (Adobe Systems Inc., San Jose, CA, USA), and Gauss-filtered ($\sigma=1$) (Fig.1). Although the specimens were not carbon-coated, electron charging did not build up as demonstrated by imaging the same bone surface repeatedly over the course of 15 minutes (Supplementary Fig.1) and by imaging the same specimen before and after carbon coating (Supplementary Fig.2). All the following post-processing analyses were implemented in MATLAB[®] (The Mathworks Inc., Natick, MA, USA).

2.1.2 Porosity analysis

A semi-automated procedure was used to segment the pores from the bony matrix (Fig.2A). A porosity mask was first created using Otsu's method (Otsu, 1979). Any surface contaminants

(e.g., dust particles) and large cracks were manually removed from the porosity mask using Photoshop CS6 (Adobe Systems, Inc., San Jose, CA). Pores with an area larger than $100 \mu\text{m}^2$ were assigned to vascular porosity (including Haversian canals, Volkmann's canals, resorption cavities) or to lacunar porosity otherwise (Fig.2B).

The heterogeneity in the spatial distribution of the vascular porosity was analyzed using Voronoi diagrams (Aurenhammer, 1991). The sides of the Voronoi polygons are located at mid-distance from neighboring pores (Fig.2C). The area of each polygon was determined without excluding the pore area (black region in Fig.2C). High coefficient of variation for the individual areas of the Voronoi polygons (*VORcv*) indicates a heterogeneous, clustered distribution of pores.

2.1.3 Mineralization heterogeneity

Given that the backscattered signal intensity is proportional to the average atomic number of a material, the mineral phase essentially dictates the qBEI intensity. Histograms of the gray-levels in the qBEI images provided the most frequently occurring gray value (*BSEpeak*) and the width at half maximum (*BSEwidth*) describing the variation in degree of mineralization over the cross-section ($\sim 10 \text{ mm}^2$) (Fig.3B).

The width of the histogram does not inform on the clustering of the heterogeneities (Supplementary Fig.3). Therefore, an additional analysis involved computing experimental variograms, which were used to describe the local inhomogeneity of tissue mineralization. Descriptions of calculating variograms can be found in previous bone studies that described the inhomogeneity in tissue elastic properties from maps of nanoindentation modulus (Dong et al., 2010) and the inhomogeneity in areal bone mineral density maps from hip scans by dual-energy X-ray absorptiometry (Dong et al., 2015). In the present study, an isotropic variogram of the qBEI image was built by computing $\gamma(h)$, the mean squared gray-level differences between pixels

separated by a distance h spanning from 1 to 250 μm . Upon fitting the experimental variogram with an exponential function,

$$\gamma(h) = c_0 + c \left(1 - e^{-\frac{3h}{L}}\right) \quad (3)$$

the asymptote of the variogram ($c+c_0$) or *sill* provided a measure of the semi-variance in mineralization over a length scale of 250 μm (Fig.3C). This length scale was chosen because it is small enough to represent the variance in mineralization at a local scale (i.e., the scale of an osteon) and it is large enough to ensure that pixels would not be auto-correlated (i.e., once the variogram levels off).

2.1.4 Microstructure analysis

Based on differences in gray levels, osteonal and interstitial tissues were manually segmented within a sub-region (1.5 mm x 1.5 mm) at the center of each qBEI image (Fig.4B) using an interactive tablet monitor (Wacom Technology Co., Vancouver, WA). Manual segmentation is commonly used to distinguish osteonal from interstitial tissue (Bernhard et al., 2013; Tommasini et al., 2008; Wachter et al., 2002; Wang et al., 2015) and increasing the image contrast for this step made the segmentation unambiguous. Area fraction of osteonal tissue ($OstAr$) with respect to the total area of the sub-region was computed for each sub-region. BSE_{peak} was computed for both the distribution of osteonal and interstitial tissue, respectively. Contrast in mineralization in this sub-region was evaluated as the ratio of the interstitial BSE_{peak} to the osteonal BSE_{peak} ($IOratio$).

2.2 Statistical analysis

In a preliminary analysis, we verified that the pores examined with qBEI from neighboring cross-sections were representative of the pores within the region where the crack actually propagated (a few millimeters away in the osteon direction, Fig.1). The vascular porosity derived from qBEI images (*VasPor*) was therefore compared to the vascular porosity of the notched region imaged with μ CT (*Ct.Po*) using the equation and correlation coefficient of the linear fit between these two quantities.

Upon running multiple linear regressions with age and gender as covariates on all parameters reported (i.e. including properties related to fracture toughness, porosity, mineralization, and microstructure), gender was only significant for K_{init} (Supplementary Table 1). Further analysis revealed that this association between gender and K_{init} was driven by two particular specimens as the p-value of gender was greater than 0.082 after excluding these donors (N=60 instead of N=62). Therefore, age but not gender was included as a covariate in subsequent regression analyses.

Statistical analyses were performed on bootstrapped data (1000 replicates) to account for the non-normality of most parameters (Shapiro-Wilk test). Pearson correlation coefficients were used to assess the linear dependence of fracture toughness parameters on potential explanatory variables related to age, porosity, mineral heterogeneity, and microstructure (Table 1). Potential predictors (age and parameters related to porosity, mineralization, and microstructure) with weak correlations ($r < 0.55$, Supplemental Table 2) and their interactions were included as independent explanatory variables in multiple linear regressions. For each model, backward stepwise elimination was used to remove non-significant terms until obtaining a combination of variables that all significantly explained the variance in the fracture toughness properties (Table 2).

Statistical significance of a predictor was reached when the associated p-value was less than 0.05. Analyses were performed using STATA 12 (StataCorp LP, College Station, TX).

3. Results

The vascular porosity estimated from qBEI images of a neighboring cross-section strongly correlated with the porosity of the material in the crack path as assessed with μ CT prior to mechanical testing ($R^2 = 87.2\%$). While the slope of the linear fit between *VasPor* and *Ct.Po* was not significantly different from unity, the intercept was significantly different from zero: qBEI yielded higher values of porosity compared to μ CT, possibly because of the lower resolution of the latter technique (Supplementary Fig.4).

Among all reported parameters, vascular porosity showed the highest, negative correlation with crack initiation toughness (K_{init}) and the energy dissipated (J) during fracture (Table 1). As higher porosity was associated with more clustered pores (Supplementary Table 2), a more heterogeneous spatial distribution of porosity was also related to a decrease in the aforementioned fracture toughness properties (Table 1). Lacunar porosity was positively correlated with fracture toughness properties (Table 1). However, this relationship may not be causal but rather reflects the fact that both lacunar porosity and fracture toughness properties decrease with age. Indeed, the correlations between lacunar porosity and fracture toughness properties were not significant when adding age as a covariate.

Among the parameters characterizing the distribution of mineralization within the matrix, the average degree of mineralization (*BSEPeak*), bulk or population heterogeneity in tissue mineralization (*BSEwidth*) and mineralization ratio between interstitial and osteonal tissue (*IOratio*) did not correlate with any of the fracture toughness properties (Table 1). However, local

heterogeneity (*sill*) as derived from the variogram analysis was greater in bone specimens with a lower resistance to crack initiation (*Kinit*) and a reduced ability to dissipate energy (*J*) (Table 1).

With respect to the microstructure, bone specimens having a greater area fraction of osteonal tissue (*OstAr*) tended to have greater resistance to crack initiation and propagation (Table 1 and Fig. 5). Microstructure, local heterogeneity in mineralization, and vascular porosity each remained significant predictors of crack initiation toughness and energy dissipated during fracture after adjusting for age. Cortical porosity had a stronger contribution to *Kinit* than age, whereas age had a stronger contribution to *Kinit* than the heterogeneity parameters (*BSEwidth* and *sill*) and *OstAr* (standardized coefficients, Table 2). The combination that best explained the age-related variance in fracture toughness properties included age, cortical porosity, and the microstructural feature related to cement lines (Table 2 and Fig.5). Most notably, none of the parameters describing the heterogeneity in mineralization (*BSEwidth*, *sill* or *IOratio*) combined with either *VasPor* or *OstAr* improved the prediction of fracture toughness.

4. Discussion

Changes in the distribution of bone mineralization occurring with aging, disease, or treatment have prompted concerns that alterations in mineralization heterogeneity may affect the fracture resistance of bone. Owing to the multifactorial nature of toughening mechanisms occurring in bone, we aimed to put into perspective the relative contribution of heterogeneity in mineralization to bone fracture resistance in comparison to other important factors. Our results obtained from 62 human donors spanning the age of adulthood (21 years to 101 years) suggest that changes in porosity and microstructure overwhelm the contribution of heterogeneity in tissue mineralization to explain the age-related loss in fracture toughness of human cortical bone.

As expected from experimental (Yeni et al., 1997) and computational studies (Besdo and Vashishth, 2012; Tang and Vashishth, 2011; Ural and Vashishth, 2007), our data confirmed the detrimental effect of an increase in intracortical porosity on bone's fracture toughness: the matrix of highly porous tissue presents higher local strains, facilitating the initiation of cracks which then propagate faster through the pores. In addition, we found that a more clustered distribution of porosity was negatively correlated with the three fracture toughness properties of human cortical bone. However, because greater vascular porosity was associated with a more clustered distribution of pores ($r = 0.86$, supplemental Table 2), the pore clustering did not help improve the prediction of fracture toughness properties when accounting for intra-cortical porosity.

In addition to porosity, bone microstructure (i.e., the compartmentalization of the matrix in osteonal and interstitial tissue) possibly plays an important role in bone's ability to resist fracture as cement lines and lamellar pattern in osteons affect the propagation of cracks in bone tissue (Chan et al., 2009; Ural and Mischinski, 2013; Zioupos, 2001). Our results suggest that an overall greater osteonal area fraction increases bone's fracture toughness properties, even when including the contribution of porosity. This suggests that the presence of relatively newer tissue within osteons and cement lines favor fracture resistance. Interestingly, *OstAr* was the only selected property to correlate with crack propagation toughness supporting the importance of cement lines to crack deflection, but significance of this relationship was lost when age was included as covariate. Histological studies of human bone have shown that linear microcracks preferentially form and propagate within interstitial bone and are arrested by the cement lines and lamellar interfaces of osteons (Diab and Vashishth, 2007): this would explain why a greater osteonal area fraction favors bone's resistance to fracture.

Even though material heterogeneity is thought to promote toughening mechanisms in composites like bone, population and local heterogeneity in tissue mineralization were negatively

correlated with crack initiation toughness and energy dissipated during fracture when age was included as covariate (Table 2); and notably, a local measure (*sill*) was a better predictor than a bulk measure (*BSEwidth*) of heterogeneity. This is consistent with findings reporting weak, negative correlations between heterogeneity in microhardness (mean ratio of interstitial to osteonal areas) and fracture toughness in which the crack propagation was parallel to the osteonal axis (Phelps et al., 2000) or fatigue strength of cortical bone in tension (Zioupos et al., 2008) and supports the notion that heterogeneity at the length scale of ~200 μm can promote crack formation by concentrating strains within the bone matrix. Nonetheless, the prevailing finding of this work is that microstructural heterogeneity in tissue mineralization did not help explain changes in fracture toughness properties after accounting for age, porosity and microstructure. This is in agreement with the findings from the largest tissue composition study to date (Boskey et al., 2016) showing that heterogeneity in various outcomes (mineral-to-matrix ratio, carbonate-to-phosphate ratio, crystallinity, acid phosphate substitution, collagen maturity) at the micron length scale is not significantly different between female subjects with and without a fracture, when controlling for age and areal bone mineral density (60 subjects in each group).

The present study brings new insights into interpreting the effect of treatment-related changes at the tissue level on bone's fracture resistance. In particular, the association between the occurrence of atypical femoral fractures and the long-term use of bisphosphonates, established as the first-line therapy for osteoporosis, has promulgated the idea that the reduced microstructural heterogeneity in mineralization observed in treated patients (Donnelly et al., 2012; Roschger et al., 2008; Zoehrer et al., 2006) may contribute to these rare, but adverse events (Ettinger et al., 2013). Our results suggest that the significant reduction in cortical porosity that follows anti-resorptive treatment (Borah et al., 2010; Misof et al., 2014; Zebaze et al., 2014) would far outweigh the shift toward a more homogenous tissue mineralization. Moreover, that shift back to

a narrower distribution may itself promote fracture resistance as menopause-related increase in remodeling likely leads to excessive heterogeneity (Roschger et al., 2008), which could decrease crack initiation toughness (Table 2). Notably, bisphosphonates remain effective in reducing fracture risk for a vast majority of patients after years of use (Chen and Sambrook, 2012; Eriksen et al., 2014), though drug holidays may minimize the impact of suppressed remodeling on the accumulation of glycation-mediated, non-enzymatic crosslinks. Generally, the present study points out that difficulty in establishing a causal relationship between tissue mineralization and skeletal fragility if underlying changes in porosity are ignored.

This study is limited to a few features of cortical bone which only capture up to 50% of the variance in fracture toughness properties highlighting the need to investigate alternative toughening mechanisms to fully comprehend bone's fracture resistance. The favorable role of osteonal tissue (Table 2) likely pertains to its concentric lamellar structure where layers of mineralized collagen fibers are laid with changing orientations (Giraud-Guille, 1988), requiring more energy for a crack to penetrate through this composite structure. Indeed, the mechanical inhomogeneity at the lamellar scale produced by different collagen fiber orientation has been described as an important toughening mechanism (Katsamenis et al., 2015) in addition to the orientation of the collagen fibrils relative to the crack direction (Peterlik et al., 2006). This suggests that heterogeneity in collagen orientation rather than in tissue mineralization could be a more important determinant of bone fracture toughness. It remains to be seen whether alterations in collagen-related properties (e.g., crosslinking profile, amount of collagen) would significantly contribute to bone's integrity in addition to cortical porosity. The non-mineral component of the matrix may actually be a more important contributor to fracture toughness than mineralization as computational models suggest that heterogeneity in plastic rather than elastic properties plays a major role in promoting energy dissipation at the sub-micron scale (Yao et al., 2011). Moreover,

material heterogeneity at length scales smaller than a micron may promote fracture toughness of cortical bone as suggested by computational modeling (Tai et al., 2007). Finally, numerous mechanisms at the nanoscale also participate in providing bone its ability to resist fracture (Turner and Katsamenis, 2014), including non-enzymatic collagen cross-links (Poundarik et al., 2015), non-collagenous proteins (Katsamenis et al., 2013; Poundarik et al., 2012), bound water (Granke et al., 2015), and microdamage (Norman et al., 1998; Seref-Ferlengez et al., 2015; Zioupos, 2001).

Another limitation of the present study was that specimens came from the femoral mid-shaft, which is not a typical fracture site. However, it is reasonable to assume that aging, diseases, or drug therapy would affect the skeleton in a systemic manner, in other words, changes in porosity and mineralization occurring at the femoral mid-shaft would also occur at the femoral neck. In a recent study, Abraham et al. (2015) showed that porosity, microindentation, and collagen crosslinks measures at the tibia could predict fragility of the femoral neck.

In summary, assessing the microstructure of cortical bone specimens from 62 human donors, we found that age, cortical porosity and osteonal fraction explained up to 50% of the variance in bone's fracture toughness properties and that including microstructural heterogeneity in tissue mineralization did not improve upon this prediction. Moreover, this heterogeneity is negatively correlated with crack initiation toughness. The findings of the present work stress the necessity to account for porosity and microstructure when evaluating the potential of matrix-related features to affect skeletal fragility.

Acknowledgements

The National Institute of Arthritis and Musculoskeletal and Skin Diseases of the National Institutes of Health (NIH) under AR063157 primarily funded this work. The micro-computed

tomography scanner was supported by the National Center for Research Resources (1S10RR027631) and matching funds from the Vanderbilt Office of Research. Additional funding to perform the work was received from the Department of Veterans Affairs, Veterans Health Administration, Office of Research and Development (1I01BX001018) and the National Science Foundation (1068988) to collect specimens and develop the fracture toughness testing protocol. SEM imaging was performed through the use of the VUMC Cell Imaging Shared Resource (supported by NIH grants CA68485, DK20593, DK58404, DK59637 and EY08126).

References

- Abraham, A.C., Agarwalla, A., Yadavalli, A., McAndrew, C., Liu, J.Y., Tang, S.Y., 2015. Multiscale Predictors of Femoral Neck In Situ Strength in Aging Women: Contributions of BMD, Cortical Porosity, Reference Point Indentation, and Nonenzymatic Glycation. *J Bone Miner Res* 30, 2207-2214.
- Ahmed, L.A., Shigdel, R., Joakimsen, R.M., Eldevik, O.P., Eriksen, E.F., Ghasem-Zadeh, A., Bala, Y., Zebaze, R., Seeman, E., Bjornerem, A., 2015. Measurement of cortical porosity of the proximal femur improves identification of women with nonvertebral fragility fractures. *Osteoporos Int* 26, 2137-2146.
- ASTM Standard E1820-15a, 2015. Standard Test Method for Measurement of Fracture Toughness.
- Aurenhammer, F., 1991. Voronoi diagrams - A survey of a fundamental geometric data structure. *ACM Comput. Surv.* 23, 345-405.
- Bala, Y., Zebaze, R., Ghasem-Zadeh, A., Atkinson, E.J., Iuliano, S., Peterson, J.M., Amin, S., Bjornerem, A., Melton, L.J., 3rd, Johansson, H., Kanis, J.A., Khosla, S., Seeman, E., 2014. Cortical porosity identifies women with osteopenia at increased risk for forearm fractures. *J Bone Miner Res* 29, 1356-1362.
- Bell, K.L., Loveridge, N., Jordan, G.R., Power, J., Constant, C.R., Reeve, J., 2000. A novel mechanism for induction of increased cortical porosity in cases of intracapsular hip fracture. *Bone* 27, 297-304.

336 Bell, K.L., Loveridge, N., Power, J., Garrahan, N., Meggitt, B.F., Reeve, J., 1999. Regional
337 differences in cortical porosity in the fractured femoral neck. *Bone* 24, 57-64.

338 Bernhard, A., Milovanovic, P., Zimmermann, E.A., Hahn, M., Djonic, D., Krause, M., Breer, S.,
339 Puschel, K., Djuric, M., Amling, M., Busse, B., 2013. Micro-morphological properties of osteons
340 reveal changes in cortical bone stability during aging, osteoporosis, and bisphosphonate treatment
341 in women. *Osteoporos Int* 24, 2671-2680.

342 Besdo, S., Vashishth, D., 2012. Extended Finite Element models of intracortical porosity and
343 heterogeneity in cortical bone. *Comp Mater Sci* 64, 301-305.

344 Bilger, N., Auslender, F., Bornert, M., Michel, J.-C., Moulinec, H., Suquet, P., Zaoui, A., 2005.
345 Effect of a nonuniform distribution of voids on the plastic response of voided materials: a
346 computational and statistical analysis. *Int J Solids Struct* 42, 517-538.

347 Borah, B., Dufresne, T., Nurre, J., Phipps, R., Chmielewski, P., Wagner, L., Lundy, M.,
348 Bouxsein, M., Zebaze, R., Seeman, E., 2010. Risedronate reduces intracortical porosity in women
349 with osteoporosis. *J Bone Miner Res* 25, 41-47.

350 Boskey, A.L., Donnelly, E., Boskey, E., Spevak, L., Ma, Y., Zhang, W., Lappe, J., Recker, R.R.,
351 2016. Examining the Relationships between Bone Tissue Composition, Compositional
352 Heterogeneity and Fragility Fracture: A Matched Case Controlled FTIR Study. *J Bone Miner*
353 *Res* 31, 1070-1081.

354 Bousson, V., Bergot, C., Wu, Y., Jolivet, E., Zhou, L.Q., Laredo, J.D., 2011. Greater tissue
355 mineralization heterogeneity in femoral neck cortex from hip-fractured females than controls. A
356 microradiographic study. *Bone* 48, 1252-1259.

357 Chan, K.S., Chan, C.K., Nicoletta, D.P., 2009. Relating crack-tip deformation to mineralization
358 and fracture resistance in human femur cortical bone. *Bone* 45, 427-434.

359 Chen, J.S., Sambrook, P.N., 2012. Antiresorptive therapies for osteoporosis: a clinical overview.
360 *Nature reviews. Endocrinology* 8, 81-91.

361 Diab, T., Vashishth, D., 2007. Morphology, localization and accumulation of in vivo
362 microdamage in human cortical bone. *Bone* 40, 612-618.

363 Dimas, L.S., Giesa, T., Buehler, M.J., 2014. Coupled continuum and discrete analysis of random
364 heterogeneous materials: Elasticity and fracture. *J Mech Phys Solids* 63, 481-490.

365 Dong, X.N., Luo, Q., Sparkman, D.M., Millwater, H.R., Wang, X., 2010. Random field
366 assessment of nanoscopic inhomogeneity of bone. *Bone* 47, 1080-1084.

367 Dong, X.N., Pinninti, R., Lowe, T., Cussen, P., Ballard, J.E., Di Paolo, D., Shirvaikar, M., 2015.
368 Random field assessment of inhomogeneous bone mineral density from DXA scans can enhance
369 the differentiation between postmenopausal women with and without hip fractures. *J Biomech*
370 48, 1043-1051.

371 Donnelly, E., Lane, J.M., Boskey, A.L., 2014. Research perspectives: The 2013 AAOS/ORS
372 research symposium on Bone Quality and Fracture Prevention. *J Orthop Res* 32, 855-864.

373 Donnelly, E., Meredith, D.S., Nguyen, J.T., Gladnick, B.P., Rebolledo, B.J., Shaffer, A.D.,
374 Lorch, D.G., Lane, J.M., Boskey, A.L., 2012. Reduced cortical bone compositional
375 heterogeneity with bisphosphonate treatment in postmenopausal women with intertrochanteric
376 and subtrochanteric fractures. *J Bone Miner Res* 27, 672-678.

377 Eriksen, E.F., Diez-Perez, A., Boonen, S., 2014. Update on long-term treatment with
378 bisphosphonates for postmenopausal osteoporosis: a systematic review. *Bone* 58, 126-135.

379 Ettinger, B., Burr, D.B., Ritchie, R.O., 2013. Proposed pathogenesis for atypical femoral
380 fractures: lessons from materials research. *Bone* 55, 495-500.

381 Giraud-Guille, M.M., 1988. Twisted plywood architecture of collagen fibrils in human compact
382 bone osteons. *Calcif Tissue Int* 42, 167-180.

383 Gourion-Arsiquaud, S., Lukashova, L., Power, J., Loveridge, N., Reeve, J., Boskey, A.L., 2013.
384 Fourier transform infrared imaging of femoral neck bone: reduced heterogeneity of mineral-to-
385 matrix and carbonate-to-phosphate and more variable crystallinity in treatment-naïve fracture
386 cases compared with fracture-free controls. *J Bone Miner Res* 28, 150-161.

387 Granke, M., Makowski, A.J., Uppuganti, S., Does, M.D., Nyman, J.S., 2015. Identifying novel
388 clinical surrogates to assess human bone fracture toughness. *J Bone Miner Res* 30, 1290-1300.

389 Hossain, M.Z., Hsueh, C.J., Bourdin, B., Bhattacharya, K., 2014. Effective toughness of
390 heterogeneous media. *J Mech Phys Solids* 71, 15-32.

391 Jordan, G.R., Loveridge, N., Bell, K.L., Power, J., Rushton, N., Reeve, J., 2000. Spatial
392 clustering of remodeling osteons in the femoral neck cortex: a cause of weakness in hip fracture?
393 *Bone* 26, 305-313.

394 Katsamenis, O.L., Chong, H.M., Andriotis, O.G., Thurner, P.J., 2013. Load-bearing in cortical
395 bone microstructure: Selective stiffening and heterogeneous strain distribution at the lamellar
396 level. *J Mech Behav Biomed Mater* 17, 152-165.

397 Katsamenis, O.L., Jenkins, T., Thurner, P.J., 2015. Toughness and damage susceptibility in
398 human cortical bone is proportional to mechanical inhomogeneity at the osteonal-level. *Bone* 76,
399 158-168.

400 Milovanovic, P., Rakocevic, Z., Djonic, D., Zivkovic, V., Hahn, M., Nikolic, S., Amling, M.,
401 Busse, B., Djuric, M., 2014. Nano-structural, compositional and micro-architectural signs of
402 cortical bone fragility at the superolateral femoral neck in elderly hip fracture patients vs. healthy
403 aged controls. *Experimental gerontology* 55, 19-28.

404 Misof, B.M., Patsch, J.M., Roschger, P., Muschitz, C., Gamsjaeger, S., Paschalis, E.P., Prokop,
405 E., Klaushofer, K., Pietschmann, P., Resch, H., 2014. Intravenous treatment with ibandronate

406 normalizes bone matrix mineralization and reduces cortical porosity after two years in male
407 osteoporosis: a paired biopsy study. *J Bone Miner Res* 29, 440-449.

408 Norman, T.L., Yeni, Y.N., Brown, C.U., Wang, Z., 1998. Influence of microdamage on fracture
409 toughness of the human femur and tibia. *Bone* 23, 303-306.

410 O'Brien, F.J., Taylor, D., Lee, T.C., 2003. Microcrack accumulation at different intervals during
411 fatigue testing of compact bone. *J Biomech* 36, 973-980.

412 Otsu, N., 1979. A Threshold Selection Method from Gray-Level Histograms. *IEEE Transactions*
413 *on Systems, Man, and Cybernetics* 9, 62-66.

414 Peterlik, H., Roschger, P., Klaushofer, K., Fratzl, P., 2006. From brittle to ductile fracture of
415 bone. *Nat Mater* 5, 52-55.

416 Phelps, J.B., Hubbard, G.B., Wang, X., Agrawal, C.M., 2000. Microstructural heterogeneity and
417 the fracture toughness of bone. *J Biomed Mater Res* 51, 735-741.

418 Poundarik, A.A., Diab, T., Sroga, G.E., Ural, A., Boskey, A.L., Gundberg, C.M., Vashishth, D.,
419 2012. Dilatational band formation in bone. *Proc Natl Acad Sci USA* 109, 19178-19183.

420 Poundarik, A.A., Wu, P.C., Evis, Z., Sroga, G.E., Ural, A., Rubin, M., Vashishth, D., 2015. A
421 direct role of collagen glycation in bone fracture. *J Mech Behav Biomed Mater* 50, 82-92.

422 Roschger, P., Paschalis, E.P., Fratzl, P., Klaushofer, K., 2008. Bone mineralization density
423 distribution in health and disease. *Bone* 42, 456-466.

424 Seref-Ferlengez, Z., Kennedy, O.D., Schaffler, M.B., 2015. Bone microdamage, remodeling and
425 bone fragility: how much damage is too much damage? *Bonekey Rep* 4, 644.

426 Shigdel, R., Osima, M., Ahmed, L.A., Joakimsen, R.M., Eriksen, E.F., Zebaze, R., Bjornerem,
427 A., 2015. Bone turnover markers are associated with higher cortical porosity, thinner cortices,
428 and larger size of the proximal femur and non-vertebral fractures. *Bone* 81, 1-6.

429 Tai, K., Dao, M., Suresh, S., Palazoglu, A., Ortiz, C., 2007. Nanoscale heterogeneity promotes
430 energy dissipation in bone. *Nat Mater* 6, 454-462.

431 Tang, S.Y., Vashishth, D., 2011. The relative contributions of non-enzymatic glycation and
432 cortical porosity on the fracture toughness of aging bone. *J Biomech* 44, 330-336.

433 Turner, P.J., Katsamenis, O.L., 2014. The role of nanoscale toughening mechanisms in
434 osteoporosis. *Curr Osteoporos Rep* 12, 351-356.

435 Tommasini, S.M., Nasser, P., Hu, B., Jepsen, K.J., 2008. Biological co-adaptation of
436 morphological and composition traits contributes to mechanical functionality and skeletal
437 fragility. *J Bone Miner Res* 23, 236-246.

438 Ural, A., Mischinski, S., 2013. Multiscale modeling of bone fracture using cohesive finite
439 elements. *Eng Fract Mech* 103, 141-152.

440 Ural, A., Vashishth, D., 2007. Effects of intracortical porosity on fracture toughness in aging
441 human bone: a microCT-based cohesive finite element study. *J Biomech Eng* 129, 625-631.

442 Ural, A., Vashishth, D., 2014. Hierarchical perspective of bone toughness – from molecules to
443 fracture. *International Materials Reviews* 59, 245-263.

444 Wachter, N.J., Krischak, G.D., Mentzel, M., Sarkar, M.R., Ebinger, T., Kinzl, L., Claes, L.,
445 Augat, P., 2002. Correlation of bone mineral density with strength and microstructural
446 parameters of cortical bone in vitro. *Bone* 31, 90-95.

447 Wang, M., Gao, X., Abdel-Wahab, A., Li, S., Zimmerman, E.A., Riedel, C., Busse, B.,
448 Silberschmidt, V., 2015. Effect of micromorphology of cortical bone tissue on crack propagation
449 under dynamic loading. *EPJ Web of Conferences* 94, 03005.

450 Yao, H., Dao, M., Carnelli, D., Tai, K., Ortiz, C., 2011. Size-dependent heterogeneity benefits the
451 mechanical performance of bone. *J Mech Phys Solids* 59, 64-74.

452 Yeni, Y.N., Brown, C.U., Wang, Z., Norman, T.L., 1997. The influence of bone morphology on
453 fracture toughness of the human femur and tibia. *Bone* 21, 453-459.

454 Zebaze, R.M., Libanati, C., Austin, M., Ghasem-Zadeh, A., Hanley, D.A., Zanchetta, J.R.,
455 Thomas, T., Boutroy, S., Bogado, C.E., Bilezikian, J.P., Seeman, E., 2014. Differing effects of
456 denosumab and alendronate on cortical and trabecular bone. *Bone* 59, 173-179.

457 Zioupos, P., 2001. Accumulation of in-vivo fatigue microdamage and its relation to
458 biomechanical properties in ageing human cortical bone. *J Microsc* 201, 270-278.

459 Zioupos, P., Gresle, M., Winwood, K., 2008. Fatigue strength of human cortical bone: age,
460 physical, and material heterogeneity effects. *J Biomed Mater Res A* 86, 627-636.

461 Zoehrer, R., Roschger, P., Paschalis, E.P., Hofstaetter, J.G., Durchschlag, E., Fratzl, P., Phipps,
462 R., Klaushofer, K., 2006. Effects of 3- and 5-year treatment with risedronate on bone
463 mineralization density distribution in triple biopsies of the iliac crest in postmenopausal women. *J*
464 *Bone Miner Res* 21, 1106-1112.

Figure legends

Figure 1: Study design. (A) Single-edge notch beam specimens were machined from the femoral mid-shaft. The notch region was scanned with μ CT to image porosity prior to mechanical testing. (B) Following fracture toughness testing, a cross-section was cut close to the fracture line, polished, and mounted on a stub with standard materials for calibration. (C) qBEI images (in gray levels) of bone from young (23-year-old, left) and old (96-year-old, right) donors.

Figure 2: Characterization of cortical porosity from qBEI images. (A) Original image from a 47 years old female donor. (B) Porosity mask: black pixels include vascular and lacunar porosity. (C) Voronoi diagrams (red) are used to quantify the spatial distribution of vascular porosity.

Figure 3: Characterization of the distribution of mineralization from qBEI images. (A) Original image from a 24-year-old male donor. (B) Histogram of gray-levels in the qBEI images provides *BSEpeak*, the most frequent gray value, and *BSEwidth*, the width of the distribution, a measure of the overall heterogeneity in mineralization at the scale of the sample. (C) Experimental variogram describes the local heterogeneity in mineralization over a fixed length scale of 250 μ m.

Figure 4: A sub-region ($1.5 \times 1.5 \text{ mm}^2$) was obtained from the center of the qBEI image. (A) Enhancing the contrast of the qBEI image facilitated the visualization of the boundaries between osteonal and interstitial tissues based on gray levels. (B) Resulting segmentation distinguished between pores (black), osteonal (gray) and interstitial (white) tissue.

Figure 5: 3D bar graphs representing fracture toughness properties (K_{init} on the left, J on the right) as a function of vascular porosity and osteonal area fraction. Simple linear regressions are plotted in the background for each variable.

Tables

Table 1: Significant Pearson's correlation coefficients and corresponding p-values calculated from bootstrapped data.

	Age	Porosity			Mineralization				Microstructure
		Lacunar porosity (<i>LacPor</i>)	Vascular porosity (<i>VasPor</i>)	Pore clustering (<i>VORcv</i>)	Degree of mineralization (<i>BSEpeak</i>)	Bulk heterogeneity (<i>BSEwidth</i>)	Local heterogeneity (<i>sill</i>)	Inters./Osteon heterogeneity (<i>IOratio</i>)	Osteon area fraction (<i>OstAr</i>)
Age	.	-0.43 <i>0.002</i>	0.33 <i>0.039</i>	0.39 <i>0.004</i>	ns ^a <i>0.346</i>	-0.27 <i>0.073</i>	ns <i>0.432</i>	-0.35 <i>0.011</i>	-0.45 <i><0.001</i>
K_{init}	-0.48 <i><0.001</i>	0.33 <i>0.020</i>	-0.65 <i><0.001</i>	-0.59 <i><0.001</i>	ns <i>0.575</i>	ns <i>0.232</i>	-0.41 <i><0.001</i>	ns <i>0.890</i>	0.44 <i><0.001</i>
K_{grow}	-0.41 <i>0.010</i>	ns <i>0.378</i>	-22.4 <i>0.063</i>	-0.31 <i>0.006</i>	ns <i>0.144</i>	ns <i>0.805</i>	ns <i>0.579</i>	ns <i>0.207</i>	0.36 <i>0.020</i>
J	-0.36 <i>0.001</i>	0.23 <i>0.071</i>	-0.38 <i><0.001</i>	-0.37 <i><0.001</i>	ns <i>0.165</i>	ns <i>0.510</i>	-0.23 <i>0.041</i>	ns <i>0.174</i>	0.42 <i><0.001</i>

^ans indicates that the correlation is not statistically significant.

Table 2: Best-fit multivariate linear combinations of parameters explaining the variance in the fracture toughness of human cortical bone obtained upon running multiple linear regressions using backward stepwise elimination.

Fracture toughness property	Explanatory variables	Linear model ^a	Adj-R ² (%)
K_{init}	age + porosity	age ($\beta = -0.29$, $p = 0.004$) VasPor ($\beta = -0.55$, $p < 0.001$) age ($\beta = -0.29$, $p = 0.011$) VORcv ($\beta = -0.47$, $p < 0.001$)	47.7 39.6
	age + heterogeneity	age ($\beta = -0.56$, $p < 0.001$) BSEwidth ($\beta = -0.33$, $p = 0.005$) age ($\beta = -0.53$, $p < 0.001$) sill ($\beta = -0.47$, $p < 0.001$)	30.2 42.5
	age + microstructure	age ($\beta = -0.35$, $p = 0.006$) OstAr ($\beta = 0.29$, $p = 0.004$)	26.8
	best combination	age ($\beta = -0.22$, $p = 0.047$) VasPor ($\beta = -0.52$, $p < 0.001$) OstAr ($\beta = 0.19$, $p = 0.033$)	49.7
K_{grow}	age + porosity	age ($\beta = -0.41$, $p < 0.001$)	17.1
	age + heterogeneity	age ($\beta = -0.41$, $p < 0.001$)	17.1
	age + microstructure	age ($\beta = -0.41$, $p < 0.001$)	17.1
	best combination	age ($\beta = -0.41$, $p < 0.001$)	17.1
J	age + porosity	age ($\beta = -0.26$, $p = 0.028$) VasPor ($\beta = -0.30$, $p = 0.007$) age ($\beta = -0.25$, $p = 0.026$) VORcv ($\beta = -0.27$, $p = 0.003$)	17.9 16.1
	age + heterogeneity	age ($\beta = -0.39$, $p < 0.001$) sill ($\beta = -0.28$, $p = 0.016$)	17.6
	age + microstructure	OstAr ($\beta = 0.42$, $p < 0.001$)	17.7
	best combination	VasPor ($\beta = -0.28$, $p = 0.001$) OstAr ($\beta = 0.34$, $p = 0.001$)	22.4

^aNone of the interaction terms were significant.

^b β is the standardized coefficients from the general linear model.

Figureg

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5