Acid site densities and reactivity of oxygen-modified transition metal carbide catalysts

Mark M. Sullivan^a and Aditya Bhan^{a, *}

^a *Department of Chemical Engineering and Materials Science*

University of Minnesota - Twin Cities

421 Washington Avenue SE

Minneapolis, Minnesota 55455

USA

* Corresponding author.

E-mail addresses: sulli931@umn.edu (M. Sullivan), abhan@umn.edu (A. Bhan).

Abstract

Acidic properties of β -Mo₂C, α -Mo₂C, W₂C, and WC were quantified by assessing the kinetics of isopropanol (IPA) dehydration at 415 K either (i) under inert He/Ar atmosphere, or (ii) with 13 kPa O₂ co-feed. Dehydration kinetics were zero-order with respect to IPA for all catalysts and under all reaction conditions. Intrinsic activation energies were similar across all catalysts (89 – 104 kJ mol⁻¹). Acid site densities calculated via in situ 2,6-di-tert-butylpyridine (DTBP) titration were used to normalize dehydration turnover frequencies (TOF). O₂ co-feed increased dehydration rates per gram by an order of magnitude for all catalysts tested, but TOF remained invariant within a factor of ~2. Mo and W based carbides showed similar dehydration kinetics regardless of O₂ co-feed, and O₂ co-feed did not alter bulk carbidic structure as noted by X-ray diffraction. Brønsted acid site provenance results from the oxophilicity of Mo and W carbides.

Keywords: Brønsted acid, dehydration, molybdenum carbide, tungsten carbide, interstitial carbide, catalysis, site density, oxophilic, transition metal

1. Introduction

Multifunctional interstitial transition metal carbide catalysts have been shown to catalyze hydrogenolysis,¹⁻³ hydrogenation,^{2,4-7} isomerization,⁸⁻¹² and hydrodeoxygenation (HDO)¹³⁻¹⁷ reactions. The diverse functionalities of transition metal carbide bulk formulations arise from different catalytically active sites generated by modification of the catalyst surface. Ribeiro et al.^{18,19} reported a bifunctional metal-acid surface of an oxygen-modified tungsten carbide formulation that catalyzed isomerization of C₅-C₇ alkanes at atmospheric pressure and 430-630 K via sequential dehydrogenation/methyl shift/hydrogenation pathways as evinced by terminal isotopic enrichment in n-heptane-1-¹³C isomerization reactions in contrast to the C₅ hydrogenolysis mechanism prevalent over noble metals that would also yield isotopic enrichment of interior carbon atoms. WC and W₂C catalysts were oxygen-modified via slow O₂ introduction (0.1 μmol s⁻¹ g⁻¹) at room temperature followed by heating under 20 kPa O₂ to 300-800 K, and catalysts were finally pretreated under H₂ flow at 673 K for 1-2 h prior to exposure to reaction conditions (95 kPa H₂). The presence of Brønsted acid sites on O*-WC_x catalysts was implicated by the methyl shift isomerization mechanism in addition to ex situ NH₃ temperature programmed desorption (TPD) studies; these acid sites were shown to be similar to acid sites on WO_x catalysts because comparable product distributions of 3,3-dimethylpentane isomerization over O*-WC and Al₂O₃-supported Pt/WO₃ catalysts were observed. Isomerization site time yields, normalized by ex situ irreversible CO chemisorption uptakes, were similar over 700-K oxygen-modified WC and W₂C catalysts (244 x 10⁻³ vs. 125 x 10⁻³ s⁻¹).^{8,18,19} Lamic and coworkers²⁰ also demonstrated isomerization of n-heptane over both bifunctional WC_x and mixed

Mo₂C/WO₂ catalysts, hypothesizing that the carbidic Mo₂C or WC_x acts as the de/hydrogenation catalyst and the acidic WO₂ provides the Brønsted acidic site necessary for the isomerization of n-heptene via a carbenium ion intermediate.

Iglesia and coworkers^{21,22} demonstrated the presence of both Brønsted and Lewis acid sites on supported WO_x catalysts that were active for both isomerization and dehydration through the use of in situ pyridine and 2,6-di-tert-butylpyridine (DTBP) titrations. Ruddy and coworkers^{23,24} demonstrated the presence of acid sites on bulk β-Mo₂C and on SBA-15-supported α-MoC_{1-x} nanoparticles via both NH₃ temperature programmed desorption (TPD) studies and density functional theory (DFT) calculations that showed comparable NH₃ binding energies between O*-MoC_x and proton-form zeolites. Although acid sites have been reported to exist across transition metal oxides and oxygen-modified transition metal carbides, quantification and comparison of acid site densities and strengths are lacking, and similarities between oxidic and carbidic acid sites have yet to be characterized.

We have previously investigated the acidic and metallic characteristics of molybdenum carbide catalytic formulations during HDO of biomass-derived oxygen-containing molecules including anisole, furfural, m-cresol, and acetone.²⁵⁻³¹ Metallic sites responsible for anisole, furfural, and m-cresol HDO can be selectively titrated using CO, and Brønsted acid sites responsible for the rate-determining isopropanol (IPA) dehydration during the sequential hydrogenation/dehydration of acetone could be selectively titrated using DTBP. These in situ titrations allow for site density and TOF measurements of the catalytically active sites without ex situ methods, yielding both the identity and quantity of active sites.

In this work, we use IPA dehydration activation energy, TOF, and site density measurements as probes of acid sites on freshly synthesized as well as oxygen-modified (O^*) transition metal carbide catalysts of molybdenum and tungsten (α - Mo_2C , β - Mo_2C , W_2C , and WC). Catalysts demonstrated extreme oxophilicity as noted by zero-order kinetics with respect to IPA pressure, indicative of a catalyst surface saturated with oxygenate. Intrinsic activation energies and dehydration turnover frequencies (TOF) were calculated using acid site densities measured via in situ DTBP titration. Selective DTBP titration both directly demonstrates the presence of Brønsted acid sites on O^* -modified carbides and allows for calculation of intrinsic dehydration TOF values. Acid site densities increased with O_2 co-feed-induced surface oxidation, but the nature of the active sites, as quantified via intrinsic activation energies and TOF, was similar across all measured catalysts regardless of bulk carbide structure, presence of O_2 co-feed, or bulk transition metal (Mo or W). The nature of the acid sites on TPR-synthesized transition metal carbides is uniform across formulations oxidized by both reactant alcohol O^* incorporation and direct O_2 co-feed at reaction conditions. The persistent and consistent nature of acid site identity with O^* source, site density, transition metal, and bulk crystal structure serves to further the understanding of catalytic applications of oxophilic transition metal carbides or other oxophilic catalytic materials from both a fundamental perspective as well as for any potential acid catalysis/HDO applications.

2. Experimental

2.1 Catalyst synthesis and passivation

All catalysts were prepared in a quartz tubular reactor (I.D. 10 mm). Catalyst precursors were heated either in a three-zone or in a one-zone split tube furnace (Applied Test Systems) under gas flows including CH₄ (Matheson, 99.97%), H₂ (Matheson, 99.999%), or He (Minneapolis Oxygen, 99.997%).

Synthesis of orthorhombic β -Mo₂C was carried out using a temperature-programmed reaction method reported previously.^{25,32,33} Batches of catalyst were synthesized using 0.03–1.0 g ammonium paramolybdate (sieved, 177–400 μ m, (NH₄)₆Mo₇O₂₄•4H₂O, Sigma, 99.98%, trace metal basis). The paramolybdate was heated at 0.06 K s⁻¹ to 623 K and held at 623 K for 12 h under total flow of 3.0 cm³ s⁻¹ of 15 vol% CH₄/H₂, followed by a temperature ramp at 0.046 K s⁻¹ from 623 K to 873 K and a temperature hold at 873 K for 2 h. The reactor was then cooled under the same gas flow to reaction temperature (415 K) to begin reaction.

Cubic α -Mo₂C (also labeled as α -MoC_{1-x})²⁴ was synthesized according to a modified method of Vitale and coworkers.³⁴ Sucrose (5 g) and ammonium paramolybdate (5 g) were dissolved in 40 mL deionized H₂O, and the mixture was homogenized and magnetically stirred at ambient temperature for 0.25 h. The mixture was then placed in an oven at 393 K for 24 h. A dark grey porous solid mass was formed; the resulting solid was crushed and used as a precursor. Approximately 2 g of this precursor was treated under flowing He, heated at 0.25 K s⁻¹ to 1073 K, held at 1073 K for 0.5 h, then cooled to ambient temperature under the same flow. This product was shown to have bulk α -Mo₂C crystal structure (see discussion in Section 3 below). Approximately 0.2 g of this precursor was then heated under flowing He to 415 K for IPA dehydration measurements

and was subsequently treated with 13 kPa O₂ co-feed under reaction conditions as dehydration rates rose until they reached a stable value.

WC and W₂C catalysts were synthesized according to a modified method of Delannoy and coworkers.³⁵ Both catalysts were synthesized with 0.03 – 0.1 g WO₃ precursor (Sigma Aldrich, 99.995% trace metal basis) using the quartz tube flow system described above under 1.82 cm³ s⁻¹ total flow of 20% CH₄/H₂ and heated at 0.0167 K s⁻¹ until their final synthesis temperature (1073 K for WC, 903 for W₂C), and finally held isothermally for 8 h. CH₄ gas flow was then removed, and the catalyst was allowed to cool to 415 K under H₂ flow.

Catalysts were passivated after reaction by treatment in flowing 1% O₂/He (Matheson, Certified Standard Purity) at 1.0 cm³ s⁻¹ for at least 0.75 h in an effort to avoid violent bulk oxidation with atmospheric O₂.^{36,37} Samples were passivated even if treated with O₂ co-feed during reaction.

2.2 Catalyst characterization

The mass fraction of molybdenum in the α -Mo₂C was analyzed by inductively coupled plasma optical emission spectroscopy (ICP-OES); experimental details are provided in Section S.1 of Supplementary Information.

X-ray diffraction (XRD) was performed with a Bruker D8 Discover 2D X-ray diffractometer equipped with a 2-D VÅNTEC-500 detector and a 0.8-mm collimator. Cu K _{α 1} and K _{α 2} radiation was used in conjunction with a graphite monochromator. Scans were performed in two or three frames for 300 s per frame. Total scan range was typically $2\theta = 20^\circ$ to 80° with the scan frames being adjusted so as to center the primary intensity peaks in each frame. The 2D scans were converted to 1D intensity vs. 2θ with a

step size of $0.04^\circ 2\theta$ and merged for analysis. A zero background holder was used with a small amount of vacuum grease for sample support.

Surface area and porosity of the passivated catalyst samples was measured using an ASAP Micromeritics 2020 analyzer. BET surface area and porosity measurements using N_2 were performed at liquid nitrogen boiling temperature. Prior to N_2 physisorption measurements, samples were degassed to $<6\ \mu\text{m Hg}$ and heated to 523 K at $0.17\ \text{K s}^{-1}$ and held for 2–4 h. BET Surface areas of oxygen-modified carbide samples were typically $<5\ \text{m}^2\ \text{g}^{-1}$, and surface areas of post-reaction samples without O_2 co-feed were typically $\sim 20 - 60\ \text{m}^2\ \text{g}^{-1}$; surface areas were not used for quantitative comparison due to their evolution with O_2 exposure³⁸ or aging time.²⁸

2.3 Reaction and titration methods

Reactions were carried out in an apparatus described previously.³² Briefly, reactants were fed to stainless steel reactor lines via either an M6 Valco syringe-free liquid handling pump or a KD Scientific syringe pump (KDS120). Reactant lines were heated by resistive heating tape to prevent condensation. 2-Propanol (ACS 99.97%), argon (Matheson, 99.999%), and helium (Minneapolis Oxygen, 99.997%) were used as received. Products and reactants at the reactor effluent were quantified using a flame ionization detector (FID) with an online gas chromatograph (Agilent 7890 GC); gas-phase separation prior to the FID was accomplished with a J&W HP-1 dimethylpolysiloxane column (50.0 m length, 320 μm I.D., 0.52 μm film). Helium was used as the column carrier gas at a flow rate of $0.15\ \text{cm}^3\ \text{s}^{-1}$. GC oven temperature profiles for reactor effluent separation typically began at 213 K for 0.058 h and were ramped to 423 K at $0.42\ \text{K s}^{-1}$.

IPA partial pressure was varied from $\sim 0.044 - 4.4$ kPa by altering liquid flow rates from ~ 10 to $800 \mu\text{L h}^{-1}$. For temperature variation experiments, reactor temperature was measured at the moment of sample injection into the GC with reactor temperature measured by a thermocouple in a thermal well on the external surface of the quartz reactor. Temperatures were raised and lowered ~ 15 K from the standard reaction temperature of 415 K; repeats of rates at multiple temperatures were performed over the course of the experiment to ensure consistency and lack of catalyst history effects.

Titration experiments were performed with liquid mixtures of IPA and 2,6-di-tert-butylpyridine (DTBP). After catalyst synthesis and possible O_2 co-feed introduction, IPA was introduced and steady state propylene production rates were obtained (typically ~ 1 h of stabilization time). IPA partial pressure variation experiments were performed first, followed by temperature variation experiments. Temperature and propylene production rates were subsequently stabilized at 415 K. The flow of reactants was then switched from pure IPA flow to the IPA/DTBP mixture at an identical volumetric flow rate. DTBP mole fraction in the IPA/DTBP mixture was $\sim 3 \times 10^{-4}$. The propylene formation rate was monitored using online gas chromatography and was linearly extrapolated to zero during titration to estimate the total DTBP uptake as a measure of acid site density.

3. Results and Discussion

Figure 1 (a) shows the rate of IPA dehydration to form propylene over in situ synthesized molybdenum and tungsten carbides without any exposure to oxygen. Rates are normalized by the total moles of metal atoms in the oxide precursor. Rates were measured in the absence of heat and mass transfer limitations (Section S.2 of

Supplementary Information). Dehydration rates typically varied <10% over the course of a ~8 h experiment to measure IPA pressure dependence, activation energy, and TOF. Fresh carbides that had not been exposed to O₂ co-feed exhibited increasing dehydration rates at early times on stream, hypothesized to be attributable to surface oxidation from deposited oxygen during an initial transient in IPA catalytic dehydration. Propylene formation rates over all carbides exhibit zero-order dependence upon IPA pressure over two orders of magnitude (~0.044 – 4.4 kPa). The zero-order dependence is in line with the expected oxophilicity of these carbides; the catalyst surface is saturated with IPA even at low reactant partial pressures. Propylene was the primary product formed. Acetone was formed in small quantities (<5% carbon selectivity) over fresh catalysts and formed negligibly once O₂ co-feed was introduced. Di-isopropylether (DIPE) was formed with typically <10% carbon selectivity. DIPE formation rates showed a positive order dependence upon IPA pressure. DIPE formation rates were not used for characterization and quantification of acid sites on the catalyst in this study due to the non-zero order kinetics and the low product formation rates. A linear dependence of carbon conversion on contact time evinced an absence of product inhibition.³²

Carbides synthesized under identical conditions were also tested for IPA dehydration with a co-feed of 13 kPa O₂, and the results are plotted in Figure 1(b). O₂ co-feed increased dehydration rates per bulk metal atom by an order of magnitude for all carbides tested in this work. The rate dependence upon IPA pressure remained invariant (zero-order), indicative of a reactant-saturated surface. These results for β -Mo₂C have been published previously,³² and the three additional carbides tested in this work behaved

similarly as characterized by zero-order kinetics and a concurrent increased dehydration rate with O₂-induced surface oxidation.

Temperature variation experiments were performed on carbides with both zero and 13 kPa O₂ co-feed, and the rates of propylene formation as a function of temperature are plotted in Figures 2(a) and 2(b). The activation energies that can be extracted from the slopes of Figures 2(a) and 2(b) are intrinsic because of the zero-order dehydration kinetics. The data presented in Figures 1(a) and 1(b) exhibit an order of magnitude increase in the measured propylene rates with oxygen co-feed, but the IPA dehydration kinetics (as quantified by the activation energy) remained invariant even with an order of magnitude increase in rate. The activation energies extracted from the slopes of Figures 2(a) and 2(b) and tabulated in Table 1 are shown to be similar.

Propylene turnover frequencies (TOF), normalized by the acid site density calculated from the extrapolated time to complete titration based off of DTBP co-feed titration experiments, are plotted in Figure 3 and also tabulated in Table 1. Acid site densities per bulk metal atom are also reported due to difficulties in accurately ascertaining oxidized sample surface area as mentioned in Section 2.2. A typical DTBP titration experiment is shown in Section S.3 of Supplementary Information. TOF values for all experiments performed in this work are plotted in Figure 3 along with TOF values calculated from intermediate O₂ co-feed pressures for W₂C and β -Mo₂C. A TOF for α -Mo₂C with no O₂ co-feed could not be calculated due to the inability of DTBP to titrate the extremely low dehydration rate. The nature of the as-synthesized α -Mo₂C surface was noticeably different from the other catalysts used in this study due to the synthesis procedure (described in the experimental section). The surface prior to O₂ co-feed was

expected to be covered in carbon residue due to the large carbon content of the sucrose in the synthesis precursor. ICP-OES of the α -Mo₂C sample showed ~37 wt% Mo as compared to the theoretical 94 wt% Mo of a pure α -Mo₂C sample. O₂ co-feed caused a ~130 h transient during which the propylene production rate rose and finally stabilized; IPA dehydration pressure dependence, activation energy, and TOF were measured at this stable dehydration rate (Section S.4 of Supplementary Information).

Propylene TOF values for all MoC_x samples varied within a factor of ~2 regardless of O₂ co-feed pressure; WC_x propylene TOF values also varied within a factor of ~2 for O₂ co-feed experiments. WC_x propylene TOF values were also typically higher than MoC_x by a factor of ~2. This implicates a similarity in the nature of the acid sites for IPA dehydration across fresh and oxygen modified carbides of molybdenum and tungsten.

Propylene rates were not entirely inhibited by DTBP co-feed; DTBP was able to irreversibly titrate 85 – 94% of the dehydration rates of O*-carbides, but DTBP could only titrate 40 – 50% of the dehydration rate of fresh carbides that had never been exposed to O₂. This could be explained by the presence of acid sites that DTBP cannot chemically bind to, such as (i) Lewis acid sites, and/or (ii) sites that are sterically inaccessible to DTBP either due to the presence of catalyst pores on the order of 1-2 nm for β -Mo₂C³² or due to closely localized acid sites (crystal edge sites). The propylene TOF was calculated by assuming that all sites are chemically identical Brønsted acid sites. The presence of Lewis acid sites or a non-uniform distribution of sites would cause a distribution in TOF values that is not captured in this single-value TOF estimation technique and would also account for the un-titrated rate; we are unable to distinguish

between the relative effects of possible Lewis acid sites or sterically inaccessible sites. However, the measured similarity in reaction order dependences, activation energies, and turnover frequencies across all catalyst samples implies the lack of a broad spectrum of active sites with varying reactivity.

The post-reaction X-ray diffraction patterns of all catalysts tested for IPA dehydration in Figures 1, 2, and 3 are presented in Figure 4. Figure 4 shows that the bulk structures of WC, W₂C, and α -Mo₂C were unaffected by O₂ co-feed at 415 K under reaction conditions. Transition metal carbide catalysts demonstrate Brønsted acidity due to surface oxidation, and the acid sites generated are similar regardless of the extent of oxidation or bulk transition metal composition as evinced by similar kinetics and propylene TOF values. Surface oxidation increases surface acid site density, but bulk carbide crystal structure remains unchanged with O₂-induced surface alterations.

The IPA dehydration kinetic parameters as reported in Table 1 are relatively independent of bulk carbide crystal structure, implying that (i) the structure and composition of the bulk carbide minimally alter the acidic properties of the catalyst surface, and (ii) oxygen modification with O₂ co-feed increased the number of acidic active sites without significantly altering the nature of the acid sites. XPS of carbide catalysts after 13 kPa of O₂ co-feed for over 12 h showed no transition metal in the carbide oxidation state (<10 atom% Mo³⁺) with the bulk of the surface atoms residing as oxides or suboxides (Mo⁵⁺ and Mo⁶⁺) as shown in Section S.5 of Supplementary Information. This increase in surface oxidation with concurrent increase in acidic active site density as measured by in situ titrations suggests that the Brønsted acid sites on the

carbide surfaces, both fresh and oxygen modified, are similar in nature to acid sites present on transition metal oxides.

While both fresh and oxygen-modified MoC_x and WC_x catalyze IPA dehydration at nearly identical rates, it is worth noting the effects of different oxophilicities of the MoC_x and WC_x catalysts shown by the effects of O_2 co-feed pressure in Figure 3. An increase from 0.3 kPa to 13.5 kPa O_2 co-feed over $\beta\text{-Mo}_2\text{C}$ did not affect the dehydration TOF (0.16 vs. 0.13 s^{-1}), but the acid site density was nearly doubled as noted by the dehydration rate per Mo atom (45 vs. 84 $\text{mol s}^{-1} \text{mol}_{\text{Mo}}^{-1}$). Conversely, O_2 co-feed of 0.4 kPa and 13 kPa over W_2C induced nearly identical TOF values (0.3 vs. 0.31 s^{-1}) as well as acid site densities (rates of 241 vs. 241 $\text{mol s}^{-1} \text{mol}_{\text{W}}^{-1}$). Dehydration rates over $\beta\text{-Mo}_2\text{C}$ increased gradually over the range of O_2 co-feed pressures from 0 – 13 kPa with O_2 pressures above ~10 kPa not affecting the dehydration rate. Conversely, O_2 co-feed of 0.4 kPa over W_2C induced a maximum dehydration rate, and higher O_2 co-feed pressures caused no additional increase in the dehydration rates as noted in Figure 3 and in Section S.6 of Supplementary Information. DeMaria et al.³⁹ used a Knudsen cell in conjunction with mass spectroscopic methods to correlate partial pressures of vaporized metal oxides to enthalpies of metal-oxygen bond formation; the greater comparative oxophilicity of tungsten with respect to molybdenum is evident from the enthalpies of formation of Mo-O and W-O bonds (485 ± 63 and 644 ± 42 kJ mol^{-1} , respectively). Oxygen co-feed over both MoC_x and WC_x catalysts generates Brønsted acid sites due to the oxophilicity of these formulations, and the acid sites generated on the catalyst surface saturate with increasing O_2 pressure, but the greater oxophilicity of WC_x in comparison to MoC_x catalysts causes the maximum acid site density to saturate at lower O_2 co-feed pressure.

4. Conclusions

Carbides of molybdenum and tungsten exhibit Brønsted acidity following carbide synthesis without exposure to O₂ as evinced by irreversible DTBP titration. Dioxygen co-feed increases the rate of acidic dehydration of IPA to propylene at 415 K by an order of magnitude over interstitial carbides of molybdenum and tungsten; O₂-induced surface oxidation does not alter the bulk carbide structures as evidenced by the unchanged post-reaction X-ray diffraction patterns. The oxophilic characteristics of fresh and O₂-modified (O*) carbides result in IPA surface saturation with partial pressures as low as 0.044 kPa and in zero-order dehydration kinetics to propylene. Intrinsic activation energies of unimolecular dehydration over fresh and O*-modified carbides were similar (89 – 104 kJ mol⁻¹) across carbide bulk structure, with or without O₂ co-feed. Propylene TOF values for fresh and O*-carbides, normalized by the calculated Brønsted acid site density obtained from extrapolation of DTBP rates of titration, were similar within a factor of ~2 for both molybdenum and tungsten carbides. The oxophilicity of the transition metal carbide formulations results in the concurrent genesis of Brønsted acidity with catalyst surface oxidation without the alteration of bulk crystal structure.

Acknowledgements

This research was supported by Office of Basic Energy Sciences, the U.S. Department of Energy under award number no. DE- SC0008418 (DOE Early Career Program). Part of this work was carried out in the College of Science and Engineering Characterization Facility, University of Minnesota, which has received capital equipment funding from the

NSF through the MRSEC program. We thank Javier Garcia Barriocanal for assistance with the X-ray diffraction studies, Rick Knurr for assistance with the ICP-OES characterization, and Bing Luo for assistance with the XPS characterization.

References

- 1 J. S. Lee, S. Locatelli, S. T. Oyama and M. Boudart, *J. Catal.*, 1990, **125**, 157–170.
- 2 G. S. Ranhotra, A. T. Bell and J. A. Reimer, *J. Catal.*, 1987, **108**, 40–49.
- 3 J. H. Sinfelt and D. J. C. Yates, *Nat. Phys. Sci.*, 1971, **229**, 27–28.
- 4 J.-S. S. Choi, G. Bugli and G. Djéga-Mariadassou, *J. Catal.*, 2000, **193**, 238–247.
- 5 H. Shou and R. J. Davis, *J. Catal.*, 2013, **306**, 91–99.
- 6 M.-L. Frauwallner, F. López-Linares, J. Lara-Romero, C. E. Scott, V. Ali, E. Hernández and P. Pereira-Almao, *Appl. Catal. A Gen.*, 2011, **394**, 62–70.
- 7 K. J. Leary, J. N. Michaels and M. Stacy, *J. Catal.*, 1986, **101**, 301–313.
- 8 E. Iglesia, J. E. Baumgartner, F. H. Ribeiro and M. Boudart, *J. Catal.*, 1991, **131**, 523–544.
- 9 A. F. Lamic, C. H. Shin, G. Djéga-Mariadassou and C. Potvin, *Appl. Catal. A Gen.*, 2006, **302**, 5–13.
- 10 E. A. Blekkan, C. Pham-Huu, M. J. Ledoux and J. Guille, *Ind. Eng. Chem. Res.*, 1994, **33**, 1657–1664.
- 11 R. B. Levy and M. Boudart, *Science (80-.)*, 1973, **181**, 547–549.
- 12 V. Keller, P. Wehrer, F. Garin, R. Ducros and G. Maire, *J. Catal.*, 1997, **166**, 125–135.
- 13 H. Ren, W. Yu, M. Saliccioli, Y. Chen, Y. Huang, K. Xiong, D. G. Vlachos and J. G. Chen, *ChemSusChem*, 2013, **6**, 798–801.
- 14 H. Ren, Y. Chen, Y. Huang, W. Deng, D. G. Vlachos and J. G. Chen, *Green Chem.*, 2014, **16**, 761–769.
- 15 K. Xiong, W. Yu, D. G. Vlachos and J. G. Chen, *ChemCatChem*, 2015, **7**, 1402–1421.
- 16 A. L. Jongerius, R. W. Gosselink, J. Dijkstra, J. H. Bitter, P. C. A. Bruijninx and B. M. Weckhuysen, *ChemCatChem*, 2013, **5**, 2964–2972.
- 17 S. Boullosa-Eiras, R. Lødeng, H. Bergem, M. Stöcker, L. Hannevold and E. A. Blekkan, *Catal. Today*, 2014, **223**, 44–53.
- 18 F. H. Ribeiro, R. a. Dalla Betta, M. Boudart, J. E. Baumgartner and E. Iglesia, *J. Catal.*, 1991, **130**, 86–105.
- 19 F. H. Ribeiro, M. Boudart, R. A. D. Betta, R. A. Dalla Betta and E. Iglesia, *J. Catal.*, 1991, **513**, 498–513.
- 20 A. F. Lamic, T. L. H. Pham, C. Potvin, J. M. Manoli and G. Djéga-Mariadassou, *J. Mol. Catal. A Chem.*, 2005, **237**, 109–114.
- 21 J. Macht, C. D. Baertsch, M. May-Lozano, S. L. Soled, Y. Wang and E. Iglesia, *J. Catal.*, 2004, **227**, 479–491.
- 22 C. Baertsch, K. T. Komala, Y. Chua and E. Iglesia, *J. Catal.*, 2002, **205**, 44–57.
- 23 J. A. Schaidle, J. Blackburn, C. A. Farberow, C. Nash, K. X. Steirer, J. Clark, D. J. Robichaud and D. A. Ruddy, *ACS Catal.*, 2016, **6**, 1181–1197.
- 24 F. G. Baddour, C. P. Nash, J. A. Schaidle and D. A. Ruddy, *Angew. Chemie Int. Ed.*, 2016, **55**, 1–5.
- 25 W. Lee, Z. Wang, R. Wu and A. Bhan, *J. Catal.*, 2014, **319**, 44–53.
- 26 C.-J. Chen, W.-S. Lee and A. Bhan, *Appl. Catal. A Gen.*, 2015, **510**, 42–48.
- 27 M. M. Sullivan and A. Bhan, *ACS Catal.*, 2016, **6**, 1145–1152.
- 28 W.-S. Lee, Z. Wang, W. Zheng, D. G. Vlachos and A. Bhan, *Catal. Sci. Technol.*,

- 2014, **4**, 2340–2352.
- 29 K. Xiong, W.-S. Lee, A. Bhan and J. G. Chen, *ChemSusChem*, 2014, **7**, 2146–2149.
- 30 W.-S. Lee, A. Kumar, Z. Wang and A. Bhan, *ACS Catal.*, 2015, **2**, 4104–4114.
- 31 M. M. Sullivan, C.-J. C.-J. Chen and A. Bhan, *Catal. Sci. Technol.*, 2016, **6**, 602–616.
- 32 M. M. Sullivan, J. T. J. T. Held and A. Bhan, *J. Catal.*, 2015, **326**, 82–91.
- 33 J. A. Schaidle, N. M. Schweitzer, O. T. Ajenifujah and L. T. Thompson, *J. Catal.*, 2012, **289**, 210–217.
- 34 G. Vitale, M. L. Frauwallner, C. E. Scott and P. Pereira-Almao, *Appl. Catal. A Gen.*, 2011, **408**, 178–186.
- 35 L. Delannoy, J.-M. Giraudon, P. Granger, L. Leclercq and G. Leclercq, *Catal. Today*, 2000, **59**, 231–240.
- 36 J. S. Lee, S. T. Oyama and M. Boudart, *J. Catal.*, 1987, **106**, 125–133.
- 37 S. K. Bej and L. T. Thompson, *Appl. Catal. A Gen.*, 2004, **264**, 141–150.
- 38 M. M. Sullivan and A. Bhan, *ACS Catal.*, 2016, **6**, 1145–1152.
- 39 G. De Maria, R. P. Burns, J. Drowart and M. G. Inghram, *J. Chem. Phys.*, 1960, **32**, 1373.

Figure 1. Propylene synthesis rates over interstitial carbide catalysts of tungsten and molybdenum, normalized per mole of W or Mo, as a function of IPA partial pressure (a) with no O_2 co-feed, or (b) with 13 kPa O_2 co-feed. $T = 415 \text{ K}$, $P = 114 \text{ kPa}$, $P_{\text{CH}_4} = 4 \text{ kPa}$ (internal standard), balance He or Ar. Total gas flow rate of $1.83 \text{ cm}^3 \text{ s}^{-1}$. Approximately 0.1 g of oxide precursor was loaded for each synthesis and subsequent reaction tests (0.2 g for $\alpha\text{-Mo}_2\text{C}$). Conversion varied from 0.1 – 19% for (a) and 0.3 – 66% for (b).

Figure 2. Propylene synthesis rates over interstitial carbide catalysts of tungsten and molybdenum, normalized per mole of W or Mo, as a function of temperature (a) with no O_2 co-feed, or (b) with 13 kPa O_2 co-feed. $P = 114$ kPa, $P_{\text{CH}_4} = 4$ kPa (internal standard), $P_{\text{IPA}} = 0.54$ or 1.1 kPa, balance He or Ar. Total gas flow rate of $1.83 \text{ cm}^3 \text{ s}^{-1}$. Approximately 0.1 g of oxide precursor was loaded for each synthesis and subsequent reaction tests (0.2 g for $\alpha\text{-Mo}_2\text{C}$). Conversion varied from 0.1 – 20% for (a) and 0.9 – 78% for (b).

Figure 3. Propylene turnover frequency (TOF) as a function of propylene synthesis rate normalized by catalyst loading for carbides of W and Mo. TOF values are listed in Table 1 and were measured on the catalyst formulations used for IPA pressure and temperature variation experiments shown in Figures 1 and 2. TOF values with O₂ co-feed pressures in between 0 and 13 kPa are also plotted for β-Mo₂C and W₂C. TOF was normalized using Brønsted acid site density measured by extrapolation of in situ DTBP titration experiments. T = 415 K, ~0.1 g_{cat} of oxide precursor, P = 114 kPa, P_{IPA} = 0.54 or 1.1 kPa, P_{CH₄} = 4 kPa (internal standard), balance He, total gas flow rate of 1.83 cm³ s⁻¹.

Figure 4. X-ray diffraction patterns of WC, W_2C , and $\alpha\text{-Mo}_2C$ catalysts after reaction with or without 13 kPa O_2 co-feed. Peak indices were obtained from the JCPDS database for WC (JCPDS PDF # 01-089-2727), W_2C (JCPDS PDF # 00-035-0776), and for $\alpha\text{-Mo}_2C$ (JCPDS PDF # 03-065-0280).

Table 1. Kinetic parameters of IPA dehydration over carbides of Mo and W with and without O₂ co-feed. Tabulated numbers were obtained from data plotted in Figures 1, 2, and 3.

	<i>No O₂ co-feed</i>				<i>13 kPa O₂ co-feed</i>			
	E_a^1	α^2	TOF ³	L^4 (/1x10 ⁻⁵)	E_a^1	α^2	TOF ³	L^4 (/1x10 ⁻⁵)
W₂C	104 ± 6	-0.05	0.14	17	100 ± 7	0.01	0.31	78
WC	89 ± 9	0.06	0.14	6	98 ± 4	0.11	0.30	82
α-Mo₂C	99 ± 8	0.08	-	-	99 ± 5	0.02	0.19	4
β-Mo₂C	92 ± 4	-0.02	0.07	6	94 ± 3	0.05	0.13	66

¹ Activation energy in units of kJ mol⁻¹

² IPA partial pressure dependence on propylene formation rate ($r = kP_{IPA}^\alpha$)

³ Propylene turnover frequency with units of (propylene s⁻¹ DTBP site⁻¹)

⁴ Brønsted acid site density, as calculated by DTBP uptake extrapolated to titrate dehydration rates completely, normalized per bulk metal atom (Mo or W)