Rapid Electrostatics-Assisted Layer-by-Layer Assembly of Near-Infrared-Active Colloidal Photonic Crystals

Khalid Askar, Sin-Yen Leo, Can Xu, Danielle Liu and Peng Jiang*

Department of Chemical Engineering, University of Florida, Gainesville, FL 32611

Abstract

Here we report a rapid and scalable bottom-up technique for layer-by-layer (LBL) assembling near-infrared-active colloidal photonic crystals consisting of large ($\geq 1 \mu\text{m}$) silica microspheres. By combining a new electrostatics-assisted colloidal transferring approach with spontaneous colloidal crystallization at an air/water interface, we have demonstrated that the crystal transfer speed of traditional Langmuir-Blodgett-based colloidal assembly technologies can be enhanced by nearly 2 orders of magnitude. Importantly, the crystalline quality of the resultant photonic crystals is not compromised by this rapid colloidal assembly approach. They exhibit thickness-dependent near-infrared stop bands and well-defined Fabry-Perot fringes in the specular transmission and reflection spectra, which match well with the theoretical calculations using a scalar-wave approximation model and Fabry-Perot analysis. This simple yet scalable bottom-up technology can significantly improve the throughput in assembling large-area, multilayer colloidal crystals, which are of great technological importance in a variety of optical and non-optical applications ranging from all-optical integrated circuits to tissue engineering.

* Corresponding author. E-mail: pjiang@che.ufl.edu.

1. Introduction

Photonic crystals are periodic dielectric materials that can control the flow of light in miniature volumes, promising for a wide spectrum of optical applications, such as all-optical integrated circuits, lossless waveguides, and low-threshold lasers [1-3]. They also provide opportunities in exploring new physical phenomena like negative refractive index and suppression or enhancement of spontaneous emission [4, 5]. Compared with complex and expensive top-down nanofabrication technologies (e.g., electron-beam lithography and focused ion-beam milling), bottom-up colloidal self-assembly renders a much simpler, faster, and cheaper approach for fabricating three-dimensionally (3-D) ordered photonic crystals operating at visible and near-infrared (NIR) wavelengths [6-11]. To enable full photonic band gaps, the replication of the self-assembled colloidal crystals in high refractive index materials (e.g., silicon) to create the so-called macroporous (or inverted) photonic crystals has been extensively exploited [12, 13]. Because silica microspheres can survive the typical harsh templating conditions, such as high temperature in the chemical vapor deposition of silicon, a large variety of methodologies like convective self-assembly [14, 15], gravitational sedimentation [16], spin-coating [17], electric or magnetic field-assisted assembly [9, 18], and physical confinement [19, 20] have been developed for assembling submicrometer-sized silica microspheres into 3-D colloidal crystals as sacrificial templates. However, spontaneous crystallization of large silica microspheres with diameter larger than 1 μm , which are needed for fabricating inverted photonic crystals operating at NIR telecommunication wavelengths, tends to be challenging, mainly due to the rapid gravitational sedimentation of large silica particles [12, 21, 22]. The same issue also hinders many other non-optical applications of self-

1
2
3
4 assembled colloidal crystals consisting of μm -sized particles, such as in fabricating
5
6 ordered macroporous membranes with large pores as 3-D scaffolds for tissue engineering
7
8 and drug delivery [23].
9

10
11 Layer-by-layer transfer of monolayer colloidal crystals formed at an air/water
12 interface, where the self-assembly process is induced by the high surface tension of water
13
14 (72.75 mN/m at 20 °C), has been widely exploited as an effective methodology in
15
16 fabricating multilayer colloidal photonic crystals with easily adjustable thicknesses [24-
17
18 38]. Moreover, this Langmuir-Blodgett-based LBL technology enables the precise
19
20 insertion of engineered artificial defects (e.g., planar defects) into 3-D photonic crystals,
21
22 crucial for achieving active photonic crystal devices [39, 40]. However, traditional LBL
23
24 colloidal assembly approaches suffer from a few major drawbacks. They usually require
25
26 sophisticated equipment (e.g., a Langmuir-Blodgett trough), and the process parameters
27
28 (e.g., surface pressure and barrier speed) need to be precisely controlled to compress the
29
30 floating microspheres into close-packed monolayers [30, 41]. More importantly, a thin
31
32 lubricating water layer between the transferred colloidal monolayer and the substrate
33
34 greatly limits the substrate withdrawal speed. A typical upstroke speed of ~ 1 mm/min is
35
36 widely used in previous studies to ensure conformal transfer of monolayer colloidal
37
38 crystals onto various substrates [30, 41, 42]. A higher substrate withdrawal speed usually
39
40 results in poor-quality colloidal crystals, or in the worst case scenario, no particle transfer
41
42 onto the substrate. This slow crystal transfer speed significantly impedes the fabrication
43
44 throughput of large-area colloidal photonic crystals, especially for assembling multilayer
45
46 photonic crystals with many colloidal layers. For instance, it takes ~ 100 min to transfer a
47
48 monolayer colloidal crystal to cover a 4-in.-sized substrate.
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

We have recently demonstrated a simple and scalable Langmuir-Blodgett-like bottom-up technology for assembling wafer-sized monolayer colloidal crystals onto both planar and non-planar substrates (e.g., multicrystalline silicon wafers) [43]. This approach does not require any sophisticated equipment and the process is easily controllable and highly reproducible. Unfortunately, similar to other Langmuir-Blodgett-based colloidal self-assembly techniques, the crystal transfer speed is very slow and it is limited to ~ 0.5 mm/min to deposit high-quality monolayer crystals. Here, we demonstrate that this speed can be greatly boosted to ~ 60 mm/min by simply using surface-modified substrates which possess opposite charges to the negatively charged silica microspheres. Multilayer colloidal photonic crystals consisting of large silica microspheres (diameter ≥ 1 μm) are then assembled in a LBL manner by this rapid approach. Critically, our optical characterization and modeling indicate that the crystalline quality of the resultant near-infrared-active photonic crystals is not compromised by the fast assembly process.

2. Experimental

2.1 Materials and Substrates

Uniform silica microspheres with diameters of 1.0, 2.5, 3.5, and 8.0 μm made by a modified Stöber method are obtained from Particle Solutions LLC (Alachua, FL). These silica particles are cleaned by 6 cycles of repeated centrifugation followed by redispersion in 200-proof ethanol. The purified silica microspheres are used in preparing a colloidal suspension with 2 wt% of silica particles dispersed in ethylene glycol. A 75 $\times$ 25 mm glass microslide cleaned using a piranha solution ($\text{H}_2\text{SO}_4\text{:H}_2\text{O}_2=4\text{:}1$ by volume) at 70°C for 60 min is rinsed with deionized water several times and then air-dried. The cleaned glass substrate is primed by 3-aminopropyltriethoxysilane (APS) using the well-

established silane-coupling reactions [17, 44], followed by rinsing with toluene and air drying. The amino groups of the surface-grafted APS molecules change the surface charges of the glass microslide from negative to positive. Deionized (DI) water (18.2 M Ω cm) is used directly from a Millipore A-10 water purification system.

2.2 Instrumentation

A KD Scientific 780-230 syringe pump is used to precisely control the withdrawal speed of the substrate in the Langmuir-Blodgett colloidal assembly process. Scanning electron microscopy (SEM) is carried out on a JEOL 6335F FEG-SEM. A thin layer of gold is sputtered onto the samples prior to imaging. Zeta potentials of silica microspheres are measured by a Brookhaven ZetaPlus unit. Fourier Transformed Infrared Spectroscopy (FTIR) is performed at normal incidence using a Thermo Electron Magna 760 spectrometer with a liquid-nitrogen-cooled mercury cadmium telluride detector.

2.3 Electrostatics-Assisted LBL Assembly of NIR-Active Colloidal Photonic Crystals

The functionalized glass substrate is then immersed in a glass Petri dish filled with deionized water. The colloidal silica-ethylene glycol suspension is added dropwise along the edge of the Petri dish. The suspension is spread immediately to form an iridescent colloidal crystal monolayer floating on the water surface [43]. Once the surface is completely covered with the floating silica microspheres, the functionalized glass microslide is vertically withdrawn at a rate of 60 mm/min controlled by the syringe pump, leading to the conformal transfer of the floating monolayer colloidal crystal onto both surfaces of the glass substrate. The strong electrostatic attraction between the positive APS-functionalized glass surfaces and the negatively charged silica microspheres (with a typical zeta potential of ~ -40 mV) is critical in achieving this high

coating speed. Our control experiments show that no particles are getting transferred onto negatively charged glass or silicon substrates with this high substrate withdrawal speed. Additionally, the electrostatic attraction makes the assembled particles adhere strongly to the glass substrate, facilitating to enhance the mechanical stability of the self-assembled colloidal monolayers [45]. The coated glass slide is then placed into the same APS/toluene solution to functionalize the surfaces of the deposited silica microspheres, reverting the negative surface charges to positive. The surface-modified coating is then immersed into the same glass Petri dish and another colloidal layer is deposited. The same process can be repeated in a LBL manner to create 3-D ordered multilayer photonic crystals with well-defined numbers of colloidal layers. The layer numbers of the resultant crystals can be easily tuned by controlling the numbers of the surface functionalization/Langmuir-Blodgett assembly cycles.

3. Results and Discussion

This novel electrostatics-assisted LBL self-assembly technology can greatly enhance the coating speed of the floating colloidal crystals, which is particularly important for improving the throughput in assembling large-area, multilayer photonic crystals. More importantly, the crystalline quality of the LBL-assembled photonic crystals is not compromised by the rapid colloidal transfer process. Fig. 1(a) shows a photograph of silica colloidal photonic crystals consisting of 1.0 μm microspheres with 1, 2, 3, 4, and 5 colloidal layers. All samples exhibit high coating uniformity over large areas. Moreover, the samples display angle-dependent iridescent colors caused by Bragg diffraction of visible light from the ordered colloidal arrays. Our extensive experiments further reveal that this simple LBL technology can be readily applied to assemble much

larger silica microspheres. This is in sharp contrast to many existing colloidal self-assembly approaches which suffer from rapid gravitational sedimentation of large silica particles [12, 21, 22]. We have successfully assembled multilayer colloidal crystals using 2.5, 3.5, and 8.0 μm silica microspheres and their coating qualities are as good as the 1.0 μm ones (see Fig. 1(b) and Fig. 1(c)). We have also demonstrated that this electrostatics-assisted LBL technology can be easily scaled-up to make high-quality multilayer photonic crystals over wafer-sized areas. Fig. S1 in the supplementary material shows photographs of LBL-assembled photonic crystals consisting of 1 μm silica microspheres with 1, 2, 3, and 5 colloidal layers on 4-in.-sized silicon wafers. It only takes ~ 2 min to transfer a highly uniform colloidal monolayer to cover a 5-in.-sized glass or silicon substrate.

Fig. 1. Photographs of LBL-assembled colloidal photonic crystals. (a) 1.0 μm silica particles with different numbers of colloidal layers. (b) 2.5 μm silica particles with different numbers of colloidal layers. (c) 1.0, 2.5, 3.5, and 8.0 μm silica particles with 5 colloidal layers.

The high crystalline quality of the LBL-assembled photonic crystals is further confirmed by using scanning electron microscope (SEM). Fig. 2(a) shows a top-view SEM image of a transferred monolayer colloidal crystal consisting of 1.0 μm silica

1
2
3
4 microspheres. The long-range hexagonal ordering of the crystal is evident from the image
5
6 and the hexagonally arranged sharp peaks in the Fourier transform of a $100\text{ }\mu\text{m}^2$ region
7
8 (inset of Fig. 2(a)). Our extensive SEM imaging also reveals that the crystalline quality of
9
10 the colloidal monolayers assembled using the rapid electrostatics-assisted LBL
11
12 methodology is apparently higher than that of the colloidal crystals assembled using
13
14 traditional Langmuir-Blodgett technology on bare glass or silicon substrates with native
15
16 negative surface charges [43]. We speculate that the strong electrostatic attraction
17
18 between the oppositely charged silica microspheres and the APS-modified substrates
19
20 leads to the rapid immobilization of the transferred particles [45, 46], which maintain the
21
22 high crystalline quality of the monolayer colloidal crystal assembled at the air/water
23
24 interface. By contrast, as shown in our previous work, the monolayer colloidal rafts
25
26 transferred onto negatively charged substrates are still floating on a thin layer of water
27
28 [43]. Capillary forces between neighboring microspheres induced by the evaporation of
29
30 the residual water are thus dominating the final colloidal crystallization process. It is
31
32 well-known that many types of defects, such as macroscopic cracks, can be introduced
33
34 into the resultant crystals, mainly caused by the high internal stress induced by the
35
36 evaporation of water [15, 47].
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Fig. 2. SEM images of LBL-assembled colloidal photonic crystals consisting of 1.0 μm silica particles with different numbers of colloidal layers. (a) 1 layer. (b) 2 layers. (c) 3 layers. (d) 4 layers. (e) 5 layers. (f) 10 layers. The inset in (a) shows a Fourier transform of a $10\ \mu\text{m} \times 10\ \mu\text{m}$ region.

Besides in-plane long-range order, the stacking of hexagonally close-packed colloidal layers perpendicular to the substrate is responsive for the diffraction observed in normal-incidence specular transmission and reflection measurements. Fig. 2(b) shows a top-view SEM image of an abraded region of a double-layer colloidal photonic crystal assembled by the electrostatics-assisted LBL technique. Although some intrinsic defects

1
2
3
4 like point defects and grain boundaries are present, the top colloidal layer retains the
5
6 hexagonal close-packed structure over the entire sample surface. Fig. 2(c)-(f) show cross-
7
8 sectional SEM images of LBL-assembled multilayer photonic crystals with 3, 4, 5, and
9
10
11 10 colloidal layers, respectively. These images reveal that the close-packed structure
12
13 extends uniformly over all layers from top to bottom for all multilayer samples. In this
14
15 close-packed geometry, whether the structure is face-centered cubic (ABCABC...),
16
17 hexagonal close-packed (ABABAB...), or randomly stacked, these images illustrate that
18
19 the LBL-assembled samples are oriented with their (111) crystalline planes parallel to the
20
21 substrate. Importantly, our extensive SEM characterization shows that macroscopic
22
23 cracks, which are commonly observed in colloidal crystals assembled by evaporation-
24
25 induced processes (e.g., convective self-assembly) [15], can be completely excluded in
26
27 all samples assembled by the new electrostatics-assisted LBL technique.
28
29
30
31
32

33 The specular transmission and reflection properties of the LBL-assisted colloidal
34
35 photonic crystals are evaluated using the Thermo Electron Magna 760 Fourier Transform
36
37 Infrared Spectroscopy. Fig. 3(a) and 3(b) show the normal-incidence reflection and
38
39 transmission spectra obtained from self-assembled colloidal photonic crystals consisting
40
41 of 1.0 μm silica microspheres with 1, 2, 3, 4, 5, and 10 colloidal layers and a bare glass
42
43 control sample. Distinct optical stop bands near 2300 nm, which are caused by the Bragg
44
45 diffraction of NIR light from the 3-D ordered colloidal multilayers, are clearly shown in
46
47 both transmission and reflection spectra. Additionally, the positions of the reflection
48
49 peaks and the transmission dips match well with each other. Another notable feature of
50
51 the spectra is the dependence of the bandwidth of the optical stop band with the number
52
53 of colloidal layers of the LBL-assembled photonic crystals. The full-width-at-half-
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 maximum (FWHM) of the reflection spectra in Fig. 3(a) is determined to be 938, 660,
5
6 538, 451, 410, and 277 nm for the crystals with 1, 2, 3, 4, 5, and 10 colloidal layers,
7
8 respectively. The apparent narrowing of optical stop bands with increasing crystal
9
10 thickness agrees with previous studies on self-assembled colloidal photonic crystals [48].
11
12 Moreover, we also use the optical characterization to evaluate the uniformity of the LBL-
13
14 assembled colloidal photonic crystals by obtaining transmission and reflection spectra
15
16 from multiple spots on the same sample. The spectra overlap well with each other,
17
18 confirming the outstanding uniformity of the resultant photonic crystals over large areas.
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Fig. 3. Normal incidence (a) reflection and (b) transmission spectra obtained from LBL-assembled colloidal photonic crystals consisting of 1.0 μm silica particles with different numbers of colloidal layers. These spectra have been vertically offset for clarity.

To gain better understanding of the optical properties of the LBL-assembled NIR-active colloidal photonic crystals, optical simulations based on a scalar-wave approximation (SWA) model are performed to complement the experimental optical measurements. In the SWA theory, Maxwell's equations are solved for a periodic

1
2
3
4 dielectric assuming that one may neglect diffraction from all but one set of crystalline
5
6 planes (for example, the (111) planes in our current case) [48]. The SWA calculations
7
8 contain no adjustable parameters as the size of the silica microspheres and the number of
9
10 colloidal layers can be well controlled, and the refractive indices of the silica particles
11
12 and air are known. Fig. 4(a) compares the experimental and SWA-simulated reflection
13
14 spectra for 1.0 μm -diameter colloidal photonic crystals with 4, 5, and 10 colloidal layers.
15
16 The experimental and theoretical spectra match extremely well in nearly all spectral
17
18 aspects, such as peak position, amplitude, and bandwidth. The strong dependence of the
19
20 bandwidth of the optical stop band on the crystal thickness (i.e., number of colloidal
21
22 layers) is also evident from the simulations. As a perfect face-centered cubic crystal
23
24 lattice is used in the SWA modeling, the excellent match between the experimental and
25
26 theoretical spectra further confirms the high crystalline quality of the LBL-assembled
27
28 colloidal photonic crystals.
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Fig. 4. (a) Comparison between the experimental (solid) and SWA-simulated (dotted) reflection spectra for colloidal photonic crystals consisting of 1.0 μm silica particles with 4, 5, and 10 colloidal layers. The arrows indicate local Fabry-Perot maxima, λ_p , chosen for thickness analysis. (b) Fringe order, p , versus Fabry-Perot maxima position, for LBL-assembled colloidal photonic crystal with 5 and 10 colloidal layers.

In addition to distinct optical stop bands originated from the Bragg diffraction of NIR light from 3-D ordered colloidal multilayers, well-defined Fabry-Perot fringes are clearly shown in the optical spectra (see Fig. 3). These fringes result from interference

between reflections from the top and bottom surfaces of the photonic crystals and are indicated by the arrows in Fig. 4(a). The spectral positions of these local maxima can be predicted using Bragg's law. At normal incidence, one particular FP maximum (e.g., the one at the longest wavelength) occurs at a wavelength, λ_1 , given by:

$$p_1 \lambda_1 = 2n_{\text{eff}} T \quad (1)$$

Here, p_1 is an integer, n_{eff} is the effective refractive index of the colloidal photonic crystal and T is the crystal thickness. Subsequent maxima appear at shorter wavelengths:

$$(p+p_1)\lambda_p = 2n_{\text{eff}} T \quad (2)$$

p is a positive integer numbering consecutive maxima from the long-wavelength fringe, p_1 . Rearranging equations (1) and (2) gives the fringe order, p :

$$p = \frac{2n_{\text{eff}}(\lambda_1 - \lambda_p)}{\lambda_1 \lambda_p} T \quad (3)$$

Thus, a plot of p versus $2n_{\text{eff}}(\lambda_1 - \lambda_p)/\lambda_1 \lambda_p$ gives a straight line with a slope of T . This linear relationship is clearly shown by the FP analysis for the 5-layer and 10-layer samples in Fig. 4(b). The good agreement between the experimental FP maxima and the theoretical predictions (straight lines) is a further testimony of the superior crystalline quality of the NIR-active photonic crystals assembled by the rapid LBL technique.

4. Conclusions

In conclusion, we have developed a new electrostatics-assisted LBL assembly technology for rapidly and scalably fabricating high-quality, NIR-active colloidal photonic crystals consisting of large silica microspheres, which are otherwise difficult to be assembled by traditional bottom-up techniques. The Langmuir-Blodgett-based crystal transfer speed can be enhanced by nearly two orders of magnitude by this electrostatics-

1
2
3
4 assisted approach, while the crystalline quality of the resultant crystals is not
5
6
7 compromised by the rapid assembly process. Our preliminary experiments have shown
8
9
10 that this scalable technology can be applied to assemble silica nanoparticles as small as
11
12
13 100 nm diameter. In addition to precisely controlling the structural parameters of
14
15
16 colloidal photonic crystals (e.g., thickness and engineered defects), this scalable
17
18
19 methodology could find many important optical and non-optical applications ranging
20
21
22 from antireflection coatings to tissue engineering [23, 49, 50].

23 **Acknowledgments**

24
25
26 This work was partially supported by the US Defense Threat Reduction Agency,
27
28
29 Basic Research Award # HDTRA1-15-1-0022, to University of Florida and an Early
30
31
32 Stage Innovations grant (Award No. NNX14AB07G) from NASA's Space Technology
33
34
35 Research Grants Program. Acknowledgments were also made to the US National Science
36
37
38 Foundation (NSF) under Award No. CMMI-1300613.
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

References

- [1] J.D. Joannopoulos, P.R. Villeneuve, S.H. Fan, Photonic crystals: Putting a new twist on light, *Nature* 386 (1997) 143-149.
- [2] J.F. Galisteo-Lopez, M. Ibisate, R. Sapienza, L.S. Froufe-Perez, A. Blanco, C. Lopez, Self-assembled photonic structures, *Adv. Mater.* 23 (2011) 30-69.
- [3] Y. Yin, J. Ge, Themed issue: the chemistry of photonic crystals and metamaterials, *J. Mater. Chem. C* 1 (2013) 6001-6002.
- [4] N. Kaina, F. Lemoult, M. Fink, G. Lerosey, Negative refractive index and acoustic superlens from multiple scattering in single negative metamaterials, *Nature* 525 (2015) 77-81.
- [5] M. Fujita, S. Takahashi, Y. Tanaka, T. Asano, S. Noda, Simultaneous inhibition and redistribution of spontaneous light emission in photonic crystals, *Science* 308 (2005) 1296-1298.
- [6] E. Armstrong, C. O'Dwyer, Artificial opal photonic crystals and inverse opal structures - fundamentals and applications from optics to energy storage, *J. Mater. Chem. C* 3 (2015) 6109-6143.
- [7] G. von Freymann, V. Kitaev, B.V. Lotsch, G.A. Ozin, Bottom-up assembly of photonic crystals, *Chem. Soc. Rev.* 42 (2013) 2528-2554.
- [8] F. Li, D.P. Josephson, A. Stein, Colloidal assembly: The road from particles to colloidal molecules and crystals, *Angew. Chem. Int. Ed.* 50 (2011) 360-388.
- [9] J. Ge, Y. Yin, Responsive photonic crystals, *Angew. Chem. Int. Ed.* 50 (2011) 1492-1522.

- [10] O.D. Velev, S. Gupta, Materials fabricated by micro- and nanoparticle assembly - The challenging path from science to engineering, *Adv. Mater.* 21 (2009) 1897-1905.
- [11] D. Yang, S. Ye, J. Ge, Solvent wrapped metastable colloidal crystals: Highly mutable colloidal assemblies sensitive to weak external disturbance, *J. Am. Chem. Soc.* 135 (2013) 18370-18376.
- [12] Y.A. Vlasov, X.Z. Bo, J.C. Sturm, D.J. Norris, On-chip natural assembly of silicon photonic bandgap crystals, *Nature* 414 (2001) 289-293.
- [13] B.T. Holland, C.F. Blanford, A. Stein, Synthesis of macroporous minerals with highly ordered three-dimensional arrays of spheroidal voids, *Science* 281 (1998) 538-540.
- [14] B.G. Prevo, O.D. Velev, Controlled, rapid deposition of structured coatings from micro- and nanoparticle suspensions, *Langmuir* 20 (2004) 2099-2107.
- [15] P. Jiang, J.F. Bertone, K.S. Hwang, V.L. Colvin, Single-crystal colloidal multilayers of controlled thickness, *Chem. Mater.* 11 (1999) 2132-2140.
- [16] R. Mayoral, J. Requena, J.S. Moya, C. Lopez, A. Cintas, H. Miguez, F. Meseguer, L. Vazquez, M. Holgado, A. Blanco, 3D long-range ordering in an SiO₂ submicrometer-sphere sintered superstructure, *Adv. Mater.* 9 (1997) 257-260.
- [17] P. Jiang, M.J. McFarland, Large-scale fabrication of wafer-size colloidal crystals, macroporous polymers and nanocomposites by spin-coating, *J. Am. Chem. Soc.* 126 (2004) 13778-13786.
- [18] J. Kleinert, S. Kim, O.D. Velev, Electric-field-assisted convective assembly of colloidal crystal coatings, *Langmuir* 26 (2010) 10380-10385.

- [19] Z. Cai, J. Teng, D. Xia, X.S. Zhao, Self-assembly of crack-free silica colloidal crystals on patterned silicon substrates, *J. Phys. Chem. C* 115 (2011) 9970-9976.
- [20] J. Zhang, A. Alsayed, K.H. Lin, S. Sanyal, F. Zhang, W.J. Pao, V.S.K. Balagurusamy, P.A. Heiney, A.G. Yodh, Template-directed convective assembly of three-dimensional face-centered-cubic colloidal crystals, *Appl. Phys. Lett.* 81 (2002) 3176-3178.
- [21] N. Vogel, S. Utech, G.T. England, T. Shirman, K.R. Phillips, N. Koay, I.B. Burgess, M. Kolle, D.A. Weitz, J. Aizenberg, Color from hierarchy: Diverse optical properties of micron-sized spherical colloidal assemblies, *Proc. Natl. Acad. Sci. USA* 112 (2015) 10845-10850.
- [22] S. Wong, V. Kitaev, G.A. Ozin, Colloidal crystal films: Advances in universality and perfection, *J. Am. Chem. Soc.* 125 (2003) 15589-15598.
- [23] C.F.C. Joao, J.M. Vasconcelos, J.C. Silva, J.P. Borges, An overview of inverted colloidal crystal systems for tissue engineering, *Tissue Eng. B* 20 (2014) 437-454.
- [24] L.N.D. Kallepalli, C. Constantinescu, P. Delaporte, O. Uteza, D. Grojo, Ultra-high ordered, centimeter scale preparation of microsphere Langmuir films, *J. Colloid Interf. Sci.* 446 (2015) 237-243.
- [25] M. Bardosova, P. Hodge, L. Pach, M.E. Pemble, V. Smatko, R.H. Tredgold, D. Whitehead, Synthetic opals made by the Langmuir-Blodgett method, *Thin Solid Films* 437 (2003) 276-279.
- [26] D. Nagao, R. Kameyama, H. Matsumoto, Y. Kobayashi, M. Konno, Single- and multi-layered patterns of polystyrene and silica particles assembled with a simple dip-coating, *Colloid Surf. A* 317 (2008) 722-729.

- 1
2
3
4 [27] M. Bardosova, M.E. Pemble, I.M. Povey, R.H. Tredgold, The Langmuir-Blodgett
5 approach to making colloidal photonic crystals from silica spheres, *Adv. Mater.* 22
6 (2010) 3104-3124.
7
8
9
10
11 [28] M. Bardosova, F.C. Dillon, M.E. Pemble, I.M. Povey, R.H. Tredgold, Langmuir-
12 Blodgett assembly of colloidal photonic crystals using silica particles prepared
13 without the use of surfactant molecules, *J. Colloid Interf. Sci.* 333 (2009) 816-819.
14
15
16
17
18 [29] L. Zhang, Z. Xiong, L. Shan, L. Zheng, T. Wei, Q. Yan, Layer-by-layer approach to
19 (2+1)D photonic crystal superlattice with enhanced crystalline integrity, *Small* 11
20 (2015) 4910-4921.
21
22
23
24
25
26 [30] S.G. Romanov, M. Bardosova, M. Pemble, C.M.S. Torres, (2+1)-dimensional
27 photonic crystals from Langmuir-Blodgett colloidal multilayers, *Appl. Phys. Lett.*
28 89 (2006) 043105.
29
30
31
32
33 [31] S.G. Romanov, M. Bardosova, I.M. Povey, M.E. Pemble, C.M.S. Torres,
34 Understanding of transmission in the range of high-order photonic bands in thin
35 opal film, *Appl. Phys. Lett.* 92 (2008) 191106.
36
37
38
39
40 [32] K.E. Tettey, M.Q. Yee, D. Lee, Layer-by-layer assembly of charged particles in
41 nonpolar media, *Langmuir* 26 (2010) 9974-9980.
42
43
44
45 [33] M.-H. Lin, H.-Y. Chen, S. Gwo, Layer-by-layer assembly of three-dimensional
46 colloidal supercrystals with tunable plasmonic properties, *J. Am. Chem. Soc.* 132
47 (2010) 11259-11263.
48
49
50
51
52 [34] X. Wang, Y. Wang, Q.M. Chen, Rapid facial fabrication of silica colloidal crystal
53 film at the air/water interface, *J. Nanosci. Nanotechnol.* 15 (2015) 9711-9716.
54
55
56
57
58
59
60
61
62
63
64
65

- [35] Y. Kusaka, N. Ishida, H. Ushijima, Role of interfacial interactions in ordering of two-dimensional colloidal self-assemblies on polyelectrolyte multilayer surfaces, *Soft Matter* 9 (2013) 3155-3163.
- [36] F. Xue, S.A. Asher, Z.H. Meng, F.Y. Wang, W. Lu, M. Xue, F.L. Qi, Two-dimensional colloidal crystal heterostructures, *RSC Adv.* 5 (2015) 18939-18944.
- [37] A. Gil, F. Guitian, Formation of 2D colloidal crystals by the Langmuir-Blodgett technique monitored in situ by Brewster angle microscopy, *J. Colloid Interf. Sci.* 307 (2007) 304-307.
- [38] Y.L. Lee, Z.C. Du, W.X. Lin, Y.M. Yang, Monolayer behavior of silica particles at air/water interface: A comparison between chemical and physical modifications of surface, *J. Colloid Interf. Sci.* 296 (2006) 233-241.
- [39] Y.X. Zhao, K. Wostyn, G. de Schaetzen, K. Clays, L. Hellemans, A. Persoons, M. Szeekeres, R.A. Schoonheydt, The fabrication of photonic band gap materials with a two-dimensional defect, *Appl. Phys. Lett.* 82 (2003) 3764-3766.
- [40] Q. Yan, L.K. Teh, Q. Shao, C.C. Wong, Y.-M. Chiang, Layer transfer approach to opaline hetero photonic crystals, *Langmuir* 24 (2008) 1796-1800.
- [41] S. Reculosa, P. Masse, S. Ravaine, Three-dimensional colloidal crystals with a well-defined architecture, *J. Colloid Interf. Sci.* 279 (2004) 471-478.
- [42] S. Reculosa, S. Ravaine, Synthesis of colloidal crystals of controllable thickness through the Langmuir-Blodgett technique, *Chem. Mater.* 15 (2003) 598-605.
- [43] B.M. Phillips, P. Jiang, B. Jiang, Biomimetic broadband antireflection gratings on solar-grade multicrystalline silicon wafers, *Appl. Phys. Lett.* 99 (2011) 191103.

- [44] S.P. Pack, N.K. Kamisetty, M. Nonogawa, K.C. Devarayapalli, K. Ohtani, K. Yamada, Y. Yoshida, T. Kodaki, K. Makino, Direct immobilization of DNA oligomers onto the amine-functionalized glass surface for DNA microarray fabrication through the activation-free reaction of oxanine, *Nucleic Acids Res.* 35 (2007).
- [45] J. Aizenberg, P.V. Braun, P. Wiltzius, Patterned colloidal deposition controlled by electrostatic and capillary forces, *Phys. Rev. Lett.* 84 (2000) 2997-3000.
- [46] D. Lee, D. Omolade, R.E. Cohen, M.F. Rubner, pH-Dependent structure and properties of TiO₂/SiO₂ nanoparticle multilayer thin films, *Chem. Mater.* 19 (2007) 1427-1433.
- [47] Y. Huang, J. Zhou, B. Su, L. Shi, J. Wang, S. Chen, L. Wang, J. Zi, Y. Song, L. Jiang, Colloidal photonic crystals with narrow stopbands assembled from low-adhesive superhydrophobic substrates, *J. Am. Chem. Soc.* 134 (2012) 17053-17058.
- [48] J.F. Bertone, P. Jiang, K.S. Hwang, D.M. Mittleman, V.L. Colvin, Thickness dependence of the optical properties of ordered silica-air and air-polymer photonic crystals, *Phys. Rev. Lett.* 83 (1999) 300-303.
- [49] K.H. Nielsen, D.K. Orzol, S. Koynov, S. Carney, E. Hultstein, L. Wondraczek, Large area, low cost anti-reflective coating for solar glasses, *Solar Energy Mater. Solar Cells* 128 (2014) 283-288.
- [50] J.A. Webb, R. Bardhan, Emerging advances in nanomedicine with engineered gold nanostructures, *Nanoscale* 6 (2014) 2502-2530.

Graphical Abstract

A rapid and scalable bottom-up technology has been developed for layer-by-layer assembling near-infrared-active colloidal photonic crystals consisting of micrometer-scale silica microspheres. This new electrostatics-assisted approach can enhance the crystal transfer speed of traditional Langmuir-Blodgett-based colloidal assembly technologies by nearly 2 orders of magnitude.