Reinhard Uecker^{*1}, Rainer Bertram¹, Mario Brützmam¹, Zbigniew Galazka¹, Thorsten M. Gesing², Christo Gugushev¹, Detlef Klimm¹, Michael Klupsch¹, Albert Kwasniewski¹,
Darrell G. Schlom^{3,4}

¹Leibniz Institute for Crystal Growth, Max-Born-Str. 2, D-12489 Berlin (Germany)

²University of Bremen, Solid State Chemical Crystallography, Institute of Inorganic Chemistry and Crystallography /FB02, Leobener Str. /NW2, and MAPEX Center for Materials and Processes, Bibliothekstraße 1, D-28359 Bremen (Germany)

³Department of Materials Science and Engineering, Cornell University, Ithaca, NY 14853-1501 (USA)

⁴Kavli Institute at Cornell for Nanoscale Science, Ithaca, New York 14853 (USA)

Dedicated to my great team in gratitude: Dr. Rainer Bertram, Mario Brützmam, Dr. Zbigniew Galazka, Dr. Steffen Ganschow, Dr. Christo Gugushev, M.Sc. Franz Kamutzki, M.Sc. Dirk Kok, Dr. Detlef Klimm, Martina Rabe, Dr. Detlev Schulz, Isabelle Schulze-Jonack, Andreas Tauchert, Elvira Thiede, Margitta Bernhagen (retired) and Dr. Peter Reiche (retired).

Abstract

The pseudobinary system $\text{LaLuO}_3\text{-LaScO}_3$ was explored in hopes of discovering new perovskite-type substrates with pseudocubic lattice parameters above 4 Å. A complete solid solution of the type $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ forms between the end members LaLuO_3 and LaScO_3 , enabling large single crystals of $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ to be grown from the melt. A single crystal with $x \approx 0.34$ was demonstrated. Considering the maximum thermal load of the iridium crucibles appropriate for Czochralski growth of this solid solution, the theoretically maximum achievable x -value is ~ 0.67 . Based on the phase diagram determined, it is anticipated that single crystals with pseudocubic lattice constants between 4.09 and 4.18 Å can be grown in this system by the Czochralski method.

Keywords: A1. Crystal structure; A1. Phase diagrams; A1. Substrates; A2. Czochralski method; B1. Perovskites; B1. Rare-earth compounds

*Corresponding author. E-mail address: reinhard.uecker@ikz-berlin.de (R. Uecker)

1. Introduction

Over the past several decades a broad range of oxide single crystals with cubic and pseudocubic perovskite structures have emerged as substrates for the epitaxy of high quality perovskite thin films [1,2,3,4,5,6,7,8,9,10,11,12,13,14,15,16,17,18,19,20,21,22]. The pseudocubic lattice parameters of the more or less commercially available oxide perovskites range, as illustrated in Fig. 1, from 3.67 Å (LuAlO₃) to 4.05 Å (LaScO₃).

Fig. 1. Pseudocubic lattice parameter of perovskite and perovskite-related films and substrates. This list is an enhanced version of the one in Ref. [23]. Except for LuAlO₃, CeScO₃, and LaScO₃, all crystals are grown at the Leibniz Institute for Crystal Growth.

When considering the need for substrates for thin films of new handy oxides with enticing properties, there exists a serious lack of perovskite substrates with lattice parameters above four Ångstroms. For many years SrTiO₃ was the perovskite-type substrate of choice with the largest lattice parameter: $a = 3.905$ Å. (KTaO₃ with $a = 3.99$ Å shows strong volatility at elevated temperatures which excludes it from many substrate applications.) The introduction of the rare earth scandates $LnScO_3$ ($Ln = Dy - La$) as substrates about a dozen years ago [19,24,25] shifted the upper limit to 3.95 - 4.05 Å. Unfortunately, the exceptionally high melting temperature of the largest of the rare earth scandates – CeScO₃ and LaScO₃ – excludes them from growth by the most appropriate method for high perfection bulk crystals, the Czochralski method, because it far exceeds the maximum thermal load of the crucible material (iridium) of about 2200 °C. Therefore, PrScO₃ with 4.02 Å has the largest pseudocubic lattice constant achievable with $LnScO_3$ substrates. Nonetheless, the more than 20 available substrates covers a lattice parameter range of 0.35 Å. This broad assortment of perovskite substrates with finely spaced pseudocubic lattice constants has enabled the misfit strain in epilayers to be precisely targeted. Such strain engineering has been exploited to enhance of the properties of some oxides as well as to access the exceptional properties of the hidden ground state of others [23].

To the best of our knowledge only one perovskite is known with a lattice parameter far above 4 Å and which can be grown as a bulk single crystal: LaLuO₃ with $a = 4.18$ Å [23,26]. As is evident from Fig. 1, in the large lattice-parameter range a significant gap existing between two lanthanum oxide containing compounds: LaScO₃ ($a = 4.05$ Å) and LaLuO₃ ($a = 4.18$ Å). Therefore, in the search of new perovskites to fill this substrate gap, it was obvious

to investigate whether LaLuO_3 and LaScO_3 form a solid solution. For this purpose, i.e., to investigate if they can be grown as bulk crystals from the melt and thereby made available as substrate crystals, the pseudobinary phase diagram LaLuO_3 - LaScO_3 was systematically investigated.

2. Methods

To investigate the crystallization within the pseudobinary system LaLuO_3 - LaScO_3 thermal investigations of different mixtures were performed with a NETZSCH STA 429, which allows measurements up to 2400 °C. Because of the maximum thermal load of iridium, the crucible material to be used for the Czochralski growth experiments planned, no mixtures with a LaScO_3 content of much more than 50 mol% were investigated.

The starting oxides for the crystal growth experiments La_2O_3 , Lu_2O_3 , and Sc_2O_3 were of 99.99% and 99.995% purity. To prepare the starting melt they were dried, mixed, sintered, and finally isostatically pressed following standard procedures. The crystals were grown by the conventional Czochralski technique with RF-heating and automatic diameter control. Because of the high melting temperature of the new crystals in the LaLuO_3 - LaScO_3 system, an iridium crucible was utilized. The diameter and height of the crucible were each 40 mm. Additionally an active iridium afterheater was installed which enabled the defined adjustment of the temperature gradients. Thermal insulation was provided by an outer alumina ceramic tube filled with zirconia granules. The growth atmosphere consisted of flowing argon (N50 quality). A pulling rate of 0.5 mm h^{-1} and a rotation rate of 15 rpm were utilized. Due to the lack of a seed crystal, an iridium rod was used instead.

Structure analysis of the crystals was provided by Rietveld refinement of X-ray powder diffraction data measured with a XRD 3003 TT (GE) ($\text{Cu } K_\alpha$ radiation, 2θ range 20 - 70°). The chemical composition of the crystals was measured using an inductively coupled plasma-optical emission spectrometer (ICP-OES) IRIS Interpid HR Duo. The samples were prepared by grinding and subsequent microwave digestion with a mixture of HNO_3 and H_2O_2 (220 °C, 20 min). Micro X-ray fluorescence (μ -XRF) elemental mappings were carried out using a Bruker M4 TORNADO spectrometer to investigate segregation during crystal growth.

3. Determination of the pseudobinary phase diagram LaLuO_3 - LaScO_3

In general, the formation of solid solutions must fulfill several preconditions:

- Both components must be isomorphous; they are (both are space group $Pnma$)
- Difference in the lattice parameters < 15%; it is ($\sim 3\%$)

- Chemical similarity; this exists
- and because LaLuO_3 and LaScO_3 are complex oxides, congruent melting behavior; they are (for LaScO_3 see [27])

As all requirements for solid solution formation between LaLuO_3 and LaScO_3 are fulfilled, our expectation is to find solid solution formation in this system.

Powders of La_2O_3 (99.995%), Lu_2O_3 (99.999%), and Sc_2O_3 (99.999%) were used as starting materials for differential thermal analysis (DTA). First, the pure oxides were checked for mass losses resulting from carbonates or hydroxides, respectively, by simultaneous DTA/TG (thermogravimetry) in flowing Ar up to 1200 °C with a NETZSCH STA 409C. Especially lanthanum oxycarbonate is known to be quite stable [28], and indeed 1.24% mass loss for La_2O_3 was observed up to 750 °C. The mass losses of Sc_2O_3 and Lu_2O_3 did not exceed 0.07% or 0.16%, respectively.

Taking these losses into account, LaLuO_3 and LaScO_3 powders were prepared by mixing stoichiometric quantities with overall compositions $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ in a mortar and annealing them in 200 mg batches in platinum crucibles inside the DTA apparatus at 1645 °C for 1 hour (heating/cooling rates 10 K/min). No significant thermal effects were observed that would indicate perovskite phase formation; nonetheless X-ray powder diffraction revealed that the powder mixtures were thoroughly reacted to form the perovskites.

These pre-reacted perovskite powders and mixtures of both, were used for high-temperature DTA measurements in a tungsten furnace. The measurements were performed with heating/cooling rates of 15 K/min in a static helium atmosphere in tungsten crucibles with lids. From time to time pure Al_2O_3 (melting point 2054 °C, heat of fusion 118.41 kJ/mol) was melted under identical experimental conditions. This calibration data was used to reduce temperature errors resulting from thermocouple drift and to estimate the heat energy sensitivity of the measurement system.

For seven mixtures $(1-x) \text{LaLuO}_3 + x \text{LaScO}_3$ with $0 \leq x \leq 0.53$ one melting peak was observed. At $x = 0$ an extrapolated onset (= melting point) at 2121 °C and a peak width of $\Delta T = 13.6$ K was measured. For all seven samples the heats of fusion were estimated by comparing the peak areas with the areas of the Al_2O_3 melting peaks, and values ranging from 60 kJ/mol to 81 kJ/mol were found. The peaks began to shift to higher temperatures and became broader (onsets $T_f = 2135$ °C or 2165 °C, and $\Delta T = 50$ K or 76 K, respectively) for $x = 0.40$ and $x = 0.53$. For the $x = 0.59$ sample the onset was at 2222 °C, but the melting peak could not be observed completely because the sample holder was destroyed near 2300 °C.

The experimental data from this study, together with Gibbs free energy data $G(T)$ for LaLuO_3 and LaScO_3 that were calculated from the component oxides by Hess' law, and the melting point of LaScO_3 , $T_f = 2390$ °C [27], were used as input parameters for a thermodynamic assessment of the pseudobinary system with FactSage [29]. For this assessment the melt was assumed to be an ideal mixture.

The results indicated a complete solid solution forms for the LaLuO_3 - LaScO_3 system, as expected. This solid solution can be described by a simple polynomial with an excess Gibbs free energy (G_{ex}) contribution of $G_{\text{ex}} = x(1-x)A$, with one single fitting parameter $A = 10.9$ kJ/mol. Fig. 2 shows the pseudobinary phase diagram that was the result of the assessment. It reproduced the experimental solidus data with an error of ± 10 K, and the generally less accurate liquidus data within ± 20 K.

Fig. 2. Assessed pseudobinary phase diagram of the LaLuO_3 - LaScO_3 system. The insert shows an azeotropic point near 8 mol% LaScO_3 .

The solid/liquid equilibrium of the system appears at very high temperatures, so that deviations from ideal behavior are small. For the melt, no excess Gibbs free energy contributions were needed to describe the experimental data reasonably. Also for the solid solution, the assumption of ideal behavior (lowest curve in Fig. 3) is not far from the real behavior, which also takes the G_{ex} term given above into account. Nevertheless, this small positive excess energy contribution results in a slight destabilization of the solid solution and is responsible for the local minima of solidus and liquidus near 8% LaScO_3 (azeotropic point). Up to ~20% LaScO_3 , the solidus and liquidus are almost identical, resulting in nearly congruent melting behavior.

Fig. 3. Gibbs free energy contributions to the solid-solution phase $(1-x)\text{LaLuO}_3 + x\text{LaScO}_3$ for $T = 2077$ °C. [G_0 -ideal Gibbs free energy of mixing; G_{id} -weighted contribution of components to the Gibbs free energy]

4. Crystal growth of $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution

To stay about 50 K below the maximum thermal load of iridium, the crystal growth experiments were started with a mixture of 67 mol% LaLuO_3 and 33 mol% LaScO_3 , which

corresponds to an x -value of 0.33 and a liquidus temperature of 2150 °C (melt 1). The grown boule had a length of about 80 mm and a diameter of 15 mm. Because it was grown from an iridium seed rod, it did not consist of one single crystal, but of several colorless, transparent grains.

4.1. Crystallization of $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution in the ternary phase diagram La_2O_3 - Sc_2O_3 - Lu_2O_3

One of the colorless, transparent grains from the beginning of the crystal was used for the determination of the chemical composition by ICP-OES. It consisted of 47.48 mol% La_2O_3 , 29.92 mol% Lu_2O_3 , and 22.60 mol% Sc_2O_3 ; this composition corresponds to $x = 0.43$. This x -value is in good agreement with the phase diagram (see Fig. 2). The La_2O_3 content, however, lies noticeably below 50 mol%. This is not surprising because the La_2O_3 content of both end members of the pseudobinary section when pulled as single crystals from stoichiometric melts also lies below 50 mol%. In the case of LaLuO_3 , our composition analysis yielded a La_2O_3 content of 47.10 mol% leading to the formula $\text{La}_{0.942}\text{Lu}_{1.058}\text{O}_3$. For LaScO_3 , the La_2O_3 content was found to be 48.45 mol% [30] leading to the formula $\text{La}_{0.94}\text{Sc}_{1.00}\text{O}_{2.91}$. Based on this knowledge, the relatively low La_2O_3 content of our solid-solution crystal is plausible. Therefore it should be emphasized that the crystallization path of the solid solution can be properly described by a pseudobinary section of the ternary phase diagram La_2O_3 - Sc_2O_3 - Lu_2O_3 , lying a few percent below 50 mol% La_2O_3 (Fig. 4).

Accordingly, subsequent growth experiments were initiated from a slightly La_2O_3 -deficient melt composition lying along the binary section shown in Fig. 4. In order to further decrease the growth temperature, the LaScO_3 content was also reduced slightly, leading to the following melt composition: La_2O_3 : 47.50 mol%; Lu_2O_3 : 38.00 mol%; Sc_2O_3 : 14.50 mol%, which corresponds to $x = 0.276$ (melt 2).

Fig. 4. Ternary phase diagram La_2O_3 - Sc_2O_3 - Lu_2O_3 .

The total length of the grown crystal was about 75 mm and its diameter was about 16 mm (Fig. 5). Despite this crystal being grown from an iridium seed rod, the boule became single crystalline shortly beyond the shoulder. The whole cylinder was colorless and transparent.

Fig. 5. Crystal grown from melt 2.

4.2. Segregation in the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution

Because of its long single-crystal section, this crystal was particularly suitable for the investigation of segregation. For this purpose, we performed XRF measurements at four different areas equally distributed over a longitudinal section of the single crystalline part of the crystal (see Fig. 5). The quantitative results of these measurements are listed in Table 1 and shown in Fig. 6.

Table 1. Crystal composition at selected areas (see Fig. 5).

As is evident in Fig. 6, the lanthanum oxide content remains unchanged at 47.50 mol% over the whole length of the crystal. This confirms the assumption that the crystallization path of the solid solution $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ lies on a pseudobinary section of the ternary phase diagram $\text{La}_2\text{O}_3 - \text{Sc}_2\text{O}_3 - \text{Lu}_2\text{O}_3$, just a few percent below 50 mol% La_2O_3 . The segregation only concerns lutetium and scandium oxide. As the content of the former increases linearly from top to bottom, the content of the latter linearly decreases.

Fig. 6. Segregation in a $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid-solution single crystal.

Extrapolation of the values given in Table 1 provided an x -value of 0.38 for the beginning of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid-solution crystal prepared from melt 2, and an x -value of 0.305 for the crystal end. All these data are in good agreement with the phase diagram (Figs. 4 and 7). The final resulting pseudobinary $\text{La}_{0.942}\text{Lu}_{1.058}\text{O}_3 - \text{La}_{0.94}\text{Sc}_{1.00}\text{O}_{2.91}$ phase diagram is shown in Fig. 7, assuming that the position of the azeotrope point does not shift significantly.

Fig. 7. Final pseudobinary phase diagram of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution including the crystallization paths of the solid solutions grown. (The composition of melt 1 is projected on this section and the dotted line shows the segregation in crystal 2 prepared from melt 2).

5. Crystallographic data

5.1. Structure

The structure of the solid solution was investigated on crystalline material obtained from melt 1. It was found that it is a distorted perovskite crystallizing in the orthorhombic space group $Pnma$ (62) -the same as LaLuO_3 and LaScO_3 (see Fig. 8). The cell parameters are $a = 5.9199(7) \text{ \AA}$, $b = 8.2422(11) \text{ \AA}$, $c = 5.7422(8) \text{ \AA}$. This corresponds to a pseudocubic lattice constant of $4.1224 \text{ \AA}$ -nearly halfway between those of the end members. The calculated density is 7.18 g/cm^3 .

Fig. 8. Crystal structure of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution.

It was found that about five percent of the lutetium atoms also occupy the A-position of the lanthanum atoms, i.e., lutetium drives lanthanum out of the structure. The explanation for this is that lutetium belongs to those 15 elements of the periodic table known to occupy both the large A- and the small B-position in a perovskite structure [31]. The resulting formula is $(\text{La}_{1.94}\text{Lu}_{0.06})(\text{Lu}_{1.106}\text{Sc}_{0.894})\text{O}_6$, i.e., the sum formula is $\text{La}_{1.94}\text{Lu}_{1.17}\text{Sc}_{0.89}\text{O}_6$. The corresponding x -value is 0.43, which exactly coincides with that measured by ICP-OES (see Sect. 4.1). This explains the “lanthanum-oxide-poor” composition of this solid solution. This special property of lutetium also occurs in the end member LaLuO_3 , resulting in a shift of the single-crystal composition to lower La_2O_3 values given by the formula $(\text{La}_{0.942}\text{Lu}_{0.058})\text{Lu}_{1.000}\text{O}_3$ (see also [17]). For the other end member, LaScO_3 , the lanthanum oxide deficiency is caused by a lanthanum deficiency on the A-site. This is thought to be due to a coupled substitution involving vacancies, which can be written as $^A\Box(2\text{La}^{3+} 3\text{O}^{2-})_{-1}$ [20].

5.2. Vegard's law

To investigate the dependence of the lattice parameters on crystal composition, the lattice parameters of both end members, LaLuO_3 and LaScO_3 , as well as those of three solid-solution samples with strongly differing x -values were measured. The experimental results and the calculated pseudocubic lattice parameters are shown in Table 2.

Table 2. Dependence of lattice parameters on solid solution composition.

In Fig. 9 the dependence of the pseudocubic lattice parameter on the composition of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution is shown. It is clear that this dependence follows Vegard's law [32,33], i.e., the lattice parameter changes linearly with the composition of the solid solution. Slight negative deviations from the rule as occurring here are known to be caused by stronger bonds between different atoms compared to those between similar atoms. Therefore, the same is true for atomic positions occupied by different atoms in a solid solution. This is even more true if the resulting bond lengths, here Lu-O and Sc-O, are significantly different, expressing the different bond strength of the corresponding bond partners. Therefore, a slight deviation from Vegard's rule is not surprising.

Fig. 9. Dependence of the pseudocubic lattice parameter on the composition of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution. (The size of the squares corresponds to the size of the error bars.)

Having established the pseudobinary phase diagram of the $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$ solid solution, we note that only these compositions can be grown by the Czochralski method. Further, if an iridium crucible is used, which is appropriate for the mildly oxidizing conditions needed to stabilize this solid solution, the maximum x -value that can be achieved is about ~ 0.67 . This limit arises from iridium crucibles being able to withstand a maximum thermal load of about 2200 °C. From Vegard's law, solid solutions with x ranging from 0 - 0.67 correspond to a pseudocubic lattice parameter range of 4.18 – 4.09 Å.

6. Summary

A new system for the single-crystal growth of large-lattice-parameter perovskites was discovered. The system LaLuO_3 - LaScO_3 forms a complete solid solution of the type $(\text{LaLuO}_3)_{1-x}(\text{LaScO}_3)_x$. The solid solution has the orthorhombic perovskite crystal structure

with space group *Pnma*. Its pseudocubic lattice parameters cover the range between 4.05 and 4.18 Å, a region in which so far no large single-crystal perovskites have been grown. Because the maximum x -value for Czochralski growth is limited to ~ 0.67 , only solid solutions with pseudocubic lattice parameters between 4.09 and 4.18 Å are realizable as bulk single crystals. We anticipate that these new solid-solution single crystals will enable the epitaxial growth of high quality thin films of promising materials whose growth until now has been stymied by the lack of suitable substrates. Examples include high-quality epitaxial films of BaSnO₃ (a transparent conducting oxide with the highest mobility of all known high-bandgap semiconductors [34]), BiScO₃ (an important constituent of a new class of high-temperature piezoelectrics [35,36]), and PbZrO₃ (an antiferroelectric material relevant to energy storage [37]). Substrates made from the diamagnetic (LaLuO₃)_{1-x}(LaScO₃)_x solid solution are also advantageous when it comes to measuring the magnetic properties of thin films grown on them, e.g., multiferroics, as the magnetic background of these substrates will be quite low.

7. Outlook

Despite the discovery of this new large-lattice-parameter perovskite crystal there still remains a lattice parameter gap between 4.05 and 4.09 Å. Further, it is not feasible to grow single crystals of CeScO₃ and LaScO₃ by the Czochralski method because of their extremely high melting temperatures, so the gap really extends downwards to PrScO₃. Thus, a substrate need still exists between 4.02 – 4.09 Å.

There is, however, some hope to close this remaining gap. It is reported that PrLuO₃ and NdLuO₃ are orthorhombic perovskites with space group *Pnma* (62) and pseudocubic lattice parameters of 4.161 and 4.145 Å, respectively [38]. Provided that they melt congruently, it is likely that they form solid solutions with the respective scandates (PrScO₃ and NdScO₃) and, that the complete systems *Ln*ScO₃-*Ln*LuO₃ (with *Ln* = Pr, Nd) can be grown as bulk crystals by the Czochralski method. Even if PrLuO₃ might melt peritectically, it is reported that it can be prepared by direct melt freezing in the form of single-phase bulk polycrystals [26]. The situation for NdLuO₃, which is reported to be metastable at high temperature [38], appears more problematic. A preliminary comparison of the XRD patterns of *Ln*LuO₃ (with *Ln* = La, Pr, Nd) solid state reaction products (reacted twice at 1600 °C for 24 h) revealed a pattern for PrLuO₃ that is fully compatible with the perovskite structure; unfortunately this was not the case for NdLuO₃. Studying the feasibility of these solid solutions is an avenue for future exploratory studies to identify additional needed perovskite substrates.

Acknowledgements

The authors thank Elvira Thiede for technical support. T.M.G. gratefully acknowledges the Deutsche Forschungsgemeinschaft (DFG) for the financial support in the Heisenberg program (GE1981/3-1 and GE1981/3-2). D.G.S. acknowledges support from the Center for Low Energy Systems Technology (LEAST), one of six centers of STARnet, a Semiconductor Research Corporation program sponsored by MARCO and DARPA.

References

-
- ¹ L. Merker, US Patent No. 2,684,910 (27 July 1954).
 - ² H. J. Scheel, J. G. Bednorz, P. Dill, *Ferroelectrics* 13 (1976) 507.
 - ³ J. G. Bednorz, H. J. Scheel, *J. Cryst. Growth* 41 (1977) 5.
 - ⁴ R. L. Sandstrom, E. A. Giess, W. J. Gallagher, A. Segmüller, E. I. Cooper, M. F. Chisholm, A. Gupta, S. Shinde, R. B. Laibowitz, *Appl. Phys. Lett.* 53 (1988) 1874.
 - ⁵ R. W. Simon, C. E. Platt, A. E. Lee, G. S. Lee, K. P. Daly, M. S. Wire, J. A. Luine, M. Urbanik, *Appl. Phys. Lett.* 53 (1988) 2677.
 - ⁶ R. Feenstra, L. A. Boatner, J. D. Budai, D. K. Christen, M. D. Galloway, D. B. Poker, *Appl. Phys. Lett.* 54 (1989) 1063.
 - ⁷ H. Asano, S. Kubo, O. Michikami, M. Satoh, T. Konaka, *Jpn. J. Appl. Phys., Part 2* 29 (1990) L1452.
 - ⁸ R. Brown, V. Pendrick, D. Kalokitis, B. H. T. Chai, *Appl. Phys. Lett.* 57 (1990) 1351.
 - ⁹ G. W. Berkstresser, A. J. Valentino, C. D. Brandle, *J. Cryst. Growth* 109 (1991) 467.
 - ¹⁰ S. Hontsu, J. Ishii, T. Kawai, S. Kawai, *Appl. Phys. Lett.* 59 (1991) 2886.
 - ¹¹ D. Mateika, H. Kohler, H. Laudan, E. Volkel, *J. Cryst. Growth* 109 (1991) 447.
 - ¹² G. W. Berkstresser, A. J. Valentino, C. D. Brandle, *J. Cryst. Growth* 109 (1991) 457.
 - ¹³ Y. Miyazawa, H. Toshima, S. Morita, *J. Cryst. Growth* 128 (1993) 668.
 - ¹⁴ G. W. Berkstresser, A. J. Valentino, C. D. Brandle, *J. Cryst. Growth* 128 (1993) 684.
 - ¹⁵ A. Lempicki, M. H. Randles, D. Wisniewski, M. Balcerzyk, C. Brecher, A. J. Wojtowicz, *IEEE Trans. Nucl. Sci.* 42 (1995) 280.
 - ¹⁶ A. G. Petrosyan, G. O. Shirinyan, C. Pedrini, C. Durjardin, K. L. Ovanesyan, R. G. Manucharyan, T. I. Butaeva, M. V. Derzyan, *Cryst. Res. Technol.* 33 (1998) 241.
 - ¹⁷ K. L. Ovanesyan, A. G. Petrosyan, G. O. Shirinyan, C. Pedrini, L. Zhang, *J. Cryst. Growth* 198-199 (1999) 497.
 - ¹⁸ P. I. Nabokin, D. Souptel, A. M. Balbashov, *J. Cryst. Growth* 250 (2003) 397.

-
- ¹⁹ R. Uecker, H. Wilke, D. G. Schlom, B. Velickov, P. Reiche, A. Polity, M. Bernhagen, M. Rossberg, *J. Cryst. Growth* 295 (2006) 84.
- ²⁰ B. Veličkov, V. Kahlenberg, R. Bertram, M. Bernhagen, *Z. Kristallogr.* 222 (2007) 466.
- ²¹ R. Uecker, B. Velickov, D. Klimm, R. Bertram, M. Bernhagen, M. Rabe, M. Albrecht, R. Fornari, D. G. Schlom, *J. Cryst. Growth* 310 (2008) 2649.
- ²² R. Uecker, D. Klimm, R. Bertram, M. Bernhagen, I. Schulze-Jonack, M. Brützm, A. Kwasniewski, T.M. Gesing, D.G. Schlom, *Acta Phys. Pol. A* 124 (2013) 295.
- ²³ D. G. Schlom, L. Q. Chen, C. J. Fennie, V. Gopalan, D. A. Muller, X. Pan, R. Ramesh, R. Uecker, *MRS Bulletin* 39 No. 2 (2014) 119.
- ²⁴ J. Schubert, O. Trithaveesak, A. Petraru, C. L. Jia, R. Uecker, P. Reiche, and D. G. Schlom, *Applied Physics Letters* 82 (2003) 3460.
- ²⁵ J. H. Haeni, P. Irvin, W. Chang, R. Uecker, P. Reiche, Y. L. Li, S. Choudhury, W. Tian, M. E. Hawley, B. Craigo, A. K. Tagantsev, X. Q. Pan, S. K. Streiffer, L. Q. Chen, S. W. Kirchoefer, J. Levy, D. G. Schlom, *Nature* 430 (2004) 758.
- ²⁶ K. L. Ovanesyan, A. G. Petrosyan, G. O. Shirinyan, C. Pedrini, L. Zhang, *Optical Materials* 10 (1998) 291.
- ²⁷ J. M. Badie, *Rev. Int. Hautes Temp. Refract.* 15 (1978) 183.
- ²⁸ A. N. Shirsat, M. Ali, K. N. G. Kaimal, S. R. Bharadwaj, D. Das, *Thermochim. Acta* 399 (2003) 167.
- ²⁹ www.factsage.com, FactSage 6.4, (2013).
- ³⁰ S. Balamurugan, U. C. Rodewald, T. Harmening, L. van Wüllen, D. Mohr, H. Deters, H. Eckert, R. Pöttgen, *Z. Naturforsch.* 65b (2010) 1201.
- ³¹ D. G. Schlom, L. Q. Chen, X. Q. Pan, A. Schmehl, and M. A. Zurbuchen, *J. Am. Ceram. Soc.* 91 (2008) 2429.
- ³² L. Vegard, *Z. Phys.* 5 (1921) 17.
- ³³ L. Vegard, *Z. Krist.* 67 (1928) 239.
- ³⁴ H. J. Kim, U. Kim, H. M. Kim, T. H. Kim, H. S. Mun, B.-G. Jeon, K. T. Hong, W.-J. Lee, C. Ju, K. H. Kim, and K. Char, *Appl. Phys. Express* 5 (2012) 061102.
- ³⁵ R. Eitel, C. A. Randall, T. R. Shrout, P. W. Rehrig, W. Hackenberger, and S.-E. Park, *Jpn. J. Appl. Phys., Part 1* 40 (2001) 5999.
- ³⁶ R. E. Eitel, C. A. Randall, T. R. Shrout, and S.-E. Park, *Jpn. J. Appl. Phys., Part 1* 41 (2002) 2099.
- ³⁷ I. Burn, D. M. Smyth, *J. Mater Sci.* 7 (1972) 339.
- ³⁸ U. Berndt, D. Maier, C. Keller, *J. Solid State Chem.* 13 (1975) 131.

Figures and tables:

Fig. 1.

Fig. 2.

Fig. 3.

Fig. 4.

Fig. 5.

Fig. 6.

Fig. 7.

Fig. 8.

Fig. 9.

Table 1.

XRF measurement area	mol%		
	La ₂ O ₃	Lu ₂ O ₃	Sc ₂ O ₃
1	47.50	33.91	18.59
2	47.50	34.55	17.95
3	47.51	35.38	17.11
4	47.50	36.17	16.33

Table 2.

	Orthorhombic lattice parameters (Å)			Pseudocubic lattice parameter (Å)
	<i>a</i>	<i>b</i>	<i>c</i>	<i>a_{pc}</i>
LaScO ₃ ; <i>x</i> =1	5.7946(5)	8.0941(8)	5.6707(5)	4.0504
ss with <i>x</i> =0.43	5.9199(7)	8.2422(11)	5.7422(8)	4.1224
ss with <i>x</i> =0.35	5.9339	8.2676	5.7552	4.1335
ss with <i>x</i> =0.265	5.9557	8.2889	5.7664	4.1447
LaLuO ₃ ; <i>x</i> =0	6.0125(7)	8.3733(10)	5.8098(7)	4.1835