Oxygen triclusters in crystalline and glassy SrB_4O_7 : high resolution ^{11}B and ^{17}O nuclear magnetic resonance analysis

Michelle LaComb^{a,*} and Jonathan F. Stebbins^a

^aDepartment of Geological Sciences, Stanford University, Stanford, CA 94305

Keywords: nuclear magnetic resonance; oxygen triclusters; glass structure; strontium tetraborate

* Correspondence should be addressed to Michelle LaComb
Tel: 1-650-723-1140
E-mail address: mlacomb@stanford.edu

Abstract

We present ^{11}B and ^{17}O magic-angle spinning (MAS) and multiple quantum (MQMAS) nuclear magnetic resonance (NMR) data for crystalline strontium tetraborate (SrB_4O_7) and the glass with corresponding $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ composition. Crystalline SrB_4O_7 contains an oxygen tricluster site (3 BO_4 neighbors) and can be used as a model compound for observing oxygen tricluster sites in the corresponding glass. NMR site parameters for the tricluster are distinguishable from those of the bridging oxygens in SrB_4O_7 , allowing for visible areas in the ^{17}O spectrum attributed solely to the presence of oxygen triclusters. By overlapping the spectra of the crystalline SrB_4O_7 and the corresponding glass there are indications for a maximum of a few percent of tricluster oxygens within the glass. This is further confirmed by calculations of expected non-bridging oxygen (NBO) content without triclusters, done using ^{11}B MAS NMR and analyzed composition, in comparison to directly measured NBO content in the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass, which suggests that up to 2% of the total oxygens within this glass are in triclusters.

1. Introduction

Given difficulties in direct measurement of atomic arrangement in amorphous materials, many models for glass structure are derived at least in part from studies of corresponding crystal structures. The vast majority of low pressure silicate, borate and $^{[4]}\text{Al}$ aluminate crystal structures contain only two oxygen species: bridging oxygens (BO, an O atom bonded to two network formers, such as Si-O-Si or B-O-B) and non-bridging oxygens (NBO, an O atom bound to a single network former and balanced by one or more network modifying cations, such as Ca-O-Al or Sr-O-B). Relative ratios of NBO:BO in typical oxide glasses play an important role in determining physical properties (such as hardness, chemical durability, and glass transition

temperature) as well thermodynamic and transport properties [1,2]. Assuming that all oxygen in glasses is similarly BO or NBO, as is commonly done in borate glass literature (harkening back to Krogh-Moe's original work on binary borates [3]), allows for the NBO content in glasses to be derived from the glass composition when boron coordination is measured by methods such as NMR.

However, in a few crystalline borates and aluminates, there exists a third type of oxygen species - oxygen triclusters, with an oxygen anion connected to three trivalent tetrahedral cations. These triclusters have been suggested to be present as a charge-balancing mechanism for structures with excess Al such as Al-rich aluminosilicate liquids [4]. Direct evidence of tricluster oxygens in glass structures is very limited, but oxygen-17 NMR can offer a unique view by allowing for direct observation of the amount of NBO present in glasses suggested to contain small amounts of tricluster oxygens. This would allow for comparison of directly measured NBO to NBO values calculated based on the standard model of glass structure, which assumes no tricluster oxygens are present.

Oxygen-17 magic angle spinning (MAS) NMR has been previously utilized to address the presence of tricluster oxygens in Al-rich aluminosilicate glass structures, suggested to be present as a charge-balancing mechanism for structures with excess NBO and to address the anomalous viscosities of these systems [5–8]. ^{17}O and ^{27}Al MAS NMR on grossite (CaAl_4O_7), which contains $\text{O}(\text{Al})_3$ triclusters, has been used to determine the expected location of NMR signals for tricluster oxygens within aluminosilicate glasses [9]. Overlapping spectral components in calcium aluminosilicate glasses permitted a small proportion of this species but confirming its

presence was not possible. However, $\{^{17}\text{O}\}^{27}\text{Al}$ heteronuclear multiple quantum correlation (HMQC) NMR has allowed for direct detection of a signal corresponding to a few percent tricluster oxygen in CaAl_2O_4 glasses [10].

Oxygen triclusters are also known in several binary borate crystal structures that are isostructural with grossite. A recent series of papers have focused attention on “tetraborate” crystals, which are frequently used as nonlinear optical materials [11]. These MB_4O_7 compounds are known to form with $\text{M} = \text{Sr}^{2+}$ [12–15], Pb^{2+} [14–16] and Eu^{2+} [17] (at ambient pressure) and Ca^{2+} [18], Hg^{2+} [19] and Sn^{2+} [20] (at high pressure), in the non-centrosymmetric $Pmn2_1$ space group. All of these are isostructural with CaAl_4O_7 .

The corresponding $\text{M}_2\text{B}_4\text{O}_7$ composition, also composed of one mole of modifier oxide and two moles of B_2O_3 (but with two monovalent modifier cations), is often labeled with the term “diborate”. A few MB_4O_7 compounds, such as low-pressure $\alpha\text{-CaB}_4\text{O}_7$, are isostructural with “diborates”, such as $\text{Na}_2\text{B}_4\text{O}_7$ [18]. The “diborate” structural group, characterized by equal amounts of $^{[3]}\text{B}$ and $^{[4]}\text{B}$, all BO , and three-membered rings, is one of the key elements in common structural models of both alkali and alkaline earth borate and borosilicate glasses [21]. Given the stability of tricluster-containing, $^{[4]}\text{B}$ -only phases, such as strontium tetraborate, of the same stoichiometry as these “diborates”, a re-examination of the glass structure of borates of this stoichiometry is needed.

In this study, we present experimental data on crystalline strontium tetraborate, in comparison to the glass of similar composition. SrB_4O_7 is of particular interest since all of the boron present are

tetrahedrally coordinated and 2/7 of all the oxygens present in the crystal are oxygen triclusters, coordinated to three such borons. The published crystal structure of strontium tetraborate [15] shows there to be four distinct oxygens, three of which are bridging oxygens, hereafter referred to by O1, O2, and O3, making up the remaining 5/7 of the oxygens, and the fourth of which is the tricluster oxygen, O4. There are two distinct types of tetrahedral borons, one of which, B1, is connected to one tricluster oxygen and three bridging oxygens, and the other, B2, connects two tricluster oxygens to each other. The use of ^{11}B and ^{17}O MAS NMR, as well as multiple-quantum magic-angle spinning (MQMAS) NMR for both ^{11}B and ^{17}O , on crystalline strontium tetraborate at a range of magnetic fields allows for careful prediction of expected spectral range of borate triclusters, if any, in the spectra of the corresponding glass.

In addition to direct analysis of oxygen-17 NMR spectra for a tricluster-like site, measurement of boron coordination and BO and NBO contents of the glass by NMR allows for an independent assessment, by mass and charge balance, of whether all oxygens present are NBO and BO or if some other oxygen species, e.g. triclusters, must be present.

2. Experimental Procedure

2.1 Sample Preparation

SrO was formed via decarbonating SrCO_3 in a Pt crucible at 1500°C for 20 hours. ^{17}O -enriched B_2O_3 was prepared from a BCl_3 solution and 42% ^{17}O -labeled H_2O as described previously [22]. 0.1 wt% Co_3O_4 was added to each sample to speed spin-lattice relaxation. These reagents were mixed and transferred to a 10% Au/Pt crucible. They were dried at 425°C for 1 hour followed by 200°C for 20 hours.

93
94 A glass of this composition was prepared by melting the mixture at 1080°C for 30 minutes in Ar
95 and quenched by dipping the outside of the crucible into water. Experimental glass samples were
96 examined with polarized light microscopy at 400x. All glass samples were homogenously
97 isotropic with no observed crystalline material. The glass transition temperatures of the samples
98 were determined using a differential scanning calorimeter (Netzch 404F3) with heating and
99 cooling rate of 10 K min⁻¹ in an Ar environment and were in agreement with previous published
100 results of T_g = 630 °C [23]. The measurements were checked for accuracy by comparing
101 measured values of the Netzch 0.5 mm disk sapphire standard to the SRM sapphire data reported
102 in the literature [24]. Differences in measured values were less than 3%.

103
104 A portion of the glass was then ground and crystallized by annealing at 850°C for 12 hours.
105 Crystal nucleation was facilitated by adding 1 wt% of previously synthesized strontium
106 tetraborate sample. The resulting crystal was then ground and re-annealed at 850°C for 5
107 additional hours.

108
109 Homogeneity of both the glass and crystalline samples was determined using a JEOL JXA-8230
110 SuperProbe (EPMA), using a beam current of 20 nA, beam size of 1 μm and an accelerating
111 voltage of 15 kV. The glass and crystalline samples were removed from a desiccator
112 immediately prior to the analytical session, ground and polished dry and then transferred
113 immediately into a high-vacuum evaporator for carbon coating. Compositional images were
114 obtained using backscattered electrons, calibrated wavelength dispersive (WDS) x-ray data and
115 energy dispersive (EDS) x-ray data. Samples were shown to be homogenous and at the nominal

composition within experimental error via specifying the boron composition and analyzing for strontium. Quantitative analysis of strontium within the samples was performed using the CITZAF matrix correction algorithms that are incorporated into the PROBE-PRBSE microanalysis and digital imaging software.

Compositions of both the glass and crystal samples were also analyzed via inductively coupled plasma-optical emission spectroscopy (ICP-OES) with 5 mg of sample dissolved in dilute HNO₃. Composition was compared to standards of appropriate molar concentrations. The glass was found to be 64.5% B₂O₃ and 35.5% SrO while the crystal was found to be 64.3% B₂O₃ and 35.7% SrO. The standard deviation for each sample was less than 1% of the value. These measured compositions were used for all calculations in this paper.

2.2 NMR spectroscopy

¹¹B NMR experiments were carried out using Varian/Chemagnetics T3 probes with Varian Infinity Plus 400 and Unity/Inova 600 spectrometers, at Larmor frequencies of 128.25 and 192.4 MHz, respectively. Samples, weighing 35-50 mg, were packed into 3.2 mm zirconia rotors and spun at the magic angle at 20 kHz. Chemical shifts are reported in ppm relative to 1.0 M boric acid at 19.6 ppm. A recycle delay of 0.5 s was used for both glass and crystal with a radio frequency pulse width of 0.3 μs (solid tip angle 30°, rf power 100 kHz).

¹⁷O NMR experiments were carried out using Varian/Chemagnetics T3 probes with Varian Infinity Plus 400, Unity/Inova 600 and Unity/Inova 800 spectrometers, at Larmor frequencies of 54.22, 81.34, and 108.4 MHz, respectively. ¹⁷O spectra are referenced to 20% ¹⁷O-enriched H₂O

at 0 ppm. For MAS spectra a pulse width of 0.3 μ s (solid tip angle 30°, rf power 100 kHz) was used with a recycle delay of 1 s for the glass and 5 s for the crystal.

Peak areas were determined from MAS spectra fitted with the program “DMFIT” [25] which allowed for simulated quadrupolar lineshapes with varying chemical shift and quadrupolar coupling parameters. To determine the total central transition intensity, the measured peak areas were further corrected to account for central transition intensity distributed into the spinning sidebands and to subtract the contribution of satellite sidebands under the central peak.

Multiple-quantum magic-angle spinning (MQMAS) ^{11}B and ^{17}O spectra were acquired at 9.4 and 14.1 T using a shifted-echo pulse sequence, as previously described [26]. For ^{11}B , the lengths of the triple-quantum excitation and reconversion pulses were 3.8 and 1.0 μ s, respectively, with an rf power of about 160 kHz. The soft 180° pulse, with pulse length of 32 μ s and an echotime of 1 ms, used an rf power of 15 kHz. For ^{17}O , the lengths of the triple-quantum excitation and reconversion pulses were 3.0 and 1.1 μ s, respectively, with an rf power of about 140 kHz. The soft 180° pulse, with pulse length of 23 μ s and an echotime of 1 ms, used an rf power of 12 kHz.

MQMAS NMR data were processed, including a shear transformation, using the “RMN” program (P.J. Grandinetti, Ohio State University). Apodizations were 100 Hz in the MAS dimension and 30 Hz in the isotropic (3QMAS) dimension. Two-dimensional spectra are plotted with ten contour lines between 15% and 100% of the maximum intensity.

3. Results

3.1 ^{11}B Spectra

As in previous ^{11}B MAS studies of alkali and alkaline earth borates, NMR spectra of crystalline SrB_4O_7 and of $\text{SrO}\cdot 2\text{B}_2\text{O}_3$ glass contain two separated peaks corresponding to trigonal boron, BO_3 groups, hereafter referred to as $^{[3]}\text{B}$, which are higher frequency and broader, and tetrahedral boron, BO_4 groups, hereafter referred to as $^{[4]}\text{B}$, which are lower frequency and narrower.

The crystalline strontium tetraborate spectrum, seen in Figure 1, shows a trigonal boron peak, centered at 11 ppm, corresponding to a minor SrB_2O_4 impurity phase formed as a result of volatilization of boron oxide during the crystallization process. This impurity phase corresponds to 4% of the total intensity measured by ^{11}B NMR as expected by the change in composition measured by ICP. The remainder of the ^{11}B intensity is located in the tetrahedral boron peak, centered at 0 ppm. This is in agreement with previous published crystal structures for SrB_4O_7 based on x-ray data, which contain only $^{[4]}\text{B}$ [15,27].

The ^{11}B MAS NMR spectrum of the glass of strontium tetraborate composition, $\text{SrO}\cdot 2\text{B}_2\text{O}_3$, shows two separated peaks (Figure 1). The higher frequency $^{[3]}\text{B}$ peak, centered at 13 ppm, accounts for 58.7% of the total intensity when corrected for spinning sideband contributions. The narrower $^{[4]}\text{B}$ peak, centered at 1 ppm, accounts for the remaining 41.3%.

The ^{11}B MQMAS NMR spectrum of the crystalline strontium tetraborate allowed for further separation of signal from tetrahedral boron sites, as seen in Figure 2. This is consistent with the crystal structure from Stein et al. [15], which shows two types of $^{[4]}\text{B}$ with equal-abundance, one of which links a tricluster oxygen to bridging oxygens, B1, and the other which links two

185 tricluster oxygens together, B2.

186
187 Slices were made through peaks in the spectra, and the peak maxima was used to approximate
188 the center-of-gravity in the MAS, defined by δ_{MAS} , and isotropic, defined by $\delta_{3\text{QMAS}}$, dimensions
189 [Table 1]. These were then used to yield estimates (for crystal) and mean values (for glass) of the
190 isotropic chemical shift, $\delta_{\text{iso}}^{\text{CS}}$, and quadrupolar product, $P_Q = C_Q(1+\eta^2/3)^{1/2}$, where C_Q is the
191 quadrupolar coupling constant and η is the asymmetry parameter. Assignment of sites was based
192 upon correlations between C_Q and tetrahedral distortion [28], as tested for results on crystalline
193 CaAl_4O_7 [9,29] (see ‘Discussion’).

194
195 The ^{11}B MQMAS NMR spectrum of the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass shows a single peak with mean
196 isotropic chemical shift and quadrupolar product values lower than those of B1. This can be seen
197 directly in the overlay of the two spectra showing the sum in the isotropic dimension (Figure 3).

199 3.2 ^{17}O Spectra

200 The oxygen-17 NMR spectra for crystalline SrB_4O_7 contain complex overlapping quadrupolar
201 lineshapes. Data from 9.4, 14.1 and 18.8 T was used to determine fitting parameters for four
202 distinct quadrupolar powder patterns corresponding to the four distinct types of oxygen found in
203 the published x-ray crystal structure. These components were fitted using DMFIT [25], results
204 are reported in Table 2 and shown in Figure 4. Listed in the table is the relative intensity of the
205 fitted peak in comparison to the total intensity of the SrB_4O_7 contribution to the central transition
206 peak. Also listed in Table 2 are the expected ranges of δ_{MAS} and $\delta_{3\text{QMAS}}$ for 14.1 T ^{17}O MQMAS
207 corresponding to these fitted parameters.

208

209 Site assignments were made based on relative intensities and on observation for ^{17}O data on
210 calcium aluminates that tricluster oxygens have decreased isotropic chemical shifts and increased
211 quadrupolar coupling constants when compared to bridging oxygens [9,10]. Assignments for the
212 three types of bridging oxygen were not possible. Total spectra generated using these parameters
213 are consistent with the experimental data gathered from 9.4, 14.1 and 18.8 T, as seen in Figure 5
214 with the experimental data stacked on top of the spectra generated from these parameters.

215

216 The ^{17}O MAS NMR spectra also show contributions from the minor SrB_2O_4 impurity phase (4%
217 of the total central transition peak) which is composed of equal amounts of BO and NBO. It can
218 be seen in Figure 6, in the fitted NBO peak centered at 140 ppm. The corresponding BO peak,
219 centered at 60 ppm, was subtracted from the total intensity of the central transition peak to yield
220 fitted intensity values for the other peaks corresponding solely to the central intensity
221 contribution from SrB_4O_7 , which causes a slight offset in the total fit as seen at -40 ppm in the
222 9.4 T spectrum.

223

224 In contrast to the spectrum of the crystal, the high-field ^{17}O MAS spectrum for the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$
225 glass shows two well-separated peaks lacking any singularities due to well-defined quadrupolar
226 lineshapes (Figure 6). Fitting of the two peaks present in the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ spectra, using multiple
227 Gaussian lineshapes to reproduce the asymmetrical form, shows that 9.7% of the total intensity
228 lies within the narrower, higher frequency peak corresponding to non-bridging oxygen. The
229 remaining 90.3% of the total central transition intensity falls within the region that, based upon
230 numerous previous ^{17}O studies of glasses [22,30–32] as well as our new analysis for the

crystalline strontium tetraborate, corresponds to bridging oxygens and any tricluster oxygens that may be present.

^{17}O MQMAS NMR for the crystalline strontium tetraborate, seen in Figure 7, showed minimal separation in the isotropic dimension, as expected from the $\delta_{3\text{QMAS}}$ values generated from the fitted parameters for the four oxygen components. Overlain on the contours for the crystalline spectra are lines corresponding to the expected ranges for ^{17}O MQMAS at 14.1 T for the fitted parameters, as listed in Table 2.

Slices made through the main peaks in the ^{17}O MQMAS spectrum for the glass, shown in Figure 7, allowed for determination of δ_{MAS} and $\delta_{3\text{QMAS}}$. These were then used to yield the mean values of the isotropic chemical shift, $\delta_{\text{iso}}^{\text{CS}} = -17.3$ ppm and quadrupolar product, $P_Q = 4.4$ MHz.

4. Discussion

4.1 ^{11}B NMR

The ^{11}B MQMAS of the crystalline SrB_4O_7 is quite similar to that of the isostructural $\beta\text{-SnB}_4\text{O}_7$, where the authors found two distinct ^{11}B sites in the crystal with similar locations in the MAS dimension and separation in the isotropic dimension, one with $\delta_{\text{iso}} = 3.4$ ppm and $C_Q = 0.7$ MHz and the other with $\delta_{\text{iso}} = 4.6$ ppm and $C_Q = 1.1$ MHz [20]. No attempt was made in that paper to assign the peaks to the two known boron sites.

To refine this distinction between the two boron sites in the SrB_4O_7 crystal structure we compared our results to ^{27}Al NMR data for the tricluster-containing calcium aluminates studied

by Stebbins et al. [9] and Skibsted et al. [29]. Single crystal NMR studies of aluminate and aluminosilicates by Ghose et al. 1973 [28] established a rough positive dependence of C_Q upon the shear strain for AlO_4 groups, ψ , as dictated by the O-Al-O bond angles using the formula $\psi = \sum |\tan(\theta_1 - \theta_0)|$, where θ_1 is the measured O-Al-O bond angle and θ_0 is the ideal tetrahedral bond angle, 109.5° . From this correlation, it is possible to assign sites from the data reported in Stebbins et al. [9] for the crystalline $CaAl_4O_7$. From the published crystal structure of grossite [33] there are two types of ^{41}Al , where Al(1), with one tricluster neighbor (analogous to B1 in SrB_4O_7) has a ψ value of 0.29 and Al(2), with two tricluster neighbors (analogous to B2 in SrB_4O_7) has a ψ value of 0.49. The trend in Ghose et al. 1973 [28] suggests that the two observed values of C_Q of 6.25 MHz and 9.55 MHz for grossite, should therefore be assigned to Al(1) and Al(2), respectively, as originally inferred by these authors and by Skibsted [29] based on qualitative considerations.

If we use this same parameter for the crystal structure of β - SnB_4O_7 [20], we find ψ values of 0.08 and 0.31 for the one-tricluster neighbor B1 and two-tricluster neighbor B2 sites, respectively. The crystal structure of SrB_4O_7 [15], yields very similar ψ values of 0.09 for B1 and 0.32 for B2. The trend predicted by Ghose [28], and seen in the tricluster-containing $CaAl_4O_7$ [9], would therefore indicate that the site with the lower measured P_Q value corresponds to the site with lower strain, B1, and the higher P_Q value to B2 in both β - SnB_4O_7 and SrB_4O_7 .

One striking difference between the ^{11}B MAS NMR spectra for the crystalline SrB_4O_7 and $SrO \cdot 2B_2O_3$ glass is the shift of the center of gravity of the ^{41}B peak to higher frequency in the glass as opposed to the crystalline compound. This can be explained by looking at the next

nearest neighbors for these ^{11}B . In the crystal all ^{11}B only have ^{11}B next nearest neighbors, whereas in the glass a large percentage of ^{11}B are likely to have ^{13}B next nearest neighbors. The resulting shift in δ_{MAS} leads to the marked differences in $\delta_{3\text{QMAS}}$, which in combination with the shift in P_Q associated with changes in bond distances and angles, can be seen clearly in the ^{11}B MQMAS spectra for the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass.

The isotropic dimension projections (sums) for ^{11}B MQMAS spectra also show dramatic differences between the SrB_4O_7 crystal and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass (Figure 3). In the isotropic dimension for the crystal, two peaks are clearly defined as a result of C_Q differences resulting from the number of neighboring tricluster oxygens connected to B1 and B2. In the glass these peaks are not clearly defined and there is a noticeable chemical shift difference in the isotropic dimension of the glass in comparison to the crystalline SrB_4O_7 , likely tied to the presence of ^{13}B in the glass.

The ^{11}B MQMAS “signature” of B bonded to tricluster oxygen is not distinctive enough to precisely constrain tricluster concentrations, if any, in the glass. However, the sum of the isotropic projection of the spectrum of the crystal compared to that of the glass does show overlap in the area assigned to B1. This indicates the possibility of the presence of some amount of boron atoms in the glass which are similarly influenced by connection to a tricluster oxygen.

4.2 ^{17}O NMR

^{17}O MAS NMR has previously been used to characterize OAl_3 oxygen triclusters by examining aluminate crystals to determine the expected locations of NMR signals for such species in

spectra of aluminosilicate glasses. Stebbins et al. [9] suggested the possible presence of minor amounts of triclusters in Ca-aluminosilicate glasses due to some intensity in the region of the spectrum corresponding to triclusters in grossite but this conclusion was not definitive. Iuga et al. [10] used high-resolution heteronuclear $\{^{17}\text{O}\}^{27}\text{Al}$ HMQC NMR to directly observe the tricluster site in crystalline CaAl_4O_7 and an area of high intensity in the corresponding region of a glass of CaAl_2O_4 composition. This study was aided by the fact that the MAS peak associated with the bridging oxygen in this system is exceptionally narrow, due to the absence of Si, allowing for the signal for tricluster oxygens to be directly observed.

In the crystalline strontium tetraborate the isotropic chemical shifts for the three bridging oxygens and the tricluster oxygens overlap to great extent. However, the tricluster oxygen has a significantly higher C_Q than any of the bridging oxygens, leading to a distinctive feature in the low frequency end of the spectra, clearly seen around 35 ppm in the 18.8 T spectra (Figure 4). This feature can be used to define an upper limit on a tricluster component in the glass that has similar parameters to the tricluster oxygen in the crystal. The glass spectrum shows an increase in isotropic chemical shift in comparison to the crystal, due to the presence of ^{13}B in the glass leading to a high abundance of bridging oxygens with $^{13}\text{B}-\text{O}-^{14}\text{B}$ as opposed to the $^{14}\text{B}-\text{O}-^{14}\text{B}$ present for all BO in the crystal. However, there remains an area of intensity in the glass corresponding to this characteristic tricluster “shoulder”, as can be seen by the comparison of the 18.8 T ^{17}O MAS NMR shown in Figure 6. While not a definitive constraint, the area of intensity in the glass spectra corresponding to the low frequency portion of the tricluster oxygen in the crystal spectra would place an upper limit of tricluster oxygens at around 3% of the total oxygens of the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass.

The possibility of a few percent of triclusters within the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass is further seen by overlapping the ^{17}O MQMAS spectra for the crystal and the glass. The MQMAS spectrum of the crystal, Figure 7, shows an area of intensity attributed solely to the tricluster oxygen, located at - 50 ppm in the isotropic dimension and 13-35 ppm in the MAS dimension. While an area of equally high intensity is not expected to be, and is not, present in the glass MQMAS spectrum there could be a small amount of intensity in this area, not visible at the 15% intensity cutoff for the plotted contours in the MQMAS data at 14.1 T, in Figure 7, but seen in the MAS spectrum. Intensity in the area attributed solely to the tricluster oxygen can also be seen in ^{17}O MQMAS at 9.4 T, though inherent problems with signal to noise in that experiment yielded challenges for quantification of this site.

4.3 Tricluster Oxygens in $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass

Triclusters are not expected in large quantities in the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass due to the presence of 56% ^{13}B , and therefore a large decrease in the probability of three ^{13}B connected to a single oxygen. There however remains questions as to whether a small percentage of tricluster oxygens can be present in the glass.

Previous studies have looked at the amount of NBO calculated from glass composition and ^{11}B NMR in comparison to that directly measured by ^{17}O NMR to observe discrepancies in the calculated percentage of NBO suggested by classical glass models [22]. To achieve a high level of accuracy, these calculations need glass composition to be constrained by chemical analysis of the sample and NMR spectra with high levels of signal to noise, as is the case in this study.

Fitting of the ^{11}B MAS NMR spectrum of the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass allowed for the determination of the relative amount of tetrahedral boron in the glass, defined as $N_4 = [^4]\text{B}/([^3]\text{B} + [^4]\text{B})$. From this value and the value of ratio of modifier oxide to boron oxide, defined in this system as $R = \text{SrO}/\text{B}_2\text{O}_3$ and determined from ICP measurements, it is possible to calculate the amount of NBO that would be expected in a glass of this composition if no triclusters are present as $\text{NBO} = 2(R - N_4)/(3 + R)$ [22]. In the case of the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass, with $N_4 = 0.413$ and $R = 0.55$, this method predicts $7.7 \pm 0.2\%$ NBO. ^{17}O MAS NMR of the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass allows for direct measurement of the area of the central transition NBO peak, centered at 143 ppm. This value was found to be $9.7 \pm 0.2\%$ NBO. The 2% discrepancy in the directly measured NBO as compared to that calculated by models that include no tricluster oxygens suggests the presence of a small, but statistically significant, amount of triclusters in the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass.

5. Conclusions

From direct observation, there are large structural differences between crystalline SrB_4O_7 and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass, as can be seen through shifts in both boron-11 and oxygen-17 NMR spectra, indicating significant changes in speciation and network connectivity. This acts as a reminder that modeling glass structure on isostructural crystals is not always the most accurate approach. However, the results of the experimental data presented in this paper do suggest the presence of a small amount of oxygen triclusters in the $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass, a structural motif which is not typically accounted for in traditional models of glass structure. A direct comparison of the amount of NBO in the glass, as measured by ^{17}O NMR, to the amount of NBO predicted by

structural models that assume no triclusters shows that there is 2% more NBO in the glass than would be predicted, suggesting the presence of a small amount of tricluster oxygens. This possibility can also be seen via comparison of the intensity found in the ^{11}B MQMAS spectra of crystalline SrB_4O_7 and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass and is further confirmed by direct observation of locations of NMR signal in the ^{17}O MAS and MQMAS spectra of crystalline SrB_4O_7 that are attributed to the tricluster site and the presence of a small amount of intensity in these locations in the corresponding glass spectra.

The presence of oxygen triclusters in glasses is important to consider for refining current models of borate glass structure, given that the addition of NBO in the network structure of glasses that contain tricluster oxygens can play an important role in the physical properties of the glass. In light of previous studies showing that boron coordination increases with pressure in borate glasses [34] as well as the presence of BO_4 triclusters in high pressure crystalline B_2O_3 [35], it may be important to consider and study the impact of the presence of tricluster oxygens in densified, boron-rich glasses.

384 **Acknowledgements:**

385 This work was supported by the National Science Foundation grants DMR-0904094 and DGE-
386 114747 in addition to a Eugene Holman Stanford Graduate Fellowship awarded to ML. The
387 authors thank Dr. Corey Liu and Professor Jodi Puglisi for access to the 18.8 T NMR
388 spectrometer in the Stanford Magnetic Resonance Laboratory. We also thank Dr. Namjun Kim
389 for assistance with ^{17}O MQMAS NMR data.

390

References:

- [1] S.K. Lee, J. Phys. Chem. B. 108 (2004) 5889.
- [2] S.K. Lee, J.F. Stebbins, Geochim. Cosmochim. Acta. 70 (2006) 4275.
- [3] J. Krogh-Moe, J. Non. Cryst. Solids. 1 (1969) 269.
- [4] E.D. Lacy, Phys. Chem. Glas. 4 (1963) 234.
- [5] M.J. Toplis, D.B. Dingwell, K.-U. Hess, T. Lenci, Am. Mineral. 82 (1997) 979.
- [6] J. Kubicki, M.J. Toplis, Am. Mineral. 87 (2002) 668.
- [7] J.F. Stebbins, Z. Xu, Nature. 390 (1997) 2041.
- [8] J.F. Stebbins, J. V. Oglesby, S.K. Lee, Chem. Geol. 174 (2001) 63.
- [9] J.F. Stebbins, J. V. Oglesby, S. Kroeker, Am. Mineral. 86 (2001) 1307.
- [10] D. Iuga, C. Morais, Z. Gan, D.R. Neuville, L. Cormier, D. Massiot, J. Am. Chem. Soc. 127 (2005) 11540.
- [11] P. Becker, Adv. Mater. 10 (1998) 979.
- [12] F. Pan, G. Shen, R. Wang, X. Wang, D. Shen, J. Cryst. Growth. 241 (2002) 108.
- [13] S. Block, A. Perloff, C.E. Weir, Acta Crystallogr. 17 (1964) 314.
- [14] A. Perloff, S. Block, Acta Crystallogr. 20 (1966) 274.
- [15] W.-D. Stein, J. Liebertz, P. Becker, L. Bohatý, M. Braden, Eur. Phys. J. B. 85 (2012) 236.
- [16] D.L. Corker, A. M. Glazer, Acta Crystallogr. Sect. B Struct. Sci. 52 (1996) 260.
- [17] K.-I. Machida, G.-Y. Adachi, J. Shiokawa, J. Acta Crystallogr. Sec. B. 36 (1980) 2008.
- [18] H. Huppertz, Z. Naturforsch. 58b (2003) 278.
- [19] H. Emme, M. Weil, H. Huppertz, Z. Naturforsch. 60b (2005) 815.
- [20] J. Knyrim, F.M. Schappacher, R. Pöttgen, J. Schmedt auf der Gunne, D. Johrendt, H. Huppertz, Chem. Mater. 19 (2007) 254.
- [21] W.J. Dell, P.J. Bray, Phys. Chem. Glas. 23 (1982) 98.

- [22] J.F. Stebbins, P. Zhao, S. Kroeker, *Solid State Nucl. Magn. Reson.* 16 (2000) 9.
- [23] M. V. Shankar, K.B.R. Varma, *J. Mater. Sci. Lett.* 15 (1996) 858.
- [24] K.M. Krupka, R.A. Robie, B.S. Hemingway, *Am. Mineral.* 64 (1979) 86.
- [25] D. Massiot, F. Fayon, M. Capron, I. King, S. Le Calve, B. Alonso, et al., *Magn. Reson. Chem.* 40 (2002) 70.
- [26] S. Wang, J.F. Stebbins, *J. Am. Ceram. Soc.* 28 (1999) 1519.
- [27] J. Krogh-Moe, *Acta Chem. Scand.* 18 (1964) 2055.
- [28] S. Ghose, T. Tsang, *Am. Mineral.* 58 (1973) 748.
- [29] J. Skibsted, E. Henderson, H. Jakobsen, *Inorg. Chem.* 32 (1993) 1013.
- [30] S. Kroeker, J.F. Stebbins, *Inorg. Chem.* 40 (2001) 6239.
- [31] J.F. Stebbins, J. Wu, L.M. Thompson, *Chem. Geol.* 346 (2013) 34.
- [32] A.M. George, S. Sen, J.F. Stebbins, *Solid State Nucl. Magn. Reson.* 10 (1997) 9.
- [33] V.I. Ponomarev, D.M. Kheiket, N.V. Belov, *Sov. Phys. - Crystallogr.* 15 (1971) 995.
- [34] L.-S. Du, J.R. Allwardt, B.C. Schmidt, J.F. Stebbins, *J. Non. Cryst. Solids.* 337 (2004) 196.
- [35] C.T. Prewitt, R.D. Shannon, *Acta. Cryst. B* 24 (1968) 869.

Table 1. Site parameters from ^{11}B MQMAS. B1 and B2 correspond to crystallographic site labels [15].

Site	$\delta_{3\text{QMAS}}(\text{ppm})$	$\delta_{\text{MAS}}(\text{ppm})$	$\delta_{\text{iso}}^{\text{cs}}(\text{ppm})$	$P_{\text{Q}}(\text{MHz})$
B1	1	-0.25	0.20	0.82
B2	3.5	-0.25	0.94	1.32
Glass	0.5	0	0.15	0.46

Table 2. Site parameters based upon spectral fitting using DMFIT of 9.4, 14.1 and 18.8 T ^{17}O MAS NMR spectra. Site number corresponds to those listed in Figure 4; except for the tricluster (O4), these do not necessarily correspond to the crystallographic site labels. Also listed are ranges of $\delta_{\text{MAS}}(\text{ppm})$ and $\delta_{3\text{QMAS}}(\text{ppm})$ corresponding to expected locations in 14.1 T ^{17}O MQMAS from these fitted parameters, shown in Figure 7.

Site	$C_{\text{Q}}(\text{MHz})$	η	$\delta_{\text{iso}}(\text{ppm})$	% intensity	assignment	$\delta_{\text{MAS}}(\text{ppm})$	$\delta_{3\text{QMAS}}(\text{ppm})$
1	5.50 ± 0.01	0.42	79.8 ± 0.2	28.84 ± 0.4	BO	50-77	-53.1
2	5.60 ± 0.01	0.25	78.2 ± 0.6	14.42 ± 0.1	BO	40-70	-52.4
3	5.55 ± 0.05	0.65	72.1 ± 0.1	27.78 ± 0.8	BO	35-70	-49.7
4	6.60 ± 0.01	0.2	68.0 ± 0.1	28.95 ± 0.4	tricluster	13-63	-50.2

Figure Captions:

Figure 1. ^{11}B MAS NMR spectrum acquired at 14.1 T of crystalline SrB_4O_7 and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass. Spinning sidebands are outside the displayed regions. Peak at 11 ppm in crystalline SrB_4O_7 spectra corresponds to a minor SrB_2O_4 impurity phase.

Figure 2. ^{11}B MQMAS spectrum for the crystalline SrB_4O_7 and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass acquired at 14.1 T. Only the region for ^{14}B is shown.

Figure 3. Sum of isotropic dimension projections from ^{11}B MQMAS spectrum for crystalline SrB_4O_7 and $\text{SrO} \cdot 2\text{B}_2\text{O}_3$ glass. Only the region for ^{14}B is shown.

Figure 4. ^{17}O MAS spectra of strontium tetraborate crystal acquired at 18.8 T. Sites labeled on the spectra correspond to those listed in Table 1: except for the tricluster (O4), these do not necessarily correspond to the crystallographic site labels.

Figure 5. ^{17}O MAS experimental spectra (upper) of crystalline strontium tetraborate acquired at 9.4, 14.1 and 18.8 T with calculated total spectra (lower) at each field using parameters listed in Table 2.

Figure 6. ^{17}O MAS spectra of strontium tetraborate crystal and glass acquired at 18.8 T. Peak centered at 140 ppm in crystal spectra corresponds to NBO of the SrB_2O_4 impurity.

415 Figure 7. ^{17}O MQMAS spectrum for the strontium tetraborate crystal and glass acquired at 14.1
416 T. Lines on crystal spectra show expected locations for, from left to right, oxygen sites 3, 4
417 (tricluster), 2, and 1 as defined in Figure 4 and Table 2.

Figure 1.

Figure 2.

Figure 3.

Figure 4.

Figure 5.

Figure 6.

Figure 7.