Effect of thermal annealing on the blue luminescence of amorphous silicon oxycarbide films

Zhenxu Lin^{a), b)}, Yanqing Guo^{a),*}, Jie Song^{a)}, Yi Zhang^{a), b)}, Chao Song^{a)}, Xiang Wang^{a)}, and Rui Huang^{a)}

a) Department of Physics and Electronic Engineering, Hanshan Normal University, Chaozhou, Guangdong 521041, China

b) Institute of Nanoscience and Nanotechnology, Central China Normal University, Wuhan 430079, China

**yqguo126@126.com*

Abstract

Amorphous silicon oxycarbide ($a\text{-SiC}_x\text{O}_y$) films that displayed blue luminescence were fabricated using very high frequency plasma-enhanced chemical vapor deposition (VHF-PECVD) at a temperature of 250 °C. The effects of thermal annealing on the photoluminescence (PL) were investigated. Thermal annealing at 600 °C resulted in a remarkable enhancement in the blue PL, which was clearly observed with the naked eyes in a bright room. The blue PL featured an excitation wavelength independent recombination dynamic on a nanosecond timescale. Neither Si nor SiC quantum dots were present in the annealed films as revealed by transmission electron microscopy. The PL results, combined with an analysis of the chemical bonds present in the films, revealed the origin of the blue PL was largely due to electron-hole pair recombination through Si-related neutral oxygen vacancy defect centers.

Keywords: silicon oxycarbide, photoluminescence, PECVD

1. Introduction

Silicon-based light-emitting materials have attracted attention over the past decade for their potential as next-generation Si photonics. Silicon-based materials, including silicon nitride (SiN_x) [1-3], silicon oxide (SiO_x) [4-10], silicon oxynitride (SiN_xO_y) [11-14], and silicon oxycarbide (SiC_xO_y) [15-18], show promise as CMOS-compatible integrated light sources. Thus, significant research efforts have been devoted to understand and optimize their structural and optical properties. SiC_xO_y generally features strong white light emission and is regarded as a promising host matrix for rare earth [16-20]. It has been reported that SiC_xO_y is more effective at enhancing the mobility and solubility of Eu^{2+} ions than is SiO_x , and thus significantly increases the PL intensity of Eu^{2+} [19]. Furthermore, the effective excitation cross section of Er, in Er-doped amorphous SiC_xO_y , is four orders of magnitude larger than that when Er is excited directly. This is a result of energy transfer between the band edges or defect levels of a- SiC_xO_y and Er ions [20]. Efficient PL from SiC_xO_y systems has been studied, although progress is slow. This is, in part because of a lack of information available to correlate the PL to other influences.

Previously, we reported that the strong light emission observed from a- SiC_xO_y films can be tuned from yellow to blue by modulating the oxygen content in the films [21]. In the present work, the effect of thermal annealing on the blue luminescence of a- SiC_xO_y films was investigated. Thermal annealing at 600 °C was found to significantly enhance the blue PL. The PL featured a wavelength independent recombination dynamic on a nanosecond timescale. The origin of the blue PL was

postulated by combining the PL results with an analysis of the microstructure and the chemical bonds within the films.

2. Experimental

a-SiC_xO_y films with a thickness of 450 nm were prepared using VHF-PECVD with a gas mixture of SiH₄, CH₄, and O₂ at flow rates of 2.5, 10, and 1.2 sccm, respectively. During the growth process, the radio frequency power, chamber pressure, and substrate temperature were 30 W, 20 Pa, and 250 °C respectively. The detailed experiment was described in previous work [21]. The as-deposited samples were dehydrogenated at 400 °C for 1 h. The samples were then annealed in a conventional furnace under a nitrogen atmosphere at 500, 600, or 700 °C for 1 h. The PL measurements were performed at ambient temperature using a Jobin Yvon fluorolog-3 spectrophotometer equipped with a 450 W steady Xe lamp. PL time decay measurements were recorded using an Edinburgh FLS980 spectrometer. The band gaps of the samples were determined using optical absorption measurements performed on a Shimadzu UV-3600 spectrophotometer on quartz samples. The microstructures of samples were characterized using a JEOL high-resolution transmission electron microscope (TEM). The Si, O and C elemental compositions within the samples were estimated using X-ray photoelectron spectroscopy (XPS). The local atomic environment and bonding configuration within the samples were recorded using Fourier transform infrared (FTIR) spectroscopy.

3. Result and discussion

The PL spectra of the as-deposited and annealed samples are shown in Fig. 1. The spectrum of the as-deposited sample displayed a broad band centered at approximately 475 nm. This broad band can be deconvoluted into a strong blue Gaussian band and a weak orange Gaussian band. The integrated intensity and the full wide at half of maximum (FWHM) of the decomposed blue and orange Gaussian bands were summarized in Table I. From Fig. 1, one can see that the blue band was found to gradually shift from 475 nm to 420 nm as the annealing temperature was increased to 600 °C. This blueshift was accompanied by a significant enhancement of the PL intensity. Thermal annealing of the films at 600 °C was found to significantly enhance the integrated PL intensity I_{PL} of the blue PL by more than two times when compared with the as-deposited sample, as shown in Table I. Notably, the strong white light emission from the sample annealed at 600 °C could be clearly observed with the naked eye in a bright room when excited with a wavelength of 325 nm from Xe lamp, Fig. 1 (inset). However, as the annealing temperature was increased to 700 °C, the intensity of blue PL dropped dramatically, while the orange band centered at approximately 625 nm become dominant. From Table I, one can also seen that the FWHM of the blue band decreased sharply with the increase of annealing temperature, while that of the orange band increased and saturated at the annealing temperature of 500 °C.

The optical band gap energies (E_{opt}) of the samples were determined using the absorption profiles and the Tauc equation $(\alpha h\nu)^{1/2} = B(h\nu - E_{opt})$, where α is the absorption coefficient and $h\nu$ is the photon energy [22], Fig. 2 (inset). The energy of

the PL peaks, and the corresponding E_{opt} values, for the films annealed at different temperatures are shown in Fig. 2. From Fig.2, one can see that the behavior of the PL peak energy for both deconvoluted bands with the annealing temperature exhibit a similar tendency to the E_{opt} . The energy of the PL peak was lower than the corresponding E_{opt} value, indicating that the PL of the samples did not originate from band to band recombination. This conclusion was supported by the absence of any Si or SiC nanocrystals within the sample annealed at 700 °C, when observed using cross-sectional high-resolution TEM (Fig. 3). To understand the origins of PL emission, the samples were excited at different wavelengths, as displayed in Fig. 4. The PL peak position observed for all samples were independent of the excitation wavelengths. This PL behavior was similar to that of the defect-related PL in which the PL peak position is independent of the excitation wavelength because of a narrow distribution of defect-related localized states [23]. This result suggested that the PL may originate from defect-related luminescence centers.

To elucidate the nature of the blue light emission in the $a\text{-SiO}_x\text{C}_y$ films, the PL lifetime of the samples were measured. The blue PL decay traces from the as-deposited and annealed samples are shown in Fig. 5. The decay traces fit the double exponential decay function:

$$I(t)=I_0+I_1 * \exp(-t/\tau_1)+ I_2 * \exp(-t/\tau_2),$$

where I_0 is the background level, I_i and τ_i ($i = 1,2$) are the amplitude and lifetime of each exponential decay component, respectively [23]. Fig. 5 shows that the blue luminescence lifetime τ of all samples contained both a fast decay component τ_1 (1.27

ns) and a long decay component τ_2 (in the range of 6.53–5.48 ns depending on the annealing temperature). The dynamic behavior of the luminescence was consistent with that observed in defect-related Si-based materials such as SiN_xO_y and SiO_x , indicating the blue band observed in our samples originated from defect states. Additionally, the fast luminescence lifetimes τ_1 determined for the samples were close to that reported by Pellegrino et al. and Nikas et al. where the PL was suggested to originate from C-related neutral oxygen vacancy (NOV) defect centers resulting from the weaker spin-orbit coupling strength of C (lower atomic number) [24, 25]. The longer luminescence lifetimes τ_2 observed from the a- SiO_xC_y films were similar to that reported by Lin [26] where the PL was ascribed to NOV defect centers in amorphous SiO_x . Therefore, the blue light emission observed from a- SiO_xC_y films may originate from C-related NOV defect centers and/or Si-related NOV defect centers.

FTIR absorption spectra for the samples are shown in Fig. 7. The spectrum of the as-deposited sample displayed distinct stretching modes at approximately 795 and 1020 cm^{-1} characteristic of Si-C and Si-O-Si bonds, respectively [27]. The shoulder on the high frequency side of the Si-O-Si mode (approximately 1260 cm^{-1}) was attributed to Si-CH₃ stretching mode[27], while the bands at approximately 2160 cm^{-1} and 2950 cm^{-1} are characteristic of Si-H and C-H stretching modes, respectively [28, 29]. The intensity of the Si-O-Si bond stretching mode increased as the annealing temperature was increased. In contrast, the intensity of hydrogen-related absorption modes dropped as the annealing temperature was increased. The hydrogen-related

absorption modes for the sample annealed at 700 °C diminished while the absorption peaks due to and Si-O-Si bonds became sharp and shifted to approximately 1040 cm⁻¹. Additionally, a distinct absorption peak located at approximately 437 cm⁻¹, characteristic of a Si-O-Si rocking mode, was observed [30]. These results indicated that the Si-H bonds broke and transformed into Si-O bonds after experiencing the high temperature annealing process. Compared Fig. 1 with Fig. 7, one can find that the intensity of the blue PL exhibits a similar tendency to the intensity of Si-O-Si bond stretching modes for the samples annealed below 700 °C. Therefore, it is suggested that the increase of the blue emission intensity is closely related to the chemical bond reconstruction, particularly the increase in concentration of Si-O bonds.

XPS was used to probe the chemical environment of the Si, C and O in the samples. The ratio of Si, C and O in the as-deposited sample was found to be 30.28%, 34.27%, and 34.43%, respectively. Thus, the dominant phase in the as-deposited sample was a C-rich SiC_{1.13}O_{1.14} (SiC-like) phase. This suggested that oxygen defect centers, such as NOV, can be formed in C-rich SiC_xO_y films due to a deviation from a perfect stoichiometry. The C content of the sample annealed at 500 °C decreased to 25.69%, while the content of Si and O increased to 38.53% and 34.79%, respectively. Therefore, the density of C-related NOV defect centers should decrease as a result of the lower C content. However, the PL intensity of the sample annealed at 500 °C increased significantly. This suggested that the blue light emission observed from the a-SiO_xC_y films originated mainly from Si-related NOV defect centers, which well

explain the correlation observed between the PL intensity and Si-O-Si stretching mode with increasing annealing temperatures (below 700 °C). We found that the dominant phase within the samples annealed at 700 °C became O-rich $\text{SiC}_{0.42}\text{O}_{1.33}$ (SiO_2 -like) due to the elimination of C atoms [31]. This was also confirmed by FTIR spectroscopy as the peaks for the Si-O-Si bond stretching modes increased in intensity and displayed a blueshift. The SiO_2 -like sample exhibited weak orange light emission with the FWHM of 190 nm, as shown in Fig. 1 and Table I. In addition, the SiO_2 -like sample featured a fast decay dynamic with nanosecond lifetimes, as revealed in Fig. 7. Thus, combining with the work of Skuja et al. [32], the orange band were temporarily ascribed to non-bridging oxygen hole centers in silicon oxide.

4. Conclusion

In summary, the effect of thermal annealing on the blue PL of a- SiC_xO_y films has been investigated. Thermal annealing of the films was found to significantly enhance the intensity of the blue PL by more than four times when compared with the as-deposited sample. The blue PL featured an excitation wavelength independent recombination dynamic on a nanosecond timescale. Using a combination of PL experiments, cross-sectional high-resolution TEM and an analysis of the chemical bonds within the films, the origin of blue emission was found to be from radiative recombination through Si-related NOV's defect centers.

Acknowledgments

This work was supported by National Natural Science Foundation of China (Nos.

61274140 and 61306003).

References

- [1] L. Pavesi, L. Dal Negro, C. Mazzoleni, G. Franzo, F. Priolo, Optical gain in silicon nanocrystals, *Nature*. 408 (2000) 440-444.
- [2] G. R. Lin, C. K. Lin, L. J. Chou, Y. L. Chueh, Synthesis of Si nanopyramids at SiO_x/Si interface for enhancing electroluminescence of Si-rich SiO_x , *Appl. Phys. Lett.* 89 (2006) 093126-093126-3.
- [3] D. Chen, Y. Liu, J. Xu, D. Wei, H. Sun, L. Xu, T. Wang, W. Li, K. Chen, Improved emission efficiency of electroluminescent device containing nc-Si/ SiO_2 multilayers by using nano-patterned substrate, *Opt. Express*. 18 (2010) 917-922.
- [4] K. Chen, X. Huang, J. Xu, D. Feng, Visible photoluminescence in crystallized amorphous Si:H/ SiN_x :H multiquantum-well structures, *Appl. Phys. Lett.* 61 (1992) 2069-2071.
- [5] N. M. Park, C. J. Choi, T. Y. Seong, S. J. Park. Quantum confinement in amorphous silicon quantum dots embedded in silicon nitride, *Phys. Rev. Lett.* 86 (2001) 1355-1357.
- [6] L. Dal Negro, J. H. Yi, L. C. Kimerling, S. Hamel, A. Williamson, G. Galli, Light emission from silicon-rich nitride nanostructures, *Appl. Phys. Lett.* 88 (2006) 183103-183103-3.
- [7] R. Huang, J. Song, X. Wang, Y. Q. Guo, C. Song, Z. H. Zheng, X. L. Wu, and P. K. Chu, Origin of strong white electroluminescence from dense Si nanodots embedded in

silicon nitride, Opt. Lett. 37 (2012) 692–694.

[8] F. Wang, D. Li, D. Yang, Q. Que, Tailoring effect of enhanced local electric field from metal nanoparticles on electroluminescence of silicon-rich silicon nitride, IEEE J Sel. Topics Quantum. Electron. 19 (2013) 4602504.

[9] C Liu, C Li, A Ji, L Ma, Y Wang, Z Cao, Exploring extreme particle density and size for blue photoluminescence from as-deposited amorphous Si-in-SiN_x films, Appl. Phys. Lett. 22 (2005) 223111–223111-3.

[10] R. Huang, Z. Lin, Z. Lin, C. Song, Y. Guo, X. Wang, J. Song, Suppression of Hole Overflow and Enhancement of Light Emission Efficiency in Si Quantum Dots based Silicon Nitride Light Emitting Diodes, IEEE J Sel. Topics Quantum. Electron. 20 (2014) 8200306.

[11] R. Huang, K. Chen, B. Qian, S. Chen, W. Li, J. Xu, Z. Ma and X. Huang, Oxygen induced strong green light emission from low-temperature grown amorphous silicon nitride films, Appl. Phys. Lett. 89 (2006) 221120-221120-3.

[12] X. Wang, R. Huang, C. Song, Y. Guo, and J. Song, Effect of barrier layers on electroluminescence from Si/SiO_xN_y multilayer structures, Appl. Phys. Lett. 102 (2013) 081114.

[13] P. Zhang, K. Chen, H. Dong, P. Zhang, Z. Fang, W. Li, J. Xu, X. Huang, Higher than 60% internal quantum efficiency of photoluminescence from amorphous silicon oxynitride thin films at wavelength of 470 nm, Appl. Phys. Lett. 105 (2014) 011113.

[14] Z. Lin, R. Huang, Y. Guo, C. Song, Z. Lin, Y. Zhang, X. Wang, J. Song, H. Li and X. Huang, Near-infrared light emission from Si-rich oxynitride nanostructures,

Opt. Mater. Express. 4 (2014) 816.

[15] J Wang, V Suendo, A Abramov, L Yu, P R i Cabarrocas, Strongly enhanced tunable photoluminescence in polymorphous silicon carbon thin films via excitation-transfer mechanism. Appl. Phys. Lett. 22 (2010) 221113–221113-3.

[16] A. Pérez-Rodríguez, O. Gonzalez-Varona, B. Garrido, P. Pellegrino, J. R. Morante, C. Bonafos, M. Carrada, A. Claverie, White luminescence from Si⁺ and C⁺ ion-implanted SiO₂ films, J. Appl. Phys. 94 (2003) 254-262.

[17] Y. Ding, H. Shirai, D. He, White light emission and electrical properties of silicon oxycarbide-based metal–oxide–semiconductor diode, Thin Solid Films. 519 (2011) 2513.

[18] S. Y. Seo, J. H. Shin, Enhancement of the green, visible Tb³⁺ luminescence from Tb-doped silicon-rich silicon oxide by C co-doping, Appl. Phys. Lett. 84 (2004) 4379-4381.

[19] S. Boninelli, G. Bellocchi, G. Franzò, M. Miritello, F. Iacona, New strategies to improve the luminescence efficiency of Eu ions embedded in Si-based matrices, J. Appl. Phys. 113 (2013) 143503.

[20] S. Gallis, M. Huang, A. E. Kaloyeros, Efficient energy transfer from silicon oxycarbide matrix to Er ions via indirect excitation mechanisms, Appl. Phys. Lett. 90 (2007) 161914-161914-3.

[21] Z. Lin, Y. Guo, C. Song, J. Song, X. Wang, Y. Zhang, R. Huang. Influence of the oxygen content in obtaining tunable and strong photoluminescence from low-temperature grown silicon oxycarbide films, J. Alloys Compd. 633 (2015)

153-156.

[22] C. Song, R. Huang, X. Wang, Y. Guo, J. Song, Y. Zhang, Z. Zheng, Effects of hydrogen on photoluminescence properties of a-SiN_x:H films prepared by VHF-PECVD, *Appl. Surf. Sci.* 258 (2011) 1290.

[23] R. Huang, Z. Lin, Y. Guo, C. Song, X. Wang, H. Lin, L. Xu, J. Song and H. Li, Bright red, orange-yellow and white switching photoluminescence from silicon oxynitride films with fast decay dynamics, *Opt. Mater. Express.* 4 (2014) 205.

[24] P. Pellegrino, A. Perez-Rodriguez, B. Garrido, O. Gonzalez-Varona, J. R. Morante, S. Marcinkevicius, A. Galeckas, J. Linnros, Time-resolved analysis of the white photoluminescence from SiO₂ films after Si and C coimplantation, *Appl. Phys. Lett.* 84 (2004) 25-27.

[25] V. Nikas, S. Gallis, M. Huang, A. E. Kaloyeros, A. P. D. Nguyen, A. Stesmans, V. V. Afanasev, The origin of white luminescence from silicon oxycarbide thin films. *Appl. Phys. Lett.* 104 (2014) 061906.

[26] G. R. Lin, C. J. Lin, K. C. Yu, Time-resolved photoluminescence and capacitance–voltage analysis of the neutral vacancy defect in silicon implanted SiO₂ on silicon substrate, *J. Appl. Phys.* 96 (2004) 3025.

[27] A. Grill, Plasma enhanced chemical vapor deposited SiCOH dielectrics: from low-k to extreme low-k interconnect materials, *J. Appl. Phys.* 93 (2003) 1785-1790.

[28] R. Huang, X. Wang, J. Song, Y. Guo, H. Ding, D. Wang, J. Xu, K. Chen, Strong orange–red light emissions from amorphous silicon nitride films grown at high pressures, *Scripta Mater.* 62 (2010) 643-645.

- [29] A. Grill, D. A. Neumayer, Structure of low dielectric constant to extreme low dielectric constant SiCOH films: Fourier transform infrared spectroscopy characterization, J. Appl. Phys. 94 (2003) 6697-6707.
- [30] S. Gallis, M. Huang, H. Efstathiadis, E. Eisenbraun, A. Kaloyeros, E. Nyein, U. Hommerich, Photoluminescence in erbium doped amorphous silicon oxycarbide thin films, Appl. Phys. Lett. 87 (2005) 091901-091901-3.
- [31] G. Bellocchi, F. Iacona, M. Miritello, T. Cesca and G. Franzò, SiOC thin films: an efficient light source and an ideal host matrix for Eu^{2+} ions, Opt. Express. 21 (2013) 20280.
- [32] L. Skuja. Optically active oxygen-deficiency-related centers in amorphous silicon dioxide. J. Non-Cryst. Solids, 239 (1998) 16-48.

Table caption

TABLE I. The integrated intensity and the full wide at half of maximum (FWHM) of the decomposed blue and orange Gaussian bands for a-SiC_xO_y films annealed at different temperatures.

Figure captions

Fig. 1. PL spectra of silicon oxycarbide samples annealed at different temperatures. The spectra were deconvoluted into a strong blue Gaussian band and a weak orange Gaussian band. The inset shows a photo of the sample annealed at 600 °C emitting light following excitation at 325 nm from a Xe lamp.

Fig. 2. Optical band gap and PL peak energy of the deconvoluted bands in a-SiO_xC_y as a function of annealing temperature. Inset shows the Tauc plot of the as-deposited sample.

Fig. 3. The cross-sectional high-resolution TEM image of the sample annealed at 700 °C.

Fig. 4. PL peak energy versus the excitation wavelength for the samples: (a) As-deposited sample, (b) the sample annealed at 500 °C, (c) the sample annealed at 600 °C, (d) the sample annealed at 700°C.

Fig. 5. Blue PL decay traces of the as-deposited sample and the samples annealed at 500 °C and 600 °C, respectively. The decay traces fit the double exponential decay function: $I(t)=I_0+I_1 * \exp(-t/\tau_1)+ I_2 * \exp(-t/\tau_2)$, where I_0 is the background level, I_i and τ_i ($i = 1,2$) are the amplitude and lifetime of each exponential decay component, respectively [23].

Fig. 6. FTIR spectra of the as-deposited and annealed samples.

Fig. 7. Orange PL decay traces of the sample annealed at 700°C.

Samples	Blue band		Orange band	
	I _{PL} (a.u.)	PL spectrum FWHM (nm)	I _{PL} (a.u.)	PL spectrum FWHM (nm)
As-deposited sample	2.2×10 ⁷	129	2.0×10 ⁷	166
Annealing at 500°C	4.2×10 ⁷	75	5.4×10 ⁷	199
Annealing at 600°C	4.5×10 ⁷	77	6.9×10 ⁷	196
Annealing at 700°C	...	...	3.6×10 ⁷	190

TABLE I

Fig. 1

Fig. 2

Fig. 3

Fig. 4

Fig. 5

Fig. 6

Fig. 7