****Displacement cascades and defect annealing in tungsten, Part II: Object kinetic Monte Carlo Simulation of Tungsten Cascade Aging**

Giridhar Nandipati^{a,1}, Wahyu Setyawan^a, Howard L. Heinisch^a, Kenneth J. Roche^{a,b}, Richard J. Kurtz^a and
Brian D. Wirth^c

^a *Pacific Northwest National Laboratory, Richland, Washington, USA*

^b *Department of Physics, University of Washington, Seattle, WA 98195, USA*

^c *University of Tennessee, Knoxville, Tennessee, USA*

ABSTRACT: The results of object kinetic Monte Carlo (OKMC) simulations of the annealing of primary cascade damage in bulk tungsten using a comprehensive database of cascades obtained from molecular dynamics [1] are described as a function of primary knock-on atom (PKA) energy at temperatures of 300, 1025 and 2050 K. An increase in SIA clustering coupled with a decrease in vacancy clustering with increasing temperature, in addition to the disparate mobilities of SIAs versus vacancies, causes an interesting effect of temperature on cascade annealing. The annealing efficiency (the ratio of the number of defects after and before annealing) exhibits an inverse U-shape curve as a function of temperature. The capabilities of the newly developed OKMC code KSOME (kinetic simulations of microstructure evolution) used to carry out these simulations are described.

I. Introduction

The operation of fusion power reactors will impose very demanding operating conditions on the plasma facing materials which must withstand severe and variable surface heat loads, damage from energetic neutrons and ions, and erosion of material by ions (or neutrals) during reactor operation. [2] Tungsten is considered the primary solid material choice for the main chamber and the divertor components in future fusion reactors due to its high melting point, low sputtering coefficient, high thermal conductivity, low transmutation probability, low tritium retention and good mechanical strength. [2, 3, 4] In a fusion environment bulk tungsten will be exposed to energetic neutrons escaping the plasma. The

** Corresponding Author

Email address: giridhar.nandipati@pnnl.gov (Giridhar Nandipati)

deuterium-tritium fusion reaction produces neutrons with a characteristic kinetic energy of 14.1 MeV. Collisions of 14.1 MeV neutrons with tungsten atoms cause radiation induced defects, transmutation and changes in microstructure, hence, degradation of its physical and mechanical properties with irradiation dose. [5] Therefore, it is important to develop predictive models of microstructure evolution for tungsten under fusion relevant conditions.

Collisions of 14.1 MeV neutrons with tungsten atoms produce tungsten primary-knock-on atoms (PKA) with various recoil energies which eventually lose their acquired kinetic energy through a sequence of collisions with other atoms, known as a displacement cascade. The cascade damage process lasts for up to tens of picoseconds as the cascade energy dissipates, and the resulting debris consists of point defects and clusters concentrated in a relatively small volume, referred to as the “primary damage region.” [6] The initial number of surviving defects created in the displacement cascade, and their size and spatial distribution in the solid will ultimately determine their effect on the irradiated microstructure,[7] as well as their subsequent reaction and diffusion kinetics as a function of time and temperature.

A common and long-standing question is how sensitive is the long-term evolution of the damage to the specific features of the primary damage defect distributions produced on picosecond time scales? [8] For example, a random distribution of Frenkel pairs compared to the heterogeneous distribution of defects produced in a cascade (as obtained from typical molecular dynamics (MD) simulations) will lead to very different damage evolution. [9, 10, 11]. The annealing simulations performed in the present study are primarily intended to evaluate how the annealing efficiency (the ratio of surviving defects after and before the annealing) depends on the morphology of the input cascade debris. The different morphologies of the input debris were obtained from MD cascade simulations at various PKA energies and temperatures. The results of single cascade annealing simulations using the OKMC method in bcc tungsten are presented here using an extensive MD database of cascades with PKA energies from 10 keV to 100 keV at temperatures of 300, 1025 and 2050 K. The OKMC simulations are intended to be an extension of MD simulations to reach a longer time-scale. Accordingly, the OKMC method is used to carry out annealing simulations at exactly the same temperature at which the cascades were generated with MD

but using a much bigger simulation box. The goal of this study is to understand how individual cascades of various energies in tungsten evolve beyond MD time-scales; especially determining what fractions of cascade defects would escape or remain in the cascade region. This paper constitutes Part II of the joint MD-OKMC cascade simulations. The results of the MD simulations are presented in a companion paper as Part I [1].

II. Kinetic Simulation of Microstructural Evolution (KSOME)

KSOME is a flexible and computationally efficient lattice-based OKMC code to simulate the long-time scale evolution of a microstructure under irradiation. Patterned after the original FORTRAN code ALSOME,[12] KSOME is significantly more sophisticated, faster and flexible. Objects of interest include vacancies, self-interstitial atoms (SIA), interstitial impurities and clusters of these defects, produced during irradiation. KSOME keeps track of the locations (more precisely their center of mass) of these objects (defects) in time. Objects or defects are characterized by their type, size, shape, position, and orientation. Significant attention has been given to make KSOME as flexible as possible. While type and size are the most commonly used parameters to describe a defect, KSOME allows use of additional parameters, if available, such as defect shape and orientation. As there is no limit to the number of parameters that may be needed to describe a defect, one goal is to enable the use of as many parameters as needed (or practical). For instance, KSOME differentiates between a $\langle 110 \rangle$ and a $\langle 111 \rangle$ dumbbell orientation of SIA, thereby allowing each to have different diffusion-reaction properties as well as transformation into one another. Orientation can also be used to represent 1D diffusion of SIAs along one of the four $\langle 111 \rangle$ directions in case of a body-centered cubic (bcc) lattice. It can even differentiate between defects with different Burgers vectors and geometries, which allows them to have different diffusion-reaction properties as well as the ability to transform into one another. For example, the code differentiates between different geometries of vacancy clusters such as voids, platelets and stacking fault tetrahedral (SFTs, for face-centered cubic (fcc) only). The present version of KSOME can deal with interactions of any combination of point defect clusters in an fcc or bcc lattice. For example, if the system includes V (vacancy), I (SIA), H (interstitial hydrogen), and He (interstitial helium) as types of point defects present in a

system, then KSOME can deal with the diffusion, emission, transformation and reaction events of those defects, including clusters of all combinations (e.g. He_mI_n , He_nV_m , H_mHe_n , H_mV_n , H_mI_n , $\text{H}_m\text{He}_n\text{I}_p$ and $\text{He}_m\text{H}_n\text{V}_p$).

In principle, the KSOME code also allows for the inclusion of extended defects such as dislocations and grain boundaries, which it presently treats as unsaturable sinks, such that any defect that is absorbed by a sink is removed from the simulation box. Free surfaces are treated as absorbing boundaries, which also act as sinks. KSOME does not have dedicated subroutines to deal with each individual type of defect, rather it is designed such that all the necessary information regarding the properties of defects such as type, size, location, orientation, anisotropy, and their diffusion-reaction processes, along with simulation parameters regarding the simulation box size, temperature and boundary conditions, are provided via text-based input files. Correspondingly, as additional information is needed and available, KSOME can be used to carry out very detailed OKMC simulations with only minimal additional work required to modify the diffusion and reaction event databases. As with all KMC approaches, much valuable information about the evolutionary path of a given system can often be obtained by determining its sensitivity to the deliberate variation of input parameter values – which is easily accomplished with KSOME.

III. Simulation Details

Simulations were performed with a cubic block of tungsten atoms having a side of length $512a$ (a is the lattice constant) or 162 nm, with each axis parallel to a $\langle 100 \rangle$ direction of the crystal. At the highest PKA energy studied here, 100 keV, the debris span distances of $75.7a$, $77.1a$ and $78.9a$ at 300 K, 1025 K and 2050 K, respectively. The chosen size of the simulation cell is large enough to capture all of the intracascade recombination events. Each defect is allowed to hop to one of eight bcc nearest neighbor lattice sites along $a/2 \langle 111 \rangle$. For the simulation of an isolated cascade in a perfect crystal, the initial SIA and vacancy defect distributions obtained from the MD cascade damage simulations were centered in the simulation cell. Absorbing boundary conditions were adopted in all three directions i.e. when a defect diffuses out of the box it is no longer tracked, and it is removed from the simulation. Employing absorbing boundary conditions enables tracking of defects, in our

case SIAs, which move far enough from the cascade region such that they can be considered spatially uncorrelated with the original cascade. The probability for these defects returning and contributing to intracascade recombination is negligible. Such defects, also sometimes called “freely migrating defects” (FMDs), are counted as escaped defects that can contribute to long-range defect migration. The fraction of FMD defects is a critical parameter in the mean field rate theory (MFRT) treatment of microstructure evolution.[13] Many major microstructural changes, such as the development of voids, dislocation networks and radiation-induced precipitation, that occur at temperatures where point defect mobility is significant, depend on long range defect migration, i.e., over distances large compared to typical primary damage dimensions of a few tens of nanometers. [7] These microstructural changes can produce macroscopic changes such as embrittlement and swelling.

The values of migration energies and pre-factors for diffusion and binding energies of defects used in the present annealing simulations are taken from the *ab initio* calculations of Becquart et al. [14] and references therein. In the present model all SIA clusters are assumed to be $\langle 111 \rangle$ loops, and the merging of two SIA clusters results immediately in the formation of a single larger $\langle 111 \rangle$ loop. SIA clusters of all sizes are considered to move with the migration energy of 0.013 eV.[15] SIA clusters larger than size five are constrained to 1D diffusion along one of four $\langle 111 \rangle$ axes. SIA clusters up to size five are allowed to change their direction of 1D motion via rotation and thereby perform mixed 1D/3D motion. The activation barrier for changing the direction of their 1D motion from one $\langle 111 \rangle$ direction to another is 0.38 eV. MD simulations do not provide information on the orientation of SIA diffusion, and since no bias was observed in the orientation of SIA clusters in the cascades obtained from MD, the direction of 1D motion was assigned randomly to the SIAs at the start of a simulation. We assume that all interstitial clusters are glissile (mobile) since there is no information available on infrequently occurring immobile SIA clusters [16, 17] in these cascades. Recently, in Fe it has been shown using a self-evolving atomistic KMC (SEAKMC) [18] method that even those clusters which appear to be sessile and stable will ultimately transform to glissile $\langle 111 \rangle$ clusters (however, this transformation happens on the time-scale of seconds which is beyond regular MD time-scales).[19] The migration/diffusion rates of SIA clusters vary with cluster size (n) according to $v_0 n^{-\alpha}$ ($v_0 =$

$6 \times 10^{12} \text{s}^{-1}, \alpha = 0.5$). We note that due to the small migration barrier of SIA clusters, the increase in their diffusion rates with temperature is very small compared to the decrease in their diffusion rates with increasing size. Therefore a change in the SIA cluster size distribution in a cascade with temperature has a greater effect on the SIA diffusion rate than the temperature.

For a single vacancy, the activation barrier for diffusion is taken as 1.66 eV, and vacancy clusters larger than five are assumed to be inactive i.e. they neither diffuse nor emit, although they interact with other defects if they are within the range of interaction. All vacancies migrate in 3D, and their diffusion rates decrease with cluster size (n) according to $n_0(q^{-1})^{n-1}$ ($v_0 = 6 \times 10^{12} \text{s}^{-1}$, $q = 1000$). Note that due to the high migration barrier and the rapid decay of the diffusion pre-factor, vacancy clusters larger than a di-vacancy are immobile even at 2050 K. The vacancy dissociation rate is given by $\Gamma_d = v_d \exp(-(E_m + E_d)/k_B T)$, where E_d is the binding energy of a vacancy to a vacancy cluster, and E_m is the migration energy of a single vacancy. The same is true for SIAs.

In OKMC simulations defects are treated as point objects with a capture radius or reaction distance. This is the distance at which a defect interacts with other defects. If the capture radii of two defects overlap, then defects are allowed to coalesce or recombine depending on their type. Also when a defect emits from a cluster it is placed outside this capture radius. Capture radius is a function of type and size of a defect and the formula were obtained from Ref. [14]. In the present simulation, due to lack of specific information about lattice distortion associated with the type and shape of a defect, it is assumed that the medium is homogenous and continuous, and that the interaction radii of the defects involved are isotropic. Other required parameters like binding energies of vacancies and SIAs were also obtained from Ref. [14].

IV. Results and Discussion

IV.1. General Details

A database of 15-20 cascades at each of the PKA energies ranging from 10 keV to 100 keV was created using MD simulations. Detailed information about how the cascade database was created, as well as the details of defect production and other additional details about the

cascades can be found in Ref.[1]. Cascades initiated in an MD simulation are allowed to evolve for about 50 ps, that is the time where the surviving point defects are so well separated such that their strain fields (capture radii) do not overlap and no further recombinations events are likely to occur during time scale of an MD simulation. Defect distributions for cascades at this stage were used as input to the OKMC simulations. If an inputted cascade has defects with overlapping capture radii, they are allowed to recombine before the simulation clock is started. Previous studies [20, 21] have shown that the results are not very sensitive to the size of the capture radii.

Two sets of clustering data were generated from the MD cascades. The first set (the default set) uses the third (NN3) and the fourth (NN4) nearest-neighbor distances to define the clusters of SIAs and vacancies, respectively. The second set of clustering data uses the second nearest neighbor distance (NN2) for both. Note that the OKMC simulations using both sets of data were carried out, and it was found that the results were similar in both cases. Irrespective of the criterion used to identify clusters, the clustering of SIAs increases with PKA energy and temperature, while the vacancy clustering increases with PKA energy but decreases significantly at the highest temperature of 2050 K. In tungsten, due to the very small change of the SIA cluster diffusion rate with temperature, clustering of SIAs and vacancies apparently have a significant effect on how cascades anneal.

For each initial MD cascade in the primary damage state, 20 OKMC aging simulations were performed with different random seeds. The results were averaged over both different cascades from the MD database and from the OKMC simulations with random seeds. Thus each data point obtained was an average over 300-400 runs. Simulations were carried out at temperatures of 300, 1025 and 2050 K for up to 10 ns. Note that 1025 K and 2050 K correspond to 0.25 and 0.5 of the melting temperature of tungsten, respectively. In addition to selecting an appropriate simulation cell size, the length of simulation time should be long enough that it captures almost all intracascade recombination and coalescence events. Simulations were also carried out for times longer than 10 ns, but due to the very fast interstitial diffusion rates it was found that almost all of the recombination and coalescence events happen in the very first few nanoseconds of the simulation; therefore results are shown for up to only 10 ns for all temperatures and PKA energies. Beyond 10 ns it was

found that the most frequent events are interstitial clusters escaping the simulation box. As mentioned in the introduction, the cascade annealing simulations provide an extension in time of the MD simulations. Moreover, it is also useful to know how much more annealing of the cascade damage is possible due to intra-cascade recombination beyond MD time-scales. Such simulations can also provide additional information such as the fraction of defects that escape the cell and the fractions of defects that are immobile, remaining in the cascade region. To understand the annealing of single cascades runtime information such as defect densities, reaction events (e.g., recombination, coalescence, emission, and transformation), average cluster sizes and their size distributions, and number densities of defects escaping the simulation cell as a function of time were also examined. To compare annealing of cascades across different PKA energies and temperatures, the numbers of surviving defects were normalized by the average number of defects at the start of the simulation, which allows the comparison of the numbers of defects lost to intracascade recombination across the different PKA energies and temperatures.

Figure 1: Surviving fraction of SIAs and vacancies as a function of time for a PKA of 75 keV at 300K.

Fig. 1 shows a plot of the surviving defect fraction ($n_d = \sum n S_d$, n = number of defect clusters of size S_d) of all SIA and vacancy type defects as a function of time for a PKA energy of 75 keV at 300 K. This plot shows common features of defect evolution across the entire range of PKA energies and temperatures that were investigated. Fig.1 shows that the initial drop

in the number of surviving defects occurs due to recombination only (surviving fraction of SIAs and vacancies are equal), and that this occurs in the very first few ns of simulated time. Beyond the recombination phase, the fraction of surviving SIAs continually drops as they diffuse beyond the boundary of the simulation box, resulting in the total number of interstitial defects being no longer equal to the number of vacancy type defects (see Fig.1). At 300 K the interstitials migrate very fast, and they very quickly diffuse away from the primary damage region while the vacancy migration rate is so low that the vacancies are effectively immobile during the time-scale of the simulation. Because of their low mobility, vacancy clusters can be considered immobile in these simulations up to 2050 K. As seen from Fig.1, after the initial decrease due to recombination with SIAs, the surviving fraction of vacancies remains nearly constant. In the present simulations mono-vacancies were observed to leave the simulation box at 2050 K at μs time-scales (not shown). Therefore, for convenience, the surviving fractions of SIAs are shown in all of the remaining plots, with the surviving fractions of vacancies shown as needed. As mentioned previously, the emission rate is determined by the sum of the binding and migration energies, and this sum is large for both SIA and vacancy clusters. Therefore, for the present simulations, emission is infrequent even at 2050K.

IV.2. Effects of PKA energy

Figure 2: Surviving fraction of SIAs (a, b & c) and vacancies (d, e & f) as a function of time for different PKAs at 300, 1025 and 2050 K

Fig. 2 shows the effect of PKA energy on the fraction of surviving defects at temperatures of 300, 1025 and 2050 K. For clarity the surviving fractions of SIAs and vacancies are plotted on different plots, but if they were plotted together they would look similar to Fig. 1. One can see from Figs. 2 (d) & (e) that at 300 K and 1025 K, after initial recombination the surviving fraction of vacancies plateaus. Within the 10 ns time-scale, due to their low mobility, vacancies do not migrate at 300 nor at 1025 K. Therefore recombination ceases once the SIAs migrate sufficiently far from the primary damage region, and consequently the number of surviving vacancies in the simulation box remains constant. Conversely, at 2050 K a slight decrease in the surviving fraction of vacancies still occurs from a few to 10 ns. This is primarily due to the migration of single vacancies. Since a single vacancy was not observed to diffuse to the boundary of the simulation box within 10 ns, the decrease of vacancy concentration at 2050 K results from vacancy diffusion and recombination with large SIA clusters that remain in the simulation box. At 2050 K the surviving fraction of vacancies eventually plateaus after about 20 ns (not shown).

From Fig. 2 it is also apparent that the fraction of defects lost to initial recombination tends to decrease with increasing PKA energy, especially at 300 and 1025 K. Perhaps this is due

to the increased clustering of SIAs and vacancies with increasing PKA energy, which reduces the number of recombination events. Increased SIA clustering also reduces the fraction of SIAs that can perform rotation, thereby reducing recombination. We find that any fluctuation in the clustering fraction is also reflected in the fraction of defects lost to initial recombination. However this behavior is not consistent at 2050 K due to the almost non-existent vacancy clustering. Based on this reasoning the loss of defects due to recombination should be the lowest for the 100 keV cascades at 300 K. Interestingly, a bigger loss of defects to recombination is observed for the 100 keV cascades (see Figs. 2 (a) & (d)) compared to cascades at other PKA energies, especially at 300 K. This can be explained based on the cascade morphology for 100 keV cascades at 300 K. A significant number of 100 keV cascades have very large vacancy clusters (>100) at their core and large SIA clusters (>60). The large drop observed in the average surviving fraction of both SIAs and vacancies is due to the annihilation of a large 1D diffusing SIA cluster, and the large vacancy cluster in the core of the cascade. At 1025 K, the reduced vacancy clustering with temperature does not create such a large effect, but the annihilation of large vacancy and SIA clusters does occur even at 1025 K.

After the initial loss of SIAs due to recombination, further loss of SIAs is primarily due to their escape from the simulation box. Fig. 3 shows a plot of the total fraction of SIAs escaped from the simulation cell after 10ns as a function of PKA energy at 300, 1025 and 2050 K. One can see from Fig.3 that the fraction of SIA escaped from the simulation box decreases with PKA energy. How SIAs escape the simulation box depends on the initial in-cascade SIA clustering and on the rate of SIA cluster growth. One expects that the number of Frenkel pairs and SIA clustering is higher for the higher PKA energies; thereby bigger SIA clusters, resulting in a lower fraction of SIAs escaping the simulation box. There is a large increase in in-cascade SIA clustering from 1025 K compared to 2050K, accordingly one can see from Fig. 3 a drop in the fraction of SIAs escaped from the simulations cell from 1025 K to 2050 K. By comparing how fast the SIAs escape the box with SIA clustering from Fig.3 in Ref. [1], it is apparent that the escape rate can be quite sensitive to in-cascade SIA clustering. For large PKA energies, even though SIAs escape at a lower rate, a very large fraction of them do escape, which contributes to long-range defect migration.

Figure 3: Total fraction of escaped SIAs after 10 ns as a function of PKA energies at 300 K, 1025 K and 2050 K

IV.3. Effect of Temperature

Figure 4: Surviving fraction of SIAs as a function of time at temperatures 300, 1025 and 2050 K at PKAs of (a) 20 (b) 30 (c) 50 (d) 60 (e) 75 and (f) 100 keV

It is expected that with increasing annealing temperature, more recombination events occur due to increased rotation of SIA clusters and faster migration of vacancies thereby

increasing the loss of defects due to initial recombination. However, Fig. 4 shows that in tungsten this is not the case. From Fig. 4 one can see that for cascades from PKA energies of 20 to 60 keV, the fraction of SIAs lost due to recombination appears to increase slightly with temperature. (see Figs. 4(a), (b), (c) & (d)). However, in most cases, the fraction of SIAs lost to recombination is very similar at 1025 and 2050 K for PKA energies up to 60 keV. Whereas for cascades at 75 and 100 keV, the fraction of SIAs lost to recombination increases with temperature from 300 K to 1025 K, then decreases at 2050 K (see Figs. 4(e) & (f)), i.e. it exhibits an inverse U-shape curve as a function of temperature. Note that the dotted line of filled red squares in Fig. 4 represents the fraction of surviving SIAs at 2050 K, which falls between the observed response at 300 K and 1025 K for 75 and 100 keV cascades. Also, with increasing temperature one expects that the fraction of SIAs escaping the simulation box should increase with temperature. However, it is obvious from Fig. 5 that at 2050 K, SIAs escape the simulation box at a slower rate (smaller slope) and also a lower fraction of SIAs escape the simulation cell during the same period of time than at 1025 K for all PKA energies. From Fig. 5 one can also see that SIAs start escaping the box at around 2 ns at 1025 K and 2050 K, and at about 3 ns at 300 K. Once again, even though at 2050 K SIAs escape at a lower rate compared to 300 K and 1025 K, a very large fraction of them escape over time, contributing to long-range defect migration.

Figure 5: Fraction of escaped SIAs as a function of time for PKA energies of 10, 20, 30, 40, 50, 60 75, and 100 keV for (a) 300K (b) 1025 K and (c) 2050 K

Figure 6: Fraction of SIAs lost due to recombination in 0.1 ns time intervals as a function of time for (a) 60 keV (b) 75 keV and (c) 100 KeV at 300, 1025 and 2050 K.

Fig. 6 shows the fraction of SIAs lost to recombination in a 0.1 ns time interval as a function of time for 60, 75 and 100 keV cascades initiated at 300, 1025 and 2050 K. One can see that almost all recombination events occur during the first nanosecond of simulation time even before SIAs start to escape from the simulation cell. Figs. 5 & 6 supports the assertion that the size of the simulation cell used is large compared to the size of a cascade even at 100 keV, and the length of the simulation is sufficiently long enough even at 2050 K to capture all intracascade recombination. Note that once the simulation cell size is large enough and the simulation time is long enough, the fraction of defects lost due to intracascade recombination will not change. Increasing the size of the simulation cell further will only alter how quickly defects, in our case SIAs, reach the boundary. Fig. 6 also shows that the fraction of SIAs lost to recombination is higher at 1025 K than at 2050K for 75 and 100 keV cascades. Fig. 7 shows the total number of recombination events after 10 ns of simulation time as a function of PKA energy for 300, 1025 and 2050 K. One can see that the total number of recombination events increase with PKA energy due to an increase in the number of Frenkel pairs. In contrast to what one expects, there is no significant increase in the total number of recombination events from 1025 K to 2050 K compared to that from 300 K to 1025 K.

Figure 7: Total number of recombination events after 10 ns of simulation time as a function of PKA for 300, 1025 and 2050 K

Among all the parameters that impact cascade aging in the short-time (100ns), the key variables are the initial spatial and size distribution of SIAs and vacancies, which depends on temperature and PKA energy, and the relative mobilities of those defects and defect clusters, which depends on cluster size and temperature. In tungsten, SIAs are highly mobile while the mono-vacancies have very slow mobility, and cascade-induced SIA clustering increases with temperature, but vacancy clustering decreases (see Fig. 3 in Ref. [1]). It appears that one of the main factors contributing to the temperature effect observed in cascade aging in tungsten is due to the temperature dependence of in-cascade SIA and vacancy clustering. From Fig. 5 in Ref. [1] one can see that at 2050 K, vacancy clustering is infrequent (except for the very rare large cluster) and large numbers of vacancies exist as isolated and are dispersed over a larger region in space, while SIAs are clustered into just a few (2 to 4) very large clusters. Note that the number of recombination events depends on the number of diffusing defect clusters, and not on the number of Frenkel pairs. Since SIA clusters are the fastest diffusing objects, a significant increase in SIA clustering should reduce the number of recombination events. Fig. 6 clearly shows that the number of recombination events does not increase very much with temperature from 1025 K to 2050 K compared to from 300 K to 1025 K. This asymmetry in cascade-induced clustering along with spatial separation of SIAs and vacancies increases the probability that a diffusing mono-vacancy will find another mono-vacancy to form an immobile cluster rather than annihilate at a mobile SIA cluster, thereby reducing recombination. However, the vacancy

mobility relative to the interstitial may not be fast enough even at 2050 K. The morphology of the cascades at 2050 K, coupled with fast SIA and slow vacancy mobility, reduces the fraction of defects that recombine.

Finally, in tungsten, cascades are compact and defect clustering is larger when compared to iron. Accordingly, elastic interactions between defects in tungsten might play a bigger role in cascade annealing when compared to iron. OKMC simulations of cascade annealing in iron, which include elastic interactions between defects [22] show that recombination is reduced by a small fraction and vacancy clustering increases slightly compared to simulations that do not consider elastic interactions. Significantly, the overall rate of recombination and escape of defects from the simulation cell did not change. In a more recent OKMC study of tungsten cascades in ion-irradiated tungsten foils, Mason *et al* [23], using randomly generated cascades, showed that elastic interaction between defects increases the rate of recombination and decreases the escape rate of dislocation loops due to elastic trapping. It was also shown that the effect of elastic interactions on recombination was mostly observed within the picoseconds time frame. In our simulations, cascades were generated from MD simulations and were followed for 50 ps before OKMC annealing. In MD, the elastic interactions are automatically included. Therefore, inclusion of elastic interactions is expected to have only minor effects on recombination in the present OKMC simulations. We realize that a more complete description of elastic interactions between defects is required before one can quantify their effect on cascade annealing.

V. Conclusions

Starting from a comprehensive cascade database obtained from MD simulations, OKMC simulations have been carried out to anneal single cascades in bulk tungsten as a function of PKA energy and temperature up to 10 ns using the newly developed code, KSOME. In tungsten, due to very fast SIA and very slow vacancy mobility, the fraction of defects lost to intracascade recombination is strongly affected by the spatial and size distribution of defects in cascades. This seems to be a key reason for a much lower fraction of defects lost to recombination at 2050 K compared to that at 1025 K, especially for higher energy PKAs. The rate at which SIAs escape from the simulation box appears to depend more sensitively on the SIA cluster size distribution than on PKA energy. Nevertheless, depending on the

PKA energy and the temperature at which cascades were initiated, 85-95% of interstitials eventually will escape intracascade recombination and contribute to long-range defect migration.

The annealing behavior of a single cascade is determined by the outcome of two key properties (1) the spatial and cluster size distribution of defects and (2) the relative mobilities of those defects (kinetic parameters). This inter-dependence is non-linear and non-intuitive. Therefore, it may be difficult to predict the annealing behavior without actually carrying out a simulation. Due to uncertainty in the kinetic parameters of SIA clusters it may be also important to carry out sensitivity studies to determine their impact on the observed annealing behavior in tungsten. Such studies may also help to better understand some aspect of cascade aging results. For example, in these simulations the linear dependence of SIA diffusion rate with temperature was not considered [15]. These studies will be the subject of future research.

Acknowledgements

The work described in this article was performed at Pacific Northwest National Laboratory, which is operated by Battelle for the United States Department of Energy under Contract DE-AC06-76RL0-1830. This material is based upon work supported by the U. S. Department of Energy, Office of Science, Office of Fusion Energy Sciences and Office of Advanced Scientific Computing Research through the Scientific Discovery through Advanced Computing (SciDAC) project on Plasma-Surface Interactions in tungsten, under Award No. DE-SC0008875. All computations were performed on CARVER at the National Energy Research Scientific Computing Center (NERSC).

References

- [1] W. Setyawan, G. Nandipati, H. L. Heinisch, K. J. Roche, R. J. Kurtz, B. D. Wirth, (companion paper Part I) <http://arxiv.org/abs/1404.6490>
- [2] G. Janeschitz, J. Nucl. Mater. 290-293 (2001) 1.
- [3] H. Bolt, V. Barabash, W. Krauss, J. Linke, R. Neu, S. Suzuki, N. Yoshida, A. U. Team, J. Nucl. Mater. 329-333 (2004) 66.
- [4] J. Roth, E. Tsitrone, T. Loarer, V. Philipps, S. Brezinsek, A. Loarte, G. F. Counsell, R.

- P. Doerner, K. Schmid, O. V. Ogorodnikova, R. A. Causey, Plasma Phys. Control 50 (2008) 103001.
- [5] G. Pintsuk, Comprehensive Nuclear Materials, Elsevier, 2012, Ch. Tungsten as Plasma-facing Material, p. 551.
- [6] R. E. Stoller, Comprehensive Nuclear Materials, Elsevier, 2012, Ch. Primary Damage Theory.
- [7] G. S. Was, Fundamentals of Radiation Materials Science: Metals and Alloys, Springer, 2007.
- [8] C. Björkas, K. Nordlund, M. J. Caturla, Phys. Rev. B 85 (2012) 024105.
- [9] C. S. Becquart, A. Souidi, C. Domain, M. Hou, L. Malerba, R. E. Stoller, J. Nucl. Mater. 352 (2006) 39.
- [10] C. J. Ortiz, M. J. Caturla, J. Comput-Aid. Mater. Des 14 (2007) 171.
- [11] J. D. Torre, C. C. Fu, F. Willaime, A. Barbu, J.-L. Bocquet, J. Nucl. Mater. 352 (2006) 42.
- [12] H. L. Heinisch, J. Nucl. Mater. 117 (1983) 46.
- [13] R. E. Stoller, S. I. Golubov, C. Domain, C. S. Becquart, J. Nucl. Mater. 382 (2008) 77–90.
- [14] C. S. Becquart, C. Domain, U. Sarkar, A. DeBacker, M. Hou, J. Nucl. Mater. 403 (2010) 75.
- [15] P. M. Derlet, D. Nguyen-Manh, S. L. Dudarev, Phys. Rev. B 76 (2007) 54107.
- [16] F. Gao, D. J. Bacon, Y. N. Osetsky, P. E. J. Flewitt, T. A. Lewis, J. Nucl. Mater. 276 (2000) 213.
- [17] E. Zarkadoula, S. L. Daraszewicz, D. M. Duffy, M. A. Seaton, I. T. Todorov, K. Nordlund, M. T. Dove, K. Trachenko, J. Phys: Condens Matter 25 (2013) 125402.
- [18] H. Xu, Y. N. Osetsky, R. E. Stoller, J. Phys: Condens Matter 24 (2012) 375402.
- [19] H. Xu, R. E. Stoller, Y. N. Osetsky, J. Nucl. Mater. 443 (2013) 66.
- [20] H. Xu, Y. N. Osetsky, R. E. Stoller, J. Nucl. Mater. 423 (2012) 102.
- [21] C. Domain, C. S. Becquart, L. Malerba, J. Nucl. Mater. 335 (2004) 121
- [22] T. S. Hudson, S. L. Dudarev, M. J. Caturla, A. P. Sutton, Philos. Mag 85 (2005) 661. □
- [23] D. R. Mason, X. Yi, M. A. Kirk, S. L. Dudarev, J. Phys: Condens Matter 26 (2014) 375701.