Synthesis and Electrochemical Characterization of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ for Fuel Cell Catalyst

Supports

Ryo H. Wakabayashi, Héctor D. Abruña*, Francis J. DiSalvo*

Department of Chemistry, Cornell University, Ithaca, New York 14853-1301

Corresponding authors:

Héctor D. Abruña: hda1@cornell.edu

Francis J. DiSalvo: fjd3@cornell.edu

Abstract

Quinary $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ of various compositions have been prepared by a co-precipitation method followed by ammonolysis. The nitride samples were examined as potential catalyst supports in polymer electrolyte membrane fuel cells. The nitride products crystallized in the rock salt (NaCl) structure over a wide range of compositions. The addition of Ta and Al was highly beneficial towards improving the chemical and electrochemical stability of TiN, without a significant loss of electrical conductivity. Platinum particles were successfully deposited on the (oxy)nitride samples, and the composite samples at some compositions were found to be comparable to Pt/carbon in their stability and catalytic activity even without optimizing the Pt deposition and dispersion processes.

Introduction

Fuel cells represent an environmentally friendly alternative to the internal combustion engine in applications such as automotive propulsion, since in principle they can operate at very high energy efficiencies, and depending on how the fuel is generated, emit zero carbon at the source of use.¹ However, prior to widespread deployment, there are several materials-related challenges that still need to be addressed in order to improve their cost, performance and durability. Currently, proton-exchange membrane fuel cells (PEMFC) use high-surface area carbon black(Vulcan)² as the catalyst support, but carbon is not thermodynamically stable under typical operating conditions. Its formal oxidation potential is only +0.207 V vs. RHE, significantly lower than the working potential of fuel cell cathodes³, although the overpotential for oxidation is high. In addition, the carbon support can be oxidized at the anode of a

fuel cell under fuel starvation conditions.⁴ Corrosion of the carbon support can result in detachment and coalescence/sintering of catalyst (Pt) particles,⁵ lowering the efficiency and lifetime of the fuel cell stack.³

Potential alternative catalyst support materials must have high electrical conductivity, chemical and electrochemical durability, high surface area, and binding affinity towards the catalyst nanoparticles.⁶ Alternate candidates include carbides,^{7,8} nitrides,^{9,10,11} and oxides.^{12,13} Of these, metal nitrides are especially promising, as many metal transition nitrides are metallic conductors, highly durable, and can be synthesized as high-surface area nanoparticles. Titanium nitride, for example, has been used as a coating material on bipolar plates of fuel cells by General Motors.¹⁴

Metal nitrides such as those of nickel,¹⁵ molybdenum^{16,17,18}, niobium,¹⁹ iron²⁰ and chromium²¹ have previously been reported as viable materials in electrochemical systems such as fuel cells. Of these, titanium nitride (TiN) is a particularly interesting and attractive candidate, since it is a metallic conductor (1.3×10^4 S/cm²²) and is known for its mechanical durability. TiN has previously been examined as a possible alternative fuel cell catalyst support material²³. In addition, titanium nitride is one of the hardest materials known (9 Mohs).²⁴ Although oxidation of nitrides to the corresponding oxides is thermodynamically favorable,²⁵ the kinetics of the reaction are very slow, sometimes resulting in the formation of only a thin surface oxide/oxy-nitride layer a few nanometers thick.²⁶ Pure TiN, however, is known to passivate (build up a thicker, insulating oxide layer) easily under acidic conditions.²⁷ In order to mitigate this tendency, several binary and ternary nitrides have been previously explored.¹⁹

Tantalum and aluminum nitrides^{10,28} have been used as dopants in titanium nitride and other nitrides to enhance corrosion resistance. Tantalum nitride (as well as titanium nitride) is used as a diffusion barrier in semiconductor devices,²⁹ pointing to its durability. Aluminum doping of TiN has been shown to improve the oxidation resistance of TiN at higher temperatures³⁰. Thin-film studies of (Ti,Al)N^{28,31,32,33} have been reported, and studies of thin-films of (Ti,Ta)N^{34,35,36} and (Ti,Ta,Al)N^{37,38,39} have been published, in which increased oxidation resistance was generally observed.

We have previously investigated the physical⁴⁰ and electrochemical⁴¹ properties of co-sputtered (Ti,Ta,Al)N thin films over a wide composition range, and found that (Ti,Ta,Al)N crystallizes in the rock-

salt structure over a broad range of compositions. In addition, even a small amount of titanium nitride introduces considerable electrical conductivity, but the optimum conductivity and durability under electrochemical conditions was obtained at relatively high titanium content (approx. 70 %). However, while thin films are useful for screening and identifying new materials, they are not presently used as catalyst supports in fuel cells due to the expense of deposition methods, the low surface area, and poor scalability. In addition, thin films and powder particles do not always show the same corrosion behavior, and to our knowledge, no powder synthesis or characterization of (Ti,Ta,Al)N (or oxynitride) has been reported. To this end, we report here on the co-precipitation synthesis of mesoporous oxynitride particles and the comparative characterization of a range of compositions.

Various synthetic methods have been reported to form powders of transition metal nitrides. They include reaction of metal alkoxides with anhydrous hydrazine⁴², ligand exchange of TiCl₄ with NH₃,⁴³ and direct nitridation of Ti powder in a nitrogen or ammonia atmosphere at high temperature. We have chosen to use the ammonolysis method with flowing ammonia, starting with oxide precursors derived from co-precipitation. This method is facile, versatile, produces high surface area particles, and is very tunable as has been shown in the literature^{44,45,46,47}. However, with this method no full conversion of the oxide to the nitride is possible, that is to say, some oxygen remains in the nitrides even after reaching equilibrium, or at least steady-state under the reaction conditions.

Experimental

Synthesis of rock-salt Ti_xTa_yAl_zN_{1-δ}O_γ (x+y+z = 1)

Ti(OBu)₄ (Aldrich 97%), Ta(OEt)₅ (Alfa Aesar 99.95%), Al(NO₃)₃·9H₂O (Sigma-Aldrich, ACS reagent), Zn(NO₃)₂·6H₂O (Sigma-Aldrich, ACS reagent), ethanol (200 proof, KOPTEC), and NH₄OH (EMD) were used as received. In a typical synthesis procedure, a stoichiometric amount (0.003 mol total Ti + Ta + Al precursors) of Al(NO₃)₃·9H₂O and excess Zn(NO₃)₂·6H₂O were placed in a three-neck round-bottom flask. Addition of zinc ions to increase macroporosity is a method that we have previously reported for synthesis of nitrides from bulk, crystalline oxides.^{48,49} The flask was then evacuated to 60

mtorr or lower on a Schlenk line. Metal nitrates are known to at least partially dehydrate under low pressure⁵⁰. After backfilling the flask with Ar, 20 mL of ethanol were added into the flask using a syringe, followed by the addition of stoichiometric amounts of the remaining metal alkoxide reagents, and stirred for several minutes. The solution was then transferred, using the cannula transfer technique, into approximately 30 mL of 1.5 M NH_4OH under rapid stirring, which resulted in the instantaneous formation of a white gel. The gel was then centrifuged to remove excess solvent and zinc ions, and was heated to 100°C to form a dry gel, followed by calcination at 450°C to form an amorphous mixed oxide precursor.

This precursor was subsequently ball-milled using a Fritsch Pulverisette 7 planetary mill to ensure that all particles were well below 1 micron in size. The mixed oxide was then heated under NH_3 (Airgas, anhydrous) flow (approx. 6 L/hr) at 800 °C for up to 24 hours, yielding fine black powders. Zn has a very high vapor pressure under the reaction conditions, and therefore sublimates away when heated at high temperature, as described in our previous work.^{48,49,51} Some samples were heated up to 950 °C in order to obtain particles that exhibit sharper XRD peaks for better fits in lattice parameter refinements.

Synthesis/Deposition of Pt nanoparticles

In order to deposit platinum, the polyol method⁵² was employed. Briefly, the nitride sample and appropriate amount of $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$ (Sigma-Aldrich) to deposit 20 wt. % Pt on the nitride were dissolved in 50 mL of ethylene glycol (Malinckrodt AR), and heated at 125-150 °C overnight. The product was then vacuum filtered, washed repeatedly with copious amount of water, and dried in air at 80°C overnight.

Physical Characterization

All samples, including precursors at various stages of synthesis, were characterized via powder X-ray diffraction using a Rigaku Ultima IV with $\text{Cu-K}\alpha$ radiation ($\lambda=1.5406 \text{ \AA}$ and $1.5444 \text{ \AA}$ for $\text{K}_{\alpha 1}$ and $\text{K}_{\alpha 2}$ respectively). Multiple samples were measured and refined. Rietveld refinements were obtained using PDXL (Rigaku). We used a Si X-ray standard to calibrate (to within $0.003 \text{ \AA}$). Scanning electron microscopy (SEM) and energy-dispersive X-ray spectroscopy (EDX) were performed using a LEO-1550 field emission SEM. Nitrogen and oxygen contents were measured using a LECO ONH836 N/O/H

analyzer (LECO Corporation, St. Joseph, Michigan). Silicon nitride (NIST 8983) was used as the standard, and samples were dried for 1 hour at 105 °C. Nitrogen adsorption/desorption isotherms were measured and surface areas were calculated using the Bräuner-Emmett-Teller theory at 77 K using a Micrometrics ASAP 2020. All samples were degassed at 150 °C for 24h on a vacuum line prior to isotherm measurements. Conductivities of the powder samples, compressed at 200 PSI, were measured using a home-built four-point probe system we described in a previous report.⁵³

Stability testing

To explore a variety of fuel cell corrosion conditions, we studied the reactivity of the (oxy)nitride products (without Pt) in acidic environments. Approximately 10 mg of the products were immersed in approximately 2 mL of 0.1M H₂SO₄ (Alfa Aesar, 99.9999%) in small glass vials, which were covered by Parafilm (Benis). The vials were immersed for 21 days in an oil bath kept at 60 °C. A photograph of the samples in vials was taken approximately every two days to monitor any visual changes, and solutions were replenished whenever the solution level decreased noticeably. After testing, the samples were washed repeatedly with de-ionized (DI) water and dried in air before taking XRD and SEM data.

Electrochemical Characterization

Glassy carbon (5 mm diameter) electrodes were polished using 1µm diamond polishing paste (Buehler) followed by 0.3 and 0.05 µm alumina powder (Extex and Buehler), and were rinsed using Millipore water (18MΩ/cm Thermo Scientific Barnstead Nanopore). These electrodes were then sonicated in 0.1M NaOH (Malinkrodt AR) for 5 minutes to activate the surface prior to deposition of the sample inks.

Inks were prepared by weighing out the appropriate amounts of sample (typically 3.9 mg) and ultrasonicing (Microson Ultrasonic Cell Disruptor XL) in 1 mL of 0.02 wt. % Nafion (Sigma 5 wt. % in ethanol, diluted with 200 proof ethanol from KOPTEC) for at least 15 minutes. Within half an hour after sonication, 5 µL of the specific ink were deposited onto a glassy carbon electrode. Inks were prepared such that Pt-containing samples would result in 20 µg/cm² of Pt loading on the electrode. For CVs of the

nitride samples without Pt deposited on them, 7.8 mg of samples were used to make inks, and deposited on the electrodes.

Cyclic voltammetry was performed in 0.1M H₂SO₄ (Alfa Aesar, 99.9999%) at room temperature. A platinum wire was used as the counter electrode and a home-made reversible hydrogen electrode (RHE) was used as the reference electrode. Samples without platinum were scanned at 50 mV/s and samples with platinum were scanned at 20 mV/s, using a Bioanalytical Systems CV-27 potentiostat. The oxygen reduction reaction on Pt/nitride samples was studied at room temperature using rotating disk electrode (RDE) voltammetry at 20 mV/s. The solution was saturated with O₂ (Airgas, Ultra High Pressure) by bubbling for 15 minutes initially and for 7 minutes after every scan to ensure that the solution remained saturated with oxygen for each scan.

Results and Discussions

Structure and compositions

Figure 1 shows pXRD patterns of Ti_xTa_yAl_zN_{1-δ}O_γ of various compositions ($0.15 \leq x \leq 1$), formed by heating the mixed oxides of the desired metal stoichiometry under ammonia at 950 °C. The nitrides crystallize in the rock salt (*Fm3m*) structure over a wide range of compositions with no visible impurity phases for medium to high Ti content ($0.15 \leq x$ if $y = z$ and $0.5 \leq x$ if y or $z = 0$). At low Ti content (Ti_{0.3}Ta_{0.7}N_{1-δ}O_γ and Ti_{0.3}Al_{0.7}N_{1-δ}O_γ), crystalline Ta₃N₅ and Al₂O₃ impurities were observed, respectively. We reported similar behavior results in a previous study of thin films deposited via co-sputtering in Ar/N₂.⁴⁰

In the specific case of TiN_{1-δ}O_γ, the lattice constant was found to be $a = 4.239 \text{ \AA}$. This is in general agreement with other reported syntheses of titanium nitride using similar synthetic methods (4.22-4.23 Å⁵⁴, 4.242 Å⁵⁵, 4.218 Å⁵¹). The observed lattice constant is also slightly smaller than the value of 4.242 Å reported in the ICDD (00-038-1420). The reported lattice parameter of bulk TiN (ICDD 00-038-1420) was made on a pristine single crystalline sample prepared by the high temperature nitridation of elemental titanium, and therefore had very low levels of oxygen impurities. Therefore the lattice constant

of the $\text{TiN}_{1.8}\text{O}_\gamma$ sample reported in this paper suggests the presence of oxygen on nitrogen sites , since $\text{O}^{2-} = 126 \text{ pm}$ and $\text{N}^{3-} = 132 \text{ pm}$.^{56,57}

When precipitated Ta_2O_5 and Al_2O_3 are heated under ammonia under identical conditions, orthorhombic, deep red Ta_3N_5 and an amorphous, slightly-gray powder (Figure 1) were observed, respectively. Apparently, when TiN is present at a sufficiently high concentration, it catalyzes the crystallization of a cubic (rock salt) products of Ta and Al nitrides.

Figure 1. pXRD patterns of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ (a) synthesized at 950 °C. (b) shows a zoomed region containing the first two peaks.

The lattice constants of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ follow Vegard's law (see Figure 2). Addition of an element with a larger atomic radius than Ti ($\text{Ti}^{3+} = 81 \text{ pm}$, $\text{Ta}^{3+} = 86 \text{ pm}$, though $\text{Ta}^{5+} = 78 \text{ pm}^{56,57}$)

increases the lattice constants slightly, while addition of an element with a smaller atomic radius than titanium ($\text{Al}^{3+} = 67.5 \text{ pm}^{56,57}$) decreases the lattice constant. When equal amounts of both tantalum and aluminum ($y = z$) were added, only a slight increase in the lattice parameter was observed as the composition changed. The X-ray peak intensity ratios between (111) and (200) near 36.8° and 42.6° change from 0.62:1 for $\text{TiN}_{1-\delta}\text{O}_\gamma$ (literature value for pure TiN: 0.75:1) to 1.01:1 in the case of $\text{Ti}_{0.33}\text{Ta}_{0.33}\text{Al}_{0.33}\text{N}_{1-\delta}\text{O}_\gamma$, which is an effect that has been previously observed.¹⁰ These results are similar to those reported in a recent study of sputtered thin film nitrides published by our collaborators.⁴⁰ The X-ray data suggest that the sample compositions are homogeneous, at least at the nanometer scale. A slight offset from the literature value of the lattice constant of TiN suggests that there are oxygen impurities in the synthesized samples (oxygen ion is smaller than nitrogen ion^{56,57}). Samples synthesized at lower temperature (800°C) showed smaller lattice constants (by $0.015 \text{ \AA}$) when compared to those synthesized at 950°C (Figure S1).

Figure 2. Lattice constant as a function of x in $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ synthesized at 950°C . Red dots: $y=z$ ($\text{Ta} = \text{Al}$); purple dots: $y = 0$ (only Ti or Ta); green dot: literature value of TiN.

Figure S2 shows EDX data of nitride samples (heated at 800 °C) at different starting/nominal metal compositions. N and O are not reported here, as the small difference in their energies (0.392 and 0.595 keV for N and O, respectively⁵⁸) makes them very difficult to distinguish by EDX. The ratio of the three metals is within the expected measurement error of the nominal ratio, further suggesting a uniform mixture of the metal ions in the nitride samples. No Zn was observed, as expected, since it sublimed out of the product under reducing conditions at elevated temperature (see Experimental section for details).

Table 1 gives the nitrogen and oxygen content of the samples (all heated at 800 °C), measured using a LECO ONH836 N/O/H thermal analyzer. For $\text{TiN}_{1.6}\text{O}_7$, the ratio of N to O was 3.4:1. A low level of H (H:O of about 8%) was also detected. The hydrogen content may arise from a small amount of adsorbed water, or –OH termination on the surface from air exposure of the product. The nitrogen-to-oxygen ratio was comparable to those seen in titanium nitride samples prepared using similar synthetic methods (N:O = 3.4:1 to 2.6:1 in Dong et al.,⁴⁵ for example). The composition of $\text{TiN}_{1.6}\text{O}_7$ sample can be calculated from these data, assuming a rock salt structure, as $\text{Ti}_{0.82}\square_{0.18}\text{N}_{0.67}\text{O}_{0.33}$ ($\square$ indicates vacancies). From these data, the average oxidation state of Ti was determined to be $\text{Ti}^{+3.38}$ (consideration of the low H content does not significantly alter the average oxidation state). In all cases, number of mol of cations was less than number of mol of anions. This also indicates that there must be cation vacancies (since the only crystalline phase has the rock salt structure and anion interstitials are highly unlikely due to the large size of the anion). In short, these (oxy)nitride samples are much more complicated than generally recognized.

x:y:z in $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.6}\text{O}_7$	mol N	mol O	mol H	mol $\square_{\text{cation}}$	Avg. charge of Ti, if all Ta = +3	Avg. charge of Ti, if all Ta = +5
1:0:0	0.772	0.228	0.020	0.18	3.38	3.38
0.7:0.15:0.15	0.672	0.328	0.027	0.19	3.41	2.99
0.33:0.33:0.33	0.402	0.598	0.036	0.37	5.37	3.37
0.7:0.3:0	0.777	0.223	0.034	0.24	3.91	3.05
0.7:0:0.3	0.573	0.427	0.038	0.20	3.33	3.33

Table 1. N/O/H amounts and corresponding proposed chemical formulas of the $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ samples synthesized at 800 °C. Mol of every ions is normalized so sum of anions add up to 1.

The samples with low amounts of aluminum ($z \leq 0.3$) had a nitrogen-to-oxygen ratio of approximately 3:1 and metal-to-anion ratio of about 0.6 to 0.8:1. Again, this indicates that, at 800 °C, the ammonolysis process leaves some oxygen behind. Therefore the oxidation states of some of the metal cations are likely to be different from +3, the expected value in a pure rock-salt (defect-free) metal nitride. If one assumes that all tantalum cations have an oxidation state of +3, the average oxidation state of titanium was found to be approximately 3.4-3.9, and if Ta ions are assumed to be +5, the average oxidation state of Ti is nearly exactly +3. The average Ta oxidation state likely lies somewhere in between, but it is very likely that a non-negligible proportion of Ta is +5, which agrees with the ammonolysis result of pure tantalum oxide (Ta_3N_5 , see Figure 1). The samples that contain 30% aluminum had significantly higher oxygen content, which is not surprising given that aluminum nitride cannot be formed from pure aluminum oxide using the synthetic method employed in this work, even at higher temperatures.

Conductivity Measurements

x:y:z in $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$	Conductivity (S/cm) at 200 PSI
1:0:0	$9.7 \cdot 10^{-2}$
0.7:0.15:0.15	$6.0 \cdot 10^{-2}$
0.33:0.33:0.33	$2.1 \cdot 10^{-3}$
0.7:0.3:0	$2.0 \cdot 10^{-2}$
0.7:0:0.3	$3.7 \cdot 10^{-2}$
Vulcan C XC72	$1.7 \cdot 10^0$

Table 2. Powder conductivity of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ samples synthesized at 800 °C measured using home-built powder conductivity measurement device.

A home-made four-point probe was used to estimate the conductivity of compressed powders at 200 PSI (Table 2). The conductivity values were somewhat lower than previously reported values for titanium nitride powders ($0.2 - 0.4 \text{ S/cm}^{55}$), likely due to inter-particle resistance from poor packing of

the grains inside the apparatus (Figure S1). Conductivities controlled by the packing of powders have been reported in previous work.⁵⁹ Whisker-like TiN particles showed conductivity on the order of 10^5 S/cm, similar to the conductivity of bulk TiN (1.3×10^4 S/cm²²), but our packed powder samples showed four orders of magnitude lower conductivity at room temperature. We therefore expect that a significant fraction of the resistance in our samples come from the contact resistance between the powder grains. Since tight particle-to-particle packing is not a necessity in fuel cells (as long as particles can make contact with the gas diffusion layer), this is not likely to be a problem in an operating fuel cell. Such behavior is not surprising because very hard materials will not deform at low pressure, resulting in poor packing and contact between particles. This contrasts with carbon black (Vulcan XC-72R), which is soft and deformable. Our electrochemical data (Figures 4 and 9, discussed later *vide infra*) suggest that inter-particle and electrode-particle contacts are sufficiently high for fuel cell applications.

Addition of tantalum and/or aluminum to TiN decreased its conductivity. Both Ta₃N₅ and AlN are wide band-gap semiconductors (2.1 eV and 6.2 eV, respectively^{60,61}), and since both Ta and Al are more oxophilic, most of the oxygens are likely coordinated to Ta and/or Al, and oxides of both are insulators. The samples with 70% Ti (by nominal composition), however, still have comparable conductivity to the samples without any Ta and/or Al.

Surface Area

The surface areas of the samples were determined by applying the Brunauer-Emmett-Teller method to the nitrogen adsorption measurements (Table 3). All samples had surface areas around 50 m²/g which is comparable to, or higher than, other nitride nanoparticles previously reported.^{19,45,53,62} The surface area per gram was lower than that of carbon black due largely to the difference in density of the materials (density of titanium nitride: 5.4 g/cm³; graphite: 2.7 g/cm³). The microscopy images (Figure 3) and the electrochemical behavior (Figures 4 and 9) suggest that the porosity is sufficiently high for the purpose of fuel cell applications.

x:y:z in $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.6}\text{O}_\gamma$	SA (m^2/g)	Sample std. dev. (m^2/g)
1:0:0	33.6	10.0
0.7:0.15:0.15	51.3	4.3
0.33:0.33:0.33	56.1	5.3
Vulcan XC72	232.1	N/A

Table 3. Surface area and standard deviation of the $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.6}\text{O}_\gamma$ synthesized at 800 °C.

Figure 3. SEM images of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.6}\text{O}_\gamma$ synthesized at 800 °C where x:y:z = (a) 1:0:0, (b) 0.7:0.15:0.15, (c) 0.33:0.33:0.33, (d) 0.7:0.3:0 and (e) 0.7:0:0.3. Scale bars are 200 nm.

Electrochemical Behavior

Cyclic voltammograms (CV) in 0.1 M H_2SO_4 can be used to understand passivation and/or corrosion behavior of materials under fuel cell-like conditions. We have chosen to modify the accelerated durability test recommended by the Department of Energy/United States Council for Automobile

Research⁶³ by cycling over a wider potential range (0.05 to 1.1 V) as we believe that cycling over such a potential range better simulates both fuel starvation and the highly oxidizing conditions at the cathode. Changes in CVs over time can be used as a proxy to assess the stability of samples under operating conditions. In Figure 4, it can be clearly seen that the addition of Ta significantly increased the stability of the TiN-based compounds. While $\text{TiN}_{1-\delta}\text{O}_\gamma$ and $\text{Ti}_{0.7}\text{Al}_{0.3}\text{N}_{1-\delta}\text{O}_\gamma$ show substantial changes in their CVs, likely due to surface oxidation of the particles to insulating oxides, the samples containing Ta showed a far smaller decrease in current. While somewhat speculative on our part, we believe that the secondary elements form a thin, stable oxide layer on the surface of the nitrides, somewhat analogous to a thin layer of chromium oxide on stainless steel.

Figure 4. Cyclic voltammograms of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ synthesized at 800 °C where x:y:z = (a) 1:0:0, (b) 0.7:0.15:0.15, (c) 0.33:0.33:0.33, (d) 0.7:0.3:0 and (e) 0.7:0:0.3 in 0.1M H_2SO_4 , scanned continuously for 24 h at 50 mV/s. Shown CVs are taken at 0 h (blue), 4 h (red) and 24 h (green) after the start of the experiment. (f) is Vulcan XC-72 as a comparison.

Chemical stability

Long-term chemical stability tests were performed by submerging small amounts (approximately 10 mg) of nitride samples in 0.1M H_2SO_4 which was kept at 60 °C in an oil bath for 3 weeks. Figure 5

(inset) shows a photograph of the particles after 21 days, in which oxidation of some samples is clearly evident from the white color of the samples. pXRD patterns (Figure 5) confirmed this visual evidence, as patterns of all white or gray samples did not have any peaks corresponding to the rock salt TiN structure, but instead showed the presence of TiO₂ (rutile) phase. The differences in overall intensities are ascribed to from variations in quantities of samples recovered. EDX data and SEM images (Figures 6 and 7) further confirm the results. All samples, except Ti_{0.7}Ta_{0.3}N₁₋₆O_γ, showed significant change in morphology after testing. In all of the samples, the amount of aluminum in the retrieved product was shown to have dropped considerably, likely due to dissolution as suggested by the Pourbaix diagram of aluminum⁶⁴. The ratio of Ti:Ta also changed in all samples except Ti_{0.7}Ta_{0.3}N₁₋₆O_γ (within the error bar, however), possibly indicating a partial loss of titanium into the solution in some cases. The corroded TiN₁₋₆O_γ and Ti_{0.7}Al_{0.3}N₁₋₆O_γ exhibited identical needle-like morphologies and had some sulfur content (by EDX), perhaps indicating the formation of titanium oxysulfate (due to the presence of sulfate anions). The EDX software detected Si in two samples, but this effect likely arises from interference with the Ta signal (Si K_α = 1.74 keV, Ta M_α = 1.71 keV⁵⁸). The small Ta signal in Ti_{0.7}Al_{0.3}N₁₋₆O_γ is very likely a contamination from other samples or Si from the glass vial used in the stability test.

Figure 5. pXRD patterns and photographs (bottom) of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.5}\text{O}_\gamma$ samples synthesized at 800 °C after 21 days of stability testing in 0.1M H_2SO_4 at 60°C. In the photograph, the particles in vials (a) and (e) are white.

Figure 6. EDX results of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1.5}\text{O}_\gamma$ samples (nominal ratio in quotation marks; synthesized at 800 °C) after 21 days of stability testing in 0.1M H_2SO_4 at 60°C. Error bars are one standard deviation calculated from ten measurements.

Figure 7. SEM images of $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ synthesized at 800 °C where x:y:z = (a) 1:0:0, (b) 0.7:0.15:0.15, (c) 0.33:0.33:0.33, (d) 0.7:0.3:0 and (e) 0.7:0:0.3 after 21 days of stability test in 0.1M H_2SO_4 at 60°C. Scale bars are 200 nm.

Pt deposition and electrochemistry using Pt/ $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$

Figure S3 shows the pXRD patterns of Pt deposited on representative $\text{Ti}_x\text{Ta}_y\text{Al}_z\text{N}_{1-\delta}\text{O}_\gamma$ samples. They show clear fcc Pt peaks and rock-salt TiN structure peaks, with Pt domain sizes of approx. 5 nm from both the refinement and the Scherrer equation, using the full width at half max (FWHM) of the Pt (200) peak (Scherrer constant = 0.94). Figure S4 shows the SEM images of nitride samples with deposited Pt nanoparticles, and Figure S5 shows bright-field TEM images of those samples. The particles appear uniform in both size and distribution, indicating that the deposition method was successful. In some of the TEM images, however, it appears that Pt particles did not disperse uniformly on some of the nitride particles. Optimization of Pt deposition and dispersion would be appropriate for further studies. Because of poor image contrast of some of the nitride particles (not very thin, higher Z than carbon), automated particle size analysis was not possible. As a consequence, there is a manual sampling error in the Pt particle size analyses, but the average and standard distribution of the particle sizes are consistent with the XRD domain size (Table S1).

The oxygen reduction reaction (ORR) was studied by depositing 20 wt. % Pt on the nitride supports. We chose this as a model reaction to test the behavior at high potentials applied to the cathode, since this condition is one of the main causes for corrosion of carbon. It is therefore important to show that an alternative material does not hinder the ORR activity. We emphasize that absolutely no carbon black was added in the ink-making process, as the corrosion of carbon supports (discussed in the Introduction section) is a significant motivation for this work. Figure S6 shows stationary CVs in nitrogen-saturated 0.1M H_2SO_4 and Figure 8 shows the RDE voltammograms of ORR in oxygen-

saturated 0.1M H₂SO₄. For comparison, 20 wt. % Pt was deposited using the identical method on Vulcan XC 72, and tested under identical conditions. The CVs of Pt/nitrides (in the absence of rotation) show typical features of platinum CVs (hydrogen adsorption and desorption, Pt oxide formation and desorption), especially after repeated scans, indicating that Pt nanoparticles are sufficiently dispersed on the nitride supports and that there is good electrical contact between the Pt nanoparticles and the substrate/support. Over at least 24 hours, nitride/Pt samples and Pt/C showed negligible difference in ORR behavior (onset potential and E_{1/2} within 20 mV, and at most 7 % decrease in limiting current). In fact, the ORR onset potential improved very slightly (5-10 mV) using nitrides instead of carbon as catalyst support. CVs (Figure 4) show no clear oxidative peak, so we anticipate that the long-term stability to be at least as good as carbon.

Figure 8. RDE voltammograms (1600 rpm) of representative samples of (a) Pt / TiN_{1.8}O_γ (20 wt. %) and (b) Pt / Ti_{0.7}Ta_{0.15}Al_{0.15}N_{1.8}O_γ (20 wt. %) synthesized at 800 °C in O₂-saturated 0.1M H₂SO₄, taken at the start of the experiment, 8 hours after the start, and 24 hours after the start of the experiment. (c) is Pt/C for comparison.

Conclusions

We have synthesized quinary Ti_xTa_yAl_zN_{1.8}O_γ of various compositions by co-precipitation followed by ammonolysis in flowing ammonia. The synthetic method using metal nitrate salts and/or alkoxides is a versatile approach that can be applied to other oxide or nitride materials. We have shown that Ti_xTa_yAl_zN_{1.8}O_γ samples crystallize in the TiN (rock-salt) structure with cationic vacancies

introduced by addition of Ta and Al as well as presence of oxygen. These materials also have high surface areas, and are sufficiently conductive to act as support materials for fuel cell catalysts. Addition of Ta and Al, especially Ta, improves the stability of titanium nitride under electrochemical conditions. Pt nanoparticles, immobilized on the nitride support, exhibited well-behaved ORR kinetics, indicating that there are no deleterious effects to the use of these nitrides as fuel cell catalyst supports.

Acknowledgment

This work is based upon work supported as part of the Energy Materials Center at Cornell (EMC²), an Energy Frontier Research Center funded by the U.S. Department of Energy, Office of Science, and Office of Basic Energy Sciences under Award Number DE-SC0001086. This work was also supported by Cornell University from September 2014 through June 2016.

The authors would like to thank Mick Thomas for his assistance with the SEM measurements, LECO Corporation (St. Joseph, MI) for the N/O/H measurements, and Prof. Franck Tessier (University of Rennes 1) for assistance with the N/O analysis measurements. This work made use of the Cornell Center for Materials Research Shared Facilities which are supported through the NSF MRSEC program (DMR-1120296).

Reference

- (1) Aricò, A. S.; Bruce, P.; Scrosati, B.; Tarascon, J.-M.; Schalkwijk, W. van Nanostructured materials for advanced energy conversion and storage devices. *Nat. Mater.* **2005**, *4*, 366–377.
- (2) Shao-Horn, Y.; Sheng, W. C.; Chen, S.; Ferreira, P. J.; Holby, E. F.; Morgan, D. Instability of Supported Platinum Nanoparticles in Low-Temperature Fuel Cells. *Top. Catal.* **2007**, *46*, 285–305.
- (3) Ioroi, T.; Akita, T.; Asahi, M.; Yamazaki, S.; Siroma, Z.; Fujiwara, N.; Yasuda, K. Platinum–titanium alloy catalysts on a Magnéli-phase titanium oxide support for improved durability in Polymer Electrolyte Fuel Cells. *J. Power Sources* **2013**, *223*, 183–189.
- (4) Cameron, D. S. Fuel Cells Science and Technology 2008. *Platin. Met. Rev.* **2009**, *53*, 147–154.
- (5) Liu, Z. Y.; Zhang, J. L.; Yu, P. T.; Zhang, J. X.; Makharia, R.; More, K. L.; Stach, E. A. Transmission Electron Microscopy Observation of Corrosion Behaviors of Platinized Carbon Blacks under Thermal and Electrochemical Conditions. *J. Electrochem. Soc.* **2010**, *157*, B906–B913.
- (6) Joo, S. H.; Choi, S. J.; Oh, I.; Kwak, J.; Liu, Z.; Terasaki, O.; Ryoo, R. Ordered nanoporous arrays of carbon supporting high dispersions of platinum nanoparticles. *Nature* **2001**, *412*, 169–172.
- (7) Wan, C.; Leonard, B. M. Iron-Doped Molybdenum Carbide Catalyst with High Activity and Stability for the Hydrogen Evolution Reaction. *Chem. Mater.* **2015**, *27*, 4281–4288.
- (8) Kimmel, Y. C.; Xu, X.; Yu, W.; Yang, X.; Chen, J. G. Trends in Electrochemical Stability of Transition Metal Carbides and Their Potential Use As Supports for Low-Cost Electrocatalysts. *ACS Catal.* **2014**, *4*, 1558–1562.

- (9) Cao, B.; Veith, G. M.; Neufeind, J. C.; Adzic, R. R.; Khalifah, P. G. Mixed Close-Packed Cobalt Molybdenum Nitrides as Non-noble Metal Electrocatalysts for the Hydrogen Evolution Reaction. *J. Am. Chem. Soc.* **2013**, *135*, 19186–19192.
- (10) Wang, L.; Northwood, D. O.; Nie, X.; Housden, J.; Spain, E.; Leyland, A.; Matthews, A. Corrosion properties and contact resistance of TiN, TiAlN and CrN coatings in simulated proton exchange membrane fuel cell environments. *J. Power Sources* **2010**, *195*, 3814–3821.
- (11) Cui, Z.; Yang, M.; DiSalvo, F. J. Mesoporous Ti_{0.5}Cr_{0.5}N Supported PdAg Nanoalloy as Highly Active and Stable Catalysts for the Electro-oxidation of Formic Acid and Methanol. *ACS Nano* **2014**, *8*, 6106–6113.
- (12) Subban, C. V.; Zhou, Q.; Hu, A.; Moylan, T. E.; Wagner, F. T.; DiSalvo, F. J. Sol–Gel Synthesis, Electrochemical Characterization, and Stability Testing of Ti_{0.7}W_{0.3}O₂ Nanoparticles for Catalyst Support Applications in Proton-Exchange Membrane Fuel Cells. *J Am Chem Soc* **2010**, *132*, 17531–17536.
- (13) Wang, D.; Subban, C. V.; Wang, H.; Rus, E.; DiSalvo, F. J.; Abruña, H. D. Highly Stable and CO-Tolerant Pt/Ti_{0.7}W_{0.3}O₂ Electrocatalyst for Proton-Exchange Membrane Fuel Cells. *J Am Chem Soc* **2010**, *132*, 10218–10220.
- (14) Li, Y.; Meng, W.-J.; Swathirajan, S.; Harris, S. J.; Doll, G. L. Corrosion resistant PEM fuel cell **2001**.
- (15) Xu, K.; Chen, P.; Li, X.; Tong, Y.; Ding, H.; Wu, X.; Chu, W.; Peng, Z.; Wu, C.; Xie, Y. Metallic Nickel Nitride Nanosheets Realizing Enhanced Electrochemical Water Oxidation. *J. Am. Chem. Soc.* **2015**.
- (16) Park, H.-C.; Lee, K.-H.; Lee, Y.-W.; Kim, S.-J.; Kim, D.-M.; Kim, M.-C.; Park, K.-W. Mesoporous molybdenum nitride nanobelts as an anode with improved electrochemical properties in lithium ion batteries. *J. Power Sources* **2014**, *269*, 534–541.
- (17) Zhang, K.; Zhang, L.; Chen, X.; He, X.; Wang, X.; Dong, S.; Han, P.; Zhang, C.; Wang, S.; Gu, L.; Cui, G. Mesoporous Cobalt Molybdenum Nitride: A Highly Active Bifunctional Electrocatalyst and Its Application in Lithium–O₂ Batteries. *J. Phys. Chem. C* **2013**, *117*, 858–865.
- (18) Ma, L.; Ting, L. R. L.; Molinari, V.; Giordano, C.; Yeo, B. S. Efficient hydrogen evolution reaction catalyzed by molybdenum carbide and molybdenum nitride nanocatalysts synthesized via the urea glass route. *J. Mater. Chem. A* **2015**.
- (19) Cui, Z.; Burns, R. G.; DiSalvo, F. J. Mesoporous Ti_{0.5}Nb_{0.5}N Ternary Nitride as a Novel Noncarbon Support for Oxygen Reduction Reaction in Acid and Alkaline Electrolytes. *Chem. Mater.* **2013**, *25*, 3782–2784.
- (20) Ding, X.; Yin, S.; An, K.; Luo, L.; Shi, N.; Qiang, Y.; Pasupathi, S.; Pollet, B. G.; Shen, P. K. FeN stabilized FeN@Pt core–shell nanostructures for oxygen reduction reaction. *J. Mater. Chem. A* **2015**.
- (21) Yang, M.; Cui, Z.; DiSalvo, F. J. Mesoporous chromium nitride as a high performance non-carbon support for the oxygen reduction reaction. *Phys. Chem. Chem. Phys.* **2013**, *15*, 7041–7044.
- (22) Petrykina, R. Y.; Shvedova, L. K. Hot pressing of transition metal nitrides and their properties. *Sov. Powder Metall. Met. Ceram.* **1972**, *11*, 276–279.
- (23) Li, Y.; Meng, W.-J.; Swathirajan, S.; Harris, S. J.; Doll, G. L. Lightweight power sources having proton exchange membrane as separator and aluminum or titanium-core contactors with protective coatings and discontinuous titanium nitride topcoats **1997**.
- (24) Lide, D. R. *CRC Handbook of Chemistry and Physics*; 86th Edition.; Taylor & Francis Group, 2005.
- (25) Saha, N. C.; Tompkins, H. G. Titanium nitride oxidation chemistry: An x-ray photoelectron spectroscopy study. *J. Appl. Phys.* **1992**, *72*, 3072–3079.
- (26) Avasarala, B.; Murray, T.; Li, W.; Haldar, P. Titanium nitride nanoparticles based electrocatalysts for proton exchange membrane fuel cells. *J. Mater. Chem.* **2009**, *19*, 1803–1805.

- (27) François, J. C.; Massiani, Y.; Gravier, P.; Grimblot, J.; Gengembre, L. Characterization and optical properties of thin films formed on TiN coatings during electrochemical treatments. *Thin Solid Films* **1993**, 223, 223–229.
- (28) Nam, N. D.; Vaka, M.; Tran Hung, N. Corrosion behavior of TiN, TiAlN, TiAlSiN-coated 316L stainless steel in simulated proton exchange membrane fuel cell environment. *J. Power Sources* **2014**, 268, 240–245.
- (29) Wittmer, M. TiN and TaN as diffusion barriers in metallizations to silicon semiconductor devices. *Appl. Phys. Lett.* **1980**, 36, 456–458.
- (30) Münz, W.-D. Titanium aluminum nitride films: A new alternative to TiN coatings. *J. Vac. Sci. Technol. A* **1986**, 4, 2717–2725.
- (31) Ait-Djafer, A. Z.; Saoula, N.; Aknouche, H.; Guedouar, B.; Madaoui, N. Deposition and characterization of titanium aluminum nitride coatings prepared by RF magnetron sputtering. *Appl. Surf. Sci.* **2015**, 350, 6–9.
- (32) Rachbauer, R.; Holec, D.; Mayrhofer, P. H. Increased thermal stability of Ti–Al–N thin films by Ta alloying. *Surf. Coat. Technol.* **2012**, 211, 98–103.
- (33) Zhu, L.; Hu, M.; Ni, W.; Liu, Y. High temperature oxidation behavior of Ti_{0.5}Al_{0.5}N coating and Ti_{0.5}Al_{0.4}Si_{0.1}N coating. *Vacuum* **2012**, 86, 1795–1799.
- (34) Liu, X.; Ma, G. J.; Sun, G.; Duan, Y. P.; Liu, S. H. The influence of Ti doping on the mechanical properties of TaN film. *Surf. Coat. Technol.* **2012**, 212, 128–133.
- (35) Koller, C. M.; Hollerweger, R.; Sabitzer, C.; Rachbauer, R.; Kolozsvári, S.; Paulitsch, J.; Mayrhofer, P. H. Thermal stability and oxidation resistance of arc evaporated TiAlN, TaAlN, TiAlTa₂N, and TiAlN/TaAlN coatings. *Surf. Coat. Technol.* **2014**, 259, Part C, 599–607.
- (36) Patel, N.; Wang, S.; Inspektor, A.; Salvador, P. A. Secondary hardness enhancement in large period TiN/TaN superlattices. *Surf. Coat. Technol.* **2014**, 254, 21–27.
- (37) Pfeiler, M.; Fontalvo, G. A.; Wagner, J.; Kutschej, K.; Penoy, M.; Michotte, C.; Mitterer, C.; Kathrein, M. Arc Evaporation of Ti–Al–Ta–N Coatings: The Effect of Bias Voltage and Ta on High-temperature Tribological Properties. *Tribol. Lett.* **2008**, 30, 91–97.
- (38) Pfeiler, M.; Scheu, C.; Hutter, H.; Schnöller, J.; Michotte, C.; Mitterer, C.; Kathrein, M. On the effect of Ta on improved oxidation resistance of Ti–Al–Ta–N coatings. *J. Vac. Sci. Technol. A* **2009**, 27, 554–560.
- (39) Kathrein, M.; Michotte, C.; Penoy, M.; Polcik, P.; Mitterer, C. Multifunctional multi-component PVD coatings for cutting tools. *Surf. Coat. Technol.* **2005**, 200, 1867–1871.
- (40) O’Dea, J. R.; Holtz, M. E.; Legard, A. E.; Young, S. D.; Burns, R. G.; Van Wassen, A. R.; Muller, D. A.; Abruña, H. D.; DiSalvo, F. J.; van Dover, R. B.; Marohn, J. A. Conductivity and Microstructure of Combinatorially Sputter-Deposited Ta-Ti-Al Nitride Thin Films. *Chem. Mater.* **2015**.
- (41) Van Wassen, A. R.; Legard, A. E.; O’Dea, J. R.; Young, S. D.; DiSalvo, F. J.; Marohn, J. A.; van Dover, R. B.; Abruña, H. D. Electrochemical Characterization of Ta-Ti-Al Nitride Thin Films. *Chem. Mater.* *Submitted*.
- (42) Kim, I.; Kumta, P. N. Hydrazide sol–gel process: A novel approach, for synthesizing nanostructured titanium nitride. *Mater. Sci. Eng. B* **2003**, 98, 123–134.
- (43) Kaskel, S.; Schlichte, K.; Chaplais, G.; Khanna, M. Synthesis and characterisation of titanium nitride based nanoparticles. *J. Mater. Chem.* **2003**, 13, 1496–1499.
- (44) Faulhaber, S.; Loeffler, L.; Hu, J.; Kroke, E.; Riedel, R.; Lange, F. F. Synthesis of nanocrystalline aluminum–gallium nitride (Al_xGa_{1–x}N; x = 0.1 to 0.5) with oxide precursors via ammonolysis. *J. Mater. Res.* **2003**, 18, 2350–2358.
- (45) Dong, S.; Chen, X.; Gu, L.; Zhou, X.; Xu, H.; Wang, H.; Liu, Z.; Han, P.; Yao, J.; Wang, L.; Cui, G.; Chen, L. Facile Preparation of Mesoporous Titanium Nitride Microspheres for Electrochemical Energy Storage. *ACS Appl. Mater. Interfaces* **2011**, 3, 93–98.

- (46) Schwenzer, B.; Loeffler, L.; Seshadri, R.; Keller, S.; Lange, F. F.; DenBaars, S. P.; Mishra, U. K. Preparation of indium nitride micro- and nanostructures by ammonolysis of indium oxide. *J. Mater. Chem.* **2004**, *14*, 637–641.
- (47) Claridge, J. B.; York, A. P. E.; Brungs, A. J.; Green, M. L. H. Study of the Temperature-Programmed Reaction Synthesis of Early Transition Metal Carbide and Nitride Catalyst Materials from Oxide Precursors. *Chem. Mater.* **2000**, *12*, 132–142.
- (48) Yang, M.; MacLeod, M. J.; Tessier, F.; DiSalvo, F. J. Mesoporous Metal Nitride Materials Prepared from Bulk Oxides. *J. Am. Ceram. Soc.* **2012**, *95*, 3084–3089.
- (49) Yang, M.; Ralston, W. T.; Tessier, F.; Allen, A. J.; DiSalvo, F. J. Mesoporous VN prepared by solid–solid phase separation. *J. Solid State Chem.* **2013**, *197*, 398–401.
- (50) Wheeler, R. C.; Frost, G. B. A Comparative Study of the Dehydration Kinetics of Several Hydrated Salts. *Can. J. Chem.* **1955**, *33*, 546–561.
- (51) Yang, M.; Cui, Z.; DiSalvo, F. J. Mesoporous titanium nitride supported Pt nanoparticles as high performance catalysts for methanol electrooxidation. *Phys. Chem. Chem. Phys.* **2012**, *15*, 1088–1092.
- (52) Zhou, Z.; Wang, S.; Zhou, W.; Wang, G.; Jiang, L.; Li, W.; Song, S.; Liu, J.; Sun, G.; Xin, Q. Novel synthesis of highly active Pt/C cathode electrocatalyst for direct methanol fuel cell. *Chem. Commun.* **2003**, 394–395.
- (53) Subban, C. V.; Smith, I. C.; DiSalvo, F. J. Interconversion of Inverse Opals of Electrically Conducting Doped Titanium Oxides and Nitrides. *Small* **2012**, *8*, 2824–2832.
- (54) Drygaś, M.; Czosnek, C.; Paine, R. T.; Janik, J. F. Two-Stage Aerosol Synthesis of Titanium Nitride TiN and Titanium Oxynitride TiOxNy Nanopowders of Spherical Particle Morphology. *Chem. Mater.* **2006**, *18*, 3122–3129.
- (55) Lee, J.-M.; Han, S.-B.; Song, Y.-J.; Kim, J.-Y.; Roh, B.; Hwang, I.; Choi, W.; Park, K.-W. Methanol electrooxidation of Pt catalyst on titanium nitride nanostructured support. *Appl. Catal. Gen.* **2010**, *375*, 149–155.
- (56) Shannon, R. D.; Prewitt, C. T. Effective ionic radii in oxides and fluorides. *Acta Crystallogr. B* **1969**, *25*, 925–946.
- (57) Shannon, R. D. Revised effective ionic radii and systematic studies of interatomic distances in halides and chalcogenides. *Acta Crystallogr. Sect. A* **1976**, *A32*, 751–767.
- (58) Bearden, J. A. X-Ray Wavelengths. *Rev. Mod. Phys.* **1967**, *39*, 78–124.
- (59) Hojo, J.; Iwamoto, O.; Maruyama, Y.; Kato, A. Defect structure, thermal and electrical properties of Ti nitride and V nitride powders. *J. Common Met.* **1977**, *53*, 265–276.
- (60) Ma, S. S. K.; Hisatomi, T.; Maeda, K.; Moriya, Y.; Domen, K. Enhanced Water Oxidation on Ta₃N₅ Photocatalysts by Modification with Alkaline Metal Salts. *J. Am. Chem. Soc.* **2012**, *134*, 19993–19996.
- (61) Lee, H. M.; Kim, D. K. High-strength AlN ceramics by low-temperature sintering with CaZrO₃–Y₂O₃ co-additives. *J. Eur. Ceram. Soc.* **2014**, *34*, 3627–3633.
- (62) Bang, J. H.; Suslick, K. S. Dual Templating Synthesis of Mesoporous Titanium Nitride Microspheres. *Adv. Mater.* **2009**, *21*, 3186–3190.
- (63) U.S. DRIVE Partnership Fuel Cell Technical Team Cell Component Accelerated Stress Test and Polarization Curve Protocols for Polymer Electrolyte Membrane Fuel Cells **2010**.
- (64) Pourbaix, M. *Atlas of Electrochemical equilibria in Aqueous Solutions*; 2nd Edition.; National Association of Corrosion Engineers, 1974.

TOC. The effect of additions of Ta and Al into TiN structure. Shifts the lattice constant, and increases its chemical stability in acidic environment.