Upconversion- and Cathodo-luminescence properties of $\text{Yb}^{3+}/\text{Ho}^{3+}/\text{Li}^{+}$ tridoped $\text{Lu}_6\text{O}_5\text{F}_8$ nanoparticles

Linna Guo ^{a, b}, Xiong Zheng ^a, Sheng Zhang ^a, Benliang Zhao ^a and Yuhua Wang ^{a, *}

^a*Department of Materials Science, School of Physical Science and Technology, Lanzhou University, Lanzhou, 730000, China*

^b*The college of Chemistry and Molecular Engineering, Zhengzhou University, Zhengzhou 450001, Henan, China*

*Corresponding author.

E-mail address: wyh@lzu.edu.cn

Tel.: +86-931-8912772 (Office)

Fax.: +86-931-8913554 (Office)

Abstract

$\text{Yb}^{3+}/\text{Ho}^{3+}/\text{Li}^{+}$ tridoped $\text{Lu}_6\text{O}_5\text{F}_8$ as a novel phosphor was prepared by a coprecipitation method. It is found that Li^{+} doping could enhance the emission intensity of $\text{Yb}^{3+}/\text{Ho}^{3+}$ codoped $\text{Lu}_6\text{O}_5\text{F}_8$ both under the excitation at 980 nm and low-voltage electron beam. Under 980 nm laser excitation, the intensity of red emission is slightly stronger than that of green emission, generating an overall yellow output in $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^{+}$ ($0\leq x\leq 8$) nanoparticles, and the reason for this phenomenon is discussed in detail. Meanwhile, under low-voltage electron beam excitation, spectral results demonstrated that the intensity of red emission is much stronger than that of green emission, yielding a red color output. Therefore, $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^{+}$ ($0\leq x\leq 8$) nanoparticles have potential applications in luminescent display panels and field emission displays.

Keywords: A. inorganic compounds; B. Optical properties; B. Luminescence; D. Phosphors

1. Introduction

As is known to all, rare-earth (RE) ions doped up-conversion (UC) materials with unique optical properties have great potential applications in the fields of displays and biomedicine [1–2], such as light emitting devices, optical data storage, biomedical fluorescent labels, etc. Meanwhile, RE ions doped cathodoluminescence (CL) materials have the advantage of much higher spatial resolution, up to a few nanometers and can be applied to field emission displays (FEDs) [3].

For UC luminescence materials, relative studies mostly focus on the design of fluoride crystals which have been demonstrated to be one of the best host materials, due to their low phonon energy and wide transparent region [4]. However, fluorides have less favorable chemical, thermal and mechanical properties compared to oxides, and thus are hard to be prepared and handled [5]. Similarly, many efficient sulfide-based compounds have been explored as low-voltage phosphors, such as $\text{Y}_2\text{O}_2\text{S}:\text{Eu}$ [6], $\text{Gd}_2\text{O}_2\text{S}:\text{Tb}$ [7], $\text{SrGa}_2\text{S}_4:\text{Eu}$ [8], etc. However, sulfide-based materials have many disadvantages, such as chemical instability, corrosion of the emitter cathode, and luminance saturation [9]. Recently, Oxyfluorides with high chemical stability and low phonon energy, are commonly considered as ideal host materials and are widely investigated [10]. $\text{Lu}_6\text{O}_5\text{F}_8$, as a new oxyfluoride matrix, is chosen as the investigated luminescent host in the present work.

Both Er^{3+} and Ho^{3+} , which have ladder-like arrangement energy levels, are frequently used as activators to generate UCL emission under NIR excitation. In our previous work, $\text{Yb}^{3+}/\text{Er}^{3+}$ codoped $\text{Lu}_6\text{O}_5\text{F}_8$ UCNPs display intense UC emission, and

the red emission is predominated in the UC spectra. By contrast, their CL emission is very weak. However, in our work it is found that the luminescence properties of Ho^{3+} whether under excitation at 980 nm or low electron beam excitation are different from that of Er^{3+} . Most reports about UC luminescence properties of Ho^{3+} show that the intensity of green emission is much higher than that of red emission, such as in $\text{Gd}_3\text{Ga}_5\text{O}_{12}$ (Ref. [11]), NaGdF_4 (Ref. [12]), $\text{Ln}_2\text{BaZnO}_5$ (Ref. [13]), La_2O_3 (Ref. [14]) and Zr_2O_3 (Ref. [15]), etc. Interestingly, in our work it is observed that the intensity of red emission of Ho^{3+} is higher than that of green emission in $\text{Lu}_6\text{O}_5\text{F}_8$ host. The dependence of excitation power on the visible and near-infrared (NIR) emissions as well as the energy levels of Yb^{3+} and Ho^{3+} has been investigated, and the above phenomenon is attributed to back energy transfer process from Ho^{3+} to Yb^{3+} and cross relaxation between two Ho^{3+} ions. This new UC emission color of Ho^{3+} will provide new possibilities for the design of more efficient devices for new applications. Moreover, we find intense red emission of Ho^{3+} in the $\text{Lu}_6\text{O}_5\text{F}_8$ host under low electron beam excitation, which is scarcely reported.

Due to its small ionic radius, Li^+ ion can be doped easily into the host lattice substitutionally or interstitially, and this will break the symmetry of the crystal field around the RE ions, leading to the enhancement of luminescence intensity[16, 17]. Herein, $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) nanoparticles were prepared to explore new optical properties on the basis of the luminescent efficiency and intensity increment by Li^+ doping. Therefore, in this paper we provide the optical properties of $\text{Yb}^{3+}/\text{Ho}^{3+}/\text{Li}^+$ -doped $\text{Lu}_6\text{O}_5\text{F}_8$ nanocrystals, which would further broaden the research

understanding of this matrix.

2. Experimental

$\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) nanoparticles were prepared by a coprecipitation method and subsequent calcination route [16]. Phase identification was performed via XRD analysis (XRD, Model D/MAX-2400 V, Rigaku, Tokyo, Japan) using $\text{Cu K}\alpha$ radiation. The size, shape and structure of the as-prepared samples were characterized by SEM (S-4800). In the measurements of UC emission, a continuous 980-nm laser diode (LD) was used for excitation source, and the emissions were collected using a HORIBA JOBIN YVON Fluorolog-3 Spectrofluorometer system. Low-voltage CL spectra were obtained using a modified Mp-Micro-S instrument.

3. Results and discussion

The representative XRD patterns of a series of $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) samples calcinated at 590 °C for 4 h are shown in Fig. 1(a). It is obvious that the locations and relative intensities of the diffraction peaks coincide well with the PDF card of $\text{Lu}_6\text{O}_5\text{F}_8$ described in Ref.[16], indicating that Li^+ ions have been dissolved into the $\text{Lu}_6\text{O}_5\text{F}_8$ host. Fig. 1(b) shows the morphology and size of $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},3\%\text{Li}^+$ which is chosen as an example, indicating the uniform agglomerated particles with rough surface and average size of about 45 nm were obtained.

Under 980 nm LD excitation at the pump power of 274.4 mW, the corresponding UC emission spectra of the as-prepared samples with different Li^+ concentrations are

shown in Fig. 2(a). Evidently, the emission intensities of Ho^{3+} : $^5\text{S}_2 \rightarrow ^5\text{I}_8$ transition around 540 nm, $^5\text{F}_5 \rightarrow ^5\text{I}_8$ transition around 665 nm and $^5\text{F}_4 \rightarrow ^5\text{I}_7$ transition around 750 nm increased remarkably with increasing Li^+ concentration from 0 to 5 mol %, and then decreased with further doping of Li^+ . This may be due to the fact that pairing or aggregation of activator ions at high concentration will lead efficient resonant energy transfer between Yb^{3+} and Ho^{3+} , and a fraction of energy migration to distant killer or quenchers followed by the appearance of quenching behaviour [18]. To the best of our knowledge, the intensity of red UC emission is usually weaker than that of green emission in $\text{Yb}^{3+}/\text{Ho}^{3+}$ couple [11-15], while spectral results demonstrated that the red emission is slightly intense than green emission in our investigated system, which was different from most cases. To understand the mechanism of the UC process, we have performed power dependence studies of $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+}$ and $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},5\%\text{Li}^+$, as shown in Fig. 2(b). In terms of every emission peak at 540, 665 and 756 nm, a plot of all the three $\ln I$ versus $\ln P$ yields a straight line with slope $n \approx 2$, indicating that all the three emissions are two-photon process whether doping Li^+ ions or not. As none of these plots show a threshold for UC emission, a photon avalanche mechanism could be ruled out [19], and the UC emission should therefore be arisen from sequential transfer of absorption energy from excited Yb^{3+} to Ho^{3+} . Typically for the $\text{Ho}^{3+}/\text{Yb}^{3+}$ couple, Yb^{3+} absorbs the excitation energy and transfers it to Ho^{3+} ions. The weaker green and NIR UC luminescence (relative to the red emission) was ascribed to the transition from the $^5\text{F}_4, ^5\text{S}_2 \rightarrow ^5\text{I}_8$ and $^5\text{F}_4, ^5\text{S}_2 \rightarrow ^5\text{I}_7$ states, respectively, while Ho^{3+} ($^5\text{F}_5$) $\rightarrow ^5\text{I}_8$ transition yields slightly stronger red

emission. In fact, nonradiative deactivation of $\text{Ho}^{3+} (^5\text{S}_2)$ could happen in three ways (shown in Fig. 2(c))[20]:

Pathway 1 Phonon relaxation of $\text{Ho}^{3+} (^5\text{S}_2, ^5\text{F}_4)$ to $^5\text{F}_5$

Pathway 2 Cross relaxation between two Ho^{3+} ions, $\text{Ho}^{3+} (^5\text{S}_2, ^5\text{F}_4) + \text{Ho}^{3+} (^5\text{I}_7) \rightarrow \text{Ho}^{3+} (^5\text{F}_5) + \text{Ho}^{3+} (^5\text{I}_6)$

Pathway 3 Back energy transfer from Ho^{3+} to Yb^{3+} , $\text{Ho}^{3+} (^5\text{S}_2, ^5\text{F}_4) + \text{Yb}^{3+} (^2\text{F}_{7/2}) \rightarrow \text{Ho}^{3+} (^5\text{I}_6) + \text{Yb}^{3+} (^2\text{F}_{5/2})$

Direct excitation of $\text{Ho}^{3+} (^5\text{S}_2, ^5\text{F}_4)$ energy level with 540 nm light did not result in any detectable red emission, implying that the feeding of $^5\text{F}_5$ level by $^5\text{S}_2$ through multiphonon relaxation (pathway 1) should be minimal. While the occurrence of Ho^{3+} to Yb^{3+} back energy transfer was obvious from study of the NIR emission of Yb^{3+} under excitation at 450 nm (inset of Fig. 2(a)), and this strongly supports that pathway 3 is a key contributor to the deactivation of $\text{Ho}^{3+} (^5\text{S}_2)$. Pathway 3 will cause the green emission decreasing, and a decrease in green emission should be accompanied by an increase in red emission. In short, pathway 2 and 3 build up the population of $\text{Ho}^{3+} (^5\text{F}_5)$ level red-emitting at the expense of green-emitting level of $\text{Ho}^{3+} (^5\text{S}_2, ^5\text{F}_4)$, leading to the stronger red emission compared with that of green. Additionally, the CIE coordinates are also investigated, as shown in Fig. 2(d). It could be easily seen that the CIE coordinates of samples doping Li^+ or not are located in the yellow region basically.

By contrast, $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+}, 1\%\text{Ho}^{3+}, x\%\text{Li}^+$ nanoparticles exhibit much stronger red emission (relative to the green emission) under excitation of a low

voltage electron beam. As shown in Fig. 3(a), under accelerating voltage of 4 kV, filament current of 70 mA, the CL spectra of $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) samples give the characteristic transitions of Ho^{3+} centered at 489 nm (2.54 eV), 543 nm (2.28 eV) and 627 nm (1.98 eV), respectively. Similar to UC emission spectra, upon increasing Li^+ concentration, peaks of the three typical emissions did not shift, while the integrated emission intensities magnified first and then decreased. Since the low-voltage cathodoluminescent materials are important for FEDs [21], we further investigated the CL properties of $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},3\%\text{Li}^+$ at various depths, as shown in Fig. 3(b). The emission intensity gradually increases as the applied voltage changes from 2 to 12 kV at a current of 70 mA. The increase in CL brightness with an increase in electron energy is attributed to the deeper penetration of the electrons into the nanoparticle body [22]. Similarly, under excitation at an accelerating voltage of 5.0 kV, the CL intensity also increases with increasing the filament current from 20 to 100 mA (Fig. 3(c)). There is no obvious saturation effect for the CL intensity with the increase of filament current and accelerating voltage, indicating that the $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},3\%\text{Li}^+$ nanoparticles are resistant to the current saturation, which is important for FED application.

4. Conclusions

$\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) nanoparticles were prepared via a simple coprecipitation synthesis route. It is found that the addition of Li^+ ions could enhance the UC and CL emission intensities in comparison with the Li^+ ions free

sample. For UC luminescence, the intensity of red emission is slightly stronger than that of green emission, generating an overall yellow color in $\text{Lu}_6\text{O}_5\text{F}_8:20\%\text{Yb}^{3+},1\%\text{Ho}^{3+},x\%\text{Li}^+$ ($0\leq x\leq 8$) nanoparticles. This phenomenon can be explained by back energy transfer process from Ho^{3+} to Yb^{3+} and cross relaxation between two Ho^{3+} ions. By contrast, under low-voltage electron beam excitation, the intensity of red emission is much stronger than that of green emission, yielding a red color output. So the discovery of $\text{Lu}_6\text{O}_5\text{F}_8$ novel phosphor is considered as a breakthrough in the field of luminescence, and $\text{Yb}^{3+}/\text{Ho}^{3+}/\text{Li}^+$ tridoped $\text{Lu}_6\text{O}_5\text{F}_8$ nanoparticles will find potential applications in photoluminescence areas, field emission display devices, etc.

Acknowledgments

This work is supported by Fundamental Research Funds for the Central Universities (No. lzujbky-2013-233) and National Science Foundation for Distinguished Young Scholars (No. 50925206).

References

- [1]. F Wang and X. G. Liu, Chem. Soc. Rev. 38 (2009) 976
- [2]. M. Haase and H. Schäfer, Angew. Chem. Int. Ed. 50 (2011) 5808
- [3]. J. C. Park, H. K. Moon, D. K. Kim, S. H. Byeon, B. C. Kim and K. S. S, Appl. Phys. Lett. 77 (2000) 2162
- [4] C. X. Li, Z. H. Xu, D. M. Yang, Z. Y. Cheng, Z. Y. Hou, P. A. Ma, H. Z. Lian and J. Lin, CrystEngComm, 14 (2012) 670

- [5]. F. Wang and X. Liu, J. Am. Chem. Soc. 130 (2008) 5642
- [6]. C. L. Lo, J. G. Duh, and B. S. Chiou, J. Electrochem. Soc. 149 (2002) H129
- [7]. J. Silver, R. Withnall, P. J. Marsh, A. Lipman, T. G. Ireland and G. R. Fern, SID Int. Symp. Dig. Tech. Pap. 36 (2005) 594
- [8]. C. Chartier, P. Benalloul, C. Barthou, J. M. Frigerio, G. O Mueller, R. M. Mach and T. Trottier, J. Phys. D: Appl. Phys. 35 (2002) 363
- [9] Y. C. Li, Y. H. Chang, Y. F. Lin, Y. J. Lin and Y. S. Chang, Appl.Phys. Lett., 89 (2006) 081110
- [10] L Tao, W. Xu, Y. S. Zhu, L. Xu, H. C. Zhu, Y. X. Liu, S. Xu, P. W. Zhou and H. W. Song, J. Mater. Chem. C, **2** (2014) 4186
- [11]. J. C. Boyer, F. Vetrone, J.A. Capobianco, A. Speghini, M. Bettinelli, Chem. Phys. Lett. 390 (2004) 403
- [12]. R. Naccache, F. Vetrone, V. Mahalingam, L. A. Cuccia, and J. A. Capobianco, Chem. Mater. 21 (2009) 717
- [13]. I. Etchart, I. Hernández, A. Huignard, M. Bérard, W. P. Gillin, Richard. J. Curry and A. K. Cheetham, J. Mater. Chem. 21 (2011) 1387
- [14]. G. G. Li, C. X. Li, Z. H. Xu, Z. Y. Cheng and J. Lin, CrystEngComm 12 (2010) 4208
- [15]. E. De la Rosa, P. Salas, H. Desirena, C. Angeles, R. A. Rodríguez, Appl. Phys. Lett. 87 (2005) 241912
- [16]. L. N. Guo, Y. H. Wang, Y. Z. Wang, J. Zhang, P. Y. Dong and W. Zeng, Nanoscale 5 (2013) 2491

- [17] K. Mishra, S.K. Singh, A.K. Singh, S.B. Rai, Mater. Res. Bull., 48 (2013) 4307
- [18] W. Li and J. Lee, J. Phys. Chem. C, 112 (2008) 11679
- [19] F. Lahoz, I. R. Martín, and J. M. Calvillo-Quintero, Appl. Phys. Lett. 869 (2005) 051106
- [20]. X. X. Luo, W. H. Cao, Mater. Lett. 61 (2007) 3696
- [21]. Y. D. Jiang, F. L. Zhang, and C. J. Summers, and Z. L. Wang, Appl. Phys. Lett. 74 (1999) 1677
- [22] X. M. Liu and J. Lin, J. Nanopart. Res. 9 (2007) 869

Figure 2

Figure 3