Identification of surface intermediates during ethylidyne formation on Pt(111) by calculation of infrared intensities and deuterium isotope shifts

Zhi-Jian Zhao, Jeffrey P. Greeley*

School of Chemical Engineering, Purdue University, West Lafayette, IN 47907

Abstract

The conversion of ethylene to ethylidyne on Pt(111) is a well-studied model reaction related to conversion of hydrocarbons over noble metal catalysts. For this chemistry, a two step mechanism that proceeds via an ethylidene intermediate has been generally accepted since the mid-1990s. However, recent DFT calculations (J. Phys Chem. C 2010, 114, 12190) have suggested that this intermediate may, in fact, be short-lived and should not be observed. Experimental verification of this prediction, though, is not straightforward, and to provide further theoretical results by which the prediction could be more easily evaluated, we present a set of benchmark calculations of infrared frequencies and intensities of candidate intermediates adsorbed on the Pt(111) surface at realistic coadsorbate coverages. The results show that only modest differences in frequencies and intensities exist between these intermediates, rendering direct spectroscopic differentiation difficult. However, by substituting the C₂ species and intermediates with deuterium, it is shown that one characteristic vibrational band of vinylidene and ethylidene can be separated by well over 100 cm⁻¹. This result provides a clear prediction that, if coupled with measured vibrational spectra of deuterium-labeled C₂ species, could definitively differentiate between the most likely intermediates in this reaction network.

Keywords

Density functional theory, adsorption, hydrogenation catalysts, ethylidyne, Pt(111), infrared spectroscopy

* To whom correspondence should be addressed. Email: jgreeley@purdue.edu, Fax: +1 (765) 494-0805, Tel: +1 (765) 494-1282

1 Introduction

The study of the chemistry of hydrocarbons over noble metal catalysts is essential to improve the activity and selectivity of many important catalytic processes in the petrochemical industry. A well-studied model reaction in this regard is the conversion of ethylene on transition metal surfaces[1-4]. On Pt(111), in particular, an important conclusion from these studies is that two types of adsorption configurations are possible for ethylene: a π -adsorbed species at very low temperatures and in certain coadsorbed systems[5], and a di- σ bonded species at temperatures higher than 52 K[6]. An additional conclusion is that, under UHV conditions, further heating of the system will irreversibly convert ethylene to ethylidyne, $\text{CH}_3\text{-C}\equiv$, which is the only stable surface species at room temperature[7]. C-C bond breaking of the C_2 species is, in turn, believed to take place at even higher temperatures, with coke formation at temperatures higher than 500 K[8].

The exact mechanism of the conversion of ethylene to ethylidyne has long been debated. Nearly all of the C_2 species, including vinyl (CH_2CH), vinylidene (CH_2C), ethylidene (CH_3CH), and ethyl (CH_3CH_2), have been proposed as intermediates during this transformation. However, based on extensive kinetic and surface spectroscopy studies, a generally accepted mechanism involving an intermediate ethylidene species gradually emerged[9-12]. This mechanism involved a 1,2 H-shift reaction from ethylene to form ethylidene, followed by a dehydrogenation step to form ethylidyne. The second dehydrogenation step was assumed to be rate-determining in order to fit available experimental results on this system.

Recent theoretical studies[1,13] on this system have pointed to a different mechanistic interpretation. The associated DFT calculations showed a high barrier, over 1.5 eV, for the direct 1,2 H-shift reaction on Pt(111). Similarly high H-shift barriers were observed on Pt(110)[14,15]. In addition, the dehydrogenation barrier from ethylidene to ethylidyne was found to be very low[1], indicating that any ethylidene that does form will be only short-lived. Further, kinetic Monte Carlo simulations based on these results[13] clearly showed that adsorbed vinylidene can be present at non-negligible coverages during ethylene conversion. A three-step mechanism which only involves hydrogenation-dehydrogenation reactions, $\text{ethylene} \rightarrow \text{vinyl} \rightarrow \text{vinylidene} \rightarrow \text{ethylidyne}$, was proposed based on these kMC results[13].

In order to provide further theoretical predictions that, when coupled with experiments, could help to conclusively identify the key intermediates in this reaction network, we present a series of benchmark calculations of the vibrational spectra of the various reactants and possible intermediates on Pt(111) at realistic coadsorbate coverages. Both frequencies and infrared intensities are determined and, by performing additional calculations of spectra for

deuterium-substituted C₂ intermediates, it is shown that one characteristic vibrational band for vinylidene can be clearly separated from those of the other adsorbates. When coupled with experiments on deuterium-substituted C₂ species, these predictions could conclusively identify the crucial intermediates in this chemistry.

2 Computational Details

The calculations are carried out with the plane-wave based Vienna *Ab-initio* Simulation Package (VASP)[16,17]. The generalized-gradient approximation (GGA), in the form of the exchange-correlation functional PW91, is employed[18]. The interaction between atomic cores and electrons is described by the projector augmented wave (PAW) method[19,20]. The ideal Pt(111) surface is modeled by periodic five-layer slabs repeated in a supercell geometry with at least 2.5 nm vacuum spacing between slabs. The equilibrium structures are taken from previously published calculations[1]. To obtain the vibrational frequencies, a normal mode analysis, where the elements of the Hessian were approximated as finite differences of gradients, is carried out, with positive and negative displacements of 0.015 Å along each Cartesian direction. A 5×5×1 *k* point grid, together with Fermi broadening with a width of 0.1 eV, are employed. The valence wave functions are expanded in a planewave basis with a cutoff energy of 520 eV, with the SCF energy convergence set to 10⁻⁷ eV.

Calculated harmonic frequencies for C-H stretching modes are generally too high to be directly compared with experiments, in view of the strong anharmonicity effects associated with these modes. A simple, and widely used, method to improve the comparison is via a scaling factor, obtained by comparing suitable calculated and experimental values[21]. A factor of 0.976±0.012 was obtained in our previous study[22], which is very close to the value, 0.969, based on values determined in another study of propylene and propylidyne chemistry over Pt(111)[23]. In the present work, the reported C-H stretching frequencies are scaled by this value, but we did not apply scaling to the other type of modes, including C-D stretching modes, since these frequencies compare well with available experimental observations[24] (differences of less than 30 cm⁻¹ for C-D stretching modes, as shown in Table 3).

The infrared intensities can be calculated from a finite difference approximation of the gradient of the dipole moment[23]. According to the metal surface selection rule, only the vibrational modes that significantly change the dipole moment in the direction perpendicular to the surface have noticeable intensity. The change of the dipole moment parallel to the surface will be cancelled out by the induced metal surface dipole moment. Thus, in our analyses, we use the *z* component (perpendicular to metal surface) of the dipole moment to represent the total electric dipole of the system. In order to rigorously converge the absolute value of the surface dipole, the vacuum spacing between slabs was increased to greater than

2.5 nm and the VASP dipole correction was applied to the potential and forces. The finite difference analyses were performed by displacing the adsorbate along each normal mode vector with a scaled vector length determined by the following equation:

$$I_i^{IR} \propto \left| \frac{d\boldsymbol{\mu}}{dQ_i} \right|^2 = \left| \frac{\boldsymbol{\mu}_z(Q + kQ_i) - \boldsymbol{\mu}_z(Q - kQ_i)}{2kQ_i} \right|^2$$

where $\boldsymbol{\mu}$ is the electric dipole moment of the system, $\boldsymbol{\mu}_z$ is the z component of the system dipole, Q is the equilibrium coordinate, Q_i is the i th normal-mode coordinate, and k is a scale factor, related to the chosen step size, which is set at 0.1 in our calculations.

3 Results and Discussion

During the conversion of ethylene over Pt(111), the most abundant surface species are ethylene and ethylidyne, depending upon the temperature. In this section, we begin by describing the simulated spectra of these abundant and easily identified surface species, and we verify the accuracy of our method by comparing the calculated intensity with experimental values recently reported by Deng et al.[8] Then, we turn to a discussion of the simulated spectra of the short-lived surface intermediates, including vinyl, vinylidene and ethylidene, in both non-deuterated and deuterated forms, and we compare the predicted spectra with experimentally observed spectra to determine the most relevant intermediates for this chemistry.

3.1 Spectra of C_2H_x surface species at saturated coverage

Ethylidyne CCH_3 . The optimized structure of ethylidyne is shown in Fig. 1. The most stable adsorption site for ethylidyne on Pt(111) is fcc, as determined by both LEED studies[25] and previous DFT calculations[1,26]. We will focus on the result at 1/3 ML since this was reported to be the saturation coverage on similar metal surfaces[13]. Due to the perpendicularly bonded nature of ethylidyne, several intense peaks are observed on the surface (Fig. 2a, Table 1). The most intense such peak is CH_3 symmetric bending (umbrella) at 1325 cm^{-1} , followed by CH_3 symmetric stretching at 2871 cm^{-1} and C-C stretching at 1107 cm^{-1} . The intensity of the latter two modes is about 65% of the intensity of the CH_3 symmetric bend. All three modes are quite close to the experimentally reported frequencies: 1340 , 2887 and 1124 cm^{-1} , respectively. The intensities of the other peaks are less than 3% of the intensity of the CH_3 symmetric bending peak. The calculated and experimental frequencies of these other peaks are also in good agreement, including CH_3 asymmetric bending (calculated 2943 , 2938 ; experimental 2939 cm^{-1}), CH_3 asymmetric bending (calculated 1406 , 1407 ; experimental 1444 cm^{-1}), and CH_3 symmetric rocking (calculated 961 , 962 ; experimental 975 cm^{-1}).

$di-\sigma$ Ethylene CH_2CH_2 . There are two modes for ethylene adsorption on Pt(111): π

adsorption with both C atoms attached to the same top site of one Pt atom via a π donor bond, and a di- σ mode with two C atoms attached to two adjacent Pt atoms at a bridge site in η^2 fashion. Experimental studies have shown that π -bound ethylene is only stable at low temperatures, and it will convert to the di- σ mode above 52 K[6]. In the following, therefore, we will focus on the discussion on the calculated spectra of di- σ ethylene since our reference experimental value was measured at 85 K. The saturation coverage of ethylene has been reported to be 1/4 ML on Pt(111)[13], and our analysis is performed at this coverage. Unlike ethylidyne, di- σ ethylene is adsorbed in flat configuration on Pt(111) (Fig. 1), leading to weaker IR signals due to the surface selection rules (Fig. 2b, Table 1). However, the sp^3 hybridized nature of di- σ ethylene causes the CH_2 groups to be slightly bent away from the Pt surface instead of parallel to Pt(111), which leads to an intense peak for the CH_2 symmetric stretching mode, located at 2913 cm^{-1} by DFT calculations. The other modes, which have moderate intensities, include CH_2 scissoring at 1419 cm^{-1} and a mixture of CH_2 wagging and C-C stretching at 1036 and 981 cm^{-1} . The location of these modes are all very close to the experimentally reported values, at 2908 , 1416 , 1042 , and 995 cm^{-1} , respectively. However, the DFT-predicted intensity of the latter two modes is about 20% of the most intense mode (CH_2 symmetric stretching), which is somewhat stronger than the corresponding peak intensities reported in Ref 8.

Other intermediates. The above results indicate that the DFT calculations successfully reproduce experimental IR spectra for stable C_2 species on Pt(111). In the following, we turn to a description of the simulated spectra of the various surface intermediates, including vinyl, vinylidene and ethylidene. All of the spectra are simulated at 1/3 ML, which is the same as the considered ethylidyne coverage. To our knowledge, there are no directly measured spectra for these intermediates on the Pt(111) surface due to the unstable nature of the species.

Vinyl $CHCH_2$. The most stable adsorption site for vinyl is fcc on Pt(111). Compared to ethylene, the tilted vinyl molecule (Fig. 1) has more IR active modes (Fig 3a, Table 2). The most intense mode is CH_2 symmetric stretching at 2880 cm^{-1} . The next two most intense modes include the symmetric mixture of CH_2 wagging and CH in-plane bending at 954 cm^{-1} and CH stretching at 2932 cm^{-1} . The other, less intense, peaks include CH_2 symmetric stretching at 3014 cm^{-1} , CH_2 scissoring at 1385 cm^{-1} , and a mixture of CH in-plane bending and C-C stretching at 1107 and 1062 cm^{-1} .

Vinylidene CCH_2 . The adsorption of vinylidene is similar to vinyl, also preferring to bind at a threefold site (Fig. 1). However, the C-C bond is more tilted away from the surface compared to the vinyl case. As shown in Fig. 3b and Table 2, the most intense mode is the CH_2 scissoring mode, and the second most intense mode is CH_2 symmetric stretching.

Several other IR active peaks include CH₂ asymmetric stretching at 3046 cm⁻¹, C-C stretching at 1260 cm⁻¹, and CH₂ rocking at 900 cm⁻¹.

Ethylidene CHCH₃. Ethylidene prefers to bind at bridge sites of Pt(111) in a μ fashion (Fig. 1). As is the case with vinyl, we observed a series of intense peaks for ethylidene (Fig 3c, Table 2). The most intense such peak is CH₃ symmetric stretching at 2863 cm⁻¹. There are three other modes which have at least half of the intensity of the strongest mode, including CH₃ asymmetric bending at 1403 cm⁻¹, a mixture of CH in-plane bending and CH₃ symmetric rocking at 1245 cm⁻¹, and C-C stretching at 1048 cm⁻¹.

3.2 Spectra of C₂D_x surface species at saturated coverage

A common technique to assist in the assignment of vibrational peaks is to substitute atoms with isotopically labeled equivalents. Isotopic substitution does not change the electronic structure of the system. However, it does affect the reduced mass of the normal modes. In general, heavier atoms increase the reduced mass, which leads to a red shift of the corresponding modes. As we show below, substitution of the hydrogen atoms in ethylene with deuterium induces frequency shifts in the intermediates that, when coupled with appropriate experiments, could lead to conclusive identification of the relevant intermediates.

By comparing with experimental spectra of C₂D₄ and CCD₃ adsorbed on Pt(111) (Table 3)[5], we observed that, for C-D stretching modes, the anharmonic effect is not as strong as it is for C-H stretching modes, and the difference between the calculated and experimental values is less than 30 cm⁻¹. Thus, we do not scale the calculated values for the surface-adsorbed species. The stretching modes shift from ~3000 cm⁻¹ in adsorbed C₂H_x (Tables 1 and 2, Figs. 2 and 3) to 2100 – 2300 cm⁻¹ in adsorbed C₂D_x (Tables 3 and 4, Figs. 4 and 5). The calculated intensities are larger for the symmetric C-D stretching modes than for the corresponding asymmetric modes. This result is quite understandable, since in general the symmetric vibrations will cause larger changes in the surface dipole perpendicular to the Pt surface.

The substituted D atoms also have strong isotope effect on the bending modes of CD_x groups. In the C₂H_x case, the bending modes have frequencies that span a large range between ~450 and 1400 cm⁻¹ (Tables 1 and 2, Figs. 2 and 3). This range shifts downwards, to about 400 – 1050 cm⁻¹, in the case of C₂D_x (Tables 3 and 4, Figs. 4 and 5). This range is at least 100 cm⁻¹ lower than the C-C stretching modes of C₂D_x, and we do not observe obvious mixing between the bending modes and C-C stretching modes in case of C₂D_x. More interestingly, all of the C-C stretching modes are now located in a narrow range between 1110 and 1139 cm⁻¹ with the exception of CCD₂. In the latter case, the C-C bond is stronger than in the other cases, which is reflected by the almost 200 cm⁻¹ higher frequency of C-C

stretching and about 0.08 Å shorter C-C bond length.

3.3 Identification of observed intermediate during ethylidyne formation

Previous studies[8,27] reported two intense modes which were related to the intermediate formed during ethylene conversion to ethylidyne: one CH stretching mode at 2957-2960 cm⁻¹, and one bending mode at 1387 cm⁻¹. These modes were assigned to ethylidene in both studies. Evidence for this assignment came from comparison with an organometallic complex, Os₂(CO)₈(CHCH₃)[28], which also shows similar vibrational modes at 2950 cm⁻¹ and 1369 cm⁻¹. Moreover, there is evidence from vibrational spectroscopy of intermediates resulting from decomposition of 1,1-diiodoethane on Pt(111)[29]. The corresponding features reported at 2972 cm⁻¹ and 1372 cm⁻¹ were assigned to ethylidene formed after dissociation of C-I bonds. These studies provide plausible evidence in support of the role of ethylidene as an intermediate in ethylene conversion to ethylidyne.

In contrast to the above picture, previous DFT calculations showed a very low barrier, less than 30 kJ mol⁻¹, for dehydrogenation of ethylidene, indicating that, even if some ethylidene could form on the Pt(111) surface, it would have a very short lifetime and would not be spectroscopically observable[1]. Moreover, both ethylidene and vinylidene can be directly formed via vinyl. The calculated barrier to form vinylidene is 4-25 kJ mol⁻¹ lower than ethylidene at different coverages, which suggests favorable selectivity towards vinylidene. Further, the hydrogenation of vinylidene has a barrier in the range of 58-80 kJ mol⁻¹, and this higher barrier could lead to slower hydrogenation of vinylidene and consequent higher coverage on the surface. Indeed, kMC simulations based on these DFT energies[13] show accumulation of vinylidene instead of ethylidene during ethylene conversion.

The calculated vibrational spectra in the present work demonstrate that vinylidene is also a good candidate for the observed intermediate. As mentioned above, multiple intense modes exist that might be experimentally observable. The calculated asymmetric stretching of CH₂ is located at 2960 cm⁻¹, while the CH₂ scissoring mode is calculated at 1415 cm⁻¹, which correspond well to the experimentally measured peaks at 2957-2960 and 1387 cm⁻¹. The calculated intensities of these two modes are larger than the intensities of the other modes for vinylidene. We note, however, that there is another mode, CH₂ rocking at 900 cm⁻¹, whose intensity which is more than half of the intensity of the 2960 cm⁻¹ peak. This mode might be observed if the measurements in reference 8 were expanded beyond 900 cm⁻¹, or if their sensitivity were increased.

It is important to note that, if we compare only the frequencies of the vibrational modes, both ethylidene and vinyl also show reasonable matches with the experimentally measured spectra of the intermediates[1]. However, when intensities are also analyzed, this

promising agreement disappears. For ethylidene, the calculated intensity of the symmetric CH_3 stretching mode at 2964 cm^{-1} is much lower than that for the other four modes. Indeed, the intensity of this peak is only about 1/5 of the most intense peak, CH_3 asymmetric stretching at 2863 cm^{-1} . There are another two intense peaks, a mixture of CH in-plane bending and CH_3 symmetric rocking at 1245 cm^{-1} , and C-C stretching at 1048 cm^{-1} , which have a similar intensity to the CH_3 asymmetric bending at 1403 cm^{-1} . However, none of these peaks were observed in previous experimental studies[8]. In the case of vinyl the calculated result showed that there is an intense peak at 954 cm^{-1} , corresponding to a mixture of CH_2 rocking and CH in-plane bending, that is not observed in the experiments. Further, the calculated intensity for the peak at 1385 cm^{-1} is weaker than the corresponding experimental intensity.

In order to further distinguish these intermediates, we also simulated the deuterium substituted spectra of these species. The C-D stretching modes of CCD_3 , CDCD_3 and CCD_2 are relatively similar to one another. However, there is one mode which belongs to CCD_2 that is almost 200 cm^{-1} away from the other modes belonging to CDCD_3 and CCD_3 . In CCD_2 , the C-C stretching mode is located at 1293 cm^{-1} . The intensity of this mode is also the strongest among all the modes of CCD_2 . Meanwhile, the non C-D stretching modes for CDCD_3 and CCD_3 are at least 200 cm^{-1} lower than the corresponding mode in CCD_2 , at 1110 cm^{-1} and 1139 cm^{-1} respectively. These results strongly suggest that, if one could observe an intermediate peak at around 1293 cm^{-1} in an experimental spectrum associated with conversion of deuterated ethylene, the importance of the vinylidene intermediate in this reaction would be confirmed.

Finally, we accounted for the impact of coadsorbates on the frequencies and intensities of the deuterated spectra. Since spectra of intermediates in experiments are generally measured with significant amounts of coadsorbed ethylidyne, we calculated the intensities of vinylidene and ethylidene (coverage of 1/9 ML) coadsorbed with 2/9 ML of ethylidyne in a (3×3) unit cell; the corresponding spectra are shown in Fig. 6. In the case of deuterated vinylidene, there is a relatively small influence caused by coadsorbed deuterated ethylidyne. The maximum shift of the frequencies is 2 cm^{-1} for modes above 500 cm^{-1} . The most intense mode is still C-C stretching at 1293 cm^{-1} . However, in the ethylidene case, the asymmetric CD_3 stretching mode shifts by 38 cm^{-1} , to 2006 cm^{-1} . In addition to the modest shift for this mode, the other CH stretching modes also shift by about $4\text{-}17\text{ cm}^{-1}$. These larger shifts for ethylidene might due to the slightly stronger repulsion between the larger ethylidene molecule and coadsorbed ethylidyne. Nevertheless, our tested coverage effect show that the peak position of vibrational modes are only slightly influenced by co-adsorbed ethylidyne.

4 Conclusions

In this study, we simulated the IR spectra of several important C₂ species in the conversion of ethylene to ethynidyne on Pt(111) by means of periodic density functional calculations. Our calculations reproduced the previous RAIRS spectra of ethylene and ethynidyne on Pt(111). Furthermore, the simulated spectra of three possible intermediate C₂ species, vinyl, vinylidene and ethynidene, suggest that vinylidene might be the experimentally detected intermediate during the ethynidyne formation process on Pt(111). Vinylidene seemed to have the best match with both the position and intensity of previously observed experimental peaks at ~2960 and 1387 cm⁻¹. Although the other C₂ species also contain vibrational modes which are located close to the experimentally observed frequencies, the intensities are rather weak. Further confirmation of the importance of the vinylidene intermediate could come from deuterium substitution experiments. Due to the slightly stronger C-C bonding in CCD₂, the C-C stretching mode located at 1293 cm⁻¹, which is almost 200 cm⁻¹ away from all the other modes belonging to CDCD₃, CCD₃ and CDCD₂. Experimental observation of this feature, combined with the present analysis of vibrational spectra and energetic arguments from previous DFT calculations and kinetic Monte Carlo simulations, would confirm that vinylidene is a key intermediate in this important model chemistry.

Acknowledgments.

This work was supported by a National Science Foundation Designing Materials to Revolutionize and Engineering our Future program (CBET1437219). Use of the Center for Nanoscale Materials was supported by the U. S. Department of Energy, Office of Science, Office of Basic Energy Sciences, under Contract No: DE-AC02-06CH11357. Computational resources provided by the National Energy Research Scientific Computing Center (NERSC) are gratefully acknowledged.

References

- [1] Z.-J. Zhao, L. V. Moskaleva, H. A. Aleksandrov, D. Başaran, N. Rösch, *J. Phys. Chem. C* 114 (2010) 12190-12201.
- [2] A. Tilekaratne, J. P. Simonovis, M. F. L. Fagúndez, M. Ebrahimi, F. Zaera, *ACS Catal.* 2 (2012) 2259-2268.
- [3] T. Okada, Y. Kim, M. Trenary, M. Kawai, *J. Phys. Chem. C* 116 (2012) 18372-18381.
- [4] T. Okada, Y. Kim, Y. Sainoo, T. Komeda, M. Trenary, M. Kawai, *J. Phys. Chem. Lett.* 2 (2011) 2263-2266.
- [5] H. Steininger, H. Ibach, S. Lehwald, *Surf. Sci.* 117 (1982) 685-698.
- [6] M. B. Hugenschmidt, P. Dolle, J. Jupille, A. Cassuto, *J. Vac. Sci. Technol. A.* 7 (1989) 3312-3316.
- [7] L. L. Kesmodel, L. H. Dubois, G. A. Somorjai, *J. Chem. Phys.* 70 (1979) 2180-2188.
- [8] R. Deng, E. Herceg, M. Trenary, *Surf. Sci.* 560, (2004) L195-L201.
- [9] F. Zaera, N. Bernstein, *J. Am. Chem. Soc.* 116 (1994) 4881-4887.
- [10] F. Zaera, *Langmuir* 12 (1996) 88-94.
- [11] F. Zaera, C. R. French, *J. Am. Chem. Soc.* 121 (1999) 2236-2243.
- [12] F. Zaera, T. V. W. Janssens, H. Öfner, *Surf. Sci.* (1996) 362-371.
- [13] H. A. Aleksandrov, L. V. Moskaleva, Z.-J. Zhao, D. Başaran, Z.-X. Chen, D. Mei, N. Rösch, *J. Catal.* 285 (2012) 187-195.
- [14] A. T. Anghel, D. J. Wales, S. J. Jenkins, D. A. King, *Chem. Phys. Lett.* 413 (2005) 289-293.
- [15] A. T. Anghel, D. J. Wales, S. J. Jenkins, D. A. King, *J. Chem. Phys.* 126 (2007) 044710.
- [16] G. Kresse, J. Hafner, *Phys. Rev. B* 49 (1994) 14251-14269.
- [17] G. Kresse, J. Furthmüller, *Comput. Mater. Sci.* 6 (1996) 15-50.
- [18] J. P. Perdew, Y. Wang, *Phys. Rev. B* 45 (1992) 13244-13249.
- [19] P. E. Blöchl, *Phys. Rev. B* 50 (1994) 17953-17979.
- [20] G. Kresse, D. Joubert, *Phys. Rev. B* 59 (1999) 1758-1775.
- [21] M. P. Andersson, P. Uvdal, *J. Phys. Chem. A* 109 (2005) 2937-2941.
- [22] Z.-J. Zhao, Hydrocarbon conversion over transition metal catalysts: A mechanistic study from first-principles calculations, Doctoral Thesis, Technische Universität München, Munich, Germany, 2012.
- [23] A. Valcárcel, J. M. Ricart, A. Clotet, F. Illas, A. Markovits, C. Minot, *J. Catal.* 241 (2006) 115-122.
- [24] S. F. Parker, N. A. Marsh, L. M. Camus, M. K. Whittlesey, U. A. Jayasooriya, G. J. Kearley, *J. Phys. Chem. A* 106 (2002) 5797-5802
- [25] L. L. Kesmodel, L. H. Dubois, G. A. Somorjai, *Chem. Phys. Lett.* 56 (1978) 267-271.
- [26] Q. Ge, D. A. King, *J. Chem. Phys.* 110 (1999) 4699-4702.
- [27] P. Cremer, C. Stanners, J. W. Niemantsverdriet, Y. R. Shen, G. Somorjai, *Surf. Sci.* 111 (1995) 111-118.
- [28] C. E. Anson, N. Sheppard, D. B. Powell, J. R. Norton, W. Fischer, R. L. Keiter, B. F. G. Johnson, J. Lewis, A. K. Bhattacharyya, S. A. R. Knox, M. L. Turner, *J. Am. Chem. Soc.* 116 (1994) 3058-3062.

[29] T. V. W. Janssens, F. Zaera, J. Phys. Chem. 100 (1996) 14118-14129.

Table 1: Calculated vibrational frequencies (intensities) of di- σ ethylene and ethylidyne on Pt(111) and assignment^a of the normal modes

Ethylidyne (CCH ₃)			di- σ Ethylene (C ₂ H ₄)		
DFT(int.) ^b	Exp. ^c	Assignment	DFT(int.) ^b	Exp. ^c	Assignment
2943(2.6) ^d	2939	CH ₃ ν_a	2992(2.5) ^d	2908	CH ₂ ν_a
2938(2.2) ^d		CH ₃ ν_a	2967(3.4) ^d		CH ₂ ν_a
2871(65) ^d		CH ₃ ν_s	2913(100) ^d		CH ₂ ν_s
	2887		2905(2.6) ^d	1416	CH ₂ ν_s
1407(0.1)		CH ₃ δ_a	1419(6.6)		CH ₂ δ
1406(0.1)		CH ₃ ρ_a	1386(0.2)		CH ₂ δ
1325(100)		CH ₃ δ_s	1180(0)		CH ₂ ρ
1107(66)		CC ν	1040(0.8)		CH ₂ ω
962(0.1)		CH ₃ ρ_s	1036(21)		CC ν / CH ₂ ω
960(0.1)		CH ₃ ρ_s	981(20)		CH ₂ ω / CC ν
			935(0.3)	995	CH ₂ ρ
			782(0.1)		CH ₂ τ
460(0)		Pt ₃ C ν_a	638(0)		CH ₂ τ
459(0)		Pt ₃ C ν_a	547(0)		PtC ν_a
404(2.3)		Pt ₃ C ν_s	449(6.7)		PtC ν_s
190(0)		CH ₃ τ	194(0)		PtC δ_{ip}
157(0)		FT / FR	141(0)		PtC δ_{op}
155(0)		FT / FR	119(0)		PtC δ_{op}

^a Notations used: ν , stretching; δ , bending; τ , twisting; ω , wagging; ρ , rocking; a, asymmetric; s, symmetric; ip, in-plane; op, out-of-plane; FR, frustrated rotation; FT, frustrated translation.

^b Unit of frequency is cm⁻¹. Intensities were shown in brackets and scaled (%) by the strongest one of each species.

^c Ref 8.

^d Scaled by 0.976

Table 2: Calculated vibrational frequencies (intensity) of relevant C₂H_n intermediates (n = 2–4) on Pt(111) and assignment^a of the normal modes

Ethylidene (CHCH ₃)		Vinyl (CHCH ₂)		Vinylidene (CCH ₂)	
DFT(int.) ^b	Assignment	DFT(int.) ^b	Assignment	DFT(int.) ^b	Assignment
2964(18) ^c	CH ₃ v _a	2942(4.6) ^c	CH ₂ v _a	3046(4.0) ^c	CH ₂ v _a
2918(0.4) ^c	CH v/CH ₃ v _a	2932(40) ^c	CH v	2960(35) ^c	CH ₂ v _s
2910(4.9) ^c	CH ₃ v _a /CH v	2880(100) ^c	CH ₂ v _s		
2863(100) ^c	CH ₃ v _s				
1404(1.4)	CH ₃ δ _a	1385(17)	CH ₂ δ	1415(100)	CH ₂ δ
1403(53)	CH ₃ δ _a	1107(14)	CH δ _{ip} /CC v	1260(5.1)	CC v
1326(22)	CH ₃ δ _s	1062(15)	CC v/CH δ _{ip}	979(0.1)	CH ₂ ρ
1245(57)	CH δ _{ip} /CH ₃ ρ _s	1010(0)	CH ₂ ρ	900(21)	CH ₂ ω
1048(52)	CC v	954(59)	CH ₂ ω	694(0)	CH ₂ τ
947(0.3)	CH ₃ ρ _a /CH δ _{op}	730(0)	CH δ _{op} /CH ₂ τ		
935(14)	CH ₃ ρ _s /CH δ _{ip}	661(0)	CH ₂ τ/CH δ _{op}		
790(0)	CH δ _{op}				
493(0.4)	Pt ₂ C v _s	569(0)	Pt ₃ C ₂ v _a	518(0)	Pt ₃ C v _a
372(0)	Pt ₂ C v _a	506(4.3)	Pt ₃ C ₂ v _s	469(0.1)	Pt ₃ C v _s
279(0)	Pt ₂ C δ	378(0)	Pt ₃ C ₂ δ _{op}	410(6.0)	FR
163(0)	CH ₃ τ	252(0)	Pt ₃ C ₂ δ _{ip}	263(2.6)	PtC ^(H2) v
107(0)	FR	222(0)	Pt ₃ C ₂ δ _{op}	212(0)	PtC ^(H2) δ
94(0.1)	FR				

^a Notations used: v, stretching; δ, bending; τ, twisting; ω, wagging; ρ, rocking; a, asymmetric; s, symmetric; ip, in-plane; op, out-of-plane; FR, frustrated rotation.

^b Unit of frequency is cm⁻¹. Intensities are shown in brackets and scaled (%) by the strongest intensity mode of each species.

^c Scaled by 0.976

Table 3: Calculated vibrational frequencies (intensity) of deuterium substituted di- σ ethylene and ethylidyne on Pt(111) and assignment^a of the normal modes

Ethylidyne (CCD ₃)			di- σ ethylene (C ₂ D ₄)		
DFT(int.) ^b	Exp. ^c	Assignment	DFT(int.) ^b	Exp. ^c	Assignment
2230(0.5)		CD ₃ ν_a	2275(1.8)		CD ₂ ν_a
2226(0.5)	2220	CD ₃ ν_a	2259(3.1)	2250	CD ₂ ν_a
2109(16)	2080	CD ₃ ν_s	2167(100)	2150	CD ₂ ν_s
			2152(1.9)		CD ₂ ν_s
1139(100)	1160	CC ν	1132(72)	1150	CC ν
1013(0)	1030	CD ₃ δ_a	1022(0.1)		CD ₂ δ
1012(0)		CD ₃ ρ_a	923(0)		CD ₂ ρ
965(1.2)	990	CD ₃ δ_s	882(53)	900	CD ₂ δ
773(0.1)	790	CD ₃ ρ_s	836(0.5)		CD ₂ ω
772(0.1)		CD ₃ ρ_s	734(2.1)	740	CD ₂ ω
436(0)		Pt ₃ C ν_a	661(0.3)		CD ₂ ρ
435(0)		Pt ₃ C ν_a	580(0.1)		CD ₂ τ
376(1.8)		Pt ₃ C ν_s	484(0.1)		PtC ν_a
137(0)		FT / FR	472(0.1)		CD ₂ τ
135(0)		FT / FR	429(18)		PtC ν_s
134(0)		CD ₃ τ	181(0.1)		PtC δ_{ip}
			116(0.1)		PtC δ_{op}
			108(0.1)		PtC δ_{op}

^a Notations used: ν , stretching; δ , bending; τ , twisting; ω , wagging; ρ , rocking; a , asymmetric; s , symmetric; ip , in-plane; op , out-of-plane; FR, frustrated rotation; FT, frustrated translation.

^b Unit of frequency is cm⁻¹. Intensities are shown in brackets and scaled (%) by the strongest intensity mode of each species.

^c Ref 5.

Table 4: Calculated vibrational frequencies (intensity) of relevant C₂D_n intermediates (n = 2–4) on Pt(111) and assignment^a of the normal modes

Ethylidene (CDCD ₃)		Vinyl (CD ₂ CD ₂)		Vinylidene (CCD ₂)	
DFT(int.) ^b	Assignment	DFT(int.) ^b	Assignment	DFT(int.) ^b	Assignment
2244(14)	CD v/CD ₃ v _a	2235(2.5)	CD ₂ v _a	2321(2.1)	CD ₂ v _a
2203(2.6)	CD ₃ v _a	2207(33)	CD v	2200(16)	CD ₂ v _s
2192(0.5)	CD v/CD ₃ v _a	2136(68)	CD ₂ v _s	1293(100)	CC v
2106(41)	CD ₃ v _s	1115(100)	CC v	995(22)	CD ₂ δ
1110(80)	CC v	972(4.8)	CD ₂ δ	800(0.2)	CD ₂ ρ
1011(0.2)	CD ₃ δ _a	865(0.2)	CD ₂ ω/CD δ _{ip}	694(14)	CD ₂ ω
1009(100)	CD ₃ δ _s /CD δ _{ip}	787(0)	CD ₂ ρ	513(0)	CD ₂ τ
994(4.5)	CD δ _{ip} /CD ₃ δ _s	694(39)	CD δ _{ip} /CD ₂ ω	465(0)	Pt ₃ C v _a
903(2.1)	CCD δ	537(0)	CD δ _{op} /CD ₂ τ	460(0.3)	Pt ₃ C v _s
766(0)	CD ₃ ρ _a /CD δ _{op}	516(2.3)	Pt ₂ C ^(H) v _s	395(10)	FR
700(2.8)	CD ₃ ρ _s /CD δ _{ip}	477(0)	CD δ _{op} /CD ₂ τ	243(4.3)	PtC ^(H2) v
574(0.1)	CD δ _{op} /CD ₃ ρ _a	470(7.6)	PtC ^(H2) v	186(0)	PtC ^(H2) δ
447(0.3)	Pt ₂ C v _s	348(0)	Pt ₂ C ^(H) v _a		
342(0.1)	Pt ₂ C v _a	237(0)	Pt ₃ C ₂ δ _{ip}		
252(0.3)	Pt ₂ C δ	197(0)	Pt ₃ C ₂ δ _{op}		
129(0.1)	CD ₃ τ				
84(0.2)	FR				
83(0.1)	FR				

^a Notations used: v, stretching; δ, bending; τ, twisting; ω, wagging; ρ, rocking; a, asymmetric; s, symmetric; ip, in-plane; op, out-of-plane; FR, frustrated rotation.

^b Unit of frequency is cm⁻¹. Intensities are shown in brackets and scaled (%) by the strongest intensity mode of each species.

Figure captions

Figure 1. Optimized structures of ethynylidyne (CCH_3); di- σ ethylene (C_2H_4); vinyl (CHCH_2); ethylidyne (CHCH_3), and vinylidene (CCH_2).

Figure 2. Simulated IR spectra of stable surface species on Pt(111): (a) ethynylidyne CCH_3 at 1/3 ML and (b) di- σ ethylene C_2H_4 at 1/4 ML.

Figure 3. Simulated IR spectra of surface intermediates with 1/3 ML coverage on Pt(111): (a) vinyl CHCH_2 ; (b) vinylidene CCH_2 ; and (c) ethylidyne CHCH_3 .

Figure 4. Simulated IR spectra of deuterium substituted surface species on Pt(111): (a) ethynylidyne CCD_3 at 1/3 ML and (b) di- σ ethylene C_2D_4 at 1/4 ML.

Figure 5 Simulated IR spectra of surface intermediates with 1/3 ML coverage on Pt(111): (a) vinyl CDCH_2 ; (b) vinylidene CCD_2 ; and (c) ethylidyne CDCH_3 .

Figure 6 Simulated IR spectra of deuterium substituted surface species and intermediates on Pt(111): (a) 1/9 ML vinylidene CCD_2 (co-adsorbed with 2/9 ML ethynylidyne CCD_3), and (b) 1/9 ML ethylidyne CDCH_3 (co-adsorbed with 2/9 ML ethynylidyne CCH_3).

Figure 1. Optimized structures of ethynylidyne (CCH_3); di- σ ethylene (C_2H_4); vinyl (CHCH_2); ethylidene (CHCH_3), and vinylidene (CCH_2).

Figure 2 Simulated IR spectra of stable surface species on Pt(111): (a) ethylidyne CCH_3 at $1/3$ ML and (b) di- σ ethylene C_2H_4 at $1/4$ ML.

Figure 3 Simulated IR spectra of surface intermediates with 1/3 ML coverage on Pt(111): (a) vinyl CHCH_2 ; (b) vinylidene CCH_2 ; and (c) ethylidene CHCH_3 .

Figure 4 Simulated IR spectra of deuterium substituted surface species on Pt(111): (a) ethynidyne CCD_3 at $1/3$ ML and (b) di- σ ethylene C_2D_4 at $1/4$ ML.

Figure 5 Simulated IR spectra of surface intermediates with 1/3 ML coverage on Pt(111): (a) vinyl CDCD_2 ; (b) vinylidene CCD_2 ; and (c) ethylidene CDCD_3 .

Figure 6 Simulated IR spectra of deuterium substituted surface species and intermediates on Pt(111): (a) 1/9 ML vinylidene CCD_2 (co-adsorbed with 2/9 ML ethylidyne CCD_3), and (b) 1/9 ML ethylidyne CDCD_3 (co-adsorbed with 2/9 ML ethylidyne CCH_3).