Interfacial Cu⁺ Promoted Surface Reactivity: Carbon Monoxide Oxidation Reaction over Polycrystalline Copper-Titania Catalysts

Sanjaya D. Senanayake,^{a} Naa Adokaley Pappoe,^b Thuy-Duong Nguyen-Phan,^a Si Luo,^d
Yuanyuan Li,^e Wenqian Xu,^a Zongyuan Liu,^d Kumudu Mudiyansele,^a Aaron Johnston-Peck,^c
Anatoly I. Frenkel,^e Ilana Heckler,^d Dario Stacchiola,^a José A. Rodríguez^{a,d}*

^a Chemistry Department and ^c Center for Functional Nanomaterials (CFN),

Brookhaven National Laboratory, Upton, NY 11973

^b The City College of New York, New York, NY 10031

^d Department of Chemistry, Stony Brook University, Stony Brook, NY 11790

^e Department of Physics, Yeshiva University, New York, NY 10016

* Corresponding Author: ssenanay@bnl.gov (Sanjaya D. Senanayake)

ABSTRACT

We have studied the catalytic carbon monoxide (CO) oxidation ($\text{CO} + 0.5\text{O}_2 \rightarrow \text{CO}_2$) reaction using a powder catalyst composed of both copper (5wt% loading) and titania ($\text{CuO}_x\text{-TiO}_2$). Our study was focused on revealing the role of Cu, and the interaction between Cu and TiO_2 , by systematic comparison between two nanocatalysts, $\text{CuO}_x\text{-TiO}_2$ and pure CuO_x . We interrogated these catalysts under *in situ* conditions using X-ray Diffraction (XRD), X-ray Absorption Fine Structure (XAFS) and Diffuse Reflectance Infrared Fourier Transform Spectroscopy (DRIFTS) to probe the structure and electronic properties of the catalyst at all stages of the reaction and simultaneously probe the surface states or intermediates of this reaction. With the aid of several *ex situ* characterization techniques including Transmission Electron Microscopy (TEM), the local catalyst morphology and structure was also studied. Our results show that a $\text{CuO}_x\text{-TiO}_2$ system is more active than bulk CuO_x for the CO oxidation reaction due to its lower onset temperature and better stability at higher temperatures. Our results also suggest that a surface Cu^+ species observed in the $\text{CuO}_x\text{-TiO}_2$ interface are likely to be a key player in the CO oxidation mechanism, while implicating that the stabilization of this species is probably associated with the oxide-oxide interface. Both *in situ* DRIFTS and XAFS measurements reveal that there is likely to be a Cu(Ti)-O mixed oxide at this interface. We discuss the nature of this Cu(Ti)-O interface and interpret its role on the CO oxidation reaction.

GRAPHICAL ABSTRACT

1. INTRODUCTION

Carbon monoxide (CO) is a highly toxic compound that is an essential component in the synthesis gas used in many chemical operations and also a byproduct of numerous industrial and automotive processes which involve the combustion of fuels. Due to ever increasing emission standards, research has focused on limiting or remediating the emissions of this pollutant. CO oxidation has thus become a very important reaction to protect the environment and the health of the general population. The removal of CO can be achieved by the catalytic oxidation process that involves O₂ and also H₂ (CO PROX) conversion into carbon dioxide (CO₂):

This process is commonly used in industry at low temperatures [1] to clean carbon monoxide streams. The CO even at low concentration can affect the use of H₂ as a viable fuel, and CO₂ is a gas that is less toxic to the environment as opposed to carbon monoxide, but is nonetheless a major contributor to greenhouse gases. Typically, the types of catalyst used for this reaction involve expensive precious metals such as Au, Pt, Rh, Pd and oxide supports such as CeO_x, FeO_x and TiO_x. Studies by Yates and co-workers have shown that the metal-oxide interface plays a determinant role in the low-temperature oxidation of CO on Au-TiO₂ catalysts [2, 3]. The key steps in the catalytic CO oxidation process likely involve the following steps:

Some of these steps involve the, Langmuir – Hinshelwood (L-H) mechanism in which both reactants are adsorbed on the catalyst surface in order to form a bimolecular reaction and the Ely–Rideal (E-R) mechanism in which only one reactant is adsorbed firmly on the catalyst while the other strikes the adsorbates from the gas phase in order to form a bond without adsorbing [4]. Between these two mechanisms, the Langmuir-Hinshelwood (L-H) mechanism has been widely proposed yet can be element (catalyst), kinetic (reactant concentration) or thermodynamic (temperature) specific.

Oxide based catalysts have a natural selectivity towards redox processes and their lower costs and high abundance compared to that of pure noble metals such as gold, platinum, silver and palladium make them highly attractive as catalysts [5,6]. In addition, mixed oxides have provided new and unique properties beyond what is obtainable from mono-oxides [7]. These mixed oxides can either be in the form of naturally occurring solid solutions (one oxide inside another) or as one oxide in contact with another at a distinct interfacial boundary [8]. Often this interfacial oxide-oxide synergy can manifest in unique geometrical, chemical or electronic properties and thus influence catalytic selectivity, which can work either cooperatively or passively to enhance catalytic activity and sustain stability [9]. The true nature of this interfacial active sites is highly composition and element specific and also very sensitive to the type of reaction (*i.e.* oxidizing vs reducing, hydrogenation vs dehydrogenation, dehydration vs dehydrogenation, etc.) where it prevails. Understanding the role of these mixed metal oxide sites and the catalysts that

encompass them requires careful and systematic analysis often incorporating *in situ* methods that are sensitive to the active state under reaction conditions.

The aim of our study is to investigate one such a mixed oxide powder catalyst composed of CuO_x and TiO_2 , a cheaper alternative to noble metals, which is highly active for the CO oxidation reaction. In the case of mixtures of CuO_x and TiO_x , there is evidence reported previously of the generation of intermixed materials such as $\text{Cu}_x\text{Ti}_y\text{O}_z$ [10-12]. The nature of the stabilization of Cu^+ species in a CuO_x - TiO_x interface and a mixed oxide was investigated systematically over model surfaces using Infrared spectroscopy (IR) and proved to be critical for catalyzing the CO oxidation reaction [10] and the epoxidation of propylene [13]. Theoretical models of this system were also studied with careful observations of the nature of the Cu^+ surface species in CuO_x - TiO_x [14]. In this work we explore such an interface in polycrystalline Cu-TiO_2 , and also make comparisons with that of a base catalyst, CuO_x , to elucidate the role of Cu^+ and the CuO_x - TiO_2 interface using several *in situ* characterization techniques. The key questions we hope to answer about the CuO_x - TiO_2 catalyst include: what are the oxidation states of Cu {Cu (0), Cu_2O (1+), CuO (2+)} and Ti species {Ti (0), TiO_2 (4+), Ti_2O_3 (3+)} that prevail during the reaction, which components/sites are the most important/active, and what are their roles in the reaction? As shown by Yates and co-workers for the Au-TiO_2 system [2,3], we also find that an interface provides the best combination of reaction sites for catalyzing CO oxidation.

2. EXPERIMENTAL

Catalyst preparation

Powders of anatase TiO_2 (Aldrich) were calcined to 500 °C in air flow prior to incorporating a cupric nitrate precursor ($\text{Cu}(\text{NO}_3)_2$, Aldrich). The 5wt% CuO_x - TiO_2 catalyst was prepared by a deposition-precipitation method (DP) using Na_2CO_3 (Alfa Aesar) as the precipitating agent,

which was added to the TiO_2 and Cu precursor in order to keep a neutral pH of 7 at 70 °C. In these conditions, the copper precipitated as $\text{Cu}(\text{OH})_2$. The Cu/TiO_2 sample was calcined to 500 °C in air flow following the deposition-precipitation process. The reduction experiments of the $\text{CuO}_x\text{-TiO}_2$ in CO and the catalytic oxidation of CO were conducted at temperatures lower than 300 °C, much smaller than that of the calcination process at 500 °C. CuO_x samples were calcined in air to 500 °C prior to experiments.

STEM

The high resolution TEM images of the $\text{CuO}_x\text{-TiO}_2$ samples were taken using a High Angular Annular Dark Field Scanning Transmission Microscopy (HAADF STEM) instrument. The powder sample was dispersed as a suspension in deionized water, sonicated for 60 seconds then introduced in drops onto a Holey-C grid and allowed to dry before imaging. Electron energy loss spectroscopy (EELS) and energy disperse X-ray spectroscopy (EDS) chemical maps were acquired on a Hitachi 2700C operated at 200 kV using convergence semi-angles of 23 and 28 mrad, respectively.

XRD

The phases with long-range order (i.e. crystalline structure) in the catalyst were examined with X-ray diffraction. The XRD study was carried out on beamline X7B ($\lambda = 0.3196\text{\AA}$) of the National Synchrotron Light Source (NSLS) at Brookhaven National Laboratory (BNL). Powder samples of 2-3 mg were loaded into a silica capillary (0.9 mm ID, 1.0 mm OD) mounted in the flow cell system. A Perkin Elmer Amorphous Silicon Detector was used to collect two-dimensional transmission diffraction data, which were subsequently processed with the program Fit2D to obtain XRD profiles. Lattice parameters and phase quantities were analyzed by the Rietveld Refinement using the program GSAS.

Temperature-resolved XRD experiments under CO oxidation conditions were also performed at beamline X7B (NSLS). Around 2 mg powder samples were loaded in a 1.0 mm OD amorphous silica capillary installed to a flow reactor. Details of the flow reactor and the experiment setting can be found at ref [15]. The sample was pre-oxidized in 5% O₂/He at 300 °C for half an hour and cooled to room temperature. The gas environment was then changed to a mixture of 2.5% CO and 1.25% O₂ balanced in He. A stepwise heating program was used: the sample was heated to 100, 150, 200, 250 °C consecutively and held at each temperature step for 30 minutes. Between two steps, the heating rate was 10 °C/min. XRD data were continuously collected throughout the experiment.

XANES / EXAFS

XANES and EXAFS were used to detect the possible existence of amorphous or non-crystalline phases in the catalyst. Cu K-edge XANES data were collected in transmission mode at the beamline X19A (NSLS) using ionization chamber detectors for measuring incident and transmitted beam intensities. In addition, a third ionization chamber was used to detect the beam through a reference Cu foil, for energy calibration and alignment purposes. The flow micro-reactor and the sample were the same ones used in the XRD experiment. The fresh catalyst powders samples from the same batch were initially treated with helium at a flow rate of 10 ml/min at room temperature. Then 5% O₂/He mixture was introduced and the EXAFS data were collected. Afterwards, the CO oxidation reaction studies were performed under a 0.5%CO/0.25%O₂/He mixture and at the same temperatures as in XRD experiment described above, while collecting EXAFS data. Details of the flow micro-reactor, the experimental setup that combined XAFS and Raman spectroscopy capability, and the description of the results of

such combination can be found in Ref. [16]. In this work we focus on the structure of the pre-reaction state that was described previously as “unique” and not understood [16, 17].

DRIFTS

DRIFTS data were collected on $\text{CuO}_x\text{-TiO}_x$ and pure CuO_x under CO oxidation conditions using a Bruker Equinox 55 FTIR spectrometer equipped with a modified Harrick Praying Mantis DRIFTS cell that was connected to a gas flow system and a mass spectrometer. Carbon monoxide and oxygen with concentrations of 5%, 20%, in helium respectively, were allowed to flow through the sample. The gas flow rate used in this study was 10 cc/min. Stepwise heating and cooling with an increment of 50 °C, starting from room temperature up to 250 °C was applied. The temperature was held for 20-30 mins at each step where the temperature reading is stabilized. The composition of the outflow gas was analyzed with a mass spectrometer.

3. RESULTS

3.1 Local morphology

The STEM images shown in Figure 1 show the local morphology of an as prepared $\text{CuO}_x\text{-TiO}_2$ catalyst that is composed of small copper oxide nanoparticles (~2-6nm) located on TiO_2 (~10-50nm). The CuO_x appears highly dispersed on the TiO_2 particles and the Z-contrast between the Cu vs Ti allows us to distinguish the two oxides from each other. The STEM image on the right show a representative spherical CuO_x nanoparticle (~2nm) that wets TiO_2 yet is very 3-dimensional in shape with partial burial of CuO_x into the TiO_2 . The interface between the Cu and Ti oxides is clearly seen with no visible overlap in the perimeter lattice.

3.2 Bulk Structure

The ex situ powder diffraction pattern of the $\text{CuO}_x\text{-TiO}_2$ system shown in Figure 2 indicates the presence of three crystalline structures associated with CuO_x and the anatase and rutile

phases of TiO_2 . The peak intensity variations indicate that the catalyst is composed predominantly of anatase rather than rutile TiO_2 . The calculated compositions of the crystalline structures of anatase, rutile and CuO are 85%, 13% and 2%, respectively. The nominal loading of CuO_x is 5% thus there is likely to be either 3% non-crystalline or very finely dispersed CuO_x species present on this catalyst.

3.3 CO Oxidation Reactivity

A comparison of the reactivity of CuO_x and $\text{CuO}_x\text{-TiO}_2$ is presented in Figure 3. The left panel shows the mass spectroscopic profile of CO (black), O_2 (green), and CO_2 (red) gases during CO oxidation in a micro-reactor at incremental heating to temperatures of 100-250°C followed by cooling. The data shows the production of CO_2 (red) at temperatures that coincide with the consumption of CO and O_2 , identifying catalytic activity of both catalysts. The comparative rate of CO_2 production for CuO_x is small at 100°C, with an earlier onset of reaction for $\text{CuO}_x\text{-TiO}_2$. This trend is prevalent with increasing temperatures with a better performance of the $\text{CuO}_x\text{-TiO}_2$ catalyst. At 150°C almost near identical deactivation of both catalysts is observed with a slow decrease in CO_2 production as a function of time. Notably, at 200 °C the $\text{CuO}_x\text{-TiO}_x$ catalyst shows good stability against a gradually deactivating CuO_x . At 250 °C both catalysts are comparable in rate of conversion and also stability. The right panel exhibits the relative yields of CO_2 product over CuO_x reference and $\text{CuO}_x\text{-TiO}_2$ catalyst. A comparison is also made with the CuO_x sample normalized per unit loading (CuO_x Normalized) with respect to the 5wt% $\text{CuO}_x\text{-TiO}_2$. It is clear that mixed oxide catalyst shows higher activity than that of the reference regardless of reaction temperature.

***In situ* XRD**

We studied the changes to the crystalline bulk structure of $\text{CuO}_x\text{-TiO}_2$ during this reaction using *in situ* XRD (Figure 4) and monitored simultaneously the reactant to product conversion. A stack plot of five XRD profiles at each temperature step is shown in Figure 4 from 25°C, 100°C, 150°C, 200°C and 250°C. No change occurred to the structures of the TiO_2 phases (anatase and rutile). In contrast, the CuO phase, represented by its (002) peak at 7.3° of 2- θ , which is seen as a shoulder to the rutile (101) peak at 7.4°, decreased in intensity from 200 to 250 °C (inset Figure 4). The weight fraction of the CuO_x phase as a function of time and temperature is plotted in the inset of Figure 4. As the amount of CuO_x dropped, no other Cu-related phases like Cu_2O and Cu metal could be positively identified by XRD. Several possibilities may be considered for this newly formed Cu-phase including that they have (i) adopted very small particle sizes, or (ii) are transformed to amorphous or poorly crystalline structure in nature, or (iii) intermixing (CuO_x and TiO_2) into the formation of a $\text{Cu}_x\text{Ti}_y\text{O}_z$ structure that is not visible to the detection by XRD. It is interesting to note that massive reduction of CuO occurred at 200 °C (Figure 4), when the production of CO_2 dramatically increased. Clearly, the conversion of CuO to CuO_{1-x} led to the formation of an active phase responsible for the CO oxidation activity. From previous experiments with Cu-CeO_x for CO oxidation under nominally similar conditions we identified Cu (I) as the active component for this reaction [18].

***In Situ* DRIFTS**

To understand the surface chemistry occurring on this $\text{CuO}_x\text{-TiO}_2$ catalyst we performed *in situ* DRIFTS under CO oxidation conditions similar to measurements described earlier. Figure 5 shows infrared spectra recorded while CuO_x (left-side panel) and $\text{CuO}_x\text{-TiO}_2$ (right-side panel) are heated to elevated temperatures incrementally (25, 100, 150, 200 and 250°C) under CO oxidation conditions.

In the panel for $\text{CuO}_x\text{-TiO}_2$ in Figure 5 (right-side), an intense peak appears at $2100\text{-}2120\text{ cm}^{-1}$ for the CO adsorbed on Cu^+ sites. This peak overlaps with one of the gas phase CO bands (the CO gas phase feature is centered at 2143 cm^{-1}). It is notably absent on the CuO_x catalyst (left-side panel). For $\text{CuO}_x\text{-TiO}_2$, the CO adsorbed on Cu^+ peak gradually decreases as the temperature increases and is small at 250°C . The decrease of the $\text{Cu}^+\text{-CO}$ peak with temperature is probably a consequence of a reduction in the number of adsorbed CO molecules. In fact, the concentration of Cu^+ in the system is probably increasing as a consequence of intermixing in the oxide-oxide interface (see inset in Figure 4). It has been reported that $\text{Cu}^+\text{-carbonyls}$ have higher frequency than 2120 cm^{-1} , ranging from 2164 to 2230 cm^{-1} [19]. The adsorbed CO on Cu^+ observed in our study is different from organometallic carbonyl compounds and hence frequencies are different. It is well known that adsorption of CO on metallic Cu is weak and not observed under the condition used in our study on powder catalysts but CO adsorbed on Cu^+ is stable and gives a peak around 2120 cm^{-1} [20,21]. Herein, no evidence showing the presence of two different types of adsorbed CO has been observed. Moreover, at 50°C a new peak appears at 2349 cm^{-1} in Figure 5 corresponding to the gas phase CO_2 indicative of the start of the CO oxidation reaction.

The left-side panel in Figure 5 shows infrared spectra recorded with CuO_x as it is heated to different temperatures under identical CO oxidation conditions. At 25°C , only gas phase CO bands centered at 2143 cm^{-1} are seen. At 150°C , a peak appears at 2349 cm^{-1} for the gas phase CO_2 indicating the beginning of the CO oxidation reaction. The intensity of the peak for gas phase CO_2 at 2349 cm^{-1} increased as the temperature is raised. A similar trend is observed in the panel for $\text{CuO}_x\text{-TiO}_2$ but, at any given temperature, the intensity for the features for CO_2 formation is always larger on the mixed-oxide system.

These DRIFTS data agree well with the *in situ* XRD and reactivity data presented earlier and show that there is a strong correlation between the activity of both CuO_x and $\text{CuO}_x\text{-TiO}_2$ to the consumption of $\text{CO}+\text{O}_2$ and the production of CO_2 . We can confirm that the process involves a transformation of CuO to CuO_{1-x} based on the XRD and XAFS data and the likely presence of CO-Cu^+ . The nature of the Cu^+ species can be further correlated to studies we have performed previously on $\text{CuO}_x\text{-TiO}_2$ model surfaces where an intermixed $\text{Cu}_x\text{Ti}_y\text{O}_z$ bound CO was identified and may prevail on this surface as an active ingredient for this reaction [10,12].

3.4 Local structure and electronic properties of Cu in $\text{CuO}_x\text{-TiO}_2$

Figure 6 shows the normalized Cu K-edge XANES (left) and Fourier transformed $k^2\chi(k)$ (right) data of 5wt% CuO/TiO_2 collected before the CO oxidation reaction (under O_2 at 25 °C), and the reference bulk oxides: CuO and Cu_2O . Both XANES and EXAFS spectra of $\text{CuO}_x\text{-TiO}_2$ are distinctly different from those of standard copper oxides, which indicate that the local environment of Cu in the $\text{CuO}_x\text{-TiO}_2$ sample is different from that in the oxides. This species is suggested to be in +2 valence state based on the existence of a weak pre-edge peak at about 8979 eV in XANES spectrum (Figure 6 (left)). This pre-edge peak appears in most Cu(II) compounds and could be regarded as a signature for a divalent copper. It represents the quadrupole-allowed $1s \rightarrow 3d$ transition, suggesting the presence of hole in the copper 3d orbitals in $\text{CuO}_x\text{-TiO}_2$ sample. For Cu (0) and Cu (I) compounds with $3d^{10}$ configuration, such pre-edge peak should not be expected. Other than the pre-edge region, spectral differences can also be observed in rising edge and maximum in XANES spectrum between $\text{CuO}_x\text{-TiO}_2$ and copper oxides. Compared to XANES spectra of copper oxides, the shoulder at the rising edge is absent and the intensity of the maximum is higher in XANES spectrum of $\text{CuO}_x\text{-TiO}_2$. The shoulder at the rising edge and the maximum are usually assigned to the dipole allowed $1s \rightarrow 4p$ transition, and

their intensities and positions/energies associate with neighboring atomic geometry [22,23]. In Cu_2O , each copper atom forms two collinear bonds with oxygen atoms which results in the split of 4p orbitals into $4p_{xy}$ and $4p_z$. The shoulder at the rising edge is assigned to $\text{Cu } 1s \rightarrow 4p_{xy}$ transition while the maximum represents $\text{Cu } 1s \rightarrow 4p_z$ transition. In CuO , each copper atom is surrounded by four nearest oxygen atoms and forms a nearly planar structure, which also causes the split of 4p orbitals to $4p_{xy}$ and $4p_z$. Due to the $3d^9$ configuration, the shoulder at the rising edge is assigned to $\text{Cu } 1s \rightarrow 4p_{xy} + \text{shakedown}$ transition and the maximum is ascribed to $1s \rightarrow 4p_z$ transition [24,25]. For $\text{CuO}_x\text{-TiO}_2$, one likely reason for the absence of shoulder peak and the presence of intense white line in XANES spectrum is the modification of local geometry around Cu, which in turn changes the 4p configuration. The unique local atomic structure around Cu in $\text{CuO}_x\text{-TiO}_2$ can also be observed in EXAFS spectra (Figure 6 (right)). For all three spectra, there are two distinct peaks. One locates at about 1.5 Å and another at about 2.5 Å. The former is ascribed to Cu-O contribution and the latter to Cu-M (metal) contribution. It can be clearly seen that the Cu-O peak in the spectrum of $\text{CuO}_x\text{-TiO}_2$ is quite intense and the position of Cu-M peak shifts to lower distance compared with those of Cu_2O and CuO . To understand the structural nature of such new copper species in $\text{CuO}_x\text{-TiO}_2$ sample, EXAFS data for $\text{CuO}_x\text{-TiO}_2$ were analyzed and quantitative results for coordination numbers (N) and bond distances (R) for Cu-O and Cu-M bonds were obtained by fitting theoretical EXAFS signals to experimental data. Four different models of local environment of Cu were used for data analysis: (i) Cu-O and Cu-Cu (the latter contribution was extracted from the CuO structure), (ii) Cu-O and Cu-Cu (the latter contribution was extracted from Cu metal), (iii) Cu-O and Cu-Ti (Cu-Ti path was created by substituting Ti by Cu in anatase TiO_2 lattice), and (iv) Cu-O, Cu-Ti and Cu-Cu. Among these four models, only the third model gave a good fit (Figure 7). This model describes the

substitutional mechanism of incorporation of Cu into TiO₂ support. To this copper species, the coordination number of Cu-O pair is 4.1 ± 0.5 and Cu-Ti pair: 1.4 ± 0.8 . The distances of Cu-O and Cu-Ti bonds are 1.942 ± 0.009 Å and 2.94 ± 0.02 Å, respectively.

In this third model all Cu-O pairs were assumed to have identical bond length and disorder. That assumption is needed, in order to lower the number of variables in the fit and satisfy Nyquist criterion [26]. From the analysis of a standard CuO system we know that such approximation causes an unphysical reduction of the coordination number indicating that different Cu-O bonds do, in fact, have different disorder factors. If approximated by a constant disorder an apparent reduction of coordination number follows [27]. Therefore, the coordination number of ca. 4 obtained for the Cu(Ti)-O sample can be also underestimated. Our XANES analysis (vide infra) shows that, indeed, an octahedral (N=6) environment of Cu is more consistent with experimental data.

As mentioned above, spectral features along the rising edge in XANES reflect local geometry around Cu atoms. Such geometrical characteristics can be obtained by first principle modeling of Cu K-edge XANES signals and are expected to be in good agreement with those derived from EXAFS analysis, for both XANES and EXAFS modeling to be valid. The XANES spectra were calculated using FEFF 9 code [28]. Simulations were first performed on copper oxides (CuO and Cu₂O) for finding optimized conditions for FEFF calculations. For all calculations, identical parameters were used to account for experimental broadening in all spectra that were all measured using same experimental setups. In calculating the XANES spectrum of the CuO_x-TiO₂ sample, the same model was used as in EXAFS analysis. In this model, Cu substitutes Ti atom and thus bonds with six oxygen atoms in octahedral symmetry (two of them are along the axial direction). The calculated XANES spectra are shown in Figure 8. The lack of the shoulder

at the rising edge, the right shift of the rising edge and the higher intensity of the maximum, all these features shown in the experimental data of $\text{CuO}_x\text{-TiO}_2$ compared to copper oxides (Figure 6 (left)) are also exhibited in the calculated spectrum for Cu(Ti)-O models designed with symmetric octahedral geometry. On the basis of the EXAFS and XANES results, it can thus be concluded that for the $\text{CuO}_x\text{-TiO}_2$ sample, Cu substitutes Ti atom and adopts the same geometry as Ti in the anatase lattice. Additionally, the fact that the shoulder peak shows up for Cu_2O and CuO , systems that possess linear and square planar geometries, respectively, while disappears for Cu(Ti)-O with octahedral geometry, suggests that additional neighboring oxygen atoms along axial direction in the local structure of Cu in the catalyst sample are responsible for the absence of the shoulder peak caused by the splitting of the 4p orbitals.

DISCUSSION

Both $\text{CuO}_x\text{-TiO}_2$ and CuO_x showed activity for the CO oxidation reaction, but $\text{CuO}_x\text{-TiO}_2$ has improved CO_2 production even at lower temperature, extended stability and better performance per Cu loading. Our results identify that the likely source of this chemistry may be attributed to several possibilities, including better dispersion of small Cu nanoparticles, the interaction between Cu and Ti either at the interface or as a mixed oxide, and the prevalence of Cu^+ on the catalyst surface. The surface chemistry and likely mechanism observed on both surface appears to be strikingly different. We demonstrate that the active catalyst surface structure can be used to tailor reaction pathways. This Cu^+ species is not observed on CuO_x despite some CO oxidation activity. The location of the Cu^+ species may likely be at the interface between Cu and Ti oxides where a mixed oxide of $\text{Cu}_x\text{Ti}_y\text{O}_z$ forms and we propose is active agent in CO oxidation. The evidence for this species forming at reaction conditions is clear from the assignment of the CO- Cu^+ species ($2100\text{-}2120\text{cm}^{-1}$) from *in situ* DRIFTS experiments, but which was also implicated

in studies over well-defined surface models [10] and DFT [14] for CO oxidation. However, it is important to note that in our polycrystalline $\text{CuO}_x\text{-TiO}_2$ catalyst, this Cu^+ rich interface is not optimized, despite high dispersion of Cu, and the likely active sites are limited to the contact points or perimeters around the Cu nanoparticles on TiO_2 . We propose that a strategy to further improve CO oxidation activity would be to atomically disperse Cu, and extend the $\text{CuO}_x\text{-TiO}_2$ interaction further through stabilization of smaller nanostructured units rich in Cu^+ . This may be an important insight for even other heterogeneous oxidation reactions, implicating that the presence of the Cu^+ sites facilitates an improved pathway for catalytic activity.

Previous studies by Yates and co-workers showed the importance of the metal-oxide interface for the low temperature oxidation of CO on Au/TiO_2 [2,3]. An oxide-oxide interface is probably responsible for the high CO oxidation activity of $\text{CuO}_x\text{-TiO}_2$. At an interface the formation of chemical bonds can modify the electronic and chemical properties of a material enhancing its catalytic activity. Furthermore, at an interface one can combine elements that have different chemical behavior which can work in a cooperative way in different steps of a catalytic process [2,3]. The results in our present study exhibit the higher activity of Cu-TiO_x for the CO oxidation and the stability of Cu^+ under the reaction conditions as similar to the previous studies on model systems [10,12]. The stability of Cu^+ in model systems is due to the formation of CuTiO_x mixed oxide. Therefore, the comparison of results on powder and model systems suggests that the formation of mixed oxide on powder system leads to the stabilization of Cu^+ which enhances the activity for CO oxidation. Based on this we present the following steps in the reaction mechanism

4. CONCLUSIONS

We have studied the catalytic CO oxidation to CO₂ using a novel mixed-oxide catalyst composed of CuO_x and TiO₂ and compared it to unsupported CuO_x. This mixed-oxide catalyst is more active for this reaction than either CuO_x or TiO₂ on its own. With the use of XRD, TEM and DRIFTS we were able to identify the local morphology, bulk structure and surface states that prevailed when the CO and O₂ reacted to produce CO₂. We discovered that the CuO_x-TiO₂ has a unique structure that helped to lower the CO oxidation reaction temperature, and that the interface between the CuO_x-TiO₂ as an intermixed oxide (Cu_xTi_yO_z) provide for the stabilization of CO-Cu⁺ that is likely to be an important part of this reaction.

AUTHOR INFORMATION

Corresponding Author

* ssenanay@bnl.gov (Sanjaya D. Senanayake)

NOTES

The authors declare no competing financial interest.

ACKNOWLEDGEMENTS

The research carried out in this manuscript was performed at Brookhaven National Laboratory, supported by the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences, and Catalysis Science Program under contract No. DE-SC0012704. This work used resources of the National Synchrotron Light Source (NSLS) and the Center for Functional Nanomaterials (CFN), that are DOE Office of Science User Facilities. AIF and YL gratefully acknowledge funding of their work by the U. S. DOE Grant No. DE-FG02-03ER15476. The

authors acknowledge the facilities support provided at the Synchrotron Catalysis Consortium (U.S. DOE Grant No. DE-SC0012335).

REFERENCES

- [1] J.S. Spendelow, J.D. Goodpaster P.J.A. Kenis A. Wieckowski, Mechanism of CO Oxidation on Pt(111) in Alkaline Media, *J. Phys. Chem. B* 110 (2006) 9545-9555.
- [2] I.X. Green, W. Tang, M. Neurock, J.T. Yates Jr., Spectroscopic Observation of Dual Catalytic Sites During Oxidation of CO on a Au/TiO₂ Catalyst, *Science* 333 (2011) 736-739.
- [3] I.X. Green, W. Tang, M. Neurock, J.T. Yates Jr., Low-Temperature Catalytic H₂ Oxidation over Au Nanoparticle/TiO₂ Dual Perimeter Sites, *Angew. Chem. Int. Ed.* 50 (2011) 10186-10189.
- [4] R.S. Johnson, A. DeLaRiva, V. Ashbacher, B. Halevi C.J. Villanueva, G.K. Smith S. Lin A.K. Datye, H. Guo, The CO Oxidation Mechanism and Reactivity on PdZn Alloys, *Phys. Chem. Chem. Phys.* 15 (2013) 7768-7776.
- [5] N.O. Savage, S.A. Akbar, P.K. Dutta, Titanium Dioxide based High Temperature Carbon Monoxide Selective Sensor, *Sens. Actuators B* 72 (2001) 239-248.
- [6] G. Xanthopoulou, G. Vekinis, Investigation of Catalytic Oxidation of Carbon Monoxide over a Cu-Cr-Oxide Catalysts made by Self-Propagating High-Temperature Synthesis, *Appl. Catal. B* 19 (1998) 37-44.
- [7] D.J. Stacchiola, S.D. Senanayake, P. Liu, J.A. Rodriguez, Fundamental Studies of Well-Defined Surfaces of Mixed-Metal Oxides: Special Properties of MO_x/TiO₂(110) {M = V, Ru, Ce, or W}, *Chem. Rev.* 113 (2013) 4373-4390.

- [8] A.C. Johnston-Peck, S.D. Senanayake, J.J. Plata, S. Kundu, W. Xu, L. Barrio, J. Graciani, J.F. Sanz, R.M. Navarro, J.L.G.; Fierro, E.A. Stach, J.A. Rodriguez, Nature of the Mixed-Oxide Interface in Ceria–Titania Catalysts: Clusters, Chains, and Nanoparticles, *J. Phys. Chem. C* 117 (2013) 14463-14471.
- [9] S. Luo, T.-D. Nguyen-Phan, A.C. Johnston-Peck, L. Barrio, S. Sallis, D.A. Arena, S. Kundu, W. Xu, L.F.J. Piper, E.A. Stach, D.E. Polyansky, E. Fujita, J.A. Rodriguez, S.D. Senanayake, Hierarchical Heterogeneity at the CeO_x – TiO_2 Interface: Electronic and Geometric Structural Influence on the Photocatalytic Activity of Oxide on Oxide Nanostructures, *J. Phys. Chem. C* 119 (2015) 2669-2679.
- [10] A.E. Baber, X. Yang, H.Y. Kim, K. Mudiyansele, M. Soldemo, J. Weissenrieder, S. Senanayake, A. Al-Mahboob, J.T. Sadowski, J. Evans, J.A. Rodriguez, P. Liu, F.M. Hoffmann, J.G. Chen, D.J. Stacchiola, Stabilization of Catalytically Active Cu^+ Surface Sites on Titanium–Copper Mixed-Oxide Films, *Angew. Chem. Int. Ed.* 53 (2014) 5336-5340.
- [11] D.J. Stacchiola, Tuning the Properties of Copper-Based Catalysts Based on Molecular in Situ Studies of Model Systems, *Acc. Chem. Res.* 48 (2015) 2151-2158.
- [12] K. Mudiyansele, S. Luo, H.Y. Kim, X. Yang, A.E. Baber, F.M. Hoffmann, S. Senanayake, J.A. Rodriguez, J.G. Chen, P. Liu, D.J. Stacchiola, How to Stabilize Highly Active Cu^+ Cations in a Mixed-Oxide Catalyst, *Catal. Today.* 263 (2016) 4-10.
- [13] X. Yang, S. Kattel, K. Xiong, K. Mudiyansele, S. Rykov, S.D. Senanayake, J.A. Rodriguez, P. Liu, D.J. Stacchiola, J.G. Chen, Direct Epoxidation of Propylene over

- Stabilized Cu⁺ Surface Sites on Titanium-Modified Cu₂O, *Angew. Chem. Int. Ed.* 54 (2015) 11946-11951.
- [14] H.Y. Kim, P. Liu, Complex Catalytic Behaviors of CuTiO_x Mixed-Oxide during CO Oxidation, *J. Phys. Chem. C* 119 (2015) 22985-22991.
- [15] J.A. Rodriguez, R. Si, J. Evans, W. Xu, J.C. Hanson, J. Tao, Y. Zhu, Active Gold-Ceria and Gold-Ceria/Titania Catalysts for CO Oxidation: From Single-Crystal Model Catalysts to Powder Catalysts, *Catal. Today* 240 (2015) 229-235.
- [16] A. Patlolla, P. Baumann, W. Xu, S.D. Senanayake, J.A. Rodriguez, A.I. Frenkel, Characterization of Metal-Oxide Catalysts in *Operando* Conditions by Combining X-Ray Absorption and Raman Spectroscopies in the Same Experiment, *Top. Catal.* 56 (2013) 896-904.
- [17] A.I. Frenkel, Q. Wang, N. Marinkovic, J.G. Chen, L. Barrio, R. Si, A.L. Camara, A.M. Estrella, J.A. Rodriguez, J.C. Hanson, Combining X-Ray Absorption and X-Ray Diffraction Techniques for In Situ Studies of Chemical Transformations in Heterogeneous Catalysis: Advantages and Limitations, *J. Phys. Chem. C* 115 (2011) 17884-17890.
- [18] S.Y. Yao, W.Q. Xu, A.C. Johnston-Peck, F.Z. Zhao, Z.Y. Liu, S. Luo, S.D. Senanayake, A. Martínez-Arias, W.J. Liu, J.A. Rodriguez, Morphological Effects of the Nanostructured Ceria Support on the Activity and Stability of CuO/CeO₂ Catalysts for the Water-Gas Shift Reaction, *Phys. Chem. Chem. Phys.* 16 (2014) 17183-17195.
- [19] S.H. Strauss, Copper(I) and Silver(I) Carbonyls. To Be or Not To Be Nonclassical, *J. Chem. Soc., Dalton Trans.* (2000) 1-6.

- [20] J.C. Hanson, R. Si, W. Xu, S.D. Senanayake, K. Mudiyansele, D. Stacchiola, J.A. Rodriguez, H. Zhao, K.A. Beyer, G. Jennings, K.W. Chapman, P.J. Chupas, A. Martínez-Arias, Pulsed-Reactant *In Situ* Studies of Ceria/CuO Catalysts using Simultaneous XRD, PDF and DRIFTS Measurements, *Catal. Today* 229 (2014) 64-71.
- [21] S. Yao, K. Mudiyansele, W. Xu, A.C. Johnston-Peck, J.C. Hanson, T. Wu, D. Stacchiola, J.A. Rodriguez, H. Zhao, K.A. Beyer, K.W. Chapman, P.J. Chupas, A. Martínez-Arias, R. Si, T.B. Bolin, W. Liu, S.D. Senanayake, Unraveling the Dynamic Nature of a CuO/CeO₂ Catalyst for CO Oxidation in *Operando*: A Combined Study of XANES (Fluorescence) and DRIFTS, *ACS Catal.* 4 (2014) 1650-1661.
- [22] L.S. Kau, D.J. Spira-Solomon, J.E. Penner-Hahn, K.O. Hodgson, E.I. Solomon, X-ray Absorption Edge Determination of the Oxidation State and Coordination Number of Copper. Application to the Type 3 Site in *Rhus Vernicifera* Laccase and Its Reaction with Oxygen, *J. Am. Chem. Soc.* 109 (1987) 6433-6442.
- [23] S.E. Shadle, J.E. Penner-Hahn, H.J. Schugar, B. Hedman, K.O. Hodgson, E.I. Solomon, X-ray Absorption Spectroscopic Studies of the Blue Copper Site: Metal and Ligand K-Edge Studies to Probe the Origin of the EPR Hyperfine Splitting in Plastocyanin, *J. Am. Chem. Soc.* 115 (1993) 767-776.
- [24] C.H. Chou, W.F. Pong, I.N. Lin, S.F. Tsai, X-ray Absorption Fine Structure (XAFS) Study of the High-T_c Superconductor Pb-Bi-Sr-Ca-Cu-O System, *Chin. J. Phys.* 29 (1991) 263-282.

- [25] N. Kosugi, H. Kondoh, H. Tajima, H. Kuroda, Cu K-edge XANES of $(\text{La}_{1-x}\text{Sr}_x)_2\text{CuO}_4$, $\text{YBa}_2\text{Cu}_3\text{O}_y$ and Related Cu Oxides. Valence, Structure and Final-State Effects on $1s$ - $4p\pi$ and $1s$ - $4p\sigma$ Absorption, Chem. Phys. 135 (1989) 149-160.
- [26] E.A. Stern, Number of Relevant Independent Points in X-ray-Absorption Fine-Structure Spectra, Phys. Rev. B Condens. Matter. 48 (1993) 9825-9827.
- [27] A. Yevick, A.I. Frenkel, Effects of Surface Disorder on EXAFS Modeling of Metallic Clusters, Phys. Rev. B 81 (2010) 115451.
- [28] J.J. Rehr, J.J. Kas, F.D. Vila, M.P. Prange, K. Jorissen, Parameter-Free Calculations of X-ray Spectra with FEFF9, Phys. Chem. Chem. Phys. 12 (2010) 5503-5513.

Figure 1. Scanning Transmission Electron Micrographs (HAADF – STEM) of as prepared CuO_x-TiO_x catalyst.

Figure 2. X-ray Diffraction (XRD) of as prepared $\text{CuO}_x\text{-TiO}_x$ catalyst.

Figure 3. CO oxidation activity of CuO_x and CuO_x-TiO_x catalysts at 100 °C, 150 °C, 200 °C and 250 °C: (left) mass spectroscopic profile of residual gases during CO oxidation over CuO_x-TiO_x; (right) Relative CO₂ yield over CuO_x and CuO_x-TiO_x catalysts, with comparison to a CuO_x that is normalized with respect to Cu loading for comparison.

Figure 4. *In situ* XRD of CuO_x-TiO_x catalysts at 100°C, 150°C, 200°C and 250°C, inset of CuO_x fraction as a function of temperature. Experimental conditions: powder sample loaded in an amorphous silica capillary installed to a gas flow reactor. XRD patterns were collected continuously during *operando* CO oxidation that was described in detail above.

Figure 5. DRIFTS data from CuO_x (left) and $\text{CuO}_x\text{-TiO}_x$ (right) catalysts at 25°C, 50°C, 100°C, 150°C, 200°C and 250°C under CO oxidation reaction conditions. Experimental conditions: DRIFTS cell was connected to a gas flow system and a mass spectrometer. The reactant composition was 5%CO and 20% O_2 balanced in H_2 with 10 cc/min.

Figure 6. XANES (left) and EXAFS (right) data of the 5wt% CuO_x-TiO₂ sample before the CO oxidation reaction, at 25 °C, under O₂ flow. XAFS spectra of copper oxides were reproduced from previous work [16] and shown here for comparison.

Figure 7. EXAFS data and fit. The fitting k range is $3\text{-}11 \text{ \AA}^{-1}$ and R range is $1.0\text{-}2.8 \text{ \AA}$.

Figure 8. Simulated XANES spectra for CuO, Cu₂O and Cu(Ti)-O with octahedral geometry.