Ni(II)NTA AuNPs as a Low-Resource Malarial Diagnostic Platform for the Rapid Colorimetric Detection of *Plasmodium falciparum* Histidine-Rich Protein-2

Christopher P. Gulka, Joshua, D. Swartz, David W. Wright*

Department of Chemistry, Vanderbilt University, Station B 351822-1822, Nashville, TN 37235-1822, United States

Corresponding author: David W. Wright. email: david.wright@vanderbilt.edu. phone: 615-322-2636. Fax: 615-322-1234.

Abstract:

Diagnosing infectious diseases remains a challenge in the developing world where there is a lack of dependable electricity, running water, and skilled technicians. Although rapid immunochromatographic tests (RDTs) have been deployed to diagnose diseases such as malaria, the extreme climate conditions encountered in these regions compounded with the discrepancies in test manufacturing have yielded varying results, so that more innovative and robust technologies are sought. Devoid of antibodies and thermally sensitive materials, we present a robust, colorimetric diagnostic platform for the detection of a malarial biomarker, *Plasmodium falciparum* Histidine-Rich Protein 2 (*Pf*HRP-II). The assay exploits the optical properties of gold nanoparticles, covalently coupling them to a Ni(II)NTA recognition element specific for *Pf*HRP-II. In the presence of the recombinant malarial biomarker (rcHRP-II), the Ni(II)NTA AuNPs begin to crosslink and aggregate in as little as one minute, triggering a red-to-purple color change in solution. To increase assay sensitivity and platform stability suitable for low-resource regions, the Ni(II)NTA AuNPs were assembled with varying spacer ligands in a mixed monolayer presentation. When assembled with a negatively charged Peg₄-thiol ligand, the Ni(II)NTA AuNPs demonstrate low nanomolar limits of rcHRP-II detection in physiological concentrations of human serum albumin and maintain excellent stability at 37°C when stored for four weeks. Detection of the malaria biomarker is also measured by capturing and processing images of aggregated gold nanoparticles with a smartphone camera. By utilizing a smartphone camera and image processing application, there is no significant difference in assay sensitivity and rcHRP-II limit of detection in comparison to a spectrophotometer, further making this diagnostic platform applicable for use in low-resource regions.

Keywords: Ni(II)NTA; Gold nanoparticles; Malaria; Low-resource diagnostics; Histidine-rich proteins; Smartphone technology

1
2
3
4 Corresponding author: David W. Wright
5 Email: David.wright@vanderbilt.edu
6
7 Phone: 615-322-2636
8 Fax: 615-343-1234
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1. Introduction

In the developing world, early, rapid, and accurate diagnosis is essential to control epidemics and curb resistance for diseases such as tuberculosis, HIV/AIDS, and malaria. Unfortunately, high healthcare costs in these regions compounded with a lack of reliable electricity, a lack of skilled technicians, and a minimal infrastructure burdens disease diagnosis. For malaria, a parasitic disease that threatens most of the developing world each year, rapid point-of-care diagnostic devices are necessitated. In order to combat diagnosis issues presented in the developing world, immunochromatographic rapid diagnostic strip tests (RDTs) have been distributed to detect malarial infection in as little as 15-30 minutes by capturing *Plasmodium falciparum* malarial parasitic antigens in patient blood samples [1]. In 2011, the World Health Organization (WHO) implemented an assessment of these strip tests and determined that only 20% retained the 200-2000 parasites/ μ L threshold range in patient blood samples recommended by the WHO [2]. One of the primary explanations for test failure included antibody degradation from long-term storage in the extreme climates encountered in low-resource regions. As a result, innovative, sensitive, and robust approaches for antigen recognition are necessitated for accurate malaria diagnosis.

Upon infection, the *Plasmodium falciparum* parasite secretes 97% of its synthetic biomarker protein, Histidine-Rich Protein-2 (*PfHRP-II*), into the host's blood, offering an attractive biomarker for disease diagnosis [3]. However, recent discoveries have revealed that *P. falciparum* strains in Senegal and India have exhibited genetic diversity, and polymorphisms in the *PfHRP-II* antigen have been discovered, further complicating diagnosis via immunoassay platforms [4,5]. Approximately ~85% of the primary

1
2
3
4 structure of *Pf*HRP-II is comprised of AHH and AHHAAD repeats, so that targeting
5
6 these histidine subunit repeats offers an alternative approach for molecular recognition
7
8
9 [6]. Ni(II)Nitrilotriacetic acid (NTA) chelation has been well established as a strategy to
10
11 extract and isolate His-tagged proteins, and this octahedral organometallic complex
12
13 retains micromolar affinity to histidine by coordinating two amino acid subunits per
14
15 molecule [7-10]. Considering *Pf*HRP-II is a naturally occurring His-tagged protein,
16
17
18 Ni(II)NTA complexes have the potential to coordinate multiple repeats per protein.
19
20

21 The coupling of a Ni(II)NTA recognition component to a more robust and
22
23 sensitive platform would alleviate many of the aforementioned issues with existing
24
25 RDTs. Colloidal gold nanoparticles offer a desirable signal transduction approach
26
27 because of their unique optical properties and biologically inert surface. In the presence
28
29 of visible light, the electrons at the AuNP particle surface oscillate in-phase with the
30
31 incident radiation, so that monodisperse colloids exhibit a narrow localized surface
32
33 plasmon resonance (LSPR) band in the visible spectrum, thus transmitting bright red
34
35 colors in solution. The LSPR signal is sensitive to changes in the dielectric environment
36
37 encompassing the particles, inspiring applications in both sensor and diagnostic
38
39 development. Shifting the LSPR band can be induced by the physical aggregation of as
40
41 little as 2-10 particles, which ultimately triggers a color change in solution [11-13].
42
43
44 Although the gold surface is understood to be biologically inert, colloidal gold
45
46 nanoparticles are well known for their facile ligand coupling via covalent Au-thiol
47
48 chemistry, providing a robust and stable interface capable of enduring the extreme
49
50 climates typically found in South America, sub-Saharan Africa, and southern Asia where
51
52 malaria is endemic [14]. By exploiting these properties, colloidal gold nanoparticles have
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 been well established as aggregation-induced colorimetric sensors for detection of nucleic
5
6 acids, proteins, small molecules, and metal ions [15-19].
7
8

9 In this investigation, we aim to create a robust, low-resource colorimetric
10
11 indicator for malaria diagnosis by selectively and rapidly aggregating Ni(II)NTA AuNPs
12
13 only in the presence of a recombinant *Pf*HRP-II (rcHRP-II) biomarker, triggering a
14
15 spectrophotometric redshift and subsequently, a red-to-purple color change (Figure 1). A
16
17 custom, thiolated Ni(II)NTA recognition ligand has been previously synthesized and
18
19 validated in our lab as a proof-of-concept design with Ni(II)NTA Au and AgNPs by
20
21 detecting histidine-rich peptide mimics [20]. However, the activity of Ni(II)NTA AuNPs
22
23 has never been assessed against *Pf*HRP-II and the limits of detection for the peptide
24
25 mimics are outside of the clinically relevant range for malaria diagnosis. We also aspire
26
27 to optimize the AuNP platform with varying spacer ligands for enhanced signal and
28
29 stability, along with validating the diagnostic utility of these particles in a complex
30
31 physiological matrix, mimicking patient samples. Additionally, smartphones are
32
33 emerging as rapid detection technologies in the medical industry, especially through the
34
35 use of high dynamic range cameras and image processing applications. The rapid
36
37 colorimetric detection of explosives, pH, and disease biomarkers has been previously
38
39 detected and analyzed using smartphone technology and processing [21-24]. The ability
40
41 to capture a color image of aggregated nanoparticles with a smartphone and subsequently
42
43 analyze the respective signal intensity using an application would reduce user bias and
44
45 aid in low-resource diagnosis of infectious diseases.
46
47
48
49
50
51
52
53
54

55 **2. Experimental**

56 *2.1. Materials and reagents*

57
58
59
60
61
62
63
64
65

1
2
3
4 Citrate-stabilized gold nanoparticles (15 nm) were purchased from Ted Pella, Inc. Thiol-
5
6 dPeg₄-acid (Peg₄) was purchased from Quanta Biodesign, Ltd. Recombinant *P.*
7
8 *falciparum* Histidine-Rich Protein-II (rcHRP-II) was purchased from CTK Biotech. The
9
10 thiolated NTA recognition ligand was synthesized previously in our lab. 11-
11
12
13
14 Mercaptoundecanoic acid (MUA) and 6-mercaptohexanol (MHOL) were both purchased
15
16 from Sigma Aldrich. The confounding proteins, human serum albumin (HSA) and
17
18 glutathione-S-transferase (GST), were purchased from Sigma Aldrich. All other
19
20 materials/buffers were purchased from either Sigma Aldrich or Fisher Scientific. All
21
22 deionized was used with a resistivity greater than 18 MΩ•cm².
23
24

25 26 *2.2 Instrumentation and equipment*

27
28 UV-vis spectra were taken with an Agilent 8453 spectrophotometer with a photodiode
29
30 array detector. Spectrophotometric assays were performed in Corning 384 well plates and
31
32 measured with a Biotek Synergy H4 plate reader. Electron microscopy images were taken
33
34 with a CM 20 transmission electron microscope at 200 kV. A Malvern Zetasizer was
35
36 utilized for in-solution dynamic laser light scattering size distribution measurements. An
37
38 Eppendorf 5415D microcentrifuge was used to centrifuge AuNPs in 1.5 mL Eppendorf
39
40 tubes. A Thermo Reciprocal Shaking Bath was utilized to store the particles at 37°C.
41
42 Photographs of suspended Ni(II)NTA AuNPs were taken with an iPhone 4S smartphone
43
44 (Apple, CA).
45
46
47
48
49

50 51 *2.3 Synthesis of Ni(II)NTA AuNPs*

52
53 A 2 nM aliquot of 15 nm citrate-stabilized AuNPs was incubated with 5 μM thiolated
54
55 NTA ligand and 5 μM spacer ligand and allowed to assemble on the particle surface
56
57 overnight. For synthesis of the 100% Ni(II)NTA AuNPs, 10 μM thiolated NTA ligand
58
59
60
61
62
63
64
65

was incubated with the particles and assembled overnight. The next morning 1 mL aliquots of NTA-functionalized AuNPs were washed by centrifugation at 7200 gs for 45 minutes. The supernatant was removed and the particles were resuspended in 0.1 M 4-(2-hydroxyethyl)-1-piperazineethanesulfonic acid (HEPES) buffer containing 0.025% Tween 20 (pH 7.4). This process was repeated three additional times and finally suspended in 0.1 M HEPES containing 0.025% Tween 20 (pH 7.4). Next, 10 μM NiCl_2 was added to the particles and incubated for 24 hours. After charging with Ni^{2+} , the particles were washed three times with 0.1 M HEPES buffer containing 0.025% Tween 20 (pH 7.4). After decanting the final supernatant, the particles were suspended in 0.1 M 2-(N-morpholino) ethanesulfonic acid (MES) buffer containing 0.025% Tween 20 (pH 5.5). The particles were finally filtered through a 0.22 μm syringe filter.

2.4. rcHRP-II-induced aggregation assays with Ni(II)NTA AuNPs

A 5 μL volume of rcHRP-II dissolved in deionized water was mixed with a 45 μL volume of 1.15 nM AuNPs in a Corning 384 well plate. The plate was shaken for 15 minutes before taking absorbance measurements 600 nm and 525 nm for Ni(II)NTA AuNPs. A blank measurement consisted of 45 μL s of 0.1 M MES with 0.025% Tween 20 (pH 5.5) plus 5 μL deionized water. After the blank was subtracted, the aggregation signal was assessed by taking the ratio of the two selected wavelengths (A_{600}/A_{525}) and normalizing the samples containing no protein to 1. All measurements were performed in triplicate, while 6 replicates of blank measurements were recorded. All limit of detection values were generated as follows: $(\text{blank} + 3\sigma_{\text{blank}})/\text{slope}$.

2.5. rcHRP-II-induced aggregation assays with Ni(II)NTA AuNPs in human serum albumin

1
2
3
4 A 5 μL volume of rcHRP-II dissolved in 37 mg/mL HSA was mixed with a 45 μL
5
6
7 volume of 1.15 nM Peg₄:Ni(II)NTA AuNPs in a Corning 384 well plate. Particles were
8
9
10 suspended in 0.1 M MES buffer containing 125 mM imidazole and 150 mM NaCl with
11
12 0.025% Tween 20 (pH 5.5). The plate was shaken for 15 minutes before taking
13
14 absorbance measurements 600 nm and 525 nm for Ni(II)NTA AuNPs. A blank
15
16 measurement consisted of 45 μL s of 0.1 M MES in 125 mM imidazole and 150 mM
17
18 NaCl with 0.025% Tween 20 (pH 5.5) plus 5 μL 37 mg/mL human serum albumin. After
19
20 the blank was subtracted, the aggregation signal was assessed by taking the ratio of the
21
22 two selected wavelengths (A_{600}/A_{525}) and normalizing the samples containing no rcHRP-
23
24 II to 1. All measurements were performed in triplicate, while 6 replicates of blank
25
26
27 measurements were recorded.
28
29
30

31 *2.6. Low-resource Ni(II)NTA AuNP aggregation analysis with iOS application*

32

33 The Peg₄:Ni(II)NTA AuNPs were titrated against rcHRP-II in a white Costar 96 well
34
35 plates. A 180 μL Peg₄:Ni(II)NTA AuNP suspension (1.15 nM) in 0.1 M MES containing
36
37 125 mM imidazole and 150 mM NaCl with 0.025% Tween 20 (pH 5.5) was added to a
38
39 white Costar 96 well plate. Next, 20 μL s of a rcHRP-II protein solution was added to the
40
41 wells before incubating for 15 minutes. High dynamic range images of the AuNPs were
42
43 captured with an iPhone 4S camera with the iOS 7.0.6 platform. For color analysis, the
44
45 commercially available iPhone application, Color Companion (Digital Media Interactive,
46
47 LLC), was downloaded onto the iOS 7.0.6 platform for analysis of the red, blue and
48
49 green signal intensities of nanoparticle suspensions in each well. Analysis was calculated
50
51 by averaging the green and blue signal intensities and dividing it by the red signal
52
53
54
55
56
57
58
59
60
61
62
63
64
65

intensity. Blank measurements (no protein added to wells) were normalized to values of one.

3. Results and Discussion

3.1. Ni(II)NTA AuNP characterization

The functionalization of gold nanoparticles with a thiolated Ni(II)NTA recognition ligand specific for the *Pf*HRP-II malarial biomarker has the potential to create a rapid, robust diagnostic, capable of withstanding the extreme climates encountered in low-resource regions of the world. Moreover, manipulation of the gold particle surface with varying spacer ligands has the ability to improve both assay sensitivity and long-term stability in the developing world. The spacer ligands addressed in this study are shown in Figure 2. The alkanethiols, mercaptoundecanoic acid (MUA) and mercaptohexanol (MHOL) possess strong self-assembly characteristics because the van der Waals interactions between methylene units on neighboring ligands promote a strong and stable monolayer adsorbed to the gold surface [25]. MUA contains a terminal negative charge, enhancing stability of colloidal particles, while MHOL possesses a terminal alcohol, facilitating crosslinking interactions and hydrogen bonding between the protein-particle interface. Thiol-dPEG₄-Acid (Peg₄) also possesses a terminal negative charge, but possesses hydrophilic character, promoting favorable interactions among aqueous colloidal nanomaterials. In addition, poly(ethylene glycol) molecules are well-known for their anti-fouling and repellant properties versus protein and cell adsorption, further enhancing stability and reducing the risk of non-specific binding [26-29]. Upon functionalization with 50:50 ratios of Ni(II)NTA recognition ligand relative to varying spacer ligands, the particles are stable, as indicated by the bright red colors in solution,

the narrow surface plasmon resonance band in the UV-vis spectra, and the monodisperse particle size distribution in the electron microscopy images (Figure 3). Relative to citrate-stabilized gold nanoparticles, the Ni(II)NTA-functionalized particles undergo a 3-5 nm red shift in the UV-vis spectrum, which correlates to the coordination of a dielectric monolayer to the particle surface, as indicated by the 3-5 nm hydrodynamic diameter increase in laser light scattering experiments (S1).

3.2. Ni(II)NTA AuNP aggregation induced by rcHRP-II

Our previous Ni(II)NTA Au and AgNP platform demonstrating the aggregation activity of *Pf*HRP-II peptide mimics highlights the importance of pH in the assay. Below the isoelectric point of histidine (~6), the positively charged free imidazole side chains create a hydrogen bond network among neighboring proteins, thus facilitating crosslinking interactions between the Ni(II)NTA moieties on neighboring particles and the protein. In addition, below pH 7, *Pf*HRP-II primarily adopts a α -helical structure *in vitro*, orienting histidine units on the surface of the protein [30]. *Pf*HRP-II was also discovered to coordinate as many as 15-17 Fe(II) heme molecules *in vitro* via bishistidyl axial ligation, ultimately adopting a 3_{10} -helical secondary structure in the process[31]. The slightly acidic pH nature of the assay gives rise to protein orientations for favorable Ni(II)-histidine coordination and reduced steric effects, while the heme binding studies validate M(II) affinity as a recognition component. Upon reacting the Ni(II)NTA AuNPs with 100 nM rcHRP-II at pH 5.5, all particles exhibit rapid aggregation. Indicated by the significant spectrophotometric red shift, the particles physically change color from red to purple, due to plasmon band coupling from rcHRP-II-induced aggregation (Figure 4). Protein-induced aggregation is further confirmed by TEM images and the substantial

1
2
3
4 shift in size distribution of particles in dynamic laser light scattering experiments. Nearly
5
6 50% of the spectrophotometric signal given off by particle aggregation occurs after one
7
8 minute, as indicated by a substantial red shift in the UV-vis spectra (S2). Final
9
10 absorbance measurements are taken after 15 minutes, as the spectrophotometric signal
11
12 begins to level off. The rapid timeframe required to generate a signal induced by particle
13
14 aggregation compares very well with the 15-30 minute timeframe for current RDT's.
15
16
17

18
19 In order to determine the activity of the Ni(II)NTA AuNPs with varying spacer
20
21 ligands, rcHRP-II is titrated against each Ni(II)NTA AuNP platform (Figure 5). After 15
22
23 minutes incubation with rcHRP-II, the spectrophotometric signal is measured by taking a
24
25 ratio of two selected absorbance wavelengths ($A_{600\text{nm}}/A_{525\text{nm}}$) and normalizing the blank
26
27 values to 1. With the assembly of all spacer ligands, the assay limit of detection increases
28
29 by an order of magnitude relative to the 100% Ni(II)NTA AuNPs (Table 1). The
30
31 MHOL:Ni(II)NTA AuNPs exhibit the highest sensitivity along with the largest signal-to-
32
33 noise at the saturated rcHRP-II concentrations. Contrastingly the 100% Ni(II)NTA
34
35 AuNPs display the lowest sensitivity, signal-to-noise, and the highest limit of rcHRP-II
36
37 detection. The Peg₄:Ni(II)NTA AuNPs and MUA:Ni(II)NTA AuNPs exhibit excellent
38
39 limits of detection, but decreased signal and sensitivity in comparison to
40
41 MHOL:Ni(II)NTA AuNPs. It is hypothesized that steric crowding of the 100%
42
43 Ni(II)NTA ligand monolayer is responsible for the poor sensitivity and detection limits.
44
45 When Ni(II)NTA AuNPs are assembled with MUA and Peg₄ spacer ligands, the terminal
46
47 negative charge on the spacer ligand most likely repels the particles, decreasing their
48
49 overall signal and sensitivity relative to the MHOL:Ni(II)NTA AuNPs. The assembly of
50
51 Ni(II)NTA AuNPs with the small MHOL reduces steric crowding and its terminal
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 alcohol facilitates hydrogen-bonding interactions among the protein-particle interface,
5
6 ultimately favoring aggregation in the presence of rcHRP-II. Compared to the high
7
8 nanomolar limits of detection against histidine-rich peptide mimics, the Ni(II)NTA AuNP
9
10 platform assembled with spacer ligands increases the rcHRP-II limits of detection by two
11
12 orders of magnitude into clinically relevant ranges.
13
14

15 16 3.3. *Ni(II)NTA AuNP stability* 17

18
19 To determine the environmental suitability of the Ni(II)NTA AuNPs as a malarial
20
21 diagnostic, the particles with varying spacer ligands are evaluated in conditions
22
23 mimicking low-resource settings. All of the particles are stored in assay conditions in a
24
25 water bath (37°C) for a four-week time period, mimicking low-resource regions with the
26
27 most extreme temperatures and humidity. At two-week and four-week intervals, the
28
29 aggregation activity of the particles is assessed upon exposure to 100 nM rcHRP-II
30
31 (Figure 6). Ni(II)NTA AuNPs assembled with the negatively charged MUA and Peg₄
32
33 spacer ligands maintain consistent aggregation activity over the four-week time period.
34
35 We hypothesize that the stable self-assembled monolayer along with the negative
36
37 terminal charge prevents particle aggregation in solution in order to maintain stability. In
38
39 addition, the 100% Ni(II)NTA AuNPs also preserve stability at the elevated temperature
40
41 because the Ni(II)NTA complex is partially negatively charged. In contrast, the
42
43 MHOL:Ni(II)NTA AuNPs lose approximately two-thirds of their aggregation activity
44
45 after two weeks and nearly 100% activity after four weeks. It has been recently
46
47 understood that colloidal AuNPs assembled with short-chained alkanethiols lose stability
48
49 due to their overwhelming van der Waal interactions between neighboring ligands, and
50
51 aggregation ultimately occurs [32]. This study also affirms that colloidal AuNPs
52
53
54
55
56
57
58
59
60
61
62
63
64
65

assembled with longer MUA and Peg₄ ligands retain stability. The AuNP stability is further tracked by measuring variances in the UV-vis spectra at the aforementioned time intervals. The LSPR peak associated with the MHOL:Ni(II)NTA AuNPs begins to redshift after one week at 37°C. After four weeks elapsed time, these particles lose significant absorbance in the UV-vis spectrum, and the LSPR redshifts approximately 65 nm, indicating complete aggregation and a lack of stability in these conditions (S3-S4). Contrastingly, the 100% Ni(II)NTA AuNPs and MUA:Ni(II)NTA AuNPs maintain >80% of their LSPR absorbance after four weeks, while the Peg₄:Ni(II)NTA AuNPs possess >90% of their LSPR absorbance after four weeks.

3.4. Peg₄:Ni(II)NTA AuNP assay performance in human serum albumin

Peg₄:Ni(II)NTA AuNPs were chosen for further assays in human serum albumin (HSA) complex matrices because of their consistent stability and activity when stored at elevated temperatures. The Peg₄:Ni(II)NTA AuNPs retain the highest relative LSPR peak absorbance after four weeks incubation in addition to their consistent aggregation activity at 37°C. Moreover, Peg molecules are well established as anti-fouling agents, further reducing non-specific binding in our assay. A series of blocking conditions is first established for the Peg₄:Ni(II)NTA AuNPs. Imidazole is known to have millimolar affinity to Ni(II)NTA and serves as a blocking agent to physiological confounding proteins such as HSA [33]. When incubated in 0.1 M MES buffer containing imidazole and NaCl, the Peg₄:Ni(II)NTA AuNPs are stable up to 250 mM concentrations, whereas above 250 mM imidazole, the Ni(II)NTA sites become overwhelmed by imidazole, and aggregation ultimately occurs. In the presence of 100 nM rCHRP-II, imidazole enhances assay performance linearly from 0 mM to 50 mM imidazole. Between 50 mM and 250

1 mM imidazole, the maximum assay signal plateaus, whereas above 250 mM, assay signal
2 decreases due to the lack of stability of the Ni(II)NTA AuNPs (S5). A blocking condition
3 of 125 mM imidazole was chosen because at this concentration, the signal-to-noise ratio
4 is optimized and the particles are monodisperse. The particles are first titrated against
5 rcHRP-II and demonstrate a three-fold increase in sensitivity and a two-fold signal-to-
6 noise enhancement (Table 2). The protonated imidazole cations at high concentrations aid
7 in rcHRP-II-induced Ni(II)NTA AuNP aggregation by facilitating the cation-hydrogen
8 bond network among neighboring proteins, thus increasing assay sensitivity. To control
9 for non-specific interactions, the Ni(II)NTA AuNPs are titrated against the fusion protein
10 tagged onto rcHRP-II, glutathione-S-transferase (GST), and no significant aggregation is
11 evident (S6). The Peg₄:Ni(II)NTA AuNPs are also stable in plasma as indicated by the
12 lack of a UV-vis spectral shift (S8), demonstrating that no physiological confounding
13 proteins induce non-specific aggregation.

14 In order to mimic a potential patient sample, rcHRP-II is dissolved in the
15 physiological concentrations of HSA, 37 mg/mL. Upon titration, the Peg₄:Ni(II)NTA
16 AuNP colorimetric assay has the same sensitivity versus 0 mg/mL HSA, as demonstrated
17 by the spectrophotometric linear dynamic range and the similar color change upon
18 reactions with rcHRP-II (Figure 7). There is also no significant difference in limits of
19 detection when rcHRP-II is dissolved in 37 mg/mL versus 0 mg/mL HSA, demonstrating
20 the robust nature of the Peg₄:Ni(II)NTA AuNP platform (Table 2). The 125 mM
21 imidazole concentration provides adequate blocking in the complex biological matrix, but
22 does not interfere with rcHRP-II-induced aggregation when dissolved in 37 mg/mL HSA.
23 The low nanomolar limits of detection are competitive with the WHO's upper threshold

limit of detection of 2000 parasites/ μ L, which corresponds to approximately 1 nM *Pf*HRP-II. The Peg₄:Ni(II)NTA AuNP platform is also optimized for long-term exposure in low-resource environments and is equipped for utility in complex biological matrices.

3.5. Peg₄:Ni(II)NTA AuNP colorimetric analysis with smartphone application

Although Peg₄:Ni(II)NTA AuNP activity can be easily measured with a spectrophotometer in a laboratory setting, the lack of trained technicians coupled with the inconsistent electricity burdens this analytical technique in low-resource regions. However, the physical color transitions of Peg₄:Ni(II)NTA AuNP aggregates upon rcHRP-II incubation can be captured with a battery-powered iPhone and subsequently quantified with image processing applications, further making this diagnostic platform applicable to low-resource areas. Taking advantage of a commercially available iPhone application, Color Companion, photographs of suspended nanoparticles are uploaded and processed for analysis of the RGB color intensities. To achieve a raw signal intensity value, the blue and green intensities are averaged and divided by the red intensity value. The rcHRP-II biomarker is titrated with the Peg₄:Ni(II)NTA AuNPs in a white 96-well plate for enhanced contrast (S9). The wells containing AuNPs with no protein added are normalized to values of one. The signal generated by the Color Companion application yields a linear response between 0-40 nM rcHRP-II concentrations before saturation, similar to the signal generated by a spectrophotometer (Figure 8). There is also no significant difference between the sensitivity (0.038 Signal/nM) and limit of detection (5.2 nM) in comparison to spectrophotometric detection. The image capturing and processing using this smartphone platform are capable of processing and quantifying molecular recognition events in future colorimetric assays.

4. Conclusion

In this investigation, we optimized the Ni(II)NTA AuNP platform for detection of a malarial biomarker, recombinant *Pf*HRP-II, by incorporating various spacer ligands onto the surface for maximum stability and sensitivity. With the negatively charged, water-soluble Peg₄ spacer ligand assembled to the particle surface, the Ni(II)NTA AuNPs retain excellent stability when stored at 37°C for four weeks, demonstrating that this diagnostic platform can endure the harsh climates encountered in low-resource regions. In the presence of rcHRP-II, the Ni(II)NTA AuNPs aggregate in as little as one minute, while the 15-minute timeframe required to level the spectrophotometric signal is very competitive with existing malaria RDTs. The Peg₄:Ni(II)NTA AuNPs also exhibit low nanomolar limits of rcHRP-II detection when dissolved in the physiological concentration of the most abundant confounding protein, human serum albumin, overlapping the WHO's upper threshold detection limit of 2000 parasites/ μ L. Finally, the aggregated AuNPs are photographed with an iPhone camera and processed with a commercially available application, demonstrating similar sensitivity and limits of detection in comparison to a spectrophotometer. Although the optimized Ni(II)NTA AuNP colorimetric indicator displays adequate specificity and sensitivity towards histidine-rich proteins in minimally confounding matrices, establishing similar signals in blood and plasma remains a challenge. Future investigation is required in order to interface this detection strategy with our sample preparation device in order to purify and concentrate the *Pf*HRP-II biomarker from complex matrices for enhanced sensitivity and specificity [33]. Nevertheless, the simple user interface of this diagnostic platform

coupled with the rapid response times of rCHRP-II-induced AuNP aggregation makes this assay amenable to low-resource settings.

References

- [1] C.K. Murray, R.A. Gasser, Jr., A.J. Magill, S.A. Miller, Update on Rapid Diagnostic Testing for Malaria, *Clin. Microbiol. Rev.*, 21 (2008), pp. 97-110.
- [2] WHO. *World Malaria Report*, (2011).
- [3] P.L. Chiodini, K. Bowers, P. Jorgensen, J.W. Barnwell, K.K. Grady, J. Luchavez, A. H. Moody, A. Cenizal, D. Bell, The Heat Stability of Plasmodium Lactate Dehydrogenase-Based and Histidine-Rich Protein 2-Based Malaria Rapid Diagnostic Tests, *Trans. R. Soc. Trop. Med. Hyg.*, 101 (2007), pp. 331-337.
- [4] N. Wurtz, B. Fall, K. Bui, A. Pascual, M. Fall, C. Camara, B. Diatta, K.B. Fall, P.S. Mbaye, Y. Dieme, R. Bercion, B. Wade, S. Briolant, B. Pradines, Pfhrrp2 and Pfhrrp3 Polymorphisms in Plasmodium falciparum Isolates from Dakar, Senegal: Impact on Rapid Malaria Diagnostic Tests, *Malar. J.*, 12 (2013), pp. 34-41.
- [5] N. Kumar, J.P.N. Singh, V. Pande, N. Mishra, B. Srivastava, R. Kapoor, N. Valecha, A.R. Anvikar, Genetic Variation in Histidine Rich Proteins among Indian Plasmodium falciparum Population: Possible Cause of Variable Sensitivity of Malaria Rapid Diagnostic Tests, *Malar. J.*, 11 (2012), pp. 298-304.
- [6] L.J. Panton, P. Mcphie, W.L. Maloy, T.E. Wellems, D.W. Taylor, R.J. Howard, Purification and Partial Characterization of an Unusual Protein of Plasmodium falciparum: Histidine-Rich Protein II, *Mol. Biochem. Parasitol.*, 35 (1989), pp. 149-160.
- [7] K. Terpe, Overview of Tag Protein Fusions: from Molecular and Biochemical Fundamentals to Commercial Systems, *Appl. Microbiol. Technol.*, 60 (2003), pp. 523-533.
- [8] S. Mori, H.K. Takahashi, K. Yamaoka, M. Okamoto, M. Nishibori, High Affinity Binding of Serum Histidine-Rich Glycoprotein to Nickel-Nitrilotriacetic Acid: the Application to Microquantification. *Life Sci.*, 73 (2003), pp. 93-102.
- [9] P. Ghimire, J.C. Samantaray, B.R. Mirdha, A.K. Patra, A.K. Panda, Purification and Partial Characterization of PfHRP-II Protein of Plasmodium falciparum, *Southeast Asian J. Trop. Med. Public Health*, 34 (2003), pp. 739-743.
- [10] S. Knecht, D. Ricklin, A.N. Eberle, B. Ernst, Oligohis-Tags: Mechanisms of Binding to Ni²⁺-NTA Surfaces, *J. Mol. Recognit.*, 22 (2009), pp. 270-279.
- [11] U. Kreibig, L. Genzel, Optical Absorption of Small Metallic Particles, *Surf. Sci.*, 156 (1985), pp. 678-700.
- [12] M. Quinten, U. Kreibig, Optical Properties of Aggregates of Small Metal Particles, *Surf. Sci.*, 172 (1986), pp. 557-577.
- [13] E. Prodan, P.J. Nordlander, Plasmon Hybridization in Spherical Nanoparticles, *J. Chem. Phys.*, 120 (2004), pp. 5444-5454.
- [14] H. Hakkinen, The Gold-Sulfur Interface at the Nanoscale, *Nat. Chem.*, 4 (2012), pp. 443-455.
- [15] R. Elghanian, J.J. Storhoff, R.C. Mucic, R.L. Letsinger, C.A. Mirkin, Selective Colorimetric Detection of Polynucleotides Based on the Distance-Dependent Optical Properties of Gold Nanoparticles, *Science*, 277 (1997), pp. 1078-1081.

- [16] J.J. Storhoff, R. Elghanian, R.C. Mucic, C.A. Mirkin, R.L. Letsinger, One-Pot Colorimetric Differentiation of Polynucleotides with Single Base Imperfections Using Gold Nanoparticle Probes, *J. Am. Chem. Soc.*, 120 (1998), pp. 1959-1964.
- [17] F. Xia, X. Zuo, R. Yang, Y. Xiao, D. Kang, A. Vallée-Bélisle, X. Gong, J.D. Yuen, B.B.Y. Hsu, A.J. Heeger, K.W. Plaxco, Colorimetric Detection of DNA, Small Molecules, Proteins, and Ions Using Unmodified Gold nanoparticles and Conjugated Polyelectrolytes, *Proc. Nat. Acad. Sci.*, 107 (2010), pp. 10837-10841.
- [18] J. Liu, Y. Lu, A Colorimetric Lead Biosensor Using DNAzyme-Directed Assembly of Gold Nanoparticles, *J. Am. Chem. Soc.*, 125 (2003), pp. 6642-6643.
- [19] E. Boisselier, D. Astruc, Gold Nanoparticles in Nanomedicine: Preparations, Imaging, Diagnostics, Therapies and Toxicity, *Chem. Soc. Rev.*, 38 (2009), pp. 1759-1782.
- [20] J.D. Swartz, C.P. Gulka, F.R. Haselton, D.W. Wright, Development of Histidine-Targeted Spectrophotometric Sensor Using Ni(II)NTA-Functionalized Au and Ag Nanoparticles, *Langmuir*, 27 (2011), pp. 15330-15339.
- [21] L. Shen, J.A. Hagen, I. Papautsky, Point-of-care Colorimetric Detection with a Smartphone, *Lab Chip*, 12 (2012), pp. 4240-4243.
- [22] V. Oncescu, D. O'Dell, D. Erickson, Smartphone Based Health Accessory for Colorimetric Detection of Biomarkers in Sweat and Saliva, *Lab Chip*, 13 (2013), pp. 3232-3238.
- [23] S. Lee, V. Oncescu, M. Mancuso, S. Mehtac, D. Erickson, A Smartphone Platform for the Quantification of Vitamin D Levels, *Lab Chip* 14 (2014), pp. 1437-1442.
- [24] J.W. Oh, W.J. Chung, K. Heo, H.E. Jin, B.Y. Lee, E. Wang, C. Zueger, W. Wong, J. Meyer, C. Kim, S.Y. Lee, W.G. Kim, M. Zemla, M. Auer, A. Hexemer, S.W. Lee, Biomimetic Virus-Based Colourimetric Sensors, *Nat. Comm.*, 5 (2014), pp. 3043-3050.
- [25] J.C. Love, L.A. Estroff, J.K. Kriebel, R.G. Nuzzo, G.M. Whitesides, Self-Assembled Monolayers of Thiolates on Metals as a Form of Nanotechnology, *Chem. Rev.*, 105 (2005), pp. 1103-1169.
- [26] K.L. Prime, G.M. Whitesides, Self-Assembled Organic Monolayers: Model Systems for Studying Adsorption of Proteins at Surfaces, *Science*, 24 (1991), pp. 1164-1167.
- [27] K.L. Prime, G.M. Whitesides, Adsorption of Proteins onto Surfaces Containing End-Attached Oligo(ethylene oxide): A Model System Using Self-Assembled Monolayers, *J. Am. Chem. Soc.*, 115 (1993), pp. 10714-10721.
- [28] K. Bandyopadhyay, L. Shu, H. Liu, L. Echegoyen, Selective K⁺ Recognition at the Interface During Self-Assembly of a bis-Podand Thiol on a Gold Surface, *Langmuir*, 16 (2000), pp. 2706-2714.
- [29] I. Banerjee, R.C. Pangule, R.S. Kane, Antifouling Coatings: Recent Developments in the Design of Surfaces That Prevent Fouling by Proteins, Bacteria, and Marine Organisms, *Adv. Mat.*, 23 (2011), pp. 690-718.
- [30] C.E. Benedetti, J. Kobarg, T.A. Pertinhez, R.M. Gatti, O.N. de Souza, A. Spisni, R. Meneghini, Plasmodium falciparum Histidine-Rich Protein II Binds to Actin, Phosphatidylinositol 4,5-Bisphosphate and Erythrocyte Ghosts in a pH-Dependent Manner and Undergoes Coil-to-Helix Transitions in Anionic Micelles, *Mol. Biochem. Parasitol.*, 128 (2003), pp. 157-166.
- [31] E.L. Schneider, M.A. Marletta, Heme Binding to the Histidine-Rich Protein II from Plasmodium falciparum. *Biochemistry*, 44 (2005), pp. 979-986.

- 1
2
3
4 [32] H. Hinterworth, S. Kappel, T. Waitz, T. Prohaska, W. Lindner, M. Lammerhofer,
5 Quantifying Thiol Ligand Density of Self-Assembled Monolayers on Gold Nanoparticles
6 by Inductively Coupled Plasma-Mass Spectrometry, *ACS Nano*, 7 (2013), pp. 1129-1136.
7 [33] K.M. Davis, J.D. Swartz, F.R. Haselton, D.W. Wright, Low-Resource Method for
8 Extracting the Malarial Biomarker Histidine-Rich Protein II to Enhance Diagnostic Test
9 Performance, *Anal. Chem.*, 84 (2012), pp. 6136-6142.
10
11

12 **Acknowledgements**

13
14

15 Funding was graciously provided by the Bill and Melinda Gates Foundation. The authors
16 would also like to thank M. F. Richards for critical comments concerning the manuscript.
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Table 1

Ni(II)NTA AuNP Platform	LOD (nM)	95% LOD CI (nM)	Sensitivity (Signal/nM)	95% Sensitivity CI (Signal/nM)
100% Ni(II)NTA	51	39-60	0.0066	0.0050-0.0082
50:50 MHOL:Ni(II)NTA	6.6	2.4-10	0.040	0.036-0.045
50:50 Peg4:Ni(II)NTA	7.4	2.8-11	0.015	0.013-0.017
50:50 MUA:Ni(II)NTA	6.7	5.2-8.0	0.021	0.019-0.024

Table 2

[HSA] (mg/mL)	LOD (nM)	95% LOD CI (nM)	Sensitivity (Signal/nM)	95% Sensitivity CI (Signal/nM)
37	2.9	1.5-4.1	0.074	0.067-0.082
0	4.2	0.24-7.0	0.053	0.040-0.067

Figure 1

Figure 5

Figure 6

Figure 7**A** **B****37 mg/mL
HSA** **0 mg/mL
HSA** **0 nM****20 nM****40 nM****60 nM****80 nM**

Fig 1

B

Corresponding author: David W. Wright, email: David.wright@vanderbilt.edu. Phone: 615-322-2636. Fax: 615-343-1234.

Address: Vanderbilt University, Department of Chemistry, Station B 351822, Nashville, TN 37235-1822, USA

Keywords: Ni(II)NTA; gold nanoparticles; malaria; low-resource diagnostics; histidine-rich proteins; smartphone technology

Figure Captions:

Figure 1. Color change of Ni(II)NTA AuNPs upon aggregation induced by rcHRP-II.

Figure 2. Ligands assembled onto nanoparticles in this investigation.

Figure 3. Ni(II)NTA AuNP Characterization in 0.1 M MES with 0.025% Tween 20 (pH 5.5). UV-vis spectra, TEM images and suspended AuNP images of monodisperse (A) 100% Ni(II)NTA AuNPs, (B) 50:50 MHOL:Ni(II)NTA AuNPs, (C) 50:50 Peg₄:Ni(II)NTA AuNPs, and (D) 50:50 MUA:Ni(II)NTA AuNPs.

Figure 4. Aggregation of Ni(II)NTA AuNPs in the presence of 100 nM rcHRP-II at pH 5.5 for (A) 100% Ni(II)NTA AuNPs, (B) 50:50 MHOL:Ni(II)NTA AuNPs, (C) 50:50 Peg₄:Ni(II)NTA AuNPs, and (D) 50:50 MUA:Ni(II)NTA AuNPs. The top graphs represent UV-vis spectra before (solid line) and after (dashed line) adding rcHRP-II. The images on the left are the color changes the particles undergo before (left) and after (right) aggregation. The middle graphs represent dynamic laser light scattering particle size distributions before (solid line) and after (dashed line) rcHRP-II-induced aggregation. The bottom row shows TEM images of rcHRP-II-induced aggregated Ni(II)NTA AuNPs.

Figure 5. Titration of rcHRP-II with Ni(II)NTA AuNPs assembled with varying spacer ligands in 0.1 M MES with 0.025% Tween 20 (pH 5.5). (A) Spectrophotometric titrations and (B) Colorimetric titrations ranging from 0-100 nM rcHRP-II concentrations. From top, 100% Ni(II)NTA AuNPs, 50:50 MHOL:Ni(II)NTA AuNPs, 50:50 Peg₄:Ni(II)NTA AuNPs, and 50:50 MUA:Ni(II)NTA AuNPs.

Figure 6. Stability of Ni(II)NTA AuNPs at 37°C. 1 nM Ni(II)NTA AuNP suspensions at pH 5.5 are stored in sealed 1.5 mL Eppendorf tubes in a water bath at 37°C for four weeks. At two-week intervals, the particles are reacted with 100 nM rcHRP-II for 15 minutes before taking absorbance measurements at 525 nm and 600 nm.

Figure 7. Effect of Peg₄:Ni(II)NTA AuNP rcHRP-II-induced aggregation in the presence of the physiological confounding protein, HSA. Particles are suspended in 0.1 M MES containing 125 mM imidazole and 150 mM NaCl with 0.025% Tween 20 (pH 5.5). A 45 µL volume of AuNPs is reacted with 5 µL of rcHRP-II for 15 minutes before taking (A)

absorbance measurements and (B) capturing the color changes of rcHRP-II-induced aggregated AuNPs.

Figure 8. Workflow of low-resource detection of rcHRP-II using the Peg₄:Ni(II)NTA AuNP platform. (A) The Peg₄:Ni(II)NTA AuNPs were titrated with rcHRP-II and after 15 minutes, images of the suspended particles were captured with an iPhone 4S camera and uploaded into the Color Companion commercial application. In order to process the color change induced by rcHRP-II, the bullseye cursor (highlighted with the dashed red circle) was moved over a well in a white 96 well-plate and RGB signal intensities were conferred (highlighted with the dashed red box). To calculate raw signal, the green and blue signal intensities were averaged and divided by the red signal intensity values. (B) Plot of signal intensity measured with a spectrophotometer and the Color Companion commercial application. There is no significant difference in sensitivity and rcHRP-II limit of detection between the spectrophotometer and the commercial application.

Table Descriptions:

Table 1. LODs, confidence intervals, and sensitivity of rcHRP-II with each Ni(II)NTA AuNP platform in 0.1 M MES buffer containing 0.025% Tween 20 (pH 5.5).

Table 2. LODs, confidence intervals, and sensitivity of rcHRP-II using a Peg₄:Ni(II)NTA AuNP platform with 125 mM imidazole and 150 mM NaCl blocking conditions in 0.1 M MES with 0.025% Tween 20 (pH 5.5) in varying concentrations of a physiological confounding protein, human serum albumin.

Further Considerations:

Manuscript has been “spell-checked” and “grammar-checked.”

References are formatted correctly and are all mentioned in the manuscript text.

Permission has been obtained to include the Color Companion application in the publication of this work by the developers, Digital Media Interactive, LLC.

All images and figures are intended for color reproduction in print and on the web.

***List of Three Potential Reviewers**

- (1) Michael Lammerhofer, Institute of Pharmaceutical Sciences, University of Tübingen, Auf der Morgenstelle 8, 72076 Tübingen, Germany. Email: Michael.lammerhofer@uni-tuebingen.de. Phone: +49 7071 29 78793. Fax: +49 7071 29 4565
- (2) Nicholas Kotov, Dept of Chemical Engineering, University of Michigan, Ann Arbor, Michigan, USA. Email: kotov@umich.edu. Phone: (734) 763-8768. Fax: (734) 764-7453.
- (3) Jacquin Niles, Dept of Biological Engineering, Massachusetts Institute of Technology, Cambridge, MA, USA. Email: jcniles@mit.edu. Phone: Phone: (617) 324-3701. Fax: (617) 324-5698.

***Graphical Abstract (for review)**