Synthesis of [1]benzothieno[3,2-*b*][1]benzothiophene (BTBT) and its higher homologs through palladium-catalyzed intramolecular decarboxylative arylation

Sojiro Minami^a, Koji Hirano^a, Tetsuya Satoh^{a,b} and Masahiro Miura^{a,*}

^aDepartment of Applied Chemistry, Faculty of Engineering, Osaka University, Suita, Osaka 565-0871, Japan

^bJST, ACT-C, 4-1-8 Honcho, Kawaguchi, Saitama 332-0012, Japan

*Corresponding author: Tel. +81-6879-7360; fax: +81-6-6879-7362. E-mail address: miura@chem.eng.osaka-u.ac.jp (M. Miura)

ARTICLE INFO

Article history:

Received

Received in revised form

Accepted

Available online

Keywords:

Arylation

BTBT

Decarboxylation

Palladium

Thienoacene

ABSTRACT

We report herein an effective method for the construction of 4- and 7-ring benzo-fused thieno[3,2-*b*]thiophenes, involving palladium-catalyzed intramolecular decarboxylative arylation as the key step.

2009 Elsevier Ltd. All rights reserved.

Various poly-condensed arenes and heteroarenes are known to work as organic semiconductors. Particularly, thienoacene-based extended π -systems have attracted much attention, as they are robust and often show high hole mobilities in field effect transistor (FET) devices.¹ Benzo-fused thieno[3,2-*b*]thiophenes such as [1]benzothieno[3,2-*b*][1]benzothiophene (BTBT) (Figure 1) derivatives are typical promising compounds. Thus, the synthesis of BTBT and its derivatives has been studied extensively in recent years. BTBT itself has been prepared by a number of methods including the reactions of 1,2-bis(2-bromophenyl)acetylene with S₈ or Na₂S,² 2,2'-dichlorostilbene with Na₂S,³ *o*-chlorobenzaldehyde with NaSH,⁴ and benzyl chloride with S₈.^{5,6} Another effective method leading to BTBT is the iodine-promoted cyclization of 2,2'-bis(methylthio)stilbene, which was also applied to the synthesis of a largely extended thienoacene, i.e. bis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;4,5-*b'*]dithiophene (BBTBDT) and its naphtho-analog.⁷ BBTBDT was also prepared by a Pummerer-type biscyclization.⁸ Recently, Takimiya and coworkers disclosed an elegant process for the construction of BTBT as well as its higher homologs by the sequential reactions of 2[2-(trimethylsilyl)ethynyl]thioanisole with PhSCl to form the corresponding 3-(phenylthio)benzo[*b*]thiophene and its 2-bromination followed by palladium-catalyzed intramolecular C-H arylation.⁹ Despite these achievements for constructing the BTBT series of compounds, there still remains a substantial demand for further development of effective and flexible synthetic methods to enhance their utility. We herein describe a new synthetic sequence involving palladium-catalyzed intramolecular decarboxylative arylation as the key step, which enables to construct unknown

bis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;5,6-*b'*]dithiophene (*iso*-BBTBDT) skeleton as well as BTBT and BBTBDT and their alkylated derivatives. Decarboxylative arylation for constructing biaryl linkages using widely available arenecarboxylic acids as one of the coupling partners has recently emerged as an effective cross-coupling strategy that complements the relevant conventional methods employing arylmetal reagents.¹⁰

Figure 1. Structure of BTBT, BBTBDT, and *iso*-BBTBDT.

We previously reported the synthesis of 3-(arylthio)-2-arylbenzo[*b*]thiophene (**4**) of pharmaceutical interest (Scheme 1). The method with the readily available methyl 3-

Table 1. Synthesis of BTBT and C₈-BTBT by intramolecular decarboxylative arylation^a

Entry	Substrate	Ligand ^b	Base	Time (h)	Product, yield ^c (%)
1	3a	P(<i>o</i> -BP)Cy ₂	Cs ₂ CO ₃	2	5a , 77
2	3a	P(<i>o</i> -BP)Cy ₂	Na ₂ CO ₃	2	5a , 75
3	3a	P(<i>o</i> -BP)Cy ₂	K ₂ CO ₃	6	5a , 71
4	3a	P(<i>o</i> -BP)Cy ₂	CsOAc	6	5a , 75
5	3a	P(<i>o</i> -BP)Cy ₂	DABCO	6	5a , 15
6	3a	PCy ₃	Cs ₂ CO ₃	6	5a , 90
7	3a	P(<i>o</i> -BP)(<i>t</i> -Bu) ₂	Cs ₂ CO ₃	2	5a , 91 (80)
8	3b^d	P(<i>o</i> -BP)(<i>t</i> -Bu) ₂	Cs ₂ CO ₃	2	5b , (72)

^a Conditions: [3]:[Pd(OAc)₂]:[P(*o*-BP)(*t*-Bu)₂]:[Cs₂CO₃] = 1:0.1:0.2:2 (0.25 mmol of **3** was used), at 160 °C under N₂ in DMAc (2.1 mL).^b *o*-BP = biphenyl-2-yl.^c Determined by GC analysis. Value in parentheses is isolated yield.^d 0.13 mmol of **3b** was used in 1 mL of DMAc.

chlorobenzo[*b*]thiophene-2-carboxylate (**1a**) as the starting scaffold consists of nucleophilic 3-arylation and palladium-catalyzed decarboxylative 2-arylation.¹¹ This sequence may allow various 2,3-disubstitution patterns on the benzo[*b*]thiophene framework. It may be conceived that using 2-bromobenzenethiols could afford BTBT and its derivatives via intramolecular decarboxylative arylation. Consequently, we have undertaken to their synthesis based on this strategy.

Scheme 1. Preparation of 2-aryl-3-(arylthio)benzo[*b*]thiophene by nucleophilic arylthiolation and decarboxylative arylation (previous work).¹¹

We first examined the synthesis of mother BTBT by using methyl 3-[(trifluoromethyl)sulfonyloxy]-benzo[*b*]thiophene-2-carboxylate (**1b**)¹² as the starting material to test the applicability of the triflate analog of **1a** (Scheme 2), since the leaving group is required to construct a higher BTBT analog (*vide infra*).

Scheme 2. Synthesis of BTBT and its alkylated derivative (C₈-BTBT). ^a Conditions: [1b]:[2]:[K₂CO₃] = 1:1.2:2 (7.1 mmol of **2a** and 0.6 mmol of **2b** were used), 80 °C, 8–24 h in DMF under N₂. ^b Conditions: [2]:[KOH] = 1:3, EtOH/H₂O = 10:1 (v/v), 100 °C, 6–14 h under N₂. Yields of **3a** and **3b** were 53% and 65%, respectively (by two steps). ^c See Table 1.

As expected, the reaction of **1b** with 2-bromobenzenethiol (**2a**) in the presence of potassium carbonate in DMF at 80 °C gave the corresponding phenylthiolated product in 53% yield and the subsequent hydrolysis with potassium hydroxide in ethanol/H₂O proceeded quantitatively to afford 3-[2-(bromophenyl)thio]-2-benzo[*b*]thiophenecarboxylic acid (**3a**). Then, the intramolecular decarboxylative arylation of **3a** was conducted in the presence of Pd(OAc)₂ as catalyst in combination with a number of bases and ligands in DMAc at 160 °C (Table 1). Using P(*o*-BP)Cy₂ (*o*-BP = biphenyl-2-yl, CyJohnphos) as ligand, various inorganic bases including Cs₂CO₃, Na₂CO₃, K₂CO₃, and CsOAc could be used to furnish BTBT in 71–77% yields (determined by GC, Entries 1–4). The relatively strong Cs₂CO₃ was found to be superior to the other bases examined. However, a strong organic amine base, DABCO, was far less effective (Entry 5). PCy₃ and P(*o*-BP)(*t*-Bu)₂ (Johnphos) in place of P(*o*-BP)Cy₂ afforded higher BTBT yields of 90% and 91%, respectively (Entries 6 and 7). Thus, BTBT was isolated in 80% yield in Entry 7. Similarly, the use of 2-bromo-5-octylbenzenethiol (**2b**)¹³ in place of **2a** in the starting arylthiolation reaction of **1b** led to 2-octyl-BTBT **5b** (C₈-BTBT). The isolated yield of **5b** in the decarboxylative arylation step was 72% (Entry 8). It is worth noting that not only a dialkyl-BTBT, but also a monoalkyl-BTBT has been reported to show a high hole mobility.⁶

We next examined the synthesis of BBTBDT by using di(2-ethylhexyl) 3,7-bis(trifluoromethanesulfonyloxy)benzo[1,2-*b*:4,5-*b'*]dithiophene-2,6-carboxylate (**1c**) as the synthetic scaffold (Scheme 3), the preparation of which starting from commercially available 2,5-dibromoterephthalic acid was recently described by us.¹² The reaction of **1c** with **2a** followed by hydrolysis gave the corresponding diacid **6a** in 42% yield (by two steps) and the subsequent decarboxylative cyclization afforded BBTBDT in 61% yield (18% after sublimation in vacuo). The physical properties of BBTBDT have been reported.^{7,8} Using **1c** and **2b** could also be obtained 2,9-dioctyl-BBTBDT (2C₈-BBTBDT), albeit with a moderate yield.¹⁴

Scheme 3. Synthesis of BBTBBDT and 2C₈-BBTBBDT.

^aConditions: [**1c**]:[**2**]:[K₂CO₃] = 1:2.4:4 (3 mmol of **2a** and 1.2 mmol of **2b** were used), 80 °C, 18 h in DMF under N₂. ^bConditions: [**2**]:[KOH] = 1:6, EtOH/H₂O = 5:1 (v/v), 100 °C, 15–21 h under N₂. Yields of **6a** and **6b** were 42% and 75%, respectively (by two steps). ^cConditions: [**6**]:[Pd(OAc)₂]:[P(o-BP)(*t*-Bu)₂]:[Cs₂CO₃] = 1:0.2:0.4:4 (0.3 mmol of **6a** and 0.114 mmol of **6b** were used). Yields of **7a** and **7b** were 61% (18% after sublimation in vacuo) and 26%, respectively.

Butyl 3,6-bis(chloro)benzo[2,1-*b*:3,4-*b'*]dithiophene-2,6-carboxylate (**1d**) was found to be a useful scaffold for constructing an isomer of BBTBBDT (*iso*-BBTBBDT) **9a** and its dioctyl derivative **9b** (Scheme 4). Construction of the *iso*-BBTBBDT skeleton is to date unprecedented. The diester **1d** can be readily prepared by the convenient double ring-closure reaction of commercially available 1,4-phenylenediacrylic acid with thionyl chloride in the presence of pyridine followed by esterification with butanol.^{11, 15} Decarboxylative cyclization of the intermediary diacids **8a** and **8b**, which were prepared from **1d** with **2a** and **2b**, gave rise to **9a** and **9b** in 56% and 36% yields, respectively.

Scheme 4. Preparation of *iso*-BBTBBDT and 2C₈-*iso*-BBTBBDT.

^aConditions: [**1d**]:[**2**]:[K₂CO₃] = 1:2.4:4 (5.2 mmol of **2a** and 1.6 mmol of **2b** were used), 80 °C, 8 h in DMF under N₂. ^bConditions: [**2**]:[KOH] = 1:6, EtOH/H₂O = 5:1 (v/v), 100 °C, 15–21 h. Yields of **8a** and **8b** were 53% and 78%, respectively (by two steps). ^cConditions:

[**8**]:[Pd(OAc)₂]:[P(o-BP)(*t*-Bu)₂]:[Cs₂CO₃] = 1:0.2:0.4:4 (0.3 mmol of **8a** and 0.114 mmol of **8b** were used). Yields of **9a** and **9b** were 56% (32% after sublimation in vacuo) and 35% (25 % after Soxhlet extraction), respectively.

In summary, we have demonstrated that 3-(chloro)- or 3-(trifluoromethanesulfonyloxy)-benzo[*b*]thiophene-2-carboxylic acid esters in combination with 2-bromobenzenethiols are useful building-blocks for constructing BTBT and its higher homologs. Thus, by using the present strategy including palladium-catalyzed decarboxylative arylation as the key step, not only BTBT and BBTBBDT, but also a structurally new seven-ring theienoacene system, i.e. *iso*-BBTBBDT can be constructed effectively.¹⁶ Further studies of the synthesis of related derivatives by this reaction sequence and their physical properties are underway and the details will be reported in due course.

Acknowledgements

This work was partially supported by Grants-in-Aid for Scientific Research from MEXT, JSPS, JST, Japan.

Supplementary data

Supplementary data (characterization data of compounds) associated with this article can be found in the online version at doi:

References and notes

- (a) Recent reviews: Murphy, A. R.; Fréchet, J. M. J. *Chem. Rev.* **2007**, *107*, 1066. (b) Takimiya, K.; Shinamura, S.; Osaka, I.; Miyazaki, E.; *Adv. Mater.* **2011**, *23*, 4347 (c) Wang, C.; Dong, H.; Hu, W.; Liu, Y.; Zhu, D. *Chem. Rev.* **2012**, *112*, 2208. (d) Mei, J.; Diao, Y.; Appleton, A. L.; Fang, L.; Bao, Z. *J. Am. Chem. Soc.* **2013**, *135*, 6724. (e) Takimiya, K.; Nakano, M.; Kang, M. J.; Miyazaki, E.; Osaka, I. *Eur. J. Org. Chem.* **2013**, 217.
- (a) Sashida, H.; Yasuike, D. *J. Heterocyclic Chem.* **1998**, *35*, 725. (b) Li, Y.; Nie, C.; Wang, W.; Li, X.; Verpoort, F.; Duan, C. *Eur. J. Org. Chem.* **2011**, 7331.
- Saito, M.; Yamamoto, T.; Osaka, I.; Miyazaki, E.; Takimiya, K.; Kuwabara, H.; Ikeda, M. *Tetrahedron Lett.* **2010**, *51*, 5277.
- Saito, M.; Osaka, I.; Miyazaki, E.; Takimiya, K.; Kuwabara, H.; Ikeda, M. *Tetrahedron Lett.* **2011**, *52*, 285.
- Kosta, B.; Kozmik, V.; Svoboda, J. *Coll. Czech. Chem. Commun.* **2002**, *67*, 645.
- Amin, A. Y.; Khassanov, A.; Reuter, K.; Meyer-Friedrichsen, T.; Halik, M. *J. Am. Chem. Soc.* **2012**, *134*, 16548.
- Yamamoto, T.; Nishimura, T.; Mori, T.; Miyazaki, E.; Osaka, I.; Takimiya, K. *Org. Lett.* **2012**, *14*, 4914.
- Yang, Y. S.; Yasuda, T.; Adachi, C. *Bull. Chem. Soc. Jpn.* **2012**, *85*, 1186.
- Mori, T.; Nishimura, T.; Yamamoto, T.; Doi, I.; Miyazaki, E.; Osaka, I.; Takimiya, K. *J. Am. Chem. Soc.* **2013**, *135*, 13900.
- (a) Satoh, T.; Miura, M. *Synthesis* **2010**, 3395. (b) Gooßen, L. J.; Rodríguez, N.; Gooßen, K.; *Angew. Chem., Int. Ed.* **2008**, *47*, 3100.
- (a) Miyasaka, M.; Hirano, K.; Satoh, T.; Miura, M. *Adv. Synth. Catal.* **2009**, *351*, 2683. Corrigendum: (b) Miyasaka, M.; Hirano, K.; Satoh, T.; Miura, M. *Adv. Synth. Catal.* **2012**, *354*, 957.
- Ota, S.; Minami, S.; Hirano, K.; Satoh, T.; Ie, Y.; Seki, S.; Aso, Y.; Miura, M. *RSC Adv.* **2013**, *3*, 12356.
- The thiol **2b** was prepared by a conventional sequence including acetylation, nitration, reduction, and Sandmeyer reaction starting from commercially available 4-octylaniline. (a) Clemens, J. J.; Davis, M. D.; Lynch, K. R.; Macdonald, T. L. *Bioorg. Med. Chem. Lett.*, **2004**, *14*, 4903. (b) Cook, W. H.; Cook, K. H. *J. Am. Chem. Soc.*, **1933**, *55*, 1212. (c) Agou, T.; Kobayashi, J.; Kawashima, T. *Chem. Eur. J.* **2007**, *13*, 8051.
- Preparation of a dialkyl-BBTBBDT by the sulfurization of a tetrahalo precursor with S₈ was described in a patent: Watanabe, M.; Ohashi, T.; Fujita, T. *Jpn. Kokai Tokkyo Koho*, P2009-227670A.

15. Higa, T.; Krubsack, A. J. *J. Org. Chem.* **1975**, *40*, 3037. (b) Ried, W.; Oremek, G.; Ocakcioglu, B. *Liebigs Ann. Chem.* **1980**, 1424. (c) Malešević, M.; Karminsky-Zamola, G.; Bajić, M.; Boykin, D. D. *Heterocycles* **1995**, *41*, 2691.
16. *Dibutyl 3,6-bis[(2-bromophenyl)thio]benzo[2,1-b:3,4-b']dithiophene-2,7-dicarboxylate* (Scheme 4, the first step): In a 100 mL reaction flask were placed the dichloride **1d** (1.0 g, 2.18 mmol), the thiol **2a** (0.61 mL, 5.2 mmol), K₂CO₃ (1.2 g, 8.7 mmol), and DMF (20 mL), and the resulting mixture was stirred for 24 h at 80 °C under nitrogen. The reaction was quenched by adding water, extracted with chloroform, and dried over Na₂SO₄. Concentration followed by purification by column chromatography with hexane/ethyl acetate (20:1, v/v) gave the diarylthiolated diester (890 mg, 1.17 mmol, 53%) as a yellow solid. M.p. 134–135 °C; ¹H NMR (400 MHz, CDCl₃) δ 0.94 (t, *J* = 7.4 Hz, 6H), 1.42 (tq, *J* = 7.6 Hz, 7.6 Hz, 4H), 1.70 (tt, *J* = 6.8 Hz, 6.8 Hz, 4H), 4.35 (t, *J* = 6.5 Hz, 4H), 6.58–6.61 (m, 2H), 6.93–7.00 (m, 4H), 7.52–7.55 (m, 2H), 7.75 (s, 2H); ¹³C NMR (100 MHz, CDCl₃) δ 13.87, 19.35, 30.67, 66.31, 121.30, 122.80, 126.99, 127.92, 127.95, 130.66, 133.10, 134.35, 136.84, 137.93, 140.33, 161.41; HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₃₂H₂₉Br₂O₄S₄: 764.9212, found: 764.9227.
- 3,6-Bis[(2-bromophenyl)thio]benzo[2,1-b:3,4-b']dithiophene-2,7-dicarboxylic acid (8a)*: To a mixture of the diester (870 mg, 1.14 mmol) and KOH (384 mg, 6.84 mmol), water (2 mL), and ethanol (10 mL)-dioxane (4 mL) were sequentially added, and the suspension was then heated at 100 °C for 6 h under nitrogen. The resulting mixture was allowed to cool to room temperature. The precipitate formed by addition of diluted aqueous HCl was collected and washed with water, ethanol, and hexane, and then, dried under high vacuum to provide dicarboxylic acid **8a** (755 mg, 1.14 mmol, quant.) as a yellow solid. M.p. ca. 290 °C (decomposed); ¹H NMR (400 MHz, DMSO-*d*₆) δ 6.55–6.58 (m, 2H), 7.03–7.06 (m, 4H), 7.52–7.57 (m, 2H), 7.62–7.64 (m, 2H), 14.13 (bs, 2H); ¹³C NMR (100 MHz, DMSO-*d*₆) δ 120.10, 122.09, 127.32, 127.60, 128.33, 128.46, 132.88, 133.35, 137.14, 138.46, 139.40, 161.72; HRMS (FAB⁺) *m/z* (M⁺) calcd for C₂₄H₁₂Br₂O₄S₄: 649.7980, found: 649.7996.
- Bis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;5,6-*b'*]dithiophene (9a)*: In a 20 mL two-necked flask were placed the diacid **8a** (200 mg, 0.307 mmol), Pd(OAc)₂ (14 mg, 0.061 mmol) and Johnphos (37 mg, 0.123 mmol), Cs₂CO₃ (407 mg, 1.23 mmol), and DMAc (5 mL). The resulting mixture was stirred for 7 h at 160 °C under nitrogen and cooled to room temperature. The solid in the mixture was collected by filtration and washed with water, hexane, and acetone to give **9a** (69 mg, 0.171 mmol, 56%) as a yellow, practically insoluble solid. This was further purified by sublimation in vacuo under heating to give the analytical sample of **9a** (39.1 mg, 0.097 mmol, 32%). M.p. > 300 °C; HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₂₂H₁₀S₄: 402.9738, found: 402.9738; Anal. calcd for C₂₂H₁₀S₄: C, 65.64; H, 2.50%. Found: C, 65.41; H, 2.63%.
- 2,9-Dioctylbis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;5,6-*b'*]dithiophene (9b)*: This compound was prepared as above by using **8b** (100 mg, 0.114 mmol). The collected solid was washed with water, hexane, acetone, and finally with chloroform to give **9b** (24.8 mg, 0.040 mmol, 35%) as a sparingly soluble yellow solid. A further purification was made by Soxhlet extraction with chlorobenzene to afford a somewhat clear colored sample of **9b** (17.5 mg, 0.028 mmol 25%). M.p. ca. 210 °C (decomposed); ¹H NMR (400 MHz, toluene-*d*₈ at 100 °C) δ 0.90 (t, *J* = 6.4 Hz, 6H), 1.24–1.42 (m, 20H), 1.63 (tt, *J* = 6.4 Hz, 6.4 Hz, 4H), 2.61 (t, *J* = 7.4, 4H), 7.49 (s, 2H), 7.583 (s, 2H), 7.585 (d, *J* = 6.0 Hz, 2H) (one signal was overlapped by the solvent signal); HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₃₈H₄₃S₄: 627.2244, found: 627.2242.

Synthesis of [1]benzothieno[3,2-*b*][1]benzothiophene (BTBT) and its higher homologs through palladium-catalyzed intramolecular decarboxylative arylation

Sojiro Minami^a, Koji Hirano^a, Satoh Tetsuya^{a,b}, Masahiro Miura^{a,*}

^a*Department of Applied Chemistry, Faculty of Engineering, Osaka University, Suita, Osaka 565-0871, Japan*

^b*JST, ACT-C, 4-1-8 Honcho, Kawaguchi, Saitama 332-0012, Japan*

Supplementary data

Characterization data for compounds..... S1

NMR spectra of compounds.....S5

Characterization data for compounds.

Methyl 3-[(2-bromophenyl)thio]benzo[*b*]thiophene-2-carboxylate: light yellow solid; NMR (400 MHz, CDCl₃) δ 3.92 (s, 3H), 6.61 (dd, J = 7.2 Hz, 2.1 Hz, 1H), 6.94-7.01 (m, 2H), 7.38 (dd, J = 7.6 Hz, 7.6 Hz, 1H), 7.50 (dd, J = 7.6 Hz, 7.6 Hz, 1H), 7.55 (dd, J = 7.2 Hz, 2.1 Hz, 1H), 7.84 (d, J = 8.1 Hz, 1H), 7.89 (d, J = 8.1 Hz, 1H); ¹³C NMR (100 MHz, CDCl₃) δ 52.86, 121.47, 122.93, 125.42, 125.66, 126.87, 127.87, 127.89, 128.26, 130.01, 133.03, 136.21, 138.22, 140.07, 140.13, 162.13; HRMS (APCI) m/z (M^+) calcd for C₁₆H₁₁BrO₂S₂: 379.9358, found: 379.9366.

3-[(2-Bromophenyl)thio]benzo[*b*]thiophene-2-carboxylic acid (3a): light yellow solid; m.p. 207 °C; ¹H NMR (400 MHz, DMSO-*d*₆) δ 6.54 (dd, J = 7.6 Hz, 1.2 Hz, 1H), 7.07 (ddd, J = 7.6 Hz, 7.6 Hz, 1.2 Hz, 1H), 7.13 (ddd, J = 7.6 Hz, 7.6 Hz, 1.2 Hz, 1H), 7.45 (dd, J = 7.6 Hz, 7.6 Hz, 1H), 7.57 (dd, J = 7.6 Hz, 7.6 Hz, 1H), 7.66 (d, J = 8.1 Hz, 2H), 8.15 (d, J = 8.1 Hz, 1H), 13.91 (bs, 1H); ¹³C NMR (100 MHz, DMSO-*d*₆) δ 120.16, 123.60, 124.12, 125.87, 126.85, 127.22, 127.56, 127.83, 128.43, 132.87, 137.35, 138.68, 139.22, 139.27, 162.29; HRMS (FAB⁺) m/z ($[M-H]^+$) calcd for C₁₅H₈BrO₂S₂: 362.9143, found: 362.9139.

[1]Benzothieno[3,2-*b*][1]benzothiophene (5a): white solid; ¹H NMR (400 MHz, CDCl₃) δ 7.37-7.50 (m, 4H), 7.86-7.95 (m, 4H); ¹³C NMR (100 MHz, CDCl₃) δ 121.75, 124.19, 125.03, 125.16, 133.26, 133.59, 142.42.

Methyl 3-[(2-bromo-5-octylphenyl)thio]benzo[*b*]thiophene-2-carboxylate: light yellow solid; m.p. 55-56 °C; ¹H NMR (400 MHz, CDCl₃) δ 0.86 (t, J = 7.1 Hz, 3H), 0.94-1.32 (m, 12 H), 2.25 (t, J = 7.5 Hz, 2H), 3.93 (s, 3H), 6.42 (d, J = 2.1 Hz, 1H), 6.78 (dd, J = 8.1 Hz, 2.1 Hz,

1H), 7.34 (ddd, $J = 8.2$ Hz, 7.1 Hz, 1.2 Hz, 1H), 7.43 (d, $J = 8.1$ Hz, 1H), 7.48 (ddd, $J = 8.2$ Hz, 7.1 Hz, 1.2 Hz, 1H), 7.76 (dd, $J = 8.1$ Hz, 1.2 Hz, 1H), 7.88 (dd, $J = 8.1$ Hz, 1.2 Hz, 1H); ^{13}C NMR (100 MHz, CDCl_3) δ 14.25, 22.77, 28.78, 29.22, 29.34, 30.93, 31.98, 35.17, 52.84, 118.62, 122.88, 125.47, 125.51, 127.52, 127.76, 128.67, 130.66, 132.73, 135.33, 137.24, 139.84, 140.03, 142.84, 162.24; HRMS (APCI) m/z (M^+) calcd for $\text{C}_{24}\text{H}_{27}\text{BrO}_2\text{S}_2$: 492.0610, found: 492.0604.

3-[(2-Bromo-5-octylphenyl)thio]benzo[*b*]thiophene-2-carboxylic acid (3b): yellow solid; m.p. 142-143 °C; ^1H NMR (400 MHz, CDCl_3) δ 0.85 (t, $J = 7.1$ Hz, 3H), 0.96-1.34 (m, 12 H), 2.27 (t, $J = 7.5$ Hz, 2H), 6.44 (d, $J = 2.1$ Hz, 1H), 6.82 (dd, $J = 8.1$ Hz, 2.1 Hz, 1H), 7.37 (ddd, $J = 8.2$ Hz, 7.1 Hz, 1.0 Hz, 1H), 7.45 (d, $J = 8.1$ Hz, 1H), 7.51 (ddd, $J = 8.2$ Hz, 7.1 Hz, 1.2 Hz, 1H), 7.76 (dd, $J = 8.1$ Hz, 1.0 Hz, 1H), 7.91 (dd, $J = 8.1$ Hz, 1.0 Hz, 1H); ^{13}C NMR (100 MHz, CDCl_3) δ 14.24, 22.77, 28.81, 29.22, 29.38, 30.90, 31.97, 35.19, 118.96, 123.05, 125.63, 125.70, 128.08, 128.23, 128.94, 131.28, 132.94, 135.30, 136.14, 139.77, 140.69, 143.17, 165.79; HRMS (APCI) m/z ($[\text{M}-\text{H}]^+$) calcd for $\text{C}_{23}\text{H}_{24}\text{BrO}_2\text{S}_2$: 475.0395, found: 475.0407

2-Octyl-[1]benzothieno[3,2-*b*][1]benzothiophene (5b): colorless solid; m.p. 107-108 °C; ^1H NMR (400 MHz, CDCl_3) δ 0.90 (t, $J = 7.1$ Hz, 3H), 1.22-1.45 (m, 10 H), 1.71 (tt, $J = 7.6$ Hz, 7.6 Hz, 2H), 2.76 (t, $J = 7.6$ Hz, 2H), 7.28 (d, $J = 8.1$ Hz, 1H), 7.39 (dd, $J = 7.9$ Hz, 7.9 Hz, 1H), 7.45 (dd, $J = 7.9$ Hz, 7.9 Hz, 1H), 7.72 (s, 1H), 7.79 (d, $J = 8.1$ Hz, 1H), 7.87 (d, $J = 7.9$ Hz, 1H), 7.91 (d, $J = 7.9$ Hz, 1H); ^{13}C NMR (100 MHz, CDCl_3) δ 14.26, 22.82, 29.42, 29.48, 29.64, 31.84, 32.04, 36.28, 121.39, 121.54, 123.49, 124.13, 124.84, 124.94, 126.04, 131.16, 132.73, 133.42, 133.54, 140.54, 142.23, 142.73; HRMS (APCI) m/z ($[\text{M}+\text{H}]^+$) calcd for $\text{C}_{22}\text{H}_{25}\text{S}_2$: 353.1392, found: 353.1393.

Bis(2-ethylhexyl) 3,7-bis[(2-bromophenyl)thio]benzo[1,2-*b*:4,5-*b'*]dithiophene-2,6-dicarboxylate: yellow solid; m.p. 139-140 °C; ^1H NMR (400 MHz, CDCl_3) δ 0.86 (t, $J = 7.4$ Hz, 12H), 1.20-1.42 (m, 16H), 1.62 (tt, $J = 6.1$ Hz, 6.1 Hz, 2H), 4.23 (dd, $J = 11$ Hz, 5.2 Hz, 2H), 4.27 (dd, $J = 11$ Hz, 5.2 Hz, 2H), 6.53-6.56 (m, 2H), 6.96-7.01 (m, 4H), 7.56-7.58 (m, 2H), 8.44 (s, 2H); ^{13}C NMR (100 MHz, CDCl_3) δ 11.22, 14.21, 23.06, 23.93, 29.07, 30.49, 38.90, 68.75, 119.47, 120.92, 126.83, 127.28, 127.34, 128.00, 133.14, 137.63, 137.87, 140.48, 140.88, 161.75; HRMS (APCI) m/z (M^+) calcd for $\text{C}_{40}\text{H}_{44}\text{Br}_2\text{O}_4\text{S}_4$: 876.0466, found: 876.0465.

3,7-Bis[(2-bromophenyl)thio]benzo[1,2-*b*:4,5-*b'*]dithiophene-2,6-dicarboxylic acid (6a): deep yellow solid; m.p. > 300 °C; ^1H NMR (400 MHz, $\text{DMSO}-d_6$) δ 6.53 (dd, $J = 7.8$ Hz, 1.7 Hz, 2H), 7.07 (ddd, $J = 7.5$ Hz, 7.5 Hz, 1.7 Hz, 2H), 7.13 (ddd, $J = 7.8$ Hz, 7.8 Hz, 1.5 Hz, 2H), 7.67 (dd, $J = 7.5$ Hz, 1.5 Hz, 2H), 8.63 (s, 2H), 14.05 (bs, 2H); ^{13}C NMR (100 MHz,

DMSO-*d*₆) δ 119.19, 119.78, 125.13, 126.80, 127.01, 128.51, 132.87, 136.91, 137.43, 139.86, 142.34, 161.99; HRMS (FAB⁻) m/z (M^+) calcd for C₂₄H₁₂Br₂O₄S₄: 649.7980, found: 649.7982.

Bis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;4,5-*b'*]dithiophene (7a): yellow solid (practically insoluble); m.p. > 300 °C; HRMS (APCI) m/z ($[M+H]^+$) calcd for C₂₂H₁₁S₄: 402.9738, found: 402.9736; Anal. calcd for C₂₂H₁₀S₄: C, 65.64; H, 2.50%. Found: C, 65.17; H, 2.60%.

Bis(2-ethylhexyl) 3,7-bis[(2-bromo-5-octylphenyl)thio]benzo[1,2-*b*;4,5-*b'*]dithiophene-2,6-dicarboxylate: yellow solid; m.p. 63-64 °C; ¹H NMR (400 MHz, CDCl₃) δ 0.84 (t, J = 7.1 Hz, 6H), 0.866 (t, J = 6.9 Hz, 6H), 0.871 (t, J = 7.4 Hz, 6H), 0.94-1.44 (m, 40H), 1.63 (tt, J = 6.0 Hz, 6.0 Hz, 2H), 2.23 (t, J = 7.5 Hz, 4H), 4.23 (dd, J = 11 Hz, 5.4 Hz, 2H), 4.28 (dd, J = 11 Hz, 5.4 Hz, 2H), .6.37 (d, J = 2.0 Hz, 2H), 6.79 (dd, J = 8.1 Hz, 2.0 Hz, 2H), 7.45 (d, J = 8.1 Hz, 2H), 8.36 (s, 2H); ¹³C NMR (100 MHz, CDCl₃) δ 11.21, 14.21, 12.25, 22.76, 23.07, 23.94, 28.86, 29.09, 29.20, 29.38, 30.51, 30.99, 31.98, 35.23, 38.93, 68.70, 118.15, 119.55, 127.45, 127.73, 127.99, 132.90, 136.94, 137.47, 140.06, 140.21, 143.01, 161.84; HRMS (APCI) m/z (M^+) calcd for C₅₆H₇₆Br₂O₄S₄: 1100.2973, found: 1100.2972.

3,7-Bis[(2-bromo-5-octylphenyl)thio]benzo[1,2-*b*;4,5-*b'*]dithiophene-2,6-dicarboxylic acid (6b): yellow solid; ca. 260 °C (decomposed); ¹H NMR (400 MHz, DMSO-*d*₆) δ 0.70-1.18 (m, 30H), 2.20 (t, J = 7.0 Hz, 4H), 6.27 (d, J = 1.9 Hz, 2H), 6.89 (dd, J = 8.1 Hz, 1.9 Hz, 2H), 7.56 (d, J = 8.1 Hz, 2H), 8.40 (s, 2H); ¹³C NMR (100 MHz, CDCl₃) δ 13.56, 21.67, 27.49, 28.04, 28.34, 29.76, 30.95, 33.80, 117.14, 118.81, 125.55, 127.17, 127.40, 132.46, 136.23, 136.42, 138.96, 141.13, 142.28, 161.74.

2,9-Dioctylbis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;4,5-*b'*]dithiophene (7b) yellow solid (sparingly soluble); ca. 260 °C (decomposed); ¹H NMR (400 MHz, toluene-*d*₈, 100 °C) δ 0.89 (t, J = 6.8 Hz, 6H), 1.24-1.37 (m, 20H), 1.62 (tt, J = 7.0 Hz, 7.0 Hz, 4H), 2.60 (t, J = 7.4 Hz, 4H), 7.08 (d, J = 8.0 Hz, 2H), 7.50 (s, 2H), 7.59 (d, J = 8.0 Hz, 2H), 7.96 (s, 2H); HRMS (APCI) m/z ($[M+H]^+$) calcd for C₃₈H₄₃S₂: 627.2244, found: 627.2242.

Dibutyl 3,6-bis[(2-bromophenyl)thio]benzo[2,1-*b*;3,4-*b'*]dithiophene-2,7-dicarboxylate: yellow solid; m.p. 134-135 °C; ¹H NMR (400 MHz, CDCl₃) δ 0.94 (t, J = 7.4 Hz, 6H), 1.42 (tt, J = 7.6 Hz, 7.6 Hz, 4H), 1.70 (tt, J = 6.8 Hz, 6.8 Hz, 4H), 4.35 (t, J = 6.5 Hz, 4H), 6.58-6.61 (m, 2H), 6.93-7.00 (m, 4H), 7.52-7.55 (m, 2H), 7.75 (s, 2H); ¹³C NMR (100 MHz, CDCl₃) δ 13.87, 19.35, 30.67, 66.31, 121.30, 122.80, 126.99, 127.92, 127.95, 130.66, 133.10, 134.35, 136.84, 137.93, 140.33, 161.41; HRMS (APCI) m/z ($[M+H]^+$) calcd for C₃₂H₂₉Br₂O₄S₄: 764.9212, found: 764.9227.

3,6-Bis[(2-bromophenyl)thio]benzo[2,1-*b*:3,4-*b'*]dithiophene-2,7-dicarboxylic acid (8a): yellow solid; m.p. ca. 290 °C (decomposed); ¹H NMR (400 MHz, DMSO-*d*₆) δ 6.55-6.58 (m, 2H), 7.03-7.06 (m, 4H), 7.52-7.57 (m, 2H), 7.62-7.64 (m, 2H), 14.13 (bs, 2H); ¹³C NMR (100 MHz, DMSO-*d*₆) δ 120.10, 122.09, 127.32, 127.60, 128.33, 128.46, 132.88, 133.35, 137.14, 138.46, 139.40, 161.72; HRMS (FAB⁺) *m/z* (M⁺) calcd for C₂₄H₁₂Br₂O₄S₄: 649.7980, found: 649.7996.

Bis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;5,6-*b'*]dithiophene (9a): yellow solid (practically insoluble); m.p. > 300 °C; HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₂₂H₁₁S₄: 402.9738, found: 402.9738; Anal. calcd for C₂₂H₁₀S₄: C, 65.64; H, 2.50%. Found: C, 65.41; H, 2.63%.

Dibutyl 3,6-bis[(2-bromo-5-octylphenyl)thio]benzo[2,1-*b*:3,4-*b'*]dithiophene-2,7-dicarboxylate: yellow solid; m.p. 102-103 °C; ¹H NMR (400 MHz, CDCl₃) δ 0.84 (t, *J* = 7.0 Hz, 6H), 0.94 (t, *J* = 7.4 Hz, 6H), 0.96-1.32 (m, 24H), 1.42 (tq, *J* = 7.6 Hz, 7.6 Hz, 4H), 1.70 (tt, *J* = 6.8 Hz, 6.8 Hz, 4H), 2.24 (t, *J* = 7.6 Hz, 7.6 Hz, 4H), 4.35 (t, *J* = 6.6 Hz, 4H), 6.44 (d, *J* = 2.0 Hz, 2H), 6.78 (dd, *J* = 8.1 Hz, 2.0 Hz, 2H), 7.42 (d, *J* = 8.1 Hz, 2H), 7.69 (s, 2H); ¹³C NMR (100 MHz, CDCl₃) δ 13.87, 14.26, 19.36, 22.77, 28.85, 29.23, 29.37, 30.71, 30.96, 31.98, 35.19, 66.24, 118.56, 122.76, 127.64, 128.40, 131.36, 132.86, 134.28, 136.03, 137.05, 140.20, 142.99, 161.53; HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₄₈H₆₁Br₂O₄S₄: 987.1798, found: 987.1792.

3,6-Bis((2-bromo-5-octylphenyl)thio)benzo[2,1-*b*:3,4-*b'*]dithiophene-2,7-dicarboxylic acid (8b): yellow solid; m.p. 232-233 °C; ¹H NMR (400 MHz, DMSO-*d*₆) δ 0.78 (t, *J* = 7.1 Hz, 6H), 0.68-1.20 (m, 24H), 2.19 (t, *J* = 7.1 Hz, 7.1 Hz, 4H), 6.36 (d, *J* = 2.0 Hz, 2H), 6.87 (dd, *J* = 8.1 Hz, 2.0 Hz, 2H), 7.51 (d, *J* = 8.1 Hz, 2H), 7.69 (m, 2H); ¹³C NMR (100 MHz, DMSO-*d*₆) δ 13.97, 22.06, 27.62, 28.38, 28.53, 29.89, 31.30, 33.80, 117.47, 121.95, 127.70, 127.83, 129.00, 132.68, 133.22, 136.39, 137.72, 139.17, 142.55, 161.76; HRMS (FAB⁺) *m/z* (M⁺) calcd for C₄₀H₄₄Br₂O₄S₄: 874.0469, found: 874.0467.

2,9-Dioctylbis[1]benzothieno[2,3-*d*;2',3'-*d'*]benzo[1,2-*b*;5,6-*b'*]dithiophene (9b): yellow solid (sparingly soluble); m.p. ca. 210 °C (decomposed); ¹H NMR (400 MHz, toluene-*d*₈ at 100 °C) δ 0.90 (t, *J* = 6.4 Hz, 6H), 1.24-1.42 (m, 20H), 1.63 (tt, *J* = 6.4 Hz, 6.4 Hz, 4H), 2.61 (t, *J* = 7.4, 4H), 7.49 (s, 2H), 7.583 (s, 2H), 7.585 (d, *J* = 6.0 Hz, 2H) (one signal was overlapped by the solvent signal); HRMS (APCI) *m/z* ([M+H]⁺) calcd for C₃₈H₄₃S₄: 627.2244, found: 627.2242.

[¹H and ¹³C NMR Spectra of Methyl Ester of **3a**]

[¹H and ¹³C NMR Spectra of **3a**]

[^1H and ^{13}C NMR Spectra of **5a**]

5a

[^1H and ^{13}C NMR Spectra of Methyl Ester of **3b**]

[^1H and ^{13}C NMR Spectra of **3b**]

[^1H and ^{13}C NMR Spectra of **5b**]

[^1H and ^{13}C NMR Spectra of Ethylhexyl Ester of **6a**]

[^1H and ^{13}C NMR Spectra of **6a**]

[^1H and ^{13}C NMR Spectra of Ethylhexyl Ester of **6b**]

[^1H and ^{13}C NMR Spectra of **6b**]

[^1H NMR Spectrum of **7b**]

[¹H and ¹³C NMR Spectra of butyl ester of **8a**]

[^1H and ^{13}C NMR Spectra of **8a**]

[^1H and ^{13}C NMR Spectra of Butyl Ester of **8b**]

[^1H and ^{13}C NMR Spectra of **8b**]

[¹H NMR Spectrum of **9b**]