Micron thick Gd₂O₃ films for GaN/AlGa_N metal-oxide-semiconductor heterostructures

Daniel A. Grave^{a,b}, Joshua A. Robinson^a, and Douglas E. Wolfe^{a,b,c}

^a Materials Science and Engineering Department, Pennsylvania State University, State College, PA 16802, USA

^b The Applied Research Laboratory, Pennsylvania State University, State College, PA 16802, USA

^c Engineering Science and Mechanics Department, Pennsylvania State University, State College, PA 16802, USA

Abstract

One μm thick Gd₂O₃ films were grown on GaN/AlGa_N heterostructures by reactive electron beam physical vapor deposition. The films were of cubic bixbyite phase with strong (222) out-of-plane and in-plane texture. The films showed a columnar microstructure with feather-like growth. Transmission electron microscopy analysis and selected area diffraction showed highly oriented single crystal like growth near the film interface which degraded as the film thickness increased. Capacitance-voltage (C-V) characteristics show that the Gd₂O₃ device results in a negative threshold shift of approximately 1.9 V. Hysteresis of 0.9 V was extracted from the C-V curve corresponding to a trapped charge density of $6.9 \times 10^{10} \text{ cm}^{-2}$. The conduction mechanisms were found to be dominated by Poole Frenkel conduction between 50-100 °C and Schottky emission between 125-200 °C. The trap height for Poole-Frenkel conduction was 0.46 eV and the Schottky barrier height was 0.79 eV.

Introduction

Gd₂O₃ has been proposed as a material for neutron detection due to gadolinium's large thermal neutron capture cross section [1]. However, incorporation of Gd₂O₃ into solid-state microelectronic devices for this application is not well understood. A promising class of materials for neutron detection is based on the group IIIa-nitride compound semiconductors: aluminum nitride (AlN), gallium nitride (GaN), and their alloy, AlGa_N. This system has

1 already proven to be highly sensitive to charge injection from chemical and biological agents [2].
2 This phenomenon may also be exploited for radiation detection. Incorporation of Gd_2O_3 into
3 GaN/AlGaN semiconductor quantum well structures that generate charged particles could yield
4 highly sensitive detectors.

5 Deposition of single crystal Gd_2O_3 has been reported on GaN substrates in the cubic
6 [3,4], monoclinic [5], and hexagonal [6] phases. Cubic growth on GaN was shown to have single
7 crystal structure up to a thickness of 70 nm [3]. A high density of dislocations resulted from the
8 large lattice mismatch between cubic Gd_2O_3 and GaN (20%). This resulted in metal-oxide-
9 semiconductor (MOS) devices with a small breakdown field. In a recent study, a charge trapping
10 phenomena was observed in GaN/AlGaN/ Gd_2O_3 /Ni-Au MOS heterostructures due to
11 crystallization of the Gd_2O_3 film [7]. The charge trapping phenomenon resulted in a significant
12 memory window with only a time dependent charge loss.

13 While most studies have previously examined Gd_2O_3 films with small thicknesses less
14 than 100 nm, large film thickness is needed to ensure proper capture of neutrons. This study
15 details the growth of thick Gd_2O_3 films deposited on GaN / AlGaN heterostructures by reactive
16 electron beam physical vapor deposition (EB-PVD). The crystallographic phase, orientation,
17 and morphology of the films are investigated. Electrical measurements are made to determine
18 the dielectric properties and conduction mechanisms present within the film.

21 **Experimental details**

22 GaN/AlGaN structures grown on 4H-SiC substrates (CREE Inc.) were subject to a
23 reactive ion etch to isolate the active regions using a Tegal PM2 etcher. Contact lithography

techniques were then used to pattern the devices. Ohmic contacts were deposited by evaporation of Ti/Al/Ni/Au using a Kurt J. Lesker Lab 18 evaporator followed by a rapid thermal anneal at 875 °C for 60 seconds in an N₂ environment (Alwin 21 AG610 RTA sytem).

After ohmic contact annealing, gadolinium oxide (Gd₂O₃) films were then deposited on the GaN / AlGaN quantum well structures via reactive electron beam physical vapor deposition (Denton Inc.). Prior to Gd₂O₃ film deposition, the substrates were cleaned in an acetone bath for four minutes, followed by an iso-propanol bath for 1 min. The substrates were then rinsed with de-ionized water and dried with high purity (99.9999%) N₂ gas. A gadolinium metal ingot (Hefa Rare Earth), purity 99.99%, weighing between 25 and 30 g was placed in a graphite crucible and used as the evaporant material. After the samples were loaded into the deposition chamber and positioned within the heater, the chamber was first evacuated using a mechanical pump to a pressure of approximately 0.13 Pa. Subsequently, the base pressure was pumped below 8×10^{-4} Pa by use of a cryogenic pump. Cold water was flowed throughout the chamber walls to keep the chamber cooled and to prevent damage. During elevated temperature deposition, the sample temperature was ramped up and the samples allowed to soak at temperature for 10 minutes before starting the deposition process. Ultra high purity O₂ (99.9999%) was introduced to the chamber through an inlet tube 15 seconds before opening of the deposition shutter. Two quartz crystals were installed in the crystal thickness monitor before every deposition for measuring *insitu* film thickness. The source to substrate distance was 12.5 inches (31.75 cm). The substrate temperature during film deposition was 650 °C. Subsequent to film deposition, photolithography was performed to pattern the film. A 100:1 H₂O:H₂SO₄ solution was used to etch the regions of interest. This was followed by patterning and deposition of the top Ti/Au

contact with thickness of 10/100 nm. Gd_2O_3 films were also deposited on bare GaN / AlGaN substrates for materials characterization.

θ - 2θ scans were performed on the Gd_2O_3 films using a Phillips MRD diffractometer, type PW3040/00. A copper anode was used as the x-ray source. Scans were collected from a 2θ angle of 10 degrees to 90 degrees with operating voltage / current of 40kV / 45 mA. The step size was 0.02° and the time step was 1 second. The x-ray beam was set for 1.2 mm x 10 mm horizontal and vertical divergence, respectively. Pole figure measurements were also performed on select Gd_2O_3 films to determine both out-of-plane and in-plane texture. Pole figures were taken using sample tilts of $0 - 85^\circ$ in 5° steps with azimuthal rotation from $0 - 355^\circ$ with a step size of 1° and step time of 1 second.

Transmission electron microscopy (TEM) cross-sectional specimens were prepared using conventional mechanical polishing followed by Ar ion milling in a precision ion polishing system. Cross-sectional TEM and selected area diffraction (SAD) were performed in a JEOL-2010F field-emission TEM/STEM. The microscope operation voltage was 200 keV. Scanning electron microscope (SEM) surface analysis was performed using a LEO 1530 field emission SEM with operating voltage of 5 keV.

A Keithley Model 4200-SCS Semiconductor Characterization System was used to obtain capacitance-voltage (C-V) measurements for the Metal-oxide-semiconductor capacitors (MOSCAPs). A 4200-CVU integrated C-V measuring unit was used to extract these measurements. The unit was calibrated to correct for stray capacitances using open and short calibrations. The measured device area was $7.1 \times 10^{-4} \text{ cm}^2$. The C-V measurements were performed at a frequency of 1 MHz. Current-voltage-temperature (I-V-T) measurements were made in order to determine DC conduction mechanisms within the Gd_2O_3 films. The samples

were loaded onto a Cascade Microtech probe station at the Penn State Dielectric Center. An Agilent HP4140B pA meter was used to measure the current. The temperature of the stage was controlled by a Temptronic TP3000A Thermochuck system.

Results and Discussion

The θ - 2θ x-ray diffraction (XRD) pattern for the Gd_2O_3 thin films is shown in Figure 1. From peak identification, the film is of the bixbyite cubic phase with space group $\text{Ia}\bar{3}$ consistent with ICDD card #0043-1014 [8]. A strong (222) out-of-plane preferred orientation is observed. For previous growth of Gd_2O_3 thin films on GaN, single crystal cubic, monoclinic, and hexagonal Gd_2O_3 has been reported. Due to the $1\text{ }\mu\text{m}$ Gd_2O_3 film thickness and the large lattice mismatch with GaN (20%), heteroepitaxial growth is not expected. While the Gd_2O_3 film is mostly (222) oriented, a slight peak is observed from the Gd_2O_3 (400) peak.

Pole figure analysis was used to examine the in-plane texture of the Gd_2O_3 film. The pole figure of the (400) plane is shown in Figure 2. A six fold rotational symmetry is observed at a ψ angle of approximately 35° , which is consistent with the theoretical angle (35.3°) between the (111) and (440) planes. The expected symmetry around the $\langle 111 \rangle$ planes for cubic crystals is three-fold. This suggests that two orientational relationships are present related by a 180 degree rotation. A similar rotational relationship has been previously observed for bixbyite Sc_2O_3 films grown on GaN [9,10] and more recently for Gd_2O_3 films grown on GaN/AlGaIn substrates [4]. The azimuthal spread of the (111) crystallites is less than 5 degrees, suggesting good in-plane texture.

The growth of the Gd_2O_3 films were investigated further using TEM and SEM microscopy. The cross sectional growth of the $\text{Gd}_2\text{O}_3/\text{GaN}$ film is shown in the low

magnification brightfield TEM image in Figure 3a. Clear columnar growth was observed with column widths of approximately 150 – 200 nm signifying substantial grain growth. A “feathery” type growth is observed, which has been previously linked to shadowing effects in EB-PVD thermal barrier coatings [11]. Figure 3b is a high magnification brightfield TEM image of the interfacial region of the $\text{Gd}_2\text{O}_3/\text{GaN}/\text{AlGaN}$ heterostructure. Selected area diffraction patterns were taken along one column thickness. Figures 3c, 3d, and 3e correspond to SAD patterns taken from the bottom, middle, and top of one of the columns, respectively. The bottom pattern shows good single crystallinity in this part of the film and that the growing film possesses initial $\text{Gd}_2\text{O}_3(111) \parallel \text{GaN}(0001)$ heteroepitaxial relationship with the GaN substrate. From the top layer, additional diffraction spots are observed suggesting that the highly ordered structure diminishes as the film grows thicker, possibly as a result of strain minimization by nucleation of other grain orientations. An SEM image of the top surface of the film is shown in Figure 4. The surface shows two types of structures. One such structure are pyramidal tips bounded by (111) facets, consistent with the (111) oriented growth and the TEM image previously observed. In other cases, the pyramids are instead truncated, and a flat triangular facet is observed, as would be expected for epitaxial growth.

MOS capacitor measurements were then made for the $\text{GaN}/\text{AlGaN}/\text{Gd}_2\text{O}_3/\text{Ti}/\text{Au}$ MOS capacitors and compared to a control sample without the oxide layer. As shown in Figure 5, the threshold voltage of the control sample is approximately -2.9 V with a sharp transition between accumulation, depletion, and inversion. No hysteresis is observed in the voltage sweep. The C-V curve of the MOSCAP with Gd_2O_3 layer retains the sharp transition observed in the control sample, suggesting good interface quality between the Gd_2O_3 film and GaN substrate. Deposition of the Gd_2O_3 films results in a leftward shift of the C-V curve by 1.9 V, indicating

the existence of positive fixed oxide charge present within the Gd₂O₃ film. The approximately 1 V hysteresis suggests the presence of slow traps which can respond to the DC signal but cannot follow the AC signal. It is unclear, however, whether these traps are related to bulk or interface traps. The electron trap number density (Q_{ot}) can be estimated by equation 1:

$$Q_{ot} = \frac{\Delta V_H C_{ox}}{qA}$$

where ΔV_H is the hysteresis, C_{ox} is the capacitance in accumulation, q is the electronic charge, and A is the area of the capacitor. From this equation, Q_{ot} of $6.9 \times 10^{10} \text{ cm}^{-2}$ is extracted.

The I-V-T characteristics for GaN / AlGaIn / Gd₂O₃ / Ti / Au are shown in Figure 6. As observed, the curve is highly asymmetric, with the forward bias current being approximately 2 orders of magnitude higher than the reverse bias current. For the GaN / AlGaIn / Gd₂O₃ / Ti / Au MOS capacitor devices, we studied the conduction mechanisms in the positive bias region (substrate injection) under accumulation to ensure that the electric field drops only across the oxide and that no significant contributions from substrate conduction are observed. Between 50 – 100 °C, the experimental data in the positive bias regions was fitted to the Poole-Frenkel model [12] using equation 2:

$$J = (qN_C\mu)E_{ox} \left[\frac{-q(\phi - \sqrt{qE_{ox}/\pi\epsilon_r\epsilon_0})}{k_B T} \right] \quad \text{Eq. 2}$$

where J is the current density, q is the electronic charge, N_C is the density of states in the conduction band, μ is the electronic drift mobility, E_{ox} is the electric field across the oxide, ϕ is the trap energy level, ϵ_r is the oxide dielectric constant, ϵ_0 is the permittivity of free space, k_B is Boltzmann's constant, and T is the measurement temperature. From equation 2, $\ln(J/E)$ vs $V^{1/2}$

should give a linear relationship for this conduction mechanism. The fit to the data is shown in Figure 7a. Dielectric constants of 12-23 were extracted using the slope of the linear $\ln(J/E)$ vs $E^{1/2}$ plots. These values are in good agreement with the static permittivity value of 14 measured by C-V measurements. From the temperature dependence, a trap height of 0.46 eV was calculated. As the temperature is increased between 125 and 200 °C, the Poole-Frenkel model no longer holds. Instead, transition to Schottky mechanism is observed. Schottky conduction [12] is given by:

$$J = A^*T^2 \exp \left[\frac{-q(\phi - \sqrt{qE_{ox}/4\pi\epsilon_r\epsilon_0})}{k_B T} \right] \quad \text{Eq. 3}$$

where J is the current density, A^* is the Richardson constant, T is the measurement temperature, q is the electronic charge, ϕ is the Schottky barrier height, E_{ox} is the electric field across the oxide, k_B is Boltzmann's constant, ϵ_r is the oxide dielectric constant, and ϵ_0 is the permittivity of free space. Therefore, if Schottky conduction is a dominating mechanism, $\ln(J/T^2)$ vs $\sqrt{E_{ox}}$ should yield a linear plot. Schottky plots of $\ln(J/T^2)$ vs $E^{1/2}$ shown in Figure 7b yielded dielectric constants of 17-23, a good match to the static dielectric constant. A Schottky barrier height of 0.79 eV was calculated from the data.

Conclusions

We report the growth of 1 μm thick Gd_2O_3 films on GaN/AlGaN substrates. The films were (222) textured both in and out-of-plane with slight formation of (400) crystallites. The film exhibited a columnar microstructure that initially grew with initial heteroepitaxial relationship to the substrate. The single crystal like structure of the film deteriorates as the film thickness

1 increases. C-V measurements showed existence of positive fixed oxide charge and slow trapped
2 charge observed through threshold voltage shift and hysteresis, respectively. I-V-T
3 measurements showed that the devices were governed by Poole-Frenkel and Schottky emission
4 conduction mechanisms.

6 **Acknowledgements**

7 This research was sponsored by the Defense Threat Reduction Agency (DTRA) under
8 contract number DTRA01-03-D-0010-0022. Any opinions, findings, conclusions, or
9 recommendations expressed in this material are those of the authors and do not necessarily
10 reflect the views of DTRA.

References

- [1] G.F. Knoll, Radiation Detection and Measurement, 4th ed., John Wiley, Hoboken, 2010.
- [2] B.S. Kang, H.T. Wang, F. Ren, S.J. Pearton, Electrical detection of biomaterials using AlGaIn/GaN high electron mobility transistors, *J. Appl. Phys.* 104 (2008) 031101. doi:10.1063/1.2959429.
- [3] J.W. Johnson, B. Luo, F. Ren, B.P. Gila, W. Krishnamoorthy, C.R. Abernathy, S.J. Pearton, J.I. Chyi, T.E. Nee, C.M. Lee, C.C. Chuo, Gd₂O₃/GaN metal-oxide-semiconductor field-effect transistor, *Appl. Phys. Lett.* 77 (2000) 3230. doi:10.1063/1.1326041.
- [4] J.F. Ihlefeld, M. Brumbach, A.A. Allerman, D.R. Wheeler, S. Atcitty, AlGaIn composition dependence of the band offsets for epitaxial Gd₂O₃/Al_xGa_{1-x}N ($0 \leq x \leq 0.67$) heterostructures, *Appl. Phys. Lett.* 105 (2014) 012102. doi:10.1063/1.4889883.
- [5] W.H. Chang, C.H. Lee, P. Chang, Y.C. Chang, Y.J. Lee, J. Kwo, C.C. Tsai, J.M. Hong, C.-H. Hsu, M. Hong, High κ dielectric single-crystal monoclinic Gd₂O₃ on GaN with excellent thermal, structural, and electrical properties, *J. Cryst. Growth.* 311 (2009) 2183–2186. doi:10.1016/j.jcrysgro.2008.10.079.
- [6] W.H. Chang, C.H. Lee, Y.C. Chang, P. Chang, M.L. Huang, Y.J. Lee, C.-H. Hsu, J.M. Hong, C.C. Tsai, J.R. Kwo, M. Hong, Nanometer-Thick Single-Crystal Hexagonal Gd₂O₃ on GaN for Advanced Complementary Metal-Oxide-Semiconductor Technology, *Adv. Mater.* 21 (2009) 4970–4974. doi:10.1002/adma.200902101.
- [7] L.B. Chang, A. Das, R.M. Lin, S. Maikap, M.J. Jeng, S.T. Chou, An observation of charge trapping phenomena in GaN/AlGaIn/Gd₂O₃/Ni–Au structure, *Appl. Phys. Lett.* 98 (2011) 222106. doi:10.1063/1.3596382.
- [8] (n.a), International Center for Diffraction Data (ICDD), Card 00–43–1014, (1994)., (n.d.).
- [9] A.M. Herrero, B.P. Gila, C.R. Abernathy, S.J. Pearton, V. Craciun, K. Siebein, F. Ren, Epitaxial growth of Sc₂O₃ films on GaN, *Appl. Phys. Lett.* 89 (2006) 092117. doi:10.1063/1.2270058.
- [10] J.S. Jur, V.D. Wheeler, D.J. Lichtenwalner, J.-P. Maria, M.A.L. Johnson, Epitaxial growth of lanthanide oxides La₂O₃ and Sc₂O₃ on GaN, *Appl. Phys. Lett.* 98 (2011) 042902. doi:10.1063/1.3541883.
- [11] U. Schulz, S.G. Terry, C.G. Levi, Microstructure and texture of EB-PVD TBCs grown under different rotation modes, *Mater. Sci. Eng. A.* 360 (2003) 319–329. doi:10.1016/S0921-5093(03)00470-2.

[12] F.-C. Chiu, A Review on Conduction Mechanisms in Dielectric Films, Adv. Mater. Sci. Eng. 2014 (2014) 578168.

Figure Captions

Figure 1. θ -2 θ XRD pattern of Gd_2O_3 film.

Figure 2. (440) Pole figure of Gd_2O_3 film.

Figure 3. (a) Low magnification brightfield TEM image of Gd_2O_3 film deposited on GaN/AlGaIn substrate. (b) High magnification brightfield TEM image of the Gd_2O_3 /GaN interface. Selected area diffraction patterns taken from the (c) bottom, (d) middle, and (e) top regions of the film.

Figure 4. SEM top surface image of Gd_2O_3 film.

Figure 5. C-V sweep of GaN/AlGaIn/ Gd_2O_3 /Ti/Au device and control device without oxide.

Figure 6. I-V measurements of GaN/AlGaIn/ Gd_2O_3 /Ti/Au device taken at different temperatures.

Figure 7. Plots showing fit to (a) Poole-Frenkel and (b) Schottky Conduction

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7a

Figure 7b