Blocking layers for nanocomposite photoanodes in dye sensitized solar cells: Comparison of atomic layer deposition and TiCl_4 treatment

Venkata Manthina^{a,b}, Alexander G. Agrios^{a,b}

a, Department of Civil & Environmental Engineering, University of Connecticut, 261 Glenbrook Rd Unit 2037, Storrs, CT 06269, USA

b, Center for Clean Energy Engineering, University of Connecticut, 44 Weaver Rd, Storrs, CT 06269-5233, USA

Abstract

Charge recombination at the electrode/electrolyte interface can be prevented by efficient blocking layers. Here, TiO_2 blocking layers have been deposited using atomic layer deposition (ALD) and TiCl_4 treatment. The number of TiO_2 ALD cycles was optimized for I^-/I_3^- and Fc/Fc^+ electrolytes. The optimized TiO_2 ALD films' performance was compared with the TiCl_4 treated films. TiCl_4 treated films performed better than the ALD deposited films, attributed to reduction of the defects, which act as active sites of recombination.

Introduction

In the dye-sensitized solar cell (DSSC), charge recombination at the semiconductor/electrolyte interface is a major loss pathway, and particularly dominant at low light intensities[1]. The classic I^-/I_3^- electrolyte has slow recombination kinetics, but alternatives have been sought due to its large overpotential loss, complex electrochemistry and corrosive nature. Other redox couples like Fc/Fc^+ [2], $\text{Co}^{2+}/\text{Co}^{3+}$ [3] and $\text{Mn}^{3+}/\text{Mn}^{4+}$ [4] have the benefits of simple single electron transfers and minimized overpotential loss, but have higher recombination rates. The DSSC record efficiency was achieved with a cobalt complex but required an especially thin semiconductor film to offset the relatively high recombination rate [5]. Blocking layers are widely used in DSSC to prevent recombination of the electron in the semiconductor or FTO with the electrolyte. Blocking layers are often thin insulating layers of TiO_2 [6], ZnO [7, 8], ZrO_2 [9, 10], SiO_2 [9], Al_2O_3 [9, 11], MgO [12, 13], HfO_2 [14], CdO [15], or polysiloxane[16] deposited on working electrode by various techniques like spray pyrolysis[17], sputtering[18], spin coating[19], dip coating[20], chemical vapor deposition[21], sol-gel deposition[9], TiCl_4 treatment[6], chemical bath deposition[22] or atomic layer deposition[23].

Figure 1. Schematic of (a) ZnO-TiO₂ film and (b) ZnO-TiO₂ film with blocking layer.

The ideal blocking layer should cover the entire surface of the FTO and TiO₂ to prevent recombination and should not prevent electron injection. Chemical bath deposition barrier layers often increased the performance of the DSSC, but non uniform growth of barrier layers and lower precision of thickness control is observed. This led to growth of atomic layer deposition (ALD) as an alternative to chemical bath deposition. ALD offers precision thickness control in the ångström range and uniform coating. The thickness of the barrier layer is important as it can prevent electron injection, overshadowing the effect of reducing recombination or improving voltage of cell due to a conduction band rise [24]. In this report we used two simple techniques for the synthesis of the blocking layers on ZnO-TiO₂ films. Atomic layer deposition and TiCl₄ treatment were used due to low temperature and large area synthesis. We analyzed the effect of the thickness of the blocking layers on DSSC performance in conventional I⁻/I₃⁻ electrolyte and the fast recombining Fc/Fc⁺ electrolyte. The results provide understanding of the role of blocking layer thickness and insight for optimizing DSSC and other electrochemical processes like water splitting.

Experimental

Reagents and Materials. All chemicals were purchased from Sigma-Aldrich (USA) and were ACS grade. N719 was purchased from Dyesol (Australia). SnO₂: F glass (FTO, transmission > 80% in the visible spectrum; sheet resistance 8 Ω / $\square$) was purchased from Hartford Tec Glass (USA).

Electrode Fabrication. ZnO-TiO₂ (ZT) films are synthesized as reported previously [25]. TiCl₄ treatment was carried by immersing the ZT films in 40 mM TiCl₄ solution[6] at 4°C for 30 minutes and rinsed in deionized water and ethanol[26]. ALD of TiO₂ on the ZnO-TiO₂ films was carried out using a Cambridge Nanotech Savannah S100 using successive pulses of titanium isopropoxide (75°C) and deionized water (25°C) and using nitrogen as the carrier gas inside the vacuum chamber with base pressure of 2 mtorr. The substrate was held at 200°C temperature inside the ALD reactor. After the pulse of titanium isopropoxide (14 s) and water (7 s) the precursors were confined in the reactor for 30 ms to ensure complete coverage of the TiO₂ inside the mesopores of the ZT films. The chamber was flushed with nitrogen for 30 seconds between cycles to remove any byproducts. The films were sintered on a titanium hot plate at 500°C. This ALD process was previously measured to deposit 0.04 nm of TiO₂ per ALD cycle [27].

Dye Loading

Sensitization. After sintering at 500°C, films were allowed to cool to 100°C then immediately immersed in 0.3 mM N719 in ethanol. After 12 hours they were removed and rinsed in acetonitrile and dried in air. The amount of N719 adsorbed by films was measured by immersion of a dyed film in aqueous 0.1 M NaOH to desorb the dye, followed by spectroscopic determination of the dye concentration, as we reported previously [25].

Solar Cell Assembly. Each sensitized electrode was sealed against a counter electrode on a hot plate at 120°C using a hot-melt plastic frame (Solaronix, Meltonix 1170, 25 µm thick), applying light pressure with a glass rod. The assembled cell was filled with electrolyte through two holes in the counter electrode. The holes were then sealed using hot-melt plastic and a thin glass cover slide. The exposed conducting glass leads of each electrode were coated with copper tape (3M) for improved electrical conductivity.

Electrolyte Composition. Minimal electrolyte recipes were used to exclude complications due to interactions with the various additives that are commonly used. Iodide/triiodide (I^-/I_3^-) electrolyte was prepared with 0.5 M tetrabutylammonium iodide and 0.05 M iodine (I_2) in 3-methoxypropionitrile. The ferrocene/ferrocenium (Fc/Fc^+) electrolyte contained 0.1 M ferrocene and 0.05 M ferrocenium hexafluorophosphate (Aldrich) in 3-methoxypropionitrile. The Fc/Fc^+ electrolyte was prepared fresh and deoxygenated by bubbling nitrogen 10 minutes prior to cell fabrication to minimize reaction of ferrocene with oxygen.

Solar Cell Characterization. Current–voltage (J – V) measurements were made using Keithley 2400 source/meter controlled by a PC, while irradiating at 100 mW/cm² (1 sun) with AM 1.5G simulated sunlight produced by a solar simulator (Newport 91160), calibrated against a silicon reference cell with KG5 filter (PV Measurements, Inc., Boulder, CO). The DSSC active area was 1 cm².

Characterization. The morphology of ZnO-TiO₂ films treated with TiCl₄ and ALD was investigated by scanning electron microscopy (FEI Quanta FEG250 SEM in High vacuum mode) with attached EDX, and characterized by X-ray powder diffraction (XRD) using a Bruker D8

Advance X-ray diffractometer using Cu K α radiation ($\lambda = 0.154178$ nm) at a scanning rate of 0.04° s $^{-1}$ in the 2θ range from 10° to 90° .

Results and Discussion

ALD TiO₂ blocking layers on ZnO-TiO₂ films

Figure 2 shows SEM images of hybrid ZnO nanorod–TiO₂ nanoparticle (ZT) films coated with TiO₂ blocking layers of varying thickness by ALD. The increasing thickness of the blocking layer with increasing number of ALD cycles is apparent in the images. As the number of cycles goes into the hundreds it can be seen that the nanoparticles are encased in a thick TiO₂ coating. This has the effect of closing the small pores between nanoparticles, which can be expected to reduce the total surface area.

Figure 2. ALD of TiO_2 on ZnO-TiO_2 (ZT) films (a) 0, (b) 40, (c) 100, (d) 200, (e) 300, (f) 400 and (g) 500 cycles.

Figure 3. SEM image of TiCl_4 treated ZT Film.

Figure 3 shows an SEM image of a ZT film coated with a TiO_2 blocking layer via TiCl_4 treatment. This resembles the thinnest of the ALD blocking layers we produced. This is to be expected, as previous studies indicate a TiO_2 particle growth of about 1 nm after TiCl_4 treatment [28].

From the EDX spectrum in Figure 4 we can compare the mass ratio of Ti to (Ti+Zn) between the two coatings on ZT films, which is 2.63% Ti for a 100-cycle ALD film and 3.22% Ti for a TiCl_4 treated film.

Figure 4. EDX spectrum of ZT films coated with TiO_2 by (a) 100 layers of ALD and (b) TiCl_4 treatment

Effect of number of ALD cycles.

Figure 5. Current-voltage (J–V) characteristics for solar cells using ZT films with 0-500 ALD cycles and (a) I⁻/I₃⁻ or (b) Fc/Fc⁺ electrolytes, under 100 mW/cm² AM 1.5G simulated sunlight

The performance of DSSC devices with different numbers of TiO₂ ALD layers over ZT electrodes is shown in Figure 5. In both I⁻/I₃⁻ (Figure 5a) and Fc/Fc⁺ (Figure 5b) electrolytes, thin ALD coatings improved performance until an optimum thickness was reached, after which the current and voltage decreased significantly. Thin ALD layers of TiO₂ do not crystallize even upon sintering [29]. The amorphous coating lacks abundant electronic states to effectively relay charges

between the underlying TiO_2 or ZnO and species outside the coating such as dyes and triiodide, forcing such exchange to occur by tunneling, reducing electron transfer rates. Dye injection efficiency is reduced only slightly, since the dye's electron injection rate is orders of magnitude faster than its excited state decay [9]. But the slower recombination kinetics tilt the competition between electron transport and recombination toward the former, resulting in better charge collection. In competition with this favorable effect, the filling in of pores results in a reduction of surface area and a reduced amount of adsorbed dye, as shown in Figure 6. The dye loading is greatly decreased as the ALD coating becomes thicker.

The optimal number of ALD cycles iodide/triiodide electrolyte is 100 (Figure 5a). In an electrolyte with ferrocene/ferrocenium, the optimum is 300 ALD cycles (Figure 5b). Fc/Fc^+ has much higher rates of recombination with electrons in TiO_2 than iodide/triiodide. This results in thicker optimal blocking layer for Fc/Fc^+ , since it is worth sacrificing additional dye loading in order to further reduce the high recombination rate.

TiCl_4 blocking layer

In contrast to the sharp drop in dye loading with even the thinnest ALD coatings used in this study, the TiCl_4 treatment results a slight increase in dye loading (Figure 6). The TiCl_4 -treated hybrid ZT film carries about 7% more dye than an untreated ZT film. A comparison of the current–voltage characteristic of untreated, optimally ALD-treated, and TiCl_4 -treated hybrid ZT films is shown in Figure 7. The TiCl_4 treatment leads to a remarkable increase in the short-circuit current density (J_{sc}) by a factor of three compared to untreated ZT film, and by a factor of 2.2 versus the best ALD-treated film. Clearly, the 7% boost in dye loading does not account for the current increase.

We note that the TiCl_4 treatment also results in a reduced open-circuit voltage (V_{oc}) by about 90 mV versus the untreated film, and about 110 mV versus the ALD-treated film. This is despite the fact that the TiCl_4 treatment is known to reduce recombination by passivating surface defects in the TiO_2 [30]. Various defects can take place on the surface of the TiO_2 nanoparticles due to the presence of the oxygen vacancies, bridge bonded oxygen, hydroxyl groups and fivefold coordinated Ti atoms [31, 32]. Photoluminescence measurements have shown these defects to be reduced by the TiCl_4 treatment [33, 34]. This effect is seen in the dark current data for the DSSC devices (Figure 8), which indicate that both coatings substantially reduce recombination compared to the uncoated film, although the ALD coating has a larger effect on recombination.

These findings can be easily reconciled thanks to the work of Sommeling et al. [28], who found that the TiCl_4 treatment results in a positive shift of the TiO_2 conduction band by about 100 mV. This has the effect of reducing the voltage, despite the reduced recombination, while increasing injection efficiency due to the larger driving force from the dye LUMO to the TiO_2 conduction band. The result is a TiCl_4 -treated film giving a smaller V_{oc} but a much larger J_{sc} and an overall higher power conversion efficiency, specifically 1.685% for the TiCl_4 -treated film versus 0.71% for the 100-cycle ALD-coated film and 0.365% for the uncoated film. Our thinnest ALD coating, using 40 cycles, results in a film thickness of about 1.6 nm, which is comparable to the reported TiCl_4 thickness of 1 nm [28], given that both measures are approximate. It can be seen in Figure 5(a) that the 40-cycle ALD coating results in DSSC performance not significantly better than an untreated film, and far worse than the TiCl_4 coating of similar thickness. Therefore, the shift of the conduction band produced by the TiCl_4 treatment and corresponding improvement in charge injection from the dyes has a far greater effect than the reduction of recombination current, which is also provided by the ALD coating but without a similar effect on current.

Figure 6. Uptake of N719 by a ZnO nanorod–TiO₂ nanoparticle hybrid film coated with TiO₂ by 0-500 cycles of ALD or by TiCl₄ treatment

Figure 7. Current–voltage characteristics of DSSCs made from ZT hybrid films untreated or coated with TiO₂ by 100 cycles of ALD or by TiCl₄ treatment. Means of triplicate samples are shown, with dotted lines indicating 1 SD

Figure 8. Dark current measurements of TiCl_4 treated and ALD coated ZT films.

Conclusions

Nanocomposite films of ZnO nanorods coated with TiO_2 nanoparticles were coated with TiO_2 blocking layers by ALD or by TiCl_4 treatment. At the optimal thickness of 100 cycles (about 4 nm), the ALD coating significantly improves photovoltaic performance by slightly enhancing V_{oc} and significantly improving J_{sc} . However, thicker ALD layers block pores in the TiO_2 layer and greatly reduce surface area and dye loading, leading to low photocurrents. TiCl_4 -treated films have a reduced V_{oc} by about 0.1 V but make up for this with a greatly improved photocurrent, leading to significantly better DSSC performance than either untreated or ALD-coated TiO_2 , which is

attributed to a downward shift of the TiO₂ conduction band that reduces photovoltage but improves charge injection from the adsorbed dyes.

Acknowledgements

This material is based on work supported by the National Science Foundation under Grant No. CBET-1332022. XRD and SEM were carried out at the Center for Clean Energy Engineering at the University of Connecticut. The authors thank Prof. S.L. Suib for kindly allowing us to use the atomic layer deposition facility.

References

- [1] P.J. Cameron, L.M. Peter, S. Hore, How Important is the Back Reaction of Electrons via the Substrate in Dye-Sensitized Nanocrystalline Solar Cells?, *The Journal of Physical Chemistry B*, 109 (2004) 930-936.
- [2] T.W. Hamann, O.K. Farha, J.T. Hupp, Outer-sphere redox couples as shuttles in dye-sensitized solar cells. Performance enhancement based on photoelectrode modification via atomic layer deposition, *J. Phys. Chem. C*, 112 (2008) 19756-19764.
- [3] S.M. Feldt, E.A. Gibson, E. Gabrielsson, L. Sun, G. Boschloo, A. Hagfeldt, Design of Organic Dyes and Cobalt Polypyridine Redox Mediators for High-Efficiency Dye-Sensitized Solar Cells, *J. Am. Chem. Soc.*, 132 (2010) 16714-16724.
- [4] I.R. Perera, A. Gupta, W. Xiang, T. Daeneke, U. Bach, R.A. Evans, C.A. Ohlin, L. Spiccia, Introducing manganese complexes as redox mediators for dye-sensitized solar cells, *Physical Chemistry Chemical Physics*, 16 (2014) 12021-12028.
- [5] A. Yella, H.-W. Lee, H.N. Tsao, C. Yi, A.K. Chandiran, M.K. Nazeeruddin, E.W.-G. Diau, C.-Y. Yeh, S.M. Zakeeruddin, M. Grätzel, Porphyrin-Sensitized Solar Cells with Cobalt (II/III)-Based Redox Electrolyte Exceed 12 Percent Efficiency, *Science*, 334 (2011) 629-634.
- [6] S. Ito, P. Liska, P. Comte, R. Charvet, P. Pechy, U. Bach, L. Schmidt-Mende, S.M. Zakeeruddin, A. Kay, M.K. Nazeeruddin, M. Gratzel, Control of dark current in photoelectrochemical (TiO₂/I/I₃⁻) and dye-sensitized solar cells, *Chemical Communications*, (2005) 4351-4353.
- [7] E. Guillén, E. Azaceta, A. Vega-Poot, J. Idígoras, J. Echeberría, J.A. Anta, R. Tena-Zaera, ZnO/ZnO Core-Shell Nanowire Array Electrodes: Blocking of Recombination and Impressive Enhancement of Photovoltage in Dye-Sensitized Solar Cells, *J. Phys. Chem. C*, 117 (2013) 13365-13373.
- [8] S.-J. Roh, R.S. Mane, S.-K. Min, W.-J. Lee, C.D. Lokhande, S.-H. Han, Achievement of 4.51% conversion efficiency using ZnO recombination barrier layer in TiO₂ based dye-sensitized solar cells, *Applied Physics Letters*, 89 (2006) 253512-253515.

- [9] E. Palomares, J.N. Clifford, S.A. Haque, T. Lutz, J.R. Durrant, Control of Charge Recombination Dynamics in Dye Sensitized Solar Cells by the Use of Conformally Deposited Metal Oxide Blocking Layers, *Journal of the American Chemical Society*, 125 (2002) 475-482.
- [10] T.C. Li, M.r.S. Góes, F. Fabregat-Santiago, J. Bisquert, P.R. Bueno, C. Prasittichai, J.T. Hupp, T.J. Marks, Surface Passivation of Nanoporous TiO₂ via Atomic Layer Deposition of ZrO₂ for Solid-State Dye-Sensitized Solar Cell Applications, *The Journal of Physical Chemistry C*, 113 (2009) 18385-18390.
- [11] K.E. Roelofs, T.P. Brennan, J.C. Dominguez, C.D. Bailie, G.Y. Margulis, E.T. Hoke, M.D. McGehee, S.F. Bent, Effect of Al₂O₃ Recombination Barrier Layers Deposited by Atomic Layer Deposition in Solid-State CdS Quantum Dot-Sensitized Solar Cells, *The Journal of Physical Chemistry C*, 117 (2013) 5584-5592.
- [12] A. Kay, M. Grätzel, Dye-Sensitized Core-Shell Nanocrystals: Improved Efficiency of Mesoporous Tin Oxide Electrodes Coated with a Thin Layer of an Insulating Oxide, *Chemistry of Materials*, 14 (2002) 2930-2935.
- [13] P. Docampo, P. Tiwana, N. Sakai, H. Miura, L. Herz, T. Murakami, H.J. Snaith, Unraveling the Function of an MgO Interlayer in Both Electrolyte and Solid-State SnO₂ Based Dye-Sensitized Solar Cells, *The Journal of Physical Chemistry C*, 116 (2012) 22840-22846.
- [14] P. Ramasamy, M.-S. Kang, H.-J. Cha, J. Kim, Highly efficient dye-sensitized solar cells based on HfO₂ modified TiO₂ electrodes, *Materials Research Bulletin*, 48 (2013) 79-83.
- [15] M.-H. Kim, Y.-U. Kwon, Semiconductor CdO as a Blocking Layer Material on DSSC Electrode: Mechanism and Application, *The Journal of Physical Chemistry C*, 113 (2009) 17176-17182.
- [16] D. Jiang, Y. Hao, R. Shen, S. Ghazarian, A. Ramos, F. Zhou, Effective Blockage of the Interfacial Recombination Process at TiO₂ Nanowire Array Electrodes in Dye-Sensitized Solar Cells, *ACS Applied Materials & Interfaces*, 5 (2013) 11906-11912.
- [17] B. Peng, G. Jungmann, C. Jäger, D. Haarer, H.-W. Schmidt, M. Thelakkat, Systematic investigation of the role of compact TiO₂ layer in solid state dye-sensitized TiO₂ solar cells, *Coordination Chemistry Reviews*, 248 (2004) 1479-1489.
- [18] S.M. Waita, B.O. Aduda, J.M. Mwabora, G.A. Niklasson, C.G. Granqvist, G. Boschloo, Electrochemical characterization of TiO₂ blocking layers prepared by reactive DC magnetron sputtering, *Journal of Electroanalytical Chemistry*, 637 (2009) 79-83.
- [19] J.G. Lee, J.H. Cheon, H.S. Yang, D.K. Lee, J.H. Kim, Enhancement of Photovoltaic Performance in Dye-Sensitized Solar Cells with the Spin-Coated TiO₂ Blocking Layer, *Journal of Nanoscience and Nanotechnology*, 12 (2012) 6026-6030.
- [20] H. Yu, S. Zhang, H. Zhao, G. Will, P. Liu, An efficient and low-cost TiO₂ compact layer for performance improvement of dye-sensitized solar cells, *Electrochimica Acta*, 54 (2009) 1319-1324.
- [21] M. Thelakkat, C. Schmitz, H.W. Schmidt, Fully Vapor-Deposited Thin-Layer Titanium Dioxide Solar Cells, *Advanced Materials*, 14 (2002) 577-581.
- [22] J. Guo, C. She, T. Lian, Effect of Insulating Oxide Overlayers on Electron Injection Dynamics in Dye-Sensitized Nanocrystalline Thin Films†, *The Journal of Physical Chemistry C*, 111 (2007) 8979-8987.
- [23] A.K. Chandiran, A. Yella, M. Stefik, L.-P. Heiniger, P. Comte, M.K. Nazeeruddin, M. Grätzel, Low-Temperature Crystalline Titanium Dioxide by Atomic Layer Deposition for Dye-Sensitized Solar Cells, *ACS Appl. Mater. Interf.*, 5 (2013) 3487-3493.

- [24] T.P. Brennan, J.R. Bakke, I.K. Ding, B.E. Hardin, W.H. Nguyen, R. Mondal, C.D. Bailie, G.Y. Margulis, E.T. Hoke, A. Sellinger, M.D. McGehee, S.F. Bent, The importance of dye chemistry and TiCl_4 surface treatment in the behavior of Al_2O_3 recombination barrier layers deposited by atomic layer deposition in solid-state dye-sensitized solar cells, *Physical Chemistry Chemical Physics*, 14 (2012) 12130-12140.
- [25] V. Manthina, J.P. Correa Baena, G. Liu, A.G. Agrios, ZnO-TiO_2 Nanocomposite Films for High Light Harvesting Efficiency and Fast Electron Transport in Dye-Sensitized Solar Cells, *The Journal of Physical Chemistry C*, 116 (2012) 23864-23870.
- [26] N. Sakai, T. Miyasaka, T.N. Murakami, Efficiency Enhancement of ZnO -Based Dye-Sensitized Solar Cells by Low-Temperature TiCl_4 Treatment and Dye Optimization, *J. Phys. Chem. C*, 117 (2013) 10949-10956.
- [27] J.P. Correa Baena, A.G. Agrios, Antimony-Doped Tin Oxide Aerogels as Porous Electron Collectors for Dye-Sensitized Solar Cells, *J. Phys. Chem. C*, 118 (2014) 17028-17035.
- [28] P.M. Sommeling, B.C. O'Regan, R.R. Haswell, H.J.P. Smit, N.J. Bakker, J.J.T. Smits, J.M. Kroon, J.A.M. van Roosmalen, Influence of a TiCl_4 post-treatment on nanocrystalline TiO_2 films in dye-sensitized solar cells, *J. Phys. Chem. B*, 110 (2006) 19191-19197.
- [29] M. Law, L.E. Greene, A. Radenovic, T. Kuykendall, J. Liphardt, P. Yang, $\text{ZnO-Al}_2\text{O}_3$ and ZnO-TiO_2 core-shell nanowire dye-sensitized solar cells, *J. Phys. Chem. B*, 110 (2006) 22652-22663.
- [30] J. Kim, H. Choi, C. Nahm, C. Kim, S. Nam, S. Kang, D.-R. Jung, J.I. Kim, J. Kang, B. Park, The role of a TiCl_4 treatment on the performance of CdS quantum-dot-sensitized solar cells, *Journal of Power Sources*, 220 (2012) 108-113.
- [31] S. Wendt, P.T. Sprunger, E. Lira, G.K.H. Madsen, Z. Li, J.Ø. Hansen, J. Matthiesen, A. Blekinge-Rasmussen, E. Lægsgaard, B. Hammer, F. Besenbacher, The Role of Interstitial Sites in the $\text{Ti}3d$ Defect State in the Band Gap of Titania, *Science*, 320 (2008) 1755-1759.
- [32] S.M. Prokes, J.L. Gole, X. Chen, C. Burda, W.E. Carlos, Defect-Related Optical Behavior in Surface Modified TiO_2 Nanostructures, *Advanced Functional Materials*, 15 (2005) 161-167.
- [33] F.J. Knorr, D. Zhang, J.L. McHale, Influence of TiCl_4 Treatment on Surface Defect Photoluminescence in Pure and Mixed-Phase Nanocrystalline TiO_2 , *Langmuir*, 23 (2007) 8686-8690.
- [34] H.O. Seo, S.-Y. Park, W.H. Shim, K.-D. Kim, K.H. Lee, M.Y. Jo, J.H. Kim, E. Lee, D.-W. Kim, Y.D. Kim, D.C. Lim, Ultrathin TiO_2 Films on ZnO Electron-Collecting Layers of Inverted Organic Solar Cell, *The Journal of Physical Chemistry C*, 115 (2011) 21517-21520.