Application of wide-energy-gap material 3,4-di(9H-carbazol-9-yl)benzonitrile in organic light-emitting diodes

Yuya Tanaka,^a Takehiro Takahashi,^b Junichi Nishide,^c Yasuhide Hiraga,^c Hajime

Nakanotani,^d and Chihaya Adachi^{d,e,*}

^a *Research and Development Center, Japan Display Inc., Minato, Tokyo 105-0003, Japan*

^b *Research and Development Department, Hodogaya Chemical Co., Ltd., Tsukuba,*

Ibaraki 305-0841, Japan

^c *Hirata Corporation, Kita, Kumamoto 861-0198, Japan*

^d *Center for Organic Photonics and Electronics Research (OPERA), Kyushu University,*

Nishi, Fukuoka 819-0395, Japan

^e *International Institute for Carbon-Neutral Energy Research (WPI-I²CNER),*

Kyushu University, Nishi, Fukuoka 819-0395, Japan

Abstract

A material with a wide energy gap, 3,4-di(9H-carbazol-9-yl)benzonitrile (2CzBN), was synthesized and applied in organic light-emitting diodes (OLEDs). Pure blue electroluminescence with a peak wavelength of 436 nm and Commission Internationale de l'Éclairage (CIE) coordinate of (0.160, 0.084) were obtained for an OLED containing 2CzBN as an emitter, although its external emission efficiency was limited to around 1% because of the lack of thermally activated delayed fluorescence (TADF) activity. In contrast, a highly efficient TADF-based OLED was obtained when 2CzBN was used as a host instead of an emitter by taking advantage of the high triplet energy (2.92 eV) and unexpected electron transport capability of 2CzBN.

Keywords

Organic light-emitting diode, Thermally activated delayed fluorescence, Pure blue emission, Wide-energy-gap material, Charge carrier transport.

1. Corresponding author at: Center for Organic Photonics and Electronics Research (OPERA), Kyushu University, Nishi, Fukuoka 819-0395, Japan

Tel: +81-92-802-6920; Fax: +81-92-802-6921; E-mail: adachi@cstf.kyushu-u.ac.jp (C. Adachi)

1. Introduction

Organic light-emitting diodes (OLEDs) have been studied extensively with the aim of developing practical display and lighting applications since Tang and VanSlyke reported the first substantial multi-layered electroluminescent (EL) device in 1987 [1]. However, the maximum internal EL quantum efficiency (η_{IQE}) of first-generation OLEDs was limited to 25% because they contained fluorescent emitters that can harvest only singlet excitons [2, 3]. Second-generation OLEDs including room-temperature phosphorescent emitters containing heavy metals such as Pt, Os and Ir have been widely developed and nearly 100% η_{IQE} has been achieved by taking advantage of the large spin-orbit coupling of such metals [4, 5]. As an alternative to these conventional emission mechanisms, our group has extensively developed highly efficient OLEDs based on thermally activated delayed fluorescence (TADF) [6, 7]. In fact, carefully designed TADF emitters can realize η_{IQE} of nearly 100% by utilizing the efficient upconversion process from the lowest triplet state (T_1) to lowest singlet state (S_1). This noteworthy evolution has yielded the next generation of organic luminescent materials.

In the development of OLEDs, highly efficient blue emission has been a goal for both display and lighting applications. One feasible candidate to achieve such OLEDs is TADF emitters, which can be obtained through the freedom in molecular structures [8-12]. To sufficiently utilize the characteristics of TADF emitters in OLEDs, it is crucial to confine triplet excitons on the emitters; to do so, the T_1 energy of the peripheral materials adjacent to the emitters, such as host, electron- and hole-transport layers, must be higher than that of the emitters. Otherwise, the triplet excitons are readily quenched *via* energy transfer to the surrounding materials, resulting in low η_{IQE} [8, 12]. Thus, the preparation of materials with a wide gap between their highest occupied molecular orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) is of great interest in OLED research. Among various TADF materials, 1,2-bis(carbazol-9-yl)-4,5-dicyanobenzene (2CzPN) is a promising material, demonstrating a relatively wide HOMO–LUMO

gap (2.8 eV) and high T_1 energy (2.51 eV) [7, 13]. However, the emission color of 2CzPN is sky blue and its T_1 energy is not satisfactory compared with those of recently reported blue TADF emitters [8, 10].

In this work, we successively design 3,4-di(9H-carbazol-9-yl)benzonitrile (2CzBN), which has a wider HOMO–LUMO gap (3.26 eV) and higher T_1 energy (2.92 eV) compared with those of 2CzPN. These changes can be ascribed to the presence of a single cyano group. While pure blue emission with a peak EL wavelength (λ_{EL}) of 436 nm and Commission Internationale de l’Éclairage (CIE) coordinate of (0.160, 0.084) is achieved in an OLED with 2CzBN as an emitter, η_{IQE} is limited to around 1% because of the lack of TADF activity. We find that highly efficient OLEDs can be obtained using 2CzBN as a host layer by taking advantage of its high triplet energy and suitable carrier transport capability.

2. Experimental details

2.1 Synthesis and characterization

All reagents and solvents were purchased from Tokyo Chemical Industry and Wako Pure Chemical Industries, and used as received unless otherwise noted. Reaction was performed under an N_2 atmosphere in dry solvents. We synthesized 2CzBN according to the procedure shown in Scheme 1. Here, **nuclear magnetic resonance (NMR)** spectra were measured on an Avance III 500 spectrometer (Bruker), and are reported in ppm using tetramethylsilane as an internal standard (TMS = 0 ppm). **Fast atom bombardment (FAB)** mass spectrum was measured on a JEOL JMS700 MStation. The HOMO energy levels of 2CzBN was determined using an AC-3 ultraviolet photoemission spectrometer (Riken-keiki).

Scheme 1. Synthesis of 2CzBN

To a suspension of NaH (1.98 g, 60wt% dispersion in mineral oil, 49.6 mmol, washed with hexane twice) in *N*-methylpyrrolidone (NMP) was added carbazole (9.0 g, 52.9 mmol) at room temperature. The mixture was stirred for 1 h at room temperature. After that, 3,4-difluorobenzonitrile (3.0 g, 21.6 mmol) was added to the solution, and then resulted mixture was heated at 120 °C. After refluxing for 18 h, the resultant suspension was cooled to room temperature and the reaction was quenched by adding water and toluene, then filtrated through celite pad. The product was extracted by toluene three times, and the combined organic layers were washed with brine, and dried over anhydrous MgSO₄. After filtration and evaporation, the crude product was purified by column chromatography (NH silica, eluent: hexane/toluene = 2:1, v/v), washed with MeOH, and dried under vacuum to give 2CzBN as white powder (yield = 3.6g, 38%). Materials are characterized as follows; ¹H NMR (500 MHz, CDCl₃): δ 8.16 (d, *J* = 1.8 Hz, 1H), 7.99 (d, *J* = 8.3 Hz, 1H), 7.95 (dd, *J* = 8.3, 1.8 Hz, 1H), 7.82-7.75 (m, 4H), 7.18-6.97 (m, 12H); HRMS (FAB) *m/z* 433.1579, (433.1579 calcd for C₃₁H₁₉N₃, [M]⁺). The HOMO energy was estimated to be 6.20 eV by the photoelectron spectrometer.

2.2 Device preparation

First, to investigate the ability of 2CzBN as a blue emitter, an OLED with a structure of indium tin oxide (ITO)/4,4-bis[N-(1-naphthyl)-N-phenylamino]-biphenyl (α -NPD) (35 nm)/1,3-bis(9-carbazolyl)benzene (mCP) (10 nm) /10wt% 2CzBN (emitter):2,8-bis(diphenylphosphoryl)dibenzo[b,d]thiophene (PPT) (host) (20 nm)/PPT (40 nm)/LiF (0.8 nm)/Al (100

nm) (**device A**) was fabricated (Fig. 1(a)). mCP and PPT were used as hole transport and electron transport layers, respectively, and an emission layer composed of co-deposited 2CzBN:PPT was sandwiched by them because their feasible carrier transport property and high T_1 energy [13, 14]. Second, to confirm the performance of 2CzBN as a host, we fabricated the structures ITO/dipyrazino[2,3-f:20,30-h]quinoxaline-2,3,6,7,10,11-hexacarbonitrile (HAT-CN) (10 nm)/9,9'9''-triphenyl-9H,9'H,9''H-3,3':6',3''-tercarbazole (Tris-PCz) (25 nm)/mCP (10 nm)/10wt% 9-(3-(9H-carbazol-9-yl)-9-(4-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl)-9H-carbazol-6-yl)-9H-carbazole (3CzTRZ) (emitter):2CzBN (host) (30 nm)/2CzBN (10 nm)/2,7-bis(2,20-bipyridine-5-yl)triphenylene (BPy-TP2) (40 nm)/LiF (0.8 nm)/Al (100 nm) (**device B**), ITO/HAT-CN (10 nm)/Tris-PCz (35 nm)/10wt% (4s,6s)-2,4,5,6-tetra(9H-carbazol-9-yl)isophthalonitrile (4CzIPN) (emitter):2CzBN (host) (30 nm)/2,4,6-tris(biphenyl-3-yl)-1,3,5-triazine (T2T) (10 nm)/BPy-TP2 (40 nm)/ LiF (0.8 nm)/Al (100 nm) (**device C**), and ITO/HAT-CN (10 nm)/Tris-PCz (35 nm)/10wt% 1,4-dicyano-2,3,5,6-tetrakis(3,6-diphenylcarbazol-9-yl)benzene (4CzTPN-Ph) (emitter):2CzBN (host) (30 nm)/T2T (10 nm)/BPy-TP2 (40 nm)/ LiF (0.8 nm)/Al (100 nm) (**device D**) as shown in Figs. 1(b)-(d). We used 3CzTRZ, 4CzIPN, and 4CzTPN-Ph as dopants because of the typical blue, green, and red emitters showing TADF, respectively, leading to the realization of white OLEDs [7, 15]. Because of higher T_1 of 3CzTRZ (2.85 eV) than those of 4CzIPN (2.4 eV) and 4CzTPN-Ph (2.21 eV), the emission layer of **device B** was sandwiched by mCP and 2CzBN to suppress the energy transfer from the emitter [10, 16, 17]. Electron-only devices (EODs) with the structure ITO/T2T (30 nm)/host layer/T2T (10 nm)/BPy-TP2 (80 nm)/LiF (0.8)/Al (100 nm) were also prepared to evaluate the electron transport properties of various materials. Here, 2CzBN (30 nm) (**device E**), 2CzPN (30 nm) (**device F**), mCP (30 nm) (**device G**), 2CzBN (25 nm)/2CzPN (5 nm) (**device H**), and 2CzPN (25 nm)/2CzBN (5 nm) (**device I**) were used as host layers in the EODs as illustrated in Fig. 1(e). Energy levels of each material are shown in Fig. 1(f), that have been evaluated in previous reports except for 2CzBN [13,15,16]. It is expected that a hole injection from an ITO to a T2T layer is suppressed due to the large injection barrier, resulting in an

electron-only transport characteristics. Evaluations of **current density (J)** and **luminance (L)** curves as a **function of applied voltage (V) (JVL)** and **external quantum efficiency (η_{EQE})** characteristics of the OLEDs and EODs was performed with a Hamamatsu Photonics C9920-12 measurement system.

Fig. 1. (a)-(e) Device structures of OLEDs. **(f)** Energy levels of each material.

3. Results and discussion

3.1 Optical properties of 2CzBN films

Figure 2(a) shows the absorption and photoluminescence (PL) spectra of neat 2CzBN (solid line) and 10wt% 2CzBN:PPT co-deposited (dashed line) films with a thickness of 100 nm. PL quantum efficiencies of 39% and 37% were obtained for neat and co-deposited films, respectively. The PL emission peaks (λ_{PL}) of the neat (420 nm) and co-deposited (414 nm) films are much shorter than that of a 2CzPN film (473 nm) [7], indicating that 2CzBN has a wider HOMO–LUMO gap than 2CzPN. This feature originates from the presence of a single strongly electron-accepting cyano group in 2CzBN compared with two in 2CzPN. Normalized fluorescence and phosphorescence spectra of a 2CzBN neat film measured at 300 and 50 K are depicted in Fig. 2(b), respectively. From these spectra, T_1 and the gap between S_1 and T_1 (ΔE_{ST}) are estimated to be 2.92 eV from the onset of the PL emission and 0.34 eV from the difference of the onset wavelengths of the fluorescence and phosphorescence spectra, respectively. These results imply that 2CzBN can be used as not only a pure blue emitter in OLEDs but also a host for TADF emitters because it has a high T_1 level, which is essential to confine triplet excitons on emitters. As illustrated in Fig. 2(c), the prompt component is dominant in the transient PL spectra of both neat 2CzBN and 2CzBN:PPT co-deposited films, with lifetimes of 11 and 10 ns, respectively. Conventional TADF molecules typically show a prompt component (several to several tens of nanoseconds) with a transient decay time (several to several hundreds of microseconds) [7, 13]. This is because ΔE_{ST} of 2CzBN is larger than those of conventional TADF molecules, suggesting that it lacks TADF activity.

Fig. 2. (a) Normalized absorption and PL spectra of neat 2CzBN (solid line) and 2CzBN:PPT co-deposited (dashed line) films. (b) Normalized fluorescence and phosphorescence spectra measured at 300 and 50 K, respectively. (c) Transient PL spectra of 2CzBN and 2CzBN:PPT films.

3.2 Properties of an OLED with 2CzBN as an emitter

To confirm the OLED performance of 2CzBN as an emitter, the JVL and $\eta_{\text{EQE}}-J$ characteristics of **device A** were measured, as presented in Figs. 3(a) and 3(b), respectively; the inset shows the normalized EL spectrum. At a current density of 10 mA/cm², λ_{EL} and CIE coordinates were 436 nm and (0.160, 0.084), respectively. The CIE coordinate is close to the National Television System Committee specification blue of (0.140, 0.080) [12]. The maximum η_{EQE} was confirmed to be less than 1%, which is consistent with the lack of TADF activity of 2CzBN observed in Fig. 2(c).

Fig. 3. (a) JVL and (b) $\eta_{\text{ext}}-J$ curves of an OLED with 2CzBN as an emitter (**device A**). The inset shows the normalized EL spectrum.

3.3 Properties of OLEDs with 2CzBN as a host

We then examined the performance of OLEDs with 2CzBN as a host layer. JVL and $\eta_{\text{ext}} - J$ characteristics of **devices B–D** are presented in Figs. 4(a) and 4(b), respectively. The inset in Fig. 4(b) displays the normalized EL spectrum of each device. Maximum η_{EQE} of 7.9%, 17.4%, and 9.8% were obtained for **devices B, C, and D**, respectively. These values exceed the theoretical limitation of the singlet exciton production ratio of 25% for fluorescence-based OLEDs, i.e., η_{EQE} of 5%–7.5% assuming a light outcoupling efficiency of 20%–30%. These high η_{EQE} cannot be achieved unless 2CzBN has high T_1 energy and the triplet excitons are confined on the emitter, otherwise the triplet excitons on the emitter are readily quenched *via* energy transfer to the surrounding materials, resulting in low η_{IQE} [7, 8, 10, 12, 15]. Thus, these results clearly indicate that 2CzBN is a promising host material for TADF-based OLEDs.

Fig. 4. (a) J/V and (b) $\eta_{\text{ext}}-J$ curves of OLEDs with 2CzBN as the host and dopants of 3CzTRZ (circles, **device B), 4CzIPN (squares, **device C**), and 4CzTPN-Ph (triangles, **device D**). The inset in Fig. 3(b) displays the normalized EL spectrum of each device.**

3.4 Electron transport properties of 2CzBN

To investigate the charge transport properties of 2CzBN, we prepared three kinds of EODs containing 2CzBN (**device E**), 2CzPN (**device F**), and mCP (**device G**) as shown in Fig. 1(e). Figure 5 shows the J/V curves of them, clearly indicating a large difference in the electron transport properties of these three devices. While the EOD with mCP showed a small electron current and that with 2CzPN exhibited a slight increase of electron current over 8V, the EOD containing 2CzBN showed a much larger electron current. As shown in Fig. 1(f), it is expected that an electron injection from cathode to mCP is inhibited by the large energy barrier at the contacts, resulting in low electron current in **device G**. In the case of **devices E** and **F**, there is no large difference of the energy barrier between 2CzBN/cathode and 2CzPN/cathode interfaces, indicating that the dominant factor for current difference between **devices E** than **F** is not the difference of the energy barrier but the electron transport property. Thus, we conclude that 2CzBN has superior electron transport characteristics to those of mCP and 2CzPN. Furthermore, the electron current of the 2CzBN-based EOD is noticeably lowered by the insertion of a thin 2CzPN layer (5 nm) between the 2CzBN and T2T layers on the cathode side (**device H**), as shown in the inset of Fig. 5. Although the electron injection from T2T to 2CzBN layers and successive transport were observed in **device E**, the insertion of a 2CzPN layer between the 2CzBN and T2T layers on the anode side (**device I**) drastically suppressed the electron current. These results also clearly suggest that the electron transport capability of 2CzBN is much higher than that of 2CzPN. Based on these EOD characteristics, we speculate that the carrier recombination site would expand into the bulk of the emitter layer in the case of a 2CzBN

host. We believe that this property should contribute to achieving TADF-based OLEDs with long-term reliability [16].

Fig. 5. *JV* curves of EODs with host materials of 2CzBN, 2CzPN, and mCP in **device E** (circles), **device F** (triangles), and **device G** (squares), respectively. The inset shows *JV* curves of **device H** (diamonds) and **device I** (crosses).

4. Conclusion

We synthesized 2CzBN and used it as an emitter and host in OLEDs. Pure blue emission with a peak emission wavelength of 436 nm and CIE coordinate of (0.160, 0.084) was obtained at a current density of 10 mA/cm² in an OLED with 2CzBN as the emitter. High-efficiency OLEDs displaying TADF were developed when 2CzBN was used as a host material because of its high T_1 (2.92 eV) and suitable carrier transport capability. Further investigation is needed to clarify the origin of the favorable electron transport properties of 2CzBN.

Acknowledgments

YT thanks Mr. Takahiko Yamanaka for his kind cooperation in the experiments. This research was supported by the Center of Innovation (COI) Program from the Japan Science and Technology Agency (JST).

References

- [1] C.W. Tang, S.A. VanSlyke, Organic electroluminescent diodes, *Appl. Phys. Lett.* 51 (1987) 913–915.
- [2] M.A. Baldo, D.F. O'Brien, M.E. Thompson, S.R. Forrest, Excitonic singlet-triplet ratio in a semiconducting organic thin film, *Phys. Rev. B* 60 (1999) 14422.
- [3] W. Brütting, J. Frischeisen, T.D. Schmidt, B.J. Scholz, C. Mayr, Device efficiency of organic light-emitting diodes: Progress by improved light outcoupling, *Phys. Status Solidi A* 210 (2013) 44–65.
- [4] M.A. Baldo, D.F. O'Brien, Y. You, A. Shoustikov, S. Sibley, M.E. Thompson, S.R. Forrest, Highly efficient phosphorescent emission from organic electroluminescent devices, *Nature* 395 (1998) 151–154.
- [5] C. Adachi, M.A. Baldo, M.E. Thompson, S.R. Forrest, Nearly 100% internal phosphorescence efficiency in an organic light-emitting device, *J. Appl. Phys.* 90 (2001) 5048–5051.
- [6] A. Endo, M. Ogasawara, A. Takahashi, D. Yokoyama, Y. Kato, C. Adachi, Thermally activated delayed fluorescence from Sn^{4+} -Porphyrin complexes and their application to organic light-emitting diodes — A novel mechanism for electroluminescence, *Adv. Mater.* 21 (2009) 4802–4806.
- [7] H. Uoyama, K. Goushi, K. Shizu, H. Nomura, C. Adachi, Highly efficient organic light-emitting diodes from delayed fluorescence, *Nature* 492 (2012) 234–238.
- [8] Q. Zhang, B. Li, S. Huang, H. Nomura, H. Tanaka, C. Adachi, Efficient blue organic light-emitting diodes employing thermally activated delayed fluorescence, *Nat. Photon.* 8 (2014) 326–332.

- [9] S. Wu, M. Aonuma, Q. Zhang, S. Huang, T. Nakagawa, K. Kuwabara, C. Adachi, High-efficiency deep-blue organic light-emitting diodes based on a thermally activated delayed fluorescence emitter, *J. Mater. Chem. C* 2 (2014) 421–424.
- [10] S. Hirata, Y. Sakai, K. Masui, H. Tanaka, S. Y. Lee, H. Nomura, N. Nakamura, M. Yasumatsu, H. Nakanotani, Q. Zhang, K. Shizu, H. Miyazaki, C. Adachi, Highly efficient blue electroluminescence based on thermally activated delayed fluorescence, *Nat. Mater.* 14 (2015) 330–336.
- [11] T. Higuchi, H. Nakanotani, C. Adachi, High-Efficiency White organic light-emitting diodes based on a blue thermally activated delayed fluorescent emitter combined with green and red fluorescent emitters, *Adv. Mater.* 27 (2015) 2019–2023.
- [12] M. Numata, T. Yasuda, C. Adachi, High efficiency pure blue thermally activated delayed fluorescence molecules having 10H-phenoxaborin and acridan units, *Chem. Comm.* 51 (2015) 9443–9446.
- [13] K. Masui, H. Nakanotani, C. Adachi, Analysis of exciton annihilation in high-efficiency sky-blue organic light-emitting diodes with thermally activated delayed fluorescence, *Org. Electron.* 14 (2013) 2721–2726.
- [14] S.O. Jeon, K.S. Yook, C.W. Joo, J.Y. Lee, High-efficiency deep-blue-phosphorescent organic light-emitting diodes using a phosphine oxide and a phosphine sulfide high-triplet-energy host material with bipolar charge-transport properties, *Adv. Mater.* 22 (2010) 1872–1876.
- [15] J. Nishide, H. Nakanotani, Y. Hiraga, C. Adachi, High-efficiency white organic light-emitting diodes using thermally activated delayed fluorescence, *Appl. Phys. Lett.* 104 (2014) 233304.
- [16] H. Nakanotani, K. Masui, J. Nishide, T. Shibata, C. Adachi, Promising operational stability of high-efficiency organic light-emitting diodes based on thermally activated delayed fluorescence, *Sci. Rep.* 3 (2013) 2127.

[17] T.C. Wu, D.N. Congreve, M.A. Baldo, Solid state photon upconversion utilizing thermally activated delayed fluorescence molecules as triplet sensitizer, *Appl. Phys. Lett.* 107 (2015) 031103.