1 **Biochar physico-chemical properties as affected by environmental**
2 **exposure**

3

4 ***Research article***

5 Authors:

6 Giovambattista Sorrenti^{a*}, Caroline A. Masiello^b, Brandon Dugan^c, Moreno Toselli^a

7

8 Author's affiliation and address:

9 ^aDepartment of Agricultural Sciences, University of Bologna, viale G. Fanin 44, 40127

10 Bologna, Italy, g.sorrenti@unibo.it, moreno.toselli@unibo.it

11 ^bDepartments of Earth Science, BioSciences, and Chemistry, Rice University, Houston,

12 Texas 77005, USA, masiello@rice.edu

13 ^cDepartment of Earth Science, Rice University, Houston, Texas 77005, USA,

14 dugan@rice.edu

15

16 *Corresponding author:

17 Giovambattista Sorrenti

18 Department of Agricultural Sciences, University of Bologna, viale G. Fanin 44, 40127

19 Bologna, Italy

20 e-mail: g.sorrenti@unibo.it

21 Telephone number: +39 051 2096426

22 Fax number: +39 051 2096401

Graphical abstract

Abstract

To best use biochar as a sustainable soil management and carbon (C) sequestration technique, we must understand the effect of environmental exposure on its physical and chemical properties because they likely vary with time. These properties play an important role in biochar's environmental behavior and delivery of ecosystem services. We measured biochar before amendment and four years after amendment to a commercial nectarine orchard at rates of 5, 15 and 30 t ha⁻¹. We combined two pycnometry techniques to measure skeletal (ρ_s) and envelope (ρ_e) density and to estimate the total pore volume of biochar particles. We also examined imbibition, which can provide information about soil hydraulic conductivity. Finally, we investigated the chemical properties, surface, inner layers atomic composition and C1s bonding state of biochar fragments through X-ray photoelectron spectroscopy (XPS). Ageing increased biochar skeletal density and reduced the water imbibition rate within fragments as a consequence of partial pore clogging. However, porosity and the volume of water stored in particles remained unchanged. Exposure reduced biochar pH, EC, and total C, but enhanced total N, nitrate-N, and ammonium-N. X-ray photoelectron spectroscopy analyses showed an increase of O, Si, N, Na, Al, Ca, Mn, and Fe surface (0-5 nm) atomic composition (at%) and a reduction of C and K in aged particles, confirming the interactions of biochar with soil inorganic and organic phases. Oxidation of aged biochar fragments occurred mainly in the particle surface, and progressively decreased down to 75 nm.

Biochar surface chemistry changes included the development of carbonyl and carboxylate functional groups, again mainly on the particle surface. However, changes were noticeable down to 75 nm, while no significant changes were measured in the deepest layer, up to 110 nm. Results show unequivocal shifts in biochar physical and chemical properties/characteristics over short (~years) timescales.

Keywords: Charcoal, Density, Porosity, Imbibition, XPS, Ageing

1. Introduction

Biochar is the solid residue of biomass pyrolysis intentionally added to soil to sequester carbon (C) (Woolf et al., 2010), to ameliorate soil properties (Spokas et al., 2012) and to improve crop performance (Verheijen et al., 2010). Many biochar-induced ecosystem services, including improving soil water properties and ions retention, are due to its high (~75%) porosity which indicates the fraction of the total fragment volume not filled by solid (Brewer et al., 2014). Interconnected biochar pores are arranged in complex structures (Nguyen et al., 2010) and range from less than 1 nm (Sun et al., 2012; Keiluweit et al., 2010;) to pores on the order of 0.01 mm in size, reflecting the cellular arrangement of the pyrolyzed feedstocks (Bird et al., 2008; Wildman et al., 1991) Pore surface area and reactivity control biochar sorptive capacities and modulate its interactions with minerals, water, microbes, fungal hyphae and plant roots (Downie et al., 2009; Thies and Rilling, 2009; Chen et al., 2008; Warnock et al., 2007; Hockaday et al., 2006; Pietikäinen et al., 2000). Recent findings suggest that pores >50 nanometers (nm) are responsible for most of the biochar porosity (Brewer et al., 2014). This result has been validated using mercury porosimetry by Baltrėnas et al. (2015) who estimated that up to 90% of either birch or pine-derived biochar pore volume consisted of pores larger than 500 nm in diameter while pores less than 500 nm took less than 1.5 % of the total pore volume. Similarly, Laine et al. (1992) report than activated

charcoal micropore surface area is larger than macropore surface area, but macropore volumes can be more than double than micropore volume. Macropores affect hydraulic conductivity (Masiello et al., 2015; Barnes et al., 2014; Brockhoff et al., 2010; Oguntunde et al., 2008) and other hydrologic processes (e.g. infiltration, erosiveness, wettability, water retention, nutrient leaching) (Baronti et al., 2014; Bruun et al., 2014; Novak et al., 2012; Major et al., 2009). These properties impact microbial habitats (Lehmann et al., 2011), offering shelters for mycorrhizal fungi (Warnock et al., 2007).

Biochar physico-chemical properties may change after environmental exposure, challenging our ability to predict its long-term ecosystem services. Changes result from shifts in temperature, water content, tillage, fertilization and interactions with the soil matrix (Joseph et al., 2010). Density and porosity of biochar can be altered through the trapping of minerals, roots, OM or microbes (Jaafar et al., 2014; Warnock et al., 2007) shifting biochar sorption capacity, soil hydraulic conductivity and water retention (Masiello et al., 2015; Baronti et al., 2014).

Several studies report changes of biochar properties as a consequence of ageing (LeCroy et al., 2013; Lin et al., 2012; Jones et al., 2012; Joseph et al., 2010; Zimmerman, 2010; Cheng et al., 2008). However, most of these findings come from environmental exposures < 6 months or weathering induced through chemical and/or physical treatments (Yao et al., 2010).

Similarly, some studies suggest that oxidation is a surface process; others report oxidation throughout particles (Cheng et al., 2006). It seems reasonable to assume that chemical changes start at the surface, but no information exists about the progression of the oxidation front.

We evaluated porosity shifts induced by 4 years of environmental exposure by comparing fresh (never applied to the field) and field-applied biochar from the same biochar batch. We combined two pycnometry techniques to determine skeletal (ρ_s) and envelope (ρ_e) densities which allow estimation of porosity of biochar particles (Brewer et al., 2014). We also evaluated hydrologic implications of biochar ageing by an imbibition assay. Finally, we measured chemical properties, surface, inner layers elemental composition and C1s bonding state of biochar through X-ray

photoelectron spectroscopy (XPS). We hypothesized that i) environmental exposure generates physical-chemical changes of biochar fragments, ii) chemical changes are not limited to the top exposed surface iii) the extent of the changes may be rate-dependent and iv) ageing alter biochar-water interactions.

2. Materials and Methods

2.1 Experimental site and biochar characteristics

A four-year experiment was carried out using a commercial nectarine (*Prunus persica* L., Batsch) orchard (Big Top/GF677) planted in 1997 with a density of 519 trees ha⁻¹ (3.5 x 5.5 m) located in the southeastern Italian Po Valley (Tebano, Ravenna, 44° 29' N, 11° 78'E, 58 m a.s.l.) on a sandy-loam Inceptisol soil with pH =8.08, organic matter (OM) = 10.6 g kg⁻¹, cation exchange capacity (CEC) = 13.0 meq 100 g⁻¹, and total N, available P, exchangeable K, Na, Ca, and Mg of 800, 8, 97, 37, 2347, and 109 mg kg⁻¹.

The area has a temperate sub-continental climate with cold winters and warm, humid summers (T_{average} = 13.6°C; T_{highest} =40.5°C, T_{lowest} =-4.1°C). Annual precipitation ranged between 650 and 910 mm. Alleys were maintained with native grass species while tree rows were herbicided with glufosinate ammonium (DL-phosphinothricin). Trees were managed by pruning, thinning, fertilization, irrigation, and control of pest and disease according to regional guidelines (ICM, 2009). From May to August trees were drip-irrigated and yearly fertilized with 0.25 kg N tree⁻¹ (130 kg N ha⁻¹) as urea at petal fall.

The biochar we used was produced in a commercial slow-pyrolysis unit (Romagna Carbone snc, Bagnacavallo (RA), Italy) using cylindrical, vertical charcoal kiln of 8.14 m³ (2.40 m diameter and 1.80 m height). We used non-contaminated chipped hardwood (peach and grapevine at the same rate (v v⁻¹) pruning wood) slowly pyrolyzed with continuous (150 min) heating from ambient temperature (heating rate of 10-15°C min⁻¹), reaching the highest T of ~550°C with a 30 min peak

temperature hold time (Tab. S1). Charred fragments were allowed to cool to ambient conditions in the absence of O₂.

2.1.2 Experimental design

In November 2009 we distributed biochar at the rates of 5, 15, and 30 t fresh weight (fw) ha⁻¹ according to a randomized experimental block design, with 5 replicates of 5 trees each, arranged in 4 consecutive tree rows, leaving 10 unamended meters between consecutive plots. Treatments were randomly distributed in each row with at least one replicate per biochar rate in each row. Biochar was distributed on a 35 m² area per experimental plot (2 m wide along the herbicided strip) and mixed into the first 20-cm soil depth (A horizon) by a disc harrow. Control samples of biochar (never field-applied, termed here “fresh”) were hermetically stored in plastic bags four years.

2.1.2 Biochar recovery

We randomly recovered (Nov-13) ~50 biochar fragments of different sizes from each replicate. To accomplish this we removed the first 3-5 cm depth of the soil layer and carefully collected fragments from the soil by forceps, avoiding manual contact or any physical damage to the particles. We sealed the particles in polyethylene bags and transported them to the laboratory in a portable refrigerator. A composed biochar sample of ~2.5 kg (never field-applied, termed here “fresh”) from the same biochar batch (from a unique and homogenized heap of ~2 t) was stored in hermetically closed plastic bags of ~ 250 g ea. and maintained four years at room temperature, in a dry and dark place. After four years, a random subset of these stored fresh biochar fragments (~ 100 pieces) were isolated by forceps, transferred in several test tubes, then analyzed as the soil-recovered biochar fragments.

Particles were dried at 50 °C for 72 h, sieved to 1 mm and the surface of individual fragments (keeping each piece by forceps under a magnifying lens) was cleaned with a soft brush and rinsed

twice with deionized water (DI-H₂O) to remove adhering soil. Fragments were not physically damaged during handling and drying.

2.2 Biochar physical changes as affected by the environmental exposure

2.2.1 Skeletal density (ρ_s)

Skeletal density (ρ_s) is the mass of a particle divided by its volume and was determined by helium (He) pycnometry. We measured the ρ_s of ~0.1 g dry biochar mass per replicate (samples composed of about 5-6 fragments, with each piece smaller than 1 cm³) using an AccuPyc 1340 (Micromeritics, Norcross, GA) fitted with a 1 cm³ chamber (Brewer et al., 2014).

2.2.2 Envelope density (ρ_e)

Envelope density (ρ_e) is the mass of a dry biochar sample divided by the volume of its non-wetting exterior measured if an “envelope” were placed around each individual particle (Brewer et al., 2014). We measured ρ_e of biochar samples that were ~0.215 g (dry mass) per replicate (samples composed of about 8-9 fragments, with each piece smaller than 1 cm³) using a Geopyc 1360 Envelope Density Analyzer (Micromeritics, Norcross, GA). Fragments were placed in a bed of DryFlo[®] granular medium (density of ~0.4 g cm⁻³). Consolidation was achieved by continuous rotation and vibration of the cylindrical chamber as the piston was gradually pushed into the chamber until the stated 22 N force was reached (Brewer et al., 2014).

2.2.3 Porosity

Porosity (ϕ) is a function of ρ_e and ρ_s :

$$\phi = \frac{v_e - v_s}{v_e} = 1 - \frac{m/\rho_s}{m/\rho_e} = 1 - \frac{\rho_e}{\rho_s}$$

v_e and v_s = envelope and skeletal volume and m = mass.

170

171 *2.3 Imbibition assay*

172 We compared aged biochar recovered from the 30 t ha⁻¹ plots with fresh biochar particles. Samples
173 were treated as described earlier and three pairs of fragments with similar weight (± 0.04 mg) and
174 shape were selected, rinsed (DI-H₂O), and oven-dried at 75 °C for 48 h. The last washing step was
175 repeated 3 times to reduce sample hydrophobicity. Fragments were individually transferred into 75
176 mL glass tubes filled with DI-H₂O and carefully placed on the water surface, allowing the
177 fragments to float. Tubes were unsealed, never disturbed, and maintained at room temperature,
178 allowing natural water infiltration. We recorded the sinking of each fragment until particles reached
179 the bottom of the tubes. The amount of absorbed water in sunken fragments was determined by
180 massing before and after drying at 105°C (96 h).

181

182 *2.4 Biochar chemistry changes following environmental exposure*

183 *2.4.1 pH and electrical conductivity (EC)*

184 Oven-dried (105°C) samples were added to DI-H₂O at a mass ratio of 1:20 and shaken 90 min at
185 120 rpm (Rajkovich et al., 2012). pH and EC were measured on the filtered supernatant under
186 continuous stirring by a pH-meter (BasiC 20, Crison, Barcelona, Spain) and a conductimeter
187 (CDM210 Conductivity Meter, Radiometer Analytical, Copenhagen, DK).

188

189 *2.4.2 Total C, N and H content*

190 We sampled 3 mg of ground biochar for total N and H and 0.1 mg for C determination by catalytic
191 combustion (ECS 4010, Costech Analytical Technologies Inc.; Valencia, CA).

192

193 *2.4.3 KCl extractable NO₃⁻-N and NH₄⁺-N*

194 We extracted intact oven-dried biochar fragments using a 2 M KCl solution at a ratio of 1:20 (w w⁻¹).
195 Samples were shaken for 90 min at 100 rpm by an orbital shaker and the filtered (Whatman 42)

surnatant was analyzed by a continuous flow autoanalyzer (AA-3, Bran+Luebbe, Norderstadt, Germany).

2.4.4 Biochar surface atomic composition

We analyzed three fragments per replicate by XPS for relative C, O, Si, N, Na, Al, Mg, P, K, Ca, Mn, and Fe atomic composition (at%) in the top 5 nm (Fig. 1) using a PHI Quantera XPS with a focused monochromatic Al K α X-ray source for excitation at 1486.6 eV and 49.2 W. We performed high-resolution, low-intensity scans to focus on the C bonding environments with 40 scans. XPS spectra were analyzed using a nonlinear, least-squares curve-fitting program with a Gaussian–Lorentzian mixed function to optimize the spectra using MultiPak data analysis software (MultiPak V7.0.1, Ulvac-Phi, Inc.).

Figure 1. The biochar profiles scanned by X-ray photoelectron spectroscopy (XPS). Magnification obtained by a Zeiss SteREO Discovery.V20 microscope

**Depths are not strictly to scale*

2.4.5 Biochar inner layer at%

We compared fresh and aged (from 30 t ha⁻¹ plots) biochar fragments (4 replicates) for relative C, O, Si, N, and Al at% at four depths (S1=0-5nm, L2=5-10nm, L3=15-20nm and L4=30-35nm; Fig. 1).

Three additional fragments of fresh and aged biochars were used to determine the relative C, O, Si, N, and Al at% at additional depths (S1=0-5nm, L5=35-40nm, L6=70-75nm and L7=105-110nm; Fig. 1).

We calibrated the XPS assessing the etching depth by using a standard 100 nm tick of SiO₂ as a reference. The relative etching rate for C-containing compounds was extrapolated by a computer simulation (based on the exact etching rate for SiO₂) as compared with a spreadsheet provided by the manufacturer.

We deconvoluted the C1s region bonding state into component functional groups. The -C-C/-C-H/-C=C bonds exhibit the same binding energy (284.74 eV) and thus were considered together, while -C-O, -C=O and -COOH were targeted at 285.95, 287.18 and 288.56 eV.

3. Statistical Analyses

Data were evaluated according to a randomized block design with 5 replicates. Data of XPS analyses at different fragment depths were evaluated as a factorial randomized block design with 2 factors: biochar age (2 levels) and layer (4 levels). When ANOVA showed statistical effects ($p \leq 0.05$), means were separated by Student-Newman-Keuls Test; when interaction between factors was significant, 2 times standard error of means was used as the minimum difference between two statistically different means (Saville and Rowarth, 2008). Data of the imbibition assay were submitted to repeated measures analysis of variance using PROC MIXED (Little et al., 1998) in SAS 9.0 (SAS Institute Inc. Cary, NC, USA), with the fragment weight as covariant and a compound symmetry covariance structure.

4. Results and Discussion

4.1 Biochar physical properties as affected by environmental exposure

4.1.1 Density and Porosity

Field exposure induced the most significant physical changes in biochar ρ_s and ρ_e , which increased by 160 and 15 mg cm^{-3} , respectively (Fig. 2).

Figure 2. Effect of environmental exposure (4 years in field conditions) on density (skeletal and envelope) and porosity of biochar fragments (avg. $\pm$ SE $n=5$) applied at different rates as compared with fresh biochar.

ns and * = effect of biochar ageing and rate not significant or significant at $p \leq 0.05$. Bars with the same letter are not statistically different ($p \leq 0.05$) according to the Student-Newman-Keuls (SNK) test.

This increase in ρ_s may be due to biochar particle breakage and mechanical stresses (e.g. freeze-thaw cycles) as recently evidenced by Spokas et al. (2014) who reported cracks and fractures (physical disintegration) on biochar surfaces induced by water and soil exposure. This breakage may increase pore connectivity by i) connecting previously isolated pores and ii) opening externally connected pores which may represent entry points for denser minerals that may fill or partially fill

270 previously empty spaces. Similarly, capillary forces may also drive the soil solution into biochar
271 pores since plant-derived biochars have a high concentration of macropores (>50 nm) (Downie et
272 al., 2009), which are much larger than a water molecule (0.28 nm). Flowing water can carry small
273 particles in suspension (including small biochar fragments) into biochar micropores; these particles
274 may accumulate and/or clog in the pore channels (Joseph et al., 2010). Charred and non-charred
275 compounds may remain physically blocked or chemically attracted within particles, altering pore
276 connectivity (Jaafar et al., 2014; Joseph et al., 2010).

277 Recent studies support the rationale that soil particles (e.g. colloidal, dissolved, soluble inorganic
278 salts and/or aluminosilicates) can fill exposed cavities of soil-exposed biochar fragments (Spokas et
279 al., 2013; 2014).

280 Our microscopic images (Fig. 3) support the idea that interactions with minerals and/or microbes
281 change the biochar's physical properties (Jaafar et al., 2014; Brodowski et al., 2006; Liang et al.,
282 2006; Warnock et al., 2007; Hockaday et al., 2006) In our images minerals partially fill biochar
283 fractures, starting from the particle's outer edges. Newly inaccessible volumes may be occupied by
284 a combination of trapped water and/or air, leading to porosities that vary with water exposure
285 history.

Figure 3. Magnification of biochar fragments recovered from a nectarine orchard after 4 years of environmental exposure. Minerals and soil particles are adhering and/or are physically trapped over the entire particle surface. Pores appear partially or totally blocked by soil particles, likely reducing accessibility. Color magnifications were obtained by an Olympus SXZ16 microscope coupled with an Olympus digital camera whereas the others were obtained by a Zeiss SteREO Discovery.V20 microscope.

4.1.2 Ageing reduced the rate of water imbibition

Biochar pores have been classified as surface-site pores (α -type) and bulk-site pores (β -types) (Clarkson et al., 1998). As biochar become water-filled, diffusional processes allow the transition of water between the α -type and β -type pores. However, physical (pore size) and/or chemical (solid–liquid interactions) factors may interfere with water movement within biochar particles (Clarkson et al., 1998; Conte et al., 2013). When biochar pores totally or partially clog, water flow into and out of particles becomes physically hampered, hence water infiltration rate likely changes. In our biochar imbibition assay, fresh biochar sank faster than aged particles. Fresh biochar samples started to sink after 156 h and completely settled between 162 and 168 h while aged samples started sinking between 168 and 180 h, settling slowly up to 268 h, then accelerated until reaching the bottom of the tubes near 276 h (Fig. 4). The ratio of water:biochar ($w w^{-1}$) of the sunken fragments was unaffected by ageing and values were $4.98 (\pm 0.30)$ and $5.16 (\pm 0.35)$ for fresh and aged fragments, respectively. These results suggest that pore openings are becoming partially clogged, but not filled with solid materials.

However, as mentioned above, chemical factors may also interfere in the biochar-water relationship. This, in turn, refers to the development of H bonds between the water-derived O and H atoms of the biochar aromatic systems (Clarkson et al., 1998). The last interaction was elucidated by Conte et al. (2013), who suggested that water molecules may be bound to the solid carbonaceous material through non-conventional H bonds. As ageing induces the development of O- and H-containing functional groups onto the biochar surface, as a consequence of surface oxidation (Zimmerman, 2010), the last biochar-water mechanism results promoted in aged biochar with implications on the water mobility.

It seems also reasonable to hypothesize a similar reverse sense (pore drainage), with aged biochar fragments retaining water longer. In this case, and assuming water-saturated particles, the partial blocking of biochar pores may allow biochar-amended soils to hold water longer between rainfall events.

318
319

320 Figure 4. Sinking dynamics of fresh vs. aged (4 years in field conditions at the rate of 30 t ha⁻¹) biochar fragments (n=3)

321 ns, * and *** = effect not significant or significant at $p \leq 0.05$ and $p \leq 0.001$, respectively.

4.2 Biochar chemistry changes as affected by the environmental exposure

4.2.1 pH, EC, total elemental C, N, H, extractable NO_3^- -N and NH_4^+ -N concentration

Ageing decreased biochar pH and increased EC (Tab. 1).

Table 1. pH, electrical conductivity (EC), total C, H, N concentration and KCl extractable NO_3^- -N and NH_4^+ -N of different rates of aged as compared with fresh biochar fragments

Biochar	pH	EC	C	H	N	NO_3^- -N	NH_4^+ -N
		μS	$\text{g } 100 \text{ g}^{-1}$	$\text{g } 100 \text{ g}^{-1}$	$\text{g } 100 \text{ g}^{-1}$	mg kg^{-1}	mg kg^{-1}
Fresh	9.97a	903.5a	77.6a	1.41	0.23c	5.51 b	132.3 b
Aged 5 t ha ⁻¹	7.81b	129.8b	66.7b	1.48	0.92a	82.5 a	248.8 a
Aged 15 t ha ⁻¹	8.09b	144.8b	66.3b	1.40	0.73b	69.2 a	230.9 a
Aged 30 t ha ⁻¹	8.08b	158.2b	66.1b	1.21	0.97a	83.4 a	342.7 a
Significance	***	***	*	ns	***	***	**

ns, *, ** and *** = effect not significant or significant at $p < 0.05$, $p < 0.01$ and $p < 0.001$, respectively. In the same column, means followed by the same letter are not statistically different ($p < 0.05$, SNK Test)

The weathering-induced carboxylic acids functional groups lead to a decrease of basic sites on the biochar surface (Quian et al., 2014; Yao et al., 2010; Cheng et al., 2009), explaining the significant reduction of pH (~2 units) in aged biochar. This suggests that biochar liming potential is be limited to few years after its application. Hence, biochar-induced benefits in nutrient availability in acid soils may be more pronounced in the first seasons following application. Similarly, the undesirable further pH increase in alkaline soils due to biochar application may be transient.

Total C concentration was reduced by 14.5 % (± 0.18) by ageing, irrespective of the application rate (Tab. 1). The last response is partly due to mineralization of the labile C-fraction associated with biochar (Norwood et al., 2013). This mineralization may occur through the loss of volatile organic compounds generated during pyrolysis and condensed during cooling (Rajkovich et al., 2012) which are more reactive than the aromatic fractions (Joseph et al., 2010). This leads to an initial evolution of biochar-derived CO_2 in soils after its application (few months), partly attributed to biochar surface oxidation (Bruun et al., 2008; Steiner et al., 2008).

Finally, a fraction of biochar-derived C was likely lost through leaching of dissolved organic C (DOC). Mukherjee and Zimmerman (2013), for instance, measured a significantly higher DOC in the soil leachate amended with two different biochars obtained at two pyrolysis temperatures. The additional rate of DOC in the leachate was unambiguously biochar-derived, as shown by the increase in the aromaticity of the DOC measured in the biochar-amended soil leachate (Barnes et al., 2014).

However, the 14% reduction of total C concentration in biochar fragments after 4 years soil incubation appear higher compared to mean averages reported in literature (Lehmann et al., 2009; Kuzyakov, et al., 2014). To this regard, it must be mentioned that at the time of soil application, biochar was freshly produced thereby its content of water-soluble C-containing compounds was abundant, likely promoted also by the relatively low max T° (550 °C) reached during pyrolysis. In addition, a dilution effect induced by the attachment of organo-mineral complexes on the aged biochar surfaces is also reasonable, consistent with the increase of both the N_{org} and N_{min} fractions measured on the aged fragments. This last mechanism was recently proposed by Kammann et al. (2015) to explain NO₃-N capture on/in the porous biochar structure, encompassing with the development of acid and basic functional groups (as we also observed in our study) as well as the development of unconventional H-bonding.

Total N concentration increased in aged biochars by 3.8 fold, irrespective of application rate. Such increase was more pronounced when biochar was applied at 5 t ha⁻¹ (4.0 fold) and 30 t ha⁻¹ (4.2 fold) (Tab. 1). The most significant contribution to the total N increase was due to the organic N forms, which were 56% of the total N, on average. Similarly, Joseph et al. (2010) reported an increase in the N content of two different biochars mainly associated with proteins, amino acids, NH₄⁺ and N–C compounds.

Likewise, extractable inorganic N increased in aged biochar, and NO₃⁻ and NH₄⁺ concentrations were significantly higher in aged than in fresh biochar, confirming the potential of charred biomasses in N retention and reduction in N-containing GHGs emission in soils (Spokas et al.,

2012). However, recent evidences suggest that standard analytical methods (as adopted in our study) could not detect all biochar-bound nutrients, in particular nitrate-N, which may then remain frequently underestimated (Kammann et al., 2015). However, although the absolute total value we measured may be underestimated, the nitrate-N extracted from aged biochar (78.3 mg kg⁻¹) was 14 times higher than fresh biochar (5.5 mg kg⁻¹), and unlikely the total nitrate-N content of fresh biochar, would result higher than aged particles. Besides, Kammann et al. (2015) report that the non-detectable NO₃-N remains non-exchangeable and captured onto biochar particles, thereby we conclude that such portion is not available to plants.

4.2.2 Biochar C and N behave differently as it ages in soil

Consistent with the total biochar C content (Tab. 1), XPS analyses showed that environmental exposure significantly reduced biochar C at% (Tab. 2, Tab.3 and Fig. 5).

Table 2. Elemental composition (atomic concentration - at%) of aged (4-year in field conditions at 30t ha⁻¹) biochar surface (S1) and 3 depths (L2, L3 and L4) compared with fresh biochar as determined by XPS.

	C		N		O	Al	Si	
AGEING	S1		L2	L3	L4			
	(0-5 nm)		(6-10 nm)	(15-20 nm)	(30-35nm)			
Fresh	91.6	1.2	0.89	0.85	0.76	6.7	0.29	0.47
Aged	55.3	3.15	1.40	1.15	1.13	32.7	3.73	6.50
Significance	***	2SEM=0.50				***	***	***
DEPTH								
S1	68.74					24.1	1.53	3.47
L2	74.03					19.0	2.15	3.69

L3	75.01		18.2	2.25	3.49
L4	76		17.6	2.12	3.31
Significance	ns		ns	ns	ns
Interaction Ageing	ns	**	ns	ns	ns

***Depth**

385 ns, ** and *** = effect not significant or significant at $p < 0.01$ and $p < 0.001$, respectively. Interaction between biochar
386 and layer significant at $p < 0.01$. Values differing by ≥ 2 SEM are statistically different

Table 3. Atomic concentration (at%) of aged (4-year in field conditions at 30 t ha⁻¹) biochar surface (S1) and 3 depths (L5, L6 and L7) compared with fresh biochar as determined by XPS.

	C				N				O	Al	Si
AGEING	S1	L5	L6	L7	S1	L5	L6	L7			
	(0-5 nm)	(35-40 nm)	(70-75 nm)	(105-110 nm)	(0-5 nm)	(35-40 nm)	(70-75 nm)	(105-110 nm)			
Fresh	79.0	90.2	91.0	91.2	1.02	0.82	0.76	0.80	10.3	0.64	0.33
Aged	50.4	52.8	65.5	69.2	3.81	2.14	1.18	1.13	30.1	3.51	5.93
Significance	2SEM=4.82				2SEM=0.81				***	***	***
DEPTH											
S1									28.0a	1.69	3.16
L5									21.2b	2.33	3.51
L6									16.4c	2.03	2.89
L7									15.3c	2.23	2.98
Significance									***	ns	ns
Interaction		*				*			ns	ns	ns
Ageing*Depth											

ns, * and *** = effect not significant or significant at $p < 0.05$ and $p < 0.001$, respectively. In the same column, means followed by the same letter are not statistically different ($p < 0.05$, SNK Test). Interaction between biochar and depth significant at $p < 0.05$. Values differing by ≥ 2 SEM are statistically different.

Estimated depth layers: S1 (0-5 nm), L5 (35-40nm), L6 (70-75nm), L7 (105-110nm)

392

393

394 Figure 5. Atomic percentage surface elemental composition (XPS) of aged (4 years) biochar applied at different rates as compared with fresh
395 biochar

396 ns, *, ** and *** = effect of biochar ageing and rate not significant and significant at $p \leq 0.05$, $p \leq 0.01$ and $p \leq 0.001$, respectively. Within each element, bars with the same letter
397 are not statistically different ($p \leq 0.05$), according to the Student-Newman-Keuls (SNK) test.

398 Independent of the application rate, 4 years of field exposure reduced surface (0-5 nm)
 399 biochar relative C at% up to 35.5% compared to unexposed fragments (Fig. 5). The
 400 most intense reduction in biochar C at% occurred in the top 5 nm layer either in fresh (-
 401 13%) and aged biochars (-19.4%) (Tab. 2) as a response to the natural oxidation.
 402 Biochar C depletion was less intense in inner layers and no effects were observed in
 403 layers deeper than 35 nm in fresh particles. Depletion of C occurred up to 70 nm depth
 404 in aged fragments (Tab. 3). Within aged particles, biochar C at% vs depth could be fit
 405 by a positive regression model according to an exponential trend with a coefficient of
 406 determination (R^2) equal to 0.93 ($y=44.025e^{0.1167x}$). These responses suggest that
 407 exposure in croplands strongly alters biochar C surface composition and that C
 408 depletion starts from the top exposed layer and proceed toward the interior, as a
 409 consequence of both biotic and abiotic oxidation. In our experiment after 4 years
 410 biochar's relative C content was reduced by ~15% compared to its initial values. This
 411 relative reduction in C content could be due to loss of biochar C, or it could simply be
 412 the result of increased contents of other atoms relative to C (Tab. 2, Tab. 3), as
 413 mentioned above. Regardless, the amount of labile C lost compared to stable C stored
 414 in soils with biochar is still considered comparatively negligible and should not affect
 415 the C sequestration potential of biochar on a long-term basis (Joseph et al., 2010).
 416 As expected, relative N at% was unaffected within layers of fresh particles (Tab. 2 and
 417 Tab. 3). Total N concentration (Tab. 1) and N at% (Tab. 2, Tab. 3 and Fig. 5) was
 418 statistically higher in aged fragments, showing the opposite trend compared to C. In
 419 aged fragments, biochar N at% was statistically higher mostly in the top surface (Fig. 5,
 420 Tab. 2 and Tab. 3), up to 40 nm depth (Tab. 3). Ageing and depth significantly
 421 interacted with atomic N composition and it decreased progressively within aged

422 fragments as the depth increased up to 75 nm depth (L6), while no differences were
423 recorded between the deepest (L6 and L7) layers (Tab. 3). This evidence suggests that
424 mechanisms for N retention in aged biochar occur mainly in the exposed top surface,
425 but are not only limited to this. Furthermore, the C/N ratio of the biochar fragments
426 dramatically decreases as biochar ages, with potential implications for processes that are
427 C/N-influenced (e.g. microbial activity).

428

429 *4.2.3 Environmental exposure alters biochar surface K, Ca, Mn and Fe ratio*

430 Ageing significantly affected the biochar surface relative at% of K, Ca, Mn and Fe with
431 no effects induced by the application rate (Fig. 5). No differences were detected for Mg
432 and P at%. Surface relative K at% of aged biochar was reduced compared to fresh
433 biochar up to 29.3 fold for the 30 t/ha application rate (Fig. 5). On the contrary, surface
434 at% of Ca, Mn, and Fe were higher in aged fragments, with no effects induced by the
435 application rate (Fig. 5). The most abundant increase was measured for Ca which
436 increased by 90 fold while Mn at% recorded a limited increase, although significant. It
437 is worth mentioning that these changes are expressed as relative at%, which estimate the
438 relative atomic abundance ratio among scanned elements instead of giving the absolute
439 concentration. Biochar surface ageing-induced effects can be ascribed either to physical
440 or chemical mechanisms. The surface of the weathered biochar particles was finely
441 coated with soil and organic residues which appeared to adhere and/or be trapped in
442 pores and fractures, partially explaining the higher concentration for most of the
443 elements found on the biochar surface. Chemical mechanisms involved the high reactive
444 charge density of the biochar surface (Van Zwieten et al., 2010), which has adsorption
445 sites where cations, clay, and organic matter may be ionically or covalently bound,

confirming the interaction of biochar with minerals and organic compounds in soils. This may also contribute to explaining the higher values of O at% recorded in aged fragments (Fig. 5). The potential of biochar to retain minerals directly on its surface (Glaser et al., 2002) increases the ability of biochar to retain nutrients in soils. Various combinations of Al, Si, C, Fe, and Ti, and trace amounts of Ca, Mg, Mn, K, Na, P, and S were found at the external surfaces of aged greenwaste biochar particles (Joseph et al., 2010). However, the lack of change in the P and Mg atomic surface composition found in this study indicates that this process is biochar-type and soil dependent. Different processes (dissolution, hydrolysis, carbonation, decarbonation, hydration, redox reactions) and several mechanisms (H-bonding, cation-bridging, covalent bonding and hydrophobic types of interactions) are involved in biochar weathering processes as a consequence of its interactions with OM, water, adsorption of dissolved organic (e.g. root exudates) and inorganic compounds and oxidation (Joseph et al., 2010). In particular, the significant decrease of K at% in aged biochar surfaces we observed (87% in average relative to the fresh particles) may be due to the dissolution of soluble salts and organic compounds (i.e. biopolymers and low molecular weight compounds) associated with charred particles which is among the first reactions upon biochar addition to soil (Joseph et al., 2010; Shinogi et al., 2003). This is also confirmed by the reduced EC that we measured in aged particles. The dissolution process may induce a rapid increase in the availability of water soluble cations in the soil layer, where biochar is incorporated, thus when high rates are applied, biochar may represent a consistent source of K, enough to fulfill plant requirement (according to the application rate, biochar type and crop) for the first 2-3 seasons after its incorporation. However, results from a column experiment showed that weathering reduced not only the content of K

470 but also S, Ca, and P (Yao et al., 2010), suggesting that mineral release from charred
471 materials is controlled by biochar characteristics and the environment.

472

473 *4.2.4 Ageing promotes biochar oxidation, Al and Si at%*

474 Although chemically induced biochar degradation starts before incorporation in soil as a
475 result of the oxidation of exposed C rings with a high density of π -electrons (Contescu
476 et al., 1998) and free radicals (Montes- Morán et al., 2004), only once in soil does
477 biochar experience significant chemical weathering. In our experiment, ageing
478 increased values of biochar O, Al, and Si at% (Fig. 5, Tab. 2). Ageing and depth did not
479 interact in atomic O, Al, and Si composition and values of biochar O, Al, and Si at%,
480 were comparable among layers (Tab. 2 and Tab. 3). Nevertheless, depth affected atomic
481 O composition, which was reduced as the depth increased (Tab. 3). Independently of the
482 layer, values of O, Al, and Si always increased in aged biochar by 3, 5, and 18 fold,
483 respectively (Tab. 3). Environmental exposure promoted fragment's oxidation (Tab. 2
484 and 3) and, independent of the age, oxidation started from the top exposed surface and
485 was progressively reduced as depth increased down to 75 nm (Tab. 3), likely as a result
486 of both biotic and abiotic processes, although some research suggests that biotic
487 processes dominate (Zimmerman , 2010; Cheng et al., 2006). The O:C ratio of our
488 biochar surface shifted from <0.074 to >0.58 after 4 years in field conditions as a
489 consequence of the depletion of C and increase of O content. This may have
490 consequences for biochar stability in soil, since the increase of the O:C ratio has been
491 cited as a fundamental attribute in controlling the resistance to microbial mineralization
492 (Harvey et al., 2012; Spokas et al., 2010;), although it may also simply reflect the

493 increased O present in soil minerals and/or dissolved organic matter that have attached
494 to the biochar.

495

496 *4.2.5 Oxidation affects biochar C functional groups*

497 Our results show that biochar C functional groups were affected by the interaction
498 between ageing and depth (Tab. 4). The relative at% of the C functional groups always
499 increased by ageing in the top 3 layers (S1+L5+L6 layers, equal to 0-75 nm depth)
500 (Tab. 4), except for the -C-C/-C-H/-C=C bonds, where only in the top surface an
501 opposite trend was recorded (Tab. 4). No differences were measured in the deepest layer
502 (105-110 nm) between fresh and aged biochars (Tab. 4). The overall development of C
503 functional groups (-C=O, -C-O, -COOH) on the aged biochar surface as a consequence
504 of the natural oxidation which involves the increase in O and H composition (Cheng et
505 al. 2008; Yao et al. 2010; Jones et al. 2012; Lin et al. 2012; LeCroy et al. 2013; Qian
506 and Chen, 2014) This oxidation is attributed to both biotic and abiotic processes,
507 although some data suggest that biotic processes dominate (Cheng et al. 2006;
508 Zimmerman, 2010). The increased oxidation of C in the uppermost surface layers of the
509 aged biochar confirms that oxidation and/or adsorption of soil OM occurred (Joseph et
510 al. 2010). Nevertheless, different functional groups can be formed on aged biochar
511 through oxidation such as lactonic, o-quinone-like structures and ether-type oxygen
512 (Boehm, 2001). In our case, the -C-C/-C-H/C=C bonding state was always the major
513 component of both fresh and aged biochar, although after 4 years the relative
514 composition of these C bonds significantly decreased only in the top surface.
515 The most significant changes in the C1s bonding state were evident on the top surface
516 (0-5 nm), where the relative concentration of -C=O, -C-O and, to a lesser extent, -

517 COOH, were significantly higher in aged biochar. It is possible that carboxyl functional
518 groups were less developed relative to other oxidized C forms because carboxyl groups
519 may be partially decarboxylated through hydrolysis reactions occurring in solution (Yan
520 et al. 1996).

Table 4. C1s bonding state and relative atomic percentage of aged (4-year in field conditions at 30 t ha⁻¹) biochar surface (S1) and 3 depths (L5, L3 and L7) compared with the fresh biochar as determined by XPS.

	Binding Energy (eV) (avg ± std dev)															
	-C-C/-CH/-C=C				-C-O				-C=O				-COOH			
	284.79±0.05	284.76±0.06	284.75±0.04	284.75±0.05	286.14±0.46	285.96±0.29	285.91±0.21	285.85±0.12	287.53±0.5	286.91±1.28	287.16±0.61	287.19±0.22	288.76±0.39	288.87±0.32	288.61±0.45	288.73±0.35
AGEING	S1	L5	L6	L7	S1	L5	L6	L7	S1	L5	L6	L7	S1	L5	L6	L7
Fresh	75.5	67.2	65.8	65.2	13.2	23.9	24.7	25.2	5.1	5.1	5.6	5.6	6.1	3.8	3.9	4.0
Aged	51.9	79.8	78.9	73.7	27.4	15.4	16.4	18.8	12.5	3.0	3.1	4.7	8.15	1.7	1.5	2.8
Significance	2SEM=8.79				2SEM=7.35				2SEM=1.77				2SEM=1.29			
Interaction	**				*				***				*			
Ageing*Depth																

*, ** and *** = Interaction between ageing and depth significant at $p < 0.05$, $p < 0.01$ and $p < 0.001$, respectively. Values differing by ≥ 2 SEM are statistically

different.

Estimated depth layers: S1 (0-5 nm), L5 (35-40nm), L6 (70-75nm), L7 (105-110nm)

526 *4.3 Agronomical and ecological implications*

527 Our findings suggest that biochar's effects on soil hydrology may change with time,
528 raising a number of points. It seems reasonable to assume that different soil textures and
529 mineralogies interact differently with various biochars; thus biochar and ecosystem-
530 specific patterns of exterior pore blockage may be expected (Barnes et al., 2014).

531 Furthermore, shifts in soil hydrology pose several implications for water-mediated
532 processes as well as for the erosive fate of applied particles. For instance, soil leaching
533 patterns may be different in aged biochar-mixed soils compared to the immediate
534 response of biochar addition. Likewise, the influence of biochar on water retention may
535 change as biochar ages, in particular in easily drained soils and especially if a dramatic
536 reduction occurs in the number of pores between 0.01 and 0.1 mm. This pore-size range
537 in biochar is fundamental to increased plant available water since larger pores weakly
538 retain water under gravity (Jury et al., 1991) and smaller pores do not provide water in a
539 plant-accessible form (Masiello et al., 2015).

540 Water infiltration shifts the functional density of biochar as water fills internal pores
541 previously occupied by air. Once partially water-filled, the functional density of biochar
542 particles exceeds that of water and the particles sink. The sinking process seems to be
543 altered by field aging, with mineral blockages of pore throats slowing the rate of water
544 infiltration.

545 Similarly, it seems reasonable to hypothesize that it takes longer for aged fragments to
546 dry out. This lag in particle infill time may suggest implications also for the erosion rate
547 of biochar particles.

548 The porous structure of biochar provides suitable habitat for a range of microbial
549 communities (Hockaday et al., 2006; Warnock et al., 2007; Downie et al., 2009; Thies

550 and Rilling, 2009), and fungi can grow from within the pores out into the soil (Lehmann
551 et al., 2011). Pore connectivity has been suggested to modulate the availability of
552 biochar-associated labile organic compounds to microbial enzymes (Barnes et al.,
553 2014). Easier access to these sites in recently added biochar could partially explain the
554 initial high mineralization rates observed after biochar addition (Cross and Sohi, 2011).
555 Our findings suggest potential shifts in microbial colonization patterns as biochar ages
556 in soil. Due to ageing, the attachment of soil particles, changes in pore connectivity and
557 pore clogging of biochar particles may alter habitat suitability and microbial activity
558 (Lehmann et al., 2011; Thies and Rilling, 2009) reducing microbes colonization.
559 However, fractures on the weathering particles may offer new opportunities for
560 microbial colonization. Furthermore, minerals covering the external surface of biochar
561 fragments interfere with its reactive surface, limiting its sorption capacity (Joseph et al.,
562 2010) but at the same time the greater surface reactivity due to oxidation may promote
563 physical protection of biochars and, thus, its long-term stability (Brodowski et al.,
564 2006).
565 The development of O-containing C functional groups of aged biochar increases the
566 reactivity of the biochar surface, leading to an enhancement of chemical sites able to
567 retain nutrients and other organic compounds on this surface. This process is also
568 responsible for the evolution of negative charges, raising the biochar CEC over time
569 (Zimmerman, 2010).
570 These processes occurred mostly on the O-exposed biochar surface, leading to an
571 enhancement of chemical sites able to retain nutrients and other organic compounds on
572 this surface, consistent with the ion sorption pattern of our aged biochar. Oxidized
573 biochar particles may then be bound to soil minerals. Mineral attachment has been

574 indicated as one of the possible mechanisms for the slowing of biochar decomposition
575 and oxidation (Browdowski et al., 2006; Nguyen et al., 2008), acting as a control on the
576 stabilization process of charred particles.

577

578 **Acknowledgments**

579 We thank Dr. Xiaodong Gao and Dr. Bo Chen (Rice University, Houston, USA) for
580 their valuable assistance with fragment density determinations and XPS analyses. We
581 appreciated generous laboratory and equipment access provided by Dr. Helge
582 Gonnermann. We also acknowledge funding from the US NSF through grants EAR
583 0911685 and 0949337. Authors thank three anonymous reviews for their valuable
584 comments which helped to improve the manuscript.

585 **References**

- 586 Baltrėnas, P., Baltrėnaitė, E., Spudulis, E., 2015. Biochar from Pine and Birch
587 Morphology and Pore Structure Change by Treatment in Biofilter. *Water, Air, & Soil*
588 Pollution, 226(3), 1-14.
- 589
- 590 Barnes, R. T., Gallagher, M. E., Masiello, C. A., Liu, Z., Dugan, B., 2014. Biochar-
591 Induced Changes in Soil Hydraulic Conductivity and Dissolved Nutrient Fluxes
592 Constrained by Laboratory Experiments. *PLoS ONE* 9(9), e108340.
- 593
- 594 Baronti, S., Vaccari, F. P., Miglietta, F., Calzolari, C., Lugato, E., Orlandini, S.,
595 Genesio, L., 2014. Impact of biochar application on plant water relations in *Vitis*
596 *vinifera* (L.). *Eur. J. Agron.* 53, 38-44.
- 597
- 598 Bird, M.I., Ascough, P.L., Young, I.M., Wood, C.V., Scott, A.C., 2008. X-ray
599 microtomographic imaging of charcoal. *J. Archaeol. Sci.* 35(10), 2698-2706.
- 600
- 601 Boem, H.P., 2001. Carbon surface chemistry. In *Graphite and precursors*, Delhaes, P.,
602 Eds., CRC: Amsterdam, pp. 141–178.
- 603
- 604 Brewer, C.E., Chuang, V.J., Masiello, C.A., Gonnermann, H., Gao, X., Dugan, B.,
605 Driver, E.L, Panzacchi, P., Zygourakis, K., Davies, C.A., 2014. New approaches to
606 measuring biochar density and porosity. *Biomass Bioenerg.* 66, 176-185.
- 607

608 Brockhoff, S. R., Christians, N. E., Killorn, R. J., Horton, R., Davis, D.D., 2010.
609 Physical and mineral-nutrition properties of sand-based turfgrass root zones amended
610 with biochar. *Agron. J.* 102 (6), 1627-1631
611

612 Brodowski, S., John, B., Flessa, H., Amelung, W., 2006. Aggregate-occluded black
613 carbon in soil. *Eur. J. Soil Sci.* 57(4), 539–546.
614

615 Bruun, S., Jensen, E., Jensen, L., 2008. Microbial mineralization and assimilation of
616 black carbon: Dependency on degree of thermal alteration. *Org. Geochem.* 39, 839-
617 845.
618

619 Bruun, E. W., Petersen, C. T., Hansen, E., Holm, J. K., Hauggaard-Nielsen, H., 2014.
620 Biochar amendment to coarse sandy subsoil improves root growth and increases water
621 retention. *Soil Use Manage.* 30, 109–118.
622

623 Chen, B., Zhou, D., Zhu, L., 2008. Transitional adsorption and partition of nonpolar and
624 polar aromatic contaminants by biochars of pine needles with different pyrolytic
625 temperatures. *Environ. Sci. Technol.* 42(14), 5137-5143.
626

627 Cheng, C.H., Lehmann, J., Thies, J. E., Burton, S. D., Engelhard, M.H., 2006. Oxidation
628 of black carbon by biotic and abiotic processes. *Org. Geochem.* 37, 1477-1488.
629

630 Cheng, C.H., Lehmann, J., Engelhard, M.H., 2008. Natural oxidation of black carbon in
631 soils: Changes in molecular form and surface charge along a climosequence. *Geochim.*
632 *Cosmochim. Ac.* 72, 1598-1610.

633

634 Cheng, C.H., Lehmann, J., 2009. Ageing of black carbon along a temperature gradient.
635 *Chemosphere* 75, 1021–1027.

636

637 Clarkson, R.B., Odintsov, B.M., Ceroke, P. J., Fruianu, M., Belford, R. L., 1998.
638 Electron paramagnetic resonance and dynamic nuclear polarization of char suspensions:
639 surface science and oximetry. *Physics in medicine and biology* 43(7), 1907.

640

641 Conte, P., Marsala, V., De Pasquale, C., Bubici, S., Valagussa, M., Pozzi, A., Alonzo,
642 G., 2013. Nature of water-biochar interface interactions. *GCB Bioenergy* 5(2), 116-121.

643

644 Contescu, A., Vass, M., Contescu, C., Putyera, K., Schwarz, J.A., 1998. Acid buffering
645 capacity of basic carbons revealed by their continuous pK distribution. *Carbon* 36(3),
646 247–258.

647

648 Cross, A., Sohi, S.P., 2011. The priming potential of biochar products in relation to
649 labile carbon contents and soil organic matter status. *Soil Biol. Biochem.* 43(10),
650 2127-2134

651

652 Downie, A., Crosky, A., Munroe, P., 2009. Physical Properties of Biochar. In Biochar
 653 for environmental management: science and technology, Lehmann, J., Joseph, S., Eds.,
 654 Earthscan: London 2009, pp13–32.

655

656 Glaser, B., Lehmann, J., Zech, W., 2002. Ameliorating physical and chemical properties
 657 of highly weathered soils in the tropics with charcoal—a review. *Biol. Fertil. Soils* 35,
 658 219–230.

659

660 Harvey, O. R., Kuo, L. J., Zimmerman, A. R., Louchouart, P., Amonette, J. E., Herbert,
 661 B. E., 2012. An index-based approach to assessing recalcitrance and soil carbon
 662 sequestration potential of engineered black carbons (biochars). *Environ. Sci. Technol.*
 663 46, 1415–1421.

664

665 Hockaday, W. C., Grannas, A. M., Kim, S., Hatcher, P.G., 2006. Direct molecular
 666 evidence for the degradation and mobility of black carbon in soils from ultrahigh-
 667 resolution mass spectral analysis of dissolved organic matter from a fire-impacted forest
 668 soil. *Org. Geochem.* 37(4), 501-510.

669

670 ICM, 2009. Integrated Crop Management. [http://agricoltura.regione.emilia-](http://agricoltura.regione.emilia-romagna.it/produzioni-agroalimentari/doc/disciplinari/produzione-integrata/archivio-dpi/disciplinari-di-produzione-integrata-2012)
 671 [romagna.it/produzioni-agroalimentari/doc/disciplinari/produzione-integrata/archivio-](http://agricoltura.regione.emilia-romagna.it/produzioni-agroalimentari/doc/disciplinari/produzione-integrata/archivio-dpi/disciplinari-di-produzione-integrata-2012)
 672 [dpi/disciplinari-di-produzione-integrata-2012](http://agricoltura.regione.emilia-romagna.it/produzioni-agroalimentari/doc/disciplinari/produzione-integrata/archivio-dpi/disciplinari-di-produzione-integrata-2012). Last visit October 1st, 2014

673

674 Jaafar, N. M., Clode, P. L., Abbott, L. K., 2014. Microscopy observations of habitable
675 space in biochar for colonization by fungal hyphae from soil. *J. Integrative Agric.*
676 13(3), 483-490.
677

678 Jones, D. L., Rousk, J., Edwards-Jones, G., DeLuca, T. H., Murphy, D. V., 2012.
679 Biochar-mediated changes in soil quality and plant growth in a three year field trial. *Soil*
680 *Biol. Biochem.* 45, 113-124.
681

682 Joseph, S., Camps-Arbestain, M., Lin, Y., Munroe, P., Chia, C.H., Hook, J., Van
683 Zwieten, L., Kimber, S., Cowie, A., Singh, B. P., Lehmann, J., Foidl, N., Smernik, R. J.
684 2010. An investigation into reactions of biochar in soil. *Aust. J. Soil Res.* 48, 501-515.
685

686 Jury, W.A., Gardner, W.R., Gardner, W.H., 1991. Eds. *Soil Physics*, ed., John Wiley &
687 Sons, New York.
688

689 Kammann, C. I., Schmidt, H.P., Messerschmidt, N., Linsel, S., Steffens, D., Müller, C.,
690 Koyro, H-W., Pellegrino, C., Stephen, J.. 2015. Plant growth improvement mediated by
691 nitrate capture in co-composted biochar. *Scientific reports*, 5.
692

693 Keiluweit, M., Nico, P.S., Johnson, M.G., Kleber, M., 2010. Dynamic molecular
694 structure of plant biomass-derived black carbon (biochar). *Environ. Sci. Technol.*
695 44(4), 1247-53
696

697 Kuzyakov, Y., Bogomolova, I., Glaser, B., 2014. Biochar stability in soil:
698 Decomposition during eight years and transformation as assessed by compound-specific
699 ¹⁴C analysis. *Soil Biol. Biochem.* 70, 229–236
700

701 Laine, J., Yunes, S., 1992. Effect of the preparation method on the pore size distribution
702 of activated carbon from coconut shell. *Carbon* 30, 601–604.
703

704 LeCroy, C., Masiello, C.A., Rudgers, J.A., Hockaday, W.C., Silberg, J.J., 2013.
705 Nitrogen, biochar, and mycorrhizae: Alteration of the symbiosis and oxidation of the
706 char surface. *Soil Biol. Biochem.* 58, 248-254.
707

708 Lehmann, J., Czimczik, C., Laird, D., Sohi, S. 2009. Stability of biochar in soil. In
709 *Biochar for environmental management: science and technology*, Lehmann, J., Joseph,
710 S., Eds., Earthscan: London 2009, pp 183-206
711

712 Lehmann, J., Rillig, M.C., Thies, J., Masiello, C.A., Hockaday, W.C., Crowley, D.,
713 2011. Biochar effects on soil biota—a review. *Soil Biol. Biochem.* 43(9), 1812-1836.
714

715 Liang, B., Lehmann, J., Solomon, D., Kinyangi, J., Grossman, J., O'Neill, B., Neves, E.
716 G., 2006. Black carbon increases cation exchange capacity in soils. *Soil Sci. Soc. Am. J.*
717 70(5), 1719-1730.
718

719 Lin, Y., Munroe, P., Joseph, S., Kimber, S., Van Zwieten, L., 2012. Nanoscale organo-
 720 mineral reactions of biochars in ferrosol: an investigation using microscopy. *Plant Soil*
 721 357, 369–380.
 722
 723 Littell, R.C., Henry, P.R., Ammerman, C. B., 1998. Statistical analysis of repeated
 724 measures data using SAS procedures. *J. Anim. Sci. Biotechnol.* 76(4), 1216-1231
 725
 726 Major, J., Steiner, C., Downie, A., Lehmann, J. Biochar effects on nutrient leaching. In
 727 Biochar for environmental management: science and technology, Lehmann, J., Joseph,
 728 S., Eds., Earthscan: London 2009, pp 271-288.
 729
 730 Masiello, C.A., Dugan, B., Brewer, C.E., Spokas, K., Novak, J. M., Liu, Z., Sorrenti,
 731 G., 2015. Biochar effects on soil hydrology. In Biochar for environmental management:
 732 science and technology and Implementation, Lehmann, J., Joseph, S., Eds., Routledg 2nd
 733 Edition London 2009, pp 541-560.
 734
 735 Montes-Morán, M.A., Suárez, D., Menéndez, J.A., Fuente, E., 2004. On the nature of
 736 basic sites on carbon surfaces: an overview. *Carbon* 42(7), 1219–1225.
 737
 738 Mukherjee, A., Zimmerman, A. R., 2013. Organic carbon and nutrient release from a
 739 range of laboratory-produced biochars and biochar–soil mixtures. *Geoderma* 193, 122-
 740 130.
 741

742 Nguyen, B.T., Lehmann, J., Hockaday, W.C., Joseph, S., Masiello, C.A., 2010.
 743 Temperature sensitivity of black carbon decomposition and oxidation. *Environ. Sci.*
 744 *Technol.* 44 (9), 3324-3331.
 745
 746 Norwood, M. J., Louchouart, P., Kuo, L.J., Harvey, O. R., 2013. Characterization and
 747 biodegradation of water-soluble biomarkers and organic carbon extracted from low
 748 temperature chars. *Org. Geochem.* 56, 111–119.
 749
 750 Novak, J.M., Busscher, W.J., Watts, D.W., Amonette, J. E., Ippolito, J.A., Lima, I. M.,
 751 Gaskin, J., Das, K.C., Steiner, C., Ahmedna, M., Rehrich, D., Schomberg, H., 2012.
 752 Biochars Impact on Soil-Moisture Storage in an Ultisol and Two-Aridisols. *Soil Sci.*
 753 177, 310–320.
 754
 755 Nguyen, B.T., Lehmann, J., Kinyangi, J., Smernik, R., Riha, S.J., Engelhard, M.H.,
 756 2008. Long-term black carbon dynamics in cultivated soil. *Biogeochem.* 89, 295-308.
 757
 758 Oguntunde, P.G., Abiodun, B.J., Ajayi, A.E., van de Giesen, N., 2008. Effects of
 759 charcoal production on soil physical properties in Ghana. *J. Plant Nutr. Soil Sci.* 171,
 760 591–596.
 761
 762 Rajkovich, S., Enders, A., Hanley, K., Hyland, C., Zimmerman, A.R., Lehmann, J.
 763 2012. Corn growth and nitrogen nutrition after additions of biochars with varying
 764 properties to a temperate soil. *Biol. Fertil. Soils* 48(3), 271-284.
 765

766 Pietikäinen, J., Kiikkilä, O., Fritze, H., 2000. Charcoal as a habitat for microbes and its
767 effect on the microbial community of the underlying humus. *Oikos* 89, 231–242.
768

769 Qian, L., Chen, B., 2014. Interactions of Aluminium with Biochars and Oxidized
770 Biochars: Implications for the Biochar Aging Process. *J. Agric. Food Chem.* 62(2),
771 373–380.
772

773 Saville, D.J., Rowarth, J.S., 2008. Statistical measures, hypotheses, and tests in applied
774 research. *J. Natural Resources and Life Sci. Education* 37, 74–82.
775

776 Shinogi, Y., Yoshida, H., Koizumi, T., Yamaoka, M., Saito, T. 2003. Basic
777 characteristics of low-temperature carbon products from waste sludge. *Adv. Envir. Res.*
778 7(3), 661–665.
779

780 Spokas, K., Baker, J., Reicosky, D., 2010. Ethylene: Potential key for biochar
781 amendment impacts. *Plant Soil* 333, 443–452.
782

783 Spokas, K.A., Cantrell, K.B., Novak, J. M., Archer, D.W., Ippolito, J.A., Collins, H. P.,
784 Boateng, A.A., Lima, I.M., Lamb, M.C., McAloon, A. J., Lentz, R.D., Nichols, K.A.,
785 2012. Biochar: a synthesis of its agronomic impact beyond carbon sequestration. *J.*
786 *Environ. Qual.* 41(4), 973–989.
787

788 Spokas, K. A., 2013. Impact of biochar field aging on laboratory greenhouse gas
789 production potentials. *GCB Bioenergy* 5 (2), 165–176.

790

791 Spokas, K.A., Novak, J.M., Masiello, C.A., Johnson, M.G., Colosky, E.C., Ippolito, J.
792 A., Trigo, C., 2014. Physical Disintegration of Biochar: An Overlooked Process.
793 Environ. Sci. Technol. Lett. 1, 326–332.

794

795 Steiner, C., Glaser, B., Teixeira, W.G., Lehmann, J., Blum, W.E.H., Zech, W., 2008.
796 Nitrogen retention and plant uptake on a highly weathered central amazonian ferralsol
797 amended with compost and charcoal. J. Plant Nutr. Soil Sci.-Zeitschrift Fur
798 Pflanzenernahrung Und Bodenkunde 171, 893-899.

799

800 Sun, H., Hockaday, W.C., Masiello, C.A., Zygourakis, K., 2012. Multiple controls on
801 the chemical and physical structure of biochars. Ind. Eng. Chem. Res. 51(9), 3587-97.

802

803 Thies, J., Rillig, M. 2009. Characteristics of biochar: biological properties. In Biochar
804 for environmental management: science and technology, Lehmann, J., Joseph, S., Eds.,
805 Earthscan: London , pp 85-106.

806

807 Van Zwieten, L., Kimber, S., Morris, S., Chan, K. Y., Downie, A., Rust, J., Joseph, S.,
808 Cowie, A., 2010. Effects of biochar from slow pyrolysis of papermill waste on
809 agronomic performance and soil fertility. Plant Soil 327, 235-246

810

811 Verheijen, F., Jeffery, S., Bastos, A.C., van der Velde, M., Dias, I., 2010. Biochar
812 Application to Soils: A Critical Scientific Review of Effects on Soil Properties,
813 Processes and Functions. Joint Research Centre (JRC) Scientific and Technical Report

814 No EUR 24099 EN, Office for the Official Publications of the European Communities,
815 Luxembourg.

816

817 Warnock, D.D., Lehmann, J., Kuyper, T.W., Rillig, M.C., 2007 Mycorrhizal responses
818 to biochar in soil: concepts and mechanisms. *Plant Soil* 300:(1–2), 9–20.

819

820 Wildman, J., Derbyshire, F. 1991. Origins and functions of macroporosity in activated
821 carbons from coal and wood precursors. *Fuel* 70(5), 655-661.

822

823 Woolf, D., Amonette, J. E., Street-Perrott, F. A., Lehmann, J., Joseph, S. 2010.
824 Sustainable biochar to mitigate global climate change. *Nat. Commun.*, 1, 56.

825

826 Yan, F., Schubert, S., Mengel, K..1996. Soil pH increase due to biological
827 decarboxylation of organic anions. *Soil Biol. Biochem.* 28, 617–624.

828

829 Yao, F.X., Arbestain, M.C., Virgel, S., Blanco, F., Arostegui, J., Macia-Agullo, J.A.,
830 Macias, F., 2010. Simulated geochemical weathering of a mineral ash-rich biochar in a
831 modified Soxhlet reactor. *Chemosphere* 80, 724-732.

832

833 Zimmerman, A.R., 2010. Abiotic and microbial oxidation of laboratory-produced black
834 carbon (biochar). *Environ. Sci. Technol.* 44(4), 1295-1301.