Effect of Purification Method of β -Chitin from Squid Pen on the Properties of β -Chitin Nanofibers

Shin Suenaga^a, Nozomi Nikaido^b, Kazuhide Totani^b, Kazunori Kawasaki^c, Yoshihito Ito^d, Kazuhiko Yamashita^e, and Mitsumasa Osada^{a,*}

^a *Department of Chemistry and Materials, Faculty of Textile Science and Technology, Shinshu University, 3-15-1, Tokida, Ueda, Nagano 386-8567, Japan*

^b *Department of Chemical Engineering, National Institute of Technology, Ichinoseki College, Takanashi, Hagisho, Ichinoseki, Iwate 021-8511, Japan*

^c *National Institute of Advanced Science and Technology (AIST), 1-8-31, Midorigaoka, Ikeda, Osaka 563-8577, Japan*

^d *Iwate Industrial Research Institute, 2-4-25, Kitaiioka, Morioka, Iwate 020-0857, Japan*

^e *Yaegaki Bio-industry, Inc., 681, Mukudani, Hayashida, Himeji, Hyogo 678-4298, Japan*

Corresponding author. Phone: +81-268-21-5458; Fax: +81-268-21-5391

E-mail: osadam@shinshu-u.ac.jp

21   **Abstract**

22   The relationship between purification methods of β -chitin from squid pen and the
23   physicochemical properties of β -chitin nanofibers (NFs) were investigated. Two types
24   of β -chitin were prepared, with β -chitin (a $\rightarrow$ b) subjected to acid treatment for
25   decalcification and then base treatment for deproteinization, while β -chitin (b $\rightarrow$ a) was
26   treated in the opposite order. These β -chitins were disintegrated into NFs using wet
27   pulverization. The β -chitin (b $\rightarrow$ a) NF dispersion has higher transmittance and viscosity
28   than the β -chitin (a $\rightarrow$ b) NF dispersion. For the first time, we succeeded in obtaining 3D
29   images of the β -chitin NF dispersion in water by using quick-freeze deep-etch
30   replication with high-angle annular dark field scanning transmission electron
31   microscopy. The β -chitin (b $\rightarrow$ a) NF dispersion has a denser and more uniform 3D
32   network structure than the β -chitin (a $\rightarrow$ b) NF dispersion. Widths of the β -chitin (a $\rightarrow$ b)
33   and (b $\rightarrow$ a) NFs were approximately 8–25 and 3–10 nm, respectively.

34

35   *Keywords:* Chitin, Nanofiber, Star Burst

36

37 **1.Introduction**

38 Chitin is long-chain polysaccharides consisting of β -(1-4)-linked *N*-acetyl
39 anhydroglucosamine units, and has the potential for use in medical supplies, cosmetics,
40 and food [1–3] owing to high biocompatibility [4,5]. Chitin is classified α -chitin or β -
41 chitin, depending on its crystalline structure. Most chitin is purified from exoskeletons
42 of crustaceans, cell walls of fungi and yeasts, etc. as α -chitin [6]. α -Chitin has
43 antiparallel molecular chains with hydrogen bonds between the chains. On the other
44 hand, β -chitin is purified from squid pens, tubeworm housing tubes, diatom spines, etc.,
45 and the lower natural abundance compared to α -chitin [7]. The anhydrous β -chitin has
46 parallel molecular chains without significant hydrogen bonds between intermolecular
47 sheets [8,9]. The residual proteins in α -chitin from crab and shrimp can possibly trigger
48 shellfish allergies, while molluscan such as squid allergy does not appear to occur as
49 frequently compared to crustacean allergy [10]. This means that β -chitin from squid pen
50 is safer to utilize in human medical applications.

51 When α -chitin is purified from commercially available crab shell, acid treatment is
52 performed first for decalcification, followed by base treatment for deproteinization. The
53 later base treatment is believed to aid in base deacetylation for subsequent chitosan
54 production. The purification of β -chitin from squid pen also requires acid and base
55 treatments for decalcification and deproteinization. However, the relationship between
56 the purification method used to obtain β -chitin from squid pen and the physicochemical
57 properties of the resulting β -chitin nanofiber (NF) has not been reported. Therefore,
58 investigations into the overall process going from the squid pen raw material to β -chitin
59 NF are needed.

60 Chitin NF has attracted research interest in the field of materials chemistry [11,12].

61 When chitin is disintegrated into NF, the hydrophilic surface area increases, enhancing
62 the biochemical significance of the material [13,14]. As disintegrating methods of chitin
63 into NF, ultrasonication, grinding, or the Star Burst system under acidic conditions have
64 been reported [15–17]. The Star Burst system can convert α -chitin and cellulose into
65 their NFs by wet pulverization using a water jet [18]. This system uses only water
66 without the need for additional acid, achieves much lower contamination, and has high
67 throughput [19,20]. These advantages can reduce the barrier for use in medical supplies,
68 cosmetics, and food. Therefore, we adopt the Star Burst system for disintegrating β -
69 chitin into NF.

70 In this study, we prepared two types of β -chitin from squid pen, with β -chitin (a $\rightarrow$ b)
71 subjected to acid treatment for decalcification and then base treatment for
72 deproteinization, while β -chitin (b $\rightarrow$ a) was treated in the opposite order. The
73 physicochemical properties of the β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a) NFs were characterized by
74 XRD, transmittance, viscosity, and molecular weight measurement and electron
75 microscopy. In particular, 3D images of β -chitin NF were obtained with quick-freeze
76 deep-etch replication and high-angle annular dark field scanning TEM (HAADF-
77 STEM) for the first time, in order to observe the state of NF dispersion. We revealed
78 that relationship between purification methods of β -chitin and the physicochemical
79 properties of β -chitin NF.

80

81 **2. Materials and methods**

82 *2.1. Materials*

83 Squid pen contains 30% β -chitin, 70% protein, and less than 1% ash [21,22]. Two
84 types of β -chitin were prepared from a squid pen (*Todarodes pacificus*) by removing the

85 protein and ash (Fig. 1). The first one is β -chitin (a $\rightarrow$ b). 2 kg (wet weight) of squid pens
86 were soaked in 0.1 mol L⁻¹ hydrochloric acid solution (10 L) for 16 h at 15 °C to
87 remove ash, and the pens were then washed four times with distilled water (20 L per
88 wash). The decalcified squid pens were soaked in 1 mol L⁻¹ sodium hydroxide solution
89 (10 L) for 2 h at 90 °C to remove protein, and were then washed once with distilled
90 water (20 L). The protein removal process was then repeated. Afterwards, the β -chitin
91 was washed four times with distilled water (20 L per wash) until a neutral pH was
92 reached in the bulk water.

93 To obtain β -chitin (b $\rightarrow$ a), squid pens were first treated twice with 1 mol L⁻¹ sodium
94 hydroxide solution and then treated with 0.1 mol L⁻¹ hydrochloric acid solution.
95 Afterwards, the β -chitin was washed four times with distilled water until a neutral pH
96 was reached in the bulk water. The β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) were both dried
97 at 65 °C for 16 h, and then ground to obtain particles less than 100 μ m in diameter.

98 For comparison, α -chitin (< 100 μ m diameter) was obtained from Yaegaki Bio-
99 industry, Inc. and used without further purification.

100

101 *2.2. Preparation of Chitin Nanofibers*

102 The β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) powders were suspended separately in
103 distilled water at 1 wt%. The slurries were disintegrated using a Star Burst system
104 (Sugino Machine Co., Ltd.) (Fig. 2). The β -chitin slurries were pressurized from 230 to
105 240 MPa and then ejected from a nozzle (100 μ m aperture). The β -chitin slurries were
106 diagonally made to collide with each other. The disintegrated β -chitin was recovered
107 after cooling with a heat exchanger. The number of collision times (= pass) was set to 2,
108 5, and 10 passes.

109

110 2.3. Elementary Analysis

111 To evaluate the degree of *N*-acetylation, the amount of nitrogen and carbon in the β -
112 chitin (a→b) and β -chitin (b→a) powders were measured using an element analyzer
113 (Sumika Chemical Analysis Service, Ltd., SUMIGRAPH NC-1000). Acetanilide was
114 used as a reference material. The degrees of *N*-acetylation were calculated from the
115 following equation:

$$116 \text{ Degrees of } N\text{-acetylation} = (C/N - 6) / 2 \quad (1)$$

117 where *C* is moles of carbon and *N* is moles of nitrogen.

118

119 2.4. X-ray Diffraction (XRD)

120 The 1 wt% β -chitin (a→b) and (b→a) NF dispersions were dried at 75°C for 12 h.
121 The β -chitin (a→b), β -chitin (b→a), and α -chitin powder and their NFs (except α -
122 chitin) were converted into pellets approximately 1.3 cm in diameter and approximately
123 0.43 mm in thickness by pressing at approximately 750 MPa for 1 min using a hand-
124 press machine (Shimadzu Co., Ltd., SSP-10A). XRD patterns of the β -chitin (a→b) and
125 β -chitin (b→a) powder and NF were measured from 5–35° of diffraction angle 2θ (in
126 radians) using an X-ray diffractometer (Rigaku Co., Ltd., RINT 2500HF/PC) with Cu-
127 K α radiation at 40 kV and 40 mA. The crystallinity index (CI) was determined by the
128 following equation:

$$129 \text{ CI} = (I_{1-10} - I_{\text{am}}) / I_{1-10} \quad (2)$$

130 where I_{1-10} is the maximum intensity of the [1–10] mixed plane and I_{am} is the intensity
131 of the amorphous diffraction at 16° [23]. *d*-Spacing was determined using Bragg's law,
132 which states that

133 $d\text{-Spacing } [\text{\AA}] = \lambda / 2 \sin \theta$ (3)

134 where λ is the wavelength of Cu-K α radiation ($\lambda = 1.5418 \text{ \AA}$) and θ (in radians) is the
135 scattering angle.

136

137 *2.5. Fourier Transform Infrared (FT-IR) Spectroscopy*

138 The β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) powder were blended with potassium
139 chloride and converted into pellet using a mini hand-press machine (Shimadzu Co.,
140 Ltd., MHP-1). We did not use potassium bromide because the bromine affects FT-IR
141 spectra by ion-exchange with residual chlorine combined with amino group of the β -
142 chitin (b $\rightarrow$ a) powder after acid treatment. FT-IR spectra of the pellet were recorded
143 using an FT-IR spectrometer (JASCO Co., Ltd., FT/IR 4200) from 500 to 4000 cm^{-1}
144 with 4 cm^{-1} resolution and 32 scans.

145

146 *2.6. Molecular Weight Distribution*

147 The molecular weight distributions of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs
148 were measured using a gel permeation chromatography (GPC) system (Shimadzu, LC-
149 10Avp), which was equipped with a refractive index detector, a GPC column (Showa
150 Denko K. K., Shodex GPC KD-806K + KD-803), and a guard column (Showa Denko
151 K. K., Shodex GPC KD-G). Pullulan standards (Showa Denko K. K., Shodex
152 STANDARD P-82) of 708, 340, 200, 107, 47.1, 21.1, 9.6, and 5.9 kDa were used. A
153 total of 1% of the sample was dissolved in a 5% LiCl/DMAC solution with continuous
154 stirring for 2 days. Prior to measurement, the samples were filtered through a 0.45 μm
155 nylon filter. The flow rate of the mobile phase was 0.5 mL min^{-1} . The temperatures of
156 the columns and the detector were set at 30 $^{\circ}\text{C}$. A calibration curve was plotted for the

157 elution time versus the absolute molecular weight of the standards, and the relative
158 molecular weight of the β -chitin samples was estimated from the standard curve.

159

160 *2.7. Optical Transmittance*

161 The 1 wt% β -chitin NF dispersions were diluted with distilled water to 0.05 wt%
162 and sonicated for 20 minutes using an ultrasonic washing machine (SND Co., Ltd.,
163 USK-4). The 0.05 wt% β -chitin dispersions were then loaded into quartz cuvettes. The
164 transmittance was measured over a range of 200–700 nm by a spectrophotometer
165 (JASCO Co., Ltd., V-630 BIO), using distilled water as a blank.

166

167 *2.8. Viscoelastic Measurements*

168 The 1 wt% β -chitin NF dispersions were loaded into 35 mL glass bottles. The β -
169 chitin dispersions were placed in a thermostat chamber filled with water at 25 °C, and
170 the viscosity was measured with a Brookfield viscometer (Brookfield Asset
171 Management Inc., DIGITAL VISCOMETER MODEL DV-2). First, a #64 spindle was
172 used at a viscosity of more than 1000 mPa·s. A #62 spindle was then used at a viscosity
173 of less than 1000 mPa·s. These measurements were carried out at a rotational speed of
174 50 rpm for 500 s.

175

176 *2.9. Quick-Freeze Deep-Etch Replication and High-Angle Annular Dark Field Scanning* 177 *Transmission Electron Microscopy (HAADF-STEM)*

178 The 1 wt% β -chitin NF dispersions were frozen using a metal contact method; the
179 dispersions were brought into contact with a pure copper block cooled by liquid helium.
180 The frozen sample was cut at from –85 to –90 °C. The cut section was freeze-dried to

181 etch the ice, exposing the β -chitin NF. The etched surface was coated with an
182 approximately 6.5 nm layer of platinum and carbon as a replica membrane, and then
183 coated with an approximately 27 nm layer of carbon to reinforce the replica membrane.
184 The coated sample was soaked in a formic acid overnight to eliminate the β -chitin NF,
185 so that only the replica membrane remained. After the replica membrane was washed
186 with water, it was mounted on a grid. The sample was studied using a HAADF-STEM
187 (FEI, Tecnai G2F20) operating at 200 kV. When the width of the β -chitin NF was
188 estimated, we subtracted the thickness of the platinum layer from the NFs images
189 observed by the HAADF-STEM.

190

191 *2.10. Field-Emission Scanning Electron Microscopy (FE-SEM)*

192 A β -chitin NF dispersion was precipitated with a centrifuge, and the supernatant was
193 removed. We added *tert*-butyl alcohol to the precipitate, which was subsequently
194 dispersed using ultrasonication. After repeating this process several times, the solvent
195 was exchanged from water to *tert*-butyl alcohol. This mixture was then frozen at $-80\text{ }^{\circ}\text{C}$
196 and dried under vacuum. The dried β -chitin NF was coated with an osmium tetroxide
197 layer approximately 3 nm in thickness. The sample was viewed using an FE-SEM
198 (JEOL, JSM-7001F) operating at 2.0 kV.

199

200 *2.11. Transmission Electron Microscopy (TEM)*

201 The 1 wt% β -chitin NF dispersions were diluted with distilled water to 0.02 wt%
202 and sonicated for 20 min using an ultrasonication. A drop of the dispersion was mounted
203 on a carbon coated micro grid. After approximately 1 min, the excess liquid was
204 absorbed by a filter paper. A concave background was stained a drop of 2% uranyl

205 acetate for 5 min, and the excess solution was drawn off the micro grid using filter
206 paper. The negatively stained sample was left in air to dry. The sample was observed at
207 80 kV by a TEM (JEOL, JEM-2100).

208

209 **3. Results**

210 *3.1. Characterization of Purified β -Chitin Powder*

211 Before grinding to the powders, the purified β -chitin (a $\rightarrow$ b) was flexible to the
212 touch, but the purified β -chitin (b $\rightarrow$ a) was more fragile. As mentioned in the 2.1.
213 Section, the pH of bulk water was neutral at the final washing treatment of the purified
214 β -chitin. However, the pH of the distilled water added to the β -chitin (b $\rightarrow$ a) powder was
215 slightly acidic (pH $\approx$ 4), while on the other hand, the pH in the case of the β -chitin
216 (a $\rightarrow$ b) powder was about 7–8. The degree of *N*-acetylation in both β -chitin (a $\rightarrow$ b) and
217 β -chitin (b $\rightarrow$ a) powder were the same (0.96 ± 0.03). The residual proteins in both β -
218 chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) powders were about 0.08 and 0.16 wt%, respectively
219 (refer to Supplementary data). Therefore, the residual proteins almost did not affect the
220 degree of *N*-acetylation. XRD patterns of both β -chitin powders (Fig. 3) are almost the
221 same and exhibit two diffraction peaks at 8.5 and 19.7°, which correspond to the [010]
222 plane and [1–10] mixed plane, respectively. These results were similar to that of a β -
223 chitin powder reported previously [24]. The CI and *d*-spacing of the β -chitin (a $\rightarrow$ b)
224 powder were almost the same as those found in the β -chitin (b $\rightarrow$ a) powder (Fig. 3).
225 XRD patterns of the α -chitin powder is also shown in Fig. 3 and five diffraction peaks
226 at 9.3, 19.3, 20.9, 23.2, and 26.2°, corresponding to the [020], [110], [120], [130], and
227 [013] planes, respectively, were observed [6]. FT-IR spectra of both β -chitins are almost

228 the same as shown in Fig. 4, and matched that of β -chitin reported previously [24].

229

230 3.2. Characterization of β -Chitin NF

231 The XRD patterns of β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs (Fig. 3) were nearly
232 identical to that of the β -chitin powders, indicating that the β -chitin crystal structure was
233 maintained. However, the CIs of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs were
234 slightly greater than in the corresponding β -chitin powders. In addition, the peak of the
235 [010] plane of both β -chitin NFs was shifted from about 8.5° to 9.0°, indicating a
236 decrease in the d -spacing at the [010] plane from about 10.4 Å to 9.8 Å.

237 Although the XRD patterns between β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs were
238 almost the same, there were clear differences on the transmittances and the viscosities
239 between β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs as follows.

240 The transmittances of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NF dispersions at 0.05
241 wt% were shown in Fig. 5. The transmittance of both dispersions was increased by
242 increasing the pass time. The transmittance of β -chitin (a $\rightarrow$ b) NF dispersions was less
243 than 80% at 10 passes, while the transmittance of β -chitin (b $\rightarrow$ a) NF dispersions
244 reached to 80% at only 5 passes. The β -chitin (b $\rightarrow$ a) powder was disintegrated into a
245 homogeneous NF dispersion more easily than the β -chitin (a $\rightarrow$ b) powder.

246 The viscosities of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NF dispersions at 1 wt%
247 are shown in Table 1. The viscosity of the β -chitin (b $\rightarrow$ a) was similar to what has been
248 previously reported [17]. The viscosity of both dispersions was decreased by increasing
249 the pass time. The viscosity of the β -chitin (b $\rightarrow$ a) NF was 6–8 times higher than that of
250 the β -chitin (a $\rightarrow$ b) NF. The β -chitin (a $\rightarrow$ b) NF dispersion was pulpy and ran off easily

251 when inverted in a container. By contrast, the β -chitin (b $\rightarrow$ a) NF dispersion had a more
252 gel-like character and did not run off when inverted.

253 The molecular weights of the NF dispersions of β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a) are
254 shown in Table 1. The molecular weight of the β -chitin (b $\rightarrow$ a) NF was smaller than that
255 of β -chitin (a $\rightarrow$ b) NF for all pass times.

256

257 *3.3. The State of β -Chitin NF Dispersions in Water*

258 The state of β -chitin NF dispersions was observed by 3 ways, namely HAADF-
259 STEM, FE-SEM, and TEM. HAADF-STEM images are 3D, on the other hand, FE-
260 SEM and TEM images are 2D.

261 HAADF-STEM images of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) are shown in the
262 upper row of Fig. 6. HAADF-STEM 3D images were obtained as videos in this study,
263 and are available in the Supplementary data (Videos S1–4). The width of the β -chitin
264 (a $\rightarrow$ b) NF at 2 passes was approximately 10–25 nm, and thick fibers of over 100 nm in
265 width were also observed. The width of the β -chitin (a $\rightarrow$ b) NF at 10 passes was
266 approximately 8–25 nm. The width of the β -chitin (b $\rightarrow$ a) at 2 passes was approximately
267 3–15 nm. The width of the β -chitin (b $\rightarrow$ a) NF at 10 passes was approximately 3–10 nm.
268 The width of both NFs at 10 passes were thinner and more uniform than in the case of 2
269 passes, and in particular the 3D network structure of the fine β -chitin (b $\rightarrow$ a) NF was
270 uniform and dense. The depth of the replica β -chitin (a $\rightarrow$ b) NF and β -chitin (b $\rightarrow$ a) NF
271 at 10 passes were 610 and 280 nm, respectively.

272 FE-SEM images of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs are shown in the
273 middle row of Fig. 6. The width of the β -chitin (a $\rightarrow$ b) NF at 2 passes was

approximately 20–60 nm, and did not disperse uniformly. Furthermore, thick fibers over 100 nm in width were also observed. The width of the β -chitin (a $\rightarrow$ b) NF at 10 passes was approximately 10–50 nm and was more uniform than in the case of 2 passes. In contrast, the β -chitin (b $\rightarrow$ a) dispersed uniformly at only 2 passes, and the width of the β -chitin (b $\rightarrow$ a) NF was approximately 6–20 nm. The width of the β -chitin (b $\rightarrow$ a) NF at 10 passes was the same as that at 2 passes.

TEM images of the β -chitin (a $\rightarrow$ b) and β -chitin (b $\rightarrow$ a) NFs are shown in the bottom row of Fig. 6. These TEM images show the width of individual NFs within the dispersions. The width of β -chitin (a $\rightarrow$ b) NF at 2 passes was approximately 100–300 nm, and after 10 passes it was approximately 8–20 nm. The width of β -chitin (b $\rightarrow$ a) at 2 passes was approximately 4–7 nm and approximately 5–10 nm at 10 passes.

4. Discussion

For the β -chitin powders, the results of degrees of *N*-acetylation, XRD, and FT-IR indicated that the crystal and chemical structures were basically indifferent to the order of the acid and base treatments. However, for the β -chitin NFs, the increase of CI and the decrease of the *d*-spacing at the [010] plane occurred that were not observed in the β -chitin powders. The increase of CI is likely due to the rearrangement of the NF. When the β -chitin NFs were dried for XRD analysis, the β -chitin NFs would adhere to each other, arranging the contact surface of the NFs. The decrease of the *d*-spacing at the [010] plane is likely due to the desorption of water from the β -chitin crystal structure. When the crystal structure of the β -chitin was changed from the dihydrate to the anhydrous form, the *d*-spacing at the [010] plane decreased from about 11.03 Å to 9.14 Å [25]. In this work, the *d*-spacing of about 10.4 Å (i.e. the diffraction at 8.5°) is a

298 typical of the monohydrate crystal. On the other hand, the *d*-spacing of about 9.8 Å (i.e.
299 the diffraction at 9.0°) observed in the β-chitin NFs would be derived from the
300 intermediate structure between the monohydrate and the anhydrous form. When the β-
301 chitin NFs were dried, the water molecule would be desorbed easier than in the
302 corresponding β-chitin powders because the β-chitin NFs have larger surface area.

303   The molecular weight of the β-chitin (a→b) NF was greater than that of the β-chitin
304 (b→a) NF for all pass times, which is likely due to residual HCl in the purified β-chitin
305 (b→a). As mentioned in the 3.1. Section, the pH of the distilled water added to the β-
306 chitin (b→a) powder was slightly acidic (pH ≈ 4), while the pH in the case of the β-
307 chitin (a→b) powder was about 7–8. This is because the protons are released from the
308 β-chitin (b→a) molecular chains when its powder was soaked in water. In additional
309 experiments shown in the Supplementary data, we washed the β-chitin (b→a) powder
310 with additional water until the pH of the bulk material reached neutral. As a result, the
311 physicochemical properties of the washed β-chitin (b→a) NF were similar to those of
312 the β-chitin (a→b) NF, indicating that HCl remained in the β-chitin (b→a) powder. It
313 has been reported that β-chitin can have small molecules (such as water and HCl)
314 between the β-chitin molecular chains [26–28]. When the purified β-chitin (b→a) was
315 dried at 65 °C, the HCl in β-chitin was condensed. Condensed and heated HCl can
316 potentially cleave glycosidic bonds in β-chitin (i.e. hydrolysis). As a result, the
317 molecular weight of the β-chitin (b→a) NF became smaller than that of the β-chitin
318 (a→b) NF.

319   From the HAADF-STEM observation, the β-chitin (b→a) NF was thinner than the
320 β-chitin (a→b) NF at 2 passes, and all β-chitin (b→a) NFs were less than 100 nm. The

321 thinner β -chitin (b $\rightarrow$ a) would be due to electrostatic repulsions. The β -chitin powder
322 consists of an assembly of the β -chitin NFs [29]. The β -chitin (b $\rightarrow$ a) powder is
323 expected to be cationized due to protons derived from residual HCl between the β -chitin
324 (b $\rightarrow$ a) molecular chains. The electrostatic repulsions between NFs assembled in the
325 cationized β -chitin (b $\rightarrow$ a) powder promoted to disintegrate the powder into NFs,
326 therefore, the β -chitin (b $\rightarrow$ a) NF was less than 15 nm at 2 passes. The residual HCl also
327 increased the local concentration of H⁺ and Cl⁻ ions between β -chitin (b $\rightarrow$ a) NFs after
328 disintegration. To balance the osmotic pressure, the bulk water moves between the β -
329 chitin (b $\rightarrow$ a) NFs, resulting that the β -chitin (b $\rightarrow$ a) NFs could keep uniform and high
330 dispersion. On the other hand, the β -chitin (a $\rightarrow$ b) was not cationized, resulting that
331 there was not the electrostatic repulsion. For β -chitin (a $\rightarrow$ b), the energy given by the
332 Star Burst system at 2 passes was not enough to disintegrate the all powder into NFs
333 less than 100 nm, while it would be enough at 10 passes.

334 The viscosity of the β -chitin (b $\rightarrow$ a) NF was higher than that of the β -chitin (a $\rightarrow$ b)
335 NF, while the molecular weight of the β -chitin (b $\rightarrow$ a) NF was lower than that of the β -
336 chitin (a $\rightarrow$ b) NF as shown in Table 1. In general, the viscosity of dissolved polymers is
337 reduced as the molecular weight decreases [30]. As mentioned above, the β -chitin
338 (b $\rightarrow$ a) and (a $\rightarrow$ b) NF were not dissolved in water and dispersed with maintaining their
339 crystal structure. From HAADF-STEM and FE-SEM observations, the width of the β -
340 chitin (b $\rightarrow$ a) NF was thinner and more uniform than that of the β -chitin (a $\rightarrow$ b) NF,
341 indicating that entanglements of the β -chitin (b $\rightarrow$ a) NFs were higher than those of the
342 β -chitin (a $\rightarrow$ b) NFs. The higher entanglements between the β -chitin (b $\rightarrow$ a) NFs caused
343 the higher viscosity.

344 The transmittance of the β -chitin (b $\rightarrow$ a) NF was higher than that of the β -chitin
345 (a $\rightarrow$ b) NF as shown in Fig. 5. From HAADF-STEM and FE-SEM observations of the
346 β -chitin (a $\rightarrow$ b) NF at 2 passes in Fig. 6, the NFs did not disperse uniformly and thick
347 fibers over 100 nm in width were also observed. There are both dense and sparse spots
348 of the β -chitin (a $\rightarrow$ b) NF. The refraction and reflection of light occur because the
349 refractive indices of β -chitin and water are different, resulting that the transmittance of
350 the β -chitin (a $\rightarrow$ b) NF became low. On the other hand, the fine and uniform 3D network
351 structure of the β -chitin (b $\rightarrow$ a) NF inhibited the light scattering, resulting in an increase
352 of the transmittance.

353 For the first time, we were able to observe 3D images of the β -chitin NF dispersions
354 in water using quick-freeze deep-etch replication and HAADF-STEM. This method has
355 several advantages over more conventional FE-SEM and TEM techniques, as this
356 method can describe the NF dispersion in water due to the freezing sample on the
357 millisecond timescale [31] and reinforcement with a carbon layer, which inhibits NF
358 aggregation. Moreover, this method more accurately reflects the NF concentration.
359 Conversely, conventional FE-SEM methods require pretreatment (e.g. substitution of
360 dispersion medium and centrifugation or hot pressing) before observation. These
361 pretreatments would change the state and shape of NF dispersion. As a result, large
362 amorphous masses are often observed when using FE-SEM, which cannot be classified
363 as to whether not the β -chitin disintegrated or aggregated by centrifuging. For TEM
364 observations, diluting the NF dispersion is a necessary pretreatment step. TEM
365 observations are better suited to determine tertiary structures (i.e. width and length of
366 NF), but they are disadvantageous in regards to quaternary structures (i.e. the state of
367 NF dispersion). Furthermore, the accurate NF concentration is unknown in FE-SEM and

368 TEM observations due to pretreatment. Therefore, the quick-freeze deep-etch
369 replication and HAADF-STEM observation method is a promising method to
370 investigate the actual NF state in water.

371 On the HAADF-STEM (Fig. 6, Video S3, and Video S4), the depth of the β -chitin
372 (b $\rightarrow$ a) NF replica was thinner than that of the β -chitin (a $\rightarrow$ b). When the quick-freeze
373 deep-etch replication process is carried out with the same drying time, the depth of the
374 replica depends on capacity for water retention of sample. If water hardly sublimates, 3D
375 replica becomes thin, indicating that the thin sample has a high capacity for water
376 retention. Therefore, the β -chitin (b $\rightarrow$ a) NF has better water retention than the β -chitin
377 (a $\rightarrow$ b) NF; as the dense structure of the β -chitin (b $\rightarrow$ a) NF traps water in this 3D
378 network structure.

379

380 **5. Conclusions**

381 We revealed the effect of the purification treatment order of β -chitin from squid pen
382 on the physicochemical properties of the β -chitin NF. Two types of β -chitin were
383 prepared, with the β -chitin (a $\rightarrow$ b) treated by acid and base (in order) and the β -chitin
384 (b $\rightarrow$ a) treated in the opposite order. For the powder form, the chemical and crystal
385 structures of the β -chitin were almost the same regardless of treatment order. However,
386 in the NF form, the treatment order significantly affected the physicochemical
387 properties of the NFs. The β -chitin (b $\rightarrow$ a) NF dispersion showed higher transmittance
388 and higher viscosity than the β -chitin (a $\rightarrow$ b) NF dispersion. In addition, we have
389 demonstrated 3D image analysis of the β -chitin NF dispersions for the first time and it
390 showed the dispersion state of β -chitin (b $\rightarrow$ a) NF was a denser and more uniform in

391 water than that of the β -chitin (a $\rightarrow$ b) NF. The width of the β -chitin (b $\rightarrow$ a) NF was
392 approximately 3–10 nm and that of the β -chitin (a $\rightarrow$ b) NF was approximately 8–25 nm
393 at 10 passes. For the β -chitin (b $\rightarrow$ a), residual HCl in the β -chitin crystals was released
394 to elutriation, which then cationized the β -chitin NFs. The cationized β -chitin (b $\rightarrow$ a)
395 NFs have the electrostatic repulsions each other, resulting in an increase of the
396 dispersibility, transmittance, and viscosity.

397

398   **Acknowledgements**

399   This work was supported in part by JST Program for Revitalization Promotion
400   [grant number H24 Mori II-21]; JSPS KAKENHI [grant number 15K17908].

401   We thank Marutatsu Kamasui Co., Ltd for supplying the squid pen used in this
402   study.

403

404   **References**

- 405   [1] Y. Maeda, R. Jayakumar, H. Nagahama, T. Furuike, H. Tamura, *Int. J. Biol.*
406   *Macromol.* 42 (2008) 463–467.
- 407   [2] S. Gautier, E. Xhauftaire-Uhoda, P. Gonry, G.E. Pierard, *Int. J. Cosmet. Sci.* 30
408   (2008) 459–469.
- 409   [3] L.K. Han, Y. Kimura, H. Okuda, *Int. J. Obes.* 23 (1999) 174–179.
- 410   [4] R. Jayakumar, M. Prabakaran, S.V. Nair, H. Tamura, *Biotechnol. Adv.* 28 (2010)
411   142–150.
- 412   [5] B. Ding, J. Cai, J. Huang, L. Zhang, Y. Chen, X. Shi, Y. Du, S. Kuga, *J. Mater.*
413   *Chem.* 22 (2012) 5801–5809.
- 414   [6] P. Sikorski, R. Hori, M. Wada, *Biomacromolecules* 10 (2009) 1100–1105.
- 415   [7] D. Sawada, Y. Nishiyama, P. Langan, V. T. Forsyth, S. Kimura, M. Wada, *PLoS One*
416   7 (2012) e39376.
- 417   [8] Y. Nishiyama, Y. Noishiki, M. Wada, *Macromolecules* 44 (2011) 950–957.
- 418   [9] D. Sawada, Y. Nishiyama, P. Langan, V.T. Forsyth, S. Kimura, M. Wada,
419   *Biomacromolecules* 13 (2012) 288–291.
- 420   [10] C. Unterberger, F. Lubert, A. Demmel, K. Gruenwald, I. Huber, K.-H. Engel, U.
421   Busch, *Eur. Food Res. Technol.* 239 (2014) 559–566.
- 422   [11] C. Chen, D. Li, H. Yano, K. Abe, *Cellulose* 21 (2014) 3339–3346.
- 423   [12] I.F. Nata, S.S.-S. Wang, T.-M. Wu, C.-K. Lee, *Carbohydr. Polym.* 90 (2012) 1509–
424   1514.
- 425   [13] R. Izumi, S. Komada, K. Ochi, L. Karasawa, T. Osaki, Y. Murahata, T. Tsuka, T.
426   Imagawa, N. Itoh, Y. Okamoto, H. Izawa, M. Morimoto, H. Saimoto, K. Azuma, S.
427   Ifuku, *Carbohydr. Polym.* 123 (2015) 461–467.

- 428 [14] K. Azuma, T. Osaki, T. Wakuda, S. Ifuku, H. Saimoto, T. Tsuka, T. Imagawa, Y.
429 Okamoto, S. Minami, Carbohydr. Polym. 87 (2012) 1399–1403.
- 430 [15] Y. Fan, H. Fukuzumi, T. Saito, A. Isogai, Int. J. Biol. Macromol. 50 (2012) 69–76.
- 431 [16] S. Ifuku, M. Nogi, K. Abe, M. Yoshioka, M. Morimoto, H. Saimoto, H. Yano,
432 Biomacromolecules 10 (2009) 1584–1588.
- 433 [17] A.K. Dutta, H. Izawa, M. Morimoto, H. Saimoto, S. Ifuku, Journal of Chitin and
434 Chitosan Science 1 (2013) 186–191.
- 435 [18] R. Kose, T. Kondo, Sen'i Gakkaishi. 67 (2011) 91–95.
- 436 [19] S. Ifuku, K. Yamada, M. Morimoto, H. Saimoto, J. Nanomater. 2012 (2012) 1–7.
- 437 [20] Y. Watanabe, S. Kitamura, K. Kawasaki, T. Kato, K. Uegaki, K. Ogura, K.
438 Ishikawa, Biopolymers 95 (2011) 833–839.
- 439 [21] S. Hunt, M. Nixon, Comp. Biochem. Physiol., Part B: Biochem. Mol. Biol. 68B
440 (1981) 535–546.
- 441 [22] D.K. Youn, H.K. No, W. Prinyawiwatkul, Int. J. Food Sci. Technol. 48 (2013) 571–
442 577.
- 443 [23] Y. Zhang, C. Xue, Y. Xue, R. Gao, X. Zhang, Carbohydr. Res. 340 (2005) 1914–
444 1917.
- 445 [24] Y. Fan, T. Saito, A. Isogai, Biomacromolecules 9 (2008) 1919–1923.
- 446 [25] K. Kobayashi, S. Kimura, E. Togawa, M. Wada, Carbohydr. Polym. 79 (2010) 882–
447 889.
- 448 [26] Y. Saito, J.-L. Putaux, T. Okano, F. Gaill, H. Chanzy, Macromolecules 30 (1997)
449 3867–3873.
- 450 [27] J. Blackwell, Biopolymers 7 (1969) 281–298.
- 451 [28] Y. Saito, T. Okano, F. Gaill, H. Chanzy, J.-L. Putaux, Int. J. Biol. Macromol. 28

452 (2000) 81–88.

453 [29] F.-C. Yang, R.D. Peters, H. Dies, M.C. Rheinstadter, *Soft Matter* 10 (2014) 5541–
454 5549.

455 [30] M. Terbojevich, C. Carraro, A. Cosani, E. Marsano, *Carbohydr. Res.* 180 (1988)
456 73–86.

457 [31] T. Nakata, K. Sobue, N. Hirokawa, *J. Cell Biol.* 110 (1990) 13–25.

458

459 **Appendix A. Supplementary data**

460 Further information on residual proteins in the purified β -chitin can be found in S–1
461 and Table S1. The HAADF-STEM 3D videos of the 1 wt% β -chitin (a→b) (Videos S1
462 and S3) and β -chitin (b→a) (Videos S2 and S4) NF dispersions at 10 passes are
463 available. Further information on residual HCl in the β -chitin (b→a) can be found in S–
464 3 and Figs. S1–3. Their data can be found, in the online version.

465

466 **Tables**

467 Table 1. The viscosity at 1 wt% and the molecular weights of the β -chitin (a $\rightarrow$ b) and
 468 (b $\rightarrow$ a) NF dispersions.

Sample	Pass times	Viscosity (mPa·s)	Molecular weights (kDa)
β -chitin (a $\rightarrow$ b)	2	490	1800
	5	330	1730
	10	310	1450
β -chitin (b $\rightarrow$ a)	2	3100	1150
	5	2700	1240
	10	2000	1180

469

470

471 **Figure Captions**

472 Fig. 1. Purification methods of the β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a) from squid pen.

473

474 Fig. 2. Wet pulverization system using a water jet, also referred to as the Star Burst
475 system.

476

477 Fig. 3. X-ray diffraction patterns of the β -chitin (a $\rightarrow$ b), (b $\rightarrow$ a), and α -chitin powder and
478 their NFs (except for α -chitin). CI is crystallinity index (see Eq. 2), and d is d -spacing at
479 [010] plane (for α -chitin powder, d -spacing at [020] plane).

480

481 Fig. 4. FT-IR spectra of the β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a) powders.

482

483 Fig. 5. The transmittance spectra of the β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a) NF dispersions at
484 0.05 wt%

485

486 Fig. 6. Images of the NF dispersions of the β -chitin (a $\rightarrow$ b) and (b $\rightarrow$ a). In HAADF-
487 STEM, β -chitin NF dispersions was 1 wt%.

488

489

490 **Figs. 1-6 were provided as PowerPoint file**

491

Fig. 1

Effect of Purification Method of β -Chitin from Squid Pen on the Properties of β -Chitin Nanofibers

Fig. 2

Effect of Purification Method of β -Chitin from Squid Pen
on the Properties of β -Chitin Nanofibers

Fig. 3

Effect of Purification Method of β -Chitin from Squid Pen on the Properties of β -Chitin Nanofibers

Fig. 4

Effect of Purification Method of β -Chitin from Squid Pen
on the Properties of β -Chitin Nanofibers

Fig. 5

Effect of Purification Method of β -Chitin from Squid Pen on the Properties of β -Chitin Nanofibers

Fig. 6

Effect of Purification Method of β -Chitin from Squid Pen on the Properties of β -Chitin Nanofibers