Size-controlled Production of Quinacridone Nanocrystals using Hot Compressed Water

Recrystallization

Kiwamu Sue^{1,2, *}, Toshihiko Usami², Kunio Arai², Hitoshi Kasai³, Hachiro Nakanishi³,
Toshihiko Hiaki¹

1 Department of Applied Molecular Chemistry, College of Industrial Technology, Nihon University, 1-2-1 Izumi-cho, Narashino, Chiba, 275-8575, Japan

2 Graduate School of Environmental Studies, Tohoku University, Aoba 6-6-07, Aramaki, Aoba-ku, Sendai, 980-8579, Japan

3 Institute of Multidisciplinary Research for Advanced Materials, Tohoku University, Katahira 2-1-1, Sendai, 980-8577, Japan

Corresponding Author

Kiwamu Sue

Department of Applied Molecular Chemistry, College of Industrial Technology, Nihon University

1-2-1 Izumi-cho, Narashino, Chiba 275-8575 Japan

TEL & FAX : +81-47-474-2552

E-mail : k5sue@cit.nihon-u.ac.jp

Abstract

Continuous production of quinacridone nanocrystals via a hot compressed water (HCW) recrystallization method was studied using a flow-through experimental apparatus at 24 MPa at temperatures from 523 to 573 K. Quinacridone crystals were dissolved in HCW and precipitation was initiated by mixing with room temperature water (RTW), which gave the nanocrystalline product. Polyoxyethylene lauryl ether and sodium dodecyl sulphate were found to be useful for reducing aggregation of the nanocrystals. The effects of temperature and flow rate on the size of the crystals was examined; increasing the degree of supersaturation caused to crystals to decrease in size. Nanocrystals that had an average diameter of ca. 36 nm could be obtained at 573.8 K and 24 MPa at a flow rate of 10 g min⁻¹ for HCW and 100 g/min for RTW.

KEYWORDS: Quinacridone, Nanocrystal, Reprecipitation, High Temperature, Water

Introduction

Nanoscale organic crystals are attracting attention in both industry and academia because of specific properties such as colour and electroluminescence. Several synthetic methods have been proposed for such materials, such as laser ablation [1], sol-gel [2], and reprecipitation [3,4]. We previously reported a hot compressed water (HCW) recrystallization method as a possible technique for preparing organic nanocrystals [5-7] according to which, HCW, which has a low dielectric constant (ϵ) of between 5 and 50, is used to form a saturated or supersaturated solution that is mixed with water at room temperature to initiate solute precipitation [8]. Many organic compounds that are sparingly soluble in room temperature water can dissolve easily in HCW[8,9]. From the viewpoint of green chemistry, HCW has the potential to reduce the use of organic solvents and to control solubility. In the recrystallization method, organic crystals are dissolved in HCW within a saturation cell; nanocrystals are formed by mixing the saturated or supersaturated high-temperature organic, aqueous solution with a cooling solvent in a mixing tee. The cooling solvent can be pure solvents or an appropriate mixture of water, acetone, ethanol, or methanol. The size of the nanocrystals can be controlled by changing the saturation temperature and composition of the cooling solvent. Although studies have been made of the HCW recrystallization method [5-7,10], the

precipitation mechanism is unclear. To translate the method to an industrial scale, it would be useful to understand the relationship between particle size and the experimental factors associated with nucleation, crystal growth and solubility.

This paper concerns the production of quinacridone nanocrystals by HCW recrystallization and their analysis on the basis of the degree of supersaturation.

Quinacridone is a well known pigment used in inkjet and laser printers, for which, the control of particle size within the nano range is important for industrial applications [11].

Quinacridone has high thermal stability and its solubility in a variety of solvents is well known [9].

Experimental

β -quinacridone crystals was purchased from Tokyo Kasei Kogyo with a purity of 94 % and an average diameter of 1.8 μm , as measured by TEM. Ultrapure water (resistivity > 0.18 $\text{M}\Omega\cdot\text{m}$) was used for dissolution of the crystals in both the saturation and cooling solvents. Sodium dodecyl sulfate (SDS, Purity>98%) and 30t% polyoxyethylene(23) lauryl ether (POE) solution (Brij 35) were used as dispersants and were supplied by Kishida Chemical and Alfa Aesar, respectively. Both POE and SDS, were used at a concentration of 0.4, 0.8 or 1.6% in the cooling solvent.

Fig. 1 shows the flow-through experimental apparatus for production of the quinacridone nanocrystals. Ultrapure water was fed by a high-pressure pump 1 at a constant flow rate of 10 g min^{-1} and it was heated to the desired temperature with a preheater. The preheated water was allowed to flow into the saturator cell that contained 25 g of crystals. The cell was fitted with a 0.5 μm sintered stainless steel filter to retain any free quinacridone crystals. After the solution became saturated with quinacridone crystal [9], the solution was mixed with cooling solvent that contained POE or SDS surfactant at the mixing point. The cooling solvent was fed by pump 2 at flow rates of 10 - 100 g min^{-1} . The effluent was quenched to room temperature after the mixing point with an external water jacket.

The temperature in the cell was maintained within ± 0.1 K using a sheathed heater located along the inner wall. The saturation temperature is referred to as T and the solution temperature after mixing as T_0 . The system pressure was maintained at 24 ± 0.1 MPa with a back pressure regulator that was placed subsequent to the cooler.

The tubing (o.d. 1.58 mm, i.d. 0.59 mm) used in the main part of the apparatus was made of 316 stainless steel; a 1/16" tee (i.d. 0.3 mm) made of 316 stainless steel was used for the mixing point. The micro heater and 316 stainless steel tubing (o.d. 1.58 mm, i.d. 0.13 mm) were used to reduce precipitation and plugging in the tube between the saturation cell and the mixing tee that occurred as a result of decreasing temperature and flow velocity. The details of the saturation cell have been described previously [9]. To ensure that the solutions became saturated, the rotation speed of the electromagnetic stirrer was set to 1000 rpm [9].

After cooling and depressurization, the precipitated crystals were collected in a glass flask as a slurry. The solids in the effluent solution were filtered by a membrane filter, washed with pure water and dried at 333 K in an oven for 24 h. The products were observed using transmission electron microscopy (TEM, Tecnai20, Tecnai). The average particle size was determined by dynamic light scattering (DLS, DLS-6000AL, Otsuka

Electronics) and the crystal structure was analyzed by UV/VIS spectrophotometry (V-570, JASCO).

Results and Discussion

Experimental results are summarized in Table 1 from which it is apparent that the flow after mixing was turbulent with the result that the saturated solution and cooling solvent were rapidly mixed, which caused abrupt crystallization. The rapid cooling probably led to the small particle sizes shown in Table 1. The Reynolds number obtained just after the mixing tee was calculated using pure water from the flow velocities. Typical results (run 13) for TEM measurements are shown in Fig. 2. The crystal sizes determined using TEM and DLS measurements for run 13 were 50 nm and 91 nm, respectively. It is apparent that crystal size depends on the analytical method used. Typical results of absorption spectra of the quinacridone crystals dispersed in liquid are shown in Fig. 3. The absorption spectrum in the case of POE can be assigned to the single phase β -form (stable phase) of the quinacridone crystal [12]. No significant differences in absorption spectra were observed for various POE concentrations. In contrast, the absorption spectrum with SDS can be assigned to the single phase α -form (metastable phase) of the quinacridone crystal [12]; no significant differences were found in the absorption spectra for the other SDS concentrations used.

In previous work in the absence of dispersant [10], large crystals of average size 1691 nm were obtained due to strong aggregation; in contrast, the present work has shown that the

addition of dispersants reduced aggregation of the precipitated nanocrystals and allowed the formation of small crystals with an average size of 85 - 241 nm. An increase in dispersant concentration lowered crystal size, as shown in Table 1. In previous work [10], the form of the crystals obtained changed from the α -form to the β -form as the cooling water flow rate decreased. Generally, the transition from the metastable to the stable phases proceeds at high temperatures. Precipitation at high cooling water flow rates promoted formation of the metastable α -form of the crystals. In contrast, precipitation at low cooling water flow rates gave the stable β -form, probably due to the crystals having been kept at a relatively high temperature that allowed phase transition from the α - to the β -form. The crystal form of the products seemed to strongly depend on the cooling rate during precipitation. The surfactants, SDS and POE, provided stabilization of the dispersion by electrostatic repulsive forces and steric hindrance. Generally, the thermal diffusivity of water is higher than that of organic molecules such as hydrocarbons.[2] Since POE has a longer aliphatic chain than SDS, its greater hydrophobic nature prevents some water molecules from having close interactions. Thus, it seems possible that in the case of POE, β -crystals are produced by a slow cooling rate and phase transition occurs during the prolonged duration at high temperature. In contrast, the α -form is secured using SDS as a result of rapid quenching rates most likely

because of the greater quantity of water that would be attracted to the surfactant / particle precipitants.

Supersaturation S^* is the driving force for precipitation and it is defined by the following relationship [13]:

$$S^* = \ln \frac{S}{S_0} \quad (1)$$

where S and S_0 denote solubility at saturation temperature T and that at temperature after cooling T_0 , respectively. On the basis of nucleation theory [13], the diameter of a critical nucleus D^* can be expressed as:

$$D^* = \frac{4\sigma v_s}{kTS^*} \quad (2)$$

where σ , v_s , and k are the interfacial tension of the solute [N/m], the solute molecular volume in the solid phase [m³], and the Boltzmann constant [1.38x10⁻²³ nm/K], respectively. On the basis of eq 2, increasing supersaturation should give smaller particles. For example, increasing the cooling water flow rate from 10 g/min to 100 g/min at a given temperature decreases particle size (runs 1-12) and smaller nanocrystals are produced of average particle diameter 36 nm at a saturation temperature of 573.8 K and cooling water flow rate of 100 g/min (run 12). **Quinacridone solubilities in high-temperature water without dispersants** were taken from the literature [9]. Fig. 4

shows the relationship between temperature after cooling T_0 and supersaturation at temperature T determined from eq 1. As shown in Fig. 4, supersaturation increased linearly with decreasing temperature after cooling, which shows the importance of rapid cooling for the production of nanocrystals. Fig. 5 shows the relationship between supersaturation $1/S^*$ and mean particle size; as the degree of supersaturation increased, the mean particle size decreased in accordance with eq 2.

Conclusions

Quinacridone nanocrystals could be produced using hot compressed water recrystallization. The effects of saturation temperature and cooling water flow rate on particle size was analyzed on the basis of supersaturation and it was found that small nanocrystals with a mean diameter of 36 nm were obtained at a supersaturation ($1/S^*$) value <0.09 .

Acknowledgements

The authors gratefully acknowledge support for this research by a grant from the CREST (Core Research for Evolution Science and Technology) of Japan Science and Technology Corporation (JST) and also a grant from the Ministry of Education, Culture, Sports, Science, and Technology to promote multi-disciplinary research projects.

Literature Cited

- [1] Sanz N, Baldeck PL, Ibanez A. Organic nanocrystals embedded in sol-gel glasses for optical applications. *Synth. Met.* 2000;115: 229-34.
- [2] Tamaki Y, Asahi T, Masuhara H. Solvent-dependent size and phase of vanadyl phthalocyanine nanoparticles formed by laser ablation of VOPc crystal-dispersed solution. *Jpn. J. Appl. Phys.* 2003;42:2725-29.
- [3] Kasai H, Nalwa HS, Oikawa H, Okada S, Matsuda H, Minami N, Kakuta A, Ono K, Mukoh A, Nakanishi H. A novel preparation method of organic microcrystals. *Jpn. J. Appl. Phys.* 1992;31: L1132-34.
- [4] Katagi H, Kasai H, Okada S, Oikawa H, Matsuda H, Nakanishi H. Preparation and characterization of poly-diacetylene microcrystals. *J. Macromol. Sci.-Pure Appl. Chem. A* 34 1997;10:2013-24.
- [5] Komai Y, Kasai H, Hirakoso H, Hakuta Y, Katagi H, Okada S, Oikawa H, Adschiri T, Inomata H, Arai K, Nakanishi H. Preparation of organic microcrystals using supercritical fluid crystallization method. *Jpn. J. Appl. Phys.* 1999;38:L81-83.
- [6] Li B, Kasai H, Oikawa H, Okada S, Arai K, Nakanishi H. Fabrication and characterization of quinacridones nanocrystals by high-temperature and high-pressure crystallization method. *Int. J. Nanosci.* 2002;1:587-92.
- [7] Li B, Kasai H, Oikawa H, Okada S, Arai K, Nakanishi H. Monodispersed quinacridone nanocrystals prepared by a high-temperature and high-pressure liquid crystallization method. *J. Nanosci. Nanotech.* 2003;3:365-7.
- [8] Fernandez DP, Goodwin ARH, Lemmon EW, Sengers JMHL, Williams RC. A formulation for the static permittivity of water and steam at temperatures from 238 K to 873 K at pressures up to 1200 MPa, including derivatives and Debye-Hückel coefficient. *J. Phys. Chem. Ref. Data* 1997;26:1125-66.
- [9] Sue K, Usami T, Arai K, Kasai H, Nakanishi H, Hiaki T. Quinacridone solubility in hot-compressed water. *submitted to J. Chem. Eng. Data.*
- [10] Sue K, Usami T, Arai K, Kasai H, Nakanishi H, Hiaki T. Continuous production of quinacridone

nanocrystals and control of crystal form by a high-temperature water crystallization method. Jpn. J. Appl. Phys. 2006;45(No. 1B):375-378.

[11] Lincke G. A review of thirty years of research on quinacridones. X-ray crystallography and crystal engineering. Dyes and Pigments 2000;44:101-22.

[12] Filho DS, Oliveira CMF. Crystalline modifications of linear *trans*-quinacridone pigments. J. Mater. Sci. 1992;27:5101-7.

[13] Türk M. Influence of thermodynamic behaviour and solute properties on homogeneous nucleation in supercritical solutions. J. Supercrit. Fluids 2000;18:169-84.

Table 1. Experimental Conditions and Results

Run No.	F_{RTW} [g/min]	T [K]	T_0 [K]	Surfactant [*] [wt%]	Re [-]	D_m [nm]	S^* [-]
1	10	523.0	411.8	0.8	6890	241	4.9
2	20	523.1	377.7	0.8	7280	140	6.0
3	50	523.5	335.6	0.8	8960	72	7.6
4	100	523.2	318.0	0.8	12230	90	8.4
5	10	548.5	411.5	0.8	7650	102	6.5
6	20	548.0	367.6	0.8	8000	87	7.8
7	50	548.3	331.2	0.8	9590	53	9.3
8	100	547.7	316.0	0.8	12810	60	10.1
9	10	562.4	427.4	0.8	8080	116	7.1
10	20	573.7	377.8	0.8	8800	104	9.1
11	50	573.2	336.6	0.8	10270	64	10.7
12	100	573.8	320.9	0.8	13460	36	11.5
13	20	574.6	386.5	0.4	8840	91	9.1
14	20	573.1	375.6	1.6	8790	85	9.5
15	20	574.6	386.5	0.4	8820	223	9.3
16	20	573.2	375.1	1.6	8790	167	9.7
17 ^{**}	20	574.6	386.5	0.0	8840	1691	9.1

^{*} All runs used POE except for runs 15 and 16 that used SDS

^{**} Data from our previous work [10]

Figure 1. Schematic diagram of experimental set-up for quinacridone fabrication

Figure 2. TEM observation of fabricated nanocrystals at saturation temperature of 574.6 K
(run 13)

Figure 3. . Absorption spectra of quinacridone nanocrystals dispersion liquid at 574.6 K with a) 0.4 wt% POE (run 13) and b) 0.4 wt% SDS (run 15). Circle and triangle denote the α and β crystal forms, respectively.

Figure 4. Estimated supersaturation as a function of saturation temperature and temperature after cooling. Solid, dashed, and dotted lines represents the saturation temperatures of 573 K, 548 K and 523 K, respectively.

Figure 5 Comparison between mean particle size and supersaturation at given saturation temperature. Circle, triangle and square denote the saturation temperature of 523 K, 548 K, and 573 K, respectively.