New Simple Panchromatic Dyes Based on Thiadiazolo[3,4-*c*]pyridine Unit for Dye-Sensitized Solar Cells

Yong Hua,^{a,b} Hongda Wang,^a Xunjin Zhu^{a,b,*} Ashraful Islam,^c Liyuan Han,^c Chuanjiang Qin,^{c,*} Wai-Yeung Wong,^{a,b,*} Wai-Kwok Wong^{a,b,*}

^a Department of Chemistry and Institute of Molecular Functional Materials, Hong Kong Baptist University, Waterloo Road, Kowloon Tong, Hong Kong (P.R. China)
Fax: (+852)34117348, E-mail: xjzhu@hkbu.edu.hk, wkwong@hkbu.edu.hk, wywong@hkbu.edu.hk

^b Changshu Research Institute of Hong Kong Baptist University, Changshu, Jiangsu Province, 215500, P. R. China

^c Photovoltaic Materials Unit, National Institute for Materials Science, Sengen 1-2-1, Tsukuba, Ibaraki (Japan). Fax: (+81) 29-859-2304, E-mail: roverqin@gmail.com

Abstract: Three new organic D-A- π -A photosensitizers with thiadiazolo[3,4-*c*]pyridine moiety incorporated between non-planar triarylamine and cyanoacrylic acid, have been developed and applied in dye-sensitized solar cells. It has been demonstrated that the incorporation of electron-withdrawing thiadiazolo[3,4-*c*]pyridine unit can effectively tune the HOMO and LUMO energy levels, extending the absorption spectra into the deep-red region and covering the whole visible region. The photoresponse of the cells based on the three dyes reached above 800 nm, a value which is comparable to the incident photon-to-current conversion efficiency onset of the established dye N719. Typically, three different bulky electron-donating units such as triphenylamine (D1), *N,N*-bis(9,9-dimethylfluoren-2-yl)aniline (D2) and 4-(hexyloxy)-*N*-(4-(hexyloxy)phenyl)-*N*-phenylaniline (D3) were utilized to investigate their influences on the photovoltaic performances of DSSCs. The results indicate that the introduction of the strongest electron-donating 4-(hexyloxy)-*N*-(4-(hexyloxy)phenyl)-*N*-phenylaniline unit can further red-shift the

intramolecular charge transfer band and enhance light-harvesting properties, as well as retard electron recombination between electrons at the TiO_2 and oxidized species of dye or I_3^- in the electrolyte. Under simulated AM 1.5G irradiation, the cell based on the dye derived from 4-(hexyloxy)-*N*-(4-(hexyloxy) phenyl)-*N*-phenylaniline produced a short-circuit photocurrent of 14.19 mA cm^{-2} , an open-circuit photovoltage of 0.462 V, a fill factor of 0.64, corresponding to a power conversion efficiency of 4.20%. Though the power conversion efficiency is still low, the methodology of tuning the HOMO and LUMO energy levels by incorporation of an electron-withdrawing thiadiazolo[3,4-*c*]pyridine unit in such D–A– π –A dyes could be generally applied to design more efficient panchromatic sensitizers in DSSCs.

Keywords: thiadiazolo[3,4-*c*]pyridine, triarylamine, photosensitizer, dye-sensitized solar cells, panchromatic

1. Introduction

Dye-sensitized solar cells (DSSCs), referred to as the promising alternative to conventional semiconductor silicon-based solar cells, have been pioneered by Grätzel and co-workers in the last decade [1]. A DSSC is composed of a wide band gap semiconductor deposited on a translucent conducting substrate, an anchored molecular sensitizer, and a redox electrolyte (usually the I^-/I_3^- couple is found in most of the “conventional” DSSCs). While the total efficiency of the DSSC depends on the optimization and compatibility of each of its constituents, the initial requirement is that the photosensitizer should capture as many photons from sunlight as possible. Hence, the molecular design of a single photosensitizer with panchromatic light-harvesting characteristics is very crucial for highly efficient DSSCs. Towards this goal, a variety of panchromatic sensitizers have been investigated for applications in DSSCs. The ruthenium (II)-based panchromatic dye, coded as “black dye” (Figure 1) has ever been developed in which the ruthenium center is coordinated to a monoprotonated tricarboxyterpyridine ligand and three thiocyanate ligands. The spectrum response of the “black dye” covers the whole visible range and extends into

the near-infrared (NIR) region up to 920 nm, corresponding to a power conversion efficiency (PCE) of 11.1% using a high-haze TiO₂ electrode [2]. Metallophthalocyanines (MPcs) show potential as NIR photosensitizers because of their intense Q bands ($\lambda = 600\text{--}700$ nm), high molar extinction coefficients ($\epsilon > 100\,000\text{ M}^{-1}\text{cm}^{-1}$), and good thermal, chemical, and photolytic stabilities [3]. However, MPc photosensitizers displayed rather low conversion efficiencies in DSSCs. The major factors for the low efficiency of MPcs were the formation of aggregates on the surface of the TiO₂ crystal and the lack of electron transfer directionality in the excited state. On the other hand, some metal-free organic photosensitizers such as squaraine [4], cyanine [5], and bodipy [6] have been applied in DSSCs for their good absorption bands in the NIR region. Specifically, squaraine-based photosensitizers absorb strongly in the NIR spectroscopic region and the most-efficient squaraine dye to date, YR6 (Figure. 1), showed a PCE of 6.7%, as well as a good incident photon-to-current conversion efficiency (IPCE >50%) in the range of 450–700 nm [7]. Recently, the strong electron acceptor benzothiadiazole unit was incorporated between donor and anchor unit to propose a novel donor–acceptor– π -spacer–acceptor (D–A– π –A) configuration for metal-free organic sensitizers. The incorporated additional acceptor of benzothiadiazole unit in the π -conjugation can improve the distribution of donor electrons to enhance the photostability of indoline compounds, and red-shift the absorption spectra into the NIR region, resulting in high PCEs [8]. Another electron-deficient unit, thiadiazolo[3,4-*c*]pyridine (PyT), has also been explored as a strong electron acceptor in the design of polymers and small molecules with relatively lower HOMO–LUMO bandgaps for efficient organic bulk heterojunction photovoltaic solar cells [9]. It has been shown that these molecules containing the PyT unit have stronger intermolecular interactions to extend their optical absorption into the NIR region to maximize photon absorption. To the best of our knowledge, organic photosensitizers based on PyT have so far not been investigated in DSSC applications.

In this article, three new organic D–A– π –A photosensitizers with PyT moiety incorporated between a non-planar triarylamine and a cyanoacrylic acid, have been

developed and applied in DSSCs (Figure. 2). As expected, the spectrum responses of the DSSCs based on the three dyes covered the whole visible region and reached above 800 nm (Figure. 1). Typically, different bulky triarylamine units such as triphenylamine (D1), *N,N*-bis(9,9-dimethylfluoren-2-yl)aniline (D2) and 4-(hexyloxy)-*N*-(4-(hexyloxy)-phenyl)-*N*-phenylaniline (D3) were utilized as donor units to investigate their influence on the photovoltaic performances of DSSCs. While the highest PCE of 4.20% is low, the methodology of tuning the HOMO or LUMO energy levels by incorporation of PyT in such D–A– π –A dyes could be generally applied to design more efficient panchromatic photosensitizers in DSSCs.

2. Experimental Section

2.1. Materials and Reagents

All solvents and reagents were purchased from Sigma-Aldrich Company and used as received without further purification. Optically transparent FTO-conducting glass electrodes (Nippon Sheet Glass Co., Japan) with a sheet resistance of 8–10 $\Omega \text{ m}^{-2}$ and an optical transmission of greater than 80% in the visible-light range were used and cleaned using a standard procedure. A main transparent layer (12 μm) with titania particles (about 20 nm) and a scattering layer (4 μm) with titania particles (about 400 nm) were screen-printed onto the fluorine-doped tin oxide (FTO)-conducting glass substrate.

2.2. Instruments and Characterization

^1H and ^{13}C NMR spectra were recorded with a Bruker Ultrashield 400 Plus NMR spectrometer. The UV-visible absorption spectra of these dyes were measured in CH_2Cl_2 solution with a Varian Cary 100 UV-Vis spectrophotometer. High-resolution matrix-assisted laser desorption/ionization time of flight (MALDI-TOF) mass spectra were obtained with a Bruker Autoflex MALDI-TOF mass spectrometer. The cyclic voltammograms (CVs) were measured with Versastat II electrochemical work station using a normal three-electrode cell with a Pt working electrode, a Pt wire counter electrode and an Ag/Ag^+ reference electrode. The supporting electrolyte used is 0.1 M

tetra-*n*-butylammonium hexafluorophosphate in CH₂Cl₂ solution. The potential of the reference electrode was calibrated by ferrocene after each set of measurements, and all potentials mentioned in the work were against normal hydrogen electrode. The photocurrent–voltage (*J*–*V*) curves of the DSSCs were measured by using a digital source meter (2400, Keithley) under standard air mass (AM 1.5) with simulated solar illumination at 100 mW cm^{−2} (WXS-90SL2, Wacom). Monochromatic incident-photon-to-current-conversion efficiency (IPCE) spectra were measured with monochromatic incident light of 1×10^{16} photons cm^{−2} in DC mode (CEP-2000 BX, Bunko-Keiki). During the *J*–*V* and IPCE measurements, a black mask and edge were used with an aperture area of 0.25 cm². Charge-extraction from TiO₂ was calculated by integration of the transient current that was detected when the laser illumination was turned off and the DSSCs was simultaneously stepped from open-circuit to short-circuit. Intensity-modulated photovoltage spectroscopy of the open circuit was carried out by using a combination of sinusoidal low-intensity-modulated illumination from a green diode laser (Cobolt Co., Stockholm, Sweden, Samba, 532 nm, 50 mW) band constant-bias light illumination from a Xe lamp (Ushio, Tokyo, Japan, UXL-500D-O), which was attenuated (if necessary) with a neutral-density filter. An acoustic optical modulator (Isomet Co., Springfield, VA, 1205 C-1) was used to produce sinusoidal modulation of a laser beam. Electrochemical-impedance spectroscopy (EIS) measurements of all of the DSSCs were performed on a Zahner IM6e Impedance Analyzer (ZAHNER-Elektrik GmbH & CoKG, Kronach, Germany). The frequency range was 0.1 Hz–100 kHz. The magnitude of the alternative signal was 10 mV. The applied voltage bias was −0.68 V.

2.3. Fabrication of Dye-Sensitized Solar Cells

A main transparent layer (12 μm) with titania particles (about 20 nm) and a scattering layer (4 μm) with titania particles (about 400 nm) were screen-printed onto the fluorine-doped tin oxide (FTO)-conducting glass substrate. The films were then sintered at 500 °C for 1 h. The thickness of the films was measured on a Surfcom 1400A surface profiler (Tokyo Seimitsu Co. Ltd.). The films were treated with a 0.1 M aqueous solution of HCl before examination. Coating of the titania films was

carried out by immersion in a 3×10^{-4} M solution of the sensitizers in MeCN/*t*BuOH (1:1, v/v) for 24 h. The dye-covered TiO₂ electrode and the Pt counter electrode were assembled into a sandwich-type cell and sealed with a hot-melt gasket (thickness: 25 μ m) that was made of the ionomer Surlyn1702 (DuPont). Finally, the electrolyte, which consisted of 0.6M 1-methyl-3-propylimidazolium iodide (MPIImI), 0.1M LiI, 0.05 M I₂, and 0.5 M *tert*-butylpyridine in MeCN, was injected into the cell and sealed with a cover glass.

2.4. Synthesis and characterizations

5-(7-Bromo-[1,2,5]thiadiazolo[3,4-*c*]pyridin-4-yl)thiophene-2-carbaldehyde (1):

The mixture of 4,7-dibromo-[1,2,5]thiadiazolo[3,4-*c*]pyridine (1.17 g, 4 mmol), (5-formylthiophen-2-yl)boronic acid (639 mg, 4.1 mmol), Pd(PPh₃)₄ (230 mg, 0.2 mmol) and 2 N aqueous solution of K₂CO₃ (2 mL) in THF (10 mL) under N₂ atmosphere was heated to reflux for about 48 h. Then the solvent was removed under vacuum and the residue was purified by column chromatography on silica gel using a 1:4 mixture of hexane and CH₂Cl₂ as eluent to afford the red compound. Yield: 545.8 mg, (42%). ¹H NMR (400 MHz, CDCl₃): δ (ppm) 9.87 (s, 1H), 8.64 (s, 1H), 8.52 (d, *J* = 1.2 Hz, 1H), 8.45 (d, *J* = 1.2 Hz, 1H). ¹³C NMR (400 MHz, CDCl₃): δ (ppm) 190.03, 156.32, 153.52, 147.92, 145.82, 139.80, 138.19, 133.15, 126.56, 117.56. HRMS (MALDI-TOF, *m/z*): [*M*⁺] calcd for (C₁₀H₄BrN₃OS₂) **324.8979**; found, **324.8991**.

5-(7-(4-(Diphenylamino)phenyl)-[1,2,5]thiadiazolo[3,4-*c*]pyridin-4-yl)thiophene-2-carbaldehyde (2a):

The mixture of **1** (100 mg, 0.31 mmol), (4-(diphenylamino)-phenyl)boronic acid (116 mg, 0.4 mmol), Pd(PPh₃)₄ (18 mg, 0.01 mmol) and 2 N aqueous solution of K₂CO₃ (2 mL) in THF (10 mL) under N₂ atmosphere was heated to reflux for about 24 h. Then the solvent was removed under vacuum and the residue was purified by column chromatography on silica gel using a 1:3 mixture of hexane and CH₂Cl₂ as eluent to afford the dark red compound. Yield: 114 mg, (75%). ¹H NMR (400 MHz, CDCl₃): δ (ppm) 9.98 (s, 1H), 9.01 (s, 1H), 8.60 (t, *J* = 2.0 Hz, 2H), 8.18 (d, *J* = 2.0 Hz, 1H), 7.86 (d, *J* = 4.0 Hz, 1H), 7.30–7.35 (m, 4H), 7.19–7.22 (m, 5H), 7.17 (t, *J* = 2.0 Hz, 1H), 7.11–7.15 (m, 2H). ¹³C NMR (400 MHz, CDCl₃): δ (ppm) 182.94, 155.29, 153.51, 152.88, 150.69, 146.77, 145.42, 143.63, 142.38,

136.80, 131.25, 129.55, 129.10, 127.90, 125.76, 124.32, 121.11, 118.66. HRMS (MALDI-TOF, m/z): [M⁺] calcd for (C₂₈H₁₈N₄OS₂) 490.0925; found, 490.0937.

5-(7-(4-(Bis(9,9-dimethyl-9H-fluoren-2-yl)amino)phenyl)-[1,2,5]thiadiazolo[3,4-c]pyridin-4-yl)thiophene-2-carbaldehyde (2b): Using a similar procedure to 2a, 2b was separated as a purple solid. Yield: 110 mg, (71%). ¹H NMR (400 MHz, CDCl₃): δ (ppm) 9.99 (s, 1H), 9.03 (s, 1H), 8.66 (d, *J* = 2.0 Hz, 1H), 8.64 (d, *J* = 2.0 Hz, 1H), 8.20 (d, *J* = 4.0 Hz, 1H), 7.86 (d, *J* = 4.0 Hz, 1H), 7.65–7.69 (m, 4H), 7.40 (t, *J* = 4.0 Hz, 2H), 7.27–7.36 (m, 9H), 7.23 (t, *J* = 2.0 Hz, 1H), 7.21 (t, *J* = 2.0 Hz, 1H), 1.25 (s, 12H). ¹³C NMR (400 MHz, CDCl₃): δ (ppm) 182.95, 155.29, 153.65, 152.66, 150.91, 146.27, 143.67, 142.85, 138.74, 137.09, 135.47, 134.37, 133.97, 131.32, 129.19, 127.90, 126.87, 124.43, 122.59, 121.53, 120.82, 119.86, 119.67, 118.00, 113.84. HRMS (MALDI-TOF, m/z): [M⁺] calcd for (C₄₆H₃₄N₄OS₂) 722.2267; found, 722.2239.

5-(7-(4-(Bis(4-(hexyloxy)phenyl)amino)phenyl)-[1,2,5]thiadiazolo[3,4-c]pyridin-4-yl)thiophene-2-carbaldehyde (2c): Using a similar procedure to 2a, 2c was obtained as a purple solid. Yield: 100 mg, (80%). ¹H NMR (400 MHz, CDCl₃): δ (ppm) 9.97 (s, 1H), 8.98 (s, 1H), 8.55 (d, *J* = 4.0 Hz, 2H), 8.15 (d, *J* = 4.0 Hz, 1H), 7.84 (d, *J* = 4.0 Hz, 1H), 7.13–7.15 (m, 4H), 7.00–7.02 (m, 2H), 6.86–6.88 (m, 4H), 3.95 (t, *J* = 6.4 Hz, 4H), 1.75–1.81 (m, 4H), 1.45–1.49 (m, 4H), 1.25–1.37 (m, 8H), 0.90 (t, *J* = 6.4 Hz, 6H). ¹³C NMR (400 MHz, CDCl₃): δ (ppm) 182.88, 154.45, 150.59, 148.43, 141.22, 140.70, 139.68, 138.87, 134.75, 130.57, 127.74, 127.31, 126.75, 119.32, 118.94, 118.26, 116.88, 115.46, 67.64, 30.96, 28.01, 25.19, 22.00, 13.82. HRMS (MALDI-TOF, m/z): [M⁺] calcd for (C₄₀H₄₂N₄O₃S₂) 690.2722; found, 690.2787.

(E)-2-Cyano-3-(5-(7-(4-(diphenylamino)phenyl)-[1,2,5]thiadiazolo[3,4-c]pyridin-4-yl)thiophen-2-yl)acrylic acid (H1): A mixture of precursor 2a (100 mg, 0.20 mmol) and cyanoacrylic acid (40 mg, 0.50 mmol) in acetic acid (20 mL) was heated under reflux in the presence of ammonium acetate (200 mg) overnight under N₂ atmosphere. Then water was added and extracted with CH₂Cl₂. Next solvent was removed under vacuum and the crude compound was purified by column chromatography on silica gel eluting with CH₂Cl₂/MeOH (20:1, v/v) to give a purple solid. Yield: 81.0 mg

(70.0%). **Melting point:** 254-258 °C. **IR (KBr):** 3446, 2966, 2931, 2859, 2221, 1668, 1591, 1487, 1433, 1327, 1263, 1189, 1109, 806. ^1H NMR (400 MHz, DMSO-*d*): δ (ppm) 9.15 (s, 1H), 8.53 (d, *J* = 8.8 Hz, 2H), 8.44 (s, 1H), 8.22 (d, *J* = 4.0 Hz, 1H), 8.02 (d, *J* = 4.0 Hz, 1H), 7.40 (t, *J* = 7.8 Hz, 4H), 7.16–7.21 (m, 6H), 7.02 (t, *J* = 8.8 Hz, 2H). ^{13}C NMR (400 MHz, DMSO-*d*): δ (ppm) 163.35, 154.26, 150.81, 149.76, 148.44, 146.16, 144.94, 144.23, 141.84, 138.87, 137.35, 131.02, 129.83, 128.60, 127.36, 125.54, 124.55, 120.04, 118.12, 117.06, 115.01. HRMS (MALDI-TOF, *m/z*): [M^+] calcd for ($\text{C}_{31}\text{H}_{19}\text{N}_5\text{O}_2\text{S}_2$) 558.1053; found, 558.1030.

(E)-3-(5-(7-(4-(Bis(9,9-dimethyl-9H-fluoren-2-yl)amino)phenyl)-[1,2,5]thiadiazolo[3,4-*c*]pyridin-4-yl)thiophen-2-yl)-2-cyanoacrylic acid (H2): Using a similar procedure as for H1, H2 was separated as a dark-purple solid. Yield: 70 mg, (65.2%). **Melting point:** 225-230 °C. **IR (KBr):** 3446, 2966, 2924, 2859, 2221, 1625, 1593, 1455, 1431, 1313, 1266, 1186, 1110, 807. δ (ppm) ^1H NMR (400 MHz, DMSO-*d*): δ (ppm) 9.10 (s, 1H), 8.56 (d, *J* = 8.4 Hz, 2H), 8.25 (s, 1H), 8.18 (d, *J* = 3.6 Hz, 1H), 7.88 (d, *J* = 3.6 Hz, 1H), 7.72–7.78 (m, 4H), 7.48 (d, *J* = 7.2 Hz, 2H), 7.36 (d, *J* = 7.2 Hz, 2H), 7.24–7.32 (m, 4H), 7.11–7.17 (m, 4H), 1.36 (s, 12H). ^{13}C NMR (400 MHz, DMSO-*d*): δ (ppm) 163.22, 154.94, 154.30, 153.25, 150.44, 149.77, 148.47, 145.73, 144.81, 142.37, 141.46, 139.61, 138.04, 136.84, 134.91, 130.97, 128.94, 128.08, 127.42, 127.10, 126.95, 124.16, 122.70, 121.27, 120.75, 119.75, 119.60, 118.37, 118.19, 46.52, 26.64. HRMS (MALDI-TOF, *m/z*): [M^+] calcd for ($\text{C}_{49}\text{H}_{35}\text{N}_5\text{O}_2\text{S}_2$) 790.2305; found, 790.2274.

(E)-3-(5-(7-(4-(Bis(4-(hexyloxy)phenyl)amino)phenyl)-[1,2,5]thiadiazolo[3,4-*c*]pyridin-4-yl)thiophen-2-yl)-2-cyanoacrylic acid (H3): Using a similar procedure as for H1, H3 was obtained as a dark-purple solid. Yield: 82 mg, (69.7%). **Melting point:** 161-165 °C. **IR (KBr):** 3445, 2956, 2924, 2860, 2221, 1668, 1591, 1502, 1465, 1318, 1242, 1190, 1109, 826. δ (ppm) ^1H NMR (400 MHz, DMSO-*d*): δ (ppm) 9.07 (s, 1H), 8.51 (d, *J* = 7.2 Hz, 2H), 8.17 (d, *J* = 4.0 Hz, 1H), 8.12 (s, 1H), 7.81 (d, *J* = 4.0 Hz, 1H), 7.13 (d, *J* = 8.8 Hz, 4H), 6.95 (d, *J* = 8.8 Hz, 4H), 6.84 (d, *J* = 8.8 Hz, 2H), 3.96 (t, *J* = 6.4 Hz, 4H), 1.68–1.75 (m, 4H), 1.39–1.46 (m, 4H), 1.23–1.39 (m, 8H), 0.90 (t, *J* = 6.4 Hz, 6H). ^{13}C NMR (400 MHz, DMSO-*d*): δ (ppm) 156.07, 154.40, 150.68,

150.51, 148.49, 141.29, 140.70, 139.65, 138.71, 138.67, 134.78, 130.87, 127.74, 127.23, 126.76, 119.33, 118.92, 118.19, 116.91, 115.59, 110.87, 67.64, 30.97, 28.66, 25.18, 22.05, 13.88. HRMS (MALDI-TOF, m/z): [M⁺] calcd for (C₄₃H₄₃N₅O₄S₂) 758.2829; found, 758.2814.

3. Results and Discussion

3.1. Synthesis and Characterization

The synthetic procedures of the three dyes are depicted in Scheme 1. The key precursors to 4,7-dibromo-[1,2,5]thiadiazolo-[3,4-*c*]pyridine [9a], (4-(diphenylamino)phenyl)boronic acid, (4-(bis(9,9-dimethyl-9H-fluoren-2-yl)-amino)phenyl)boronic acid and (4-(bis(4-(hexyloxy)phenyl)amino)phenyl)boronic acid were synthesized according to the literature methods [10]. Compounds **1**, **2a**, **2b** and **2c** were prepared through conventional Suzuki cross-coupling reaction in good yield and the three target photosensitizers (**H1**, **H2**, **H3**) were separated after typical Knoevenagel reactions between the cyanoacrylic acid and the formylated intermediates. All the new compounds were characterized by ¹H NMR and ¹³C NMR spectroscopy and MALDI-TOF mass spectrometry.

3.2. UV-Visible Absorption Properties

The optical absorption spectra of three new dyes **H1**, **H2** and **H3** in dichloromethane solutions and adsorbed on TiO₂ films are shown in Figure 3, and the corresponding spectroscopic data are summarized in Table 1. The three dyes exhibited similar broad and strong absorption spectra covering a wide wavelength range of 300~750 nm (Figure 3a). The shorter wavelength region corresponds to the π - π^* transitions of the conjugated system and the longer wavelength region can be reasonably assigned to the efficient intramolecular charge transfer (ICT) between the donor and the acceptor. As expected, the introduction of PyT unit into the molecular frame distinctly exhibits broad and efficient optical absorption above 750 nm to maximize photon absorption. Obviously, in the three photosensitizers containing the same cyanoacetic acid unit, the ICT band is dependent upon the donor units and electron transport channels. As listed

in Table 1, the donor effect on absorption peak is **distinct**. A **bathochromic** shift of 29 and 39 nm was observed by replacing D1 (**H1**) with D2 (**H2**) and D3 unit (**H3**) in the donor moiety, respectively. This definitely indicates that the electron-donating capability is in the order of $D3 > D2 > D1$, which is consistent with the electrochemical properties (*vide infra*). In addition, the corresponding molar extinction coefficients of ICT peaks are in the order of $H3$ (585 nm, $2.87 \times 10^4 \text{ M}^{-1} \text{ cm}^{-1}$) $>$ $H2$ (575 nm, $2.46 \times 10^4 \text{ M}^{-1} \text{ cm}^{-1}$) $>$ $H1$ (546 nm, $2.14 \times 10^4 \text{ M}^{-1} \text{ cm}^{-1}$). The results clearly illustrate that the introduction of D3 donor group in **H3** is favorable for lowering the band gap and **extending the responsive wavelength to nearly 800 nm**, as well as capturing more solar light for a higher photocurrent output. When adsorbed on a transparent thin TiO_2 film, the three dyes showed broad absorption spectra in agreement with those in solutions (Figure 3b), while the ICT absorption peaks displayed a slight blue-shift of 49, 31, and 27 nm for **H1**, **H2**, and **H3**, respectively. Such a hypsochromic shift is mainly due to the deprotonation and H-aggregation between the carboxylate acid and the TiO_2 semiconductor [11]. Notably, the maximum absorption band of **H3** is less blue-shifted than that of **H1** and **H2**, indicating that the introduction of hexyloxy chain on the triarylamine moiety effectively inhibits H-aggregation.

3.3. Electrochemical Properties

To evaluate the possibility of photoelectron injection and sensitizer regeneration, the cyclic voltammograms have been performed in CH_2Cl_2 solution with ferrocene (0.4 V vs. NHE) as an external reference. The voltammograms of the three dyes (Figure 4) **showed symmetrical and reversible** behavior, indicative of high redox stability. The oxidation potentials correspond to the highest occupied molecular orbitals (HOMO), which are exclusively determined by the donors. As listed in Table 1, the HOMO levels of the three dyes are in the order of $H1$ (0.86 V) $>$ $H2$ (0.64 V) $>$ $H3$ (0.57 V). It can be rationalized that the donor groups with increasing electron-donating capability decrease the HOMO energy in the same order. Obviously, the HOMO values of the three dyes are more positive than Γ^-/I_3^- redox potential value (0.4 V), indicating that the oxidized dyes can be efficiently regenerated by the electrolyte. The

lowest unoccupied molecular orbitals (LUMO) can be calculated by the values of E_{ox} and the zero-zero bandgaps (E_{0-0}) determined from the onset of the UV-visible absorption spectra. The estimated E_{0-0} is 1.99 eV, 1.78 eV and 1.72 eV for **H1**, **H2** and **H3**, respectively. The values of the HOMO-LUMO bandgap for the three dyes are relatively low, indicating that the incorporation of PyT can effectively decrease the energy bandgap and **extend the absorption spectrum**. Subsequently, the LUMO values of the three dyes, calculated from $E_{HOMO}-E_{0-0}$ are -1.13, -1.14 V and -1.15 V for **H1**, **H2** and **H3**, respectively, which are more negative than the conduction band edge (CB) of TiO_2 (-0.5 V vs. NHE), allowing the efficient electron injection from the oxidized organic dyes into the conduction band of TiO_2 .

3.4. Theoretical Calculations

To understand the geometrical and electronic properties of these dyes, density functional theory (DFT) calculations are performed using Gaussian 03 program package at the B3LYP/6-31 G(d) level. The electron distributions of the HOMOs and LUMOs of these dyes are shown in Figure 5. **It was found that HOMOs of the three dyes are distributed mainly over the entire triarylamine donor part, while the LUMOs are mainly delocalized over cyanoacrylic acid, thiophene conjugated spacer and PyT acceptor.** Generally, the HOMO orbitals are delocalized through the donor and π -bridge in traditional D- π -A type of dyes. However, in our D-A- π -A structural dyes, this connection might be somewhat blocked from the electron-withdrawing unit PyT in the bridge. Initially, in designing dyes of D-A- π -A configuration, the electrons on the donor subunit are not directly transferred to the cyanoacetic acid subunit during the photo-excitation, but successively transferred to the electron-trap PyT subunit, then to the cyanoacetic acid subunit, and finally to TiO_2 . Here, the insufficient **overlap of the HOMO and LUMO orbitals implies that the strong acceptor** PyT may retard a fast charge transition from the donor to the anchor group, which is partly ascribed to the relatively low PCE based on the three dyes, regardless of their panchromatic light response.

3.5. Photovoltaic Performance

Figure 6 shows the IPCE spectra of DSSCs based on the three dyes as a function of light excitation wavelength. Notably, these DSSCs exhibited remarkably broad IPCE spectra covering the whole visible region with the threshold wavelength over 800 nm, which matched well with the threshold wavelength of the absorption spectra when adsorbed onto TiO₂ films. It means that incorporation of PyT unit in the three dyes with good delocalization between the donor and the acceptor can broaden the absorption spectrum to get a broad IPCE. From the IPCE curves, the IPCE exceeded 50% in the spectral range of 300–650 nm for the three photosensitizers, and the solar cells based on **H3** showed the highest IPCE value of 65% at 583 nm. These results also indicate that **H3** dye possesses better light-harvesting ability and would generate a higher photocurrent among the three dyes.

The photocurrent-voltage (J – V) characteristics of all devices are shown in Figure 7. The parameters of DSSCs fabricated with these dyes, i.e., short-circuit current (J_{sc}), open-circuit photovoltage (V_{oc}), fill factor (FF), and total power conversion efficiency (η), are summarized in Table 2. DSSC based on dye **H3** shows the highest PCE of 4.20% with a relatively higher $J_{sc} = 14.19 \text{ mA cm}^{-2}$, $V_{oc} = 0.462 \text{ V}$, and FF = 0.64 under AM 1.5 irradiation. And the dyes **H1** and **H2** sensitized solar cells displayed relatively inferior photovoltaic performance (η) of 2.63 % and 3.58% due to the lower J_{sc} and V_{oc} . Compared with dyes **H1** and **H2**, the significant improvement of photovoltaic performances for **H3** should be attributed to the more efficient light harvesting, effective electron injection and slower charge recombination rate (*vide infra*). For example, the LUMO energy levels of the three dyes are in the order of **H3** (–1.15 V) < **H2** (–1.14 V) < **H1** (–1.13 V), indicating that DSSC based on **H3** exhibited the most effective electron injection from the excited dye into the CB of TiO₂. As a result, DSSC based on **H3** showed the highest V_{oc} and J_{sc} due to its better molar extinction coefficient, broad IPCE curve and high electron-injection efficiency. In addition, D3 appended with a long hexyloxy chain in **H3** can effectively suppress dye-aggregation and retard charge recombination in DSSC (*vide infra*) [12].

3.6. Electrochemical Impedance Spectroscopy

Electrochemical Impedance Spectroscopy (EIS) has been performed to elucidate the interfacial charge recombination process in DSSCs based on these dyes under the dark condition. As shown in Figure 8, a major semicircle for each dye was observed in the EIS Nyquist plot, which is related to the resistance of electron transport at the $\text{TiO}_2/\text{dye}/\text{electrolyte}$ interface, i.e. the resistance of the recombination between electrons on TiO_2 conduction band and I_3^- species in the electrolyte [13]. The larger is the semicircle, the slower the recombination kinetics. It is clear that dye **H3** exhibited the highest recombination resistance, which is most likely due to the long hexyloxy chain on D3 that more efficiently closes up the area for direct contact between TiO_2 and the electrolytes [10]. A high V_{oc} is related to a low rate of charge recombination. The trend observed is definitely consistent with the V_{oc} values of the cells. As for dye **H3**, the introduction of a bulky electron-donating unit D3 appended with long hexyloxy chain can not only further extend absorption spectrum, but also efficiently provide a surface blocking layer on the TiO_2 surface and impede a direct contact between the charge and oxidized species (I_3^-) in the electrolyte [10].

4. Conclusions

In conclusion, three new D-A- π -A photosensitizers incorporating with electron-withdrawing unit PyT as an additional acceptor have been synthesized and applied in DSSCs. It has been demonstrated that the incorporation of the PyT unit can effectively tune the HOMO and LUMO energy levels and extend the absorption spectra into deep red region by decreasing the energy bandgap. As expected, the photoresponses of DSSCs based on the three dyes covered the whole visible region and reached above 800 nm, which are comparable to the incident IPCE onset of N719. Specifically for dye **H3**, the introduction of a bulky electron-donating unit D3 appended with hexyloxy chain results in a further red-shift of the ICT band and an enhanced light-harvesting property, as well as a retarded electron recombination between the charge and oxidized species (I_3^-) in the electrolyte. Though the

conversion efficiency of 4.20% is still low, the approach of tuning the HOMO or LUMO energy level by incorporation of electron-withdrawing PyT unit in such D–A– π –A dyes could be generally applied in the design of more efficient panchromatic photosensitizers in DSSCs.

Acknowledgements

We thank the National Natural Science Foundation of China (NSFC) (91222201), Hong Kong Research Grants Council (HKBU202210, HKBU202811 and HKBU203011) and Hong Kong Baptist University (FRG2/12-13/050, FRG2/11-12/007) for financial support. W.-K.W. and W.-Y.W. also thank a grant from Areas of Excellence Scheme, University Grants Committee, Hong Kong (Project No. [AoE/P-03/08]). C. J. and L. H. thank financially supports from Core Research for Evolutional Science and Technology (CREST) of the Japan Science and Technology Agency.

References

- [1] a) B. O'Regan, M. Grätzel. A low-cost, high-efficiency solar cell based on dye-sensitized colloidal TiO₂ films. *Nature* 1991; 353: 737–740; b) M. K. Nazeeruddin I. R. A. Kay, R. Humphry-Baker, E. Mueller, P. Liska, N. Vlachopoulos, M. Grätzel. Conversion of light to electricity by cis-XzBis(2,2'-bipyridyl-4,4'-dicarboxylate)ruthenium(II) charge-transfer sensitizers (X = Cl-, Br-, I-, CN-, and SCN-) on nanocrystalline TiO₂ electrodes. *J. Am. Chem. Soc* 1993; 115: 6382–6390; c) M. K. Nazeeruddin, R. Splivallo, P. Liska, P. Comte, M. Grätzel. A swift dye uptake procedure for dye sensitized solar cells. *Chem. Commun* 2003; 12: 1456–1457; d) M. K. Nazeeruddin, P. Péchy, M. Grätzel. Efficient panchromatic sensitization of nanocrystalline TiO₂ films by a black dye based on atrithiocyanato–ruthenium complex. *Chem. Commun* 1997; 18: 1705–1706; e) L. Y. Han, A. Islam, H. Chen, C. Malapaka, B. Chiranjeevi, S. F.

- Zhang, X. D. Yang, M. Yanagida. High-efficiency dye-sensitized solar cell with a novel co-adsorbent. *Energy Environ. Sci* 2012; 5: 6057–6060.
- [2] a) Y. Numata, S. P. Singh, A. Islam, M. Iwamura, A. Imai, K. Nozaki, L. Y. Han. Enhanced light-harvesting capability of a panchromatic Ru(II) sensitizer based on π -extended terpyridine with a 4-methylstyryl group for dye-sensitized solar cells. *Adv. Funct. Mater* 2013; 23: 1817–1823; b) S. H. Liu, H. S. Fu, Y. M. Cheng, K. L. Wu, S. T. Ho, Y. Chi and P. T. Chou. Theoretical study of N749 dyes anchoring on the (TiO₂)₂₈ surface in DSSCs and their electronic absorption properties. *J. Phys. Chem. C* 2012; 116: 16338–16345; c) M. K. Nazeeruddin, P. Pechy, T. Renouard, S. M. Zakeeruddin, R. Humphry-Baker, P. Comte, P. Liska, L. Cevey, E. Costa, V. Shklover, L. Spiccia, G. B. Deacon, C. A. Bignozzi, M. Grätzel. Engineering of efficient panchromatic sensitizers for nanocrystalline TiO₂-based solar cells. *J. Am. Chem. Soc* 2001; 123: 1613–1624;
- [3] a) S. Paek, H. Choi, C. Kim, N. Cho, S. So, K. Song, M. K. Nazeeruddin, J. Ko. Efficient and stable panchromatic squaraine dyes for dye-sensitized solar cells. *Chem. Commun* 2011; 47: 2874–2876; b) N. Robertson. Catching the Rainbow: Light Harvesting in Dye-Sensitized Solar Cells. *Angew. Chem. Int. Ed* 2008; 47: 1012–1014; c) J. J. He, G. Benko, F. Korodi, T. Polivka, R. Lomoth, B. Akermark, L. C. Sun, A. Hagfeldt, V. Sundstrom. Modified phthalocyanines for efficient near-IR sensitization of nanostructured TiO₂ electrode. *J. Am. Chem. Soc* 2002; 124: 4922–4932; d) M. Kimura, H. Nomoto, N. Masaki, S. Mori. Dye molecules for simple co-sensitization process: fabrication of mixed-dye-sensitized solar cells. *Angew. Chem. Int. Ed* 2012; 51(18): 4371–4374; e) M. E. Ragoussi, J. J. Cid, J. H. Yum, G. Torre, D. D. Censo, M. Grätzel, M. K. Nazeeruddin. Carboxyethynyl anchoring ligands: a means to improving the efficiency of phthalocyanine-sensitized solar cells. *Angew. Chem. Int. Ed* 2012; 52(18): 4375–4379.
- [4] a) J. Y. Li, C.Y. Chen, W. C. Ho, S. H. Chen, C. G. Wu. Unsymmetrical squaraines incorporating quinoline for near infrared responsive dye-sensitized solar cells. *Org. Lett* 2012; 14(21): 5420–5423; b) S. Kim, G. K. Mor, M. Paulose, O. K. Varghese,

- C. Baik, C. A. Grimes. Molecular design of near-IR harvesting unsymmetrical squaraine dyes. *Langmuir* 2010; 26(16): 13486–13492; c) J. H. Yum, P. Walter, S. Huber, D. Rentsch, T. Geiger, F. Nuesch, F. D. Angelis, M. Grätzel, M. K. Nazeeruddin. Efficient far red sensitization of nanocrystalline TiO₂ flms by an unsymmetrical squaraine dye. *J. Am. Chem. Soc* 2007; 129(34): 10320-10321.
- [5] P. K. Sudeep, K. Takechi, P. V. Kamat. Harvesting photons in the infrared. electron injection from excited tricarboyanine dye (IR-125) into TiO₂ and Ag@TiO₂ core-shell nanoparticles. *J. Phys. Chem. C* 2007; 111(1): 488–494.
- [6] S. Kolemen, O. A. Bozdemir, Y. Cakmak, G. Barin, S. Erten-Ela, M. Marszalek, J. H. Yum, S. M. Zakeeruddin, M. K. Nazeeruddin, M. Grätzel, E. U. Akkaya. Optimization of distyryl-Bodipy chromophores for efficient panchromatic sensitization in dye sensitized solar cells. *Chem. Sci* 2011; 2: 949–954.
- [7] a) M. Kimura, J. Masuo, Y. Tohata, K. Obuchi, N. Masaki, T. N. Murakami, N. Koumura, K. Hara, A. Fukui, R. Yamanaka, S. Mori. Improvement of TiO₂/dye/electrolyte interface conditions by positional change of alkyl chains in modified panchromatic Ru complex dyes. *Chem. Eur. J* 2013; 19(3): 1028–1034; b) C. Qin, W.-Y. Wong; L. Han. Squaraine dyes for dye-sensitized solar cells: recent advances and future challenges. *Chem. Asian J* 2013; 8(8): 1706–1719.
- [8] a) Y. Z. Wu, W. H. Zhu. Organic sensitizers from D– π –A to D–A– π –A: effect of the internal electron-withdrawing units on molecular absorption, energy levels and photovoltaic performances. *Chem. Soc. Rev* 2013; 42: 2039–2058; b) Y. Z. Wu, X. Zhang, W. Q. Li, Z. S. Wang, H. Tian, W. H. Zhu. Hexylthiophene-featured D–A– π –A structural indoline chromophores for coadsorbent-free and panchromatic dye-sensitized solar cells. *Adv Energy Mater* 2012; 2(1): 149–156; c) S. Haid, M. Marszalek, A. Mishra, M. Wielopolski, J. Teuscher, J. E. Moser, R. Humphry-Baker, S. M. Zakeeruddin, M. Grätzel, P. Bauerle. Significant improvement of dye-sensitized solar cell performance by small structural modification in π -conjugated donor–acceptor dyes. *Adv. Funct. Mater* 2012; 22(6): 1291–1302; d) R. Y. Y. Lin, C. P. Lee, Y. C. Chen, J. D. Peng, T. C. Chu, H. H. Chou, H. M. Yang, J. T. Lin, K. C. Ho. Benzothiadiazole-containing

donor–acceptor–acceptor type organic sensitizers for solar cells with ZnO photoanodes. *Chem. Commun* 2012; 48: 12071–12073.

- [9] a) Y. Sun, S. C. Chien, H. L. Yip, Y. Zhang, K. S. Chen, D. F. Zeigler, F. C. Chen, B. P. Lin, A. K. Y. Jen. High-mobility low-bandgap conjugated copolymers based on indacenodithiophene and thiadiazolo[3,4-*c*]pyridine units for thin film transistor and photovoltaic applications. *J. Mater. Chem* 2011; 21: 13247–13255; b) N. Blouin, A. Michaud, D. Gendron, S. Wakim, E. Blair, R. Neagu-Plesu, M. Belletete, G. Durocher, Y. Tao, M. Leclerc. Toward a rational design of poly(2,7-carbazole) derivatives for solar cells. *J. Am. Chem. Soc* 2008; 130(2): 732–742; c) G. C. Welch, L. A. Perez, C. V. Hoven, Y. Zhang, X. D. Dang, A. Sharenko, M. F. Toney, E. J. Kramer, T. Q. Nguyen, G. C. Bazan, A modular molecular framework for utility in small-molecule solution-processed organic photovoltaic devices. *J. Mater. Chem* 2011; 21: 12700–12709; d) H. X. Zhou, L. Q. Yang, S. C. Price, K. J. Knight, W. You. Enhanced photovoltaic performance of low-bandgap polymers with deep LUMO levels. *Angew. Chem. Int. Ed* 2010; 49(43): 7992–7995; e) S. Steinberger, A. Mishra, E. Reinold, J. Levichkov, C. Uhrich, M. Pfeiffer, P. Bäuerle. Vacuum-processed small molecule solar cells based on terminal acceptor-substituted low-band gap oligothiophenes. *Chem. Commun* 2011; 47: 1982–1984; f) G. C. Welch, G. C. Bazan. Lewis acid adducts of narrow band gap conjugated polymers. *J. Am. Chem. Soc* 2011; 133(12): 4632–4644; g) L. Ying, B. B. Y. Hsu, H. M. Zhan, G. C. Welch, P. Zalar, P. L. E. J. Kramer, T. Q. Nguyen, A. J. Heeger, W. Y. Wong, G. C. Bazan. Regioregular pyridal[2,1,3]thiadiazole π -conjugated copolymers. *J. Am. Chem. Soc* 2011; 133: 18538–18541.
- [10] Y. Hua, B. Jin, H. D. Wang, X. J. Zhu, W. J. Wu, M. S. Cheung, Z Y. Lin, W. Y. Wong, W. K. Wong. New phenothiazine-based dyes for efficient dye-sensitized solar cells: positioning effect of a donor group on the cell performance. *J. Power Sources* 2013; 237: 195–203.
- [11] a) J. Y. Mao, F. L. Gao, W. J. Ying, W. J. Wu, J. Li, J. L. Hua. Benzotriazole-bridged sensitizers containing a furan moiety for dye-sensitized

- solar cells with high open-circuit voltage performance. *Chem. Asian J* 2012; 7(5): 982–991; b) Y. Hua, S. Chang, D. D. Huang, X. Zhou, X. J. Zhu, J. Z. Zhao, T. Chen, W. Y. Wong, W. K. Wong. Significant improvement of dye-sensitized solar cell performance using simple phenothiazine-based dyes. *Chem. Mater* 2013; 25(10): 2146–2153.
- [12] a) S. Kim, D. Kim, H. Choi, M. S. Kang, K. Song, S. O. Kang, J. Ko. Enhanced photovoltaic performance and long-term stability of quasi-solid-state dye-sensitized solar cells *via* molecular engineering. *Chem. Commun.* 2008; 40: 4951–4953; b) C. Qin, A. Islam, L. Han, Incorporating a stable fluorenone unit into D–A– π –A organic dyes for dye-sensitized solar cells. *J. Mater. Chem.* 2012; 22: 19236–19243.
- [13] a) F. R. Dai, Y. C. Chen, L. L. F, W. J. Wu, C. H. Cui, T. G. P, X. Z. Wang, J. T. Lin, H. Tian, W. Y. Wong, Unsymmetric platinum(II) bis(aryleneethynylene) complexes as photosensitizers for dye-sensitized solar cells. *Chem. Asian J* 2012; 7(6): 1426–1434; b) J. Shi, J. N. Chen, Z. F. Chai, H. Wang, R. L. Tang, K. Fan, M. Wu, H. W. Han, J. G. Qin, T. Y. Peng, Q.Q. Li, Z. Li. High performance organic sensitizers based on 11,12-bis(hexyloxy) dibenzo[*a,c*]phenazine for dye-sensitized solar cells. *J. Mater. Chem* 2012; 22: 18830–18838.

Table 1. Photophysical and electrochemical properties of the three organic dyes.

Dye	$\lambda_{\max}$ [nm] ^a ($\epsilon/10^4 \text{ M}^{-1} \text{ cm}^{-1}$)	$\lambda_{\max}$ [nm] ^b	E_{ox} [V] ^c	E_{0-0} [eV] ^d	E_{ox}^* [V] ^e
H1	546 (2.14)	497	0.86	1.99	−1.13
H2	575 (2.46)	544	0.64	1.78	−1.14
H3	585 (2.87)	558	0.57	1.72	−1.15

^a Absorption maximum in $1 \times 10^{-5} \text{ mol L}^{-1} \text{ CH}_2\text{Cl}_2$ solution. ^b Absorption maximum on TiO_2 film. ^c Oxidation potential in CH_2Cl_2 solution containing 0.1 M (*n*-C₄H₉)₄NPF₆ with a scan rate 100 mV s^{-1} (vs. NHE). ^d E_{0-0} was determined from the onset of absorption spectra. ^e $E_{\text{ox}}^* = E_{\text{ox}} - E_{0-0}$.

Table 2. Photovoltaic parameters of the dyes in liquid based DSSCs at full sunlight (AM 1.5G, 100 mW cm^{-2}).

Dye	J_{sc} [mA cm^{-2}]	V_{oc} [V]	FF	η [%]
H1	11.23	0.367	0.64	2.63
H2	12.00	0.432	0.69	3.58
H3	14.19	0.462	0.64	4.20

Legends for Figures and Scheme

Figure 1. Chemical structures of **N719**, **YR6** and “black dye”.

Figure 2. Chemical structure of new dyes **H1**, **H2** and **H3**.

Scheme 1. Synthetic routes for the dyes **H1**, **H2** and **H3**. Reaction conditions: (a) $\text{Pd}(\text{PPh}_3)_4$, K_2CO_3 (2 N), THF/reflux; (b) $\text{Pd}(\text{PPh}_3)_4$, K_2CO_3 (2 N), THF, reflux; (c) CNCH_2COOH , CH_3COOH , $\text{CH}_3\text{COONH}_4$, reflux.

Figure 3. Absorption spectra of dyes (a) in CH_2Cl_2 solution and (b) on TiO_2 films.

Figure 4. Cyclic voltammograms of dyes **H1–H3** in CH_2Cl_2 solution.

Figure 5. Frontier molecular orbitals of the HOMO and LUMO (right) calculated by DFT on a B3LYP/6-31 G (d)* level.

Figure 6. IPCE curves of organic dyes **H1–H3**.

Figure 7. The photocurrent-voltage ($J-V$) curves of DSSCs.

Figure 8. EIS Nyquist plots for DSSCs based on the dyes under dark.

Figure 1

Figure 2

Scheme 1

Figure 3(a)

Figure 3(b)

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Graphical Abstract