Breakdown voltage and triggering probability of SiPM from IV curves at different temperatures

N. Dinu^{a,b}, A. Nagai^{c,*}, A. Para^d

^awas with the Laboratory of Linear Accelerator & University Paris 11, CNRS / IN2P3,
91898 Orsay Cedex, France

^bshe is now with ARTEMIS laboratory, CNRS/INSIS, UCA, OCA, F-06304, Nice Cedex,
France

^cis with the Laboratory of Linear Accelerator & University Paris 11, CNRS / IN2P3, 91898
Orsay Cedex, France

^dis with the Fermi National Accelerator Laboratory, Batavia IL, 60510-5011 USA

Abstract

This work presents a physical model describing the IV curves of SiPM detectors allowing to easily determine important device parameters like breakdown voltage V_{BD} and the shape of Geiger triggering probability P_{Geiger} . We measured IV curves and tested our IV model in a temperature range $-35^{\circ}C < T < +35^{\circ}C$ on various SiPMs from two vendors (Hamamatsu devices of $3 \times 3mm^2$ total area and $50 \times 50\mu m^2$ μ cell size, 2011 and 2015 year production runs and KETEK devices of $0.5 \times 0.5mm^2$ total area and $50 \times 50\mu m^2$ μ cell size, 2015 production run). The shape of IV curve can be described in terms of Geiger probability and afterpulsing in a very large current range of $10^{-12}A < I_{post-BD} < 10^{-5}A$ over the full working range of all tested devices. It has been also found that V_{BD} from IV curves is slightly higher (few hundred mV) than the "breakdown voltage" determined from the usual method of linear fit of gain as a function of bias voltage, this discrepancy reflecting the fundamental difference in the physical significance of the "breakdown voltage" determined by these two methods. The recent generation of SiPMs have very wide working range and there is an evidence phenomena beyond afterpulsing like heating or non-quenched pulses contributing to the fast increase of the current at high bias

*Corresponding author

Email address: nagai@lal.in2p3.fr (A. Nagai)

voltages.

Keywords: Silicon PhotoMultiplier, Geiger triggering probability, breakdown voltage, IV model

2010 MSC: 00-01, 99-00

1. Introduction

Silicon PhotoMultiplier (SiPM) detector has become an alternative photon detector for many applications that would employ typically PMTs or MA-PMT. Its important advantages such as compactness, speed of response, insensitivity
5 to magnetic fields, high gain, and low operating voltage, make it very attractive in medical imaging applications for diagnostic and therapeutic purposes [1, 2] as well as for high energy physics [3] or astrophysics experiments [4, 5]. To achieve the best performance for a given application, the important device parameters related to avalanche multiplication such as breakdown voltage V_{BD} and trig-
10 gering probability P_{Geiger} have to be known. Usually these parameters are determined from dynamic-type measurements (so-called AC) which require quite complicated data acquisition system (i.e. amplifier, oscilloscope), long data taking time and precise analyzing procedure of SiPM pulses [6, 7]. Use of static-type measurements (so-called DC) would significantly simplify the analysis procedure
15 particularly for large scale production, since it requires only current-voltage IV measurements with simple connection of the device to a source-measure instrument. The inverse logarithmic derivative method is often used to determine V_{BD} from IV curves [8]. This method postulates that the breakdown voltage corresponds to the maximum of the inverse logarithmic derivative of a current.
20 It is lacking physical motivation and the resulting breakdown voltage depends on the relative magnitude of the avalanche-induced current and the parasitic currents [9]. In this paper, we present a physical model describing the shape of the IV curves over the full working range of various SiPMs in terms of a linearly rising current due to free carriers modified by the Geiger probability
25 P_{Geiger} near the breakdown and the afterpulsing effects at higher bias voltages.

A comparison of detectors characteristics like V_{BD} and P_{Geiger} calculated using our IV model with those determined from AC measurements is also given.

2. SiPM samples and experimental set-up

We have examined three Hamamatsu MPPC detectors (called hereafter, for simplicity, HPK SiPM) of $3 \times 3 \text{ mm}^2$ total area and $50 \times 50 \mu\text{m}^2$ μcell size (S10931-050P – 2011 year production run; S13082-050CS(X) and S13360-3050CS, 2015 year production run) and two KETEK SiPM devices of $0.5 \times 0.5 \text{ mm}^2$ total area and $50 \times 50 \mu\text{m}^2$ μcell size (SiPM19-W3-MP50NT - no trenches; SiPM19-W3-MP50-V1 with trenches, both devices of 2015 year production run). Based on the vendors data sheets, both HPK and KETEK SiPMs are optimized for blue light detection (i.e. p^+/n junction implanted in an n-type epitaxial layer grown on n-type silicon substrate).

The SiPM sample under study is measured in the temperature range $-35^\circ\text{C} < T < +35^\circ\text{C}$ of 10°C step using a closed-cycle He cryocooler working on the Gifford McMahon thermodynamic principle (i.e. compressor, cold end, gas lines) and a vacuum chamber at $P < 10^{-4} \text{ mbar}$.

A copper disk, in tight contact with the cold end, was used to attach simultaneously four SiPM samples and temperature sensors. One temperature sensor, close to the SiPM under test, was used as reference, while the others were used to control the uniformity of temperature over the full surface of the Cu disk.

The reference temperature sensor together with a heater (50Ω) allowed to control and stabilize the temperature to the desired value using the PID system of a LakeShore 335 temperature controller. Each measurement is carried out after waiting for stabilization of temperature (typically half an hour), until the reference sensor reports the temperature to be within 0.1°C with respect to the desired value.

Using the described set-up, both DC and AC tests were performed on our SiPMs samples. During DC measurements, the SiPM sample was directly con-

55 nected to a Keithley 2611 source-meter for bias voltage supply and current measurement and the IV characteristics were acquired in dark conditions at various temperatures.

During AC measurements, the SiPM sample is connected to a Miteq AU-1332 amplifier (gain = 55 dB, bandwidth = 500 MHz) while the data acquisition 60 (i.e. waveforms) is provided by a Tektronix TDS5054 oscilloscope (bandwidth of 20 MHz was used for noise suppression). The readout electronics was located outside the vacuum chamber, at room temperature, to provide the same experimental conditions (amplifier gain, electronic noise level) independent of temperature. A Pylas diode laser of 635 nm wavelength has been employed to 65 illuminate the surface of the SiPM with low intensity light pulses (few photons/pulse) via an optical fiber entering the vacuum chamber.

3. Dynamic AC acquisitions / waveform analysis

The breakdown voltage, V_{BD} , and P_{Geiger} have been firstly determined by analyzing the waveforms acquired using AC set-up. At each temperature 10000 70 waveforms of $2\mu s$ length were acquired at different bias voltages V_{bias} . Data acquisition was triggered by the laser controller, the laser signal being positioned at $1.55\mu s$ after the beginning of the waveform. The breakdown voltage of SiPM changes with temperature [8, 10] and therefore, the range of bias voltages, V_{bias} , corresponding to each SiPM sample was selected to correspond to the same 75 overvoltage ($\Delta V = V_{bias} - V_{BD}$) for all temperatures. The HPK SiPM sample from 2011 was measured in a ΔV range of $0.4V < \Delta V < 2.7V$, while both HPK and KETEK SiPM samples from 2015 were measured in a ΔV range of $0.4V < \Delta V < 10V$. The upper limit of the bias voltage range is imposed by onset of strong afterpulsing leading to the amplifier saturation and baseline 80 shifts. The Hamamatsu devices from 2011 have a working ΔV range of only 2.7 V while the latest generation of both vendors have a larger $\Delta V \sim 10V$, showing a considerable improvement of SiPM technology.

Single SiPM pulses (i.e. corresponding to one $\mu cell$) were identified in each

85 waveform and their characteristics like amplitude, charge Q and arrival time have been determined. The device gain G has been calculated as $G = \langle Q \rangle / e$, where $\langle Q \rangle$ is the mean value of a single avalanche charge, e - is the elementary charge (more details on AC analysis can be found in the Refs. [6, 7]).

The gain of the device grows linearly with the bias voltage for all measured devices. The linear fit is used to determine the breakdown voltage V_{BD} and μ_{cell} 90 capacitance $C_{\mu cell}$ (the slope of the line). Detailed analysis of V_{BD} dependence on temperature for all SiPM samples as well as their comparison with V_{BD} values determined from the IV characteristics are presented in the Section V (i.e. Fig. 3).

Laser light intensity was kept constant throughout the entire exposure but 95 the average number of detected photons varies with the conditions, reflecting the variation of the Geiger probability with the operating conditions. Variation of the magnitude of the observed response to the laser (average number of detected photons, k_{laser}) can be used to determine the variation of the P_{Geiger} . A value of k_{laser} is determined by using the Poisson statistics:

$$k_{laser} = -\ln(P(0)) \quad (1)$$

100 where $P(0)$ is a fraction of recorded waveforms with no SiPM signal observed within a 20 ns gate centered on the expected arrival time of the laser signal. The observed value of k_{laser} was corrected for dark SiPM pulses which can appear during the 20 ns laser gate using an auxiliary "dark" gate :

$$k_{laser}^{corr} = -\ln(P(0)) + \ln(P_{dark}(0)) = N_{phot} \times P_{Geiger} \quad (2)$$

The absolute scale of the P_{Geiger} is not known as we do not know the average 105 number of photons illuminating the SiPM, N_{phot} . We have normalized the P_{Geiger} to be 1 at the highest bias voltage at $T = +35^0C$ (independently for each device). An example of the dependence of P_{Geiger} on the overvoltage, $\Delta V = V_{bias} - V_{BD}$, for measured SiPM samples is presented in Fig. 1. Following

Figure 1: $P_{Geiger-AC}$ vs. ΔV at $25^{\circ}C$ for various SiPM samples

McIntyre [11] the P_{Geiger} can be parameterized as:

$$P_{Geiger}(\Delta V) = 1 - \exp(p \cdot \Delta V) \quad (3)$$

where p is the parameter depending on the SiPM design and composition of free carriers. Such a parameterization provides a good description of our experimental data as shown in Fig. 1 (dots). Fig. 1 demonstrates that the working range of the 2011 HPK device was too small to allow reaching the maximum of P_{Geiger} , while the technology of 2015 devices, independent of the vendor, is greatly improved, allowing operation near the plateau of P_{Geiger} .

4. Static DC acquisitions / IV model

The experimental IV characteristics of SiPM samples from various vendors are presented in Fig. 2 for the temperature range $-35^{\circ}C < T < +35^{\circ}C$. For all temperatures and devices the IV curves have similar shapes indicating several regimes of the bias voltage:

- Pre-breakdown, I_{pre-BD} , with relatively slow increase of the current being a combination of surface dark current (i.e. ionic impurities deposited on the surface during device fabrication) and the bulk dark current (i.e.

Shockley-Read-Hall (SRH) thermal carrier's generated in the depleted re-
 125 gion and carriers resulting from trap-assisted or band-to-band tunneling).
 We parameterize this component as:

$$I_{pre-BD}(V_{bias}) = \exp(a \cdot V_{bias} + b) \quad (4)$$

This parameterization ignores the increase of the carrier-induced current
 due to increase of the gain.

- "just-above" the breakdown voltage the current is dominated by the Geiger
 130 discharges produced by bulk free carriers. The current grows linearly with
 the overvoltage, it is in addition multiplied by the Geiger probability,
 which is the primary factor determining the shape of the IV curve in this
 region:

$$I_{post-BD}(V_{bias}) = \frac{dN_{carriers}}{dt} \cdot C_{\mu cell} \cdot P_{Geiger} \cdot (V_{bias} - V_{BD})^2 \quad (5)$$

- "far-above" the breakdown voltage the free carriers induced current is
 135 further amplified by afterpulsing and cross-talk effects. Due to their non-
 linear nature the afterpulses are expected to be the dominant effect leading
 to the multiplicative factor [12]

$$G_{AP}(V_{bias}) = 1 + \frac{P_{ap}(V_{bias})}{1 - P_{ap}(V_{bias})} \quad (6)$$

where $P_{ap}(V_{bias})$ denotes the probability that an afterpulse will be pro-
 duced by a single avalanche. $P_{ap}(V_{bias})$ should be linearly rising with
 140 overvoltage and the recursive nature of afterpulsing leads to a continuous
 current at a some voltage, V_{cr} , where $P_{ap}(V_{cr}) = 1$, thus

$$P_{ap}(V_{bias}) = \frac{\Delta V}{V_{cr} - V_{BD}} \quad (7)$$

- Post - "second breakdown" region, where run-away afterpulses and non-
 quenching effects lead to a continuous current limited by the total series
 resistance of the device.

145 Taking into account all these contributions, the $I_{post-BD}$ can be expressed
as:

$$I_{post-BD}(V_{bias}) = \exp(a \cdot V_{bias} + b) + \frac{dN_{carriers}}{dt} \cdot \frac{V_{cr} - V_{BD}}{V_{cr} - V_{bias}} \times \quad (8)$$

$$\times (1 - \exp[p \cdot (V_{bias} - V_{BD})]) \cdot C_{\mu cell} \times (V_{bias} - V_{BD})$$

where a , b , $dN_{carriers}/dt$, V_{cr} , V_{BD} , $C_{\mu cell}$, and p are free parameters. This formula has been used to fit the experimental IV characteristics and the fits are shown in Fig. 2 a) to e) (i.e. lines). The values of V_{BD} and V_{cr} obtained from
150 the fit are also indicated in the tables of Fig. 2.

A very good agreement of the simple model (i.e. eq. 8) with the experimental data for all devices over large range of currents $10^{-12}A < I_{post-BD} < 10^{-5}A$ allows for a robust determination of characteristics of SiPMs from the IV curves, in particular the breakdown voltage and the Geiger probability.

155 In the case of the 2011 HPK device, the $V_{cr} \sim 2.7V$ and our model describes well the experimental data over the entire working range showing that the physical phenomena determining the 2nd breakdown of this device is the afterpulsing, as described by the model. Discrepancy between the model and the data just below the breakdown voltage, especially at higher temperatures,
160 is attributed to the neglect of the contribution of proportional amplification.

Recent technological improvements have resulted in major reduction of afterpulsing and cross-talk thus allowing a much larger range of the bias voltages. Comparing the model with the IV curves for recent devices, we observe that at large overvoltage values there are indications of additional physical phenomena
165 which contribute to an additional increase of the current (i.e. internal heating, non-quenched pulses) and may limit the range of applicability of the simple model presented here. The overvoltage region and the magnitude of these new phenomena depends on the vendor, hence it may be related to the detector design or to technological details.

Figure 2: Reverse IV characteristics (dots) and fit (lines) for various SiPM samples in T range $-35^{\circ}\text{C} < T < +35^{\circ}\text{C}$

5. Comparison of parameters from DC / AC acquisitions

A comparison between V_{BD-DC} values obtained from DC acquisitions /IV model and the V_{BD-AC} calculated from AC acquisitions/ waveform analysis at various temperatures is presented in Fig. 3. Both methods are in good agreement regarding the temperature variation of the breakdown voltage, but there is a significant and systematic difference: the values of the V_{BD-DC} are few hundreds mV higher than the values of V_{BD-AC} for all measured devices and temperatures. This discrepancy reflects the fundamental difference in the physical significance of the "breakdown" voltage determined by these two methods. The "IV-based" measurement is sensitive to the onset of avalanche phenomenon and it determines the "breakdown" as defined by the fundamental papers of McIntyre. The AC/gain linearity method determines the voltage to which the voltage across the diode is reduced to quench the avalanche. The latter is naturally lower than the former and our results are consistent with this expectation.

Fig. 4 shows a comparison between $P_{Geiger-DC}$ shape obtained from DC acquisitions /IV model and the $P_{Geiger-AC}$ shape calculated from AC acquisitions/ waveform analysis at various temperatures for Hamamatsu S13360-3050CS device. A very good agreement is observed between two methods for $-35^{\circ}\text{C} < T < +15^{\circ}\text{C}$, while an emerging disagreement is observed at higher

Figure 3: V_{BD-DC} and V_{BD-AC} vs temperature for various SiPMs: a) HPK and b) KETEK

Figure 4: $P_{Geiger-DC}$ and $P_{Geiger-AC}$ vs. ΔV of an HPK SiPM (2015) at various T

temperatures, $25^{\circ}C$ and above. These studies are in their preliminary stages
 190 and there are several systematic effects which need to be investigated. The
 IV curve is due to avalanches produced by free carriers (presumably gener-
 ated by both electrons and holes) whereas AC acquisition is performed with
 red light (i.e. avalanches are mostly generated by holes since our devices are
 $p^{+}/n/n-epi/n-type$ design). Therefore, the difference between the two Geiger
 195 probabilities at high temperatures could be related to the difference in the nature
 of the primary carriers [13].

6. Conclusions

In this paper we reported a physical model describing the SiPM IV shape over full device working range. Devices from two vendors and different production runs were studied in a temperature range of $-35^{\circ}C < T < +35^{\circ}C$. It has been shown that the shape of the IV curve can be described in terms of the Geiger probability and afterpulsing for all devices in the bias range of $V_{BD} < V_{bias} < V_{cr}$ and large currents range of $10^{-12}A < I_{post-BD} < 10^{-5}A$. The model allows determination of important device parameters as breakdown voltage V_{BD} and the shape of triggering probability P_{Geiger} . The V_{BD} is slightly higher (few hundreds mV) than the "breakdown voltage" determined from the usual method of a linear fit of gain as a function of bias voltage. The difference could be related to the different physical interpretation of the resulting parameters. The recent generation of SiPMs have a very wide working range and there is an evidence phenomena beyond afterpulsing like internal heating or non-quenched pulses contributing to the current at higher bias voltage.

7. Acknowledgment

The authors thanks to LAL mechanical and infrastructure services for the precious help in designing and building the cryogenic set-up, as well as to SERDI/GRED group for providing lasers and measurement instruments. A special thanks is given to Hammoudi Nourredine from IPNO laboratory for his advises on calibration of the cryogenic set-up. This work was supported by the Laboratory of Linear Accelerator (LAL) and the Labex Physique des 2 Infinis et des Origines (P2IO), under the project SONIM. Fermi National Accelerator Laboratory is operated by Fermi Research Alliance, LLC under Contract No. De-AC02-07CH11359 with the United States Department of Energy.

References

- [1] G. Llosa, N. Belcari, M. Bisogni, G. Collazuol, S. Marcatili, M. Boscardin, M. Melchiorri, A. Tarolli, C. Piemonte, N. Zorzi, P. Barrillon, S. Bondil-

- 225 Blin, V. Chaumat, C. de La Taille, N. Dinu, V. Puill, J.-F. Vagnucci, A. D.
Guerra, First results in the application of silicon photomultiplier matrices
to small animal PET, Nuclear Instruments and Methods in Physics Re-
search Section A: Accelerators, Spectrometers, Detectors and Associated
Equipment 610 (2009) 196 – 199. New Developments In Photodetection
230 NDIP08.
- [2] N. Dinu, T. A. Imando, A. Nagai, L. Pinot, V. Puill, S. Callier, B. Jan-
vier, C. Esnault, M.-A. Verdier, L. Raux, V. Vandenbussche, Y. Charon,
L. Menard, SiPM arrays and miniaturized readout electronics for compact
gamma camera, Nuclear Instruments and Methods in Physics Research
235 Section A: Accelerators, Spectrometers, Detectors and Associated Equip-
ment 787 (2015) 367 – 372. New Developments in Photodetection NDIP14.
- [3] D. Jeans, the CALICE collaboration, Results of the CALICE scintillator
ECAL beamtest at DESY, Journal of Physics: Conference Series 160 (2009)
012026.
- 240 [4] L. Gruber, G. S. M. Ahmed, S. E. Brunner, P. Bhler, J. Marton, K. Suzuki,
Position sensitive SiPM detector for Cherenkov applications, Journal of
Instrumentation 6 (2011) C11024.
- [5] S. Korpar, Status and perspectives of solid state photon detectors, Nu-
clear Instruments and Methods in Physics Research Section A: Accelera-
245 tors, Spectrometers, Detectors and Associated Equipment 639 (2011) 88 –
93. Proceedings of the Seventh International Workshop on Ring Imaging
Cherenkov Detectors.
- [6] A. Nagai, Silicon Photomultiplier for Medical Imaging Analysis of SiPM
characteristics-, Proceedings of Journes de Rencontre Jeunes Chercheurs
250 (2013) 43–47.
- [7] N. Dinu, A. Nagai, A. Para, Studies of MPPC detectors down to cryogenic
temperatures , Nuclear Instruments and Methods in Physics Research Sec-

tion A: Accelerators, Spectrometers, Detectors and Associated Equipment
787 (2015) 275 – 279. New Developments in Photodetection {NDIP14}.

- 255 [8] N. Serra, G. Giacomini, A. Piazza, C. Piemonte, A. Tarolli, N. Zorzi, Ex-
perimental and TCAD Study of Breakdown Voltage Temperature Behavior
in n^+/p SiPMs, IEEE Transactions on Nuclear Science 58 (2011) 1233–
1240.
- [9] E. Garutti, M. Ramilli, C. Xu, W. Hellweg, R. Klanner, Characteriza-
260 tion and X-ray damage of Silicon Photomultipliers, Proceedings of Science
PoS(TIPP2014)070 (2014).
- [10] N. Dinu, C. Bazin, V. Chaumat, C. Cheikali, A. Para, V. Puill, C. Sylvia,
J. F. Vagnucci, Temperature and bias voltage dependence of the MPPC
detectors (2010) 215–219.
- 265 [11] R. J. McIntyre, Theory of Microplasma Instability in Silicon, Journal of
Applied Physics 32 (1961) 983–995.
- [12] A. Para, Afterpulsing in Silicon Photomultipliers: Impact on the Photode-
tectors Characterization, arXiv 1503.01525 [physics.ins-det] (2015).
- [13] W. G. Oldham, R. R. Samuelson, P. Antognetti, Triggering phenomena
270 in avalanche diodes, IEEE Transactions on Electron Devices 19 (1972)
1056–1060.