Targeted delivery to bone and mineral deposits using bisphosphonate ligands

Lisa E. Cole,^{1,3} Tracy Vargo-Gogola^{2,3} and Ryan K. Roeder^{1,3}

¹Department of Aerospace and Mechanical Engineering
Bioengineering Graduate Program
University of Notre Dame
Notre Dame, IN 46556, USA

²Department of Biochemistry and Molecular Biology
Indiana University Simon Cancer Center
Indiana University School of Medicine – South Bend
South Bend, IN 46617, USA

³Harper Cancer Research Institute
University of Notre Dame
Notre Dame, IN 46556, USA

Submitted to: *Advanced Drug Delivery Reviews*

Keywords: Bisphosphonate; Bone; Calcifications; Drug Delivery; Hydroxyapatite;
Diagnostic Imaging; Radiotherapy; Targeted Delivery

Correspondence: Ryan K. Roeder, Ph.D.
Associate Professor
Department of Aerospace and Mechanical Engineering
Bioengineering Graduate Program
148 Multidisciplinary Research Building
University of Notre Dame
Notre Dame, IN 46556

Phone: (574) 631-7003
Email: roeder@nd.edu

Funding Sources: National Science Foundation (DMR-1309587)
St. Joseph Regional Medical Center
Walther Cancer Foundation

1   **Abstract**

2   The high concentration of mineral present in bone and pathological calcifications is
3   unique compared with all other tissues and thus provides opportunity for targeted delivery of
4   pharmaceutical drugs, including radiosensitizers and imaging probes. Targeted delivery enables
5   accumulation of a high local dose of a therapeutic or imaging contrast agent to diseased bone or
6   pathological calcifications. Bisphosphonates (BPs) are the most widely utilized bone-targeting
7   ligand exhibiting high binding affinity to hydroxyapatite mineral. BPs can be conjugated to an
8   agent that would otherwise have little or no affinity for the sites of interest. This article
9   summarizes the current state of knowledge and practice for the use of BPs as ligands for targeted
10   delivery to bone and mineral deposits. The clinical history of BPs is briefly summarized to
11   emphasize the success of these molecules as therapeutics for metabolic bone diseases.
12   Mechanisms of binding and the relative binding affinity of various BPs to bone mineral are
13   introduced, including common methods for measuring binding affinity *in vitro* and *in vivo*.
14   Current research is highlighted for the use of BP ligands for targeted delivery of BP conjugates
15   in various applications, including (1) therapeutic drug delivery for metabolic bone diseases, bone
16   cancer, other bone diseases, and engineered drug delivery platforms; (2) imaging probes for
17   scintigraphy, fluorescence, positron emission tomography, magnetic resonance imaging, and
18   computed tomography; and (3) radiotherapy. Last, and perhaps most importantly, key structure-
19   function relationships are considered for the design of drugs with BP ligands, including the tether
20   length between the BP and drug, the size of the drug, the number of BP ligands per drug,
21   cleavable tethers between the BP and drug, and conjugation schemes.

1. Introduction

Bone pathologies and pathological calcifications in soft tissues can be diagnosed and treated by targeted delivery of imaging probes and pharmaceuticals to these mineral sites. Metabolic bone diseases are characterized by an increase in bone resorption resulting in an imbalance between bone formation and resorption [1]. These diseases include osteoporosis, Paget's disease, bone cancers or metastases, and osteomalacia. The imbalance between bone formation and resorption results in undesired effects such as bone loss, enlarged or weak bones, and fractures [1]. Pathological calcifications are deposits of mineral in soft tissues, such as arterial calcifications in atherosclerosis [2-4], microcalcifications in breast tissue [5], and kidney stones [6]. These abnormal mineral deposits can cause pain, tissue malfunction, and possibly even death if not detected and treated.

The high concentration of mineral present in bone and pathological calcifications is distinct compared with all other tissues and thus provides opportunity for targeted delivery of drugs, including radiosensitizers and imaging probes. Targeted delivery enables the specific accumulation of a high local concentration of a therapeutic or imaging contrast agent to diseased bone or pathological calcifications. One approach to target agents with little or no affinity for bone or mineral deposits is to conjugate the agent to a mineral-binding molecule. Bisphosphonates (BPs) are the most widely utilized bone-binding ligand due to exhibiting high binding affinity to hydroxyapatite mineral. The high binding affinity of BPs for hydroxyapatite is a well-established property of BPs that was discovered in the 1960s and has led to the widespread use of BPs as drugs to treat metabolic bone disorders [7].

The overall goal of this review is to summarize the current state of knowledge and practice for the use of BPs as ligands for targeted delivery to bone and mineral deposits (Fig. 1).

The clinical history of BPs is first summarized to highlight the success of these molecules as drugs for metabolic bone diseases, due to the high binding affinity between BPs and bone mineral. Mechanisms of binding and the relative binding affinity of various BPs to bone mineral are introduced, including common methods for measuring binding affinity *in vitro* and *in vivo*. Current research is highlighted for the use of BP ligands for targeted delivery in various applications, including therapeutic drug delivery, imaging probes, and radiotherapy (Fig. 1). Last, and perhaps most importantly, key structure-function relationships are considered for the design of drugs with BP ligands, including the tether length between the BP and drug, the size of the drug, the number of BP ligands per drug, cleavable tethers between the BP and drug, and conjugation schemes.

2. History of bisphosphonates

BPs are a class of molecules used clinically to treat metabolic bone diseases by inhibiting the process of bone resorption. The first evidence for the biological function of BPs was reported by Fleisch and colleagues in 1968 [8]. Inorganic pyrophosphate (Fig. 2) was discovered to inhibit the formation and dissolution of calcium phosphonate crystals [9], suggesting that pyrophosphate regulates bone resorption and formation. BPs were subsequently synthesized as a more chemically stable analog of pyrophosphate, where the oxygen molecule bound to the two phosphonate molecules in pyrophosphate (P-O-P) was replaced by a carbon (P-C-P) (Fig. 2). This elemental substitution resulted in bonds that were resistant to degradation, creating biologically active molecules that were similar in structure to pyrophosphate and capable of being delivered to bone *in vivo* without degradation by hydrolysis [10]. The first synthesized BPs (sodium dichloromethylene diphosphonate, sodium methylene diphosphonate, and sodium ethane-1-hydroxy-1,1-diphosphonate) were shown to significantly impair *in vivo* bone resorption

in rats [10-12], which sparked interest in exploring BP compounds as therapeutics for bone diseases.

A BP therapeutic was first used in humans to inhibit undesired calcification. In 1969, etidronate (Fig. 2) was given to a child with fibrodysplasia ossificans progressiva to treat ectopic calcification [13]. Etidronate was also used to treat ectopic calcifications after spinal cord injury or total hip replacement [8]. However, the efficacy of etidronate in these cases has been inconclusive, perhaps due to the relatively lower binding affinity of etidronate discussed below. Additionally, the dose required to inhibit pathological calcifications in humans, such as kidney stones, was found to also impact normal mineralization [14]. Therefore, etidronate was abandoned for use as an inhibitor of ectopic calcification [8]. The next clinical use of a BP was a bone-targeting radionuclide for nuclear imaging [15], which was developed in the 1970s and is still used today. Bone scintigraphy is a nuclear imaging technique used to detect areas of high bone turnover associated with stress fractures, Paget's disease lesions, and bone cancers or metastases. A BP molecule is conjugated to a gamma-emitting technetium isotope, such that the radionuclide rapidly accumulates in areas of high bone metabolism after intravascular delivery due to the high binding affinity of BP to bone mineral.

BPs are currently the most widely used therapeutic in the treatment of metabolic bone diseases. BPs were introduced for the treatment of osteoporosis in the 1990s and are now the most commonly prescribed pharmaceutical for the treatment of postmenopausal bone loss with annual sales of millions of dollars [16]. The efficacy of BPs for inhibiting bone resorption is largely due to the ability of BPs to selectively bind to bone mineral [7,17] facilitating uptake by osteoclasts during osteoclastic-mediated bone resorption. BPs inhibit the recruitment and differentiation of osteoclasts, and cause morphological cellular changes and osteoclast apoptosis

[7,18-21], leading to reduced bone resorption. The high selectivity of BPs for mineral also results in a low overall cytotoxicity profile [22], which facilitated rapid clinical adoption of these drugs. There are seven BPs drugs currently approved for clinical use in the U.S. by the Food and Drug Administration, which differ in the structure of the side groups (R_1 and R_2) (Fig. 2).

3. Bisphosphonate binding to bone and mineral deposits

The structure of both the mineral and the BP has been shown to affect binding affinity and must therefore be considered when choosing the appropriate BP ligand for targeting. The most extensive research has focused solely on the interaction between hydroxyapatite mineral and BPs, due to widespread clinical use of BPs as therapeutics for metabolic bone diseases.

3.1. Effects of mineral type and crystal structure

Bone contains the overwhelming majority of mineral in the human body and is therefore crucial for calcium homeostasis. However, relatively minute amounts of pathological mineral deposits can also be associated with disease and are therefore crucial for diagnosis. The mineral phase of bone is a highly substituted carbonated apatite, which has a chemical and crystal structure similar to hydroxyapatite ($\text{Ca}_5(\text{PO}_4)_3\text{OH}$). Pathological mineral deposits occurring within soft tissues are most commonly composed of hydroxyapatite or calcium oxalate (CaC_2O_4).

BPs exhibit a relatively greater binding affinity to hydroxyapatite compared with other calcium minerals such as calcium oxalate, calcium carbonate, or calcium pyrophosphate [23-26]. This suggests that the chemical binding of BPs is dependent on the crystal structure of the mineral surface, where an increased concentration and the most appropriate spacing of superficial Ca^{2+} on hydroxyapatite surfaces enables a higher binding. This relationship is further

evidenced by a lower binding affinity of BPs for carbonated apatite versus pure hydroxyapatite due to the distortion of the crystal structure by the substitutions present in carbonated apatite [11,27]. The high binding affinity of BPs to hydroxyapatite compared with other calcium minerals is important for both targeting or avoiding bone. BPs used to treat metabolic bone diseases leverage selectivity for hydroxyapatite. On the other hand, if BP ligands are intended to deliver therapeutics or imaging probes to mineral deposits other than bone, the majority of the dose may be taken up by bone rather than the desired mineral site. High skeletal uptake of an agent intended to target pathological calcifications may be detrimental for efficient targeting, dosing, and avoiding off-target side-effects. Therefore, additional means may be needed to independently target bone versus pathological calcifications. However, pathological calcifications are most commonly found in tissues that are normally without mineral deposits when healthy (e.g., kidneys, aorta, breasts) and sufficiently distanced from bone tissue, such that BP conjugate imaging agents can still be effective in detecting these calcifications in spite of high skeletal uptake.

Hydroxyapatite selectivity may also be clinically useful in mammographic screening for breast cancer by detecting breast microcalcifications. Microcalcifications composed of hydroxyapatite are more commonly associated with cancerous lesions compared with those composed of calcium oxalate, which are nearly always associated with benign lesions [5]. A BP conjugated near-infrared imaging probe demonstrated selectivity for hydroxyapatite microcalcifications over calcium oxalate microcalcifications *in vitro* [28] and *in vivo* in rats [26]. This creates opportunity to reduce or eliminate unnecessary biopsies due to false positive detection of calcium oxalate microcalcifications by screening microcalcifications based on the mineral composition.

3.2. Effects of bisphosphonate molecular structure

The molecular structure of BPs (Fig. 2) greatly affects binding affinity to hydroxyapatite (Fig. 3). The P-C-P backbone presenting two phosphonate groups for chelating calcium ions on hydroxyapatite surfaces in a bidentate structure is critical for binding (Fig. 3). Other similar compounds, such as monophosphates or compounds with P-N-P or P-C-C-P backbones exhibit reduced binding affinity for hydroxyapatite [7]. The R₁ side group (Fig. 2) affects the binding affinity. BPs having an –OH in the R₁ [29] exhibit increased affinity due to the capacity for tridentate binding to hydroxyapatite (Fig. 3) [27].

The R₂ side group was originally thought to only impact the pharmacological activity of BP but recent studies demonstrated effects of the R₂ side groups on binding affinity [11]. The kinetic binding affinity of six different BPs for hydroxyapatite was measured to increase in the following order: clodronate, etidronate, risedronate, ibandronate, alendronate, zoledronate [11]. Thus, BPs with a nitrogen in the R₂ side group (zoledronate, alendronate, ibandronate, risedronate) exhibited a greater binding affinity than the non-nitrogen containing BPs (etidronate and clodronate) (Fig. 2). Molecular modeling has suggested that the nitrogen side groups may directly contribute to the binding affinity via hydrogen bonding with hydroxyl groups on hydroxyapatite surfaces (Fig. 3) [27,30]. The binding affinity was influenced by both the angle and distance of the N-H-O bond, with optimal binding occurring at a bond angle $\geq 125^\circ$ and a bond distance of 3 Å [27,30]. Based on these 3-D models, the molecular structure of alendronate is most advantageous (132°, 2.7 Å), providing an explanation for the higher binding affinity of alendronate compared with other nitrogen-containing BPs [27,30]. Differences in binding affinity were also explained by changes in the zeta potential of hydroxyapatite surfaces after adsorption of BPs *in vitro*, due to the charge associated with the R₂ side groups at pH 7.4. As

BPs with positively charged R₂ side groups (zoledronate, alendronate, ibandronate) bind the mineral surface, the zeta potential of the hydroxyapatite surface shifts to become more positively charged. This attracts the negatively charged phosphonate groups of BPs to bind due to electrostatic attraction and increases the binding capacity on the mineral surface [27].

3.3. Comparisons to other mineral-targeting ligands

Many other molecules besides BPs also exhibit bone-targeting characteristics. Many noncollagenous proteins that are found in bone exhibit binding affinity to hydroxyapatite [31] due to repeating amino acids such as glutamic or aspartic acid [32-34]. These amino acids exhibit a negative charge due to carboxylate ligands, which chelate calcium ions on the surface of hydroxyapatite. Peptides with glutamic acid and aspartic acid repeating units exhibited specific hydroxyapatite binding *in vitro* [34,35] and *in vivo* [35].

Direct comparisons between the binding affinity of BPs and glutamic or aspartic acid have varied in the literature. Peptides with eight repeating units of aspartic or glutamic acid exhibited faster and greater binding to hydroxyapatite compared with pamidronate or alendronate for up to 1 h *in vitro*, but a similarly high binding affinity for 2 to 24 h [36,37]. On the other hand, a peptide with six repeating units of aspartic acid did not exhibit greater binding to hydroxyapatite compared with tiludronate after 5 min incubation *in vitro* [35]. These studies suggest that the relative binding affinity of amino acids and BPs is governed by the number of peptide repeating units, the type of BP, and the incubation time.

Fundamental differences in the binding affinity of bone-targeting gold nanoparticles (NPs) have also been demonstrated. Gold nanoparticles (Au NPs) surface functionalized with alendronate exhibited faster and greater binding to hydroxyapatite *in vitro* and damaged bone tissue *ex vivo* compared with glutamic acid or phosphonic acid [38,39]. The alendronate-

functionalized Au NPs exhibited a six- or sixteen-fold greater binding affinity to hydroxyapatite when compared with glutamic or phosphonic acid-functionalized Au NPs, respectively, despite having fewer molecules adsorbed to the Au NP surface [38].

The use of amino acids as mineral targeting ligands has potential advantages and limitations compared with BPs. Unlike BPs, amino acids can be enzymatically degraded and cleared from the body after mineral binding [36], which minimizes the potential of cytotoxicity. However, the *in vivo* binding of aspartic acid to hydroxyapatite was lower compared with alendronate due to the high binding affinity of alendronate described above and possibly also due to rapid clearance of aspartic acid from circulation due to a highly negative charge [37]. Ligands which promote rapid clearance and excretion are expected to require a higher dose for effective mineral targeting compared with BPs, but this has not yet been confirmed by experiments. Although the remainder of this review will focus exclusively on the use of BPs, continued work to develop other mineral-targeting ligands is important for the future of mineral-targeting pharmaceuticals and imaging probes.

3.4. Common methods used to measure binding affinity

3.4.1. Langmuir adsorption Isotherms

BP binding to mineral *in vitro* is most commonly modeled using Langmuir equilibrium adsorption isotherms as,

$$V = \frac{V_{max} \cdot K \cdot c}{1 + K \cdot c}$$

where V is the amount adsorbed (mol m^{-2}), V_{max} is the adsorption maximum (mol m^{-2}), c is the molar equilibrium solution concentration (mol L^{-1}), and K is the equilibrium affinity constant (L

mol⁻¹) [27,40,41]. The adsorption maximum (V_{max}) and equilibrium affinity constant (K) are commonly calculated using linear regression after a double reciprocal transformation of the data [40]; however, nonlinear least squares regression provides more powerful and direct method for determining these parameters from the data [38,40,42]. Langmuir adsorption isotherms enable quantitative comparison of the binding affinity between BPs and/or BP conjugates, where the binding affinity of a BP molecule may change after conjugation to a payload.

Studies which report only the percent of the initial BP concentration that binds to the mineral substrate for a given experiment only provide one data point within the overall binding equilibrium between BP and the mineral, and thus an incomplete picture. Moreover, the initial concentrations of the BP (or BP conjugate) and mineral substrate must be the same between experiments in order to compare results using percent binding. Therefore, initial *in vitro* experiments investigating the binding affinity of BPs or BP conjugates should measure the equilibrium binding constant (K) and adsorption maximum (V_{max}) from the Langmuir adsorption isotherm to enable comparison with other studies.

3.4.2. *In vitro* methods

The binding of BPs to hydroxyapatite mineral is commonly evaluated *in vitro* by incubating specified concentrations of BPs and hydroxyapatite crystals for a specified amount of time and then separating the unbound BP from the hydroxyapatite crystals with bound BP. The concentration of unbound BPs is measured using various methods described below, and the bound concentration is calculated from this data and the known initial concentration of BP. The most common methods for measuring the unbound BP involve labeling the BP or payload with radionuclides, nanoparticles, or aromatic residues. Common radionuclides include iodine-125 (¹²⁵I), technetium-99 (^{99m}Tc), and terbium-160 (¹⁶⁰Tb), which are detected using a gamma-

counter and calibrated to known BP or payload concentrations [41,43-50]. BPs have been conjugated to gold nanoparticles allowing the initial and unbound concentration of gold to be measured using inductively coupled plasma optical emission spectroscopy (ICP-OES) [38,39,42] or ultra-violet (UV) absorbance [51]. Aromatic residues, which exhibit UV absorbance, were linked to peptides conjugated to BPs and the absorbance was correlated to the peptide concentration [36]. Note, that all the methods described above allow for the use of Langmuir models, but many of these studies only measured the percent binding of the BP conjugate for a single set of experimental conditions.

The crystal growth inhibition assay is another common *in vitro* method used to evaluate the binding affinity of BPs to hydroxyapatite mineral [11,52,53]. Briefly, hydroxyapatite crystals are formed in an environment with constant thermodynamic driving force (pH 7.4, 37°C) [54] and a volume of titrant, which has a specific concentration of BP, is added to maintain this environment. The volume of titrant is measured as a function of time to calculate the crystal growth rate. This growth rate is related to the Langmuir equilibrium adsorption isotherm as,

$$\frac{R_o}{R_o - R_i} = 1 + \frac{I}{KC}$$

where R_o and R_i are growth rates ($\text{mol m}^{-2} \text{min}^{-1}$) in the absence and presence of BP, respectively, C is the molar concentration of BP in solution (mol L^{-1}), and K is the adsorption affinity constant (L mol^{-1}) [11].

Nuclear magnetic resonance spectroscopy (NMR) has also been used to measure the binding affinity of BPs to hydroxyapatite [55,56]. Solid-state NMR allowed for direct investigations of the molecular structure and binding energy of different BPs bound to hydroxyapatite [55], while liquid-state NMR was used to measure the concentration of unbound

BPs, after incubating with hydroxyapatite, based on calibrations of the peak intensity [56]. Both solid-state and liquid-state NMR measurements allow for the use of Langmuir models.

The relative binding affinity of clinically available BPs has exhibited differences in rank order when using different *in vitro* measurement methods (Table 1). Although the differences are relatively small, it is important to recognize that different *in vitro* measurement methods can result in variations in measured binding affinities. Therefore, the reported binding affinity of a BP measured using one method should not be directly compared to that of a BP or BP conjugate measured a different method. Investigations of new BP molecules or conjugates require thorough characterization of the binding affinity.

The binding affinity of BPs to hydroxyapatite is also dependent on the *in vitro* environment, including the pH, ionic strength, and phosphonate concentration [11]. Therefore, these factors should be noted in experimental methods. Additionally, the binding affinity measured *in vitro* should not be assumed to reflect the *in vivo* binding affinity, as the presence of serum proteins on the surface of mineral will reduce the overall binding *in vivo*. For example, media containing serum proteins dramatically reduced binding affinity of BP conjugates to hydroxyapatite *in vitro* [38,45], but may best mimic the *in vivo* interaction of BP and mineral surfaces [43].

3.4.3 *In vivo* methods

The delivery and binding of BPs *in vivo* are also commonly monitored using radiolabeled-BP conjugates, such as ¹²⁵I- or ^{99m}Tc-labeled BPs or BP complexes. Radiolabeled BP conjugates are delivered intravenously and animals are euthanized after a specified time to measure the concentration of radionuclide in explanted tissues [43,44,46,49,59-62]. The biodistribution of BPs has been commonly measured in bones, such as femora and tibiae, and

organs, such as the kidneys, liver, spleen, heart, intestines, and brain. The concentration of BPs in the blood is measured as the bone-to-blood ratio to examine the clearance of BPs from the blood and the binding of BPs to bone. Radionuclide-labeled BPs can also be used to monitor BP binding and biodistribution longitudinally *in vivo*, avoiding the need to euthanize animals at each study time point [47]. However, as will be discussed below, the short-half life of radionuclides prevents tracking BPs *in vivo* over time periods exceeding 24 h. Therefore, BPs were recently conjugated to fluorophores in order to monitor the biodistribution, binding, and retention of BPs *in vivo* for up to 7 days after administration [63].

The ability to track BPs *in vivo* provides investigators with a powerful tool to investigate the targeted delivery and biodistribution of BP conjugates. The uptake and distribution of BPs in the skeleton is influenced by the delivery route and sites of active bone remodeling. Oral administration results in only ~0.7% of the total dose reaching the skeleton, while ~65% of the total dose reaches the skeleton after intravenous administration [64,65]. BP uptake is greater in trabecular bone compared with cortical bone due to greater blood flow, surface area, and bone turnover in trabecular bone [64]. BPs also accumulate in active sites of bone resorption more than bone formation due to a larger area of exposed hydroxyapatite crystals available for BP binding. Importantly, the uptake and biodistribution of BPs may be altered by the addition of a payload. Therefore, evaluations of BP conjugates require the ability to track BP conjugates *in vivo* over extended time periods after delivery.

4. Applications of bisphosphonates as a targeting ligand

4.1. Therapeutic drug delivery

4.1.1. Metabolic bone disease

Osteoporosis and other metabolic bone diseases are commonly treated with BPs [16,66] due to the high binding affinity of BPs to bone and their ability to inhibit bone resorption by promoting osteoclast apoptosis [18]. A number of recent reviews have thoroughly summarized the current state of knowledge of BPs used clinically (Fig. 2) as therapeutics for metabolic bone diseases [67-69]. Therefore, this information will not be covered here, although it is important to note that there has been mounting concern over limitations and potential negative side effects associated with long-term use of BPs [17], which has led to intense investigation of other potential drugs and targets to treat metabolic bone diseases. We will instead focus on BP conjugates investigated as therapeutics for metabolic bone diseases.

Molecular complexes have been formed by conjugating BPs to either catabolic (inhibitors of bone resorption) or anabolic (inducers of bone formation) drugs (Table 2). BPs were conjugated to many of these agents to enable targeted delivery of drugs that would otherwise have no affinity to bone. Thus, the functional role of the BP molecule in these complexes is exclusively for targeted delivery and not pharmacological activity, although clinical translation will require investigation of the latter given the known activity of BPs.

Estrogen replacement therapy has been considered an option to treat postmenopausal osteoporosis as estrogen depletion is known to decrease bone mass [70]. However, systemic delivery of estrogen has limited efficacy as estrogen receptors are present in many tissues besides bone tissue and increased levels of estrogen in postmenopausal women have been associated with an increased risk of certain cancers, such as breast or uterine cancer [70]. Therefore, various schemes have been investigated to conjugate BP to 17 β -estradiol as means to increase the dose of estrogen delivered to bone tissue, while decreasing estrogen accumulation in other soft tissues [71-76]. The *in vivo* efficacy of these complexes has varied from no added benefit of

the bone-targeting ligand [71] to a selective increase in bone mineral density compared with weight change of the uterus, indicating that the BP ligand enabled targeted delivery of 17 β -estradiol [72,73]. The reason for the difference in the efficacy between these studies may be due to a difference in the dose of 17 β -estradiol delivered, with the higher dose stimulating an increase in bone mass and demonstrating benefit of the BP targeting ligand [72,73].

BPs have also been conjugated to other anabolic agents such as prostaglandin E₂ [77], agonists against the EP4 receptor for prostaglandin E₂ [78], and parathyroid hormone (PTH) [79]. Prostaglandin E₂ is an enzymatically-derived metabolite of polyunsaturated fatty acids, which can stimulate bone formation leading to increased bone mass [80], but undesired side effects after systemic delivery of prostaglandin E₂ has limited use as a therapeutic. Therefore, alendronate was conjugated to prostaglandin E₂ for targeted delivery to mineral which was verified *in vitro* and *in vivo* [77]. Unfortunately, neither the alendronate-conjugated prostaglandin E₂ nor free drug were able to overcome the bone mass loss in a rat model of osteoporosis, possibly due to instability of the prostaglandin E₂ molecule [77]. Therefore, alendronate ligands were conjugated to an agonist against the EP4 receptor for prostaglandin E₂ in an attempt to improve *in vitro* stability and therapeutic efficacy compared with BP-conjugated prostaglandin E₂ complexes [78]. This complex enabled targeted delivery *in vivo*, but the biological efficacy has not yet been evaluated. PTH is another promising anabolic agent to treat osteoporosis that is limited by a broad biodistribution and inefficient targeting after systemic delivery. PTH was conjugated with BP ligands via a hydrazine linkage, resulting in targeted delivery to bone *in vitro* while retaining the biological activity of PTH [79].

Antiresorptive agents, including calcitonin [47,81] and osteoprotegerin [48], have been investigated as alternatives to BPs for the treatment of osteoporosis. Calcitonin is used in the

treatment of Paget's disease, bone metastases, and osteoporosis [82], which inhibits osteoclast-mediated bone resorption [83]. However, free calcitonin has a very short half-life and is rapidly cleared from the body, reducing the dose that reaches the bone. Furthermore, calcitonin receptor is expressed by non-skeletal cell types in addition to osteoclasts, which also reduces the dose delivered to the bone. Therefore, calcitonin was conjugated with BP for targeted delivery to bone [47,81]. BP-conjugated calcitonin exhibited high binding affinity to hydroxyapatite mineral *in vitro* and bone *in vivo* compared with free calcitonin [47,81,84], and the biological cellular activity of calcitonin was maintained after BP conjugation [81,84]. BP-conjugated calcitonin also preserved the bone volume and bone mineral density more than non-targeted calcitonin in a rat model of osteoporosis [84]. Osteoprotegerin is a factor that disrupts the RANK – RANKL signaling pathway, leading to decreased osteoclastogenesis [48]. BP-conjugated osteoprotegerin exhibited greater hydroxyapatite binding *in vitro* and bone binding *in vivo* compared with free osteoprotegerin [48]. However, the biological activity and therapeutic efficacy of BP-conjugated osteoprotegerin has not yet been evaluated.

The concept of conjugating BPs to proteins that promote bone formation and healing was introduced by Uludag and coworkers in 2000 [45] and has continued into the present with a significant body of work reviewed elsewhere [59,85,86]. Protein-based therapeutics are promising options to treat bone diseases by directly modulating cellular signaling mechanisms [85]. However, most proteins do not exhibit specific binding to hydroxyapatite but have ubiquitous targets throughout the body. Therefore, BP molecules could be conjugated to proteins to improve bone-targeting, reduce the required dose, and reduce extraosseous accumulation of the proteins. BPs have been conjugated to many model proteins, such as bovine serum albumin, lysozyme, and IgG, and exhibited increased bone uptake compared with free

protein *in vivo* [45,61]. Therefore, these studies suggest that BPs can be used as a targeting ligand to deliver proteins to bone tissue.

4.1.2. Bone cancer and metastases

The skeleton is a common site for cancer metastasis [87,88]. Tumors in the skeleton alter the normal homeostasis of bone by disrupting the bone remodeling cycle which leads to bone pain, fractures, and hypocalcemia [89]. Treatment options are typically limited to reducing bone pain via palliative radiation therapy, analgesics, or BPs [89]. Radiotherapy and chemotherapy agents can be used to treat the tumor, but are not always successful depending on the tumor type [90]. BPs can be used to treat and prevent skeletal morbidity or hypercalcemia associated with metastases [89,90]. Recent preclinical studies have provided evidence that BPs may also have an antitumor effect by inducing cancer cell apoptosis and inhibiting cell invasion [91], suggesting that BPs may be used to treat the tumor in addition to the surrounding bone.

The need for improved therapeutics is particularly great in bone cancers due to the problems associated with surgical resection of skeletal lesions and the development of chemoresistant tumors. As with many cancer types, targeted therapies are being investigated as a means to improve therapeutic outcomes by enabling the delivery of a high concentration of an antitumor agent to the tumor site and reducing adverse side effects associated with systemic delivery of non-targeted drugs [92]. Therefore, the high binding affinity of BPs for bone is being investigated as a means to enable targeted delivery of antitumor agents to metastases (Table 3) to promote the accumulation of BPs in areas of high bone turnover resulting in greater retention of BP conjugates in cancerous lesions compared with healthy bone.

One of the first studies demonstrated that cisplatin conjugated with phosphonates exhibited greater antitumor activity compared with cisplatin alone in an osteosarcoma model in

rats [93], but did not determine whether the enhanced activity was due to targeted delivery or the combined antitumor effects of cisplatin and BP. BP-cisplatin conjugates were more recently shown to enhance anticancer effects compared with cisplatin alone using an *in vitro* cell culture model where delivery does not play a role [94]. Therefore, future studies need to measure the accumulation of BP-cisplatin conjugates in bone metastases *in vivo* and compare the therapeutic efficacy of BP-cisplatin versus cisplatin alone, BP alone, and co-delivery of cisplatin and BP alone. Other BP-conjugated chemotherapy agents that have been investigated include BP conjugated to taxanes [95-97], platinum complexes [98], camptothecin [99], gemcitabine [49,100-102], doxorubicin [103,104], methotrexate [105], proteasome inhibitors [106,107], arabinocytidine [108], and an anti-angiogenic agent, TNP-470, which is a synthetic analog of fumagillin [109]. Overall, BP conjugation has been repeatedly shown to improve targeted delivery of these agents to bone metastases. In some cases, targeted delivery reduced systemic toxicity compared with the free drug and/or free BP [96,104,109].

4.1.3. Other bone diseases

Inflammatory bone diseases include osteomyelitis, which is an infection in the bone that causes an inflammatory response and bone necrosis [110], and rheumatoid arthritis, which is an autoimmune disorder that can eventually lead to bone erosion [111]. Both of these diseases must be treated with large doses of pharmaceuticals in order to deliver a sufficient amount to the bone [112]. Targeted delivery of antibiotics or anti-inflammatory agents could help to reduce the overall dose.

Antibacterial agents conjugated with BPs exhibited 13-fold greater binding to bone powder compared with the free agents and were able to inhibit bacterial growth in an *in vitro* model of osteomyelitis even after the BP-antibacterial conjugate was first bound to the bone *ex*

vivo [113]. More recently, prodrugs have been developed to release the antibacterial agent from the BP conjugate in order to improve the biological activity of the drug [112,114]. These BP-antibacterial agent prodrugs exhibited high binding affinity and activity both *in vitro* and *in vivo* [114].

Diclofenac is an anti-inflammatory drug used to treat rheumatoid arthritis, which can lead to negative gastrointestinal side effects [115]. BP-diclofenac conjugates have been developed as a bone-targeted drug to treat inflammatory bone diseases [116,117]. BP-diclofenac conjugates exhibited greater bone accumulation *in vivo* compared with free diclofenac [116] and improved therapeutic efficacy, as measured by a reduction in the mean effective dose that was necessary to reduce swelling in a rat model of arthritis and a reduction in side effects compared with the free drug [116]. However, it is important to note that the accumulation of BP-diclofenac in the liver was dose-dependent; a 10-fold increase in administered dose resulted in decreased bone accumulation but increased liver accumulation [116,117]. Therefore, dose escalation studies will be important to determine the most appropriate dose for therapeutic efficacy.

Legg-Calvé-Perthes disease results in osteonecrosis of the hip joint in children due to a temporary block in the blood supply [118]. BP-functionalized gold nanoparticles were proposed as a drug delivery system to treat osteonecrosis [119]. Osteoclastogenesis and osteoclast function was decreased *in vitro* after incubation with BP-functionalized gold nanoparticles, but not citrate-coated gold nanoparticles [119]. Interestingly, the ability of BP-functionalized gold nanoparticles to induce osteoclast apoptosis *in vitro* demonstrated that the cellular activity of BP was not hindered after conjugation to a payload. However, the delivery of BP-functionalized gold nanoparticles to areas of osteonecrosis *in vivo* may be challenging due to a lack of blood supply and must be evaluated.

4.1.4. Engineered drug delivery platforms

Synthetic polymers and nanoparticles have been conjugated to BPs and investigated as drug delivery platforms for a variety of applications. Synthetic polymers such as poly(ethylene glycol) (PEG) [37,51,120], poly(ethylenimine) [121], poly(L-lysine) [121], *N*-(2-hydroxypropyl)methacrylamide (HPMA) [37,58], and poly(γ -benzyl-L-glutamate) (PBLG) [122] have been conjugated to BP as versatile bone-targeting drug carriers and have universally exhibited high binding affinity to hydroxyapatite. Water-soluble polymers [123] are attractive drug carriers due to biocompatibility, biodegradation *in vivo*, and an ability to increase the water solubility of many hydrophobic drugs. Additionally, polymers can be used to increase the size of small molecule drugs and thereby limit the biodistribution [62], which might increase the dose that can be delivered to challenging targets like bone.

BP-functionalized nanoparticles have been developed as carriers to deliver drugs to bone. The goal of using nanoparticles for drug delivery is to enable (1) specific drug targeting and delivery, (2) reduced off-target side effects, and (3) increased therapeutic efficacy through higher delivered doses [124]. Nanoparticles can also enable the drug to be encapsulated, instead of conjugated to the nanoparticle surface, which may be advantageous if chemical conjugation affects the drug activity [60]. The majority of BP-functionalized nanoparticle drug delivery systems have consisted of liposomes [125-128] or polymeric nanoparticles [107,129-132], as these are readily loaded with a variety of different drugs and surface functionalized with BP molecules. Calcium phosphonate nanoparticles were also conjugated with BP and proposed as a highly biocompatible bone-targeted drug delivery system [133]. BP-functionalized nanoparticles have almost universally exhibited high binding affinity to hydroxyapatite *in vitro* regardless of

the payload (e.g., liposome versus polymer) [107,125-129,132,133], although there have been no direct comparisons between different systems.

4.2. Imaging

Bone-targeting nuclear imaging agents were among the first applications of BPs with the introduction of ^{99m}Tc and BP conjugates in the 1970s [134]. Bone scintigraphy has become a common nuclear imaging technique with more than 3 million bone scans performed in the United States in 2005 [135]. ^{99m}Tc -BP conjugates are delivered intravascularly and target exposed hydroxyapatite mineral such that uptake is imaged to detect areas of high bone turnover, such as Paget's disease lesions and bone cancers or metastases.

The chemical structure of clinically available ^{99m}Tc -BP conjugates, such as ^{99m}Tc -methylene diphosphonate (^{99m}Tc -MDP) and ^{99m}Tc -hydroxymethylene diphosphonate (^{99m}Tc -HMDP), are not ideal for the intended application of targeting and labeling areas of high bone turnover for non-invasive imaging [136]. A lack of chemical stability *in vivo* reduces specificity due to lower bone uptake and higher soft tissue uptake of ^{99m}Tc [136]. Furthermore, slow blood clearance or bone uptake requires long time intervals between administration and imaging (~3-4 h) [136]. The chemical structure of ^{99m}Tc -BP conjugates are not well-defined, but are thought to be mixtures of monomers and polymer species which have different properties leading to low overall efficacy and consequently requiring the administration of high doses [136]. Furthermore, the BP acts as both the radionuclide chelator and bone-targeting ligand [137] (Fig. 4a). This dual function of the BP molecule lowers the overall binding affinity of ^{99m}Tc -BP conjugates due to only one of the phosphonate groups being free for binding to hydroxyapatite surfaces [138].

The limitations of ^{99m}Tc -BP conjugates have motivated research aimed at improving radionuclide-BP conjugates for bone scintigraphy, as well as research for new targeted imaging

agents for other imaging modalities, such as near-infrared (NIR) fluorescence imaging, positron emission tomography (PET), magnetic resonance imaging (MRI), and X-ray imaging with computed tomography (CT). New imaging agents are developed for the goal of improved clinical diagnostic imaging of bone metabolism, bone metastases, or pathological calcifications. Additionally, new imaging agents that are designed to track BP *in vivo* can facilitate improved understanding of BP binding, biodistribution, and pharmacokinetics in preclinical drug development.

4.2.1. Novel bone scintigraphy agents

A number of studies have investigated the use of bifunctional chelator ligands to separate the BP from the radionuclide (Fig. 4b), allowing the BP to function exclusively for bone-targeting [23,138-144]. The availability of both phosphonate groups for bone-targeting results in increased binding affinity, increased kinetics for bone uptake, decreased soft tissue uptake, and reduced time required between administration and imaging [138]. Examples of bifunctional chelator ligands include 6-hydrazinopyridine-3-carboxylic acid (HYNIC) [138,142], pyrazolyl-containing backbones [139,140], and diethylene triamine pentaacetic acid (DTPA) [144], among others [23,141,143]. ^{99m}Tc -bifunctional-BP complexes exhibited increased *in vitro* binding affinity and faster binding kinetics to hydroxyapatite crystals compared with ^{99m}Tc -MDP [23,138]. A few ^{99m}Tc -bifunctional-BP complexes have enabled higher bone uptake *in vivo* compared with ^{99m}Tc -MDP [138,142,143], although others have exhibited similar bone uptake at the time points investigated [23,140]. Therefore, the greatest benefit of the bifunctional ligands has thus far been a greater bone-to-blood ratio of the ^{99m}Tc -bifunctional-BP complexes [138,140,142,143], which should reduce the time delay between contrast agent administration and imaging.

4.2.2. Targeted fluorescence imaging

Fluorescently-labeled BPs have been investigated for monitoring bone metabolism and for tracking the biodistribution of BPs *in vivo*. The first NIR fluorescent BP conjugate was developed by Frangioni and coworkers in 2001 by conjugating pamidronate to the NIR fluorophore, IRDye78 [25]. The conjugate enabled *in vivo* fluorescence imaging of osteoblast activity in mice with greater sensitivity and spatial resolution compared with bone scintigraphy using ^{99m}Tc -MDP, suggesting NIR-BP conjugates could be used for non-invasive imaging of bone activity. This conjugate also enabled *in vivo* fluorescence imaging of vascular calcifications [145] and breast microcalcifications [26,146], including dual-mode NIR/SPECT imaging of breast microcalcifications when combined with ^{99m}Tc -MDP [28].

NIR-BP imaging probes using pamidronate recently became commercially available (OsteoSense™, Perkin Elmer) and have been used in a wide range of preclinical animal models investigating, for example, noninvasive, longitudinal imaging of bone metabolism [147-150] (Fig. 5a), site-specific BP deposition and retention [148], bone regeneration in novel tissue engineering applications [151], and the formation of pathological calcifications such as kidney stones [152], vascular calcifications [153] (Fig. 6a), and breast microcalcifications [154]. Additional novel NIR probes conjugated to BPs other than pamidronate have also been developed, including alendronate [155] and risedronate [156]. NIR imaging was therefore also used to compare differences in the binding affinity and biodistribution of different BPs *in vivo* [63] (Fig. 5b).

Bone-targeting fluorescent imaging probes have become powerful tools in preclinical animal models to monitor bone metabolism or track BP *in vivo* as longitudinal imaging can be conducted over weeks. This is a direct advantage over ^{99m}Tc -BP agents and nuclear imaging as

^{99m}Tc has a biological half-life of only one day which prevents studying the retention of BPs *in vivo* [148]. Additionally, the high sensitivity of optical imaging techniques enables detection of very small pathological calcifications, which could provide a means to study the initial formation of these mineral deposits *in vivo*. However, fluorescence imaging of bones in humans is limited by the overall depth penetration. Frangioni and coworkers calculated an exponential decay constant of $k = -0.43 \text{ mm}^{-1}$ from their experiments using IRDye78 *in vivo*, demonstrating that the NIR signal intensity decreased by 50% at 2.5 mm from the skin surface [25]. Therefore, despite their utility in preclinical studies, bone-targeted fluorescent probes are not likely to replace the current bone scintigraphy agents, such as ^{99m}Tc-MDP, for clinical imaging in humans.

4.2.3. Targeted PET, MRI, X-ray imaging

Although clinical use of targeted BP imaging agents has been dominated by bone scintigraphy, there have been recent efforts to develop BP-functionalized contrast agents for other imaging modalities, including positron emission tomography (PET), magnetic resonance imaging (MRI), and X-ray imaging with computed tomography (CT). Bone or mineral targeted imaging agents for PET, MRI, and CT could provide a translational pathway for improved clinical diagnostic imaging of skeletal abnormalities, such as tumors or pathological calcifications. Na¹⁸F-fluoride PET is already used clinically for imaging bone metastases and is considered superior to ^{99m}Tc-MDP scintigraphy due to a demonstrated increase in sensitivity and specificity [157]. Additionally, PET imaging can be conducted 30-90 minutes after contrast agent administration compared with 3-6 h for bone scintigraphy [157]. However, Medicare and Medicaid will not currently reimburse providers for PET imaging of benign diseases [135], inhibiting widespread use. MRI enables high spatial resolution and detection sensitivity without radiation exposure to the patient [158]. Although MRI produces strong soft tissue contrast,

contrast agents are needed to image mineralized tissues or deposits [159]. CT provides anatomic imaging with high spatial and temporal resolution [158], especially for bone. CT is also offers relatively wide availability and lower cost compared with MRI and PET, and lower radiation exposure than SPECT or PET, which utilize radioisotopes and require combined CT for anatomic imaging. However, CT has a relatively low sensitivity compared to SPECT, PET, or MRI, and low soft tissue contrast compared with MRI [160].

PET and MRI agents rely on the conjugation of BP molecules to a chelator, such as 1,4,7,10-tetraazacyclododecane-1,4,7,10-tetraacetic acid (DOTA) or 1,4,7-triazacyclononane-*N,N',N''*-triacetic acid (NOTA), which complex with positron-emitting radionuclides for PET imaging or lanthanide metals for MRI imaging [136]. A BP-DOTA conjugate, (4-[(bisphosphonomethyl)carbamoyl]methyl)-7,10-bis(carboxymethyl)-1,4,7,10-tetraazacyclododec-1-yl)acetic acid (BPAMD), was first introduced in 2005 as a bone targeting chelator for gadolinium (Gd) to create Gd(III)-BPAMD complexes for T1 MRI imaging [161]. Gd(III)-BPAMD binding to hydroxyapatite *in vitro* led to a significant increase in MRI relativity demonstrating the potential of this contrast agent to enable MRI imaging of bone mineral [161]. Novel PET agents have been synthesized by labeling BPAMD with positron-emitting gallium-68 (^{68}Ga BPAMD) [162-164]. The first human clinical study demonstrated greater uptake and improved detection of bone metastases with ^{68}Ga BPAMD compared with the current clinically available PET agent, ^{18}F -fluoride [162]. In general, BP-DOTA conjugates have exhibited high binding affinity *in vitro* [50,161,163,165-167] and *in vivo* [162-167]. BP-DOTA conjugates also exhibited greater binding affinity than $^{99\text{m}}\text{Tc}$ -MDP [164,165], indicating their utility for bone-specific imaging using PET or MRI, comparable to bone scintigraphy.

Recently, other BP-DOTA conjugates have been synthesized for PET and MRI to improve the *in vivo* binding affinity and blood clearance by altering the structure or increasing the length of the spacer between the BP and DOTA or NOTA [41,165,167]. The replacement of an amine group at the link between DOTA and BP with a negatively charged phosphonic acid group resulted in greater binding affinity *in vitro* [41] and *in vivo* [167] compared with BPAMD, and similar bone uptake compared to ^{99m}Tc -MDP and ^{18}F -fluoride [164]. ^{68}Ga NOTA-BP agents exhibited high binding affinity to hydroxyapatite *in vitro* and bone *in vivo*, as well as a greater bone-to-blood ratio compared with ^{99m}Tc -MDP and ^{18}F -fluoride [165]. Therefore, these new BP-DOTA conjugates with greater separation between DOTA and BP are promising for PET and MRI imaging of bone or mineral pathologies [136]. However, the higher cost of PET or MRI compared with bone scintigraphy may inhibit widespread clinical use of these technologies for bone imaging.

X-ray contrast agents based on BP-functionalized gold nanoparticles (BP-Au NPs) were investigated as potential imaging agents for microdamage in bone tissue [38,39,42] and pathological calcifications, specifically breast microcalcifications [168,169], based on the high binding affinity of BP-Au NPs to hydroxyapatite [38]. Au NPs were surface functionalized with alendronate through adsorption of the amine side group to the Au NP surface opposite the two phosphonate groups for binding to hydroxyapatite [38]. BP-Au NPs targeted microcalcifications due to specific binding to hydroxyapatite and enabled improved sensitivity and specificity via contrast-enhanced detection of model breast microcalcifications within the surrounding mammary tissue [168,169], including radiographically dense mammary tissues [170].

The major challenge for the use of targeted contrast agents to image bone or pathological mineral deposits with CT is the need to deliver a sufficient mass concentration for contrast

enhancement [171]. For example, the theoretical minimum detectable mass concentration of gold in bone is ~0.34 wt% or ~3.4 mg Au/g bone tissue [171,172]. Thus, CT has a relatively low sensitivity and requires higher concentrations of contrast agents compared with MRI, which can detect millimolar concentrations, or nuclear imaging (SPECT, PET), which can detect micromolar concentrations [173].

In summary, BP-conjugated imaging agents have been developed for nuclear (SPECT, PET), optical (NIR), MRI, and X-ray (CT) imaging. Depending on the intended target, BPs can be conjugated to an imaging probe for any of the different modalities (Fig. 6). For example, atherosclerotic vascular calcifications have been targeted and imaged *in vivo* using BP-conjugated NIR [153] or SPECT [174] contrast agents (Fig. 6a), while breast microcalcifications associated with cancer were also targeted and imaged *in vivo* using BP-conjugated NIR [29], SPECT [29], and X-ray/CT [169,170] contrast agent (Fig. 6b). A logical next step will be to combine or design BP-conjugated imaging probes for dual- or tri-modal imaging. For example, Bhushan *et al.* developed a novel NIR/SPECT probe for imaging breast microcalcifications [29], which could be used to target and image bone metastases as well as to assess the utility of NIR imaging *in vivo*.

4.3. Radiotherapy

Targeted radiotherapy to the skeleton is currently used clinically to treat pain caused by bone metastases [136]. In particular, internal radiotherapy uses close-range α -, β -, and γ -emitting radionuclides, which are targeted to the skeleton and selectively taken up by bone metastases to deliver a high local dose of radiation. Samarium-153-ethylene diamine tetramethylene phosphonate (^{153}Sm -EDTMP) has proven clinically effective in reducing the pain associated with bone metastases [175]. The phosphonic acid group (EDTMP) is complexed to Sm and facilitates

binding of the radionuclide to bone. However, this complex is very unstable *in vivo* and thus requires co-administration of free EDTMP [176]. Rhenium-188 (^{188}Re) is a radionuclide, similar in chemistry to $^{99\text{m}}\text{Tc}$, which has been complexed with HEDP (^{188}Re -HEDP) as a targeted radionuclide [177], similar to $^{99\text{m}}\text{Tc}$ -HEDP agents. Clinical trials have indicated that ^{188}Re -HEDP may be effective as a β -emitting radiotherapy agent for bone metastases [177]. However, similar to the disadvantages of $^{99\text{m}}\text{Tc}$ -HEDP discussed above, ^{188}Re -HEDP degrades quickly *in vivo* inhibiting retention of the radionuclide at the lesion [136].

New BP-radionuclide conjugates are being investigated to improve chemical stability and binding affinity for delivery of a high local dose to bone metastases. Bifunctional ligands are being investigated to separate the BP molecule from the radionuclide chelating groups, using parallel strategies discussed above for $^{99\text{m}}\text{Tc}$ -BP conjugates. Isolating the BP molecule from the radionuclide enables both phosphonate groups to bind to mineral surfaces. This strategy resulted in increased *in vivo* binding and accumulation in areas of high bone turnover compared with ^{188}Re -HEDP agents in mice [176,178,179]. Many other radionuclides, including ^{211}At [180,181], ^{160}Tb [50], and ^{125}I or ^{131}I [180,182] have been conjugated with BPs and investigated in preliminary studies for targeted radiotherapy using different emitters.

5. Design considerations for future investigations

The use of BPs as a targeting ligand for the delivery of therapeutic drugs or imaging probes requires the design of novel molecular conjugates (Fig. 1). The functional requirements of these conjugates are to target and bind to mineral with high affinity, while not altering the function of the therapeutic agent or imaging probe that is being delivered. These functional requirements can be met by designing the molecular structure of the conjugates, but systematic study of structure-function relationships has been lacking. Therefore, we have identified several

key aspects of molecular structure for the design of agents utilizing BPs as a targeting ligand, including the tether length between the BP and payload, the size of the payload, the number of BP ligands per payload, cleavable tethers between the BP and payload, conjugation of BPs to the payload, and comparison between BPs and other mineral targeting ligands.

5.1. Tether Length

The tether length is the length of the molecular linker or spacer between the BP molecule and payload, but not necessarily the physical distance between the two, as linkers tend to be flexible molecules. Longer tether lengths are thought to reduce steric hindrance between the payload and targeting ligand enabling greater binding affinity, as the targeting ligand is free to interact with the intended surface. However, studies have demonstrated that a shorter tether length between BPs and a protein resulted in greater binding to hydroxyapatite *in vitro* [183] and *in vivo* [184]. This apparent paradox was explained in a review by Zhang *et al.* [86] by (1) a greater local concentration of BPs per payload as a shorter tether length reduces the spacing between BPs, (2) non-specific interactions between the protein itself and hydroxyapatite, and (3) possible electrostatic or hydrophobic interactions between the tether and hydroxyapatite. Another group reported no effect of the tether length for an amine terminated R₂ side group on binding to hydroxyapatite *in vitro* when no protein was attached [53], but all the investigated tether lengths exhibited a greater binding affinity compared with unmodified BP suggesting that an increased tether length promoted interactions of the R₂ side group with the hydroxyapatite surface (cf., Fig. 3c.). The same group also demonstrated no effect of tether length on binding to hydroxyapatite *in vitro* when the protein was attached [79]. Therefore, the effect of the tether length on the binding affinity of BP-protein conjugates is not yet clear and must be determined for new BP-protein conjugates.

The tether length of a polyethylene glycol (PEG) spacer between polymer nanoparticles and BP has been shown to affect the binding affinity to hydroxyapatite *in vitro* [129]. A PEG spacer with a molecular weight of 2000 Da exhibited lower binding to hydroxyapatite compared with 550 and 750 Da, which was attributed to folding of the longer chains inhibiting interaction between the BP and hydroxyapatite [129]. Interestingly, unpublished data in our lab has indicated BP-PEG-conjugated gold nanoparticles with a PEG spacer molecular weight of 2000 Da resulted in greater binding to hydroxyapatite *in vitro* compared with 1000 or 5000 Da. Therefore, the effect of the tether length on the binding affinity of BP-nanoparticle conjugates is also not yet clear and must be determined for new BP-nanoparticle conjugates.

5.2. Size of the payload

The size of the payload is well-known to affect the biodistribution and accumulation of BP conjugates *in vivo*, especially after intravenous administration. In order to reach active bone forming units within cortical or trabecular bone after systemic intravenous delivery, BP conjugates must extravasate blood vessels through capillary fenestrae, which are normally up to 60 nm in size [185,186] and up to 150 nm in size within tumors [187]. Therefore, BP conjugates should be smaller than this size for targeted delivery to bone or bone metastases [60]. BP molecules (Fig. 2), BP-radionuclide conjugates, and BP-conjugated fluorophores are well below this size. The increase in molecular weight due to a conjugated radionuclide or fluorophore was shown to slightly alter the biodistribution compared with free BPs, but delivery to bone was not hindered [65]. However, the delivery of BP-conjugated nanoparticles and macromolecules to bone may be limited by size.

BP-functionalized bovine serum albumin (BSA) nanoparticles, with a 77 nm hydrodynamic diameter, exhibited very little bone-targeting in rats after intravenous

administration [60], suggesting that the nanoparticle size may have hindered delivery to bone. In contrast, BP-functionalized nanoparticles with a hydrodynamic diameter of 195 nm [107] and 115 or 170 nm [132] exhibited significant bone accumulation after intravascular administration. Note, however, that the two latter studies only reported a relative fluorescence and did not measure the concentration or percent of the initial dose that was delivered to bone. Nonetheless, the drug encapsulated within the BP-functionalized nanoparticle did induce changes in bone mass and architecture, suggesting that the nanoparticles were delivered to the skeleton [107]. Thus, the effect of BP conjugate size on delivery to bone, especially for nanoparticles and macromolecules greater than 10 nm in size, is not well understood but fundamentally important.

Targeted delivery to pathological calcifications may also be limited by blood supply to the host tissue and the ability of BP conjugates to extravasate vessels. For example, kidney stones must be targeted by agents smaller than the 5.5 nm glomerular filtration cutoff for passage through the kidneys [188]. The size of BP conjugates designed to target breast microcalcifications is currently unknown and may be dependent on the presence of a tumor with leaky vasculature. Therefore, the delivery of BP conjugates to pathological calcifications requires different design constraints compared with delivery to the skeleton. Efficient delivery to pathological calcifications may be improved by local administration [169] or tailoring the overall size of the BP conjugate to limit bone perfusion and increase blood circulation [62].

5.3. Number of BP ligands per payload

An increased number of BP ligands per payload has been demonstrated to promote greater binding affinity to hydroxyapatite in numerous *in vitro* studies [42,43,45,62,107,125,189], but *in vivo* studies have reported varying results [43,62]. The amount of alendronate conjugated to an HPMA copolymer did not result in differences in

skeletal accumulation at any time point after intravascular injection [62]. In contrast, a dendritic tetra(bisphosphonic acid) molecule conjugated to BSA exhibited greater skeletal accumulation compared with a similar complex with fewer BP groups per BSA, but the measured difference in BPs per BSA was small suggesting that other factors may have contributed to the differences in skeletal accumulation [43]. Once again, the effect of the number of BP ligands per payload on binding affinity to hydroxyapatite is not well understood and warrants further investigation. Characterization of ligand density on nanoparticles and macromolecules can be challenging but, by way of example, methods have been developed for measuring the surface density of BPs on gold nanoparticles [42].

5.4. Cleavable tethers

Cleavable molecular tethers between the BP molecule and payload are intended to be stable during delivery and then labile after the BP binds to the mineral to enable local release of the payload [53]. Therefore, molecular linkages are designed to be cleavable under physiological conditions that are specific to the targeted site of interest. Examples include a pH-triggered linkage that is labile at low pH, such as in areas of bone resorption or fracture healing [53], or a disulfide linkage that is cleavable in the presence of thiols [44,190,191]. Simpler methods include designing a hydrolyzable molecular linker that degrades slowly *in vivo* [99]. However, this method requires that the degradation rate is carefully controlled to be longer than the circulation time in order to deliver the agent to the bone before being degraded. The release of a chemotherapy drug from a BP molecule by hydrolysis of a cleavable tether exhibited a half-life of 40 h *in vitro* [99]. Whether or not this half-life is suitable for *in vivo* delivery to bone is not known. Overall, cleavable molecular tethers are a nascent but promising strategy for the targeted delivery of drugs to bone and pathological calcifications using BP ligands.

5.5. Conjugation scheme

The methods used to conjugate BP molecules to the payload must neither alter the activity of the payload nor eliminate the binding affinity of BPs. As described above, bifunctional ligands have been designed for conjugating BPs to radionuclides to free both phosphonate groups for bone-targeting [23,136-142]. BP-radionuclide conjugates with bifunctional ligands exhibited greater binding affinity compared with traditional designs where the BP molecule acts as both the metal chelator and bone-targeting group [23,136]. In general, conjugation schemes that preserve the availability of both phosphonate groups for chelating calcium ions are necessary for maintaining a high binding affinity to mineral. Therefore, molecular linkages for conjugation should attach via the R_1 or R_2 side chains.

Uludag and colleagues have investigated multiple schemes for conjugating BPs to proteins [86] and polymers [121,189] for delivery to bone paying careful attention to location(s) of BP attachment to the molecular structure to maintain bioactivity. First, aminoBPs were conjugated to the lysine amino acids in BSA and shown to exhibit greater binding affinity to hydroxyapatite *in vitro* and increased bone localization *in vivo* compared with unmodified BSA [45,61]. However, this conjugation scheme attached BPs to the protein core, which was thought to negatively impact the protein bioactivity [192], although this was not investigated as BSA was just a model protein. Therefore, a new scheme was developed for conjugating BPs to carbohydrate groups, which do not play a role in the bioactivity of most proteins [192]. The carbohydrate conjugation scheme resulted in greater binding affinity to hydroxyapatite *in vitro* compared with the previous scheme using lysine amino acids [192]. However, both the carbohydrate and lysine conjugation schemes resulted in no bone binding *in vivo* while the lysine scheme with a much shorter linker did result in bone binding [184].

The preceding studies highlight that the conjugation scheme – including the conjugation chemistry, molecular length, and placement on the payload – affects the mineral binding affinity and therefore must be considered. Also, the conjugation scheme that enables the greatest binding affinity *in vitro* may not reflect the greatest binding affinity *in vivo* or may compromise bioactivity *in vivo*. Studies comparing drug activity for different conjugation schemes would provide insight into a possible design tradeoff between the binding affinity to mineral and the bioactivity of the payload. Finally, the role and relative importance of the R₁ and R₂ side groups in binding and bioactivity could be further elucidated by investigating conjugation to either separately, but to our knowledge there have been no direct comparisons of conjugation at the R₁ versus R₂ side groups.

6. Conclusion and future outlook

The conjugation of BP ligands to pharmaceutical drugs, including imaging probes and radiosensitizers, enables targeted delivery to bone and pathological calcifications. BPs are ideal for targeting bone due to exhibiting a high binding affinity to hydroxyapatite. One of the first clinical uses of BPs was to deliver an imaging agent (⁹⁹Tc-MDP) to sites of high bone turnover and BP molecules subsequently became the most widely used therapeutic in the treatment of metabolic bone diseases. No other BP conjugates have been approved for clinical use since ⁹⁹Tc-MDP; however, a number of BP conjugates have shown new promise to address important clinical needs. Bifunctional chelator ligands have improved the specificity of current ⁹⁹Tc-BP agents [138,140,142,143], which may enable lowering the administered dose and improving the safety to patients. Fluorescent BP conjugate imaging probes have been commercialized (OsteoSense™, Perkin-Elmer) and are now a widely used research tool in preclinical investigations of metabolic bone disease [147-150], bone regeneration [151], and pathological

calcifications [152-154]. BP functionalized gold nanoparticles have enabled targeted delivery and contrast-enhanced X-ray detection of breast microcalcifications within murine mammary tissues [169], which may translate to improving the sensitivity and specificity of mammography for detecting breast cancer, especially in women with dense breast tissue [170]. The conjugation of BP ligands to chemotherapy agents has enabled targeted delivery of a greater dose of pharmaceutical to bone tissue while reducing detrimental off-target side-effects [96,109], which may improve the efficacy of cancer therapeutics in the treatment of bone cancer and metastases. The successful clinical translation of these and other promising new BP conjugates will require several important directions of scientific inquiry to determine (1) the pharmacological activity of both the conjugate and BP in appropriate preclinical models, (2) the minimum required dose, and (3) the most effective delivery route (e.g., oral vs. intravenous), among others. This review attempted to highlight the wide-range of agents that can be conjugated to BPs for targeted delivery and gaps in our knowledge of fundamental structure-function relationships. Future efforts should therefore focus on closing the knowledge gaps and translating BP conjugates as new pharmaceutical drugs for targeting bone and mineral deposits.

Acknowledgments

This review was completed with support from the National Science Foundation (DMR-1309587), St. Joseph Regional Medical Center, and Walther Cancer Foundation. The authors gratefully acknowledge Dr. Elena Aikawa (Brigham and Women's Hospital, Boston, MA) and Dr. Philip Blower (Kings College London, UK) for providing the NIR fluorescence and SPECT images, respectively, of vascular calcifications targeted by a BP conjugated contrast agents in Figure 6a.

References

- [1] G.A. Rodan, T.J. Martin, Therapeutic approaches to bone diseases, *Science*. 289 (2000) 1508–1514. doi:10.1126/science.289.5484.1508.
- [2] T.M. Doherty, K. Asotra, L.A. Fitzpatrick, J.-H. Qiao, D.J. Wilkin, R.C. Detrano, *et al.*, Calcification in atherosclerosis: Bone biology and chronic inflammation at the arterial crossroads, *Proc. Natl. Acad. Sci. USA*. 100 (2003) 11201–11206. doi:10.1073/pnas.1932554100.
- [3] L. Wexler, B. Brundage, J. Crouse, R. Detrano, V. Fuster, J. Maddahi, *et al.*, Coronary artery calcification: Pathophysiology, epidemiology, imaging methods, and clinical implications: A statement for health professionals from the American Heart Association, *Circulation*. 94 (1996) 1175–1192. doi:10.1161/01.cir.94.5.1175.
- [4] N. Alexopoulos, P. Raggi, Calcification in atherosclerosis, *Nat. Rev. Cardiol.* 6 (2009) 681–688. doi:10.1038/nrcardio.2009.165.
- [5] M.P. Morgan, M.M. Cooke, G.M. McCarthy, Microcalcifications associated with breast cancer: An epiphenomenon or biologically significant feature of selected tumors? *J. Mammary Gland Biol. Neoplasia*. 10 (2005) 181–187. doi:10.1007/s10911-005-5400-6.
- [6] H. Xu, A.L. Zisman, F.L. Coe, E.M. Worcester, Kidney stones: An update on current pharmacological management and future directions, *Expert Opin. Pharmacother.* 14 (2013) 435–447. doi:10.1517/14656566.2013.775250.
- [7] R.G.G. Russell, Bisphosphonates: The first 40 years, *Bone*. 49 (2011) 2–19. doi:10.1016/j.bone.2011.04.022.
- [8] H. Fleisch, Bisphosphonates: Mechanisms of action, *Endocr Rev.* 19 (1998) 80–100.
- [9] H. Fleisch, R.G.G. Russell, S. Bisaz, P.A. Casey, R.C. Muhlbauer, The influence of

pyrophosphate analogues (diphosphonates) on the precipitation and dissolution of calcium phosphate *in vitro* and *in vivo*, *Calcif. Tissue Res.* 2 (1968) 10. doi:10.1007/BF02065192

[10] M.D. Francis, R.G.G. Russell, H. Fleisch, Disphosphonates inhibit formation of calcium phosphate crystals *in vitro* and pathological calcification *in vivo*, *Science*. 165 (1969) 1264–1266.

[11] G.H. Nancollas, R. Tang, R.J. Phipps, Z. Henneman, S. Gulde, W. Wu, *et al.*, Novel insights into actions of bisphosphonates on bone: Differences in interactions with hydroxyapatite, *Bone*. 38 (2006) 617–627. doi:10.1016/j.bone.2005.05.003.

[12] H. Fleisch, H. Fleisch, R.G.G. Russell, R.G.G. Russell, M.D. Francis, M.D. Francis, Diphosphonates inhibit hydroxyapatite dissolution *in vitro* and bone resorption in tissue culture and *in vivo*, *Science*. 165 (1969) 1262–1264. doi:10.1126/science.165.3899.1262

[13] C.A.L. Bassett, A. Donath, F. Macagno, R. Preisig, H. Fleisch, M.D. Francis, Disphosphonates in the treatment of myositis ossificans, *The Lancet*. 294 (1969) 845. doi.org/10.1016/S0140-6736(69)92295-8

[14] J.M. Baumann, S. Bisaz, H. Fleisch, M. Wacker, Biochemical and clinical effects of ethane-1-hydroxy-1,1-diphosphonate in calcium nephrolithiasis, *Clin. Sci. Mol. Med.* 54 (1978) 509–516.

[15] I. Fogelman, R.G. Bassett, J.G. Turner, D.L. Citrin, I.T. Boyle, W.R. Greig, The use of whole-body retention of Tc-99m disphosphonate in the diagnosis of metabolic bone disease, *J. Nucl. Med.* 19 (1978) 270–275.

- 838 [16] D.K. Wysowski, P. Greene, Trends in osteoporosis treatment with oral and intravenous
839 bisphosphonates in the United States, 2002–2012, *Bone*. 57 (2013) 423–428.
840 doi:10.1016/j.bone.2013.09.008.
- 841 [17] M. Pazianas, B. Abrahamsen, Safety of bisphosphonates, *Bone*. 49 (2011) 103–110.
842 doi:10.1016/j.bone.2011.01.003.
- 843 [18] F.H. Ebetino, A.-M.L. Hogan, S. Sun, M.K. Tsoumpra, X. Duan, J.T. Triffitt, *et al.*, The
844 relationship between the chemistry and biological activity of the bisphosphonates, *Bone*.
845 49 (2011) 20–33. doi:10.1016/j.bone.2011.03.774.
- 846 [19] A.M. Flanagan, T.J. Chambers, Dichloromethylenebisphosphonate (Cl2MBP) inhibits
847 bone resorption through injury to osteoclasts that resorb Cl2MBP-coated bone, *Bone*. 6
848 (1989) 33–43.
- 849 [20] M. Ito, M. Chokki, O. Y, Y. Satomi, Y. Azuma, T. Ohta, *et al.*, Comparison of the
850 cytotoxic effects of bisphosphonate *in vitro* and *in vivo*, *Calcif. Tissue Int.* 63 (1998)
851 143–147.
- 852 [21] D.E. Hughes, K.R. Wright, H.L. Uy, A. Sasaki, T. Yoneda, G.D. Roodman, *et al.*,
853 Bisphosphonates promote apoptosis in murine osteoclasts *in vitro* and *in vivo*, *J. Bone*
854 *Miner. Res.* 10 (1995) 1478–1487. doi:10.1002/jbmr.5650101008
- 855 [22] E.M. Lewiecki, Safety of long-term bisphosphonate therapy for the management of
856 osteoporosis, *Drugs*. 71 (2011) 791–814. doi:10.2165/11585470-000000000-00000.
- 857 [23] R. Torres Martin de Rosales, C. Finucane, S.J. Mather, P.J. Blower, Bifunctional
858 bisphosphonate complexes for the diagnosis and therapy of bone metastases, *Chem.*
859 *Commun.* (2009) 4847–4849. doi:10.1039/b908652h.

- 860 [24] H. Hyun, H. Wada, K. Bao, J. Gravier, Y. Yadav, M. Laramie, *et al.*, Phosphonated near-
861 infrared fluorophores for biomedical imaging of bone, *Angew. Chem. Int. Ed.* 53 (2014)
862 10668–10672. doi:10.1002/anie.201404930.
- 863 [25] A. Zaheer, R.E. Lenkinski, A. Mahmood, A.G. Jones, L.C. Cantley, J.V. Frangioni, *In*
864 *vivo* near-infrared fluorescence imaging of osteoblastic activity, *Nat. Biotechnol.* 19
865 (2001) 1148–1154. doi:10.1038/nbt1201-1148
- 866 [26] R.E. Lenkinski, M. Ahmed, A. Zaheer, J.V. Frangioni, S.N. Goldberg, Near-infrared
867 fluorescence imaging of microcalcification in an animal model of breast cancer, *Acad.*
868 *Radiol.* 10 (2003) 1159–1164. doi:10.1016/S1076-6332(03)00253-8
- 869 [27] R.G.G. Russell, N.B. Watts, F.H. Ebetino, M.J. Rogers, Mechanisms of action of
870 bisphosphonates: Similarities and differences and their potential influence on clinical
871 efficacy, *Osteoporosis Int.* 19 (2008) 733–759. doi:10.1007/s00198-007-0540-8.
- 872 [28] K.R. Bhushan, P. Misra, F. Liu, S. Mathur, R.E. Lenkinski, J.V. Frangioni, Detection of
873 breast cancer microcalcifications using a dual-modality SPECT/NIR fluorescent probe, *J.*
874 *Am. Chem. Soc.* 130 (2008) 17648–17649. doi:10.1021/ja807099s.
- 875 [29] E. van Beek, M. Hoekstra, M. Van de Ruit, C. Lowik, S. Papapoulos, Structural
876 requirements for bisphosphonate actions *in vitro*, *J. Bone Miner. Res.* 9 (1994) 1875–
877 1882. doi:10.1002/jbmr.5650091206
- 878 [30] F.H. Ebetino, B.L. Barnett, R.G.G. Russell. A computational model delineates
879 differences in hydroxyapatite binding affinities of bisphosphonate [abstract]. *J. Bone*
880 *Miner. Res.* 20 [Suppl 1]:S259. doi:10.1002/jbmr.5650201305

- 881 [31] R. Fujisawa, Y. Kuboki, Preferential adsorption of dentin and bone acidic proteins on the
882 (100) face of hydroxyapatite crystals, *Biochim. Biophys. Acta.* 1075 (1991) 56–60.
883 doi:10.1016/0304-4165(91)90074-Q
- 884 [32] J. Moradian-Oldak, F. Frolow, L. Addadi, S. Weiner, Interaction between acidic matrix
885 macromolecules and calcium phosphate ester crystals: Relevance to carbonate apatite
886 formation in biomineralization, *Proc. Biol. Sci.* 247 (1992) 47–55.
- 887 [33] L. Addadi, S. Weiner, Interactions between acidic proteins and crystals: Stereochemical
888 requirements in biomineralization, *Proc. Natl. Acad. Sci. USA.* 82 (1985) 4110–4114.
- 889 [34] R. Fujisawa, Y. Wada, Y. Nodasaka, Y. Kuboki, Acidic amino acid-rich sequences as
890 binding sites of osteonectin to hydroxyapatite crystals, *Biochim. Biophys. Acta.* 1292
891 (1996) 53–60. doi:10.1016/0167-4838(95)00190-5
- 892 [35] S. Kasugai, R. Fujisawa, Y. Waki, K. Miyamoto, K. Ohya, Selective drug delivery
893 system to bone: Small peptide (Asp)(6) conjugation, *J. Bone Miner. Res.* 15 (2000) 936–
894 943. doi: 10.1359/jbmr.2000.15.5.936
- 895 [36] M.B. Murphy, J.D. Hartgerink, A. Goepferich, A.G. Mikos, Synthesis and *in vitro*
896 hydroxyapatite binding of peptides conjugated to calcium-binding moieties,
897 *Biomacromolecules.* 8 (2007) 2237–2243. doi:10.1021/bm070121s.
- 898 [37] D. Wang, S. Miller, M. Sima, P. Kopecková, J. Kopecek, Synthesis and evaluation of
899 water-soluble polymeric bone-targeted drug delivery systems, *Bioconjugate Chem.* 14
900 (2003) 853–859. doi:10.1021/bc034090j.
- 901 [38] R.D. Ross, R.K. Roeder, Binding affinity of surface functionalized gold nanoparticles to
902 hydroxyapatite, *J. Biomed. Mater. Res.* 99A (2011) 58–66. doi:10.1002/jbm.a.33165.

- 903 [39] R.D. Ross, L.E. Cole, R.K. Roeder, Relative binding affinity of carboxylate-,
904 phosphonate-, and bisphosphonate-functionalized gold nanoparticles targeted to damaged
905 bone tissue, *J. Nanopart. Res.* 14 (2012) 1175. doi:10.1007/s11051-012-1175-z.
- 906 [40] D.G. Kinniburgh, General purpose adsorption isotherms, *Environ. Sci. Technol.* 20
907 (1986) 895–904. doi: 10.1021/es00151a008.
- 908 [41] T. Vitha, V. Kubíček, P. Hermann, Z.I. Kolar, H.T. Wolterbeek, J.A. Peters, *et al.*,
909 Complexes of DOTA-bisphosphonate conjugates: Probes for determination of adsorption
910 capacity and affinity constants of hydroxyapatite, *Langmuir.* 24 (2008) 1952–1958.
911 doi:10.1021/la702753j.
- 912 [42] R.D. Ross, L.E. Cole, J.M.R. Tilley, R.K. Roeder, Effects of functionalized gold
913 nanoparticle size on X-ray attenuation and substrate binding affinity, *Chem. Mater.* 26
914 (2014) 1187–1194. doi:10.1021/cm4035616.
- 915 [43] G. Bansal, J.E.I. Wright, C. Kucharski, H. Uluda, A dendritic tetra(bisphosphonic acid)
916 for improved targeting of proteins to bone, *Angew. Chem. Int. Ed.* 44 (2005) 3710–3714.
917 doi:10.1002/anie.200500350.
- 918 [44] J.E.I. Wright, S.A. Gittens, G. Bansal, P.I. Kitov, D. Sindrey, C. Kucharski, *et al.*, A
919 comparison of mineral affinity of bisphosphonate–protein conjugates constructed with
920 disulfide and thioether linkages, *Biomaterials.* 27 (2006) 769–784.
921 doi:10.1016/j.biomaterials.2005.06.012.
- 922 [45] H. Uludag, N. Kousinioris, T. Gao, D. Kantoci, Bisphosphonate conjugation to proteins
923 as a means to impart bone affinity, *Biotechnol. Prog.* 16 (2000) 258–267.
924 doi:10.1021/bp990154m.

- 925 [46] G. Bansal, S.B.A. Gittens, H. Uludag, A di(bisphosphonic acid) for protein coupling and
926 targeting to bone, *J. Pharm. Sci.* 93 (2004) 2788–2799. doi:10.1002/jps.20186.
- 927 [47] Y. Yang, K.H. Bhandari, A. Panahifar, M.R. Doschak, Synthesis, characterization and
928 biodistribution studies of ^{125}I -radioiodinated di-PEGylated bone targeting salmon
929 calcitonin analogue in healthy rats, *Pharm. Res.* 31 (2013) 1146–1157.
930 doi:10.1007/s11095-013-1237-7.
- 931 [48] M.R. Doschak, C.M. Kucharski, J.E.I. Wright, R.F. Zernicke, H. Uludag, Improved bone
932 delivery of osteoprotegerin by bisphosphonate conjugation in a rat model of
933 osteoarthritis, *Mol. Pharm.* 6 (2009) 634–640. doi:10.1021/mp8002368.
- 934 [49] A.A. El-Mabhough, C.A. Angelov, R. Cavell, J.R. Mercer, A $^{99\text{m}}\text{Tc}$ -labeled gemcitabine
935 bisphosphonate drug conjugate as a probe to assess the potential for targeted
936 chemotherapy of metastatic bone cancer, *Nucl. Med. Biol.* 33 (2006) 715–722.
937 doi:10.1016/j.nucmedbio.2006.06.004.
- 938 [50] C. Rill, Z.I. Kolar, G. Kickelbick, H.T. Wolterbeek, J.A. Peters, Kinetics and
939 thermodynamics of adsorption on hydroxyapatite of the [^{160}Tb]terbium complexes of the
940 bone-targeting ligands DOTP and BPPED, *Langmuir.* 25 (2009) 2294–2301.
941 doi:10.1021/la803562e.
- 942 [51] G.M.S. Zayed, J.K.V. Tessmar, Heterobifunctional poly(ethylene glycol) derivatives for
943 the surface modification of gold nanoparticles toward bone mineral targeting, *Macromol.*
944 *Biosci.* 12 (2012) 1124–1136. doi:10.1002/mabi.201200046.
- 945 [52] Z.J. Henneman, G.H. Nancollas, F.H. Ebetino, R.G.G. Russell, R.J. Phipps,
946 Bisphosphonate binding affinity as assessed by inhibition of carbonated apatite

947 dissolution *in vitro*, J. Biomed. Mater. Res. 85A (2008) 993–1000.
 948 doi:10.1002/jbm.a.31599.

949 [53] J.N. Yewle, D.A. Puleo, L.G. Bachas, Enhanced affinity bifunctional bisphosphonates for
 950 targeted delivery of therapeutic agents to bone, Bioconjugate Chem. 22 (2011) 2496–
 951 2506. doi:10.1021/bc2003132.

952 [54] P. Koutsoukos, Z. Amjad, M.B. Tomson, G.H. Nancollas, Crystallization of calcium
 953 phosphates. A constant composition study, J. Am. Chem. Soc. 102 (1980) 1553–1557.
 954 doi: 10.1021/ja00525a015.

955 [55] S. Mukherjee, Y. Song, E. Oldfield, NMR investigations of the static and dynamic
 956 structures of bisphosphonates on human bone. A molecular model. J. Am. Chem. Soc.
 957 130 (2008) 1264–1273. doi:10.1021/ja0759949.

958 [56] W. Jahnke, C. Henry, An *in vitro* assay to measure targeted drug delivery to bone
 959 mineral, ChemMedChem. 5 (2010) 770–776. doi:10.1002/cmdc.201000016.

960 [57] C.-T. Leu, E. Luegmayr, L.P. Freedman, G.A. Rodan, A.A. Reszka, Relative binding
 961 affinities of bisphosphonates for human bone and relationship to antiresorptive efficacy,
 962 Bone. 38 (2006) 628–636. doi:10.1016/j.bone.2005.07.023.

963 [58] M.A. Lawson, Z. Xia, B.L. Barnett, J.T. Triffitt, R.J. Phipps, J.E. Dunford, *et al.*,
 964 Differences between bisphosphonates in binding affinities for hydroxyapatite, J. Biomed.
 965 Mater. Res. 92B (2010) 149–155. doi:10.1002/jbm.b.31500.

966 [59] H. Uludag, Bisphosphonates as a foundation of drug delivery to bone, Curr. Pharm.
 967 Design. 8 (2002) 1929–1944. doi: 10.2174/12812023393585.

- 968 [60] G. Wang, C. Kucharski, X. Lin, H. Uludag, Bisphosphonate-coated BSA nanoparticles
 969 lack bone targeting after systemic administration, *J. Drug Target.* 18 (2010) 611–626.
 970 doi:10.3109/10611861003622560.
- 971 [61] H. Uludag, J. Yang, Targeting systemically administered proteins to bone by
 972 bisphosphonate conjugation, *Biotechnol. Prog.* 18 (2002) 604–611.
 973 doi:10.1021/bp0200447.
- 974 [62] H. Pan, M. Sima, P. Kopecková, K. Wu, S. Gao, J. Liu, *et al.*, Biodistribution and
 975 pharmacokinetic studies of bone-targeting N-(2-hydroxypropyl)methacrylamide
 976 copolymer-alendronate conjugates, *Mol. Pharm.* 5 (2008) 548–558.
 977 doi:10.1021/mp800003u.
- 978 [63] A.J. Roelofs, C.A. Stewart, S. Sun, K.M. Biazewska, B.A. Kashemirov, C.E. McKenna,
 979 *et al.*, Influence of bone affinity on the skeletal distribution of fluorescently labeled
 980 bisphosphonates *in vivo*, *J. Bone Miner. Res.* 27 (2012) 835–847. doi:10.1002/jbmr.1543.
- 981 [64] J.H. Lin, Bisphosphonates: A review of their pharmacokinetic properties, *Bone*, 18
 982 (1996) 74–85 doi: 10.1016/8756-3282(95)00445-9.
- 983 [65] S. Cremers, S. Papapoulos. Pharmacology of bisphosphonates, *Bone*, 49 (2011) 42–49.
 984 doi: 10.1016/j.bone.2011.01.014.
- 985 [66] S.T. Harris, N.B. Watts, H.K. Genant, C.D. McKeever, Effects of risedronate treatment
 986 on vertebral and nonvertebral fractures in women with postmenopausal osteoporosis: A
 987 randomized controlled trial, *J. Am. Med. Ass.* 282 (1999) 1344–1352. doi:
 988 10.1001/jama.282.14.1344.
- 989 [67] R. Eastell, J.S. Walsh, N.B. Watts, E. Siris, Bisphosphonates for postmenopausal
 990 osteoporosis, *Bone*. 49 (2011) 82–88. doi:10.1016/j.bone.2011.02.011.

991 [68] P.D. Delmas, Treatment of postmenopausal osteoporosis, *Lancet*. 359 (2002) 2018–2026.
 992 doi:10.1016/S0140-6736(02)08827-X.

993 [69] E.F. Eriksen, A. Díez-Pérez, S. Boonen, Update on long-term treatment with
 994 bisphosphonates for postmenopausal osteoporosis: A systematic review, *Bone*. 58 (2014)
 995 126–135. doi:10.1016/j.bone.2013.09.023.

996 [70] B.L. Riggs, L.J. Melton, The prevention and treatment of osteoporosis, *New Engl. J.*
 997 *Med.* 327 (1992) 620–627.

998 [71] F. Bauss, A. Esswein, K. Reiff, G. Sponer, B. Müller-Beckmann, Effect of 17 β -estradiol-
 999 bisphosphonate conjugates, potential bone-seeking estrogen pro-drugs, on 17 β -estradiol
 1000 serum kinetics and bone mass in rats, *Calcif. Tissue Int.* 59 (1996) 168–173.

1001 [72] J. Fujisaki, Y. Tokunaga, T. Takashashi, S. Kimura, F. Shimojo, T. Hata, Osteotropic
 1002 drug delivery system (ODDS) based on bisphosphonic prodrug. Biological disposition
 1003 and targeting characteristics of osteotropic estradiol, *Biol. Pharm. Bull.* 20 (1997) 1183–
 1004 1187. doi: org/10.1248/bpb.20.1183.

1005 [73] J. Fujisaki, Y. Tokunaga, T. Takashashi, F. Shimojo, S. Kimura, T. Hata, Osteotropic
 1006 drug delivery system (ODDS) based on bisphosphonic prodrug. I.v. effects of osteotropic
 1007 estradiol on bone mineral density and uterine weight in ovariectomized rats, *J. Drug*
 1008 *Target.* 5 (1998) 129–138. doi: 10.3109/10611869808995866.

1009 [74] P.C.B. Page, M.J. McKenzie, J.A. Gallagher, Novel synthesis of bis(phosphonic acid)-
 1010 steroid conjugates, *J. Org. Chem.* 66 (2001) 3704–3708. doi:10.1021/jo001489h.

1011 [75] P.C.B. Page, J.P.G. Moore, I. Mansfield, M.J. McKenzie, W.B. Bowler, J.A. Gallagher,
 1012 Synthesis of bone-targeted oestrogenic compounds for the inhibition of bone resorption,
 1013 *Tetrahedron*. 57 (2001) 1837–1847. doi: 10.1016/S0040-4020(00)01164-9.

- 1014 [76] M. Morioka, A. Kamizono, H. Takikawa, A. Mori, H. Ueno, S.-I. Kadowaki, *et al.*,
 1015 Design, synthesis, and biological evaluation of novel estradiol-bisphosphonate conjugates
 1016 as bone-specific estrogens, *Bioorg. Med. Chem.* 18 (2010) 1143–1148.
 1017 doi:10.1016/j.bmc.2009.12.041.
- 1018 [77] L. Gil, Y. Han, E.E. Opas, G.A. Rodan, R. Ruel, J.G. Sedor, *et al.*, Prostaglandin E2-
 1019 bisphosphonate conjugates: potential agents for treatment of osteoporosis, *Bioorg. Med.*
 1020 *Chem.* 7 (1999) 901–919. doi:10.1016/S0968-0896(99)00045-0
- 1021 [78] S. Arns, R. Gibe, A. Moreau, M.M. Morshed, R.N. Young, Design and synthesis of novel
 1022 bone-targeting dual-action pro-drugs for the treatment and reversal of osteoporosis,
 1023 *Bioorg. Med. Chem.* 20 (2012) 2131–2140. doi:10.1016/j.bmc.2012.01.024.
- 1024 [79] J.N. Yewle, D.A. Puleo, L.G. Bachas, Bifunctional bisphosphonate for delivering PTH(1-
 1025 34) to bone mineral with enhanced bioactivity, *Biomaterials.* 34 (2013) 3141–3149.
 1026 doi:10.1016/j.biomaterials.2013.01.059.
- 1027 [80] M. Li, D.D. Thompson, V.M. Paralkar, Prostaglandin E2 receptors in bone formation, *Int.*
 1028 *Orthop.* 31 (2007) 767–772. doi:10.1007/s00264-007-0406-x.
- 1029 [81] K.H. Bhandari, M. Newa, H. Uludag, M.R. Doschak, Synthesis, characterization and *in*
 1030 *vitro* evaluation of a bone targeting delivery system for salmon calcitonin, *Int. J. Pharm.*
 1031 394 (2010) 26–34. doi:10.1016/j.ijpharm.2010.04.015.
- 1032 [82] Y.-H. Lee, P.J. Sinko, Oral delivery of salmon calcitonin, *Adv. Drug Delivery Rev.* 42
 1033 (2000) 225–238. doi: 10.1016/S0169-409X(00)00063-6.
- 1034 [83] D. Naot, J. Cornish, The role of peptides and receptors of the calcitonin family in the
 1035 regulation of bone metabolism, *Bone.* (2008) 1–6. doi:10.1016/j.bone.2008.07.003.

1036 [84] K.H. Bhandari, M. Newa, J. Chapman, M.R. Doschak, Synthesis, characterization and
1037 evaluation of bone targeting salmon calcitonin analogs in normal and osteoporotic rats, *J.*
1038 *Control. Release.* 158 (2012) 44–52. doi:10.1016/j.jconrel.2011.09.096.

1039 [85] S. Gittens, G. Bansal, R. Zernicke, H. Uludag, Designing proteins for bone targeting,
1040 *Adv. Drug Delivery Rev.* 57 (2005) 1011–1036. doi:10.1016/j.addr.2004.12.015.

1041 [86] S. Zhang, G. Gangal, H. Uludag, “Magic bullets” for bone diseases: Progress in rational
1042 design of bone-seeking medicinal agents, *Chem. Soc. Rev.* 36 (2007) 507.
1043 doi:10.1039/b512310k.

1044 [87] R.E. Coleman, Clinical features of metastatic bone disease and risk of skeletal morbidity,
1045 *Clin. Cancer Res.* 12 (2006) 6243s–6249s. doi:10.1158/1078-0432.CCR-06-0931.

1046 [88] G.R. Mundy, Metastasis to bone: causes, consequences and therapeutic opportunities,
1047 *Nat. Rev. Cancer.* 2 (2002) 584–593. doi:10.1038/nrc867.

1048 [89] R.E. Coleman, E.V. McCloskey, Bisphosphonates in oncology, *Bone.* 49 (2011) 71–76.
1049 doi:10.1016/j.bone.2011.02.003.

1050 [90] R.E. Coleman, Metastatic bone disease: clinical features, pathophysiology and treatment
1051 strategies, *Cancer Treat. Rev.* 27 (2001) 165–176. doi:10.1053/ctrv.2001.0210.

1052 [91] H.L. Neville-Webbe, M. Gnant, R.E. Coleman, Potential anticancer properties of
1053 bisphosphonates, *Semin. Oncol.* 37 (2010) S53–65. doi:
1054 10.1053/j.seminoncol.2010.06.008.

1055 [92] L. Brannon-Peppas, J.O. Blanchette, Nanoparticle and targeted systems for cancer
1056 therapy, *Adv. Drug Delivery Rev.* 56 (2004) 1649–1659. doi:10.1016/j.addr.2004.02.014.

- 1057 [93] T. Klenner, P. Valenzuela-Paz, B.K. Keppler, G. Angres, H.R. Scherf, F. Wingen, *et al.*,
 1058 Cisplatin-linked phosphonates in the treatment of the transplantable osteosarcoma *in vitro*
 1059 and *in vivo*, *Cancer Treat. Rev.* 17 (1990) 253–259. doi: 10.1016/0305-7372(90)90056-L.
- 1060 [94] Z. Xue, M. Lin, J. Zhu, J. Zhang, Y. Li, Z. Guo, Platinum(ii) compounds bearing bone-
 1061 targeting group: synthesis, crystal structure and antitumor activity, *Chem. Commun.* 46
 1062 (2010) 1212. doi:10.1039/b922222g.
- 1063 [95] K. Miller, R. Erez, E. Segal, D. Shabat, R. Satchi-Fainaro, Targeting bone metastases
 1064 with a bispecific anticancer and antiangiogenic polymer-alendronate-taxane conjugate,
 1065 *Angew. Chem. Int. Ed.* 48 (2009) 2949–2954. doi:10.1002/anie.200805133.
- 1066 [96] K. Miller, A. Eldar-Boock, D. Polyak, E. Segal, L. Benayoun, Y. Shaked, *et al.*,
 1067 Antiangiogenic antitumor activity of HPMA copolymer–paclitaxel–alendronate conjugate
 1068 on breast cancer bone metastasis mouse model, *Mol. Pharm.* 8 (2011) 1052–1062.
 1069 doi:10.1021/mp200083n.
- 1070 [97] K.R. Chaudhari, A. Kumar, V.K.M. Khandelwal, A.K. Mishra, J. Mönkkönen, R.S.R.
 1071 Murthy, Targeting efficiency and biodistribution of zoledronate conjugated docetaxel
 1072 loaded pegylated PBCA nanoparticles for bone metastasis, *Adv. Funct. Mater.* 22 (2012)
 1073 4101–4114. doi:10.1002/adfm.201102357.
- 1074 [98] N. Margiotta, F. Capitelli, R. Ostuni, G. Natile, A new dinuclear platinum complex with a
 1075 nitrogen-containing geminal bisphosphonate as potential anticancer compound
 1076 specifically targeted to bone tissue, *J. Inorg. Biochem.* 102 (2008) 2078–2086.
 1077 doi:10.1016/j.jinorgbio.2008.07.008.

- 1078 [99] R. Erez, S. Ebner, B. Attali, D. Shabat, Chemotherapeutic bone-targeted bisphosphonate
1079 prodrugs with hydrolytic mode of activation, *Bioorg. Med. Chem. Lett.* 18 (2008) 816–
1080 820. doi:10.1016/j.bmcl.2007.11.029.
- 1081 [100] A.A. El-Mabhouh, J.R. Mercer, ^{188}Re -labelled gemcitabine/bisphosphonate (Gem/BP): a
1082 multi-functional, bone-specific agent as a potential treatment for bone metastases, *Eur. J*
1083 *Nucl. Med. Mol. Imaging.* 35 (2008) 1240–1248. doi:10.1007/s00259-008-0728-y.
- 1084 [101] A.A. El-Mabhouh, P.N. Nation, J.T. Abele, T. Riauka, E. Postema, A. McEwan, *et al.*, A
1085 conjugate of gemcitabine with bisphosphonate (Gem/BP) showed potential as a targeted
1086 bone-specific therapeutic agent in an animal model of human breast cancer metastases,
1087 *Oncol. Res.* 19 (2011) 287–295. doi.org/10.3727/096504011X13021877989874
- 1088 [102] A.A. El-Mabhouh, C.A. Angelov, A. McEwan, G. Jia, J.R. Mercer, Preclinical
1089 investigations of drug and radionuclide conjugates of bisphosphonates for the treatment
1090 of metastatic bone cancer, *Cancer Biother. Radiopharm.* 19 (2014) 627–640.
1091 doi:10.1089/cbr.2004.19.627
- 1092 [103] O. Fabulet, G. Sturtz, Synthesis of gem-bisphosphonic doxorubicin conjugates,
1093 *Phosphorus Sulfur Silicon Relat. Elem.* 101 (1995) 225–234. doi:
1094 10.1080/10426509508042521.
- 1095 [104] K. Hochdörffer, K. Abu Ajaj, C. Schäfer-Obodozie, F. Kratz, Development of novel
1096 bisphosphonate prodrugs of doxorubicin for targeting bone metastases that are cleaved
1097 pH dependently or by cathepsin B: Synthesis, cleavage properties, and binding properties
1098 to hydroxyapatite as well as bone matrix, *J. Med. Chem.* 55 (2012) 7502–7515.
1099 doi:10.1021/jm300493m.

- 1100 [105] F. Hosain, R.P. Spencer, H.M. Couthon, G.L. Sturtz, Targeted delivery of antineoplastic
 1101 agent to bone: Biodistribution studies of technetium-99m-labeled gem-bisphosphonate
 1102 conjugate of methotrexate, *J Nucl Med.* 37 (1996) 105–107.
- 1103 [106] J.K. Agyin, B. Santhamma, S.S. Roy, Design, synthesis, and biological evaluation of
 1104 bone-targeting proteasome inhibitors for multiple myeloma, *Bioorg. Med. Chem. Lett.*,
 1105 23 (2013) 6455–6458. doi:10.1016/j.bmcl.2013.09.043.
- 1106 [107] A. Swami, M.R. Reagan, P. Basto, Y. Mishima, N. Kamaly, S. Glavey, *et al.*, Engineered
 1107 nanomedicine for myeloma and bone microenvironment targeting, *Proc. Natl. Acad. Sci.*
 1108 USA. 111 (2014) 10287–10292. doi:10.1073/pnas.1401337111.
- 1109 [108] M.M. Reinholz, S.P. Zinnen, A.C. Dueck, D. Dingli, G.G. Reinholz, L.A. Jonart, *et al.*, A
 1110 promising approach for treatment of tumor-induced bone diseases: Utilizing
 1111 bisphosphonate derivatives of nucleoside antimetabolites, *Bone.* 47 (2010) 12–22.
 1112 doi:10.1016/j.bone.2010.03.006.
- 1113 [109] E. Segal, H. Pan, L. Benayoun, P. Kopecková, Y. Shaked, J. Kopecek, *et al.*, Enhanced
 1114 anti-tumor activity and safety profile of targeted nano-scaled HPMA copolymer-
 1115 alendronate-TNP-470 conjugate in the treatment of bone malignances, *Biomaterials.* 32
 1116 (2011) 4450–4463. doi:10.1016/j.biomaterials.2011.02.059.
- 1117 [110] D.P. Lew, F.A. Waldvogel, Osteomyelitis, *Lancet.* 364 (2004) 369–379. doi:
 1118 10.1016/S0140-6736(04)16727-5.
- 1119 [111] E. Romas, Bone loss in inflammatory arthritis: mechanisms and therapeutic approaches
 1120 with bisphosphonates, *Best Pract. Res. Clin. Rheumatol.* 19 (2005) 1065–1079.
 1121 doi:10.1016/j.berh.2005.06.008.

- 1122 [112] K.S.E. Tanaka, E. Dietrich, S. Ciblat, C. Métayer, F.F. Arhin, I. Sarmiento, *et al.*,
 1123 Synthesis and in vitro evaluation of bisphosphonated glycopeptides for the treatment of
 1124 osteomyelitis, *Bioorg. Med. Chem. Lett.* 20 (2010) 1355–1359.
 1125 doi:10.1016/j.bmcl.2010.01.006.
- 1126 [113] P. Herczegh, T.B. Buxton, J.C. McPherson, Á. Kovács-Kulyassa, P.D. Brewer, F.
 1127 Sztaricskai, *et al.*, Osteoadsorptive bisphosphonate derivatives of fluoroquinolone
 1128 antibacterials, *J. Med. Chem.* 45 (2002) 2338–2341. doi:10.1021/jm0105326.
- 1129 [114] T.J. Houghton, K.S.E. Tanaka, T. Kang, E. Dietrich, Y. Lafontaine, D. Delorme, *et al.*,
 1130 Linking bisphosphonates to the free amino groups in fluoroquinolones: Preparation of
 1131 osteotropic prodrugs for the prevention of osteomyelitis, *J. Med. Chem.* 51 (2008) 6955–
 1132 6969. doi:10.1021/jm801007z.
- 1133 [115] R. Altman, B. Bosch, K. Brune, P. Patrignani, C. Young, Advances in NSAID
 1134 development: Evolution of diclofenac products using pharmaceutical technology, *Drugs.*
 1135 75 (2015) 859–877. doi:10.1007/s40265-015-0392-z.
- 1136 [116] H. Hirabayashi, T. Takahashi, J. Fujisaki, T. Masunaga, S. Sato, J. Hiroi, *et al.*, Bone-
 1137 specific delivery and sustained release of diclofenac, a non-steroidal anti-inflammatory
 1138 drug, via bisphosphonic prodrug based on the Osteotropic Drug Delivery System
 1139 (ODDS), *J. Control. Release* 70 (2001) 183–191. doi: 10.1016/S0168-3659(00)00355-2.
- 1140 [117] H. Hirabayashi, T. Sawamoto, J. Fujisaki, Y. Tokunaga, S. Kimura, T. Hata, Dose-
 1141 dependent pharmacokinetics and disposition of bisphosphonic prodrug of diclofenac
 1142 based on osteotropic drug delivery system (ODDS), *Biopharm. Drug Dispos.* 23 (2002)
 1143 307–315. doi:10.1002/bdd.323.

- 1144 [118] M.L. Young, D.G. Little, H.K.W. Kim, Evidence for using bisphosphonate to treat Legg-
 1145 Calvé-Perthes disease, *Clin. Orthop. Relat. Res.* 470 (2012) 2462–2475.
 1146 doi:10.1007/s11999-011-2240-0.
- 1147 [119] F. Fanord, K. Fairbairn, H. Kim, A. Garces, V. Bhethanabotla, V.K. Gupta,
 1148 Bisphosphonate-modified gold nanoparticles: A useful vehicle to study the treatment of
 1149 osteonecrosis of the femoral head, *Nanotechnology.* 22 (2010) 035102.
 1150 doi:10.1088/0957-4484/22/3/035102.
- 1151 [120] H. Katsumi, M. Takashima, J.-I. Sano, K. Nishiyama, N. Kitamura, T. Sakane, *et al.*,
 1152 Development of polyethylene glycol-conjugated alendronate, a novel nitrogen-containing
 1153 bisphosphonate derivative: Evaluation of absorption, safety, and effects after
 1154 intrapulmonary administration in rats, *J. Pharm. Sci.* 100 (2011) 3783–3792.
 1155 doi:10.1002/jps.22620.
- 1156 [121] S. Zhang, J.E.I. Wright, N. Özber, H. Uludag, The interaction of cationic polymers and
 1157 their bisphosphonate derivatives with hydroxyapatite, *Macromol. Biosci.* 7 (2007) 656–
 1158 670. doi:10.1002/mabi.200600286.
- 1159 [122] L. de Miguel, M. Noiray, G. Surpateanu, B.I. Iorga, G. Ponchel, Poly(γ -benzyl-L-
 1160 glutamate)-PEG-alendronate multivalent nanoparticles for bone targeting, *Int. J. Pharm.*
 1161 460 (2014) 73–82. doi:10.1016/j.ijpharm.2013.10.048.
- 1162 [123] S. D'Souza, H. Murata, M.V. Jose, S. Askarova, Y. Yantsen, J.D. Andersen, *et al.*,
 1163 Engineering of cell membranes with a bisphosphonate-containing polymer using ATRP
 1164 synthesis for bone targeting, *Biomaterials.* 35 (2014) 9447–9458.
 1165 doi:10.1016/j.biomaterials.2014.07.041.

- 1166 [124] W.H. De Jong, P.J. Borm, Drug delivery and nanoparticles: Applications and hazards,
1167 Int. J. Nanomed. 3 (2008) 133–149.
- 1168 [125] V. Hengst, C. Oussoren, T. Kissel, G. Storm, Bone targeting potential of bisphosphonate-
1169 targeted liposomes. Preparation, characterization and hydroxyapatite binding *in vitro*, Int.
1170 J. Pharm. 331 (2007) 224–227. doi:10.1016/j.ijpharm.2006.11.024.
- 1171 [126] G. Wang, N.Z. Mostafa, V. Incani, C. Kucharski, H. Uludağ, Bisphosphonate-decorated
1172 lipid nanoparticles designed as drug carriers for bone diseases, J. Biomed. Mater. Res.
1173 100A (2011) 684–693. doi:10.1002/jbm.a.34002.
- 1174 [127] G. Wang, M.E. Babadagli, H. Uludağ, Bisphosphonate-derivatized liposomes to control
1175 drug release from collagen-hydroxyapatite scaffolds, Mol. Pharm. 8 (2011) 1025–1034.
1176 doi:10.1021/mp200028w.
- 1177 [128] T. Anada, Y. Takeda, Y. Honda, K. Sakurai, O. Suzuki, Synthesis of calcium phosphate-
1178 binding liposome for drug delivery, Bioorg. Med. Chem. Lett. 19 (2009) 4148–4150.
1179 doi:10.1016/j.bmcl.2009.05.117.
- 1180 [129] S.-W. Choi, J.-H. Kim, Design of surface-modified poly(D,L-lactide-*co*-glycolide)
1181 nanoparticles for targeted drug delivery to bone, J. Control. Release. 122 (2007) 24–30.
1182 doi:10.1016/j.jconrel.2007.06.003.
- 1183 [130] E. Cenni, D. Granchi, S. Avnet, C. Fotia, M. Salerno, D. Micieli, *et al.*, Biocompatibility
1184 of poly(D,L-lactide-*co*-glycolide) nanoparticles conjugated with alendronate,
1185 Biomaterials. 29 (2008) 1400–1411. doi:10.1016/j.biomaterials.2007.12.022.
- 1186 [131] E. Cenni, S. Avnet, D. Granchi, C. Fotia, M. Salerno, D. Micieli, *et al.*, The effect of
1187 poly(D,L-lactide-*co*-glycolide)-alendronate conjugate nanoparticles on human osteoclast

precursors, J. Biomat. Sci. Polym. Ed. 23 (2012) 1285-1300.
doi:10.1163/092050611X580373.

[132] S.W. Morton, N.J. Shah, M.A. Quadir, Z.J. Deng, Z. Poon, P.T. Hammond, osteotropic therapy via targeted layer-by-layer nanoparticles, Adv. Healthcare Mater. 3 (2014) 867-875. doi:10.1002/adhm.201300465.

[133] Y.-L. Khung, K. Bastari, X.L. Cho, W.A. Yee, S.C.J. Loo, Designing calcium phosphate-based bifunctional nanocapsules with bone-targeting properties, J. Nanopart. Res. 14 (2012) 911. doi:10.1007/s11051-012-0911-8.

[134] G. Subramanian, J.G. McAfee, R.J. Blair, F.A. Kallfelz, F.D. Thomas, Technetium-99m-methylene diphosphonate - A superior agent for skeletal imaging: Comparison with other technetium complexes, J. Nucl. Med. 16 (1975) 744–755.

[135] A.I. Brenner, J. Koshy, J. Morey, C. Lin, J. Di Poce, The bone scan, Semin. Nucl. Med. 42 (2012) 11–26. doi:10.1053/j.semnuclmed.2011.07.005.

[136] E. Palma, J.D.G. Correia, M.P.C. Campello, I. Santos, Bisphosphonates as radionuclide carriers for imaging or systemic therapy, Mol. Biosyst. 7 (2011) 2950. doi:10.1039/c1mb05242j.

[137] K. Libson, E. Deutsch, B.L. Barnett, Structural characterization of a ^{99}Tc -diphosphonate complex. Implications for the chemistry of $^{99\text{m}}\text{Tc}$ skeletal imaging agents, J. Am. Chem. Soc. 102 (1980) 2476–2478.

[138] K. Ogawa, T. Mukai, Y. Inouye, M. Ono, H. Saji, Development of a novel $^{99\text{m}}\text{Tc}$ -chelate-conjugated bisphosphonate with high affinity for bone as a bone scintigraphic agent, J. Nucl. Med. 47 (2006) 2042–2047.

- 1210 [139] E. Palma, B.L. Oliveira, J.D.G. Correia, L. Gano, L. Maria, I.C. Santos, *et al.*, A new
1211 bisphosphonate-containing $^{99m}\text{Tc}(\text{I})$ tricarbonyl complex potentially useful as bone-
1212 seeking agent: synthesis and biological evaluation, *J. Biol. Inorg. Chem.* 12 (2007) 667–
1213 679. doi:10.1007/s00775-007-0215-0.
- 1214 [140] E. Palma, J.D.G. Correia, B.L. Oliveira, L. Gano, I.C. Santos, I. Santos, $^{99m}\text{Tc}(\text{CO})_3$ -
1215 labeled pamidronate and alendronate for bone imaging, *Dalton Trans.* 40 (2011) 2787.
1216 doi:10.1039/c0dt01396j.
- 1217 [141] K. Verbeke, J. Rozenski, B. Cleynhens, H. Vanbilloen, T. de Groot, N. Weyns, *et al.*,
1218 Development of a conjugate of ^{99m}Tc -EC with aminomethylenediphosphonate in the
1219 search for a bone tracer with fast clearance from soft tissue, *Bioconjugate Chem.* 13
1220 (2002) 16–22. doi:10.1021/bc0001600.
- 1221 [142] L. Liu, G. Zhong, Y. Wei, M. Zhang, X. Wang, Synthesis and biological evaluation of a
1222 novel ^{99m}Tc complex of HYNIC-conjugated aminomethylenediphosphonate as a potential
1223 bone imaging agent, *J. Radioanal. Nucl Chem.* 288 (2011) 467–473. doi:10.1007/s10967-
1224 010-0942-5.
- 1225 [143] C. Fernandes, S. Monteiro, P. Mendes, L. Gano, F. Marques, S. Casimiro, *et al.*,
1226 Biological assessment of novel bisphosphonate-containing $^{99m}\text{Tc}/\text{Te}$ -organometallic
1227 complexes, *J. Organomet. Chem.* 760 (2014) 197–204.
1228 doi:10.1016/j.jorganchem.2013.10.038.
- 1229 [144] N. Chadha, D. Sinha, A.K. Tiwari, K. Chuttani, A.K. Mishra, Synthesis, biological
1230 evaluation and molecular docking studies of high-affinity bone targeting *N,N'*-bis
1231 (alendronate) diethylenetriamene-*N,N'*-triacetic acid: A bifunctional bone scintigraphy
1232 agent, *Chem. Biol. Drug Des.* 82 (2013) 468–476. doi:10.1111/cbdd.12194.

1233 [145] A. Zaheer, M. Monzur, A.M. De Grand, T.G. Morgan, G. Karsenty, J.V. Frangioni,
 1234 Optical imaging of hydroxyapatite in the calcified vasculature of transgenic animals,
 1235 Arterioscler. Thromb. Vasc. Biol. 26 (2006) 1132–1136.
 1236 doi:10.1161/01.ATV.0000210016.89991.2a.

1237 [146] K.R. Bhushan, E. Tanaka, J.V. Frangioni, Synthesis of conjugatable bisphosphonates for
 1238 molecular imaging of large animals, Angew. Chem. Int. Ed. 46 (2007) 7969–7971. doi:
 1239 10.1002/anie.200701216.

1240 [147] K.M. Kozloff, R. Weissleder, U. Mahmood, Noninvasive optical detection of bone
 1241 mineral, J. Bone Miner. Res. 22 (2007) 1208–1216. doi:10.1359/jbmr.070504.

1242 [148] K.M. Kozloff, L.I. Volakis, J.C. Marini, M.S. Caird, Near-infrared fluorescent probe
 1243 traces bisphosphonate delivery and retention *in vivo*, J. Bone Miner. Res. 25 (2010)
 1244 1748–1758. doi:10.1002/jbmr.66.

1245 [149] R.J. Tower, G.M. Campbell, M. Müller, O. Will, C.C. Glüer, S. Tiwari, Binding kinetics
 1246 of a fluorescently labeled bisphosphonate as a tool for dynamic monitoring of bone
 1247 mineral deposition *in vivo*, J. Bone Miner. Res. 29 (2014) 1993–2003.
 1248 doi:10.1002/jbmr.2224.

1249 [150] F.M. Lambers, F. Stuker, C. Weigt, G. Kuhn, K. Koch, F.A. Schulte, *et al.*, Longitudinal
 1250 *in vivo* imaging of bone formation and resorption using fluorescence molecular
 1251 tomography, Bone. 52 (2013) 587–595. doi:10.1016/j.bone.2012.11.001.

1252 [151] Y. Zilberman, I. Kallai, Y. Gafni, G. Pelled, S. Kossodo, W. Yared, *et al.*, Fluorescence
 1253 molecular tomography enables *in vivo* visualization and quantification of nonunion
 1254 fracture repair induced by genetically engineered mesenchymal stem cells, J. Orthop.
 1255 Res. 26 (2008) 522–530. doi:10.1002/jor.20518.

- 1256 [152] J.L. Figueiredo, C.C. Passerotti, T. Sponholtz, H.T. Nguyen, R. Weissleder, A novel
 1257 method of imaging calcium urolithiasis using fluorescence, *J. Urol.* 179 (2008) 1610–
 1258 1614. doi: 10.1016/j.juro.2007.11.100.
- 1259 [153] E. Aikawa, M. Nahrendorf, J.L. Figueiredo, F.K. Swirski, T. Shtatland, R.H. Kohler, *et*
 1260 *al.*, Osteogenesis associates with inflammation in early-stage atherosclerosis evaluated by
 1261 molecular imaging *in vivo*, *Circulation.* 116 (2007) 2841–2850.
 1262 doi:10.1161/circulationaha.107.732867.
- 1263 [154] D.D. Felix, J.C. Gore, T.E. Yankeelov, T.E. Peterson, S. Barnes, J. Whisenant, *et al.*,
 1264 Detection of breast cancer microcalcifications using ^{99m}Tc-MDP SPECT osteosense
 1265 750EX FMT imaging, *Nucl. Med. Biol.* 42 (2015) 269–273.
 1266 doi:10.1016/j.nucmedbio.2014.11.010.
- 1267 [155] F.P. Coxon, K. Thompson, A.J. Roelofs, F.H. Ebetino, M.J. Rogers, Visualizing mineral
 1268 binding and uptake of bisphosphonate by osteoclasts and non-resorbing cells, *Bone.* 42
 1269 (2008) 848–860. doi:10.1016/j.bone.2007.12.225.
- 1270 [156] A.J. Roelofs, F.P. Coxon, F.H. Ebetino, M.W. Lundy, Z.J. Henneman, G.H. Nancollas, *et*
 1271 *al.*, Fluorescent risedronate analogues reveal bisphosphonate uptake by bone marrow
 1272 monocytes and localization around osteocytes *in vivo*, *J. Bone Miner. Res.* 25 (2010)
 1273 606–616. doi:10.1359/jbmr.091009.
- 1274 [157] C.G. Mick, T. James, J.D. Hill, P. Williams, M. Perry, Molecular imaging in oncology:
 1275 ¹⁸F-sodium fluoride PET imaging of osseous metastatic disease, *Am. J. Roentgenol.* 203
 1276 (2014) 263–271. doi:10.2214/AJR.13.12158.
- 1277 [158] A. Elliott, Medical imaging, *Nucl. Instrum. Meth. Phys. Res. A.* 546 (2005) 1–13.
 1278 doi:10.1016/j.nima.2005.03.127.

- 1279 [159] T. Hamaoka, J.E. Madewell, D.A. Podoloff, G.N. Hortobagyi, N.T. Ueno, Bone imaging
1280 in metastatic breast cancer, *J. Clin. Oncol.* 22 (2004) 2942–2953.
1281 doi:10.1200/JCO.2004.08.181.
- 1282 [160] M.F. Kircher, J.K. Willmann, Molecular body imaging: MR imaging, CT, and US. Part I.
1283 principles, *Radiology*. 263 (2012) 633–643. doi:10.1148/radiol.12102394.
- 1284 [161] V. Kubíček, J. Rudovský, J. Kotek, P. Hermann, L. Vander Elst, R.N. Muller, *et al.*, A
1285 bisphosphonate monoamide analogue of DOTA: A potential agent for bone targeting, *J.*
1286 *Am. Chem. Soc.* 127 (2005) 16477–16485. doi:10.1021/ja054905u.
- 1287 [162] M. Fellner, R.P. Baum, V. Kubíček, P. Hermann, I. Lukeš, V. Prasad, *et al.*, PET/CT
1288 imaging of osteoblastic bone metastases with ^{68}Ga -bisphosphonates: First human study,
1289 *Eur. J. Nucl. Med. Mol. Imaging*. 37 (2010) 834–834. doi:10.1007/s00259-009-1355-y.
- 1290 [163] M. Fellner, B. Biesalski, N. Bausbacher, V. Kubíček, P. Hermann, F. Rösch, *et al.*, ^{68}Ga -
1291 BPAMD: PET-imaging of bone metastases with a generator based positron emitter, *Nucl.*
1292 *Med. Biol.* 39 (2012) 993–999. doi:10.1016/j.nucmedbio.2012.04.007.
- 1293 [164] M. Meckel, M. Fellner, N. Thieme, R. Bergmann, V. Kubicek, F. Rösch, *In vivo*
1294 comparison of DOTA based ^{68}Ga -labelled bisphosphonate in non-tumour models. *Nucl.*
1295 *Med. Biol.* 40 (2013) 823–830. doi:10.1016/j.nucmedbio.2013.04.012.
- 1296 [165] K. Suzuki, M. Satake, J. Suwada, S. Oshikiri, H. Ashino, H. Dozono, *et al.*, synthesis and
1297 evaluation of a novel ^{68}Ga -chelate-conjugated bisphosphonate as a bone-seeking agent
1298 for PET imaging, *Nucl. Med. Biol.* 38 (2011) 1011–1018.
1299 doi:10.1016/j.nucmedbio.2011.02.015.
- 1300 [166] K. Ogawa, K. Takai, H. Kanbara, T. Kiwada, Y. Kitamura, K. Shiba, *et al.*, Preparation
1301 and evaluation of a radiogallium complex-conjugated bisphosphonate as a bone

1302 scintigraphy agent, Nucl. Med. Biol. 38 (2011) 631–636.
 1303 doi:10.1016/j.nucmedbio.2010.12.004.

1304 [167] T. Vitha, V. Kubíček, P. Hermann, L.V. Elst, R.N. Muller, Z.I. Kolar, *et al.*,
 1305 Lanthanide(III) complexes of bis(phosphonate) monoamide analogues of DOTA: Bone-
 1306 seeking agents for imaging and therapy, J. Med. Chem. 51 (2008) 677–683.
 1307 doi:10.1021/jm7012776.

1308 [168] L.E. Cole, T. Vargo-Gogola, R.K. Roeder, Bisphosphonate-functionalized gold
 1309 nanoparticles for contrast-enhanced X-ray detection of breast microcalcifications,
 1310 Biomaterials. 35 (2014) 2312–2321. doi:10.1016/j.biomaterials.2013.11.077.

1311 [169] L.E. Cole, T. Vargo-Gogola, R.K. Roeder, Contrast-enhanced X-ray detection of breast
 1312 microcalcifications in a murine model using targeted gold nanoparticles, ACS Nano. 8
 1313 (2014) 7486–7496. doi:10.1021/nn5027802.

1314 [170] L.E. Cole, T. Vargo-Gogola, R.K. Roeder, Contrast-enhanced X-ray detection of
 1315 microcalcifications in radiographically dense, ACS Nano. In Press (2015).

1316 [171] L.E. Cole, R.D. Ross, J.M. Tilley, T. Vargo-Gogola, R.K. Roeder, Gold nanoparticles as
 1317 contrast agents in x-ray imaging and computed tomography, Nanomedicine. 10 (2015)
 1318 321–341. doi:10.2217/nnm.14.171.

1319 [172] K. Kouris, N.M. Spyrou, D.F. Jackson, Minimum detectable quantities of elements and
 1320 compounds in a biological matrix, Nucl. Instrum. Meth. A. 187 (1981) 539–545. doi:
 1321 10.1016/0029-554X(81)90386-4.

1322 [173] H. Lusic, M.W. Grinstaff, X-ray-computed tomography contrast agents, Chem. Rev. 113
 1323 (2013) 1641–1666. doi:10.1021/cr200358s.

- 1324 [174] J.K. Bordoloi, D. Berry, I.U. Khan, K. Sunassee, R.T.M. de Rosales, C. Shanahan, *et al.*,
1325 Technetium-99m and rhenium-188 complexes with one and two pendant bisphosphonate
1326 groups for imaging arterial calcification, *Dalton Trans.* 44 (2015) 4963–4975.
1327 doi:10.1039/c4dt02965h.
- 1328 [175] H. Hirabayashi, J. Fujisaki, Bone-specific drug delivery systems. approaches via
1329 chemical modification of bone-seeking agents, *Clin. Pharmacokinet.* 42 (2003) 1319–
1330 1330.
- 1331 [176] R. Torres Martin de Rosales, C. Finucane, J. Foster, S.J. Mather, P.J. Blower, $^{188}\text{Re}(\text{CO})$
1332 3-dipicolylamine-alendronate: A new bisphosphonate conjugate for the radiotherapy of
1333 bone metastases, *Bioconjugate Chem.* 21 (2010) 811–815. doi:10.1021/bc100071k.
- 1334 [177] F.M. Paes, A.N. Serafini, Systemic metabolic radiopharmaceutical therapy in the
1335 treatment of metastatic bone pain, *Semin. Nucl. Med.* 40 (2010) 89–104.
1336 doi:10.1053/j.semnuclmed.2009.10.003.
- 1337 [178] T. Uehara, Z.L. Jin, K. Ogawa, H. Akizawa, K. Hashimoto, M. Nakayama, *et al.*,
1338 Assessment of ^{186}Re chelate-conjugated bisphosphonate for the development of new
1339 radiopharmaceuticals for bones, *Nucl. Med. Biol.* 34 (2007) 79–87.
1340 doi:10.1016/j.nucmedbio.2006.10.001.
- 1341 [179] K. Ogawa, T. Mukai, Y. Arano, M. Ono, H. Hanaoka, S. Ishino, *et al.*, Development of a
1342 rhenium-186-labeled MAG3-conjugated bisphosphonate for the palliation of metastatic
1343 bone pain based on the concept of bifunctional radiopharmaceuticals, *Bioconjugate*
1344 *Chem.* 16 (2005) 751–757. doi:10.1021/bc040249w.

1345 [180] R.H. Larsen, K.M. Murud, G. Akabani, P. Hoff, O.S. Bruland, M.R. Zalutsky, ^{211}At - and
 1346 ^{131}I -labeled bisphosphonates with high *in vivo* stability and bone accumulation, J. Nucl.
 1347 Med. 40 (1999) 1197–1203.

1348 [181] Y. Yang, N. Liu, J. Liao, M. Pu, Y. Liu, M. Wei, *et al.*, Preparation and preliminary
 1349 evaluation of ^{211}At -labeled amidobisphosphonates, J. Radioanal. Nucl. Chem. 283 (2009)
 1350 329–335. doi:10.1007/s10967-009-0384-0.

1351 [182] E. Årstad, P. Hoff, L. Skattebøl, A. Skretting, K. Breistøl, Studies on the synthesis and
 1352 biological properties of non-carrier-added [^{125}I and ^{131}I]-labeled
 1353 arylalkylidenebisphosphonates: Potent bone-seekers for diagnosis and therapy of
 1354 malignant osseous lesions, J. Med. Chem. 46 (2003) 3021–3032.
 1355 doi:10.1021/jm021107v.

1356 [183] S.A. Gittens, P.I. Kitov, J.R. Matyas, R. Loebenberg, H. Uludag, Impact of tether length
 1357 on bone mineral affinity of protein-bisphosphonate conjugates, Pharm Res. 21 (2004)
 1358 608–616. doi:10.1023/b.pham.0000022407.05163.01.

1359 [184] S.A. Gittens, G. Bansal, C. Kucharski, M. Borden, H. Uludag, Imparting mineral affinity
 1360 to fetuin by bisphosphonate conjugation: A comparison of three bisphosphonate
 1361 conjugation schemes, Mol. Pharmaceutics. 2 (2005) 392–406. doi:10.1021/mp050017u.

1362 [185] H. Sarin, Physiological upper limits of pore size of different blood capillary types and
 1363 another perspective on the dual pore theory of microvascular permeability, J. Angiogen.
 1364 Res. 2 (2010) 14. doi:10.1186/2040-2384-2-14.

1365 [186] M.L. Knothe Tate, “Whither flows the fluid in bone?” An osteocyte's perspective, J.
 1366 Biomech. 36 (2003) 1409–1424. doi:10.1016/S0021-9290(03)00123-4.

- 1367 [187] M.K. Danquah, X.A. Zhang, R.I. Mahato, Extravasation of polymeric nanomedicines
 1368 across tumor vasculature, *Adv. Drug Delivery Rev.* 63 (2001) 623–639.
 1369 doi:10.1016/j.addr.2010.11.005.
- 1370 [188] H.S. Choi, W. Liu, P. Misra, E. Tanaka, J.P. Zimmer, B.I. Ipe, M.G. Bawendi, J.V.
 1371 Frangioni, Renal clearance of nanoparticles, *Nat. Biotechnol.* 25 (2007) 1165–1170. doi:
 1372 10.1038/nbt1340.
- 1373 [189] S.A., K. Bagnall, J.R. Matyas, R. Löbenberg, H. Uludag, Imparting bone mineral affinity
 1374 to osteogenic proteins through heparin–bisphosphonate conjugates, *J. Control. Release.*
 1375 98 (2004) 255–268. doi:10.1016/j.jconrel.2004.05.001.
- 1376 [190] G. Bansal, J.E.I. Wright, S. Zhang, R.F. Zernicke, H. Uludag, Imparting mineral affinity
 1377 to proteins with thiol-labile disulfide linkages, *J. Biomed. Mater. Res.* 74A (2005) 618–
 1378 628. doi:10.1002/jbm.a.30334.
- 1379 [191] S. Zhang, J.E.I. Wright, G. Bansal, P. Cho, H. Uludag, Cleavage of disulfide-linked
 1380 fetuin-bisphosphonate conjugates with three physiological thiols, *Biomacromolecules.* 6
 1381 (2005) 2800–2808. doi:10.1021/bm050273s.
- 1382 [192] S.A. Gittens, J.R. Matyas, R.F. Zernicke, H. Uludag, Imparting bone affinity to
 1383 glycoproteins through the conjugation of bisphosphonates, *Pharm. Res.* 20 (2003) 978–
 1384 987. doi: 10.1023/a:102445903306.

1385 **Table 1:** The relative binding affinity of common BPs measured *in vitro* by different methods.

Study	Method	Substrate	Rank Order ¹	Fold Difference ²
Nancollas <i>et al.</i> , 2006 [11]	Constant composition crystal growth	Hydroxyapatite	ZOL > ALN > IBN > RIS > ETO > CLO	1.6
Leu <i>et al.</i> , 2006 [57]	Radiolabeled	Human bone powder	ALN > ZOL ≈ PAM ≈ RIS > ETO > IBN > TLN > CLO	1.9
Henneman <i>et al.</i> , 2008 [52]	Constant composition crystal growth	Carbonated apatite	ZOL > ALN > RIS	1.17
Lawson <i>et al.</i> , 2010 [58]	Liquid chromatography	Hydroxyapatite	ZOL > RIS	1.4
Jahnke <i>et al.</i> , 2010 [56]	NMR	Hydroxyapatite Human bone powder	PAM > ALN > ZOL > RIS > IBN	2.1 1.95

1386 ¹ALN = alendronate, CLO = clodronate, ETO = etidronate, IBN = ibandronate, PAM = pamidronate, RIS = risdronate, TLN =
1387 tiludronate, ZOL = zoledronate.

1388 ²Fold difference is based on the difference between the greatest and lowest binding affinity.

1389 **Table 2:** Pharmaceutical drugs conjugated to BPs to treat metabolic bone diseases.

Drug ¹	Summary of Results	Reference(s)
17β-estradiol	Bone loss was inhibited in rat models of osteoporosis.	Bauss <i>et al.</i> , 1996, [71] Fujisaki <i>et al.</i> , 1997, 1998 [72,73] Page <i>et al.</i> , 2001, [74,75] Morioko <i>et al.</i> , 2010 [75]
PGE ₂	Bone formation was stimulated <i>in vivo</i> at a 30-fold lower dose than free PGE ₂ . Cortical bone osteopenia was not able to be recovered in rats.	Gil <i>et al.</i> , 1999 [77]
Agonist against EP4 receptor	~6-9% of the initial dose was taken up by long bones in rats and the drug was released with a half-life up to 2 weeks. The therapeutic efficacy has not been examined.	Arns <i>et al.</i> , 2012 [78]
PTH	<i>In vitro</i> binding to hydroxyapatite was greater than free PTH. Bioactivity was greater than free PTH during <i>in vitro</i> cell culture.	Yewle <i>et al.</i> , 2013 [79]
Calcitonin	A high binding affinity was measured both <i>in vitro</i> and <i>in vivo</i> . Therapeutic efficacy was greater than free calcitonin in an osteoporotic rat model.	Bhandari <i>et al.</i> , 2010, 2012 [81,84] Yang <i>et al.</i> , 2013 [47]
OPG	A two- and four-fold greater uptake was enabled in normal and osteoarthritic bone, respectively, compared with free OPG.	Doschak <i>et al.</i> , 2009 [48]

1390 ¹EP4 = prostaglandin E receptor 4, OPG = osteoprotegerin, PGE₂ = prostaglandin E₂, PTH =
1391 parathyroid hormone.

1392 **Table 3:** Antitumor agents conjugated to BP for the treatment of bone cancers.

Drug	Summary of Results	Reference(s)
Cisplatin	Anti-tumor activity was greater than the non-targeted drug <i>in vivo</i> .	Klenner <i>et al.</i> , 1990 [93]
Taxanes	A high binding affinity was exhibited to hydroxyapatite <i>in vitro</i> and bone tumors <i>in vivo</i> . Anti-tumor activity was greater than the non-targeted drug and free BPs, <i>in vitro</i> and <i>in vivo</i> .	Miller <i>et al.</i> , 2009 [95] Miller <i>et al.</i> , 2011 [96] Chaudhari <i>et al.</i> , 2012 [97]
Camptothecin	A high binding affinity to hydroxyapatite was exhibited <i>in vitro</i> .	Erez <i>et al.</i> , 2008 [98]
Gemcitabine	A high binding affinity was exhibited to hydroxyapatite <i>in vitro</i> and bone <i>in vivo</i> . Anti-tumor activity was greater than the free drug and control groups <i>in vivo</i> .	El Mabhouh <i>et al.</i> , 2008 [99], 2006 [49], 2011 [104], 2014 [103]
Doxorubicin	A high binding affinity to hydroxyapatite was exhibited <i>in vitro</i> .	Hochdörffer <i>et al.</i> , 2012 [104]
Methotrexate	A high binding affinity to bone was exhibited <i>in vivo</i> .	Hosain <i>et al.</i> , 1996 [105]
Proteasome inhibitors	Binding to hydroxyapatite was greater than the non-targeted drug <i>in vitro</i> and <i>in vivo</i> . Anti-tumor activity was greater than the non-targeted drug, <i>in vitro</i> and <i>in vivo</i> , leading to increased overall survival of mice.	Agyin <i>et al.</i> , 2013 [106] Swami <i>et al.</i> , 2014 [107]
Arabinocytidine	The incidence of bone metastases and overall tumor burden was decreased in mice compared with no drug or zoledronate at the same dose.	Reinholz <i>et al.</i> , 2010 [108]
TNP-470	Anti-tumor activity was greater and cytotoxicity lower than the non-targeted drug or alendronate <i>in vivo</i> .	Segal <i>et al.</i> , 2011 [109]

1393

1394 **Figure captions**

1395 **Figure 1:** Schematic diagram showing the use of bisphosphonates, either alone or conjugated to
1396 various pharmaceuticals, fluorophores, radionuclides, chelation complexes, macromolecules, and
1397 nanoparticles, for targeting mineral in bone and pathological calcifications for drug delivery,
1398 diagnostic imaging, and radiotherapy.

1399 **Figure 2:** Molecular structure of pyrophosphate and bisphosphonates, including the seven BPs
1400 that are approved for clinical use by the U.S. Food and Drug Administration. Differences in
1401 binding affinity (Table 1) and biological activity are primarily governed by the R₁ (red) and R₂
1402 (blue) side groups.

1403 **Figure 3:** Schematic representation of BP binding to a hydroxyapatite crystal surface, showing
1404 (a) bidentate binding involving the two phosphonates, (b) tridentate binding from the R₁ side
1405 group (OH), and (c) additional interactions from a nitrogen containing R₂ side group (e.g.,
1406 alendronate). **These interactions have been investigated in detail using 3-D computational**
1407 **models [27,30].**

1408 **Figure 4:** Molecular structure of ^{99m}Tc-BP conjugates. (a) In the ^{99m}Tc-BP conjugates currently
1409 used clinically, the BP acts as both the radionuclide chelator and bone-targeting group, which
1410 potentially limits the bone targeting capacity of these agents *in vivo*. (b) Bifunctional chelating
1411 ligands are being investigated as linkers between the BP and radionuclide, freeing the
1412 phosphonate groups to function exclusively for bone-targeting.

1413 **Figure 5:** Examples of *in vivo* bone-targeted fluorescence imaging using BP conjugates. (a) A
1414 fluorescently-tagged BP was delivered to mice *in vivo* and the accumulation of BP at the tibia

1415 was monitored using fluorescent molecular tomography. Reprinted with permission from Tower
1416 *et al.* 2014 [149]. (b) Risedronate and two lower binding affinity analogues were conjugated to
1417 fluorescent molecules and co-administered to growing rats *in vivo* to investigate differences in
1418 the biodistribution, binding, and retention of BPs with different affinity within bone. In sites
1419 with active formation (arrows), the lower affinity BP (blue) was found buried underneath newly
1420 formed bone, while the higher affinity BP (red) was closer to the newly formed surface. In
1421 quiescent sites (arrowheads), there was no difference in penetration depth. Reprinted with
1422 permission from Roelofs *et al.* 2012 [63].

1423 **Figure 6:** BP-conjugated imaging probes have been developed for targeting bone and
1424 pathological calcifications in a wide array of imaging modalities, including nuclear (SPECT,
1425 PET), optical (NIR fluorescence), MRI, and X-ray (CT) imaging. (a) Atherosclerotic vascular
1426 calcifications have been targeted and imaged in rodents *in vivo* with probes comprising BPs
1427 conjugated to NIR [153] or SPECT [174] contrast agents. (b) Breast microcalcifications
1428 associated with cancer were also targeted and imaged *in vivo* using probes comprising BPs
1429 conjugated to NIR, SPECT, and X-ray/CT contrast agents. The NIR and SPECT images were
1430 adapted with permission from Bhushan *et al.* 2008, J Am Chem Soc, 130:17648-17649 [28].
1431 Copyright 2008 American Chemical Society. X-ray image adapted with permission from Cole *et*
1432 *al.* 2014, ACS Nano, 8:7486-7496 [169]. Copyright 2014 American Chemical Society.

Figure

(a)

Atherosclerosis

NIR Imaging

SPECT/CT

(b) Breast Microcalcifications