Poly(lactic acid) – Mass Production, Processing, Industrial Applications, and End of Life

*Castro-Aguirre, E.^a; Iñiguez-Franco, F.^a; Samsudin, H.^b; Fang, X.^c;
Auras, R.^{a*}*

1 **Abstract**

2 Global awareness of material sustainability has increased the demand for bio-
3 based polymers like poly(lactic acid) (PLA), which are seen as a desirable alternative to
4 fossil-based polymers because they have less environmental impact. PLA is an aliphatic
5 polyester, primarily produced by industrial polycondensation of lactic acid and/or ring-
6 opening polymerization of lactide. Melt processing is the main technique used for mass
7 production of PLA products for the medical, textile, plasticulture, and packaging
8 industries. To fulfill additional desirable product properties and extend product use, PLA
9 has been blended with other resins or compounded with different fillers such as fibers,
10 and micro and nanoparticles. This paper presents a review of the current status of PLA
11 mass production, processing techniques and current applications, and also covers the
12 methods to tailor PLA properties, the main PLA degradation reactions, PLA products'
13 end-of-life scenarios and the environmental footprint of this unique polymer.

14

15 Keywords: polylactic acid, lactide, polymer processing, bio-based, compostable,
16 degradation, hydrolysis, life cycle assessment

17

18 Chemical compounds studied in this article

19 Lactic acid (PubChem CID: 612); L-Lactic acid (PubChem CID: 107689); D-Lactic acid
20 (PubChem CID: 61503) ; Lactate (PubChem CID: 91435)

1 Abbreviations

AATCC	American Association of Textile Chemists and Colorists
ABS	Acrylonitrile butadiene styrene
AD	Anaerobic digestion
APR	Association of Postconsumer Plastic Recyclers
CFA	Chemical foaming agent
CNT	Carbon nanotube
CWM	Corn wet mill
DFS	Direct fuel substitution
DMR	Direct measurement respirometer
δ_p	Solubility parameter
E_{act}	Average energy of activation
EFP	Environmental footprint
EGMA	Poly(ethylene-glycidyl methacrylate)
EPA	Environmental Protection Agency
ESR	Electron spin resonance
EVOH	Ethylene vinyl alcohol
GHG	Greenhouse gas
GWP	Global warming potential
HA	Hydroxyapatite
HDPE	High density poly(ethylene)
HDT	Heat deflection temperature
HHV	Higher heating values
HRC	Hydrogen release compound
IC	Industrial composting
IR	Infrared
ISBM	Injection stretch blow molding
LA	Lactic acid
LCA	Life cycle assessment
LDPE	Low density poly(ethylene)

LF	Landfilling
LLDPE	Linear low density poly(ethylene)
MCC	Microcrystalline cellulose
MD	Machine direction
MFR	Melt flow rate
MMT	Montmorillonite
MR	Mechanical recycling
MSW	Municipal solid waste
MSWI	Municipal solid waste incineration
MWCNT	Multiwall carbon nanotube
M_w	Weight average molecular weight
M_n	Number average molecular weight
m_L	Sound velocity
m_{Sh}	Sound velocity of propagation of transverse waves
NAPCOR	National Association for PET Container Resources
n	Intrinsic viscosity
OI	Oxygen index
PA	Polyamide
PAE	Polyamide elastomer
PBAT	Poly(butylene adipate-co-terephthalate)
PBS	Polybutylene succinate
PBSA	Poly(butylene succinate-co-adipate)
PBSL	Poly(butylene succinate-co-l-lactate)
PC	Polycarbonate
PCDI	Polycarbodiimide
PCL	Poly (ϵ -caprolactone)
PCR	Post-consumer recycled
PDLA	Poly(D-lactic acid)
PDLLA	Poly(D,L-lactic acid)
PE	Polyethylene
PEG	Poly(ethylene glycol)

PENNR	Primary energy from nonrenewable resources
PEO	Poly(ethylene oxide)
PET	Poly(ethylene terephthalate)
PEVA	Polyethylene-co-vinyl acetate
PFA	Physical foaming agent
PGA	Polyglycolic acid
PGS	Poly(glycerol sebacate)
PHAs	Poly(hydroxyalkanoates)
PHB	Polyhydroxybutyrate
PHBHxx	Poly[(3-hydroxybutyrate)-co-(3-hydroxyhexanoate)]
PHBV	poly(3-hydroxybutyrate-co-3-hydroxyvalerate)
PIP	Poly(<i>cis</i> -1,4-isoprene)
PLA	Poly(lactic acid)
PLLA	Poly(L-lactic acid)
PP	Poly(propylene)
PPC	Poly(propylene carbonate)
PS	Polystyrene
PTAT	Poly(tetramethylene adipate-co-terephthalate)
PTFE	Polytetrafluoroethylene
PTT	Poly(trimethylene terephthalate)
PU	Poly(ether)urethane
PVC	Polyvinyl chloride
PVOH	Polyvinyl alcohol
RH	Relative humidity
RIC	Resin identification code
ROP	Ring-opening polymerization
SCORIM	Shear-controlled orientation in injection molding
SF	Silk fibroin
SIC	Solvent induced crystallization
SPC	Soy protein concentrate
SPI	Soy protein isolate

TKGM	Thermoplastic konjac glucomannan
TNPP	Tris(nonylphenyl) phosphite
TPO	Thermoplastic polyolefin elastomer
$T_{d,0}$	Initial decomposition temperature
$T_{d,1/2}$	Half decomposition temperature
T_g	Glass transition temperature
T_m	Melting temperature
T_{mc}	Melt crystallization temperature
U.S.	United States
UV	Ultraviolet
V_c	Molar volume of semicrystalline polymer
V_g	Molar volume of glassy amorphous
V_w	Van der Waals volume
ΔH_m	Enthalpy

1

2

3

4

1 1 Introduction

2 Poly(lactic acid) (PLA) is a biodegradable and bio-based aliphatic polyester
3 derived from renewable sources such as corn sugar, potato, and sugar cane. PLA has
4 played a central role in replacing fossil-based polymers for certain applications [1, 2]. As
5 a compostable polymer, PLA is considered a promising alternative to reduce the
6 municipal solid waste (MSW) disposal problem by offering additional end-of-life
7 scenarios [3]. High weight average molecular weight (M_w) PLA is generally produced by
8 polycondensation and/or ring-opening polymerization (ROP) [4]. NatureWorks LLC is
9 the major producer of PLA, with a capacity of 150,000 metric ton year in its U.S.
10 manufacturing facility (in Blair, Nebraska) [2, 5]. Due to great market penetration,
11 worldwide attention, and the rise of PLA production [6], the number of published
12 research studies and reports about PLA have exponentially increased in the last 25
13 years, as shown in Figure 1.

14 <Figure 1>

15 The use of PLA was initially limited to medical applications due to its high cost
16 and low availability, but high M_w PLA now can be processed by injection molding, sheet
17 and film extrusion, blow molding, foaming, fiber spinning, and thermoforming. Also, PLA
18 provides comparable optical, mechanical, thermal, and barrier properties when
19 compared with commercially available commodity polymers such as polypropylene
20 (PP), poly(ethylene terephthalate) (PET), and polystyrene (PS), expanding its
21 commercial range of applications [2, 5]. In the medical field, PLA is extensively used
22 because of its biocompatibility with the human body, including for applications such as

1 medical implants, surgical sutures and medical devices [8-12]. In addition, PLA has
2 been used for applications such as fibers, textiles, plasticulture, serveware, packaging
3 containers (*i.e.*, food packaging for short-life products), and environmental remediation
4 films [13]. PLA is considered as a Generally Recognized as Safe (GRAS) material by
5 the U.S. Food and Drug Administration (FDA). However, PLA has also some limitations
6 (*e.g.*, poor toughness), so research efforts are centered on obtaining PLA products with
7 particular desired properties by blending PLA with other biodegradable and non-
8 biodegradable resins, and/or by compounding PLA with fillers such as fibers or micro
9 and nanoparticles.

10 This critical review focuses on the status of PLA polymer regarding its mass
11 production, the main processing techniques, and methods that have been used to
12 extend PLA applications on the basis of its intrinsic properties. Furthermore, this review
13 provides a panorama of the current main applications categorized according to PLA
14 commercial usage, and an overview of different environments to which PLA products
15 can be exposed during their lifetime that lead to their degradation, including hydrolysis
16 in non-medical applications. Finally, the end-of-life scenarios of PLA products as well as
17 the cradle-to-grave and cradle-to-cradle environmental footprint (EFP) are discussed.

18 19 **2 PLA Resin Production**

20 Lactic acid (LA), also named 2-hydroxy propionic acid, is the basic monomer of
21 PLA. The monomer exists as two stereo isomers, L-LA and D-LA. Figure 2 shows the
22 different chemical structures of these two isomers [2].

1 <Figure 2>

2 The two main methods to produce LA are by bacterial fermentation of
3 carbohydrates or by chemical synthesis [14]. Bacterial fermentation is the preferred
4 industrial process used by NatureWorks LLC and Corbion[®], the two major producers of
5 PLA. Chemical synthesis has many limitations, including limited production capacity,
6 inability to produce only the desired L-LA isomer, and high manufacturing costs [15].

7 The bacterial fermentation processes to produce LA can be classified as
8 homofermentative or heterofermentative methods, depending on the bacteria used. In
9 the heterofermentative method, 1 mole of hexose produces less than 1.8 moles of LA,
10 along with significant levels of other metabolites such as acetic acid, ethanol, glycerol,
11 mannitol, and carbon dioxide. However, in the homofermentative method, 1 mole of
12 hexose can produce an average of 1.8 moles of LA, with minor levels of other
13 metabolites, which means every 100 g of glucose could yield more than 90 g of LA. The
14 homofermentative method is more frequently used by industry due to its greater
15 production yields and lower levels of by-products in comparison with the
16 heterofermentative method [16].

17 In the homofermentative method, species of the *Lactobacillus* genus, such as *L.*
18 *delbrueckii*, *L. amylophilus*, *L. bulgaricus* and *L. leichmanii*, are used under conditions of
19 a pH range from 5.4 to 6.4, a temperature range from 38 to 42 °C, and a low oxygen
20 concentration. The nutrients used to feed the bacteria can be simple sugars, such as
21 glucose and maltose from corn or potato or other sources such as vitamin-B, amino
22 acids, and nucleotides provided by rich corn steep liquor. In general, batch production

processes can yield 1 to 4.5 g.L⁻¹.h⁻¹ of LA, whereas continuous processes can achieve 3 to 9.0 g.L⁻¹.h⁻¹ of LA. On a larger scale, cell recycle reactors can produce up to 76 g.L⁻¹.h⁻¹ [16, 17]. After the initial production process, the LA must be purified by distillation if it will be used for pharmaceutical and food derivative purposes. NatureWorks LLC is currently using a lower pH process to produce LA, which reduces the amount of calcium hydroxide and sulfuric acid by-products, resulting in the lower production of calcium sulphate (gypsum) [5]. Corbion[®], through a proprietary technology, produces LA in a gypsum-free process, which uses second generation feedstocks (*i.e.*, plant-based materials such as corn stover, bagasse, wheat straw, and wood chips) [18, 19].

LA can be used to produce PLA of variable molecular weights; however, usually only the high M_w PLA has major commercial value in the fiber, textile, plasticulture, and packaging industries. Figure 3 shows the three main methods available to produce high M_w PLA from LA: (1) direct condensation polymerization; (2) direct polycondensation in an azeotropic solution; and (3) polymerization through lactide formation [17].

<Figure 3>

The direct condensation polymerization process involves three main steps: 1) free water removal, 2) oligomer polycondensation, and 3) melt polycondensation of high M_w PLA. A detailed description of this process can be found in Hartmann [17]. Direct condensation polymerization is generally considered the least expensive process to produce high M_w PLA. However, the necessity to use chain coupling agents and adjuvants to obtain a solvent-free PLA increases the costs of the products and the complexity of the process [14, 17, 20, 21].

Direct polycondensation in an azeotropic solution is the method applied by Mitsui Toatsu Chemicals, Inc. to produce high M_w PLA [22]. In the process, no chain extenders or adjuvants are used. The PLA is produced by a direct condensation while the condensation water is continuously removed by the azeotropic distillation. The process includes reduction of the distillation pressure of LA for 2–3 h at 130 °C, and the majority of the condensation water is removed. Catalyst is added along with diphenyl ester. A tube packed with 3-Å molecular sieves is attached to the reaction vessel, and the solvent is returned to the vessel via the molecular sieves for an additional 30–40 h at 130 °C. Finally, the polymer is isolated as is or it is dissolved and precipitated for further purification. The effect of different catalysts on the azeotropic dehydration of LA in diphenyl ether and additional details of the technique is reported elsewhere [17, 22].

NatureWorks LLC, the major producer of high M_w PLA based on the original Cargill-Dow patented process [23], combines a solvent-free process and a distillation process to produce PLA with controlled molecular weights in a multi-step process. The LA is first condensed to form low M_w prepolymer PLA. With controlled depolymerization, the cyclic dimer, also referred as lactide, is produced from the low M_w prepolymer PLA [24]. The lactide in the liquid form is purified by distillation. The PLA with controlled molecular weight is produced by the ring opening of lactide and then polymerization with catalyst [16, 17, 25, 26]. Figure 4 shows the basic process design to produce high M_w PLA.

<Figure 4>

PLA produced from this process can be derived from different amounts of L- and D-lactide. The lactide reactor produces a combination of LA, LA oligomers, water, *meso*-lactide and impurities [18]. The mixture must be purified, in this case by vacuum distillation through a series of columns. Due to the difference in boiling points of lactide and *meso*-lactide (Figure 5), the highest M_w PLA is derived from L-lactide and a small amount of *meso*-lactide. The higher the stereochemical purity of the lactide mixture, the higher the stereochemical purity of the PLA. The NatureWorks LLC process results in a large amount of *meso*-lactide, so the properties of the PLA resin obtained through this process can vary according to the amount of *meso*-lactide in the mix. PLA with a large amount of 93% L-LA can crystallize.

<Figure 5>

Although a higher amount of *meso*-lactide in the monomer of PLA contributes to some advantages, such as easier processing and production of amorphous PLA, its presence compromises the thermal stability of PLA (*i.e.*, low heat deflection temperature (HDT)) for a wide range of applications [18]. The presence of *meso*-lactide in poly(L-lactic acid) (PLLA) also may cause deteriorative changes of the crystallinity and biodegradation properties of the materials [27]. Therefore, it is generally desirable for PLA monomer to contain a low amount of *meso*-lactide. Although the production of *meso*-lactide is considered undesirable and often is associated with impurities, NatureWorks LLC has made it possible to refine this monomer into various functionalities. Applications of the *meso*-lactide by-product include its use as chemical intermediates in various surfactants, coatings, and copolymers [28]. *Meso*-lactide can be separated easily from either (*S,S*)-lactide or (*R,R*)-lactide due to its volatile nature.

1 Commonly used methods to perform separation of *meso*-lactide from either (S,S)-
2 lactide or (R,R)-lactide are fractional distillation, melt crystallization and solvent
3 recrystallization [29]; however, these methods pose some difficulties in separating
4 *meso*-lactide from other impurities. NatureWorks LLC has patented a process in which
5 *meso*-lactide can be separated from crude lactide efficiently by means of an enriched
6 stream of a minimum 0.8-mole-fraction of *meso*-lactide and forming a purified (S,S)- and
7 (R,R)-lactide stream. Futerra S.A., a joint venture company between Galactica and Total
8 Petrochemicals, has also patented a method to produce *meso*-lactide, D-lactide, and L-
9 lactide by back biting depolymerization of PLA. The process starts by employing a
10 controlled temperature (200–290 °C) and a reduced pressure in a presence of catalyst
11 and co-catalyst to depolymerize PLA into its dimeric cyclic esters form. The resultant
12 PLA components are depolymerized into a vaporized form in a reaction zone. This
13 vaporized form is then condensed and the *meso*-lactide, D-lactide, and L-lactide
14 produced are recovered separately or together. This invention, which is regarded as the
15 second generation of PLA, can produce D-lactide and *meso*-lactide with high throughput
16 for the production of poly(D-lactic acid) (PDLA) or co-polymers consisting of L- and D-
17 LA enantiomers without the need to start off with LA [30].

18 Extensive research has also been conducted to produce lactide and PLA via low
19 manufacturing and production costs and with enhanced properties [31, 32]. Various
20 catalysts, ranging from metal, cationic, and organic, have been used during
21 polymerization of PLA to achieve high M_w and high optical purity [33]. Metal complexes
22 are reported to be one of the most efficient catalysts for the production of stereoblock
23 isotactic PLA via ROP of *rac*-lactide due to its ability to control parameters such as

1 molecular and chain microstructure [34]. Dusselier *et al.* [35] reported the production of
2 lactide through a direct Brønsted acidic zeolite-based catalytic process, which obtains
3 considerably larger lactide yields than with the controlled ROP of low M_w PLA. Yang *et*
4 *al.* [34] investigated the production of PLA by *rac*-lactide using monoanionic
5 aminophenolate ligands with metal complexes in the presence of solvents such as
6 tetrahydrofuran and 2-propanol. Monomeric zinc silylamido complexes with acrylamine
7 coordination ligands produced a low degree of heterotactic PLA, and similar complexes
8 with alkylamine coordination ligands produced isotactic PLA. The stereoselectivity of the
9 *rac*-lactide polymerization was affected by the pattern of the monoanionic
10 aminophenolate ligands coordination. Moreover, complexes of tetrametallic lithium and
11 sodium diamino-bis(phenolate) were investigated for their efficacy in the polymerization
12 of *rac*-lactide, and these complexes were able to produce PLA with narrow M_w
13 dispersities [36].

14 A recent study reported the use of a biodiesel fuel by-product, glycerol, to
15 produce *rac*-lactide, a monomer for producing stereoblock PLA [37]. The method
16 employed a hydrothermal reaction in the presence of alkaline catalyst to produce
17 racemic lactide. The lactide was further purified by acidizing sodium lactate with sulfuric
18 acid, and the resultant lactide was extracted with ethyl acetate to obtain refined lactide.
19 A mixture of lactide isomers (crude lactide) containing both *rac*-lactide and *meso*-lactide
20 were produced via dimerization of lactic acid (*i.e.*, reactive distillation at temperature of
21 210–230 °C and a pressure of 5–10 mmHg). The levels of *rac*-lactide and *meso*-lactide
22 in the crude lactide were reported to be 32.8 and 32.6%, respectively, with 34.6%
23 impurities (*i.e.*, LA and oligomer). This crude lactide was then purified with ethyl acetate

1 in a N₂ atmospheric condition via three-time recrystallization to obtained a refined *rac*-
2 lactide of 99.1% purity, with *meso*-lactide (0.2%) and other impurities (0.7%) [37].

3 Zhu and Chen [38] also reported a new approach to convert *meso*-lactide to *rac*-
4 lactide. On the basis of the “frustrated Lewis pair” concept, this approach utilized the
5 epimerization of *meso*-lactide to *rac*-lactide using 1,4-diazabicyclo [2.2.2] octane
6 (DABCO)/ tris(pentafluorophenyl) borane 95% (B(C₆F₅)₃) at 2M in toluene, which
7 resulted in 95.4% conversion. This study investigated different types of Lewis acids with
8 different molar concentrations and different polar and non-polar solvents to find
9 optimized conversion of *meso*-lactide to *rac*-lactide. The epimerization method used in
10 this study is versatile since it was able to effectively convert lactide stereoisomers
11 regardless of ratio into *rac*-lactide [38].

13 **3 PLA Processing**

14 The methods for processing PLA are well-established polymer-manufacturing
15 techniques used for other commercial polymers such as PS and PET [39]. Melt
16 processing is the main technique for mass production of high *M_w* PLA in which the PLA
17 resin obtained (as shown in Figure 4) is converted into end products such as consumer
18 goods, packaging, and other applications. Melt processing is characterized by heating
19 the material above its melting temperature, shaping the molten polymer into desired
20 shapes, and finally cooling to stabilize its final dimensions. Processing of PLA has been
21 extensively reviewed [1, 40]. The main objectives of this section are to summarize the
22 key methods used to process PLA and then to provide a short update of new research

1 since our last review of PLA processing [1]. Additionally, we direct the reader to a
2 number of contributions that explain each processing technique in further detail.

3 The limiting factors for processing PLA are similar to those for fossil-based
4 polymers: degradation at the upper limits of temperature and shear, and poor
5 homogeneity at the lower limits [39]. However, understanding PLA's thermal,
6 crystallinity, and melt rheological behaviors is critical to optimize its processing and
7 component qualities. Detailed information about these properties is provided elsewhere
8 [13]. PLA is a hygroscopic material and very sensitive to high relative humidity (RH) and
9 temperature [39]. Before PLA can be processed, it should be dried to a water content
10 less than 100 ppm (0.01%, w/w) to avoid hydrolysis (M_w reduction), as discussed in
11 section 6.1. During industrial production, PLA is mostly dried to values below 250 ppm
12 water (0.025%, w/w). If PLA is processed at temperatures higher than 240 °C or with
13 longer residence times, the PLA resin should be dried below 50 ppm water to avoid
14 number average molecular weight (M_n) reduction [1, 41]. To achieve effective drying,
15 the dew point of the drying air should be equal or lower than -40 °C, with an airflow rate
16 greater than 0.03 m³.h⁻¹.kg⁻¹ of resin throughput. After the PLA resin is properly dried,
17 melt extrusion is the most important technique for continuous melt processing of high
18 M_w PLA consumer goods.

19 3.1 Extrusion

20 Extrusion of PLA in a heated screw is the first step before any further processing
21 of PLA, such as injection, thermoforming or spinning, takes place. Commercial PLA
22 resins can be processed by using conventional screws equipped with a general-purpose

1 screw of L/D ratio (ratio of flight length of the screw to its outer diameter) of 24 to 30. If
2 PLA is processed in extruders designed for polyolefins, and the extruder is working near
3 to its maximum power, the extruder may not have enough torque to process PLA. So, it
4 is recommended to process PLA in extruders regularly used for polyesters or PS, with
5 similar performance profile. The recommended compression ratio (ratio of the flight
6 depth in the feed section to the flight depth in the metering section) for PLA processing
7 is in the range of 2 to 3. The extruder provides the heat to melt the resins by heater
8 bands wrapped around the barrel; however, the majority of heat input is provided by the
9 friction of the resin between the screw and the barrel. Thus, to ensure that all the
10 crystalline domains of the semicrystalline PLA are melted, and to achieve an optimal
11 melt viscosity for processing, the heaters are usually set at 40 to 50 °C higher than the
12 melting temperature (T_m). The melt rheological properties of PLA play an important role
13 in how the polymer flows during extrusion. Melt viscosities of High M_w PLA melt
14 viscosities are in the order of 5,000–10,000 P (500–1000 Pa.s) at shear rates of 10–50
15 s^{-1} ; these polymer grades are equivalent to M_w of ~100,000 Da for injection molding to
16 ~300,000 Da for cast film extrusion applications [1]. Extruding PLA at high temperatures
17 can cause thermal degradation (as explained in section 6.2), so the temperature profile
18 during extrusion of PLA should be tightly controlled. The thermal degradation of PLA
19 can be attributed to several factors: (a) hydrolysis by trace amounts of water; (b) zipper-
20 like depolymerization; (c) oxidative, random main-chain scission; (d) intermolecular
21 transesterification to monomer and oligomeric esters; and (e) intramolecular
22 transesterification resulting in formation of monomer and oligomer lactides of low M_w
23 [40]. Processing PLA above 200 °C can degrade PLA through intra and intermolecular

1 ester exchange, *cis*-elimination, and radical and concerted non-radical reactions
2 resulting in the production of CO, CO₂, acetaldehyde, and methyl ketone [42].
3 Depending on the rate of the degradation reaction, the end product can be lactide or
4 acetaldehyde. Formation of lactide during extrusion can affect the optical purity of the
5 final extruded PLA; reduce the melt viscosity; produce fuming of lactide (*i.e.*, lactide
6 vapor produced during extrusion); and can condense on equipment surfaces, such as
7 chilled rollers and molds, which is known as “plate out.” To avoid lactide fuming and
8 condensation, the temperature of the surfaces should be increased. Table 1 shows the
9 recommended processing temperatures for a number of commercially available
10 NatureWorks LLC PLA resins known as Ingeo™ PLA.

11

1 Table 1 Properties and processing temperatures of selected commercially available Ingeo™ PLA resins

	2500HP [43]	3001D [44]	4032D [45]	6060D [46]	7001D [47]	8052D [48]
Application	Extrusion - Crystalline sheets	Injection molding	Biaxially oriented films	Fiber melt spinning	Injection stretch blow molding	Foam
Specific gravity, ASTM D792	1.24	1.24	1.24*	1.24	1.24	1.24
MFR, g/10 min (210 °C, 2.16 kg) ASTM D1238	8	22	N/A	8-10	6	14
Melt temperature, °C	210	200	210	N/A	200-220	200
Feed throat, °C	45	20	45	N/A	20	20
Feed temperature, °C	190	150/165**	180	N/A	180	165
Compression section, °C	200	195	190	N/A	210	195
Metering section, °C	210	205	200	N/A	210-220	205
Nozzle,	N/A	205	200	N/A	210-220	205
Adapter, °C	210	N/A	N/A	N/A	N/A	N/A
Die, °C	210	N/A	N/A	N/A	N/A	N/A
Mold, °C	N/A	25	200	N/A	21-38	25
Screw speed, rpm	20 - 150	100-175	20-100	N/A	N/A	100-175
Back pressure, MPa	N/A	0.345- 0.689	0.414- 0.483	N/A	0.689- 1.379	0.345- 0.689

2 Notes: * ASTM 1505, **150°C amorphous / 165°C crystalline. N/A: Not available

3.2 Injection molding

PLA is primarily injected on machines that have a reciprocating screw extruder, as shown in Figure 6. In this case, the screw is designed to reciprocate within the barrel to inject the molten polymer into the mold cavities. At the start, the molds close and the nozzle opens, and the screw moves forward, injecting the molten polymer into the mold cavity. Since the polymer shrinks during cooling, the screw is maintained in the injection position by holding pressure steady. Then, the nozzle is closed and the screw starts retracting. During the cooling cycle of the molds, the screw rotates and conveys the melt polymer forward; sufficient cooling time should be provided to produce stable parts. Cycle time of the injection part is extremely important to control shrinkage of the PLA injection-molded parts, which are generally brittle due to the accelerated physical aging of PLA, which is attributed to its low glass transition temperature (T_g). PLA parts produced with low M_n are subjected to faster aging. Likewise, PLA injection-molded parts could exhibit low crystallinity due to the slow crystallization rate of PLA. Furthermore, in order to avoid excessive shrinkage, processing parameters such as mold temperature, packing pressure, cooling rate, and post-mold cooling treatment should be properly controlled. A complete explanation of how to optimize the cycling time for PLA injection-molded parts and reduce shrinkage is provided elsewhere [1].

<Figure 6>

Shear-controlled orientation in injection molding (SCORIM) is a technique that allows the enhancement of mechanical properties of semicrystalline polymers, like PLA, by tailoring the morphology of the solidifying polymer melt using an in-mold shearing

1 action that is externally controlled [39]. As in conventional injection molding, the
2 processing cycle begins with the filling of the cavity. The SCORIM unit, which has two
3 cylinders with their own melt flow path and three operation modes (A, B and C), then
4 can manipulate the melt. Mode-A consists of an out of phase reciprocation of the two
5 pistons; Mode-B consists of an in-phase operation to pump more melt into the cavity;
6 and Mode-C consists of applying hydrostatic pressure by two cylinders for offsetting
7 volumetric shrinkage [3].

8 **3.3 Injection stretch blow molding**

9 Injection stretch blow molding (ISBM) is primarily used to produce bottles. Figure
10 7 shows a general ISBM process for making PLA bottles. ISBM requires the initial
11 production of a parison or preform by injection molding. Then, the preform is transferred
12 to a blow molding machine where it is heated at around 90 °C, and the preform is
13 stretched in both the axial and hoop directions to achieve biaxial orientation, which
14 improves the physical and barrier properties of PLA bottles. Additives are added to the
15 PLA resins to optimize the absorption of energy by the preform from the infrared lamps,
16 so that optimal stretching is achieved. PLA preforms tend to shrink after reheat in
17 regions near the neck and the end cap (*i.e.*, regions where the residual injection
18 stresses are largest.) Residual stresses can be minimized by properly designing the
19 preform. ISBM can be conducted in one or two stages where the preform is produced
20 during the same step as blowing or it is just produced in two consecutive steps [1]. PLA
21 resins show strain-hardening when stretched to a high strain ratio. Therefore, stretching
22 of PLA should be programmed to obtain PLA bottles with optimal sidewall orientation

and thickness. Under-stretched preforms result in bottles with large wall thickness variation and lower mechanical properties. Over-stretched preforms result in stress whitening due to the formation of micro-cracks on the bottle surface that diffract light. Preform axial stretch ratios of 2.8–3.2 and hoop stretch ratios of 2–3, with the desirable planar stretch ratio of 8–11, are recommended [1]. Introducing standard features in the bottle design, such as transition shape, step changes, and pinch points on the core and cavity, may help to improve PLA bottle performance. Preform designs are also important for obtaining bottles with good clarity and physical properties, which usually depends on the bottle design and the blow mold equipment; however, there is little information about that in the literature due to the proprietary nature of this information.

<Figure 7>

3.4 Cast film and sheet

Cast is the main method to produce films with thickness ≤ 0.076 mm and sheets with thickness typically ≥ 0.25 mm. During the production of cast films, molten PLA is extruded through a lip die and quenched on polished chrome rollers refrigerated with cooled water. Cast films usually have a low crystallinity and transparent appearance due to the rapid cooling provided by the chilled rolls. Cast film extrusion has the advantages of providing good optical properties, high production rate, and good control of film thickness [39]. Deckle systems to control film and sheet edge trimming are generally avoided to reduce the effect that the degraded molten PLA introduces in the edge instability. The gap of the die is set to around 10% higher than the thickness of the film and/or sheet to obtain the right film and sheet dimensions. Table 1 shows the

recommended temperatures to extrude PLA films and sheets (PLA 4032D and 2500HP). Horizontal roll stacks are used to produce PLA films and sheets due to the polymer's low melt strength. Roller temperature between 25–50 °C is recommended to avoid lactide condensation, and by using an exhaust system around the die, lactide buildup can be controlled. Additionally, good contact between the web and the rolls is recommended to minimize lactide buildup. Slitting and web handling of PLA is similar to that for PS. Rotary shear knives are recommended for trimming the edge of PLA web since razor knives could yield rough edges and break the web. Orientation between 2 and 10 times its original length will improve PLA thermal and impact sheet properties. PLA films produced from 98% L-lactide can be subjected to 2 to 3 times machine direction (MD) stretch ratios, and 2 to 4 times transverse stretch ratios. When a larger amount of D-lactide is present in PLA, more amorphous sheet or film is produced, and larger stretch ratios can be obtained. Extruded PLA films and sheets have excellent optical properties and high Young's modulus, but low elongation at break and toughness [40]. Table 2 shows the main optical, physical, thermal, mechanical, and barrier properties of PLA films. Figure 8 shows the production of biaxially oriented PLA extrusion cast film.

Production of PLA film by blown film technologies is rarely done since PLA has weaker melt strength, and so formation of a stable bubble during extrusion is challenging. Attempts to create PLA blown film have been conducted by using viscosity enhancers. Most of the additives used to increase the melt strength of the PLA are proprietary [40]. Besides low melt strength, PLA is stiff, so when collapsing the bubble

1 during blown film production, permanent wrinkles may be produced. The problem of
2 dead-fold properties can be overcome by also introducing additives.

3 <Figure 8>

4 Table 2 Selected average optical, physical, mechanical, and barrier
5 properties of PLA films reported from a number of studies using different
6 grades of PLA, adapted and modified from Auras [49].

Optical	
Refractive index, ^{(a), [50]}	1.35-1.45
Clarity	Clear - yellow
Thermo-Physical	
Density amorphous, ^[51] kg.m ⁻³	1250
Density 100 % crystalline, ^{(b), [50]} kg.m ⁻³	1490
Van der Waals volume (V _w), ^{(c), [50]} cm ³ .mol ⁻¹	34.45
Molar volume of glassy amorphous (V _g), ^{(c), [50]} cm ³ .mol ⁻¹	55.12
Molar volume of semicrystalline polymer (V _c), ^{(c), [50]} cm ³ .mol ⁻¹	49.44
Solubility parameter (δ _p), 25°C, ^[2] MPa ^{0.5}	19-20.5
T _g , ^[52] °C	50-80
T _m , ^[52] °C	130-180
Initial decomposition temperature (T _{d,0}), ^[53] °C	335
Half decomposition temperature (T _{d,1/2}), ^[53] °C	395
Average energy of activation (E _{act}), ^[53] kJ.mol ⁻¹	205-297
Enthalpy (ΔH _m), ^[54] 100%, J.g ⁻¹	93
Crystallinity, ^[53] %	0 – 40
Heat deflection temperature, ^[55] °C	55 – 65
Vicat penetration temperature, ^[55] °C	59
Thermal conductivity x10 ⁻⁴ , ^[1] cal.cm ⁻¹ .s ⁻¹ . °C ⁻¹	2.9
Heat capacity, ^[1] cal.g ⁻¹ .°C ⁻¹	0.39
Thermal expansion coefficient x10 ⁻⁶ , ^[1] °C ⁻¹	70
Surface tension, ^[2] dyn.cm ⁻¹	42.0
Friction coefficient, ^[2]	0.37

Melt flow Index, ^{(d), [2]} , g. min ⁻¹	0.85
Rheological	
Mark-Houwink constants	
K , ^{(e), [56]} , mL.g ⁻¹	0.0174
a , ^{(e), [56]}	0.736
Mechanical	
Tensile strength @ yield, ^[2] , MPa	0.88
Elastic modulus, ^[2] , GPa	8.6
Elongation at break, ^[2] , %	3-30
Flexural strength, ^[55] , MPa	70
Flexural modulus, ^[55] , GPa	3.8
Unnotched Izod Impact, ^[55] , J.m ⁻¹	106
Notched Izod Impact, ^[55] , J. m ⁻¹	26
Rockwell hardness, ^[55]	88
Impact strength	Poor
Barrier	
Oxygen permeability $\times 10^{-18}$, ^{(f), [52, 54]} , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹ @25°C	1.21 ± 0.07
Oxygen activation energy, ^{(f), [52, 54]} , kJ.mol ⁻¹ [25-45°C]	41.43 ± 3.5
Carbon dioxide permeability $\times 10^{-17}$, ^{(g), [52]} , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹ @25°C	2.77 ± 0.05
Carbon dioxide activation energy, ^{(g), [52]} , kJ.mol ⁻¹	15.65 ± 0.63
Nitrogen permeability $\times 10^{-19}$, ^[57] , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹	468
Nitrogen activation energy, ^[57] , kJ.mol ⁻¹	11.2
Water permeability $\times 10^{-14}$, ^{(h), [52, 54]} , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹ @25°C	1.75 ± 0.05
Water activation energy, ^{(h), [52, 54]} , kJ.mol ⁻¹	-9.73 ± 0.27
d-limonene permeability $\times 10^{-19}$, ^{(i), [58, 59]} , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹	<1.0
Ethyl acetate permeability $\times 10^{-19}$, ^{(i), [58, 59]} , kg.m.m ⁻² .s ⁻¹ .Pa ⁻¹	5.34*
Methane permeability $\times 10^{-18}$, ^[57] , m ³ (STP).m.m ⁻² .s ⁻¹ .Pa ⁻¹	7.50
Methane activation energy, ^[57] , kJ.mol ⁻¹	13
Helium transmission rate $\times 10^{-6}$, ^{(j), [60]} , cm ³ .cm.m ⁻² .s ⁻¹ .kPa ⁻¹	10.30

- 1 N/A: Not available
- 2 Note: (a) Refractive index values for PLA were calculated by Gladstone and Dale, Vogel, and Lloyenga methods; (b)
- 3 density of 100% PLA was calculated according to the group contribution method; (c) PLA value was calculated using
- 4 the group contribution method; (d) PLA value measured at 200°C and 5 kg according ASTM D1238; (e) PLA value
- 5 was measured according to ASTM D445 and D446 (PLA values were determined in tetrahydrofuran at 30 °C); (f)
- 6 oxygen activation energy is reported for temperatures between 25-45°C; (g) carbon dioxide activation energy is

reported for temperatures between 25-45°C; (h) water activation energy is reported for temperatures between 10-37.8°C; (i) ethyl acetate values of PLA at 3030 Pa and 30°C and 9435 Pa and 30°C, respectively; d-limonene values of PLA at 245 Pa and 45°C and 45 Pa and 23°C, respectively; (j) value of amorphous PLA at 23°C and 0% RH.

3.5 Thermoforming

Thermoforming is a standard method to produce PLA containers, such as clamshell, cups, and food trays, extensively used for short-shelf-life product packaging applications. Thermoforming is a process in which a pliable plastic is pressed into a final shape by vacuum or air pressure. Figure 9 shows the steps to produce a thermoformed PLA part. Generally, a PLA sheet (thickness >10 mil or 254 µm) is extruded as previously described, heated, introduced to a mold where it is pre-stretched and then formed (assisted or not by a plunger) to obtain the final PLA container. Initial heating of the PLA film is by infrared (IR) lamps; the IR wavelength should match the maximum absorbance of the polymer being thermoformed. PLA sheets are thermoformed at temperatures around 80–110 °C. Aluminum molds are recommended for thermoforming PLA. As in the case of ISBM, orientation improves toughness of PLA containers; therefore, thermoformed parts are less brittle than PLA sheet, especially in regions highly stretched during the forming operations rather than flanges and lips. Clamshells produced from PLA sheets show better drop-impact properties at freezing temperature (-20 °C) than PET and PS clamshells [61]. PLA sheets produced with 100% recycled PLA flakes showed a reduction of M_n of around 5% compared with the original PLA samples; however, this reduction did not affect the production of PLA containers with 100% post-consumer recycled (PCR) PLA content [62].

1 <Figure 9>

2 **3.6 Other processes – Foaming and fibers**

3 PLA resins are used in foam and textile applications. Although methodologies for
4 these applications are well established for other commercial polymers, until now the
5 amount of commercial PLA (by weight) marketed in these forms has been minor.
6 Obtaining lightweight materials with improved cushioning, insulation, and structural
7 performance is a major reason to produce PLA foam parts. Initially, PLA foams were
8 extensively used for medical applications (sutures, implants, and screws), but it is also a
9 promising bioplastic for use in relatively short-lived applications like transport packaging
10 (loose-fill packaging, insulation, and cushioning) or disposable cutlery. In this context,
11 PLA would allow an alternative disposal route and replace fossil-based foams since the
12 polymer is biodegradable and based on renewable resources [63].

13 Most commercial foaming of PLA is obtained by batch or continuous processes.
14 In these processes, a physical or chemical foaming agent (PFA or CFA) is introduced in
15 the PLA matrix. PFAs are dissolved in the molten PLA matrix and undergo a physical
16 change, such as volatilization of a liquid or release of compressed gas, during foaming.
17 Examples of PFAs are hydrocarbons and halogenated hydrocarbons and gases such as
18 N₂, CO₂, and Ar. CFAs are chemical compounds which are stable at room temperature,
19 such as sodium bicarbonate, azodicarbonamide, *p,p'*-oxybis(benzene) sulfonyl
20 hydrazide, *p*-toluene sulfonyl semicarbazide, and 5-phenyltetrazole, but after a set
21 change of temperature and pressure conditions these compounds convert to gas by
22 undergoing a chemical reaction that provides gas to nucleate bubbles inside the PLA

1 matrix and create the foam structure. CFAs can react endothermically (*i.e.*, absorption
2 of heat during decomposition), or exothermically (*i.e.*, release of heat during
3 decomposition) [64]. Generally, CFAs are selected to be used at temperatures close to
4 the processing temperature of the polymer. In the case of PLA, a number of PFAs and
5 CFAs have been used such as CO₂, N₂, and BIH40 (a CFA produced by Boehringer
6 Ingelheim Chemicals) [64].

7 During the batch process, a gas (N₂, CO₂ or a mixture) is saturated into the PLA
8 matrix at a pressure below 800 MPa at room temperature in a chamber. Then, the
9 saturated PLA sample is removed from the chamber, and the solubility of the blowing
10 agents is suddenly reduced by increasing the temperature and/or reducing the
11 pressure, so that bubbles can nucleate. Finally, the produced cells are vitrified by
12 reducing the temperature below the T_g of the PLA matrix. Figure 10 a shows a
13 representation of a batch process.

14 The continuous microcellular foaming process was developed to overcome some
15 of the drawbacks of the batch process, for example, the time required to saturate the
16 samples. In a continuous process, a blowing agent, generally a gas, is introduced into
17 the molten PLA matrix in a modified extruder (Figure 10 b). After that, the saturated gas
18 PLA matrix is solution mixed and transferred to a static mixer, which guarantees the
19 single-phase solution. Finally, the microcellular nucleation occurs in the nozzle of the
20 extruder unit due to the rapid pressure drop. PLA foaming is affected by a number of
21 parameters such as initial crystallinity, melt rheology, fillers, amount of CFAs, and
22 processing conditions. A detailed review of PLA microcellular foams can be found

elsewhere PLA foam samples have been reported to increase Notched Izod impact strength by more than triple while reducing the specific density by almost half [64].

PLA's low melt strength is the main drawback of using it for foaming applications; however, new modifiers are being investigated to induce crosslinking, chain extension, or grafting to increase the molecular weight and the melt properties such as shear and elongational viscosity. Gottermann *et al.* [63] reported that the use of modifiers, such as organic peroxide, multifunctional epoxide, styrene maleic anhydride, isocyanurate + diisocyanate, and bisoxazoline + diisocyanate, helps to increase the M_w of commercially available PLA. In most cases the foam density decreased and cell size increased (except with multifunctional epoxide), and when modified with organic peroxide and multifunctional epoxide the elongational viscosity of PLA increased [63].

<Figure 10>

Spinning of PLA fibers has been used to produce PLA fibers for suture applications. PLA fibers are gaining importance since they have lower water barrier properties. Conventional processes and finishing technologies can be used for processing PLA fabrics; PLA shows similar properties to other synthetic fibers, but requires modified dyeing and finishing techniques due to its low affinity to conventional water-soluble dyes [65]. PLA fibers can be used to produce breathable garments. Among the important criteria to produce fibers are: *i*) to control moisture content to be less than 50 ppm to avoid any possible hydrolytic degradation, and *ii*) to achieve an optimum drawing temperature ($>PLA's\ T_g$) and drawing speed (200–9000 m.min⁻¹) to obtain appropriate crystallinity and strong PLA fibers [66]. During spinning of PLA

1 fibers, the microstructure of the polymer chains is oriented in the axis direction of the
2 fiber, so a fiber with very high aspect ratio (length to diameter) and orientation can be
3 produced. Spinning of fibers produces a controlled molecular orientation and spatial
4 arrangement of the PLA structure. In modern spinning processes, a molten polymer or
5 solution is extruded through a small orifice and is elongated by applying an external
6 force. Then, the polymer filament is cooled and precipitated. Further processing of the
7 polymer filament may take place, such as drawing, unidirectional stretching, and texture
8 control. PLLA with a M_w around 0.5 to 3.5×10^5 Da is used for melt spinning through a
9 two-stage process that includes melt spinning and hot drawing [67]. A standard melt
10 spinning process is represented in Figure 11. A typical melt temperature profile for PLA
11 resin melt spinning is shown in Table 2. A general extrusion process, as described in
12 section 3.1, is used to produce the fibers; however, the spin pack plays an extremely
13 important role since it delivers the molten PLA previously filtered to remove impurities to
14 the spinneret plate through the spinneret holes. The spinneret holes have a specific
15 ratio of length to diameter to achieve the desirable shear flow mode. Spinneret plates
16 can be monofilament or multifilament. Deniers, the unit used to quantify filaments, is
17 defined as weight in grams of a 9,000-m long filament. For PLA, the recommended
18 diameter of the spinneret holes range from 0.2–0.35 mm with a typical ratio of 2 to 3.
19 Larger hole diameters are necessary for filaments greater than 6 deniers. After the
20 filament is produced, it is air cooled at temperatures about 15–30 °C in an air quench
21 zone or chamber, which cools the filament through its melt crystallization temperature
22 (T_{mc}) and to its T_g . When the spun filament temperature is below the T_g , the spinning
23 process is considered complete. Then, the spun filament needs to be finished and

wound up. A detailed description of the production of melt spinning PLA fibers can be found elsewhere [67].

Solution spinning of PLA can also be carried out to avoid the substantial hydrolytic degradation that happens during melt spinning. During solution spinning, PLA is extruded as in melt spinning, but then the spinneret is submerged in a spinning bath, so that the PLA melting point is immediately depressed to below room temperature. After that, the solvent is removed by solvent-assisted coagulation or evaporation. Two main methods are used for solution spinning: wet and dry spinning. During wet spinning, PLA is dissolved in a solvent such as tetrahydrofuran, chloroform and/or dichloromethane, and then it is extruded in a submerged bath with a mixture of a solvent and a non-solvent (e.g., toluene at 110 °C) to induce coagulation. Generally, PLLA with $M_w < 3 \times 10^5$ Da is not suitable for wet spinning. During dry spinning, after the PLLA dope solution (e.g., PLLA in chloroform) is extruded, and pumped through a multi-hole spinneret, it is introduced in a chamber with circulating heated air/gas, so that the solvent can evaporate. PLA fibers are used for textiles and medical applications; examples of these applications are presented in section 5.2.

<Figure 11>

4 Tailoring PLA Properties

Although PLA has many desirable properties for consumer good applications, there are limitations for all-purpose use, as with any polymer. Researchers have been trying to expand PLA use and applications by blending PLA with a number of

1 biodegradable and non-biodegradable resins, and/or by compounding PLA with a
2 number of fillers such as fibers and micro and nanoparticles. Covering all of the blends
3 and composites in a short overview is a daunting task, and a number of review papers
4 have been written to discuss the improvements of PLA properties [68-73]. Therefore,
5 this section provides a summary of the main resins used to blend and/or compound with
6 PLA, and it will direct the reader to the original work to obtain additional information.

7 Blending of PLA with biodegradable and non-biodegradable polymers has been
8 extensively reported [71-73]. Figure 12 shows the main biodegradable and non-
9 biodegradable resins blended with PLA. PLA is considered a brittle polymer, so
10 extensive research has been conducted to improve its toughness for different
11 applications [74, 75]. In general, a rubbery polymer with low T_g (generally below 20 °C
12 of the use temperature) is blended with PLA at a low ratio to create small rubber
13 domains between 0.1 and 1.0 μm with good interfacial adhesion to PLA, so that the
14 rubber domains can dissipate the impact energy when PLA is failing through fracture
15 [76]. Beside an improvement in toughness, different polymers have been blended to
16 PLA to improve properties such as optical [75, 77], barrier [78-83], thermal [74], and
17 biodegradation [84-88].

18 <Figure 12>

19 A polymer composite is defined as a material that has two or more distinct
20 phases. One of the phases is a discontinuous phase considered as the reinforcement
21 phase dispersed in a continuous or matrix phase. The reinforcement phase can be
22 fibers and/or micro and nano particles. The main goal of adding a reinforcement phase

1 to PLA is to tailor its properties, such as elongation at break [81, 132-141], heat
2 resistance [138, 142, 143], dimensional stability [137, 144-147], barrier [132, 137, 140,
3 148, 149], and cost [150], to overcome some of PLA's shortcoming properties compared
4 with fossil commodity polymers, as well as brittleness and low thermal stability [2]. Since
5 the main engineering properties of a composite result from the discontinuous phase,
6 PLA has been reinforced with natural and synthetic fibers, micro and nano fillers [73,
7 151].

8 Fibers with a larger length to diameter ratio can be used to carry load in fiber-
9 PLA composites, and increase their applications [73]. Natural and synthetic fibers have
10 been used to reinforce PLA. Dispersion and orientation of the fibers play a crucial role in
11 obtaining PLA composites with the desired properties. Adhesion between the PLA
12 matrix and the fibers is a strong controlling parameter of the final composite properties
13 since enhancement of the composite performance is strongly attributed to the adhesion
14 between the continuous and discontinuous phases. Wood and non-wood natural fibers,
15 such as cotton, jute, flax, kenaf, sisal, and hemp, are extremely attractive to be
16 compounded with PLA since they are 100% renewable and so a fully bio-based
17 composite is obtained. Synthetic fibers, such as glass and carbon-based, are also
18 commonly used to reinforce PLA parts since they have extremely high tensile strength,
19 which improves the final mechanical properties of the composite [73].

20 Fillers in micro and nano sizes have played an increasing role in creating
21 composites with lower cost and environmental footprint. Inorganic fillers, such as talc,
22 mica, hydroxyapatite, carbon black, and gypsum, have been used for many decades to

reinforce polymers since they can enhance PLA mechanical properties with a small amount of composite. Lately, the addition of nanoparticles has gained attention since adding nanoscale clay particles results in significant improvement of material performance. Some of the specific nanocomposite properties that are enhanced through the exfoliation of these nanoparticles include mechanical [152-160], barrier [132, 137, 140, 148, 149, 160, 161], and thermal properties [156, 157, 160]. The mechanical property of polymers with a nanoclay loading of 3–6% can achieve equivalent mechanical properties (*i.e.*, tensile strength, impact strength, flexural modulus) to a polymer with up to 30 wt% fillers at the microscale (*i.e.*, glass and mineral fibers, etc.) [162, 163]. Since clay platelets are considered impermeable to small molecules (*e.g.*, gasses, liquids), and their presence in the polymer matrix extends the diffusion path of small molecules through a tortuous path, nanoclays can improve the barrier of the nanocomposite [164]. Although a recent study showed that in the case of organic compounds, it is the sorption of the compound to the surfactant added to the nanoclay that modifies the barrier property of PLA (*i.e.*, by modifying the solubility parameters) [165]. The high thermal stability of clays allows their use in polymers for heat-resistant and flame-retardant applications. Enhancement in polymer thermal stability is affected by the size of clay particles; nanoclays with an aspect ratio (lateral dimension vs thickness) greater than 100 are usually preferred [163]. Well-dispersed nanoclay particles in a polymer matrix can act as both a superior heat insulator [166] and mass transport barrier [167]. Figure 13 shows the diameter or thickness of selective micro and nanofillers that have been added to PLA.

<Figure 13>

5 PLA Industrial Applications

Production of PLA for industrial applications has risen steeply due to its competitive cost and the positive public perception of the polymer's environmental footprint. Industrial applications for PLA can be categorized into two main groups: consumer durable goods and consumer non-durable goods. From an economic perspective, consumer durable goods are commodity products with a lifetime of more than three years such as appliances, cars, and medical products. Consumer non-durable goods are products having a lifetime up to three years such as packaging, short-term medical items, and serviceware [189]. In some cases these product categories may overlap, depending on the PLA design. The next section lays out the industrial applications for PLA according to commercial usage categories: medical, fibers and textiles, packaging and serviceware, environmental remediation, and others.

5.1 Medical

Since the early 1960s, PLA has been used for medical applications such as implants and medical devices. PLA found a favorable niche for medical implants since it degrades over time, therefore the removal step of an implant is not required. Also, LA is naturally produced by the body and has no known toxicity effect on humans. Various applications for PLA as medical implants include tissue growth, bone grafting, and fracture fixation devices. PLA is commonly used in combination with other polymers and/or proteins, such as polyglycolic acid (PGA), glass fiber, collagen, carbon fiber, and hydroxyapatite (HA) ceramic, to improve its functionality for stabilization of fractures, fixation of tendons and ligaments, and improvement of mechanical properties. On the

1 other hand, degradation of PLA has been reported to lower the pH of cells/tissues due
2 to the accumulation of LA, leading to inflammation of the in-contact tissue [190]. Zhou
3 and Li [191] reported that a composite of PLA-chitosan could alleviate this inflammation
4 issue, as the presence of chitosan neutralizes the PLA-induced pH sites [10, 191]. In
5 addition, PLA composite implants may help treat any organ loss or malfunction by
6 stimulating the growth of the natural cells around the polymer part. The American
7 Society of Plastic Surgeons has recently promoted dermal fillers made of PLA. Such a
8 filler works by stimulating the production of collagen in the human body and is intended
9 for facial improvement [192]. Although extensive documentation is available on the use
10 of PLA composites as medical implants, reports on clinical practice using these implants
11 are scarce, which could be due to possible compatibility issues between the human
12 body and PLA implants. Fast or slow degradation of PLA implants may cause some
13 defense reaction from the human host. Moreover, the toxicity effect may occur for long-
14 term use [190].

15 The use of PLA medical devices to replace metallic medical devices has been
16 researched for more than a decade. PLA has been sought as an alternative to solve
17 issues associated with metal device implants such as possible corrosion and distortion
18 of magnetic resonance images [192]. For example, Zimmer Biomet[®], a musculoskeletal
19 health solutions company, produced Bio-Statak[®], a tissue attachment device made of
20 PLLA that is resorbable and was reported to have comparable pullout strength to metal
21 devices [193]. Researchers from the Fraunhofer Institute in Germany in 2010 developed
22 PLA composite screws that are claimed to closely mimic real bone strength as an
23 alternative to titanium surgical implants [194]. Other companies, such as Arthrex[™],

Phusis, Gunze, Takiron, and Linvatec, have commercialized PLA medical devices for use as interference screws, miniplates, rods, and suture anchors. Most of the aforementioned medical devices are made through a drawing process of PLLA with $M_w > 7.0 \times 10^4$ Da [190]. This process helps to strengthen the property of the devices to be as close as possible to real bones, and is achieved as a result of the orientation and crystallinity of PLA. The drawing process of PLLA also seems to affect the piezoelectricity property of the devices; this property is associated with stimulation of bone growth [190]. PLA seems to be a better option than metal, but in the case of bone grafting, PLA has slower effect on bone resorption. Moreover, some mechanisms of PLA degradation in the human body are not fully understood. In 2005, Mitek Sports Medicine launched a biocomposite implant known as Biocryl[®] Rapide[®], with the claim of superior function over PLA. By 2013, this biocomposite had reportedly been used for knee and shoulder implants in more than 250,000 patients [195]. Additional examples of PLA use in medical applications are provided in the other reviews of this series. Advanced tailoring and molecular modification of PLA are still needed to expand PLA's function as medical implants.

5.2 Fibers and textiles

PLA can be processed into fibers by spinning, as explained in section 3.6. PLA is suitable for fiber applications due to its ability to absorb organic compounds and its wicking properties. Since the polymer is fairly polar, it can absorb moisture, which makes PLA a suitable candidate for wipes. For example, Biovation[®] developed a PLA single-use antimicrobial wipe. Fraunhofer UMSICHT and FKUR developed water filters

1 based on PLA blend fibers (Bio-Flex® S 9533)—this blend is reported to contain
2 adsorbent carbon made of coconut shells [196]. Since PLA has excellent wicking
3 properties, the polymer also can be used for disposable products. For example,
4 Biovation launched disposable antimicrobial blood pressure cuff shields called
5 Bioarmour™—this product is composed of 74 wt% PLA and is intended to protect a
6 patient's skin from being directly in contact with the cuff and provides comfort for
7 patients due to its breathability [197]. Ahlstrom Corporation recently introduced a fine-
8 filament web filter for tea made from PLA fibers—the polymer's wicking ability allows the
9 infusion of the tea flavor into hot water [198].

10 PLA fibers also are of interest to the automotive industry. Approximately 10% of a
11 vehicle compartment is made of plastic. Various companies, including Ford Motor
12 Company, are looking into environmentally friendly polymer options for car interior parts
13 such as carpets, floor mats, and trim parts. Some companies have started producing
14 parts with different bio-products such as PLA, flax, jute, and cotton. A conference on
15 bio-based materials for automotive applications (bio!CAR) was held in Stuttgart,
16 Germany, in September 2015. However, some obstacles must be solved, such as
17 emission of undesirable odors when the polymer is at high temperature, time span of
18 degradation processes, and moisture effects towards materials, before PLA can be fully
19 implemented for such applications [199]. Ford Motor Company performed a study
20 comparing PET and PLA-based seat fabrics to investigate automotive requirement
21 properties such as seam fatigue, flammability, resistance to abrasion and snagging. The
22 study found that PLA met most of the requirements for automotive fabrics and had
23 comparable performance to PET, but failed in the flammability and abrasion tests [200].

1 Other biopolymers, such as polyurethane and soy-based polymers, have been
2 investigated for their use in the automotive industry by Daimler AG, Fiat, and the Toyota
3 Motor Group. These major car producers are primarily concerned with the durability of
4 the biopolymers [201]. Some improvements are needed before PLA can replace fossil-
5 based polymers in the car industry.

6 The use of PLA to replace major synthetic polymers, such as nylon and PET, in
7 the textile industry is increasing. PLA textiles are being used by garment industries (*i.e.*,
8 apparel, homeware). Although PET-cotton blends are a common combination in apparel
9 for established brands like Nike®, Gap®, and Under Armour®, PLA itself is seen as a
10 promising alternative due to its wicking properties and breathability, making PLA a
11 comfortable material for apparel manufacturing. The Hohenstein Research Institute
12 tested the use of PLA and PLA-cotton blends in garments, and found that PLA is
13 suitable for sports apparel due to its thermal insulation and buffering capacity to sweat,
14 among other specifications [202]. PLA had high resiliency when used for making
15 jackets. Also, the ability of PLA to withstand laundry service with multiple washing was
16 tested and was in accordance with the American Association of Textile Chemists and
17 Colorists (AATCC) standards. However, some issues are associated with PLA textiles,
18 such as the pressing and ironing temperatures, which are limited to temperatures lower
19 than those acceptable for PET and cotton [202]. The dyeing and finishing processes for
20 textiles often undergo conditions involving temperature, pH, and time, thus imposing a
21 challenge for PLA since the polymer is susceptible to degradation under the
22 aforementioned conditions [202]. PLA has good retention and crimp properties, so it is
23 suitable for knitted and embroidered textiles. Another application for PLA textile is in

homeware use such as curtains, pillowcases, and rugs [203]. Early in 2015, Kansai University and TeijinTM developed a new wearable piezoelectric device to detect "directional changes and arbitrary displacement"—this device is made of laminated PLLA and PDLA [204]. In summary, there is significant potential for PLA to be used by the fiber and textile industries, but its limitations remain an issue and more development and changes are needed for PLA to compete with existing fossil-based polymers.

5.3 Packaging and serviceware

The use of PLA in packaging and serviceware has largely increased over the last five years. Research is being performed by both academia and industry with collaborative works between the two to strengthen the green-packaging market to meet consumer demands for packaging derived from renewable resources. PLA has numerous challenges for commercial packaging applications due to its limited mechanical and barrier performance. However, PLA package performance has been improved significantly by tailoring polymer processing, blending with other polymers, and adding compounds, such as nucleating agents, antioxidants, and plasticizers, to meet the end needs [205].

For example, oriented and non-oriented PLA can be produced by tailoring PLA processing. Oriented PLA has considerable thermal resistance with good clarity over non-oriented PLA. Although oriented PLA films pose desirable characteristics, their brittleness is still of concern due to the fragility and loud noise produced by the packages. Frito Lay introduced a compostable PLA bag for their SunChips[®] brand in 2010, but this bag underwent major public scrutiny over the loud crinkling sounds during

1 bag handling. The bags were later removed completely from the market [206, 207].
2 Oriented PLA films are also used for bakery packaging and gift cards [205]. Meanwhile,
3 non-oriented PLA sheets are preferred for use as thermoformed clamshells to package
4 fresh products [208] and other products with short shelf life. These clamshells are still
5 being used to pack some Wal-Mart products. Other companies have claimed that the
6 shelf life of the packaged fruits is 10–15% longer in PLA containers [209]. However, the
7 low barrier properties of PLA towards moisture and gases may cause limitations in other
8 applications. Table 3 shows examples of products that have been and/or continue to be
9 packaged in PLA containers.

10 Major European markets showed early interest in the use of commercialized
11 PLA. Danone[®], for example, launched yogurt cups made of PLA for its Germany
12 market, which accounted for 80% of the total volume of their Activia product line [210].
13 Other thermoformed PLA products also are available by various companies (Table 3).
14 Packages produced from non-oriented PLA, however, are limited to non-heat
15 applications. Some other commercial packaging applications for PLA include shrink
16 films and shrink labels. For PLA to meet the requirements for these types of
17 applications, it needs to exhibit shrinkage, which is commonly observed for oriented
18 PLA at temperature above 60 °C with a reported shrinkage ratio of 70% [205]. ConAgra
19 Foods uses recycled PLA shrink film (produced and supplied by EarthFirst[®]) as tamper-
20 evident seals for its three leading table spread brands: Fleischmann's[®], Blue Bonnet[®],
21 and Parkay[®] [211] (Table 3). The use of oriented PLA as shrink labels does have a
22 slight limitation since PLA's shrinkage ratio is low at around 70 °C, which results in
23 whitening of the label due to the crystallization process. Thus, lamination with other

polyester films or blending other polymers with amorphous PLA are used to ameliorate PLA shrinkage properties [205]. Commercial use of PLA shrink labels was reported for soft drink products manufactured by S&B Foods, Nisshin Oilio, and Asahi [205].

PLA is used to produce bottles for water and juices; however, this market is not extensive. Common production for PLA bottles is ISBM, as previously explained. Application for PLA bottles is limited only to non-carbonated beverages due to the insufficient creep behavior of PLA and low barrier towards CO₂ (which results in product with a lack of carbonation). Vitamore[®] carbonated drink in PLA was reported to have shelf life of about 6 months with a moderate loss of CO₂ [212]. Further improvements are needed to tailor the barrier properties of PLA for products with a longer shelf life to expand commercial applications. Some examples of PLA bottled products for the beverage market are listed in Table 3. Despite numerous efforts by manufacturers in introducing PLA-based bottles into the market, further development is needed to obtain PLA bottles with the required commercial properties to compete with the established fossil-based polymers. Nevertheless, Coca Cola[®] has shown interest in bio-based materials, such as high density poly(ethylene) (HDPE) made from sugarcane molasses, for their Odwalla juice beverage line [213]. Tetra Pak, one of the world's leading packaging companies, recently launched a new bio-based carton made of certified paperboard, and bio-based low density poly(ethylene) (LDPE) films with bio-based HDPE caps named Tetra Rex[®]. Valio, a dairy producer in Finland, is currently using these Tetra Pak[®] cartons for Eila lactose-free semi skimmed milk drink for the Finnish market [214].

Production of PLA containers for serviceware applications, such as microwaveable containers and single-use disposable drinking cups, is challenging since PLA is susceptible to heat deformation. For such applications, a higher heat deflection temperature (HDT) is desirable as it allows the molten polymer to mold faster and to retain its dimensional shape once the formed polymer is removed from the mold. The HDT of PLA is reported to be between 55 and 65 °C [1, 215], which is too low for producing thermally stable PLA containers for a non-refrigerated supply chain. Therefore, nucleating agents, such as alkylene bisamide [205], Ecopromote[®]—a biodegradable nucleating agent by Nissan Chemical [216], talc, and PDLA, are often incorporated into the PLA [205]. The presence of a nucleating agent helps to induce faster crystallization of PLA, so an increase in HDT can be achieved. For example, Corbion Purac[®] produces PURALACT[®] lactide serviceware, which is microwaveable and has a comparable impact resistance to acrylonitrile butadiene styrene (ABS); production is achieved by manipulating the stereochemistry of PLA with D-lactide monomers, but no further process details have been disclosed by the company [217]. SelfEco, a company under VistaTek LLC, has produced party serviceware items from PLA and its blends [218]. Teknor Apex has developed a PLA series (Terraloy BP-34001) with improved impact strength and HDT of 135 J.m⁻¹ and 112 °C, respectively, which are higher than those of standard PLA (impact strength = 33 J.m⁻¹; HDT = 55–65 °C). Teknor Apex claimed that this new compound contains 78 wt% PLA and has the ability for rapid processing with shorter cycle times [219]. It is likely that thermal resistant food serviceware made of PLA will become more available in the coming years.

1 Table 3 Selected examples of packaging containers produced from PLA

Trademark/ Commercialized Brand	Year Active	Improved Functions	Applications	Remarks	Ref.
Tenova, Sweden	2003-current	None	Shopping bags	Bags composed of 45 wt% PLA and 55 wt% Ecoflex	[220]
Biota®, U.S.	2004-2006	None	Bottled waters	Advertised as biodegradable bottles No longer on market due to company bankruptcy	[221, 222]
Wal-Mart, U.S.	2005-current	None	Strawberries, Brussel sprouts	Advertised as biodegradable clamshells Among the first company to use commercialized PLA	[208]
Del-Monte, U.S.	2005-current	None	Fresh-cut produce	Advertised as biodegradable clamshells	[223]
SPAR, Austria	2005-current	None	Organic pears, apples, tomatoes	Advertised as biodegradable thermoformed with flexible PLA lid	[209]
Hypermarket chain Auchan, France	2005-current*	None	Fresh salads	Advertised as biodegradable containers	[224]
Newman's Own, U.S.	2005-current*	None	Organic salads	Advertised as biodegradable containers	[225]
Pacific Pre-Cut, U.S.	2005-current*	None	Freshly prepared salads	Advertised as biodegradable containers	[226]
Vitamore®, Ihr Platz (drugstore chain), Germany	2006-current	None	Bottled beauty, energy and memory drinks	Advertised as 100% bio-based bottles	[212]
Huhtamaki, Finland	2006-current	None	Dessert cups	Advertised as biodegradable containers	[227]
Greenware®, Fabri-Kal, U.S.	2008-current	None	Cold drink cups, lids and portion containers	100% biodegradable	[228]
Noble Juice, U.S.	2008-current	None	Organic and non-organic citrus juice bottles	100% biodegradable	[229]
Apple Inc., U.S.	2008-current*	None	iTunes prepaid gift cards	Current status in market unknown	[230]
Sant' Anna, Italy	2008-current	None	Bottled water	100% biodegradable	[231]

				bottles with PE lids	
Fleischmann's®, Blue Bonnet®, Parkay®; ConAgra Foods, U.S.	2009-current	Improved shrinkage performance	Tamper evident seals for tablespreads	Made of recycled PLA Claimed to reduce 20% of facility's energy consumption	[211]
Reddi-Wip®, PAM®; ConAgra Foods, U.S.	2009-current	Improved shrinkage performance	Shrink labels for cream whipped topping and cooking spray	Made of recycled PLA Claimed to reduce 20% of facility's energy consumption	[211]
Shiseido-Urara, China	2009-current	None	Bottled shampoo	Favorable reception in Chinese market as an environmentally friendly option Bottles are 50 wt% PLA and 50 wt% HDPE	[232]
Wal-Mart; Sams-Club, Mexico	2010-current*	None	Small white onion	No longer on the market Advertised as biodegradable clamshells	[233]
Sunchips®, Frito Lay, U.S.	2010-2014	Thermal resistance	Potato chips bags	Bags withdrawn from the market within a year due to loud crinkling noise Original flavor was retained for a while after incident, but is no longer available Bags composed of 94 wt% PLA, 6 wt% adhesive and ink, 0.2 wt% aluminum liner	[206, 207]
Activia®, Danone, Germany	2010/2011-current	None	Yogurt	Improved carbon footprint by 25% 43% less fossil resource usage than original package	[210]
Stonyfield Farm®, U.S.	2010/2011-current	None	Organic yogurt multipack cups	Cups composed of 93 wt% PLA, 4 wt% titanium dioxide and 3 wt% compounded additives 48% reduction of greenhouse gas emissions	[234]
Polenghi LAS, Italy	2010-current	None	Bottled lemon juice	Claimed to be first blown extrusion PLA bottle in EU market	[235, 236]
Ceramis®, Amcor's Swiss	2011-current	High barrier towards O2,	Snacks (pouches)	Silicon oxide coating provides excellent	[237]

		moisture, aroma compounds	Fruits and vegetables (thermoformed) Breads	barrier for PLA	
Track & Field, Brazil	2011-current*	None	Capsules for athletic apparel	Current status in market is unknown	[238]
PURALACT®, Netherlands	2013-current	Thermoformed containers able to tolerate boiling temperature	Single-use hot beverage cups	Conversion to PLA packaging line is feasible by using an existing PS line	[239]
PURALACT®, Netherlands	2013-current	Comparable impact resistance to ABS	Serviceware	Safe food contact application, and the containers are microwavable	[217]

1 * Current (2016) market availability could not be confirmed.

2

3 **5.4 Plasticulture**

4 Plasticulture is the use of plastics for agricultural applications. Plastics are used
5 for applications such as *i)* to protect soils from erosion and plants from weed, insects,
6 and birds via mulch films, *ii)* to function as drip irrigation tubing, and *iii)* to cover tunnels
7 of greenhouses (Figure 14 & Figure 15). The use of plastics for agricultural applications
8 started in the 1950s to improve and increase the growth and production of agricultural
9 products [240]. Conventional non-renewable plastics are the default choice in the
10 plasticulture industry, and poly(ethylene) (PE) is the main polymer in use. However,
11 various issues regarding the use of non-renewable plastics are of increasing concern
12 among agricultural personnel and consumers. Among these issues are cost of waste
13 management, end-of-life options, and consumer demands for more environmentally
14 friendly options. Waste management handling is expensive, due to the additional labor
15 cost for the removal of conventional plastics after use and associated transportation
16 costs. Also, the end-of-life option is not feasible since landfill soil may become
17 contaminated with pesticide residues from the used plastics. Similarly, recycling is not

an option and open burning is illegal in several states in the U.S. [241]. Therefore, biodegradable plastics, such as PLA, poly(hydroxyalkanoates) (PHAs), starch, and poly(butylene adipate-co-terephthalate) (PBAT), are seen as attractive options to help solve these issues [242].

<Figure 14>

<Figure 15>

The implementation of biodegradable plastics in the plasticulture industry is still at the early stage and is mostly done at the research level due to the high per-pound cost of the polymers. The most promising outcome to be expected from the use of biodegradable plastics for plasticulture is that they are able to biodegrade after use.

Although, as discussed above, PLA has considerable potential for various industrial applications, the use of homopolymer PLA in the plasticulture industry has been limited due to its poor mechanical and thermal properties. Mulch films (Figure 15) made with PLA alone are deemed insufficient to protect soils and plants due to brittleness. The relatively high T_g of PLA and less available amorphous region limit the food sources for microorganisms to initiate the biodegradation process at low temperatures [240]. Consequently, PLA is blended with other biodegradable polyesters to produce commercialized PLA-based mulch films [240]. Commercialized PLA-based mulch films are commonly made with plasticizers, and those that incorporate LA derivatives or oligomers demonstrate an accelerated biodegradation process [243, 244]. The accelerated biodegradation of plasticized PLA-based mulch films could be attributed to the introduction of free volume in the PLA polymer matrix, allowing the

diffusion of surrounding water into the polymer, thus promoting hydrolysis and, in turn, increasing the accessibility of microorganisms to their food sources. This described phenomenon is called bulk erosion. Another phenomenon involved in the biodegradation process is known as surface erosion [2]. Details on hydrolysis of PLA-based films in non-medical environments are provided in section 6.

5.5 Environmental remediation

Removal of contaminants from the environment is known as environmental remediation or bioremediation. Remediation is one waste management method available today to treat water and wastewater by employing mostly sorption and denitrification mechanisms. Theoretically, it is believed that the efficiency of these mechanisms relies on Van der Waals interaction and electronic affinity between contaminants and sorption/source media [245]. The sorption/source media may be adsorbents such as activated carbon, zeolite, and polymers. Biodegradable polymers, such as PCL, PBS, poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV), and PLA, have the potential to be used for environmental remediation [246]. These polymers act either by absorbing the contaminants from any contaminated system (sorption mechanism) or by supplying carbon and energy to microorganisms to facilitate the denitrification mechanism.

PLA, among other biodegradable polymers, is being investigated for possible use in environmental remediation due to its availability as a raw material and its relatively lower price. One example of commercialized PLA used for environmental remediation is Hydrogen Release Compound (HRC[®]), produced by Regenesis Bioremediation

Products (San Clemente, CA). This product is manufactured in a liquid and a gel-like form intended for controlled-release of LA for certain durations [247]. However, to a certain extent, PLA characterization and research for environmental applications are limited. The efficiency of biodegradable polymers for environmental applications relies on their T_g . In the case of PLA, its ability to adsorb contaminants would be limited to conditions $>60\text{ }^{\circ}\text{C}$ [246]. In addition, PLA has more resistance to microbial activity than that of other biodegradable polymers like PCL [248]. The resistance of PLA toward microbial activity is mainly due to the high molecular weight of PLA ($\geq 2.0 \times 10^5$ Da). Thus microorganisms need more time to use PLA as their food source; hydrolysis should reduce the M_w to be manageable for the microorganisms to use it. Consequently, lower molecular weight PLA is likely a better candidate for the denitrification mechanism. Studies on PLA with $M_w < 1.0 \times 10^4$ Da showed a significantly greater removal rate of nitrogen than for PLAs of higher molecular weight [246]. Meanwhile, the focus for environmental remediation applications seems to lie with other aforementioned biodegradable polymers (*i.e.*, PCL, PBS, PHBV) due to their effectiveness in adsorbing contaminants, such as chlorophenols, at room temperature [246].

5.6 Other applications

Some other commercialized or potential applications of PLA include paints, cigarette filters, 3D printing, and parts for space exploration [249]. A 3D portable on-board printer was developed by collaborative work of Altran Italia, Thales Alenia Space, and the Italian Institute of Technology for use in space; the printer was produced with

1 approximately 5.5 kg of PLA. PLA characteristics, such as glossiness and multicolor
2 appearance, make PLA one of the main choices for 3D printing. A high accuracy for
3 dimensional parts can be achieved with PLA because it poses less warp behavior than
4 commonly used printing filament materials like ABS [249]. PLA has been used to
5 develop tow fibers for cigarette filters by D.M. Enterprises Pvt. Limited (Hong Kong) to
6 replace cellulose acetate tow, an invention that may help to reduce cigarette litter.
7 Although cellulose acetate is a natural product, its degradation is relatively slow; the
8 addition of acid may improve the degradation rate. However, concentrated acid worked
9 better to accelerate the degradation process of cellulose acetate, thus it is not a safe
10 choice for such applications [250]. Therefore, the use of biodegradable polymers like
11 PLA may alleviate the current degradation issue associated with cigarette filters.

12 Another newly developed application of PLA is as a water-based paint: Fujitsu
13 Laboratories Ltd. developed this product to reduce the level of volatile organic
14 compounds commonly found in solvent-based paints. Isocyanate reactant was used to
15 improve the stability of PLA emulsion and, in turn, the quality for its final application as
16 water-based paint [251]. Additionally, Fujitsu in collaboration with Toray Industries, Inc.
17 in 2005, developed a PLA alloy that had high heat resistance and flame retardant used
18 to mass produce the Fujitsu's FMV-BIBLO notebook models [252]. Similarly, PEGA
19 D&E of PEGATRON Corp. collaborated with the Plastic Industry Development Center
20 (Taichung, Taiwan) to produce an alloy consisting of both PLA and medical recycled PC
21 for use in consumer electronics [253].

1 Many newer applications of PLA surfaced with the help of existing and newly
2 developed technologies. Most of these applications were achieved through a
3 fundamental understanding of the physicochemical, mechanical, stereo-chemical, and
4 morphological properties of PLA.

6 **PLA Degradation**

7 PLA polymeric parts can be exposed to different environments during their
8 lifetime, which may promote their degradation. Degradation leads to irreversible
9 changes of the polymer until it gradually fails due to the loss of various properties. Such
10 loss of properties can occur under different mechanisms, including chemical hydrolysis,
11 microbial, photochemical, thermal, and enzymatic degradation, which mainly occur by
12 main chain scission or side chain scission [2, 254, 255]. Depending on the application,
13 degradation of PLA can be an advantage or a disadvantage. In the case of mulch films
14 or contaminated packages, degradation through different mechanisms is one of the
15 advantages of PLA. In this section, the main mechanisms of PLA degradation in
16 commercial applications are discussed. Biodegradation in medical settings can be found
17 in the other sections of this PLA series.

18 **6.1 Hydrolysis**

19 Hydrolytic degradation takes place when PLA is exposed to moisture: the ester
20 groups of the main chain of the polymer are cleaved, resulting in a decrease of
21 molecular weight and the release of soluble oligomers and monomers. The products of

1 the hydrolysis self-catalyze the reaction [256-258]. Thus, hydrolysis of PLA starts by
2 the diffusion of water molecules into the amorphous regions, which in turn initiates the
3 cleavage of the ester bonds. Then, degradation continues in the boundary layer of the
4 crystalline domains [259, 260]. The following reaction shows the hydrolysis of the ester
5 groups of aliphatic polyesters, as in PLA, in the presence of water:

6 Information regarding PLA hydrolysis in non-medical applications, such as in
7 food packaging, plasticulture, and environmental remediation, is scarce. Only a few
8 studies have been done in different environments and media (other than in medical
9 settings) in which PLA can be in contact with water during its use, leading to hydrolysis
10 reactions.

11 For example, PLA has been used in plasticulture as mulch films (as shown in
12 section 5.4) where PLA can be affected by a number of abiotic factors, such as
13 temperature, pH, soil moisture, and UV radiation, which all play relevant roles in the
14 degradation. During abiotic degradation, the mulch films are fragmented, the tensile
15 strength of the material weakens, and a slight reduction of M_w occurs [240], then PLA is
16 converted into CO_2 , water, and inorganics. Hydrolysis is one of the mechanisms that
17 helps degrade PLA in this environment. Furthermore, in other agriculture applications,
18 for example during controlled release of herbicides for stimulating the plant growth and
19 improving yield, hydrolysis of PLA takes place since the material is exposed to high RH
20 or put in direct contact with water [8, 261, 262].

1 In packaging applications, when PLA is used for fresh produce or beverage
2 containers, it is exposed to humid environments that can trigger hydrolysis reactions.
3 Copinet *et al.* reported that at high RH the rate of hydrolysis increases due to absorption
4 of water molecules into PLA. As a result, a decrease of the M_w was observed, leading to
5 a reduction in T_g from 60 to 19.4 °C when exposed to 100% RH, and a 50% reduction of
6 of the initial percent elongation at break at 30 °C in 15 and 10 weeks when PLA films
7 were exposed to 50 and 100% RH, respectively [263].

8 PLA containers have been developed to be in contact with water, cold-chain
9 dairy, and juices, so the PLA is in contact with different environments at different pH and
10 polarity. The medium pH influences the rate of hydrolysis of PLA-based materials. In
11 strong acidic and basic media, polymer chains are more easily degraded since the
12 hydrolysis reactions are catalyzed by the presence of hydronium and hydroxide ions
13 (Figure 16) [264-267]. For example, if PLA is used for a citrus juice bottle, the PLA will
14 be exposed to an acidic medium (pH <4) making the hydrolysis mechanism proceed via
15 chain-end scission [257, 268].

16 <Figure 16>

17 In PLA containers used for alcoholic products, ethanol will swell the PLA matrix,
18 act as plasticizer, and increase the chain mobility; as a result, the PLA will be subjected
19 to solvent induced crystallization (SIC) [269-271]. To certify polymers for food contact
20 applications, common food simulants are used for migration studies, including 95%
21 ethanol, 50% ethanol, and water for fatty, alcoholic, and aqueous liquid products,
22 respectively [272, 273]. PLA films exposed to alcohol solutions at 40 °C undergo

hydrolysis, in turn causing a large reduction of M_n , especially when PLA films are exposed to 50% ethanol [274] (Figure 17).

<Figure 17>

Temperature also plays a crucial role in the hydrolysis of PLA in non-medical applications. The rate of degradation of PLA increases with temperature, resulting in faster cleavage of the ester bonds [258, 263, 275, 276]. When PLA is immersed in water at 30, 40, and 50 °C, chain scission is accelerated as temperature increases, and an increment of carbonyl index attributed to the formation of carboxyl groups during hydrolysis is also expected [277].

6.2 Thermal degradation

PLA is susceptible to thermal degradation during processing, leading to a decrease in M_w and the rheological and mechanical properties of processed PLA parts. Thermal degradation of PLA can be attributed to the hydrolysis initiated by residuals of water during processing, unzipping depolymerization reaction, random main-chain scission, and intramolecular and intermolecular transesterification (Figure 18) [278]. Therefore, drying PLA resins before processing is highly recommended.

A number of studies have addressed the complex mechanism of the thermal degradation of PLA. Kopinke *et al.* [279, 280] proposed that the dominant pathway of the PLA thermal degradation above 200 °C is intra- and intermolecular ester exchange, *cis*-elimination, radical and concerted nonradical reactions. McNeill and Leiper [281] stated that the mechanism is based upon a hydroxyl end-initiated ester interchange,

1 non-radical process. Aoyagi *et al.* [282] and Abe *et al.* [283] proposed that PLA not only
2 follows one mechanism during pyrolysis but this thermodegradation also involves more
3 than two pathways, such as random scission, unzipping depolymerization, and
4 intermolecular transesterification. Furthermore, changes of activation energies of the
5 thermal degradation process have been reported, with increasing weight loss using
6 isothermal methods going from 103 to 72 kJ.mol⁻¹, 80 to 160 kJ.mol⁻¹ and 170 to 190
7 kJ.mol⁻¹ involving complex kinetic mechanisms [282, 284, 285].

8 <Figure 18>

9 Thermal degradation of PLA is a complex phenomenon leading to the
10 appearance of different compounds such as low molecular weight molecules and linear
11 and cyclic oligomers with different M_w and lactide. Other degradation products have
12 been detected such as CO, CO₂, acetaldehyde, and methyl ketone [280, 281, 285].
13 Kopinke *et al.* [280] found that temperatures above 270 °C lead to degradation of PLA
14 and that the formation of acetaldehyde increases with temperature. However, McNeill
15 and Leiper [281] showed that during degradation temperatures in the range of 230–440
16 °C, acetaldehyde was formed in the highest concentration at 230 °C and then a
17 decreasing effect was observed at 440 °C. The decrease in proportion can be explained
18 by the thermal degradation of acetaldehyde, involving chain reactions to obtain the by-
19 products CH₄ and CO.

20 PLA thermal degradation is influenced by several factors such as initial M_w ,
21 moisture, and residual polymerizing catalysts [287, 288]. Moisture in the resin,
22 temperature, and residence time in the extruder during processing contribute to the

1 decrease in M_n and stress and strain at break due to the dependency of these
2 parameters on M_w [289, 290]. The presence of residual metals is a parameter that also
3 causes drastic thermal degradation of PLA. Kopinke *et al.* [280] showed that PLA in the
4 presence of residual Sn from the polymerization process leads to a selective
5 depolymerization step producing lactide. Cam and Marucci [291] observed that the
6 presence of residual metals assists thermal degradation in PLA, affecting the onset
7 temperature in the order of Fe > Al > Zn > Sn. Furthermore, the presence of stannous
8 octoate catalyst ($\text{Sn}(\text{Oct})_2$) in a proportion of 0.5, 1, and 5 wt%, accelerated the
9 degradation of PLA. The presence of 5 wt% of $\text{Sn}(\text{Oct})_2$, even at the low temperature of
10 160 °C, accelerates PLA degradation [278, 292]. Abe *et al.* [283] found that Zn
11 catalyzes intermolecular transesterification to produce linear PLA oligomers, and
12 selective unzipping depolymerization of cyclic PLA oligomers to produce lactides.

13 Improving the thermal stability of PLA to avoid the degradation of the polymer
14 during processing, via end-protection or using chain extenders, has been studied. End-
15 protection of the hydroxyl group has been assessed due to the mechanism of pyrolysis
16 in PLA by a back-biting reaction, which causes an unzipping depolymerization starting
17 from the hydroxyl ends of the chains [280, 281, 284]. One method is by the acetylation
18 process, which not only achieves end protection, but also is capable of removing
19 residual metals that accelerate degradation of PLA [283, 288, 291, 293]. Fan *et al.* [293]
20 studied the relationship between the effects of the acetylation and metal content by
21 acetic anhydride where the stabilization was due to the elimination of residual Sn. On
22 the other hand, chain extenders, such as tris (nonylphenyl) phosphite (TNPP),
23 polycarbodiimide (PCDI) and Joncryl[®], have been used where the onset temperature of

degradation is increased due to the reduction of active sites on the chain end per mass by the production of longer polymer chains [273, 294, 295].

6.3 Photodegradation

PLA is exposed to sunlight during its lifetime for applications in plasticulture, packaging containers, or films, thereby inducing plastic degradation due to the low wavelength and high-energy UV radiation. Other applications involve the use of UV irradiation for sterilization of biomedical and pharmaceutical products. The carbonyl group presence in the PLA chemical structure absorbs UV radiation at about 280 nm via $n-\pi^*$ electron transition, thus increasing the susceptibility of PLA to photodegradation [296].

Aliphatic polyesters, including PLA, photodegrade under UV and sunlight exposure via the Norrish II mechanism (Figure 19) whereby chain scission of the main chain occurs and the formation of C=C double bonds takes place along with carboxyl end groups and where the reaction is triggered by the electron transition at C=O [297-300]. The main-chain scission of PLA during photodegradation occurs randomly; the photodegradability is higher in the amorphous regions than in crystalline regions, resulting in the reduction of M_w where anhydride groups are formed and decreasing the rate of crystallization [299, 301, 302]. When UV radiation penetrates the polymer, the degradation proceeds via bulk erosion where the light penetrates the polymer without a significant reduction in its intensity regardless of the chemical structure and the crystallinity of the polymer [302].

1 <Figure 19>

2 Other basic mechanisms have been proposed to predict the degradation of PLA
3 products by UV irradiation. Janokar *et al.* [303], studying the effect of wavelength on
4 PLA photodegradation at a range of 232–500 nm, concluded that photodegradation
5 mainly occurs between 200–300 nm and proposed two mechanisms. One mechanism
6 leads to breakage of the main chain C-O by a photolysis reaction (Figure 20 a), and the
7 other leads to the formation of hydroperoxide derivatives and subsequent degradation
8 compounds containing carboxylic acid and diketone end groups by photooxidation
9 (Figure 20 b).

10 <Figure 20>

11 UV irradiation can have different effects in PLA. UV irradiation can cause a
12 decrease in M_w of PLA; UV also causes an increase in M_w distribution, which has an
13 effect on mechanical properties, such as the decrease in stress and strain at break,
14 where PLA becomes brittle over time [302-305]. Furthermore, a faster degradation
15 takes places when exposure time to UV light increases [301].

16 The combination of different factors can affect the degradation of PLA. Copinet *et*
17 *al.* [263] studied the effect of temperature and humidity of PLA exposed to UV irradiation
18 at 315 nm, where the UV light accelerated the reduction of molecular weight, T_g ,
19 percentage of elongation at break, and crystallinity at different temperatures and RH.
20 During this study, from the cleavage of C-C bonds of the main chain, two radicals were
21 supposed to be produced (Figure 21), and two others from cleavage at C-O of the main
22 chain (Figure 22 a), and from cleavage of ester bonds (Figure 22 b).

1 <Figure 21>

2 <Figure 22>

3 Besides UV light, PLA can be exposed to different kinds of radiation such as γ -
4 irradiation when the material undergoes a γ -sterilization process. The effect of γ -
5 radiation has been studied by Balbanalbi *et al.* [306] using electron paramagnetic
6 resonance (ESR) spectroscopy, where the radicals formed during degradation were the
7 result from the scission of the ester bonds and hydrogen abstraction from the methane
8 groups of PLA main chain. Birkinshaw *et al.* [307] examined the effect of γ -radiation on
9 the molded poly-D,L-lactide, where changes in mechanical properties and reduction in
10 M_w were observed, making the sample brittle due to random chain scission of the
11 polymer. γ -radiation occurs mainly in the amorphous region of the polymer [308].

13 7 End-of-life Scenarios for PLA

14 According to the 2015 Global Sustainable Development Report, the increasing
15 global awareness of sustainability is noticeably changing consumer preferences, and
16 producers have to adapt to meet those preferences [309], along with the need of tools
17 that allow the assessment of environmental impacts of materials [310]. Consequently,
18 there is increasing demand for bio-based polymers to replace traditional fossil-based
19 polymers, as the latter are perceived to have higher environmental footprints [3, 5, 311].

20 PLA is likely the most popular bio-based polymer. It is recyclable and
21 biodegradable under industrial composting (IC) conditions through an initial hydrolysis

process [2], and it has been proposed to be used especially in cases where plastics become highly contaminated and are difficult to recover through recycling such as food packaging and agricultural mulch films. While PLA is derived from renewable resources and offers an alternative disposal route (*i.e.*, composting), there are limitations to its implementation due to the lack of suitable infrastructure for sorting, recycling, and/or composting PLA products at their end of life [3].

The European Commission introduced a five-level waste hierarchy in the European Waste Directive 2008/98/EC, which includes: 1) prevention, 2) reuse, 3) recycling, 4) other recovery, and 5) disposal [312]. Likewise, the U.S. Environmental Protection Agency (EPA) has a four-level integrated waste management hierarchy, including: 1) source reduction (including reuse), 2) recycling (including composting), 3) combustion with energy recovery, and 4) disposal through landfill [313, 314]. The four components are important within the integrated waste management system as shown in Figure 23.

<Figure 23>

PLA is a special polymer since it can be treated in all levels of the hierarchy, including composting as an end-of-life scenario [315]. However, according to *U.S. EPA Advancing Sustainable Materials Management: Facts and Figures 2013* [314], about 254,110 thousands of tons of MSW were generated in the U.S. in 2013, from which about 25.5% was recycled, 8.8% was composted, 12.9% was combusted with energy recovery, and 52.8% was discarded in landfills. Packaging and containers comprised the biggest portion (29.8%) of the MSW, from which only about 5.2% of plastic

1 packaging was recovered, mostly PET (24.8%) and HDPE (16%). On the other hand,
2 from the 50 thousand tons of PLA waste that was generated (mostly for plates and
3 cups, packaging, and other non-durable goods), only a negligible amount (less than 5
4 thousand tons, 10%) was recovered through recycling and/or composting [313, 314].

5 **7.1 Source reduction (reuse)**

6 For new applications of PLA to enter the market, it is important to analyze in
7 more detail the preferred end-of-life scenarios [315]. Waste management hierarchy
8 emphasizes source reduction by designing products, especially packaging, to achieve
9 material reduction (lightweighting), longer product life, and reuse [313, 314, 316].

10 Lightweighting of PLA has been of great interest not only for its economic value
11 but also for waste reduction. Nevertheless, with this approach one must consider the
12 possibility of reduced mechanical functionality of the PLA. Efforts made over the years
13 to produce lightweight PLA materials with good physical and mechanical properties
14 include producing reinforced PLA with fibers/fillers, PLA composites, and foamed PLA,
15 to name a few. PLA–sugar-beet composite materials produced by compression-heating
16 techniques have reduced density compared with PLA; however, the mechanical
17 properties of the composite materials were affected negatively with increasing amounts
18 of sugar beet pulp [317]. Peinado *et al.* [318] fabricated PLA reinforced with
19 functionalized sepiolite-aminosilane grafted filler and CFA to produce lightweight PLA
20 with improved mechanical properties. Although the addition of CFA significantly reduced
21 the material density, its mechanical properties were compromised in the absence of the
22 functionalized sepiolite filler. A synergistic effect of the CFA and the functionalized

sepiolite was reported, where the density of the material was significantly reduced with an improved modulus. Additionally, the application of lightweight PLA-cellulose fiber composite was extended to the automotive industry for use as floor-load materials [319]. The composite with 50 wt% fiber fraction demonstrated the highest tensile strength due to the ability of this fiber to form hydrogen bonding networks within PLA matrices. The composites with 50 wt% fiber fraction with fixed nominal density of 0.2, 0.3, and 0.4 g/cm³ met the flexural stress and stiffness for the supportable load floor weight of vehicle specifications [319]. As the market for PLA parts increase, we expect additional research of technologies to lightweight PLA.

In the case of retail packaging, a wide-scale reuse system for materials has restricted potential due to the logistics and cost involved in returning empty containers to suppliers [320]. PLA packaging is not the exception. On a much smaller scale, PLA products and packaging could be reused (whether for its primary purpose or not) by households, assuming the PLA products and packaging maintain the desired properties, functionality, and safety.

7.2 Recycling

Following the hierarchy, the next preferable disposal route of PLA would be recycling, which can be either chemical or mechanical [62, 321, 322]. PLA packaging, such as water bottles or blisters, usually has low contamination, making recycling a viable route to recover the material [62]. However, as previously mentioned, the lack of infrastructure to collect PLA and the logistics required to recover make it challenging to collect and recycle PLA. The economic cost involved in recycling at the post-consumer

level does not usually favor the recovery and recycling of plastics other than HDPE and PET (mostly bottles); these two post-consumer resins have a big market demand since they can be used to form new bottles or other products like fibers, clothes, carpets, and textiles [62, 323].

During chemical recycling, PLA is hydrolyzed at a high temperature to yield LA, which can be readily polymerized to high M_w PLA [62, 321, 322]. The disadvantage of chemical recycling is that it is still complex and expensive [62]. NatureWorks LLC have successfully recycled off-grade IngeoTM by using chemical recycling [324].

Mechanical recycling (MR) would be the easiest and cheapest way to recycle post-consumer PLA, and it involves recovering, sorting, regrounding, and reprocessing (*i.e.*, melt processing) the PLA waste [62]. However, there is a debate on whether PLA can be successfully recycled in the current plastics recycling infrastructure due to the contamination of the recycling stream. According to Cornell [323], for PLA to be mechanically recycled, it must be either completely fungible with existing recycled resins or be available in sufficient quantity to achieve the needed critical mass. On one hand, there are some initiatives to facilitate the recycling of PLA through the existing infrastructure for recovery and sorting. One initiative is to improve the material identification by establishing a new resin identification code (RIC) exclusive to PLA since it currently falls in the category of “7-OTHER” according to the ASTM D7611 – Standard Practice for Coding Plastic Manufactured Articles for Resin Identification; this category is shared with other uncoded materials such as polycarbonate, ethylene vinyl alcohol, to name a few. Other initiatives are focused on the use of technologies like

1 near-infrared or black light illumination to facilitate the sorting of PLA from the waste
2 stream [325]. Thus, if there are sufficient PLA containers entering the waste stream,
3 recycling entrepreneurs may explore means of recovering and recycling PLA in a cost-
4 effective fashion. Various organizations, such as the Bioplastics Recycling Consortium
5 and Greenplastics Inc., were formed to develop solutions for post-consumer bioplastic
6 materials [326, 327]. On the other hand, the National Association for PET Container
7 Resources (NAPCOR) and the Association of Postconsumer Plastic Recyclers (APR)
8 have refuted the idea of mixing biopolymers like PLA into the existing stream of recycled
9 containers, expressing concerns regarding the cost of separation and processing,
10 increased contamination, and reduced quality of the recycled material [323, 328].

11 **7.3 Composting**

12 Biodegradation is considered to be nature's way of recycling [4, 329]. PLA is
13 biodegradable under IC conditions starting with an hydrolysis process, in which ultimate
14 PLA degradation results from the action of naturally occurring microorganisms at a high
15 temperature (58 °C) and 50% RH [329]. Figure 24 shows a typical large-scale
16 composting process in which biodegradable materials decompose, resulting in compost,
17 CO₂, H₂O, and minerals. There are three indispensable factors for polymer
18 biodegradation to take place: substrate (chemical structure and conformation),
19 environment (temperature, oxygen, and moisture) and microorganisms (metabolic
20 pathways and enzymes) [330, 331].

21 <Figure 24>

Biodegradation of polymers (including PLA) usually takes place in two main steps: primary degradation, in which fragmentation of the polymer chain occurs due to hydrolysis or another oxidative reaction, and ultimate biodegradation, in which the microorganisms assimilate the low M_w chains formed (Figure 25) [330-332].

<Figure 25>

Biodegradation can be evaluated by different analytical techniques, either in a direct or an indirect approach [333], but respirometric methods are usually preferred to evaluate biodegradation of polymers in laboratory settings [330]. Respirometric methods directly measure the consumption of oxygen or the evolution of CO_2 [333]. A number of standards have been developed to define the requirements and the methodologies to assess the biodegradability of plastic materials [4]. ASTM D5338 and ISO 14855 are the main standards describing the measurement of an aerobic biodegradation of plastic materials under composting conditions by analysis of evolved CO_2 [334, 335]. Table 4 shows a basic comparison between these two standards.

Table 4 General requirements to test biodegradation under laboratory conditions and comparison between ASTM D5338 and ISO 14855 standards [334, 335], reproduced from Castro-Aguirre, E. [336].

Requirement		ASTM D5338	ISO 14855
Apparatus	Number of bioreactors	At least 12	At least 9
	Volume of bioreactors	2 to 5 L (sufficient headspace)	2 L or higher (sufficient headspace)
	Aeration	Water saturated CO_2 -free	Dry or water saturated CO_2 -free
		Accurate flow rate	At pre-set flow rate
	Sensor	Specific sensors or	Infrared analyzer

		appropriate gas chromatographs	Gas chromatograph
Compost Inoculum	Age	2-4 months old	2-4 months old
	Homogeneity	Sieved on a screen <10 mm Allows addition of structural material	Sieved on a screen of about 0.5 to 1 cm Allows addition of structural material
	Dry solids	Between 50 and 55%	Between 50 and 55%
	Volatile solids	Ash content <70%	No more than 15% of wet or 30% of dry solids
	pH	Between 7 and 8.2	Between 7 and 9
	Production of carbon dioxide	Between 50 and 150 mg of CO ₂ per gram of volatile solids over the first 10 days	Between 50 and 150 mg of CO ₂ per gram of volatile solids over the first 10 days
	C/N ratio	Between 10 and 40	Between 10 and 40
Substrate	Shape	Granules, powder, film, simple shapes	Granules, powder, film, simple shapes
	Surface area	2×2 cm max.	2×2 cm max.
	Positive control	Cellulose (particle size <20 µm)	Cellulose (particle size <20 µm)
	Negative control	Polyethylene	Not required
Other	Temperature	58 ± 2°C	58 ± 2°C
	Water content	About 50%	About 50%
	Ratio of mixture	6:1 sample (dry solids)	6:1 sample (dry solids)
	Frequency of measurement	At least daily	At least twice per day
	Test period	At least 45 days	Not exceeding 6 months
	Incubation	Dark or diffused light	Dark or diffused light
	Oxygen concentration	6% or higher	6% or higher

1

2

3

4

5

The aerobic biodegradation of PLA film (Ingeo™ 2003D) in compost was evaluated by using an in-house-built direct measurement respirometer (DMR) following the methodology described by Selke *et al.* [337], in which bioreactors containing PLA, blank (compost only), and cellulose (positive reference) were tested. Figure 26 a shows

1 that the PLA film produced a significantly higher amount of CO₂ than the blank, meaning
2 that microorganisms were able to use the carbon from the polymer for their metabolic
3 processes. The amount of CO₂ produced by the PLA film is comparable with that for the
4 positive reference in the same time period. Figure 26 b shows that the PLA film
5 mineralized above 70% after two months of composting. PLA also presented a lag time
6 during the first 3 weeks of the test, which is related to the primary degradation where
7 the M_w of the polymer should be reduced to around 9.0×10^3 Da (data not shown) for
8 the microorganisms to start the ultimate degradation or mineralization.

9 <Figure 26>

10 Composting would be the optimal end-of-life option for contaminated PLA.
11 However, there are only few existing composting facilities that accept biodegradable
12 plastic materials since most are concerned that biodegradable plastics are not easily
13 distinguishable from conventional plastics and that quality control is difficult [315].

14 Similar to recycling, there is a big challenge for collecting and sorting PLA waste
15 from other MSW so that the PLA can be sent to the composting facilities. Hence, the
16 benefit provided by PLA of offering an additional disposal route (biodegradation or
17 composting) is only realized if PLA is disposed in an appropriate waste management
18 system that uses their biodegradable features [320]; otherwise, the PLA would
19 accumulate like other plastic materials in the landfill.

20 **7.4 Incineration with energy recovery**

1 The incineration of waste is not only a volume-reduction practice, but it has
2 evolved to waste-to-energy plants in which energy is recovered from waste materials to
3 produce heat or electricity, followed by the disposal of the fly and bottom ashes.
4 Incineration of waste with energy recovery also reduces the dependency of using fossil
5 resources and other fuel sources. Even though air pollution is often the main concern
6 about incineration, the improvements in gas cleaning technology allow the reduction of
7 pollutants released to the atmosphere [338, 339].

8 Thus, some of the energy content of plastics can be recovered by incineration,
9 and reasonable energy efficiency can be achieved through various approaches such as
10 co-fuelling of kilns [320]. Disposing PLA waste via incineration recovers the energy
11 embedded in PLA, representing a CO₂-neutral method of energy production, and it
12 contributes to the conservation of fossil resources [340]. However, energy recovery
13 does not reduce the demand for raw material used in plastic production [320], and it is
14 also important to consider the composition of the emitted combustion gases [340].

15 NatureWorks LLC reported that Ingeo™ resin heat content is about 19.5 MJ.kg⁻¹
16 [341]. This value is in agreement with the calorific values reported by Laußmann *et al.*
17 [340] (Figure 27), who carried out comparative experiments between biopolymers,
18 fossil-based polymers, and fuels. They concluded that biopolymers, including PLA, are
19 suitable for thermal energy recovery since they have calorific values comparable to
20 cellulosic-based materials, and they do not produce additional toxicologically critical
21 substances during combustion [340].

22 <Figure 27>

7.5 Landfill

The less preferable option to dispose PLA is landfilling (LF). According to the U.S. EPA, although disposal of MSW to landfill decreased from 145.3 million tons in 1990 to 134.3 million tons in 2013, landfill remains the most economic and attractive method for handling MSW [313, 314]. LF has some environmental impacts primarily due to gas and leachate formation, including health hazards, fires and explosions, vegetation damage, unpleasant odors, landfill settlement, ground water pollution, air pollution, and global warming [342]. The drawback of disposing plastics in landfills lies in the fact that most plastic materials do not degrade in a practical period of time and end up accumulating [343]. Landfills usually do not provide the appropriate environment to promote degradation, and their conditions vary considerably by geography [344]. On the other hand, PLA biodegradation is highly dependent on temperature and moisture, since these two factors promote hydrolysis of the polymer chains, and in turn accelerate biodegradation. At mesophilic temperatures little or no degradation of PLA is observed [344].

According to NatureWorks LLC, their resin Ingeo™ is stable in landfill conditions with no statistically significant quantity of methane released. Studies performed under accelerated landfill conditions at different temperatures and moisture levels found that the amorphous PLA did generate a small amount of methane in the test at 35 °C, but no methane was generated in the test at ambient temperature. Semicrystalline PLA did not generate a significant amount of methane in any of the tests. The company also pointed

out that it is likely that any degradation of PLA in a landfill would require a chemical hydrolysis step prior to any biodegradation [344].

8 Environmental Footprint of PLA

The increasing global awareness of sustainability is changing the perceptions and preferences of consumers; therefore, environmental assessment tools are being used to evaluate the EFP of systems and products [310]. An EFP is a quantitative measurement describing how human activities can inflict different impacts on global sustainability considering the environmental, social, and economic indicators [345].

Life cycle assessment (LCA) can be used to evaluate the EFP of PLA. LCA is a method to assess the environmental performance of products and/or potential impacts of a system considering raw materials acquisition, production, use, and disposal [346, 347]. LCA is conventionally thought of as a “cradle-to-grave” approach; however, in the last few years a “cradle-to-cradle” approach has been introduced [345].

<Figure 28>

In other words, LCA systematically evaluates each of the life stages of a product or product system, in which environmental inputs (resources) and environmental outputs (emission and waste) are produced and the impacts to human health and environment are calculated. LCA results are interpreted in relation to the objectives of the study [346, 347]. LCA studies are mostly conducted under the framework of the international standards ISO 14040 and 14044 [348, 349], which provide requirements,

1 recommendations, and guidelines about methods and techniques for quantifying inputs
2 and outputs, and impact characterization [346, 347].

3 The EFP of PLA resins and/or PLA products can be evaluated using midpoint
4 impact categories [350]. Additionally, measuring key indicators such as greenhouse
5 gases (GHG) emissions and non-renewable energy use, and comparing the data
6 between PLA and traditional polymers (e.g., PET and PS) can give insights about PLA
7 environmental performance.

8 In 2003, NatureWorks LLC published the first cradle-to-gate life cycle inventory
9 data (ecoprofile) for its PLA (Ingeo™) based on the 140,000-t/y plant design, in which
10 they provided some information regarding the production technology [351]. In 2007, the
11 company provided an updated ecoprofile based on the actual data collected from its
12 production facilities, and also provided a more accurate description of the manufacturing
13 system and LCA calculation procedure [352]. In 2010, NatureWorks LLC published an
14 updated ecoprofile based on the production technology improvements and also
15 benchmarked the results for energy requirements and GHG emissions with data for a
16 selection of fossil-based polymers [353]. Recently (2015), the company published an
17 updated PLA ecoprofile providing a detailed description of the production of its resin
18 (now 150,000-t/y plant) and focused on the corn feedstock used to produce Ingeo™ and
19 on the PLA intrinsic zero material carbon footprint, as explained below [5, 345].

20 One of the advantages of using bio-based biodegradable polymers like PLA is to
21 help replenish the carbon cycle (Figure 29) [329]. When using renewable carbon
22 feedstock to manufacture plastic materials instead of fossil carbon feedstock, there is an

intrinsic zero material carbon footprint value proposition; in other words, the carbon footprint reduction arises from the material itself and not necessarily from the process of converting the feedstock to products (process carbon footprint) [354].

<Figure 29>

Fossil resources could be considered renewable, but it takes more than a million years for biomass to be converted into fossil fuels. Since the rate of consumption is much greater than the rate of replenishment, mass imbalance occurs in the carbon cycle. In contrast, biodegradable polymers made from bio-based materials, such as corn and corn starch, can be produced and converted into biomass in similar time frames [329]. Figure 30 shows the global warming potential (GWP), primary energy from nonrenewable resources (PENNR), such as oil, gas, coal, and uranium, and water uptake for 1 kg of Ingeo™ PLA resin [5]. One of the main value propositions for using PLA to replace other fossil-based polymers, is the lower GWP due to carbon sequestration during the corn-growing stage.

<Figure 30>

Several authors have done LCAs regarding the performance of PLA in comparison with other materials like PET and PS for different applications, in which PLA could be a good substitute for clamshell containers, trays, and water bottles [311, 355-358]. Table 5 and Figure 31 show general information about the EFP of PLA in comparison with other polymers.

Table 5 Environmental footprint of 1 kg of selected commercial polymer resins as available in Ecoinvent 3.2 and reported using Simapro 8.0.5 with ReCiPe (E) Midpoint Indicator considering the World as the geographical region.

Impact category	PLA	Nylon 6-6	PET	HDPE	LLDPE	LDPE	PP	PS
Climate change, kg CO ₂ eq	2.7907	7.0460	2.4813	1.6815	1.6055	1.8154	1.7666	2.9690
Ozone depletion, kg CFC ⁻¹¹ eq	2.18E-07	2.61E-09	1.48E-07	1.18E-09	4.75E-08	1.13E-09	8.85E-10	5.46E-09
Terrestrial acidification, kg SO ₂ eq	0.0218	0.0295	0.0121	0.0064	0.0057	0.0078	0.0062	0.0112
Freshwater eutrophication, kg P eq	0.0004	0.0003	0.0001	1.23E-06	9.03E-07	1.42E-06	4.33E-05	3.56E-06
Marine eutrophication, kg N eq	0.0065	0.0091	0.0002	0.0001	0.0001	0.0002	0.0002	0.0003
Human toxicity, kg 1,4-DB eq	9.4123	1.7760	4.6504	0.4946	0.2917	0.6967	0.4113	0.6617
Photochemical oxidant formation, kg NMVOC	0.0115	0.0205	0.0087	0.0086	0.0065	0.0093	0.0076	0.0096
Particulate matter formation, kg PM10 eq	0.0063	0.0082	0.0040	0.0020	0.0021	0.0023	0.0019	0.0033
Terrestrial ecotoxicity, kg 1,4-DB eq	0.0089	0.0002	0.0018	1.51E-05	1.13E-05	2.04E-05	1.21E-05	0.0003
Freshwater ecotoxicity, kg 1,4-DB eq	0.0090	0.0037	0.0021	0.0004	0.0002	0.0005	0.0003	0.0009
Marine ecotoxicity, kg 1,4-DB eq	3.5355	2.5132	2.9761	0.2391	0.1561	0.3246	0.1915	0.9059
Ionizing radiation, kBq U235 eq	0.1398	0.0006	0.0785	0.0002	0.0002	0.0003	0.0002	0.0004
Agricultural land occupation, m ² a	1.1321	0.0009	0.1035	0.0004	0.0003	0.0003	0.0003	0.0006
Urban land occupation, m ² a	0.0674	0.0006	0.0147	0.0002	0.0001	0.0002	0.0002	0.0004
Natural land transformation, m ²	0.0004	-2.04E-06	0.0004	-3.77E-07	-4.39E-08	-7.27E-07	-3.98E-07	-1.25E-06
Water depletion, m ³	0.2726	0.2262	0.0714	0.0136	0.0443	0.0176	0.0156	0.0524
Metal depletion, kg Fe eq	0.1538	0.0046	0.1646	0.0015	0.0019	0.0029	0.0015	0.0108
Fossil depletion, kg oil eq	0.8246	2.6814	1.5455	1.5908	1.5628	1.5684	1.5716	1.8711
Non-renewable energy, MJ primary	41.739	135.86	73.182	76.398	74.090	78.223	74.636	87.542

1 <Figure 31>

2 Such a comparison is effective only if: a) polymer weights in the studied
3 applications are quite similar; b) contributions to impact categories are dominated by the
4 polymer-pellet production; c) energy requirements for converting the polymer into
5 product are relatively small or relatively similar; d) use phase is similar; e) the same
6 recycling or end-of-life routes are employed; f) the same level of detail in the life cycle
7 inventory data-collection process was used; g) the same LCA methodology was used;
8 h) the same database for upstream inventory data was used; and i) the same life cycle
9 impact assessment methodology, indicators, and characterization factors (+version)
10 were used [5]. Given the above, the climate change of IngeoTM and PLA have large
11 differences since carbon sequestration has not been accounted for in PLA. If this factor
12 is taken into consideration, a global warming potential of PLA would be 0.9 kg CO₂ eq
13 per kg of resin vs 0.62 kg CO₂ eq per kg of resin for IngeoTM. Thus a large benefit is
14 obtained using the new reported data for IngeoTM [5]. In the case of non-renewable
15 energy, similar values are reported by Vink and Davies and the current data are
16 available in Ecoinvent 3.2. In the case of water depletion, the new values reported by
17 Vink and Davies make sure to properly account for water uptake from river and ground
18 for the Blair manufacturing plant, excluding the water for hydropower installations and
19 rainwater. So, a much lower water EFP is reported for IngeoTM, provided that water
20 consumption is similar to that for polyolefins.

21 A large controversy exists regarding the use of the arable food land for plastic
22 materials [359-361]. Vink and Davies reported, based on Carus [362], that 0.00046% of

1 the 5 billion hectares of agricultural land available will be required to supply the corn
2 needed for the 150,000 t/y Ingeo™ production in Blair, and if we imagine a scenario
3 where the 300 million tons of plastics annually produced in the world were to be
4 replaced by bio-based polymers with the same land use per kg of PLA, 0.9% of the 5
5 billion hectares of agricultural land available will be required [5, 362, 363].

6 An LCA study has been done recently regarding the end-of-life options for PLA
7 [315]. In their study, Rossi *et al.* performed an LCA of the end-of-life options for
8 biodegradable packaging based on the waste hierarchy mentioned in section 7. Figure
9 32 shows the system boundary, which covers the primary material production and end-
10 of-life treatment processes such as MR, IC, anaerobic digestion (AD), direct fuel
11 substitution in industrial facility (DFS), incineration with heat recovery in MSW
12 incinerator (MSWI), and LF. Details of the life cycle inventory for each scenario can be
13 found elsewhere [315].

14 <Figure 32>

15 Rossi *et al.* [315] used IMPACT 2002+ LCIA method to evaluate the
16 environmental impacts for the different end-of-life scenarios complemented by water
17 withdrawal and turbinated water indicators. Global warming impacts for PLA dynamically
18 assessed over a 100-year time horizon are presented in Figure 33, in which IC has the
19 highest net impact (measured in kg of CO₂ eq. per kilogram of dry PLA packaging
20 without food contamination after deduction of the treatment credits) and MR has the
21 lowest net impact.

22 <Figure 33>

Likewise, Figure 34 shows the non-weighted scores of the PLA production and end-of-life scenarios for each midpoint category, in which for most impact categories MR was the least-burdening option. On the other hand, IC and LF were the least favorable options for most impact categories.

<Figure 34>

However, the authors emphasize that those conclusions are only valid under the stated hypotheses since other factors may lead to different conclusions. Additional studies are needed to ensure that this preliminary finding can be translated to other boundary conditions and can be applied to other regions.

9 Final Remarks

The range of PLA applications for consumer durable and non-durable goods has increased significantly since industrial methodologies, such as polycondensation and ROP, allowed the production of high M_w PLA to reach the market. At present, the main producer of the commercially available high M_w PLA derived from corn is NatureWorks LLC. Additional producers (e.g., Corbion[®]) are expected to reach the market with PLA derived from plant-based materials and/or biomass waste, which should increase its availability and further commercial applications.

Additional research has been focused on understanding and enhancing the physical and mechanical properties of PLA by, for example, deriving commercial PLA from *rac*-lactide. Extensive work has been conducted on blending PLA with

1 biodegradable and non-biodegradable polymers and on using fillers at the micro and
2 nano scales to create blends and composites with optimal properties, lower cost, and
3 less environmental footprint. All these new variations of PLA-based materials target
4 enhanced performance of PLA while sometimes at the expense of losing the
5 biodegradability of the polymer matrix and reducing its industrial commercial recovery.
6 Thus, new materials should be produced while keeping in mind that they need to be
7 recovered by the more preferred routes of the waste management hierarchy (*i.e.*,
8 source reduction, recycling, composting, incineration with energy recovery, and landfill).

9 The methods used for PLA mass production are well-established polymer-
10 manufacturing techniques (*i.e.*, extrusion, injection molding, blow molding,
11 thermoforming, foaming, and spinning). Therefore, PLA has found extended
12 applications such as fibers, textiles, plasticulture, serviceware, and packaging
13 containers via established processing technologies. However, use of different PLA
14 structures may complicate the performance and/or use of these methods. Additional
15 research may be needed in the production of the new *rac*-lactide derived PLA.

16 One of the main value propositions for PLA is its intrinsic degradation, which can
17 be triggered when PLA is exposed to different environments. Thus, degradation of PLA
18 can be seen as an advantage or disadvantage depending on the application. Extensive
19 research has been conducted on the degradation of PLA in human, processing, and
20 composting environments. However, additional research is needed to assess the
21 degradation of PLA and its modification when in contact with different solvents and
22 simulants.

1 Furthermore, the increasing awareness of sustainability is highly influencing
2 consumer preferences towards bio-based polymers, and PLA has the potential to
3 become one of the major commercialized polymers. PLA can be derived from
4 renewable resources, such as regular crops, plant-based materials, and biomass waste,
5 and it could be treated in all levels of the waste management hierarchy. In this regard,
6 however, there are still limitations due to the lack of suitable infrastructure for sorting,
7 recycling, and/or composting PLA products at their end of life. So, efforts should be
8 centered on working with industries, commodity groups, industry associations, and
9 government groups to improve the recovery rate of PLA.

10 Finally, life cycle assessment has been used to evaluate the environmental
11 footprint of PLA, providing useful information about the environmental impacts that PLA
12 may have during raw material acquisition, production, use, and disposal. Robust data
13 exists about the PLA resin production from one producer, NatureWorks LLC. However,
14 sufficient information is missing regarding the use and end-of-life scenarios of PLA
15 parts.

16 In conclusion, PLA has transcended from a minor bio-based polymer player in
17 the market of commercial fossil-based polymers to be considered as part of a new
18 solution for an increasingly recognized new bio-based economy. Present and future
19 efforts in developing PLA for an array of applications should secure PLA's status as one
20 of the major new bio-based polymers.

21

10 Acknowledgments

Authors, C-A, E. and I-F, F., thank the Mexican National Council for Science and Technology (CONACYT), the Mexican Secretariat of Public Education (SEP) and the Government of Mexico for providing financial support through a Ph.D. fellowship. A, R. would like to acknowledge the support of the USDA National Institute of Food and Agriculture and Michigan AgBioResearch, Hatch project R. Auras.

11 References

- [1] L.-T. Lim, R. Auras, M. Rubino, Processing technologies for poly (lactic acid), *Prog. Polym. Sci.* 33 (2008) 820-852.
- [2] R. Auras, B. Harte, S. Selke, An overview of polylactides as packaging materials, *Macromolecular Bioscience* 4 (2004) 835-864.
- [3] J. Ren, *Biodegradable poly (lactic acid): synthesis, modification, processing and applications*, Springer Science & Business Media, 2011.
- [4] E. Rudnik, *Compostable polymer materials*, Elsevier, 2010.
- [5] E.T. Vink, S. Davies, Life Cycle Inventory and Impact Assessment Data for 2014 Ingeo™ Polylactide Production, *Industrial Biotechnology* 11 (2015) 167-180.
- [6] A.S. Mirabal, L. Scholz, M. Carus, Market study on bio-based polymers in the world—capacities, production and applications: status quo and trends towards 2020, Nova-Institute, GmbH (2013).
- [7] Web of Science. Available:
http://apps.webofknowledge.com.proxy1.cl.msu.edu/WOS_GeneralSearch_input.do?product=WOS&search_mode=GeneralSearch&SID=4A6KOlgZ3TGlifH8Fk9&preferencesSaved=. Access date December 7th, 2015.
- [8] K.M. Nampoothiri, N.R. Nair, R.P. John, An overview of the recent developments in polylactide (PLA) research, *Bioresour. Technol.* 101 (2010) 8493-8501.
- [9] A.J. Lasprilla, G.A. Martinez, B.H. Lunelli, A.L. Jardini, R. Maciel Filho, Poly-lactic acid synthesis for application in biomedical devices—A review, *Biotechnol. Adv.* 30 (2012) 321-328.
- [10] R.P. Pawar, S.U. Tekale, S.U. Shisodia, J.T. Totre, A.J. Domb, Biomedical Applications of Poly (Lactic Acid), *Recent. Pat. Regen. Med.* 4 (2014) 40-51.

- 1 [11] M. Vert, Aliphatic polyesters: great degradable polymers that cannot do everything,
2 Biomacromolecules 6 (2005) 538-546.
- 3 [12] M. Vert, G. Schwarch, J. Coudane, Present and future of PLA polymers, J.
4 Macromol. Sci., Pure Appl. Chem. 32 (1995) 787-796.
- 5 [13] R. Auras, L.T. Lim, S. Selke, H. Tsuji, Poly(lactic acid). Synthesis, Structures,
6 Properties, Processing, and Applications, John Wiley & Sons, Inc., New Jersey, 2010.
- 7 [14] H.R. Kricheldorf, I. Kreiser-Saunders, C. Jürgens, D. Wolter, Polylactides-synthesis,
8 characterization and medical application, Macromol. Symp. 103 (1996) 85-102.
- 9 [15] R. Datta, M. Henry, Lactic acid: recent advances in products, processes and
10 technologies—a review, J. Chem. Technol. Biotechnol. 81 (2006) 1119-1129.
- 11 [16] G. Kharas, F. Sanchez-Riera, D. Severson, Polymers of lactic acid, in: D.P. Mobley
12 (Ed.), Plastics from microbes: microbial synthesis of polymers and polymer precursors,
13 Hanser Publishers, Munich, 1994, pp. 93-137.
- 14 [17] M.H. Hartmann, High molecular weight polylactic acid polymers, in: D.L. Kaplan
15 (Ed.), Biopolymers from renewable resources, Springer, Heidelberg/Berling, 1998, pp.
16 367-411.
- 17 [18] W. Groot, J.v. Krieken, O. Sliekersl, S. de Vos, Production and purification of lactic
18 acid and lactide, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.), Poly(lactic acid).
19 Synthesis, Structures, Properties, Processing, and Applications, John Wiley & Sons,
20 Inc., New Jersey, 2010, pp. 3-16.
- 21 [19] Corbion. Available: <http://www.corbion.com/about-corbion/innovation>. Access date
22 December 14th, 2015,
- 23 [20] S.-H. Hyon, K. Jamshidi, Y. Ikada, Synthesis of polylactides with different molecular
24 weights, Biomaterials 18 (1997) 1503-1508.

- 1 [21] Y. Zhao, Z. Wang, J. Wang, H. Mai, B. Yan, F. Yang, Direct synthesis of poly (D,
2 L-lactic acid) by melt polycondensation and its application in drug delivery, J. Appl.
3 Polym. Sci. 91 (2004) 2143-2150.
- 4 [22] M. Ajioka, K. Enomoto, K. Suzuki, A. Yamaguchi, The basic properties of poly
5 (lactic acid) produced by the direct condensation polymerization of lactic acid, J.
6 Environ. Polym. Degr. 3 (1995) 225-234.
- 7 [23] P. Gruber, M. O'Brien, Polylactides "Natureworks® PLA", Biopolymers Online
8 (2005).
- 9 [24] A.C. Albertsson, I.K. Varma, Recent developments in ring opening polymerization
10 of lactones for biomedical applications, Biomacromolecules 4 (2003) 1466-1486.
- 11 [25] R.E. Drumright, P.R. Gruber, D.E. Henton, Polylactic acid technology, Adv. Mater.
12 12 (2000) 1841-1846.
- 13 [26] S. Jacobsen, H.-G. Fritz, P. Degée, P. Dubois, R. Jérôme, New developments on
14 the ring opening polymerisation of polylactide, Ind. Crop. Prod. 11 (2000) 265-275.
- 15 [27] S. Inkinen, M. Hakkarainen, A.-C. Albertsson, A. Södergård, From lactic acid to
16 poly (lactic acid)(PLA): characterization and analysis of PLA and its precursors,
17 Biomacromolecules 12 (2011) 523-532.
- 18 [28] NatureWorks, NatureWorks Introduces Its Next Generation Polymer Grade Lactide,
19 in: Ingeo™ M700, the meso-lactide stereoisomer delivers higher performance than
20 prior alternatives in a host of industrial applications, NatureWorks, Minnetonka, MN,
21 2013.
- 22 [29] R.D. Benson, E.S. Sumner, J.D. Schroeder, Methods for Producing Lactide with
23 Recycle of Meso-Lactide, in, NatureWorks LLC, 2010.
- 24 [30] C.B. Penu, B., Production of meso-lactide, d-lactide and l-lactic by back biting of
25 polylactide, in, Futerro S.A., 2014.

- 1 [31] P. Hormnirun, E.L. Marshall, V.C. Gibson, R.I. Pugh, A.J. White, Study of ligand
2 substituent effects on the rate and stereoselectivity of lactide polymerization using
3 aluminum salen-type initiators, *Proc. Natl. Acad. Sci. U. S. A.* 103 (2006) 15343-15348.
- 4 [32] T.M. Ovitt, G.W. Coates, Stereochemistry of lactide polymerization with chiral
5 catalysts: new opportunities for stereocontrol using polymer exchange mechanisms, *J.*
6 *Am. Chem. Soc.* 124 (2002) 1316-1326.
- 7 [33] K. Masutani, Y. Kimura, PLA Synthesis. From the Monomer to the Polymer, in: A.
8 Jimenez, M. Peltzer, R. Ruseckaite (Eds.), *Poly(lactic acid) Science and Technology:*
9 *Processing, Properties, Additives and Applications*, The Royal Society of Chemistry,
10 2014, pp. 3-31.
- 11 [34] Y. Yang, H. Wang, H. Ma, Stereoselective Polymerization of rac-Lactide Catalyzed
12 by Zinc Complexes with Tetradentate Aminophenolate Ligands in Different Coordination
13 Patterns: Kinetics and Mechanism, *Inorg. Chem.* 54 (2015) 5839–5854.
- 14 [35] M. Dusselier, P. Van Wouwe, A. Dewaele, P.A. Jacobs, B.F. Sels, Shape-selective
15 zeolite catalysis for bioplastics production, *Science* 349 (2015) 78-80.
- 16 [36] D. Alhashmialameer, N. Ikpo, J. Collins, L.N. Dawe, K. Hattenhauer, F.M. Kerton,
17 Ring-opening polymerization of rac-lactide mediated by tetrametallic lithium and sodium
18 diamino-bis (phenolate) complexes, *Dalton Trans.* 44 (2015) 20216-20231.
- 19 [37] T. Hasegawa, N. Nomura, T. Moriya, H. Nishikawa, S. Yamaguchi, H. Kishida,
20 Synthesis of Racemic Lactide Using Glycerol By-product from Biodiesel Fuel Production
21 Process as Feedstock, *Energy Procedia* 56 (2014) 195-200.
- 22 [38] J.-B. Zhu, E.Y.-X. Chen, From meso-Lactide to Isotactic Polylactide: Epimerization
23 by B/N Lewis Pairs and Kinetic Resolution by Organic Catalysts, *J. Am. Chem. Soc.* 137
24 (2015) 12506-12509.

- 1 [39] M. Jamshidian, E.A. Tehrany, M. Imran, M. Jacquot, S. Desobry, Poly-Lactic Acid:
2 production, applications, nanocomposites, and release studies, *Compr. Rev. Food Sci.*
3 *Food Saf.* 9 (2010) 552-571.
- 4 [40] L.-T. Lim, K. Cink, Vanyo, Processing of Poly(lactic acid), in: R. Auras, L.T. Lim, S.
5 Selke, H. Tsuji (Eds.), *Poly(lactic acid). Synthesis, Structures, Properties, Processing,*
6 *and Applications*, John Wiley & Sons, Inc., New Jersey, 2010, pp. 191-215.
- 7 [41] NatureWorks. Crystallizing and Drying Ingeo™ Biopolymer. Available:
8 [http://www.natureworkslc.com/~media/Technical_Resources/Processing_Guides/Proc](http://www.natureworkslc.com/~media/Technical_Resources/Processing_Guides/ProcessingGuide_Crystallizing-and-Drying_pdf.pdf)
9 [essingGuide_Crystallizing-and-Drying_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Processing_Guides/ProcessingGuide_Crystallizing-and-Drying_pdf.pdf). Access date December 9th, 2015.
- 10 [42] F.-D. Kopinke, M. Remmler, K. Mackenzie, M. Möder, O. Wachsen, Thermal
11 decomposition of biodegradable polyesters—II. Poly (lactic acid), *Polym. Degrad. Stab.*
12 53 (1996) 329-342.
- 13 [43] NatureWorks. Ingeo™ Biopolymer 2500HP Technical Data Sheet. Available:
14 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_2500HP_extrusion_pdf.pdf?la=en)
15 [TechnicalDataSheet_2500HP_extrusion_pdf.pdf?la=en](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_2500HP_extrusion_pdf.pdf?la=en). Access date December 9th,
16 2015.
- 17 [44] NatureWorks. Ingeo™ Biopolymer 3001D Technical Data Sheet. Available:
18 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_3001D_injection-molding_pdf.pdf)
19 [TechnicalDataSheet_3001D_injection-molding_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_3001D_injection-molding_pdf.pdf). Access date December 9th,
20 2015.
- 21 [45] NatureWorks. Ingeo™ Biopolymer 4032D Technical Data Sheet. Available:
22 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_4032D_films_pdf.pdf)
23 [TechnicalDataSheet_4032D_films_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_4032D_films_pdf.pdf). Access date December 9th, 2015.
- 24 [46] NatureWorks. Ingeo™ Biopolymer 6060D Technical Data Sheet. Available:
25 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_6060D_fiber-melt-spinning_pdf.pdf)
26 [TechnicalDataSheet_6060D_fiber-melt-spinning_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_6060D_fiber-melt-spinning_pdf.pdf). Access date December 9th,
27 2015.

- 1 [47] NatureWorks. Ingeo™ Biopolymer 7001D Technical Data Sheet. Available:
2 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/
3 TechnicalDataSheet_7001D_bottles_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_7001D_bottles_pdf.pdf). Access date December 9th, 2015.
- 4 [48] NatureWorks. Ingeo™ Biopolymer 8052D Technical Data Sheet. Available:
5 [http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/
6 TechnicalDataSheet_8052D_foam_pdf.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Technical_Data_Sheets/TechnicalDataSheet_8052D_foam_pdf.pdf). Access date December 9th, 2015.
- 7 [49] R. Auras, Poly (lactic acid), in: K. Yam (Ed.) Encyclopedia Of Polymer Science and
8 Technology, John Wiley & Sons, Inc., New Jersey, 2010, pp. 967-983.
- 9 [50] K.D. Van, P. Krevelen, Properties of polymers: Their estimation and correlation with
10 chemical structure, third ed., Elsevier, Amsterdam, 1997.
- 11 [51] D. Witzke, Introduction to properties, engineering, and prospects of polylactide
12 polymers, in, Thesis, Michigan State Univ, Michigan, 1997.
- 13 [52] R.A. Auras, B. Harte, S. Selke, R. Hernandez, Mechanical, physical, and barrier
14 properties of poly (lactide) films, J. Plast. Film Sheet. 19 (2003) 123-135.
- 15 [53] G. Kale, R. Auras, S.P. Singh, Comparison of the degradability of poly (lactide)
16 packages in composting and ambient exposure conditions, Packag. Technol. Sci. 20
17 (2007) 49-70.
- 18 [54] R. Auras, B. Harte, S. Selke, Effect of water on the oxygen barrier properties of poly
19 (ethylene terephthalate) and polylactide films, J. Appl. Polym. Sci. 92 (2004) 1790-1803.
- 20 [55] R. Bhardwaj, A.K. Mohanty, Advances in the properties of polylactides based
21 materials: a review, J. Biobased Mater. Bio. 1 (2007) 191-209.
- 22 [56] J.R. Dorgan, Rheology of Poly(lactic acid), in: R. Auras, L.T. Lim, S. Selke, H. Tsuji
23 (Eds.), Poly(lactic acid). Synthesis, Structures, Properties, Processing, and
24 Applications, John Wiley & Sons, Inc., New Jersey, 2010, pp. 125-139.

- 1 [57] H.J. Lehermeier, J.R. Dorgan, J.D. Way, Gas permeation properties of poly (lactic
2 acid), J. Membr. Sci. 190 (2001) 243-251.
- 3 [58] R.A. Auras, Solubility of gases and vapors in polylactide polymers, in: T.M. Letcher
4 (Ed.), Thermodynamics, Solubility and Environmental Issues, Elsevier, Amsterdam,
5 2007, pp. 343-368.
- 6 [59] R. Auras, B. Harte, S. Selke, Sorption of ethyl acetate and d-limonene in poly
7 (lactide) polymers, J. Sci. Food Agric. 86 (2006) 648-656.
- 8 [60] G. Colomines, S. Domenek, V. Ducruet, A. Guinault, Influences of the
9 crystallisation rate on thermal and barrier properties of polylactide acid (PLA) food
10 packaging films, Int. J. Mater. Form. 1 (2008) 607-610.
- 11 [61] R. Auras, S.P. Singh, J. Singh, Performance evaluation of PLA against existing
12 PET and PS containers, J. Test. Eval. 34 (2006) 530.
- 13 [62] C. Chariyachotilert, S.E. Selke, R.A. Auras, S. Joshi, Assessment of the properties
14 of poly (L-lactic Acid) sheets produced with differing amounts of post-consumer recycled
15 poly (L-lactic Acid), J. Plast. Film Sheet. 28 (2012) 314-335.
- 16 [63] S. Gottermann, S. Weinmann, C. Bonten, Foams made from modified standard
17 PLA, in: Bioplastics, Polymedia Publisher GmbH, Germany, 2015, pp. 38-40.
- 18 [64] L.M. Matuana, Foaming, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.), Poly(lactic
19 acid). Synthesis, Structures, Properties, Processing, and Applications, John Wiley &
20 Sons, Inc., New Jersey, 2010, pp. 273-291.
- 21 [65] O. Avinc, A. Khoddami, Overview of poly (lactic acid)(PLA) fibre, Fibre Chem. 42
22 (2010) 68-78.
- 23 [66] M. Mathur, M.A. Hira, Specialty Fibres-IV: Poly Lactic Acid Fibres, Man-Made
24 Textiles in India 51 (2008) 232-237.

- 1 [67] A.K. Agrawal, Spinning of Poly(lactic acid) Fibers, in: R. Auras, L.T. Lim, S. Selke,
2 H. Tsuji (Eds.), Poly(lactic acid). Synthesis, Structures, Properties, Processing, and
3 Applications, John Wiley & Sons, Inc., New Jersey, 2010, pp. 323-341.
- 4 [68] H. Liu, J. Zhang, Research progress in toughening modification of poly (lactic acid),
5 J. Polym. Sci., Part B: Polym. Phys. 49 (2011) 1051-1083.
- 6 [69] H. Balakrishnan, A. Hassan, M. Imran, M.U. Wahit, Toughening of polylactic acid
7 nanocomposites: A short review, Polym. Plast. Technol. Eng. 51 (2012) 175-192.
- 8 [70] L. Natureworks, Technology Focus Report: Toughened PLA, Availbale online at:
9 [http://www. natureworkslc.](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Tough)
10 [com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Tough](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Tough)
11 [ened-Ingeo_pdf. pdf](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Tough) (2007).
- 12 [71] S. Detyothin, A. Kathuria, W. Jaruwattanayon, S.E.M. Selke, R. Auras, Poly(lactic
13 acid) Blends, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.), Poly(lactic acid).
14 Synthesis, Structures, Properties, Processing, and Applications, John Wiley & Sons,
15 Inc., New Jersey, 2010, pp. 227-266.
- 16 [72] L. Yu, E. Petinakis, K. Dean, H. Liu, Poly(lactic acid)/Starch Blends, in: R. Auras,
17 L.T. Lim, S. Selke, H. Tsuji (Eds.), Poly(lactic acid). Synthesis, Structures, Properties,
18 Processing, and Applications, John Wiley & Sons, Inc., New Jersey, 2010, pp. 217-225.
- 19 [73] S.B. Ghosh, S. Bandyopadhyay-Ghosh, M. Sain, Composites, in: R. Auras, L.T.
20 Lim, S. Selke, H. Tsuji (Eds.), Poly(lactic acid). Synthesis, Structures, Properties,
21 Processing, and Applications, John Wiley & Sons, Inc., New Jersey, 2010, pp. 293-307.
- 22 [74] V. Mittal, T. Akhtar, N. Matsko, Mechanical, Thermal, Rheological and
23 Morphological Properties of Binary and Ternary Blends of PLA, TPS and PCL,
24 Macromol. Mater. Eng. 300 (2015) 423-435.

- 1 [75] B. Meng, J. Deng, Q. Liu, Z. Wu, W. Yang, Transparent and ductile poly(lactic
2 acid)/poly(butyl acrylate) (PBA) blends: Structure and properties, *Eur. Polym. J.* 48
3 (2012) 127-135.
- 4 [76] Natureworks, Technology Focus Report: Toughened PLA, Available online at:
5 [http://www. natureworkslc.](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Toughened-Ingeo_.pdf)
6 [com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Tough](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Toughened-Ingeo_.pdf)
7 [ened-Ingeo_.pdf](http://www.natureworkslc.com/~media/Technical_Resources/Properties_Documents/PropertiesDocument_Toughened-Ingeo_.pdf). pdf (2007).
- 8 [77] W. Zhang, Z. Gui, C. Lu, S. Cheng, D. Cai, Y. Gao, Improving transparency of
9 incompatible polymer blends by reactive compatibilization, *Mater. Lett.* 92 (2013) 68-70.
- 10 [78] H. Abdillahi, E. Chabrat, A. Rouilly, L. Rigal, Influence of citric acid on thermoplastic
11 wheat flour/poly(lactic acid) blends. II. Barrier properties and water vapor sorption
12 isotherms, *Ind. Crop. Prod.* 50 (2013) 104-111.
- 13 [79] I. Armentano, Processing and characterization of plasticized PLA/PHB blends for
14 biodegradable multiphase systems, *Express Polym. Lett.* 9 (2015) 583-596.
- 15 [80] V. Jost, R. Kopitzky, Blending of polyhydroxybutyrate-co-valerate with polylactic
16 acid for packaging applications--reflections on miscibility and effects on the mechanical
17 and barrier properties, *Chem. Biochem. Eng. Q.* 29 (2015) 221.
- 18 [81] M. Boufarguine, A. Guinault, G. Miquelard-Garnier, C. Sollogoub, PLA/PHBV Films
19 with Improved Mechanical and Gas Barrier Properties, *Macromol. Mater. Eng.* 298
20 (2013) 1065-1073.
- 21 [82] S.M. Razavi, S. Dadbin, M. Frounchi, Oxygen-barrier properties of poly(lactic
22 acid)/poly(vinyl acetate-co-vinyl alcohol) blends as biodegradable films, *J. Appl. Polym.*
23 *Sci.* 125 (2012) E20-E26.
- 24 [83] N.E. Suyatma, A. Copinet, L. Tighzert, V. Coma, Mechanical and barrier properties
25 of biodegradable films made from chitosan and poly (lactic acid) blends, *J. Polym.*
26 *Environ.* 12 (2004) 1-6.

- 1 [84] R. Kwiatkowski, P. Dacko, SAXS Studies of Heating/Cooling Cycle Behavior of
2 Biodegradable BTA/PLA-b Blends, *Macromol. Symp.* 296 (2010) 478-486.
- 3 [85] J.M. Onyari, F. Mulaa, J. Muia, P. Shiundu, Biodegradability of Poly (lactic acid),
4 Preparation and Characterization of PLA/Gum Arabic Blends, *J. Polym. Environ.* 16
5 (2008) 205-212.
- 6 [86] Y.-X. Weng, L. Wang, M. Zhang, X.-L. Wang, Y.-Z. Wang, Biodegradation behavior
7 of P(3HB,4HB)/PLA blends in real soil environments, *Polym. Test.* 32 (2013) 60-70.
- 8 [87] M. Zhang, N.L. Thomas, Blending polylactic acid with polyhydroxybutyrate: The
9 effect on thermal, mechanical, and biodegradation properties, *Adv. Polym. Tech.* 30
10 (2011) 67-79.
- 11 [88] Q. Zhao, S. Wang, M. Kong, W. Geng, R.K.Y. Li, C. Song, D. Kong, Phase
12 morphology, physical properties, and biodegradation behavior of novel PLA/PHBHHx
13 blends, *J. Biomed. Mater. Res. B.* 100B (2012) 23-31.
- 14 [89] Y.F. Kim, C.N. Choi, Y.D. Kim, K.Y. Lee, M.S. Lee, Compatibilization of immiscible
15 poly (l-lactide) and low density polyethylene blends, *Fiber. Polym.* 5 (2004) 270-274.
- 16 [90] K.S. Anderson, S.H. Lim, M.A. Hillmyer, Toughening of polylactide by melt blending
17 with linear low-density polyethylene, *J. Appl. Polym. Sci.* 89 (2003) 3757-3768.
- 18 [91] K.S. Anderson, M.A. Hillmyer, The influence of block copolymer microstructure on
19 the toughness of compatibilized polylactide/polyethylene blends, *Polymer* 45 (2004)
20 8809-8823.
- 21 [92] Y. Wang, M.A. Hillmyer, Polyethylene-poly (L-lactide) diblock copolymers:
22 Synthesis and compatibilization of poly (L-lactide)/polyethylene blends, *J. Polym. Sci.,*
23 *Part A: Polym. Chem.* 39 (2001) 2755-2766.
- 24 [93] G. Biresaw, C. Carriere, Compatibility and mechanical properties of blends of
25 polystyrene with biodegradable polyesters, *Composites Part A* 35 (2004) 313-320.

- 1 [94] J.-S. Yoon, S.-H. Oh, M.-N. Kim, I.-J. Chin, Y.-H. Kim, Thermal and mechanical
2 properties of poly (l-lactic acid)–poly (ethylene-co-vinyl acetate) blends, *Polymer* 40
3 (1999) 2303-2312.
- 4 [95] C.M. Lee, E.S. Kim, J.S. Yoon, Reactive blending of poly (L-lactic acid) with poly
5 (ethylene-co-vinyl alcohol), *J. Appl. Polym. Sci.* 98 (2005) 886-890.
- 6 [96] C.-H. Ho, C.-H. Wang, C.-I. Lin, Y.-D. Lee, Synthesis and characterization of TPO–
7 PLA copolymer and its behavior as compatibilizer for PLA/TPO blends, *Polymer* 49
8 (2008) 3902-3910.
- 9 [97] Y. Li, H. Shimizu, Improvement in toughness of poly (l-lactide)(PLLA) through
10 reactive blending with acrylonitrile–butadiene–styrene copolymer (ABS): morphology
11 and properties, *Eur. Polym. J.* 45 (2009) 738-746.
- 12 [98] H.-J. Jin, I.-J. Chin, M.-N. Kim, S.-H. Kim, J.-S. Yoon, Blending of poly (L-lactic
13 acid) with poly (cis-1, 4-isoprene), *Eur. Polym. J.* 36 (2000) 165-169.
- 14 [99] H. Tsuji, H. Muramatsu, Blends of aliphatic polyesters: V non-enzymatic and
15 enzymatic hydrolysis of blends from hydrophobic poly (l-lactide) and hydrophilic poly
16 (vinyl alcohol), *Polym. Degrad. Stab.* 71 (2001) 403-413.
- 17 [100] L. Zhang, C. Xiong, X. Deng, Miscibility, crystallization and morphology of poly (β -
18 hydroxybutyrate)/poly (d, l-lactide) blends, *Polymer* 37 (1996) 235-241.
- 19 [101] G.-X. Chen, H.-S. Kim, E.-S. Kim, J.-S. Yoon, Compatibilization-like effect of
20 reactive organoclay on the poly (L-lactide)/poly (butylene succinate) blends, *Polymer* 46
21 (2005) 11829-11836.
- 22 [102] R. Wang, S. Wang, Y. Zhang, C. Wan, P. Ma, Toughening modification of
23 PLLA/PBS blends via in situ compatibilization, *Polym. Eng. Sci.* 49 (2009) 26.
- 24 [103] Y. Wang, J.F. Mano, Biodegradable poly (L-lactic acid)/poly (butylene
25 succinate-co-adipate) blends: Miscibility, morphology, and thermal behavior, *J. Appl.*
26 *Polym. Sci.* 105 (2007) 3204-3210.

- 1 [104] C. Ludvik, G. Glenn, A. Klamczynski, D. Wood, Cellulose fiber/bentonite
2 clay/biodegradable thermoplastic composites, *J. Polym. Environ.* 15 (2007) 251-257.
- 3 [105] N. Zhang, Q. Wang, J. Ren, L. Wang, Preparation and properties of biodegradable
4 poly (lactic acid)/poly (butylene adipate-co-terephthalate) blend with glycidyl
5 methacrylate as reactive processing agent, *J. Mater. Sci.* 44 (2009) 250-256.
- 6 [106] T.-Y. Liu, W.-C. Lin, M.-C. Yang, S.-Y. Chen, Miscibility, thermal characterization
7 and crystallization of poly (l-lactide) and poly (tetramethylene adipate-co-terephthalate)
8 blend membranes, *Polymer* 46 (2005) 12586-12594.
- 9 [107] W. Zhang, L. Chen, Y. Zhang, Surprising shape-memory effect of polylactide
10 resulted from toughening by polyamide elastomer, *Polymer* 50 (2009) 1311-1315.
- 11 [108] Y. Li, H. Shimizu, Toughening of polylactide by melt blending with a biodegradable
12 poly (ether) urethane elastomer, *Macromol. Biosci.* 7 (2007) 921-928.
- 13 [109] Y. Hu, Y. Hu, V. Topolkaraev, A. Hiltner, E. Baer, Aging of poly (lactide)/poly
14 (ethylene glycol) blends. Part 2. Poly (lactide) with high stereoregularity, *Polymer* 44
15 (2003) 5711-5720.
- 16 [110] J. Zhang, L. Jiang, L. Zhu, J.-I. Jane, P. Mungara, Morphology and properties of
17 soy protein and polylactide blends, *Biomacromolecules* 7 (2006) 1551-1561.
- 18 [111] H. Zhu, X. Feng, H. Zhang, Y. Guo, J. Zhang, J. Chen, Structural characteristics
19 and properties of silk fibroin/poly (lactic acid) blend films, *J. Biomater. Sci., Polym. Ed.*
20 20 (2009) 1259-1274.
- 21 [112] C. Xu, X. Luo, X. Lin, X. Zhuo, L. Liang, Preparation and characterization of
22 polylactide/thermoplastic konjac glucomannan blends, *Polymer* 50 (2009) 3698-3705.
- 23 [113] M. Peesan, P. Supaphol, R. Rujiravanit, Preparation and characterization of
24 hexanoyl chitosan/polylactide blend films, *Carbohydr. Polym.* 60 (2005) 343-350.

- 1 [114] Y. Wan, H. Wu, A. Yu, D. Wen, Biodegradable polylactide/chitosan blend
2 membranes, *Biomacromolecules* 7 (2006) 1362-1372.
- 3 [115] M. Shibata, Y. Inoue, M. Miyoshi, Mechanical properties, morphology, and
4 crystallization behavior of blends of poly (L-lactide) with poly (butylene succinate-co-L-
5 lactate) and poly (butylene succinate), *Polymer* 47 (2006) 3557-3564.
- 6 [116] S. Ghosh, J.C. Viana, R.L. Reis, J.F. Mano, Development of porous lamellar poly
7 (l-lactic acid) scaffolds by conventional injection molding process, *Acta Biomater.* 4
8 (2008) 887-896.
- 9 [117] Y.-H. Na, Y. He, X. Shuai, Y. Kikkawa, Y. Doi, Y. Inoue, Compatibilization effect of
10 poly (ϵ -caprolactone)-b-poly (ethylene glycol) block copolymers and phase morphology
11 analysis in immiscible poly (lactide)/poly (ϵ -caprolactone) blends, *Biomacromolecules* 3
12 (2002) 1179-1186.
- 13 [118] C.-C. Chen, J.-Y. Chueh, H. Tseng, H.-M. Huang, S.-Y. Lee, Preparation and
14 characterization of biodegradable PLA polymeric blends, *Biomaterials* 24 (2003) 1167-
15 1173.
- 16 [119] N. López-Rodríguez, A. López-Arraiza, E. Meaurio, J. Sarasua, Crystallization,
17 morphology, and mechanical behavior of polylactide/poly (ϵ -caprolactone) blends,
18 *Polym. Eng. Sci.* 46 (2006) 1299-1308.
- 19 [120] L. Wang, W. Ma, R. Gross, S. McCarthy, Reactive compatibilization of
20 biodegradable blends of poly (lactic acid) and poly (ϵ -caprolactone), *Polym. Degrad.*
21 *Stab.* 59 (1998) 161-168.
- 22 [121] T. Ke, X. Sun, Effects of moisture content and heat treatment on the physical
23 properties of starch and poly (lactic acid) blends, *J. Appl. Polym. Sci.* 81 (2001) 3069-
24 3082.
- 25 [122] T. Ke, X. Sun, Thermal and mechanical properties of poly (lactic acid) and starch
26 blends with various plasticizers, *T. ASAE* 44 (2001) 945-953.

- 1 [123] T. Ke, X. Sun, Melting behavior and crystallization kinetics of starch and poly
2 (lactic acid) composites, *J. Appl. Polym. Sci.* 89 (2003) 1203-1210.
- 3 [124] T. Ke, S.X. Sun, P. Seib, Blending of poly (lactic acid) and starches containing
4 varying amylose content, *J. Appl. Polym. Sci.* 89 (2003) 3639-3646.
- 5 [125] R.M. Rasal, D.E. Hirt, Toughness decrease of PLA-PHBHHx blend films upon
6 surface-confined photopolymerization, *J. Biomed. Mater. Res. Part A* 88 (2009) 1079-
7 1086.
- 8 [126] W. Ning, Z. Xingxiang, Y. Jiugao, F. Jianming, Partially miscible poly (lactic
9 acid)-blend-poly (propylene carbonate) filled with carbon black as conductive polymer
10 composite, *Polym. Int.* 57 (2008) 1027-1035.
- 11 [127] T.W. Yoo, H.G. Yoon, S.J. Choi, M.S. Kim, Y.H. Kim, W.N. Kim, Effects of
12 compatibilizers on the mechanical properties and interfacial tension of polypropylene
13 and poly (lactic acid) blends, *Macromol. Res.* 18 (2010) 583-588.
- 14 [128] J.B. Lee, Y.K. Lee, G.D. Choi, S.W. Na, T.S. Park, W.N. Kim, Compatibilizing
15 effects for improving mechanical properties of biodegradable poly (lactic acid) and
16 polycarbonate blends, *Polym. Degrad. Stab.* 96 (2011) 553-560.
- 17 [129] Z.-y. Gui, C. Lu, Y.-f. Li, S.-j. Cheng, Preparation and Characterization of PGS-
18 PLA Blend Composite [J], *Journal of East China University of Science and Technology*
19 (Natural Science Edition) 1 (2009) 012.
- 20 [130] H. Zou, C. Yi, L. Wang, W. Xu, Crystallization, hydrolytic degradation, and
21 mechanical properties of poly (trimethylene terephthalate)/poly (lactic acid) blends,
22 *Polym. Bull.* 64 (2010) 471-481.
- 23 [131] H.T. Oyama, Super-tough poly (lactic acid) materials: Reactive blending with
24 ethylene copolymer, *Polymer* 50 (2009) 747-751.

- 1 [132] M.P. Arrieta, E. Fortunati, F. Dominici, E. Rayón, J. López, J.M. Kenny, PLA-
2 PHB/cellulose based films: Mechanical, barrier and disintegration properties, Polym.
3 Degrad. Stab. 107 (2014) 139-149.
- 4 [133] N. Graupner, Application of lignin as natural adhesion promoter in cotton fibre-
5 reinforced poly(lactic acid) (PLA) composites, J. Mater. Sci. 43 (2008) 5222-5229.
- 6 [134] N. Graupner, A.S. Herrmann, J. Müssig, Natural and man-made cellulose fibre-
7 reinforced poly(lactic acid) (PLA) composites: An overview about mechanical
8 characteristics and application areas, Composites Part A 40 (2009) 810-821.
- 9 [135] Y. Hu, Q. Wang, M. Tang, Preparation and properties of Starch-g-PLA/poly(vinyl
10 alcohol) composite film, Carbohydr. Polym. 96 (2013) 384-388.
- 11 [136] I.S.M.A. Tawakkal, R.A. Talib, K. Abdan, C.N. Ling, Mechanical and physical
12 properties of kenaf-derived cellulose (KDC)-filled polylactic acid (PLA) composites,
13 BioResources 7 (2012) 1643-1655.
- 14 [137] E. Jalalvandi, R. Majid, T. Ghanbari, H. Ilbeygi, Effects of montmorillonite (MMT)
15 on morphological, tensile, physical barrier properties and biodegradability of polylactic
16 acid/starch/MMT nanocomposites, J. Thermoplast. Compos. Mater. 28 (2015) 496-509.
- 17 [138] A.K. Mohapatra, S. Mohanty, S.K. Nayak, Study of Thermo-Mechanical and
18 Morphological Behaviour of Biodegradable PLA/PBAT/Layered Silicate Blend
19 Nanocomposites, J. Polym. Environ. 22 (2014) 398-408.
- 20 [139] K. Nuñez, C. Rosales, R. Perera, N. Villarreal, J.M. Pastor, Nanocomposites of
21 PLA/PP blends based on sepiolite, Polym. Bull. 67 (2011) 1991-2016.
- 22 [140] J.-W. Rhim, S.-I. Hong, C.-S. Ha, Tensile, water vapor barrier and antimicrobial
23 properties of PLA/nanoclay composite films, LWT-Food Sci. Technol. 42 (2009) 612-
24 617.
- 25 [141] G.-X. Zou, X. Zhang, C.-X. Zhao, J. Li, The crystalline and mechanical properties
26 of PLA/layered silicate degradable composites, Polym. Sci. Ser. A 54 (2012) 393-400.

- 1 [142] M. Sabzi, L. Jiang, M. Atai, I. Ghasemi, PLA/sepiolite and PLA/calcium carbonate
2 nanocomposites: A comparison study, J. Appl. Polym. Sci. 129 (2013) 1734-1744.
- 3 [143] S. Siengchin, Reinforced Flax Mat/Modified Polylactide (PLA) Composites:
4 Impact, Thermal, and Mechanical Properties, Mech. Compos. Mater. 50 (2014) 257-
5 266.
- 6 [144] A. Araújo, G. Botelho, M. Oliveira, A.V. Machado, Influence of clay organic
7 modifier on the thermal-stability of PLA based nanocomposites, Appl. Clay Sci. 88-89
8 (2014) 144-150.
- 9 [145] L. Basilissi, G. Di Silvestro, H. Farina, M.A. Ortenzi, Synthesis and
10 characterization of PLA nanocomposites containing nanosilica modified with different
11 organosilanes II: Effect of the organosilanes on the properties of nanocomposites:
12 Thermal characterization, J. Appl. Polym. Sci. 128 (2013) 3057-3063.
- 13 [146] B.-K. Chen, C.-C. Shih, A.F. Chen, Ductile PLA nanocomposites with improved
14 thermal stability, Composites Part A 43 (2012) 2289.
- 15 [147] M. Iturrondobeitia, A. Okariz, T. Guraya, A.M. Zaldua, J. Ibarretxe, Influence of the
16 processing parameters and composition on the thermal stability of PLA/nanoclay
17 bio-nanocomposites, J. Appl. Polym. Sci. 131 (2014) 9120-9127.
- 18 [148] G. Gorrasi, R. Pantani, M. Murariu, P. Dubois, PLA/halloysite nanocomposite
19 films: water vapor barrier properties and specific key characteristics, Macromol. Mater.
20 Eng. 299 (2014) 104-115.
- 21 [149] E. Picard, E. Espuche, R. Fulchiron, Effect of an organo-modified montmorillonite
22 on PLA crystallization and gas barrier properties, Appl. Clay Sci. 53 (2011) 58-65.
- 23 [150] P.M.S. Souza, A.R. Morales, M.A. Marin-Morales, L.H.I. Mei, PLA and
24 montmorillonite nanocomposites: Properties, biodegradation and potential toxicity, J.
25 Polym. Environ. 21 (2013) 738-759.

- 1 [151] S.S. Ray, Nanocomposites, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.),
2 Poly(lactic acid). Synthesis, Structures, Properties, Processing, and Applications, John
3 Wiley & Sons, Inc., New Jersey, 2010, pp. 311-321.
- 4 [152] R.T. De Silva, P. Pasbakhsh, S.M. Lee, A.Y. Kit, ZnO deposited/encapsulated
5 halloysite–poly (lactic acid) (PLA) nanocomposites for high performance packaging films
6 with improved mechanical and antimicrobial properties, *Appl. Clay Sci.* 111 (2015) 10-
7 20.
- 8 [153] H. Ebadi-Dehaghani, H.A. Khonakdar, M. Barikani, S.H. Jafari, Experimental and
9 theoretical analyses of mechanical properties of PP/PLA/clay nanocomposites,
10 *Composites Part B* 69 (2015) 133-144.
- 11 [154] M.R. Kamal, V. Khoshkava, Effect of cellulose nanocrystals (CNC) on rheological
12 and mechanical properties and crystallization behavior of PLA/CNC nanocomposites,
13 *Carbohydr. Polym.* 123 (2015) 105-114.
- 14 [155] S.-M. Lai, S.-H. Wu, G.-G. Lin, T.-M. Don, Unusual mechanical properties of melt-
15 blended poly(lactic acid) (PLA)/clay nanocomposites, *Eur. Polym. J.* 52 (2014) 193.
- 16 [156] Q.K. Meng, M. Hetzer, D. De Kee, PLA/clay/wood nanocomposites: nanoclay
17 effects on mechanical and thermal properties, *J. Compos. Mater.* 45 (2011) 1145-1158.
- 18 [157] G. Ozkoc, S. Kemaloglu, Morphology, biodegradability, mechanical, and thermal
19 properties of nanocomposite films based on PLA and plasticized PLA, *J. Appl. Polym.*
20 *Sci.* 114 (2009) 2481-2487.
- 21 [158] S.I. Pirani, P. Krishnamachari, R. Hashaikeh, Optimum loading level of nanoclay
22 in PLA nanocomposites: Impact on the mechanical properties and glass transition
23 temperature, *J. Thermoplast. Compos. Mater.* 27 (2014) 1461-1478.
- 24 [159] Q. Shi, C. Zhou, Y. Yue, W. Guo, Y. Wu, Q. Wu, Mechanical properties and in
25 vitro degradation of electrospun bio-nanocomposite mats from PLA and cellulose
26 nanocrystals, *Carbohydr. Polym.* 90 (2012) 301.

- 1 [160] M. Yourdkhani, T. Mousavand, N. Chapleau, P. Hubert, Thermal, oxygen barrier
2 and mechanical properties of polylactide-organoclay nanocomposites, *Compos. Sci.*
3 *Technol.* 82 (2013) 47.
- 4 [161] M. Farmahini-Farahani, H. Xiao, Y. Zhao, Poly lactic acid nanocomposites
5 containing modified nanoclay with synergistic barrier to water vapor for coated paper,
6 *Journal of Applied Polymer Science* 131 (2014) n/a-n/a.
- 7 [162] H.A. Patel, R.S. Somani, H.C. Bajaj, R.V. Jasra, Nanoclays for polymer
8 nanocomposites, paints, inks, greases and cosmetics formulations, drug delivery
9 vehicle and waste water treatment, *Bull. Mater. Sci.* 29 (2006) 133-145.
- 10 [163] F. Uddin, Clays, nanoclays, and montmorillonite minerals, *Metall. Mater. Trans. A*
11 39 (2008) 2804-2814.
- 12 [164] S.S. Ray, M. Okamoto, Polymer/layered silicate nanocomposites: a review from
13 preparation to processing, *Prog. Polym. Sci.* 28 (2003) 1539-1641.
- 14 [165] X. Fang, S. Domenek, V. Ducruet, M. Réfrégiers, O. Vitrac, Diffusion of aromatic
15 solutes in aliphatic polymers above glass transition temperature, *Macromolecules* 46
16 (2013) 874-888.
- 17 [166] M.W. Noh, D.C. Lee, Synthesis and characterization of PS-clay nanocomposite by
18 emulsion polymerization, *Polym. Bull.* 42 (1999) 619-626.
- 19 [167] M. Zanetti, S. Lomakin, G. Camino, Polymer layered silicate nanocomposites,
20 *Macromol. Mater. Eng.* 279 (2000) 1-9.
- 21 [168] J.-M. Raquez, Y. Habibi, M. Murariu, P. Dubois, Polylactide (PLA)-based
22 nanocomposites, *Prog. Polym. Sci.* 38 (2013) 1504-1542.
- 23 [169] D. Wu, L. Wu, M. Zhang, Y. Zhao, Viscoelasticity and thermal stability of
24 polylactide composites with various functionalized carbon nanotubes, *Polym. Degrad.*
25 *Stab.* 93 (2008) 1577-1584.

- 1 [170] K. Shameli, M.B. Ahmad, W.M.Z.W. Yunus, N.A. Ibrahim, R.A. Rahman, M. Jokar,
2 M. Darroudi, Silver/poly (lactic acid) nanocomposites: preparation, characterization, and
3 antibacterial activity, *Int. J. Nanomedicine* 5 (2010) 573.
- 4 [171] N.L.G. De Rodriguez, W. Thielemans, A. Dufresne, Sisal cellulose whiskers
5 reinforced polyvinyl acetate nanocomposites, *Cellulose* 13 (2006) 261-270.
- 6 [172] J. Araki, M. Wada, S. Kuga, T. Okano, Influence of surface charge on viscosity
7 behavior of cellulose microcrystal suspension, *J. Wood Sci.* 45 (1999) 258-261.
- 8 [173] S. Beck-Candanedo, M. Roman, D.G. Gray, Effect of reaction conditions on the
9 properties and behavior of wood cellulose nanocrystal suspensions, *Biomacromolecules*
10 6 (2005) 1048-1054.
- 11 [174] I. Kvien, B.S. Tanem, K. Oksman, Characterization of cellulose whiskers and their
12 nanocomposites by atomic force and electron microscopy, *Biomacromolecules* 6 (2005)
13 3160-3165.
- 14 [175] J. Araki, M. Wada, S. Kuga, T. Okano, Birefringent glassy phase of a cellulose
15 microcrystal suspension, *Langmuir* 16 (2000) 2413-2415.
- 16 [176] X.M. Dong, J.-F. Revol, D.G. Gray, Effect of microcrystallite preparation conditions
17 on the formation of colloid crystals of cellulose, *Cellulose* 5 (1998) 19-32.
- 18 [177] Y. Habibi, L. Foulon, V. Aguié-Béghin, M. Molinari, R. Douillard, *Langmuir–*
19 *Blodgett films of cellulose nanocrystals: Preparation and characterization*, *J. Colloid*
20 *Interface Sci.* 316 (2007) 388-397.
- 21 [178] Y. Habibi, L.A. Lucia, O.J. Rojas, Cellulose nanocrystals: chemistry, self-
22 assembly, and applications, *Chem. Rev.* 110 (2010) 3479-3500.
- 23 [179] S.J. Hanley, J. Giasson, J.-F. Revol, D.G. Gray, Atomic force microscopy of
24 cellulose microfibrils: comparison with transmission electron microscopy, *Polymer* 33
25 (1992) 4639-4642.

- 1 [180] J.-F. Revol, On the cross-sectional shape of cellulose crystallites in *Valonia*
2 *ventricosa*, *Carbohydr. Polym.* 2 (1982) 123-134.
- 3 [181] C. Gauthier, Nanocomposite materials from latex and cellulose whiskers, *Polym.*
4 *Adv. Technol.* 6 (1994) 351355.
- 5 [182] M. Huda, L. Drzal, A. Mohanty, M. Misra, The effect of silane treated-and
6 untreated-talc on the mechanical and physico-mechanical properties of poly (lactic
7 acid)/newspaper fibers/talc hybrid composites, *Composites Part B* 38 (2007) 367-379.
- 8 [183] H.S. Kim, B.H. Park, J.H. Choi, J.S. Yoon, Mechanical properties and thermal
9 stability of poly (L-lactide)/calcium carbonate composites, *J. Appl. Polym. Sci.* 109
10 (2008) 3087-3092.
- 11 [184] M. Murariu, L. Bonnaud, P. Yoann, G. Fontaine, S. Bourbigot, P. Dubois, New
12 trends in polylactide (PLA)-based materials:“Green” PLA–Calcium sulfate (nano)
13 composites tailored with flame retardant properties, *Polym. Degrad. Stab.* 95 (2010)
14 374-381.
- 15 [185] M. Bühler, P.-E. Bourban, J.-A.E. Månson, Cellular composites based on
16 continuous fibres and bioresorbable polymers, *Composites Part A* 39 (2008) 1779-1786.
- 17 [186] G. Koronis, A. Silva, M. Fontul, Green composites: a review of adequate materials
18 for automotive applications, *Composites Part B* 44 (2013) 120-127.
- 19 [187] A. Bledzki, A. Jaszkievicz, Mechanical performance of biocomposites based on
20 PLA and PHBV reinforced with natural fibres–A comparative study to PP, *Compos. Sci.*
21 *Technol.* 70 (2010) 1687-1696.
- 22 [188] A. Le Duigou, P. Davies, C. Baley, Seawater ageing of flax/poly (lactic acid)
23 biocomposites, *Polym. Degrad. Stab.* 94 (2009) 1151-1162.
- 24 [189] Consumer Good, in: E. Britannica, 2015.

- 1 [190] S. Suzuki, Y. Ikada, Medical Applications, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji
2 (Eds.), Poly(lactic acid). Synthesis, Structures, Properties, Processing, and
3 Applications, Wiley Publishers, New Jersey, 2010, pp. 443-456.
- 4 [191] C.R.L. Zhou, L.H., Application of Novel PLA/Chitosan Composite Materials on
5 Bone Tissue Scaffolds, Australasian Society for Biomaterials and Tissue Engineering 8
6 (2004) 1572.
- 7 [192] D.M. Inc., Biocryl Rapide: TCP/PLGA Composite, in, DePuy Mitek, Raynham, MA,
8 2005.
- 9 [193] Z. Inc. Zimmer(R) Bio-Statak(R) Soft Tissue Attachment Device. Available:
10 [http://www.zimmer.com/content/dam/zimmer-web/documents/en-US/pdf/surgical-](http://www.zimmer.com/content/dam/zimmer-web/documents/en-US/pdf/surgical-techniques/trauma/Zimmer-Biostatak-Soft-Tissue-Attachment.pdf)
11 [techniques/trauma/Zimmer-Biostatak-Soft-Tissue-Attachment.pdf](http://www.zimmer.com/content/dam/zimmer-web/documents/en-US/pdf/surgical-techniques/trauma/Zimmer-Biostatak-Soft-Tissue-Attachment.pdf). Access date Sept 15,
12 2015, 2015.
- 13 [194] T. Deligio, PLA Composite Screws Replace Titanium in Surgical Implants, in:
14 Plastics Today, 2010.
- 15 [195] A. Hamilton, Mitek Sports Medicine Introduces New Interference Screw Design
16 For Faster, Easier Insertion, in, PR Newswire, Chicago, 2013.
- 17 [196] S.M.A. Bianca, Award-winning Water Filter Made from Bioplastic, in, Fraunhofer
18 Institute UMSICHT, 2014.
- 19 [197] K. Seitz, Biovation Launches Bioarmour™ Blood Pressure Cuff Shield, in:
20 Biovation Launches Bioarmour™ Blood Pressure Cuff Shield, An Infectious Disease
21 Barrier Product For Hospitals And Healthcare Facilities, Biovation, 2015.
- 22 [198] Ahlstrom. Ahlstrom BioWeb® Ultrasonic and Heatseal Teabags. Available:
23 [http://www.ahlstrom.com/en/Products/Food-and-Beverage/Tea-bags/BioWeb-](http://www.ahlstrom.com/en/Products/Food-and-Beverage/Tea-bags/BioWeb-Ultrasonic-heatsealable-teabags/)
24 [Ultrasonic--heatsealable-teabags/](http://www.ahlstrom.com/en/Products/Food-and-Beverage/Tea-bags/BioWeb-Ultrasonic-heatsealable-teabags/). Access date September 2nd, 2015.

- 1 [199] Ford researchers aim to create greener, lighter plastics. Available:
2 [http://www.reliableplant.com/Read/20034/ford-researchers-aim-to-create-greener,-](http://www.reliableplant.com/Read/20034/ford-researchers-aim-to-create-greener,-lighter-plastics)
3 lighter-plastics. Access date Sept 2nd, 2015.
- 4 [200] S.K. Ghosh, S., Application of Poly(lactic acid) Fibres in Automotive Interior,
5 Indian J. Fibre Text. 32 (2007) 119-121.
- 6 [201] K. So, Automotive Giants Turn to Bioplastics Worldwide, in, Plastics News,
7 Brussel, 2012.
- 8 [202] D. Farrington, J. Lunt, S. Davies, R. Blackburn, Poly (lactic acid) fibers, in: R.
9 Blackburn (Ed.), Biodegradable and sustainable fibres, Woodhead Publishing Limited,
10 Cambridge, England, 2005, pp. 191-220.
- 11 [203] M. Mochizuki, Textile Applications, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.),
12 Poly (Lactic Acid): Synthesis, Structures, Properties, Processing, and Applications, John
13 Wiley & Sons, Inc., New Jersey, 2010, pp. 469-476.
- 14 [204] T. Limited, Kansai Univ., Teijin Develop World's First Piezoelectric Fabrics for
15 Wearable Devices, in, BioSpace, Tokyo, Japan, 2015.
- 16 [205] S. Obuchi, S. Ogawa, Packaging and other commercial applications, in: R. Auras,
17 L.T. Lim, S. Selke, H. Tsuji (Eds.), Poly (lactic acid): Synthesis, Structures, Properties,
18 Processing, and Applications, John Wiley & Sons, Inc., New Jersey, 2010, pp. 457-467.
- 19 [206] D. Sullivan. Chipmaker's All-Or-Nothing Claim Sets The Bar In Big And Bold.
20 Available: [http://www.biocycle.net/2010/08/17/chipmakers-all-or-nothing-claim-sets-the-](http://www.biocycle.net/2010/08/17/chipmakers-all-or-nothing-claim-sets-the-bar-in-big-and-bold/)
21 bar-in-big-and-bold/. Access date September 2nd, 2015.
- 22 [207] K. Siranosian. New SunChips Bag: 90% Plant-based, 100% Compostable.
23 Available: <http://www.triplepundit.com/2010/02/new-sunchips-bag-compostable/>. Access
24 date Sept 2nd, 2015.
- 25 [208] M. Rosenthal, SAM'S CLUB Partners with NatureWorks PLA to Help the
26 Environment, in, NatureWorks LLC, 2005.

- 1 [209] NatureWorks, SPAR Austria Enhances Freshness of Produce with NatureWorks
2 PLA, in, NatureWorks, Linz, Austria, 2005.
- 3 [210] A.M. Mohan. Danone First to Switch to PLA for Yogurt Cup in Germany. Available:
4 http://www.greenerpackage.com/bioplastics/danone_first_switch_pla_yogurt_cup_germ
5 any. Access date September 2nd, 2015.
- 6 [211] J. Mochal, ConAgra Foods' New, Renewable Shrink Film Technology to Reduce
7 Impact on the Environment, in, ConAgra Foods, Omaha, NE, 2009.
- 8 [212] Bioplastics, First PLA Bottle in Germany, in: Bioplastics, Bioplastics, 2006, pp. 20-
9 21.
- 10 [213] R. Cernansky. Odwalla Juice Transitioning to 'PlantBottles' - HDPE Plastic From
11 Plant-Based Materials. Access date September 2nd, 2015.
- 12 [214] T. Pak, Fully Renewable Carton Package Now on the Shelves, in: A world first for
13 Valio and Tetra Pak, Tetra Pak, 2015.
- 14 [215] A. Mohanty, M. Misra, L. Drzal, Sustainable bio-composites from renewable
15 resources: opportunities and challenges in the green materials world, J. Polym. Environ.
16 10 (2002) 19-26.
- 17 [216] Y. Kasai, Nucleating Agents for inducing the Crystallization of PLA-
18 Ecopromote(R), in: Innovation Takes Root Conference, Orlando, FL, 2012.
- 19 [217] C. Purac, Bioplastics Product Profile: PLA Injection Molded Serviceware, in: C.
20 Purac (Ed.), Corbion, 2013.
- 21 [218] K. Jansen, Serving Up Plant-Based Plastics, in, Plastic News, Rosement, IL,
22 2015.
- 23 [219] D. Smock, New Bioplastic Feature Higher HDT, Impact Strength, in, DesignNews,
24 2011.

- 1 [220] Compostable Grocery Bags. Available: [http://advantage-](http://advantage-environment.com/livsmedel/compostable-grocery-bags/)
2 [environment.com/livsmedel/compostable-grocery-bags/](http://advantage-environment.com/livsmedel/compostable-grocery-bags/). Access date September 2nd,
3 2015.
- 4 [221] B. Bregar, PLA Bottle Maker Biota Enters Bankruptcy, in, PlasticNews, 2007.
- 5 [222] R. Lingle, PLA Makes Splash in Bottled Water, in: Packaging World, Packaging
6 World, 2004.
- 7 [223] A. ElAmin. Wal-Mart Signals Move to Natural Packaging. Available:
8 [http://www.foodproductiondaily.com/Packaging/Wal-Mart-signals-move-to-natural-](http://www.foodproductiondaily.com/Packaging/Wal-Mart-signals-move-to-natural-packaging)
9 [packaging](http://www.foodproductiondaily.com/Packaging/Wal-Mart-signals-move-to-natural-packaging). Access date September 2nd, 2015.
- 10 [224] Delhaize Expands Biodegradable Packaging Switch. Access date Sept 2nd, 2015.
- 11 [225] NatureWorks, Nature-Based Packaging for Fresh Cut Produce in High Demand,
12 in: NatureWorks(R) PLA Offereing Brand Owners and reatilers a Solution Consumers
13 Desire, NatureWorks, Minnetonka, MN, 2005.
- 14 [226] NatureWorks, Pacific Pre-Cut Enhance The Freshness of Its Brand with
15 NatureWorks PLA Packaging for Fresh-Packed Salads., in, NatureWorks, Minnetonka,
16 MN, 2005.
- 17 [227] Bioplastics, Huhtamaki Awarded Silver: Huhtamaki's PLA Dessert Cup Successful
18 in the Annual UK Starpack Competition, in: Bioplastics, Bioplastics, 2006, pp. 7.
- 19 [228] Fabri-Kal. Fabri-Kal Announces Addition to Greenware Product Family. Available:
20 <http://www.fabri-kal.com/fabri-kal-announces-addition-to-greenware-product-family/>.
21 Access date October 10, 2015.
- 22 [229] NatureWorks, Award, in: IngeoNews, 2008.
- 23 [230] R. Thompson, Packaging, PLA, in, Sustainable Is Good, 2007.
- 24 [231] PLA Bottles Soon To Be Released in Italy, in: Packaging Europe, Packaging
25 Europe, 2008.

- 1 [232] Shiseido, Shiseido to Commercialize Polylactic Acid Containers with Low
2 Environmental Load: To Be Introduced to URARA Brand Exclusively for the Chinese
3 Market, in, Shiseido, 2009.
- 4 [233] H. Soto-Valdez, PLA clamshells, in: H. Samsudin (Ed.), 2011.
- 5 [234] A.M. Mohan. Stonyfield Farm Makes Studied Switch to PLA for Yogurt Multipacks.
6 Available:
7 [http://www.greenerpackage.com/regulations/stonyfield_farm_makes_studied_switch_pl](http://www.greenerpackage.com/regulations/stonyfield_farm_makes_studied_switch_pla_yogurt_multipacks)
8 [a_yogurt_multipacks](http://www.greenerpackage.com/regulations/stonyfield_farm_makes_studied_switch_pla_yogurt_multipacks). Access date September 2nd, 2015.
- 9 [235] Polenghi. Bio Bottle. Available: <http://www.polenghigroup.it/en/sostenibilita/>.
10 Access date October 10, 2015.
- 11 [236] P. Strategies, Bio Bottle Is First in Europe, in: Packaging Strategies, 2010.
- 12 [237] M. Beune. Barrier Films: SiOx Barrier Benefits. Available: [http://www.pffc-](http://www.pffc-online.com/coat-lam/coatings/8832-siox-barrier-benefits-1001)
13 [online.com/coat-lam/coatings/8832-siox-barrier-benefits-1001](http://www.pffc-online.com/coat-lam/coatings/8832-siox-barrier-benefits-1001). Access date October
14 24th, 2015.
- 15 [238] Bioplastics, PLA Capsules for Athletic Apparel, in: Bioplastics, Bioplastics, 2011.
- 16 [239] C. Purac, Bioplastics Product Profile: PLA Thermoformed Single-Use Hot
17 Beverage Cups, in: C. Purac (Ed.), Corbion, 2013.
- 18 [240] D.G. Hayes, S. Dharmalingam, L.C. Wadsworth, K.K. Leonas, C. Miles, D. Inglis,
19 Biodegradable agricultural mulches derived from biopolymers, in: C.S. Kishan Khemani
20 (Ed.), Degradable polymers and materials: Principles and practice, American Chemical
21 Society, Washington, DC, 2012, pp. 201-223.
- 22 [241] S. Kasirajan, M. Ngouajio, Polyethylene and biodegradable mulches for
23 agricultural applications: a review, Agron. Sustain. Dev. 32 (2012) 501-529.

- 1 [242] T. Kijchavengkul, Design of biodegradable aliphatic aromatic polyester films for
2 agricultural applications using response surface methodology, in: Packaging, Michigan
3 State University, Michigan, 2010.
- 4 [243] M. Hakkarainen, S. Karlsson, A.C. Albertsson, Influence of low molecular weight
5 lactic acid derivatives on degradability of polylactide, J. Appl. Polym. Sci. 76 (2000) 228-
6 239.
- 7 [244] S.R. Andersson, M. Hakkarainen, A.-C. Albertsson, Tuning the polylactide
8 hydrolysis rate by plasticizer architecture and hydrophilicity without introducing new
9 migrants, Biomacromolecules 11 (2010) 3617-3623.
- 10 [245] Y. Matsuzawa, Z.-I. Kimura, Y. Nishimura, M. Shibayama, A. Hiraishi, Removal of
11 Hydrophobic Organic Contaminants from Aqueous Solutions by Sorption onto
12 Biodegradable Polyesters, J. Water Resour. Prot. 2 (2010) 214-221.
- 13 [246] A. Hiraishi, Environmental Applications, in: R. Auras, L. Lim, S. Selke, H. Tsuj
14 (Eds.), Poly(Lactic Acid), John Wiley & Sons, Inc., Hoboken, NJ, 2010, pp. 469-476.
- 15 [247] S.S. Koenigsberg, Hydrogen Release Compound (HRC): A Novel Technology for
16 the Bioremediation of Chlorinated Hydrocarbons, in: Proceedings of the 1999
17 Conference on Hazardous Waste Research, St. Louis, MO, 1999.
- 18 [248] G. Caruso, Plastic Degrading Microorganisms as a Tool for Bioremediation of
19 Plastic Contamination in Aquatic Environments, J. Pollut. Eff. Cont. 3 (2015) e112.
- 20 [249] L. Chilson. The Difference between ABS and PLA for 3D Printing. Available:
21 [http://www.protoparadigm.com/news-updates/the-difference-between-abs-and-pla-for-](http://www.protoparadigm.com/news-updates/the-difference-between-abs-and-pla-for-3d-printing/)
22 [3d-printing/](http://www.protoparadigm.com/news-updates/the-difference-between-abs-and-pla-for-3d-printing/). Access date November 30th, 2015.
- 23 [250] R.M. Robertson, W.C. Thomas, J.N. Suthar, D.M. Brown, Accelerated degradation
24 of cellulose acetate cigarette filters using controlled-release acid catalysis, Green
25 Chem. 14 (2012) 2266-2272.

- 1 [251] F.L. Ltd. Fujitsu Laboratories Develops Industry's First Bio-Derived, Water-based
2 Paint. Available: [http://www.fujitsu.com/global/about/resources/news/press-](http://www.fujitsu.com/global/about/resources/news/press-releases/2014/1210-01.html)
3 [releases/2014/1210-01.html](http://www.fujitsu.com/global/about/resources/news/press-releases/2014/1210-01.html). Access date November 30th 2015.
- 4 [252] Fujitsu, Fujitsu and Toray Develop World's First Environmentally-Friendly Large-
5 Size Plastic Housing for Notebook PCs. Available:
6 <http://www.fujitsu.com/global/about/resources/news/press-releases/2005/0113-01.html>.
7 Access date February 28th, 2016.
- 8 [253] PEGA. Available: <http://www.pegadesign.com/en/portfolio-pla.html>. Access date
9 February 28th, 2016.
- 10 [254] W.L. Hawkins, Polymer Degradation and Stabilization, Springer-Verlag, Berlin,
11 1984.
- 12 [255] R. Muller, Biodegradability of polymers: Regulations and methods of testing. , in:
13 A. Steinbuchel (Ed.), Biopolymer, General Aspects and Special Application, Wiley
14 Publishers, 2008, pp. 366-388.
- 15 [256] H. Tsuji, Hydrolytic Degradation, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.),
16 Poly(lactic acid). Synthesis, Structures, Properties, Processing, and Applications, John
17 Wiley & Sons, Inc., New Jersey, 2010, pp. 345-381.
- 18 [257] S. De Jong, E.R. Arias, D. Rijkers, C. Van Nostrum, J. Kettenes-Van den Bosch,
19 W. Hennink, New insights into the hydrolytic degradation of poly (lactic acid):
20 participation of the alcohol terminus, Polymer 42 (2001) 2795-2802.
- 21 [258] S. Lyu, J. Schley, B. Loy, D. Lind, C. Hobot, R. Sparer, D. Untereker, Kinetics and
22 time-temperature equivalence of polymer degradation, Biomacromolecules 8 (2007)
23 2301-2310.
- 24 [259] E. Fischer, H.J. Sterzel, G. Wegner, Investigation of the structure of solution
25 grown crystals of lactide copolymers by means of chemical reactions, Kolloid Z. Z.
26 Polym. 251 (1973) 980-990.

- 1 [260] C. Chu, Hydrolytic degradation of polyglycolic acid: tensile strength and
2 crystallinity study, *J. Appl. Polym. Sci.* 26 (1981) 1727-1734.
- 3 [261] Y.-N. Chang, R.E. Mueller, E.L. Iannotti, Use of low MW polylactic acid and lactide
4 to stimulate growth and yield of soybeans, *Plant Growth Regul.* 19 (1996) 223-232.
- 5 [262] C. Xiang, A.G. Taylor, J.P. Hinestroza, M.W. Frey, Controlled release of nonionic
6 compounds from poly (lactic acid)/cellulose nanocrystal nanocomposite fibers, *J. Appl.*
7 *Polym. Sci.* 127 (2013) 79-86.
- 8 [263] A. Copinet, C. Bertrand, S. Govindin, V. Coma, Y. Couturier, Effects of ultraviolet
9 light (315 nm), temperature and relative humidity on the degradation of polylactic acid
10 plastic films, *Chemosphere* 55 (2004) 763-773.
- 11 [264] J.H. Jung, M. Ree, H. Kim, Acid-and base-catalyzed hydrolyses of aliphatic
12 polycarbonates and polyesters, *Catal. Today* 115 (2006) 283-287.
- 13 [265] K. Makino, H. Ohshima, T. Kondo, Mechanism of hydrolytic degradation of poly (L-
14 lactide) microcapsules: effects of pH, ionic strength and buffer concentration, *J.*
15 *Microencapsulation* 3 (1986) 203-212.
- 16 [266] H. Tsuji, Y. Ikada, Properties and morphology of poly (L-lactide). II. Hydrolysis in
17 alkaline solution, *J. Polym. Sci., Part A: Polym. Chem.* 36 (1998) 59-66.
- 18 [267] Y. Ikada, H. Tsuji, Biodegradable polyesters for medical and ecological
19 applications, *Macromol. Rapid Commun.* 21 (2000) 117-132.
- 20 [268] H.S. Burdurlu, N. Koca, F. Karadeniz, Degradation of vitamin C in citrus juice
21 concentrates during storage, *J. Food Eng.* 74 (2006) 211-216.
- 22 [269] H. Tsuji, K. Sumida, Poly (L-lactide): v. effects of storage in swelling solvents on
23 physical properties and structure of poly (L-lactide), *J. Appl. Polym. Sci.* 79 (2001) 1582-
24 1589.

- 1 [270] S. Sato, D. Gondo, T. Wada, S. Kanehashi, K. Nagai, Effects of various liquid
2 organic solvents on solvent-induced crystallization of amorphous poly (lactic acid) film,
3 J. Appl. Polym. Sci. 129 (2013) 1607-1617.
- 4 [271] J. Gao, L. Duan, G. Yang, Q. Zhang, M. Yang, Q. Fu, Manipulating poly (lactic
5 acid) surface morphology by solvent-induced crystallization, Appl. Surf. Sci. 261 (2012)
6 528-535.
- 7 [272] FDA. Guidance for Industry: Preparation of Premarket Submissions for Food
8 Contact Substances: Chemistry Recommenda- tions. Food and Drug Administration.
9 Available:
10 <http://www.fda.gov/Food/GuidanceRegulation/GuidanceDocumentsRegulatoryInformati>
11 [on/IngredientsAdditivesGRASPackaging/ucm081818.htm](http://www.fda.gov/Food/GuidanceRegulation/GuidanceDocumentsRegulatoryInformati) - iid1a. Access date
12 September 15th, 2015.
- 13 [273] 10/2011/EU Commission regulation on plastic materials and articles intended to
14 come into contact with food. The European Commission., Official Journal of the
15 European Union 12 (2011) 15.11.2011.
- 16 [274] F. Iñiguez-Franco, G. Burgessa, D. Holmes, X. Fanga, M. Rubino, H. Soto-Valdez,
17 R. Auras, Concurrent induced solvent crystallization and hydrolytic degradation of PLA
18 by water-ethanol solutions. Paper to be published, (2016).
- 19 [275] M.K. Mitchell, D.E. Hirt, Degradation of PLA fibers at elevated temperature and
20 humidity, Polym. Eng. Sci. 55 (2015) 1652-1660.
- 21 [276] K. Fukushima, D. Tabuani, M. Dottori, I. Armentano, J. Kenny, G. Camino, Effect
22 of temperature and nanoparticle type on hydrolytic degradation of poly (lactic acid)
23 nanocomposites, Polym. Degrad. Stab. 96 (2011) 2120-2129.
- 24 [277] W. Tham, Z.M. Ishak, W. Chow, Water absorption and hygrothermal aging
25 behaviors of SEBS-g-MAH toughened poly (lactic acid)/halloysite nanocomposites,
26 Polym. Plast. Technol. Eng. 53 (2014) 472-480.

- 1 [278] K. Jamshidi, S.-H. Hyon, Y. Ikada, Thermal characterization of polylactides,
2 Polymer 29 (1988) 2229-2234.
- 3 [279] F.-D. Kopinke, K. Mackenzie, Mechanistic aspects of the thermal degradation of
4 poly (lactic acid) and poly (β -hydroxybutyric acid), J. Anal. Appl. Pyrolysis 40 (1997) 43-
5 53.
- 6 [280] F.-D. Kopinke, M. Remmler, K. Mackenzie, Thermal decomposition of
7 biodegradable polyesters—I: Poly (β -hydroxybutyric acid), Polym. Degrad. Stab. 52
8 (1996) 25-38.
- 9 [281] I. McNeill, H. Leiper, Degradation studies of some polyesters and
10 polycarbonates—2. Polylactide: degradation under isothermal conditions, thermal
11 degradation mechanism and photolysis of the polymer, Polym. Degrad. Stab. 11 (1985)
12 309-326.
- 13 [282] Y. Aoyagi, K. Yamashita, Y. Doi, Thermal degradation of poly [(R)-3-
14 hydroxybutyrate], poly [ϵ -caprolactone], and poly [(S)-lactide], Polym. Degrad. Stab. 76
15 (2002) 53-59.
- 16 [283] H. Abe, N. Takahashi, K.J. Kim, M. Mochizuki, Y. Doi, Thermal degradation
17 processes of end-capped poly (L-lactide) s in the presence and absence of residual zinc
18 catalyst, Biomacromolecules 5 (2004) 1606-1614.
- 19 [284] A. Babanalbandi, D.J.T. Hill, D.S. Hunter, L. Kettle, Thermal stability of poly (lactic
20 acid) before and after γ -radiolysis, Polym. Int. 48 (1999) 980-984.
- 21 [285] H. Zou, C. Yi, L. Wang, H. Liu, W. Xu, Thermal degradation of poly (lactic acid)
22 measured by thermogravimetry coupled to Fourier transform infrared spectroscopy, J.
23 Therm. Anal. Calorim. 97 (2009) 929-935.
- 24 [286] H. Nishida, Thermal degradation, in: R. Auras, L.T. Lim, S. Selke, H. Tsuji (Eds.),
25 Poly(lactic acid). Synthesis, Structures, Properties, Processing, and Applications, Wiley
26 Publishers, New Jersey, 2010, pp. 401-412.

- 1 [287] P. Degée, P. Dubois, R. Jérôme, Bulk polymerization of lactides initiated by
2 aluminium isopropoxide, 3. Thermal stability and viscoelastic properties, *Macromol.*
3 *Chem. Phys.* 198 (1997) 1985-1995.
- 4 [288] O. Wachsen, K. Platkowski, K.-H. Reichert, Thermal degradation of poly-L-
5 lactide—studies on kinetics, modelling and melt stabilisation, *Polym. Degrad. Stab.* 57
6 (1997) 87-94.
- 7 [289] V. Taubner, R. Shishoo, Influence of processing parameters on the degradation of
8 poly (L-lactide) during extrusion, *J. Appl. Polym. Sci.* 79 (2001) 2128-2135.
- 9 [290] H. Tsuji, I. Fukui, Enhanced thermal stability of poly (lactide) s in the melt by
10 enantiomeric polymer blending, *Polymer* 44 (2003) 2891-2896.
- 11 [291] D. Cam, M. Marucci, Influence of residual monomers and metals on poly (L-
12 lactide) thermal stability, *Polymer* 38 (1997) 1879-1884.
- 13 [292] A. Södergård, J. Näsman, Stabilization of poly (L-lactide) in the melt, *Polym.*
14 *Degrad. Stab.* 46 (1994) 25-30.
- 15 [293] Y. Fan, H. Nishida, Y. Shirai, Y. Tokiwa, T. Endo, Thermal degradation behaviour
16 of poly (lactic acid) stereocomplex, *Polym. Degrad. Stab.* 86 (2004) 197-208.
- 17 [294] N. Najafi, M. Heuzey, P. Carreau, P.M. Wood-Adams, Control of thermal
18 degradation of polylactide (PLA)-clay nanocomposites using chain extenders, *Polym.*
19 *Degrad. Stab.* 97 (2012) 554-565.
- 20 [295] R. Al-Itry, K. Lamnawar, A. Maazouz, Improvement of thermal stability, rheological
21 and mechanical properties of PLA, PBAT and their blends by reactive extrusion with
22 functionalized epoxy, *Polym. Degrad. Stab.* 97 (2012) 1898-1914.
- 23 [296] W. Sakai, N. Tsutsumi, Photodegradation and radiation degradation, in: R. Auras,
24 L.-T. Lim, S. Selke, H. Tsuji (Eds.), *Poly(lactic acid): Synthesis, Structures, Properties,*
25 *Processing, and Applications*, John Wiley & Sons, Inc., New Jersey, 2010, pp. 413-421.

- 1 [297] E. Ikada, M. Ashida, Promotion of photodegradation of polymers for plastic waste
2 treatment, J. Photopolym. Sci. Technol. 4 (1991) 247-254.
- 3 [298] E. Ikada, Role of The Molecular Structure in The Photodecomposition of
4 Polymers, J. Photopolym. Sci. Technol. 6 (1993) 115-122.
- 5 [299] E. Ikada, Photo-and bio-degradable polyesters. Photodegradation behaviors of
6 aliphatic polyesters, J. Photopolym. Sci. Technol. 10 (1997) 265-270.
- 7 [300] E. Ikada, Relationship between Photodegradability and Biodegradability of Some
8 Aliphatic Polyesters, J. Photopolym. Sci. Technol. 12 (1999) 251-256.
- 9 [301] L. Santonja-Blasco, A. Ribes-Greus, R. Alamo, Comparative thermal, biological
10 and photodegradation kinetics of polylactide and effect on crystallization rates, Polym.
11 Degrad. Stab. 98 (2013) 771-784.
- 12 [302] H. Tsuji, Y. Echizen, Y. Nishimura, Photodegradation of biodegradable polyesters:
13 A comprehensive study on poly (l-lactide) and poly (ϵ -caprolactone), Polym. Degrad.
14 Stab. 91 (2006) 1128-1137.
- 15 [303] A.V. Janorkar, A.T. Metters, D.E. Hirt, Degradation of poly (L-lactide) films under
16 ultraviolet-induced photografting and sterilization conditions, J. Appl. Polym. Sci. 106
17 (2007) 1042-1047.
- 18 [304] K.-L.G. Ho, A.L. Pometto III, Effects of electron-beam irradiation and ultraviolet
19 light (365 nm) on polylactic acid plastic films, J. Environ. Polym. Degr. 7 (1999) 93-100.
- 20 [305] K.-L.G. Ho, A.L. Pometto III, P.N. Hinz, Effects of temperature and relative
21 humidity on polylactic acid plastic degradation, J. Environ. Polym. Degr. 7 (1999) 83-92.
- 22 [306] A. Babanalbandi, D. Hill, J. O'Donnell, P. Pomery, A. Whittaker, An electron spin
23 resonance study on γ -irradiated poly (l-lactic acid) and poly (d, l-lactic acid), Polym.
24 Degrad. Stab. 50 (1995) 297-304.

- 1 [307] C. Birkinshaw, M. Buggy, G. Henn, E. Jones, Irradiation of poly-D, L-lactide,
2 Polym. Degrad. Stab. 38 (1992) 249-253.
- 3 [308] J. Collett, L. Lim, P. Gould, Gamma-irradiation of biodegradable polyesters in
4 controlled physical environments, Polymer Prepr. Am. Chem. Soc. 30 (1989) 468-469.
- 5 [309] Global Sustainable Development Report. Briefs Available:
6 [https://sustainabledevelopment.un.org/content/documents/1870GSDR%202015%20Bri](https://sustainabledevelopment.un.org/content/documents/1870GSDR%202015%20Briefs.pdf)
7 [efs.pdf](https://sustainabledevelopment.un.org/content/documents/1870GSDR%202015%20Briefs.pdf) Access date October 24th, 2015.
- 8 [310] M.A. Curran, Life cycle assessment: a review of the methodology and its
9 application to sustainability, Curr. Opin. Chem. Eng. 2 (2013) 273-277.
- 10 [311] S. Madival, R. Auras, S.P. Singh, R. Narayan, Assessment of the environmental
11 profile of PLA, PET and PS clamshell containers using LCA methodology, J. Clean
12 Prod. 17 (2009) 1183-1194.
- 13 [312] Directive 2008/98/EC of the European Parliament and of the Council of 19
14 November 2008 on waste and repealing certain directives. Available: [http://eur-](http://eur-lex.europa.eu/legal-content/EN/TXT/PDF/?uri=CELEX:32008L0098&from=EN)
15 [lex.europa.eu/legal-content/EN/TXT/PDF/?uri=CELEX:32008L0098&from=EN](http://eur-lex.europa.eu/legal-content/EN/TXT/PDF/?uri=CELEX:32008L0098&from=EN) Access
16 date October 26th, 2015.
- 17 [313] EPA, Advancing Sustainable Materials Management: 2013 Fact Sheet Available:
18 http://www3.epa.gov/epawaste/nonhaz/municipal/pubs/2013_advncng_smm_fs.pdf.
19 Access date September 14th, 2015.
- 20 [314] EPA, Advancing Sustainable Materials Management: Facts and Figures 2013
21 Available:
22 http://www3.epa.gov/epawaste/nonhaz/municipal/pubs/2013_advncng_smm_rpt.pdf.
23 Access date September 14th, 2015.
- 24 [315] V. Rossi, N. Cleeve-Edwards, L. Lundquist, U. Schenker, C. Dubois, S. Humbert,
25 O. Jolliet, Life cycle assessment of end-of-life options for two biodegradable packaging

- 1 materials: sound application of the European waste hierarchy, *J. Clean Prod.* 86 (2015)
2 132-145.
- 3 [316] E. Kosior, R.M. Braganca, P. Fowler, Lightweight compostable packaging:
4 literature review, *The Waste & Resources Action Programme* 26 (2006) 1-48.
- 5 [317] L. Liu, M.L. Fishman, K.B. Hicks, C.-K. Liu, Biodegradable composites from sugar
6 beet pulp and poly (lactic acid), *J. Agric. Food. Chem.* 53 (2005) 9017-9022.
- 7 [318] V. Peinado, L. García, Á. Fernández, P. Castell, Novel lightweight foamed poly
8 (lactic acid) reinforced with different loadings of functionalised Sepiolite, *Compos. Sci.*
9 *Technol.* 101 (2014) 17-23.
- 10 [319] Y. Du, N. Yan, M.T. Kortschot, Novel lightweight sandwich-structured bio-fiber-
11 reinforced poly (lactic acid) composites, *J. Mater. Sci.* 49 (2014) 2018-2026.
- 12 [320] R.C. Thompson, C.J. Moore, F.S. Vom Saal, S.H. Swan, Plastics, the environment
13 and human health: current consensus and future trends, *Phil. Trans. R. Soc. B* 364
14 (2009) 2153-2166.
- 15 [321] A. Jarerat, Y. Tokiwa, H. Tanaka, Production of poly (L-lactide)-degrading enzyme
16 by *Amycolatopsis orientalis* for biological recycling of poly (L-lactide), *Appl. Microbiol.*
17 *Biotechnol.* 72 (2006) 726-731.
- 18 [322] V. Piemonte, S. Sabatini, F. Gironi, Chemical recycling of PLA: a great opportunity
19 towards the sustainable development?, *J. Polym. Environ.* 21 (2013) 640-647.
- 20 [323] D.D. Cornell, Biopolymers in the existing postconsumer plastics recycling stream,
21 *J. Polym. Environ.* 15 (2007) 295-299.
- 22 [324] NatureWorks. End-of-life options. Feedstock Recycling. Available:
23 <http://www.natureworkslc.com/The-Ingeo-Journey/End-of-Life-Options/Feedstock->
24 [Recycling.](http://www.natureworkslc.com/The-Ingeo-Journey/End-of-Life-Options/Feedstock-) Access date October 13th, 2015.

- 1 [325] NatureWorks. End-of-life options. Recycling. Available:
2 <http://www.natureworksllc.com/The-Ingeo-Journey/End-of-Life-Options/Recycling>.
3 Access date October 13th, 2015.
- 4 [326] D. Bellm. New business buys post-consumer PLA for use in packaging. Available:
5 [http://www.packagingdigest.com/smart-packaging/new-business-buys-post-consumer-](http://www.packagingdigest.com/smart-packaging/new-business-buys-post-consumer-pla-use-packaging)
6 [pla-use-packaging](http://www.packagingdigest.com/smart-packaging/new-business-buys-post-consumer-pla-use-packaging) Access date October 13th, 2015.
- 7 [327] D. Bellm. Sustainable packaging: First new company formed to recycle PLA.
8 Available: [http://www.packagingdigest.com/smart-packaging/sustainable-packaging-](http://www.packagingdigest.com/smart-packaging/sustainable-packaging-first-new-company-formed-recycle-pla)
9 [first-new-company-formed-recycle-pla](http://www.packagingdigest.com/smart-packaging/sustainable-packaging-first-new-company-formed-recycle-pla). Access date October 13th, 2015.
- 10 [328] NAPCOR refutes claims that PLA can be recycled with PET. Available:
11 [http://www.packagingdigest.com/smart-packaging/napcor-refutes-claims-pla-can-be-](http://www.packagingdigest.com/smart-packaging/napcor-refutes-claims-pla-can-be-recycled-pet)
12 [recycled-pet](http://www.packagingdigest.com/smart-packaging/napcor-refutes-claims-pla-can-be-recycled-pet) Access date October 13th, 2015.
- 13 [329] T. Kijchavengkul, R. Auras, Compostability of polymers, *Polym. Int.* 57 (2008) 793-
14 804.
- 15 [330] A.A. Shah, F. Hasan, A. Hameed, S. Ahmed, Biological degradation of plastics: a
16 comprehensive review, *Biotechnol. Adv.* 26 (2008) 246-265.
- 17 [331] S. Grima, V. Bellon-Maurel, P. Feuilleley, F. Silvestre, Aerobic biodegradation of
18 polymers in solid-state conditions: a review of environmental and physicochemical
19 parameter settings in laboratory simulations, *J. Polym. Environ.* 8 (2000) 183-195.
- 20 [332] T. Leejarkpai, U. Suwanmanee, Y. Rudeekit, T. Mungcharoen, Biodegradable
21 kinetics of plastics under controlled composting conditions, *Waste Manage. (Oxford)* 31
22 (2011) 1153-1161.
- 23 [333] V. Mittal, Characterization techniques for polymer nanocomposites, John Wiley &
24 Sons, Weinheim, Germany, 2012.

- 1 [334] ASTM Standard D5338-11, Standard Test Method for Determining Aerobic
2 Biodegradation of Plastic Materials Under Controlled Composting Conditions.
3 Incorporating Thermophilic Temperatures, West Conshohocken, PA, 2011.
- 4 [335] International Standard ISO 14855-1:2005(E), Determination of the ultimate
5 aerobic biodegradability of plastic materials under controlled composting conditions -
6 Method by analysis of evolved carbon dioxide - Part 1: General Method, in, Geneva,
7 Switzerland, 2005.
- 8 [336] E. Castro Aguirre, Design and construction of a medium-scale automated direct
9 measurement respirometric system to assess aerobic biodegradation of polymers, in:
10 School of Packaging, Michigan State University, Michigan, 2013.
- 11 [337] S. Selke, R. Auras, T.A. Nguyen, E. Castro Aguirre, R. Cheruvathur, Y. Liu,
12 Evaluation of Biodegradation-Promoting Additives for Plastics, Environ. Sci. Technol. 49
13 (2015) 3769-3777.
- 14 [338] M. Grosso, A. Motta, L. Rigamonti, Efficiency of energy recovery from waste
15 incineration, in the light of the new Waste Framework Directive, Waste Manage.
16 (Oxford) 30 (2010) 1238-1243.
- 17 [339] A. Damgaard, C. Riber, T. Fruergaard, T. Hulgaard, T.H. Christensen, Life-cycle-
18 assessment of the historical development of air pollution control and energy recovery in
19 waste incineration, Waste Manage. (Oxford) 30 (2010) 1244-1250.
- 20 [340] C. Laußmann, U. Land, B. Münster, G.H.-J. Endres, F. Hannover, G.U. Giese, A.-
21 S. Kitzler, A. Papierveredelung, Disposal of Bio-Polymers via Energy Recovery, in:
22 Bioplastics magazine 2010, pp. 42-43.
- 23 [341] NatureWorks. End-of-life options. Incineration. Available:
24 <http://www.natureworkslc.com/The-Ingeo-Journey/End-of-Life-Options/Incineration>.
25 Access date October 13th, 2015.

- 1 [342] M. El-Fadel, A.N. Findikakis, J.O. Leckie, Environmental impacts of solid waste
2 landfilling, *J. Environ. Manage.* 50 (1997) 1-25.
- 3 [343] S.E. Selke, *Plastics recycling and biodegradable plastics: The Complete Guide to*
4 *Properties and Performance*, McGraw-Hill, New York, 2006.
- 5 [344] J.J. Kolstad, E.T. Vink, B. De Wilde, L. Debeer, Assessment of anaerobic
6 degradation of Ingeo™ polylactides under accelerated landfill conditions, *Polym.*
7 *Degrad. Stab.* 97 (2012) 1131-1141.
- 8 [345] L. Čuček, J.J. Klemeš, Z. Kravanja, A review of footprint analysis tools for
9 monitoring impacts on sustainability, *J. Clean Prod.* 34 (2012) 9-20.
- 10 [346] J. Potting, How to Approach the Assessment?, in: M.A. Curran (Ed.), *Life Cycle*
11 *Assessment Handbook: A Guide for Environmentally Sustainable Products* John Wiley
12 & Sons, Inc., Cincinnati, OH, USA, 2012, pp. 391-412.
- 13 [347] K.A. Weitz, *Life Cycle Assessment and End of Life Materials Management*, in:
14 M.A. Curran (Ed.), *Life Cycle Assessment Handbook: A Guide for Environmentally*
15 *Sustainable Products* John Wiley & Sons, Inc., Cincinnati, OH, USA, 2012, pp. 249-266.
- 16 [348] International Standard ISO 14040. *Environmental Management – Life Cycle*
17 *Assessment – Principles and Framework*, in, Geneva, Switzerland, 2010.
- 18 [349] International Standard ISO 14044. *Environmental Management – Life Cycle*
19 *Assessment – Requirements and Guidelines*, in, Geneva, Switzerland, 2006.
- 20 [350] O. Jolliet, M. Margni, R. Charles, S. Humbert, J. Payet, G. Rebitzer, R.
21 Rosenbaum, IMPACT 2002+: a new life cycle impact assessment methodology, *Int. J.*
22 *Life. Cycle. Assess.* 8 (2003) 324-330.
- 23 [351] E.T. Vink, K.R. Rabago, D.A. Glassner, P.R. Gruber, Applications of life cycle
24 assessment to NatureWorks™ polylactide (PLA) production, *Polym. Degrad. Stab.* 80
25 (2003) 403-419.

- 1 [352] E.T. Vink, D.A. Glassner, J.J. Kolstad, R.J. Wooley, R.P. O'Connor, Original
2 research: the eco-profiles for current and near-future NatureWorks® polylactide (PLA)
3 production, *Industrial Biotechnology* 3 (2007) 58-81.
- 4 [353] E.T. Vink, S. Davies, J.J. Kolstad, ORIGINAL RESEARCH: The eco-profile for
5 current Ingeo® polylactide production, *Industrial Biotechnology* 6 (2010) 212-224.
- 6 [354] R. Narayan, Carbon footprint of bioplastics using biocarbon content analysis and
7 life-cycle assessment, *MRS Bull.* 36 (2011) 716-721.
- 8 [355] S. Papong, P. Malakul, R. Trungkavashirakun, P. Wenunun, T. Chom-in, M.
9 Nithitanakul, E. Sarobol, Comparative assessment of the environmental profile of PLA
10 and PET drinking water bottles from a life cycle perspective, *J. Clean Prod.* 65 (2014)
11 539-550.
- 12 [356] M. Joo, N. Lewandowski, R. Auras, J. Harte, E. Almenar, Comparative shelf life
13 study of blackberry fruit in bio-based and petroleum-based containers under retail
14 storage conditions, *Food Chem.* 126 (2011) 1734-1740.
- 15 [357] F. Gironi, V. Piemonte, Life cycle assessment of polylactic acid and polyethylene
16 terephthalate bottles for drinking water, *Environ. Prog. Sustain. Energy* 30 (2011) 459-
17 468.
- 18 [358] U. Suwanmanee, T. Leejarkpai, Y. Rudeekit, T. Mungcharoen, Life cycle energy
19 consumption and greenhouse gas emissions of polylactic acid (PLA) and polystyrene
20 (PS) trays, *Nat. Sci.* 44 (2010) 703-716.
- 21 [359] N. Peelman, P. Ragaert, B. De Meulenaer, D. Adons, R. Peeters, L. Cardon, F.
22 Van Impe, F. Devlieghere, Application of bioplastics for food packaging, *Trends Food*
23 *Sci. Tech.* 32 (2013) 128-141.
- 24 [360] M. Carus, S. Piotrowski, Land use for bioplastics, *Bioplastics Magazine* 4 (2009)
25 4.

- 1 [361] V. Piemonte, F. Gironi, Land-use change emissions: How green are the
2 bioplastics?, Environ. Prog. Sustain. Energy 30 (2011) 685-691.
- 3 [362] M. Carus, Agricultural resources for bioplastics, in: Bioplastics Magazine 2011,
4 pp. 44-46.
- 5 [363] European Bioplastics. Bioplastics Facts and Figures. Available: [http://european-](http://european-bioplastics.org)
6 [bioplastics.org](http://european-bioplastics.org) Access date December 14th, 2015.

1 List of Figures

2 Figure 1 Number of research reports published since 1990 based on the Web of
3 Science search using keywords "PLA", "PLLA", "PDLA", "polylactic acid", "polylactide",
4 and "poly(lactic acid)" [7].

5 Figure 2 Chemical structure of L(+) and D(-) lactic acid.

6 Figure 3 The manufacturing processes to produce high molecular weight PLA, adapted
7 from Hartmann [17].

8 Figure 4 NatureWorks LLC commercial process for producing high molecular weight
9 PLA, adapted from Auras *et al.* [2] and Vink *et al.* [5].

10 Figure 5 Diastereomeric structures of lactide (3,6-dimethyl-1,4-dioxane-2,5-dione). T_m of
11 L-lactide, D-lactide, *meso*-lactide, and *rac*-lactide are 96, 96–97, 53, and 125 °C,
12 respectively, adapted from Vert *et al.* [18].

13 Figure 6 Major components of an injection molding machine showing the extruder
14 (reciprocal screw) and clamp units. "Reprinted from Progress in Polymer Science, 33,
15 Lim *et al.*, Processing technologies for poly (lactic acid), 820-852, Copyright (2008), with
16 permission from Elsevier" [1].

17 Figure 7 Injection stretch blow molding (ISBM) of PLA bottle. "Reprinted from Progress
18 in Polymer Science, 33, Lim *et al.*, Processing technologies for poly (lactic acid), 820-
19 852, Copyright (2008), with permission from Elsevier" [1].

1 Figure 8 Biaxial oriented extrusion cast film machine, adapted from “Reprinted from
2 Progress in Polymer Science, 33, Lim *et al.*, Processing technologies for poly (lactic
3 acid), 820-852, Copyright (2008), with permission from Elsevier” [1].

4 Figure 9 Production of a thermoforming part, reproduced “Reprinted from Progress in
5 Polymer Science, 33, Lim *et al.*, Processing technologies for poly (lactic acid), 820-852,
6 Copyright (2008), with permission from Elsevier” [1].

7 Figure 10 Schematic of microcellular foaming process: a) batch process, b) continuous
8 process; 1 to 6 are the main regions of the extruder; adapted from Matuana [64].

9 Figure 11 Schematic representation of melt spinning setup: (1) extruder drive, (2)
10 single-extruder - 24 to 36:1 L/D ratio, (3) hopper, (4) screw, (5) manifold, (6) static
11 mixer, (7) metering pump, (8) metering pump drive, (9) spin pack, (10) mesh filters, (11)
12 distributor, (12) spinneret, (13) cross-flow quench chamber, (14) freshly spun yarn, (15)
13 godet, (16) idler roller, (17) friction-driven winder, (18) yarn bobbin, adapted from
14 Agrawal [67].

15 Figure 12 Selected biodegradable and non-biodegradable blends of PLA polymers:
16 PLA-LDPE [89], PLA-LLDPE [90], PLLA-LLDPE [90-92], PLLA-HDPE [91], PLA-PS [93],
17 PLLA-PEVA [94], PLLA-EVOH [95], PLA-TPO [96], PLLA-ABS [97], PLLA-PIP [98],
18 PLA-PVOH [99], PLA-PHB [100] PLLA-PBS [101, 102], PLA-PBSA [103], PLA-PBAT
19 [104, 105], PLLA-PTAT [106], PLA-PAE [107], PLA-PU [108], PLA-PEG [109], PLA-SPI
20 [110], PLA-SPC [110], PLA-SF [111], PLA-TKGM [112], PLA-Chitosan [83, 113],
21 PDLLA-Chitosan [114], PLLA-Chitosan [114], PLLA-PBSL [115], PLLA-PEO [116],
22 PLLA-PCL [117-119], PDLLA-PCL [117], PLA-PCL [120], PLA-Starch [121-124], PLA-

1 PHBHxx [125], PLA-PPC [126], PLA-PP [127], PLA-PC [128], PLA-PGS [129], PLA-PTT
2 [130], and PLA-EGMA [131].

3 Figure 13 Average scale dimensions of selected fillers in PLA composites: MMT
4 (montmorillonite) [168], CNT (carbon nanotube) [169], Ag [170], sisal [171], wood [168,
5 172, 173], MCC (microcrystalline cellulose) [174], sepiolite [168], cotton [175, 176],
6 ramie [177, 178], MWCNT (multiwall carbon nanotube), graphene, algal [179, 180],
7 tunicin [181], halloysite [148], talc3 [182], CaCO₃ [183], talc2 [182], CaSO₄ [184], talc1
8 [182], glass fiber [185, 186], abaca fiber [187], jute fiber [187], cotton fiber [187], hemp
9 fiber [187], and flax fiber [186, 188].

10 Figure 14 (left) tomato plots covered with mulch films; (right) high tunnel or
11 overwintering house.

12 Figure 15 Cradle to gate, grave, and cradle life cycle flowchart of plastic mulch films.
13 After removal of conventional mulch films, they can be reused, recycled, incinerated,
14 and/or landfilled. Biodegradable mulch provides the same end-of-life scenario routes
15 and also can be composted.

16 Figure 16 Hydrolytic chain cleavage mechanisms of PLA in alkaline (a) and acidic (b)
17 media. "Reprinted from Polymer, 42, Jong *et al.*, New insights into the hydrolytic
18 degradation of poly(lactic acid): participation of the alcohol terminus, 2795-2802,
19 Copyright (2001), with permission from Elsevier" [257].

20 Figure 17 Ln (M_n) as a function of time during hydrolysis of PLA films into water, 95%
21 ethanol, or 50% ethanol at 40 °C.

1 Figure 18 Thermodegradation mechanisms of PLA. "Reprinted from: Poly(lactic acid).
2 Synthesis, structure, properties, processing, and applications, Nishida, Thermal
3 degradation, 401-412, Copyright (2010), with permission from John Wiley & Sons, Inc."
4 [286].

5 Figure 19 Photodegradation of PLA via Norish II mechanism, adapted from Tsuji *et al.*
6 [302].

7 Figure 20 Mechanisms of photodegradation of PLA, adapted from Janokar *et al.* [303].

8 Figure 21 Radicals generated during photodegradation of PLA from cleavage of C-C
9 bonds, adapted from Copinet *et al.* [263].

10 Figure 22 Radicals generated during photodegradation of PLA (a) from C-O and (b)
11 ester bond cleavage, adapted from Copinet *et al.* [263].

12 Figure 23 Diagram of solid waste management, adapted from the U.S. Environmental
13 Protection Agency in Advancing Sustainable Materials Management [314].

14 Figure 24 Large-scale commercial composting process. "Reprinted from Polymer
15 International, 57, Kijchavengkul *et al.*, Compostability of polymers, 793-804, Copyright
16 (2008), with permission from Wiley" [329].

17 Figure 25 Schematic of polymer biodegradation mechanism, adapted from Leejarkpai *et*
18 *al.* [332].

19 Figure 26 a) Amount of CO₂ evolved from blank, cellulose, and PLA film; b) Percentage
20 mineralization of cellulose and PLA film.

Figure 27 Calorific values of selected materials, adapted from Laußmann *et al.* [340].

Figure 28 Cradle-to-gate, cradle-to-grave, and cradle-to-cradle representations of production, consumption, and disposal of bio-based polymers from renewable resource via composting. "Reprinted from Polymer International, 57, Kijchavengkul *et al.*, Compostability of polymers, 793-804, Copyright (2008), with permission from Wiley" [329].

Figure 29 Carbon cycle of fossil-based polymers and bio-based polymers. Renewable resource pathway (green arrows); fossil resource pathway (black arrows); and pathway for both renewable and fossil resources (gray arrow), adapted from Kijchavengkul *et al.* [329].

Figure 30 GWP, primary energy of non-renewable resources expressed as higher heating values (HHV), and net water uptake for the production system of Ingeo™ resin, adapted from Vink and Davies [5].

Figure 31 Climate change, non-renewable energy, water depletion for 1 kg of PLA and other commercial polymers as available in Ecoinvent 3.2 and reported using Simapro 8.0.5 with Recipe (E) Midpoint Indicator considering the World as the geographical region, and Ingeo™ adapted from Vink and Davies [5].

Figure 32 PLA life cycle and boundary of the studied system. Adapted from Rossi *et al.* [315].

Figure 33 Comparison of dynamically-assessed global warming impacts over 100 years associated with the six end-of-life treatments for PLA. The bars on the left side present

1 production impacts of the resin (cradle-to-gate) for comparison purposes, adapted from
2 Rossi *et al.* [315].

3 Figure 34 Comparison of end-of-life options for PLA for each midpoint category,
4 adapted from Rossi *et al.* [315].

5

Figure 1

Figure 2

(*S*)-Lactic acid
L-(+)-Lactic acid

(*R*)-Lactic acid
D-(-)-Lactic acid

Figure 3

Figure 4

Figure 5

(S-S)-lactide
"L-lactide"

(R-R)-lactide
"D-lactide"

(S-R)-lactide
"meso-lactide"

50:50 mix = rac-lactide

Figure 6

Figure 7

Figure 8

Figure 9

Figure 10

Figure 11

Figure 12

Figure 13

Figure 14

Figure 15

Figure 16

Lactic Acid Oligomer DP 7

Lactic Acid Oligomer DP 5

Lactide

Lactic Acid

(a)

Lactic Acid Oligomer DP7

Lactic Acid Oligomer DP6

Lactic Acid

(b)

Figure 17

Figure 18

Figure 19

Figure 20

(a)

(b)

Figure 21

Figure 22

(a)

(b)

Figure 23
Changes in package design Changes in purchasing habits Changes in industrial practices Recovery for recycling (including composting)

Figure 24

Figure 25

Figure 26

Figure 27

Figure 28

Figure 29

Figure 30

Figure 31

Figure 32

Figure 33

Figure 34