1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Optical and electrical properties of pressureless sintered transparent

(K_{0.37}Na_{0.63})NbO₃-based ceramics

Dong Yang, Chao Ma, Zupei Yang[†], Lingling Wei, Xiaolian Chao,

Zhenyu Yang, Jinglun Yang

Key Laboratory for Macromolecular Science of Shaanxi Province

School of Materials Science and Engineering, Shaanxi Normal University, Xi'an, 710062, Shaanxi,

P. R. China

Corresponding author:

Key Laboratory for Macromolecular Science of Shaanxi Province

School of Materials Science and Engineering

Shaanxi Normal University, Xi'an, 710062, Shaanxi, P. R. China

Tel: +86-29-8153-0718; Fax: +86-29-8153-0702

E-mail address: yangzp@snnu.edu.cn

Abstract

Lead-free $(1-x)(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3-x\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ($x=0.050, 0.070, 0.090, 0.095$ and 0.100) transparent ferroelectric ceramics have been fabricated by pressureless sintering procedure. Transmittance of $0.91(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3-0.09\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ceramics sintered in sealed alumina crucible was 15% higher than those sintered unsealed in air. By increasing the content of $\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$, the phase structure of $(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ ceramics transformed from orthorhombic to tetragonal symmetry first and then to pseudo cubic symmetry. The $0.91(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3-0.09\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ceramics exhibited high density (98%), high transmittance (60%) in the near-IR region and relatively good electrical properties ($\epsilon_r = 1914$, $\tan\delta = 0.037$, $T_c = 147^\circ\text{C}$, $P_r = 6.88 \mu\text{C}/\text{cm}^2$, $E_c = 8.49 \text{ kV}/\text{cm}$). Meanwhile, the introduction of $\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ induced a composition fluctuation in the $(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ lattice and made the ceramics more relaxor-like, which would lead to a further reduction of light scattering. These results demonstrated that $0.91(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3-0.09\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ could be promising lead-free transparent ferroelectric ceramics.

Keywords: Ceramics; X-ray diffraction; Ferroelectrics; Optical properties; Relaxors

1. Introduction

Transparent ferroelectric ceramics are unique because of their high transparency and electro-optic effect (EO) under an electric field [1-4]. Unlike single crystals (e.g. LiNbO_3) [5], polycrystalline transparent ceramics could be produced at low cost following well-developed technologies [6, 7]. For example, $(\text{Pb, La})(\text{Zr, Ti})\text{O}_3$ (PLZT) ceramics showed a high photoelectric effect, and $[\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3]$ - $[\text{PbTiO}_3]$ (PMN-PT) is most suitable for almost all of visible lights to mid-IR optical applications [8-10]. However, PLZT and PMN-PT exhibit some disadvantages that restrict their further development for electronic devices. These include a poor hysteresis response to electric fields, aging and fatigue, and reduction of the driving voltage [11]. In addition, both PLZT and PMN-PT ceramics contain lead, which is harmful to environment [12, 13]. Therefore, it is desirable to develop lead-free transparent ceramics.

In recent years, sodium potassium niobate (KNN) polycrystalline ceramics have been studied as a promising substitute for the lead-zirconate-titanate (PZT) ferroelectric materials because of their high piezoelectric constant and outstanding electrical properties [14-22]. Du [23] *et al.* observed a transparent phenomenon in the $0.96(\text{K}_{0.5}\text{Na}_{0.5})\text{NbO}_3$ - $0.04(\text{Bi}_{0.5}\text{Na}_{0.5})\text{TiO}_3$ ceramics, but the influencing factors on optical properties of the ceramics were not discussed. Chan [24] *et al.* employed a sol-gel method and hot-pressing sintering to prepare $(\text{K}_{0.5}\text{Na}_{0.5})_{0.95}\text{Li}_{0.05}\text{Nb}_{0.95}\text{Bi}_{0.05}\text{O}_3$ transparent ceramics with optical transmittance reaching 60 % in the near-IR region. However, the high cost of hot-pressing sintering is not adaptable to industrial applications.

Phase structures with high symmetry and high density are necessary for preparing transparent ceramics [25]. Cubic Sc_2O_3 shows excellent optical properties (high bulk refractive index $n_H = 2.0$ when $\lambda = 300$ nm, and high band gap $E_g = 5.7$ eV) [26], These properties allow Sc_2O_3 to be an

alternative material to improve the optical properties of KNN ceramics. In addition, the ionic of Ca^{2+} (1.34Å, CN = 12) is smaller than those of K^+ (1.64Å, CN = 12) and Na^+ (1.39Å, CN = 12). The ionic radius of Sc^{3+} (0.75Å, CN = 6) is larger than that of Nb^{5+} (0.64 Å, CN = 6). The unbalanced valence and different radii of Ca^{2+} , K^+ , Na^+ , Sc^{3+} , and Nb^{5+} may induce some structure transformation in orthorhombic $(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ through introducing $\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$. In addition to possible structural transformations, potential varieties in optical and electrical properties are also of key research interest.

In this study, transparent $(1-x)(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ - $x\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ceramics were prepared by using pressureless sintering in sealed alumina crucibles. The effects of $\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ on structure, transparency, dielectric, ferroelectric and piezoelectric properties of the $(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ ceramics were investigated.

2. Experimental

$(1-x)(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3$ - $x\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ($0.050 \leq x \leq 0.100$) ($(1-x)\text{KNN}$ - $x\text{CSN}$) powders were synthesized by using solid state reaction.. Powers of Na_2CO_3 , K_2CO_3 , CaCO_3 , Nb_2O_5 and Sc_2O_3 were ball-milled for 24 h using zirconia balls in ethanol media. The dried slurries were calcined at 950 °C for 5 h. After re-milling for 12 h, the calcined powders were mixed with 5 wt% solution of polyvinyl alcohol (PVA) and then pressed at 300 MPa into 15 mm diameter pellets. After burning off the PVA, the pellets were sintered at 1220 °C for 4 h in a sealed alumina crucible containing the calcined powders (denoted as sealed). Pellets were also sintered at 1220 °C for 4 h in air (denoted as unsealed)

Phase structure characterization was performed by using X-ray diffraction (XRD, MiniFlex600, Rigaku, Tokyo, Japan, $\text{CuK}\alpha$). Density was measured following the Archimedes method using

distilled water. The fracture surface microstructure was observed by using scanning electron microscopy (SEM, SU 8020, Hitachi Company, Tokyo, Japan). Energy dispersive X-ray spectroscopy (EDS) attached to the SEM was used to analyze the chemical compositions of the fracture surface.

The samples were polished to 0.5 mm thickness. To obtain flatter surfaces, selected samples were additionally polished using a diamond slurry with a particle size of 0.5 μm . The optical transmission spectrum from 200 to 2000 nm was measured by using ultraviolet-visible-near infrared (UV-vis-NIR) spectroscopy (UV-3600; Shimadzu, Kyoto, Japan). For electrical measurements, silver paste was coated on both surfaces and heated at 840 $^{\circ}\text{C}$. Dielectric properties were measured at 1, 10, 100 and 1 MHz using an impedance analyzer (E4980A; Agilent Technologies, Santa Clara, California, USA) in a temperature range from -200 $^{\circ}\text{C}$ to 500 $^{\circ}\text{C}$. The samples were polarized in silicone oil at 3 kV/mm for 25 min at 80 $^{\circ}\text{C}$. the piezoelectric coefficient (d_{33}) was recorded from 1-day-aged samples using a quasistatic piezoelectric d_{33} meter (ZJ-3d, Institute of Acoustics Academic Sinica, Beijing, China). Room-temperature polarization-electric field (P-E) loops were measured at 1 Hz by using a ferroelectric tester.

3. Results and discussion

The $0.91(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3\text{-}0.09\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ (KNN-CSN9) ceramics were pressurelessly sintered at 1220 $^{\circ}\text{C}$ for 4 h in either sealed (denoted as KNN-CSN9-Sealed) or unsealed (denoted as KNN-CSN9-Unsealed) alumina crucibles.

Fig. 1 (a) shows XRD patterns of the KNN-CSN9 ceramics. Both samples show a pure perovskite phase structure with no observed impurity phases. Crystal lattice and lattice parameters (a , b and c) have been calculated from XRD data using the least square method and are summarized in

Table 1. No significant differences in lattice parameters are observed and the values of a/c are close to 1 for both samples. This suggests that the phase structure of the two KNN-CSN9 samples is pseudo cubic.

Fig. 1 (b, c) shows the transparent properties of the KNN-CSN9 ceramics. Fig. 1 (b) shows that a clear image can be observed through the KNN-CSN9-Sealed ceramic, suggesting a higher transparency. According to Fig. 1(c), the transmittance (T) is 60% and 45% at 1064 nm for the KNN-CSN9-Sealed sample and the KNN-CSN9-Unsealed sample, respectively. The transmittance difference between two samples is about 15% (Table. 1). The relative density (RD) of the KNN-CSN9-Sealed sample is 98%, which is higher than that of the KNN-CSN9-Unsealed sample (95%). The difference in transmittance between the two samples can be attributed to the heterogeneous density with less light scattering in the sealed ceramics. The relatively lower density of the KNN-CSN9-Unsealed sample may be due to the loss of K^+ and Na^+ ions during the sintering process [27]. However, sintering in the sealed alumina crucibles should prevent the loss of K^+ and Na^+ .

Fig. 2 (a, b) shows SEM images of fracture surface for the KNN-CSN9 samples. Grains of about 1 μm with clear grain boundaries are observed in the KNN-CSN9-Sealed sample. The KNN-CSN9-Sealed sample also shows low porosity and a high density. A high density with fewer pores is beneficial for transmittance as the scattering of incident light is reduced. The KNN-CSN9-Unsealed sample exhibits a blurry surface of grains and grain boundaries, which may be attributed to the loss of K^+ and Na^+ . EDS data (Fig. 2(c and d)) shows the different K^+ and Na^+ contents in the two samples. The element molar ratio of the KNN-CSN9-Sealed sample is K:Na:Nb = 0.27:0.57:1.00 (Fig. 2(c)). This is nearer to the stoichiometric ratio (K:Na:Nb = 0.35:0.60:1.00) and

1 higher than that of the KNN-CSN9-Unsealed sample (K:Na:Nb = 0.17:0.31:1.00) (Fig. 2(d)). This
2
3 demonstrates that the sealed sintering procedure is an effective approach to prevent the loss of K^+ and
4
5 Na^+ .
6
7

8
9 Fig. 3 (a) shows the dielectric constant and dielectric loss measured at 1 MHz from 40 °C to
10
11 500 °C of the KNN-CSN9 samples. The maximum dielectric constant (ϵ_{max}) of the
12
13 KNN-CSN9-Sealed ceramic is 3279, which is higher than that of the KNN-CSN9-Unsealed ceramic
14
15 (2752) (Table 1). Polarization-electric field (P - E) hysteresis loops of the KNN-CSN9 ceramics
16
17 measured at 1 Hz at 30 kV/cm and near room temperature are shown in Fig. 3 (b). Both samples
18
19 exhibit a typical ferroelectric polarization hysteresis loop. The KNN-CSN9-Sealed ceramic shows a
20
21 higher remnant polarization P_r of 6.88 $\mu C/cm^2$ and a lower coercive field E_c of 8.49 kV/cm than the
22
23 KNN-CSN9-Unsealed sample. The KNN-CSN9-Sealed ceramic exhibits higher piezoelectric
24
25 constant $d_{33} = 35$ pC/N than the KNN-CSN9-Unsealed ceramic ($d_{33} = 15$ pC/N). The better electrical
26
27 properties of the KNN-CSN-Sealed ceramic can be attributed to its less defect and higher density.
28
29
30
31
32
33
34
35

36 Fig. 4 (a and b) shows XRD patterns of the $(1-x)KNN-xCSN$ ceramics with different CSN
37
38 contents. All samples exhibit a pure perovskite structure. Fig. 4 (b) plots fine scanning XRD
39
40 patterns in the 2θ range from 44° to 47° for all samples. Two diffraction peaks $(200)_O$ and $(020)_O$ at
41
42 45-47° are observed when $x = 0.050$. When $x = 0.070$, the diffraction peaks change to $(002)_T$ and
43
44 $(200)_T$, only one peak (200) is observed, suggesting that the structure of the $(1-x)KNN-xCSN$
45
46 ceramics has transformed firstly from orthorhombic to tetragonal symmetry and then to a pseudo
47
48 cubic symmetry. This may be attributed to the replacement of the octahedral center Nb^{5+} (0.64 Å) by
49
50 Sc^{3+} (0.75 Å), expanding of oxygen octahedral, and the replacement of K^+ (1.64Å) and Na^+ (1.39Å)
51
52 by Ca^{2+} (1.34Å).
53
54
55
56
57
58
59
60
61
62
63
64
65

To further confirm the effect of CSN content on the crystal lattice, lattice parameters of a , b , c and the ratio of a/c were calculated from the XRD data using the least square method (Table 2). With increasing content of CSN, the value of a/c varied from 1.0434 to 0.9900. This suggests that a phase transformation occurs from an orthorhombic to a pseudo cubic. The pseudo cubic phase structure at $0.090 \leq x \leq 0.100$ eliminates the optical scattering, similar to that observed in $\text{Pb}_{0.91}\text{La}_{0.09}(\text{Zr}_{0.65}\text{Ti}_{0.35})\text{O}_3$ ceramics [1]. The cubic-like structure can reduce the birefringence, and leads to higher light transmittance. In addition, with increasing content of CSN, the RD of the $(1-x)\text{KNN}-x\text{CSN}$ ceramics increases when $x \leq 0.090$ and then decreases when $x > 0.090$. The maximum RD of the $(1-x)\text{KNN}-x\text{CSN}$ ceramics is 98% when $x = 0.090$. These results indicate that CSN has a positive effect on the densification of the samples.

The optical properties of the $(1-x)\text{KNN}-x\text{CSN}$ ceramics are shown in Fig. 5. As observed in Fig. 5 (a), as x is increased from 0.050 to 0.100, the optical transparency initially increases and then decreases. When $x = 0.090$, the sample shows the maximum transmittance. This is in accordance with the RD results. From the results shown in Table 2 and Fig. 5 (a), it can be stated that with a higher structural symmetry and higher ceramic density, then the greater transmittance is achieved. Fig. 5 (b) shows the optical transmittance spectrum of the $(1-x)\text{KNN}-x\text{CSN}$ ceramics measured from 200-2000 nm. The $(1-x)\text{KNN}-x\text{CSN}$ ceramics show excellent optical performance above 780 nm. The $(1-x)\text{KNN}-x\text{CSN}$ ceramics with $x = 0.090$ also has a superior transmittance, as shown in Fig. 5 (c). The transmittance of 60% for KNN-CSN9 ceramic at 1064 nm could be used in Nd:YAG solid lasers applications.

A strong absorption is also observed in the near ultraviolet light (390 nm) due to the transition of electrons from the valance band to the conduction band. According to the Tauc equation, the

optical band gap energy (E_g) can be estimated from the absorption spectra [28, 29]. For a direct transition, the relationship between E_g and the absorption coefficient α is given by:

$$(\alpha h\nu)^2 = A(h\nu - E_g) , \quad (1)$$

where ν is the photon frequency, h is Planck's constant and A is a constant. The absorption coefficient can be calculated from the transmittance (T) by

$$\alpha = \frac{1}{t} \ln \left(\frac{1}{T} \right) \quad (2)$$

where t is the thickness of the sample. Therefore, E_g was determined for the (1- x)KNN- x CSN ceramics by plotting $(\alpha h\nu)^2$ versus $h\nu$ and extrapolating the linear portion of the curve to zero, as shown in Fig. 6 (a-e). The calculated E_g of the (1- x)KNN- x CSN ceramics (when $x = 0.050, 0.070, 0.090, 0.095$ and 0.100) is 2.96 eV, 3.02 eV, 3.04 eV, 3.00 eV and 2.96 eV, respectively. Fig. 6 (f) shows the E_g of the (1- x)KNN- x CSN ceramics with x . The highest $E_g = 3.04$ eV of the KNN-CSN9 ceramic is in good agreement to the previously reported value (3.09 eV) of for the highest transmittance in $(K_{0.5}Na_{0.5})_{0.95}Li_{0.05}Nb_{0.95}Bi_{0.05}O_3$ transparent ceramic [24]. This suggests that the band gap of the $0.91(K_{0.37}Na_{0.63})NbO_3$ - $0.09Ca(Sc_{0.5}Nb_{0.5})O_3$ ceramic corresponds to the transition from the top of the valence bands occupied by O_{2p} electron state to the bottom of the conduction bands which is dominated by the empty Nb_{4d} electron state.

Fig. 7 (a-e) shows the temperature dependence of dielectric permittivity and dielectric loss of the (1- x)KNN- x CSN ceramics at different frequencies measured from -200 to 500 °C. A phase transition of orthorhombic-tetragonal (T_{O-T}) is observed in Fig. 7 (a) at about 150 °C. In Fig. 7 (b), the phase transition, at about 0 °C, of T_{O-T} cannot be observed in the KNN-CSN7 ceramic. The phase transition of T_{O-T} then completely disappears in the KNN-CSN9 ceramic, as shown in Fig. 7 (c). This implies that the structure changes to the pseudo cubic phase. A similar phenomenon has also been

observed by Yang [30] *et al.* who added Ta to $(\text{K}_{0.44}\text{Na}_{0.52}\text{Li}_{0.04})(\text{Nb}_{0.96}\text{Sb}_{0.04})\text{O}_3$. The dielectric constant is also seen to decrease slightly with increasing frequency. This phenomenon implies that the ceramics are relaxor-like. With increasing content of CSN the Curie temperature (T_c) decreases from 285 °C to 124 °C. In addition, the ϵ_{max} initially increases and then decreases with increasing CSN content. The KNN-CSN9 has the highest ϵ_{max} value(3279) and has a T_c of 147 °C.

It is well known that above Curie temperature, the dielectric permittivity of a normal ferroelectric should obey the Curie-Weiss law:

$$\epsilon = \frac{C}{T - T_{CW}} \quad , \quad (3)$$

$$\Delta T_m = T_B - T_m \quad , \quad (4)$$

$$\frac{1}{\epsilon} - \frac{1}{\epsilon_m} = \frac{(T - T_m)^\gamma}{C} \quad , \quad (5)$$

where C is the Curie-Weiss constant, T_{CW} is the Curie-Weiss temperature, T_B is the Burns' temperature (determined from the inverse dielectric permittivity [31]), T_m is the temperature of the maximum dielectric permittivity and γ is a diffusion coefficient [32]. Normal ferroelectrics, relaxor-like ferroelectrics and ideal relaxor ferroelectrics are identified when $\gamma=1$, $1 < \gamma < 2$, and $\gamma=2$ respectively. Plots of inverse dielectric permittivity versus temperature at 1 MHz are shown in Fig. 8 (a-e) and are used to obtain the value of T_{CW} . It is found that with increasing CSN content. the dielectric permittivity of the $(1-x)\text{KNN}-x\text{CSN}$ ceramics deviates from the Curie-Weiss law. An increase in ΔT_m is observed with increasing x , and a maximum value of 161 °C is obtained when $x = 0.090$ (Table 3.). This indicates that the relaxor behavior is enhanced with increasing CSN content.

Fig. 8 (f) shows the plots of $\log(1/\epsilon - 1/\epsilon_m)$ as a function of $\log(T - T_m)$ at 1 MHz for the $(1-x)\text{KNN}-x\text{CSN}$ ceramics. A linear relationship is observed for all samples. The slope of the fitting curve is used to determine the γ value, and can be used to confirm the effect of the CSN content on the

relaxor behavior of the (1- x)KNN- x CSN ceramics. The γ value increases from 1.68 to 1.85 with increasing CSN content. The fitting results obtained by the Curie-Weiss law are listed in Table 3. The result demonstrates that the (1- x)KNN- x CSN ceramics exhibit relaxor behavior. The relaxational behavior in relaxor ferroelectrics can be explained by the composition fluctuation theory [33, 34]. Because of their large ionic radii, Na⁺(1.39 Å), K⁺(1.64 Å) and Ca²⁺(1.34 Å) in the (1- x)KNN- x CSN ceramics occupy the A site of ABO₃ perovskite structure. Ca²⁺ possesses a different valence and ionic radius to Na⁺ and K⁺, resulting in the formation of local electric fields. These local structure distortions cause local charge imbalance and local elastic fields. Similar phenomenon also occurs at the B site of the ABO₃ perovskite structure, where Nb⁵⁺(0.64 Å) and Sc³⁺(0.75 Å) exhibit different valences and ionic radii. These models are based on the local distortion of the crystal structure, leading to the composition fluctuation, and resulting in the relaxor behavior.

Fig. 9 (a and b) shows polarization-electric field (P - E) hysteresis loops of the (1- x)KNN- x CSN ceramics measured at 1 Hz at 30 kV/cm near room temperature. The KNN-CSN5 ceramic exhibits a typical hysteresis loop with a coercive field (E_c) of 10.97 kV/cm and remnant polarization (P_r) of 9.39 $\mu\text{C}/\text{cm}^2$. With increasing CSN content, E_c and P_r decrease slowly when $0.050 \leq x \leq 0.090$. A more rapid decrease is then observed when $0.090 < x \leq 0.100$ (Fig. 9 (b)), which may be attributed to the composition fluctuation. Fig. 9 (c) shows piezoelectric constants d_{33} of the (1- x)KNN- x CSN ceramics. For all samples, d_{33} decreases slowly when $x \leq 0.090$ and decreases more rapidly when $0.090 < x \leq 0.100$. The highest piezoelectric coefficient is 52 pC/N for KNN-CSN5. The decrease in d_{33} can be attributed to the composition fluctuation and the structure transformation.

4. Conclusions

Lead-free transparent $(1-x)\text{KNN}-x\text{CSN}$ ceramics with remarkable optical transparency were prepared by using a pressureless sintering method. The presence of CSN induced phase transformations from an orthorhombic to a pseudo cubic symmetry, via a tetragonal phase. This transition might reduce optical anisotropy and enhance the optical transparency of the ceramics. The introduction of Ca^{2+} and Sc^{3+} induced a composition fluctuation, making the ceramics more relaxor-like. This resulted in the elimination of light scattering due to the presence of the pseudo cubic phase with high symmetry. Of all samples, KNN-CSN9 ceramics showed the highest density (98%), greatest transmittance (60%) in the near-IR region, and relatively good electrical properties ($\epsilon_r = 1914$, $\tan\delta = 0.037$, $T_c = 147\text{ }^\circ\text{C}$, $P_r = 6.88\text{ }\mu\text{C}/\text{cm}^2$, $E_c = 8.49\text{ kV}/\text{cm}$). These results demonstrate that the $0.91(\text{K}_{0.37}\text{Na}_{0.63})\text{NbO}_3\text{-}0.09\text{Ca}(\text{Sc}_{0.5}\text{Nb}_{0.5})\text{O}_3$ ceramic could be promising lead-free transparent ferroelectric ceramics.

Acknowledgments

This work has been supported by the National Science Foundation of China (NSFC) (Grant No.51572163, 51577111, 51172136, 21401123 and 51107077), the Fundamental Research Funds for the Central Universities (Program No.GK201403006, No.GK201402061, No.GK201301002, GK201101003 and GK201101004), Innovation Funds of Graduate Programs, Shaanxi Normal University (Grant No.X2014YB05), Scientific and Technology Research Project in Xi'an [Program No. CXY1342(4)].

References

- [1] J. G. Wu, D. Q. Xiao, J. G. Zhu, Potassium-sodium niobate lead-free piezoelectric materials: past, present, and future of phase boundaries, *Chem. Rev.* 115 (2015) 2559-2595.
- [2] X. P. Wang, J. G. Wu, D. Q. Xiao, J. G. Zhu, X. J. Cheng, T. Zheng, B. Y. Zhang, X. J. Lou, X. J. Wang, Giant piezoelectricity in potassium-sodium niobate lead-free ceramics, *J. Am. Chem. Soc.* 136 (2014) 2905-2910.
- [3] S. F. Wang, J. Zhang, D. W. Luo, F. Gu, D. Y. Tang, Z. L. Dong, G. E. B. Tan, W. X. Que, T. S. Zhang, S. Li, L.B. Kong, Transparent **ceramics**: processing, materials and applications, *Prog. Solid. State. Chem.* 41 (2013) 20-54.
- [4] A. Krell, J. Klimke, T. Hutzler, Transparent compact ceramics: **inherent** physical issues, *Opt. Mater.* 31 (2009) 1144-1150.
- [5] R. V. A. Murthy, K. S. Bartwal, K. Lal, Growth of nearly perfect LiNbO_3 single crystals, *Mater. Sci. Eng. B* 18 (1993) L4-L6.
- [6] R. Johnson, P. Biswas, P. Ramavath, R. S. Kumar, G. Padmanabham, Transparent polycrystalline ceramics: an overview, *Trans. Indian Ceram. Soc.* 71 (2012) 73-85.
- [7] S. Tanaka, T. Takahashi, K. Uematsu, Fabrication of transparent crystal-oriented polycrystalline strontium barium niobate ceramics for electro-optical application, *J. Eur. Ceram. Soc.* 34 (2014) 3723-3728.
- [8] G. H. Haertling, C. E. Land, Recent improvements in the optical and electrooptic properties of **PLZT** ceramics, *Ferroelectrics* 3 (1972) 269-280.
- [9] G. S. Snow, Fabrication of transparent electrooptic PLZT ceramics by atmosphere sintering, *J. Am. Ceram. Soc.* 56 (1973) 91-96.

- [10] K. K. Li, Y. Lu, W. Wang, Electro-optic ceramic material and device, U.S. Patent 6, 890, 874, 2005.
- [11] A. Sternberg, Transparent ferroelectric ceramics: properties and applications, Ferroelectrics 91 (1989) 53-67.
- [12] G. H. Haertling, Ferroelectric ceramics: history and technology, J. Am. Ceram. Soc. 82 (1999) 797-818.
- [13] P. K. Panda, Review: environmental friendly lead-free piezoelectric materials, J. Mater. Sci. 44 (2009) 5049-5062.
- [14] Y. Saito, H. Takao, T. Tani, T. Nonoyama, K. Takatori, T. Homma, T. Nagaya, M. Nakamura, Lead-free piezoceramics, Nature 432 (2004) 84-87.
- [15] M. Ichikia, L. Zhang, M. Tanaka, R. Maeda, Electrical properties of piezoelectric sodium-potassium niobate, J. Eur. Ceram. Soc. 24 (2004) 1693-1697.
- [16] J. Rödel, W. Jo, K. T. P. Seifert, E. M. Anton, T. Granzow, D. Damjanovic, Perspective on the development of lead-free piezoceramics, J. Am. Ceram. Soc. 92 (2009) 1153-1177.
- [17] Y. F. Chang, Z. P. Yang, Y. T. Hou, Z. H. Liu, Z. L. Wang, Effects of Li content on the phase structure and electrical properties of lead-free $(K_{0.46-x/2}Na_{0.54-x/2}Li_x)(Nb_{0.76}Ta_{0.20}Sb_{0.04})O_3$ ceramics, Appl. Phys. Lett. 90 (2007) 232905.
- [18] Y. F. Chang, Z. P. Yang, L. R. Xiong, Z. H. Liu, Z. L. Wang, Phase structure, microstructure, and electrical properties of Sb-modified (K, Na, Li)(Nb, Ta)O₃ piezoelectric ceramics, J. Am. Ceram. Soc. 91 (2008) 2211-2216.
- [19] J. F. Li, K. Wang, F. Y. Zhu, L. Q. Cheng, F. Z. Yao, (K, Na) NbO₃-based lead-free piezoceramics: fundamental aspects, processing technologies, and remaining challenges, J. Am.

Ceram. Soc. 96 (2013) 3677-3696.

- [20] X. P. Wang, J. G. Wu, D. Q. Xiao, X. J. Cheng, T. Zheng, B. Y. Zhang, X. J. Lou, J. G. Zhu, Large d_{33} in (K, Na)(Nb, Ta, Sb)O₃-(Bi, Na, K)ZrO₃ lead-free ceramics, J. Mater. Chem. A 2 (2014) 4122-4126.
- [21] J. G. Wu, J. Q. Xiao, T. Zheng, X. P. Wang, X. J. Cheng, B. Y. Zhang, D. Q. Xiao, J. G. Zhu, Giant piezoelectricity of (K, Na)(Nb, Sb)O₃-(Bi, Na, K, Pb)ZrO₃ ceramics with rhombohedral-tetragonal (RT) phase boundary, Scripta Mater. 88 (2014) 41-44.
- [22] X. P. Wang, J. G. Wu, D. Q. Xiao, J. G. Zhu, X. J. Cheng, T. Zheng, B. Y. Zhang, X. J. Lou, X. J. Wang, Giant piezoelectricity in potassium-sodium niobate lead-free ceramics, J. Am. Chem. Soc. 136 (2014) 2905-2910.
- [23] H. L. Du, W. C. Zhou, D. M. Zhu, L. Fa, S. B. Qu, Y. Li, Z. B. Pei, Sintering characteristic, microstructure, and dielectric relaxor behavior of (K_{0.5}Na_{0.5})NbO₃-(Bi_{0.5}Na_{0.5})TiO₃ lead-free ceramics, J. Am. Ceram. Soc. 91 (2008) 2903-2909.
- [24] F. L. Li, K. W. Kwok, Fabrication of transparent electro-optic (K_{0.5}Na_{0.5})_{1-x}Li_xNb_{1-x}Bi_xO₃ lead-free ceramics, J. Eur. Ceram. Soc. 33 (2013) 123-130.
- [25] G. R. Li, W. Ruan, J. T. Zeng, H. R. Zeng, L. Y. Zheng, L. S. Kamzina, Y. Kopylov, V. Kravchenko, The effect of domain structures on the transparency of PMN-PT transparent ceramics, Opt. Mater. 35 (2013) 722-726.
- [26] Y. Wang, B. Lu, X. Sun, T. Sun, H. Xu, Synthesis of nanocrystalline Sc₂O₃ powder and fabrication of transparent Sc₂O₃ ceramics, Adv. Appl. Ceram. 110 (2011) 95-98.
- [27] Q. Zhang, B. P. Zhang, H. T. Li, P. P. Shang, Effects of Na/K ratio on the phase structure and electrical properties of Na_xK_{1-x}NbO₃ lead-free piezoelectric ceramics, Rare Metals 29 (2010)

220-225.

- [28] A. El-Korashy, A. A. El-Fadl, Temperature dependence of the optical band gap of nearly perfect K_2ZnCl_4 single crystals in the ferroelectric phase, *Physica B* 271 (1999) 205-211.
- [29] Z. Wang, H. S. Gu, Y. M. Hu, K. Yang, M. Z. Hu, D. Zhou, J. G. Guan, Synthesis, growth mechanism and optical properties of (K, Na)NbO₃ nanostructures, *CrystEngComm* 12 (2010) 3157-3162.
- [30] Z. P. Yang, Y. F. Chang, L. L. Wei, Phase transitional behavior and electrical properties of lead-free (K_{0.44}Na_{0.52}Li_{0.04})(Nb_{0.96-x}Ta_xSb_{0.04}), *Appl. Phys. Lett.* 90 (2007) 042911.
- [31] C. J. Stringer, T. R. Shout, C. A. Randall, High-temperature perovskite relaxor ferroelectrics: A comparative study, *J. Appl. Phys.* 101 (2007) 054107.
- [32] K. Uchino, S. Nomura, Critical exponents of the dielectric constants in diffused-phase-transition crystals, *Ferroelectrics* 44 (1982) 55.
- [33] I. W. Chen, Structural origin of relaxor ferroelectrics-revisited, *J. Phys. Chem. Sol.* 61 (2000) 197-208.
- [34] A. A. Bokov, Z. G. Ye, Recent progress in relaxor ferroelectrics with perovskite structure, *J. Mater. Sci.* 41 (2006) 31-52.

Figure captions

Fig. 1. (a) XRD patterns, (b) photograph and (c) optical transmission characteristics of the KNN-CSN9 ceramics.

Fig. 2. SEM micrographs of fracture surfaces of the KNN-CSN-Sealed (a) and KNN-CSN9-Unsealed (b) samples, EDS spectrum of surfaces of the KNN-CSN9-Sealed (c) and KNN-CSN9-Unsealed (d) samples.

Fig. 3. (a) Temperature dependences of dielectric constant at 1 MHz, (b) polarization-electric field (P - E) hysteresis loops of the KNN-CSN9 ceramics sintering at different conditions.

Fig. 4. XRD patterns of the $(1-x)$ KNN- x CSN ceramics sintered at 1220 °C for 4 h.

Fig. 5. (a) Photograph and (b, c) optical transmission characteristics of the $(1-x)$ KNN- x CSN transparent ceramics.

Fig. 6. Plots of $(\alpha h\nu)^2$ versus $h\nu$, energy band gap E_g for the $(1-x)$ KNN- x CSN ceramics.

Fig. 7. (a-e) Temperature dependences of dielectric constant and dielectric loss at different frequencies (1 kHz, 10 kHz, 100 kHz, 1 MHz) of the $(1-x)$ KNN- x CSN ceramics, (f) Curie temperature (T_c) and the max dielectric constant ($\epsilon_{\max}$) at 1MHz of the $(1-x)$ KNN- x CSN ceramics.

Fig. 8. (a-e) Inverse dielectric permittivity at 1 MHz as a function of temperature for the $(1-x)$ KNN- x CSN ceramics; (f) $\log(1/\epsilon - 1/\epsilon_m)$ as a function of $\log(T - T_m)$ at 1 MHz for the $(1-x)$ KNN- x CSN ceramics.

Fig. 9. (a) P - E hysteresis loops, (b) remnant polarization P_r and coercive field E_c , (c) piezoelectric constants d_{33} of the $(1-x)$ KNN- x CSN ceramics.

Tab. 1. Lattice parameters, relative density (RD), electric and ferroelectric properties of the KNN-CSN9 ceramics.

Sample	Lattice parameters				RD	T@1064 nm	$\epsilon_{\max}$	T_c (°C)	P_r ($\mu\text{C}/\text{cm}^2$)	E_c (kV/cm)	d_{33} (pC/N)
	a (Å)	b (Å)	c (Å)	a/c							
Sealed	3.9534	3.9295	3.8936	1.0154	98%	59.93%	3279	147	6.88	8.49	35
Unsealed	3.9510	3.9422	3.9310	1.0051	95%	45.25%	2752	134	4.35	9.61	15

Tab. 2. Lattice parameters and relative density (RD) of the (1-x)KNN-xCSN ceramics.

	Lattice parameters				RD
	a (Å)	b (Å)	c (Å)	a/c	
$x=0.050$	4.0264	3.9173	3.8588	1.0434	95%
$x=0.070$	3.9833	3.9292	3.8841	1.0255	93%
$x=0.090$	3.9534	3.9295	3.8936	1.0154	98%
$x=0.095$	3.9482	3.9502	3.9513	0.9992	97%
$x=0.010$	3.9326	3.9529	3.9724	0.9900	97%

Tab. 3. Curie–Weiss temperature (T_{CW}), temperature above which the dielectric constant follows the Curie–Weiss law (T_B), deviation (ΔT_m),

Curie–Weiss constant (C), and diffuseness (γ) for the (1-x)KNN-xCSN ceramics at 1 MHz.

	(1-x)KNN-xCSN				
	$x=0.050$	$x=0.070$	$x=0.090$	$x=0.095$	$x=0.010$
T_{CW} (°C)	274	225	183	175	148
$C \sim 10^5$ (°C)	1.55	1.47	1.46	1.48	1.50
T_B (°C)	340	320	309	297	268
$\Delta T_m = T_B - T_m$ (°C)	46	103	161	159	154
γ	1.68	1.78	1.85	1.83	1.80

Figure

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9