A study of the physical properties of single crystalline Fe₅B₂P.

Tej N Lamichhane^{a,b}, Valentin Taufour^b, Srinivasa Thimmaiah^b, David S. Parker^c, Sergey L. Bud'ko^{a,b}, Paul C. Canfield^{a,b}

^aDepartment of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, U.S.A.

^bAmes Laboratory, Iowa State University, Ames, Iowa 50011, U.S.A.

^cMaterials Science and Technology Division, Oak Ridge National Laboratory, Oak Ridge, TN 37831

Abstract

Single crystals of Fe₅B₂P were grown by self-flux growth technique. Structural and electrical and magnetic anisotropic properties are studied. The Curie temperature of Fe₅B₂P is determined to be 655 ± 2 K. The saturation magnetization is determined to be $1.72 \mu_B/\text{Fe}$ at 2 K. The temperature variation of the anisotropy constant K_1 is determined for the first time, reaching $\sim 0.50 \text{ MJ/m}^3$ at 2 K, and it is comparable to that of hard ferrites. The saturation magnetization is found to be larger than the hard ferrites. The first principle calculations of saturation magnetization and anisotropy constant are found to be consistent with the experimental results.

Keywords: single crystal, magnetization, demagnetization factor, Arrott plot, transition temperature, anisotropy constant

1. Introduction

The existence of the ternary Fe₅B₂P phase was first reported in 1962[1, 2]. The first reference reported the detailed structural information and the Curie temperature for the Fe₅B₂P phase. The second reference reported the structural details using X-ray and chemical analysis. Its structural prototype is tetragonal Cr₅B₃ with the space group $D_{4h}^{1s} - I4/mcm$. The Curie temperature was reported to fall between 615 K to 639 K, depending upon the B content. In 1967, another study reported a Curie temperature of 628 K and a saturation magnetization of $1.73 \mu_B/\text{Fe}$ [3]. The Fe₅B₂P phase was also studied using Mössbauer spectroscopy and X-ray diffraction in 1975 [4]. In addition to confirming the Curie temperature range as well as the average saturation magnetic moment per Fe atom, the Mössbauer study identified the average moment contributed by each of the Fe lattice sites in the Fe₅B₂P unit cell. The Fe(2) (or 4c) sites contribute $2.2 \mu_B/\text{Fe}$. The Fe(1) (or 16l) sites contribute $1.6 \mu_B/\text{Fe}$. The average extrapolated moment of the both sites at 0 K was reported to be $1.73 \mu_B/\text{Fe}$.

Fe₅B₂P is specifically interesting as a possible high transition temperature, rare earth free, hard ferromagnetic material. Given that all prior work on Fe₅B₂P was made on polycrystalline samples, we developed a single crystal growth protocol, measured thermodynamic and transport properties of single crystalline samples, and determined the magnetic anisotropy of this material. The anisotropy constant K_1 is positive, indicating that the c axis is the easy axis of magnetization, and has a comparable size and temperature dependence as hard ferrites such as SrFe₁₂O₁₉ and BaFe₁₂O₁₉.

2. Experimental Details

2.1. Crystal growth

As part of our effort to search for new, or poorly characterized ferromagnetic compounds, we have developed single crys-

tal growth protocols for transition metal rich, chalcogenide and pnictide binary and ternary phases. In a manner similar to some of our earlier transition metal - sulphur work, [5, 6] we started by confirming our ability to contain Fe-P binary melts in alumina crucibles sealed in amorphous silica ampoules. As outlined by Canfield and Fisk [7] and Canfield, [8] sealed ampoules were decanted after slow cooling by use of a centrifuge. Crucibles with alumina filters [9, 10] were used to allow assessment and even reuse of the decanted liquid. For this experiment, a mixture of freshly ball milled iron powder and red phosphorous lumps were placed in an alumina crucible in an atomic ratio of Fe : P = 0.83 : 0.17. A homogenous liquid exists at 1060 °C (i.e. there was no crystal growth upon cooling from 1200 °C to 1060 °C and all of the material decanted). For similar temperature profiles, an initial melt of Fe_{0.86}P_{0.14} lead to the growth of dendritic Fe whereas for initial melts of Fe_{0.81}P_{0.19}, Fe_{0.79}P_{0.21} and Fe_{0.77}P_{0.23} faceted Fe₃P was grown. These data are all consistent with the binary phase diagram [11] and indicate that the Fe-P binary melt does not have a significant partial pressure of phosphorous and does not react with alumina.

After some optimization, an initial stoichiometry of Fe₇₂P₁₈B₁₀ was used to grow single phase Fe₅B₂P plates. Ball milled Fe (Fe lumps obtained from Ames lab), red phosphorous lumps (Alfa Aesar, 99.999% (metal basis)), and crystalline boron pieces (Alfa Aesar, 99.95%) were placed in an alumina crucible / filter assembly, sealed in a partial pressure of Ar in an amorphous silica tube (as shown schematically in figure 1). The ampoule was heated over 3 hours to 250 °C, remained at 250 °C for 3 hours, heated to 1200 °C over 12 hours, held at 1200 °C for 10 hours, and then cooled to 1160 °C over 75 hours. After cooling to 1160 °C the ampoule was decanted using a centrifuge and plate like single crystals of Fe₅B₂P could be found on the growth side of the alumina filter. In order to confirm that the growth of crystals took place from a complete liquid, we decanted one growth at 1200 °C, instead of cooling to 1160 °C,

Figure 1: A schematic assembly of the crystal growth ampoule.

Figure 2: (a) The acid etched single crystals image of $\text{Fe}_5\text{B}_2\text{P}$ (b) Laue pattern along the hard axis [100] and (c) Laue pattern along the easy axis [001] of magnetization.

and indeed found all of the material decanted.

After growth, single crystals were cleaned by etching in a roughly 6 molar HCl solution. Figure 2(a) shows a picture of the etched single crystals.

2.2. Physical properties measurement

The crystal structure and lattice parameters of $\text{Fe}_5\text{B}_2\text{P}$ were determined with both single crystal and powder x-ray diffraction (XRD). The crystal structure of $\text{Fe}_5\text{B}_2\text{P}$ was determined from single-crystal XRD data collected with the use of graphite monochromatized $\text{MoK}\alpha$ radiation ($\lambda = 0.71073 \text{ \AA}$) at room temperature on a Bruker APEX2 diffractometer. Reflections were gathered by taking four sets of 360 frames with 0.5° scans in ω , with an exposure time of 25 s per frame and the crystal-to-detector distance was 5 cm. The measured intensities were corrected for Lorentz and polarization effects. The intensities were further corrected for absorption using the program SADABS, as implemented in Apex 2 package [12].

For powder XRD, etched single crystals of $\text{Fe}_5\text{B}_2\text{P}$ were selected and finely powdered. The powder was evenly spread over the zero background single crystal silicon wafer sample holder with help of a thin film of Dow Corning high vacuum grease. The powder diffraction pattern was recorded with Rigaku Miniflex diffractometer using copper $K\alpha$ radiation source over 8.5 hours (at a rate of 3 sec dwell time for per 0.01° to cover the 2θ value up to 100°).

To identify the crystallographic orientation of the single crystal plates, Laue diffraction patterns were obtained using a Multiwire Laboratories, Limited spectrometer. The resistivity anisotropy data were measured in a four-probe configuration using a Quantum Design Magnetic Property Measurement System (MPMS) for temperature control and the external device control option to interface with a Linear Research, Inc. ac (20mA, 16 Hz) resistance bridge (LR 700). To make the resistivity anisotropy data more reliable, resistivity bar for both [100] and [001] axes were taken from the same crystal as shown in the inset of figure 5.

The sample preparation for magnetization measurements is a major step in a magnetic anisotropy study. The etched crystal was cut into a rectangular prismatic shape and the dimensions were determined with a digital Vernier caliper.

Temperature and field dependent magnetization was measured using the MPMS up to room temperature and a Quantum Design Versalab Vibration Sample Magnetometer (VSM) with an oven option for higher temperature ($T < 1000 \text{ K}$). In MPMS, plastic straw was used to align the sample in desired directions. The sample was glued to the VSM sample heater stick with Zircar cement obtained from ZIRCAR Ceramics Inc.. While gluing, the sample was pushed into the thin layer of Zircar paste spread on the heater stick to ensure a good thermal contact with the heater stick. When the sample was firmly aligned with the desired direction it was covered with Zircar cement uniformly. Finally, the VSM heater stick, with the sample glued on it, was covered with a copper foil so as to (i) better control the heat

radiation in the sample chamber, (ii) maintain a uniform temperature inside the wrapped foil (due to its good thermal conductivity), and (iii) further secure the sample throughout the measurement.

In the VSM, both zero field cooled (ZFC) as well as field cooled (FC) magnetizations were measured and found to be almost overlapping. The difference between the measured data in the VSM and the MPMS was found to be less than 3% at 300 K (i.e. at the point of data overlap). We normalized the magnetization data from the MPMS with FC VSM data to get a smooth curve for the corresponding applied field.

2.3. Determination of demagnetization factor for transition temperature and anisotropy constant measurement

Figure 3: An analysis of $M(H)$ isotherms taken at $T = 2, 50, 100, 150, 200, 250, 300$ K and plotted as M^2 versus H/M to determine the demagnetization factor. The H/M axis intercept at 0.45 is the experimental demagnetization factor for easy axis of magnetization.

The demagnetization factors along different directions were determined by using a formula developed by Aharoni [13]. The calculated demagnetization factors for the field along a, b, and c axes were determined to be 0.21, 0.29, and 0.50 respectively. To verify that demagnetization factors were accurate, we prepared a M^2 versus $\frac{H}{M}$ plot for the lower temperature $M(H)$ data along the easy axis of magnetization as shown in figure 3. The X-intercept gives the directly measured experimental value of the demagnetization factor along the easy magnetization axis [14]. In figure 3, we can clearly see that all the M^2 curves are overlapping near the M^2 axis indicating that the demagnetization factor along the easy magnetization direction does not depend on temperature. A value of demagnetization factor of 0.45 was determined along the c axis which is not that different from the value of 0.50 inferred from the sample dimensions. Based on this result, we readjusted the two hard axes demagnetization factors in proportion such that the total sum of all 3 of them is 1. The experimentally readjusted values for demagnetization factors were 0.231, 0.319 and 0.45 along a, b and c axes respectively. With the benefit of fourfold symmetry of $\text{Fe}_5\text{B}_2\text{P}$ unit cell perpendicular to its c axis, magnetization was measured along a and c axes and corresponding demagnetization factors were used to calculate the corrected internal magnetic

field (H_{int}). Here $H_{\text{int}} = H_{\text{applied}} - NM$, where N is the demagnetization factor and M is the magnetization.

3. Results and discussion

Figure 4: (a) Powder x-ray diffraction pattern of $\text{Fe}_5\text{B}_2\text{P}$ (b) Enlarged powder X-ray diffraction pattern in between 2θ value of 34° to 46° to show the weak impurity peaks 1 and 2.

3.1. Lattice parameters determination

The structure solution and refinement for single crystal data was carried out using SHELXTL program package [15]. The final stage of refinement was performed using anisotropic displacement parameters for all the atoms. The refined composition was $\text{Fe}_5\text{B}_{2.12}\text{P}_{0.88(1)}$ with residual $R1 = 2.3\%$ (all data). The off-stoichiometry was due to partial replacement of phosphorus by boron on 4a site in the structure. According to the previous report [4] $\text{Fe}_5\text{B}_2\text{P}$ shows a considerable phase width. All the details about the atomic positions, site occupancy factors, and displacement parameters for crystal of $\text{Fe}_5\text{B}_{2.12}\text{P}_{0.88(1)}$ are given in tables 1, and 2.

$\text{Fe}_5\text{B}_2\text{P}$ has a tetragonal unit cell with lattice constants $a = 5.485(3) \text{ \AA}$ and $c = 10.348(3) \text{ \AA}$. While analysing the powder pattern, the CIF file obtained from single crystal data was used and the powder pattern was fitted with Rietveld analysis using GSAS EXPGUI software package [16, 17]. During the Rietveld analysis, Fe sites were supposed to be fully occupied and thermally rigid whereas P and B occupation number were released between each other with help of constraints. Finally, a well fitted powder diffraction pattern with $R_p = 0.0828$ was obtained as shown in figure 4(a). The lattice parameters from this measurement are in close agreement (less than 0.2 % deviation) with our single crystal data as well as previously reported data [2, 4]. A final stoichiometry of the powder sample was determined to be $\text{Fe}_5\text{B}_{2.11}\text{P}_{0.89}$. This stoichiometry is in agreement

Table 1: Crystal data and structure refinement for Fe₅B₂P.

Empirical formula	Fe ₅ B _{2.12} P _{0.88}
Formula weight	329.42
Temperature	293(2) K
Wavelength	0.71073 Å
Crystal system, space group	Tetragonal, <i>I4/mcm</i>
Unit cell dimensions	a=5.485(3) Å b = 5.485(3) Å c = 10.348(6) Å
Volume	311.3(4) 10 ³ Å ³
Z, Calculated density	4, 7.029 g/cm ³
Absorption coefficient	22.905 mm ⁻¹
F(000)	615
Crystal size	0.01 x 0.05 x 0.08 mm ³
θ range (°)	3.938 to 31.246
Limiting indices	-7 ≤ h ≤ 7 -7 ≤ k ≤ 7 -14 ≤ l ≤ 14
Reflections collected	2113
Independent reflections	152 [R(int) = 0.0433]
Completeness to θ = 25.242°	100.00%
Absorption correction	multi-scan, empirical
Refinement method	Full-matrix least-squares on F ²
Data / restraints / parameters	152 / 0 / 17
Goodness-of-fit on F ²	1.101
Final R indices [I > 2σ(I)]	R1 = 0.0140, wR2 = 0.0289
R indices (all data)	R1 = 0.0180, wR2 = 0.0299
Extinction coefficient	0.0243(3)
Largest diff. peak and hole	0.485 and -0.474 e.Å ⁻³

Table 2: Atomic coordinates and equivalent isotropic displacement parameters (Å²) for Fe₅B₂P. U(eq) is defined as one third of the trace of the orthogonalized U_{ij} tensor.

atom	Occ	x	y	z	U _{eq}
Fe1	1	0.0000	0.0000	0.0000	0.005(1)
Fe2	1	0.1701(1)	0.6701(1)	0.1403(1)	0.005(1)
P3	0.88(1)	0.0000	0.0000	0.2500	0.004(1)
B3	0.12(1)	0.0000	0.0000	0.2500	0.004(1)
B4	1	0.6175(2)	0.1175(2)	0.0000	0.005(1)

with our single crystal XRD composition of Fe₅B_{2.12}P_{0.88(1)}. Two tiny unidentified peaks denoted by 1 and 2 in figure 4 were noticed in all batches of Fe₅B₂P measured. A possible origin for these peaks is an excess amount of unreacted boron trapped in crystal. We suspected boron because it has many overlapping diffraction peaks with Fe₅B₂P as well as with these two tiny humps denoted by 1 and 2 and enlarged in figure 4(b).

Here we don't believe that the traces of unreacted boron can affect the magnetic properties of the sample in a significant manner because boron is non-magnetic. It is possible that boron impurities are responsible for the residual resistivity being rather large (17-35 micro-ohm cm), although this can also come from the small off-stoichiometry due to partial replacement of phosphorus by boron on 4a site in the structure.

3.2. Identification of crystallographic orientation

The Laue diffraction pattern shown in figure 2(b) was obtained with the X-ray beam parallel to the plane of the plate [100]. The Laue pattern shown in figure 2(c) was obtained with the X-ray beam perpendicular to the plane of the plate [001]. The obtained Laue diffraction patterns were analysed with the OrientExpress analysis software [18]. The Laue pattern analysis revealed that the crystals facets were grown along [100], [010], and [001] directions.

3.3. Resistivity measurement

Figure 5: Resistivity of Fe₅B₂P below the room temperature with an excitation current being parallel to [100] and [001] directions. The inset picture shows the electrical resistivity bars obtained from the same single crystal to measure the electrical resistivity anisotropy property.

The resistivity data of a single crystalline sample helps to test its quality. The resistivities of Fe₅B₂P with currents parallel to [100] and [001] directions are measured from room temperature down to 2 K; the resistivity is found to be metallic in nature as shown in figure 5. The residual resistivity ratio ($RRR = \rho(300 \text{ K})/\rho(2 \text{ K})$) of the Fe₅B₂P sample is estimated to be nearly 3.6 in [100] direction and 2.8 in [001] direction. The resistivity for easy axis of magnetization [001] is found to be greater than hard axis [100] of magnetization. The electrical anisotropy is found to be opposite than magnetic anisotropy for Fe₅B₂P. It is hard to correlate the magnetic and electrical

anisotropic properties of $\text{Fe}_5\text{B}_2\text{P}$. The residual resistivity $\rho(2\text{ K})$ is roughly $17\ \mu\Omega\text{cm}$ in [100] direction and $35\ \mu\Omega\text{cm}$ in [001] direction respectively. These values are consistent with some residual disorder in the sample (e.g. the P and B site disorder on the P_3 site).

Figure 6: Temperature dependent magnetization of $\text{Fe}_5\text{B}_2\text{P}$ at various magnetizing field along [100] and [001] directions and saturation magnetization, M_s , inferred from $M(H)$ isotherms.

3.4. Measurement of magnetization and saturation magnetization

The temperature dependent magnetization of $\text{Fe}_5\text{B}_2\text{P}$ along the easy [001] and hard [100] axes in various magnetizing field strengths in terms of μ_B/Fe are reported in figure 6. As the field strength increases, the moment increases and saturates. The saturating field for the easy axis was found to be nearly 0.8 T and $M(T)$ data in an applied field of 1 T is the same as saturation magnetization obtained from $M(H)$ isotherms data (not shown here). The magnetization along the hard axis has not reached saturation in an external field of 1 T and forms a concave parabola around 150 K as shown in the green curve of figure 6. We have not systematically investigated the origin of the parabolic curve below 400 K for $M(T)$ with $H = 1\text{ T}||[100]$. It reaches to saturation with higher applied magnetic field and looks like the magnetization curve along the easy axis of magnetization. One possible explanation for a low applied field and low temperature region valley in magnetization curve is the following. As the sample is cooled down, the anisotropy field (H_a) increases (typically H_a (T) varies as $M_s(T)^2$) resulting in a decrease of the sample macroscopic magnetization. Indeed, for $H_\perp < H_a$, we have $M_\perp = H_\perp * M_s/H_a$ which gives a curve similar to the one observed for $M(T)$ with $H = 0.1\text{ T}||[100]$. When taking into account the demagnetization factor, $N_\perp$, we have $M_\perp = H_\perp * M_s/(H_a + N_\perp * M_s)$. As the domains are becoming more elongated, $N_\perp$ will decrease upon cooling. This can give rise to a parabolic curve with a minimum as the one observed for $H = 1\text{ T}||[100]$. Another explanation is that such parabolic curve could originate from a peculiar high value of the higher order anisotropy constant K_2 (T) which was assumed to be zero at higher temperature.

Below the Curie temperature, the $M(T)$ curves at low field are almost constant because the applied field is less than the demagnetizing field. The saturation magnetization (M_s) data were determined from the Y-intercept of linear fit of $M(H)$ isotherms plateau (as shown in figure 8) at 2 K, 50 K and in an interval of 50 K up to 650 K. The saturation magnetization at 2 K was found to be $1.72\ \mu_B/\text{Fe}$ which is very close to the previously reported value of $1.73\ \mu_B/\text{Fe}$ [3, 4].

Figure 7: The Arrott plot of $\text{Fe}_5\text{B}_2\text{P}$. Here $M(H)$ isotherms were measured for the prismatic sample from 648 K to 668 K with a spacing of 1 K. Internal magnetic field (H_{int}) was determined with an experimentally measured demagnetization factor (0.45) for the easy axis of magnetization. The temperature corresponding to M^2 versus H_{int}/M isotherm passing through origin gives the Curie temperature. The Curie temperature is determined to be $655 \pm 2\text{ K}$.

3.5. Determination of transition temperature

A M^2 versus H_{int}/M Arrott plot was used to determine the Curie temperature. The Curie temperature corresponds to Arrott plot curve that passes through the origin. For our sample, the Arrott curve corresponding to 655 K is passing through the origin. Hence the Curie temperature of $\text{Fe}_5\text{B}_2\text{P}$ is determined to be $655 \pm 2\text{ K}$, where the error includes an instrumental uncertainty of $\pm 1\text{ K}$ inherent to such a high temperature measurement in a VSM and a reproducibility error due to sample gluing process on the heater stick resulting in a variation in thermal coupling. This Curie temperature is a little bit higher than the previously reported window of 615 K to 639 K [3, 4].

To make sure our measurement was correct, magnetization of a piece of a nickel wire obtained from the Alfa Aesar company (99.98 % metal basis) was measured with the same VSM heater stick. Using the criterion from reference [19], the Curie temperature of nickel sample was determined to be $625 \pm 2\text{ K}$ which is in agreement with VSM Tech Note [20]. The Curie temperature of nickel is reported to fall between 626 to 633 K [21]. These results confirm the accuracy of measured Curie temperature.

3.6. Determination of anisotropy constant K_1

The anisotropy constant K_1 is the measure of anisotropy energy density and strongly depends on the unit cell symmetry and temperature. One of the conceptually simplest methods of measuring the anisotropy constant of an uniaxial system is

Figure 8: An example of determination of K_1 at 300 K with an appropriate axes units so as to obtain the area in terms of MJ/m^3 unit.

to determine the area between the easy and hard axes $M(H)$ isotherms [22]. Here we measured both the easy and hard axes isothermal $M(H)$ curves starting from 2 K. Then we measured $M(H)$ curves from 50 K to 800 K in 50 K intervals. A typical example of determination of the anisotropy constant by measuring the anisotropy area between two magnetization curves is shown in figure 8.

Figure 9: Temperature variation of the anisotropy constant K_1 of $\text{Fe}_5\text{B}_2\text{P}$ and comparison with $\text{SrFe}_{12}\text{O}_{19}$ and $\text{BaFe}_{12}\text{O}_{19}$ from ref. [23].

The temperature dependence of K_1 is shown in Fig. 9. K_1 is positive, indicating that the c axis is the easy axis of magnetization, in agreement with a previous calculation using a simple point charge model [4].

We have compared the anisotropy constant K_1 and saturation magnetization M_s of $\text{Fe}_5\text{B}_2\text{P}$ with the single crystal data of hard ferrites $\text{SrFe}_{12}\text{O}_{19}$ and $\text{BaFe}_{12}\text{O}_{19}$ [23]. The anisotropy constant of $\text{Fe}_5\text{B}_2\text{P}$ is greater at low temperature than either of these ferrites. The $\text{Fe}_5\text{B}_2\text{P}$ sample becomes comparable to that of $\text{SrFe}_{12}\text{O}_{19}$ at room temperature but decreases slightly faster than both $\text{BaFe}_{12}\text{O}_{19}$ and $\text{SrFe}_{12}\text{O}_{19}$ above room temperature as shown in figure 9. However, the nature of variation of the satu-

Figure 10: Temperature variation of the saturation magnetization M_s of $\text{Fe}_5\text{B}_2\text{P}$ and comparison with $\text{SrFe}_{12}\text{O}_{19}$ and $\text{BaFe}_{12}\text{O}_{19}$ from ref. [23].

ration magnetization of $\text{Fe}_5\text{B}_2\text{P}$ is different than the hard ferrites as shown in figure 10. Both of the ferrites show a roughly linear decrease of saturation magnetization with increasing temperature whereas the saturation magnetization of $\text{Fe}_5\text{B}_2\text{P}$ is found to be significantly non-linear in T and also significantly larger for $T < 600$ K. The saturation magnetization of $\text{Fe}_5\text{B}_2\text{P}$ is $1.53 \mu_B/\text{Fe}$ at 300 K, which is already larger than the value of $1.16 \mu_B/\text{Fe}$ in $\text{SrFe}_{12}\text{O}_{19}$. Since $\text{Fe}_5\text{B}_2\text{P}$ contains less non-magnetic elements, the volume magnetization of 915 kA/m for $\text{Fe}_5\text{B}_2\text{P}$ is more than twice that of $\text{SrFe}_{12}\text{O}_{19}$ (377 kA/m [23]).

4. First principles calculations

In an effort to understand the observed magnetic properties - in particular, the saturation magnetization and magnetocrystalline anisotropy - of $\text{Fe}_5\text{B}_2\text{P}$, we have performed first principles calculations using the augmented plane-wave density functional theory code WIEN2K [24] within the generalized gradient approximation (GGA) of Perdew, Burke and Ernzerhof [25]. Sphere radii of 1.77, 2.15 and 2.06 Bohr were used for B, Fe and P, respectively, and an RK_{max} of 7.0 was employed, where RK_{max} is the product of the smallest sphere radius and the largest plane-wave expansion wave vector. The experimental lattice parameters from Ref. [2] were used and all internal coordinates were relaxed. All calculations, the internal coordinate relaxation excepted, employed spin-orbit coupling and a total of approximately 10,000 k -points in the full Brillouin zone were used for the calculation of magnetic anisotropy. For these calculations we computed total energies for the magnetic moments parallel to (100) and (001) and computed the anisotropy as the difference in these energies.

As in the experimental work we find a strong ferromagnetic behavior in $\text{Fe}_5\text{B}_2\text{P}$, with a saturation magnetic moment of $1.79 \mu_B$ per Fe, which includes an average orbital moment of approximately $0.03 \mu_B$ for each of the Fe sites. We present the calculated density-of-states in Fig. 11. The theoretical saturation value is in good agreement with the experimental 2 K moment of $1.72 \mu_B$ per Fe. Small negative moments of $-0.1 \mu_B$

and $-0.06 \mu_B$ per atom are found for the B and P atoms respectively, while the spin moments for the three distinct inequivalent Fe atoms are 1.79, 1.79 and $2.08 \mu_B$. These are significantly smaller than the values for bcc Fe (approximately $2.2 \mu_B$) and for the Fe atoms in hexagonal Fe_3Sn (approximately $2.4 \mu_B/\text{Fe}$ [26]), limiting the potential performance as a hard magnetic material. Figure 11 displays the reason for this, with the spin-minority DOS substantially larger than the spin-majority DOS around the Fermi energy, reducing the moment.

Figure 11: The calculated density-of-states of Fe_5PB_2

As in the experiment, the calculated easy axis of the magnetization is the c -axis, with a $T = 0$ value for the first anisotropy constant K_1 of 0.46 MJ/m^3 , which is in excellent agreement with the experimental value of 0.48 MJ/m^3 . On a per-Fe basis this is $44 \mu\text{eV}$. This is much larger than the $\sim 1 \mu\text{eV}$ value for bcc Fe [27], as might be expected given the non-cubic symmetry of $\text{Fe}_5\text{B}_2\text{P}$, but is roughly consistent with the $60 \mu\text{eV}/\text{Co}$ value for hcp Co. This is again indicative of the usual requirement of an anisotropic crystal structure for significant magnetic anisotropy. Regarding the structure itself, in the perfectly ordered $\text{Fe}_5\text{B}_2\text{P}$ structure, eight of the ten Fe atoms have three boron nearest neighbors and two next-nearest phosphorus neighbors, with the other two Fe atoms having four boron nearest neighbors. There are no nearest-neighbor Fe-Fe bonds, which is perhaps surprising in a structure which is over 60 atomic percent Fe. One may suppose that a variegated bonding configuration, with a range of atoms bonding with the Fe atoms, might be favorable for the magnitude, though not necessarily the *sign* (i.e. axial or planar) of the anisotropy, but this is apparently not realized in this material. In any case, the theoretical calculations are generally quite consistent with the results of the experimental work performed.

5. Conclusions

Single crystals of $\text{Fe}_5\text{B}_2\text{P}$ were grown using a self flux growth method within a 40°C window of cooling. The electrical and magnetic anisotropy properties were studied. The Curie temperature of $\text{Fe}_5\text{B}_2\text{P}$ was determined to be $655 \pm 2 \text{ K}$. The saturation magnetization was determined to be $1.72 \mu_B/\text{Fe}$ at 2 K .

The temperature variation of the anisotropy constant K_1 was determined for the first time, reaching $\sim 0.50 \text{ MJ/m}^3$ at 2 K , and found to be comparable to that of hard ferrites. The saturation magnetization, in unit of kA/m is found to be larger than the hard ferrites. The first principle calculation values of saturation magnetization and anisotropy constant using augmented plane-wave density functional theory code were found to be consistent with experimental work.

6. Acknowledgement

We thank T. Kong, U. Kaluarachchi, K. Dennis, and A. Sapkota for useful discussion. The research was supported by the Critical Material Institute, an Energy Innovation Hub funded by U.S. Department of Energy, Office of Energy Efficiency and Renewable Energy, Advanced Manufacturing Office. This work was also supported by the Office of Basic Energy Sciences, Materials Sciences Division, U.S. DOE. The first principle calculation of this work was performed in Oak Ridge National Laboratory.

- [1] E. Fruchart, A.-M. Triquet, R. Fruchart, A. Michale, Two New Ferromagnetic Compounds in the Ternary System Iron-Phosphorous-Boron (in French), *Compt. Rend. Acad. Sci. Paris* 255 (1962) 931–933.
- [2] S. Rundqvist, X-Ray Investigation of the Ternary System Fe-P-B. Some Features of the System Cr-P-B, Mn-P-B and Ni-P-B, *Acta Chem. Scand.* 16 (1962) 1.
- [3] A.-M. Blanc, E. Fruchart, R. Fruchart, Magnetic and Crystallographic Studies of the $(\text{Fe}_{1-x}\text{Cr}_x)_3\text{P}$ Solution Solids and the Ferromagnetic Phase $\text{Fe}_5\text{B}_2\text{P}$ (in French), *Ann. Chim.*, t.2.
- [4] L. Häggström, R. Wäppling, E. Ericsson, Y. Andersson, S. Rundqvist, Mossbauer and X-ray studies of Fe_5PB_2 , *J. Solid State Chem.* [doi:10.1016/0022-4596\(75\)90084-5](https://doi.org/10.1016/0022-4596(75)90084-5).
- [5] X. Lin, S. L. Bud'ko, P. C. Canfield, Development of viable solutions for the synthesis of sulfur bearing single crystals, *Philos. Mag.* 92 (19-21) (2012) 2436–2447. [doi:10.1080/14786435.2012.671552](https://doi.org/10.1080/14786435.2012.671552).
- [6] Q. Lin, V. Taufour, Y. Zhang, M. Wood, T. Drtina, S. L. Budko, P. C. Canfield, G. J. Miller, Oxygen trapped by rare earth tetrahedral clusters in Nd_4FeOS_6 : Crystal structure, electronic structure, and magnetic properties, *J. Solid State Chem.* 229 (0) (2015) 41 – 48. [doi:http://dx.doi.org/10.1016/j.jssc.2015.05.020](http://dx.doi.org/10.1016/j.jssc.2015.05.020).
- [7] P. C. Canfield, Z. Fisk, Growth of single crystals from metallic fluxes, *Philos. Mag.* 65 (6) (1992) 1117–1123. [arXiv:http://arxiv.org/abs/10.1080/13642819208215073](http://arxiv.org/abs/10.1080/13642819208215073), [doi:10.1080/13642819208215073](https://doi.org/10.1080/13642819208215073).
- [8] P. C. Canfield, *Solution Growth of Intermetallic Single Crystals: A Beginners Guide, Properties and Applications of Complex Intermetallics*, (World Scientific, Singapore, 2010) (2010) 93–111.
- [9] P. C. Canfield, T. Kong, U. S. Kaluarachchi, N. H. Jo, *Use of frit-disc crucibles for routine and exploratory solution growth of single crystalline sample.*, *arXiv:1509.08131 [cond-mat.mtrl-sci]*. URL <http://arxiv.org/abs/1509.08131>
- [10] C. Petrovic, P. C. Canfield, J. Y. Mellen, Growing intermetallic single crystals using in situ decanting, *Philos. Mag.* 92 (19-21) (2012) 2448–2457. [doi:10.1080/14786435.2012.685190](https://doi.org/10.1080/14786435.2012.685190).
- [11] H. Ohtani, N. Hanaya, M. Hasebe, S. Teraoka, M. Abe, *Fe-P Phase Diagram, ASM Alloy Phase Diagrams Database*, P. Villars, editor-in-chief; H. Okamoto and K. Cenzual, section editors. URL <http://www1.asminternational.org/AsmEnterprise/APD,ASMInternational,MaterialsPark,OH,2006>.
- [12] Bruker, APEX-2, Bruker AXS Inc., Madison, Wisconsin, USA, 10th ed. (2013).
- [13] A. Aharoni, Demagnetizing factors for rectangular ferromagnetic prisms, *J. Appl. Phys.* 83 (6) (1998) 3432–3434. [doi:10.1063/1.367113](https://doi.org/10.1063/1.367113).
- [14] A. Arrott, *Criterion for ferromagnetism from observations of magnetic isotherms*, *Phys. Rev.* 108 (1957) 1394–1396. [doi:10.1103/PhysRev.108.1394](https://doi.org/10.1103/PhysRev.108.1394). URL <http://link.aps.org/doi/10.1103/PhysRev.108.1394>
- [15] SHELXTL-v2008/4, Bruker AXS Inc., Madison, Wisconsin, USA, 2013.

- [16] A. Larson, R. V. Dreele, "General Structure Analysis System (GSAS)", Los Alamos National Laboratory Report LAUR (1994) 86–748.
- [17] B. H. Toby, EXPGUI, a graphical user interface for GSAS, J. Appl. Cryst. 34 (2001) 210–213.
- [18] J. laugier, B. Bochu, [LMGP-Suite Suite of Programs for the interpretation of X-ray Experiments](#), ENSP/Laboratoire des Matériaux et du Gnie Physique, BP 46. 38042 Saint Martin d'Hres, France.
URL [WWW:http://www.inpg.fr/LMGPandhttp://www.ccp14.ac.uk/tutorial/lmgp/](http://www.inpg.fr/LMGPandhttp://www.ccp14.ac.uk/tutorial/lmgp/)
- [19] A. Arrott, J. E. Noakes, [Approximate equation of state for nickel near its critical temperature](#), Phys. Rev. Lett. 19 (1967) 786–789. doi:10.1103/PhysRevLett.19.786.
URL <http://link.aps.org/doi/10.1103/PhysRevLett.19.786>
- [20] Quantum Design, Tech Note 1097-202, Measured Curie Temperature of the VSM Oven Nickel Standard Sample .
- [21] B. Legendre, M. Sghaier, [Curie temperature of nickel](#), Journal of Thermal Analysis and Calorimetry 105 (1) (2011) 141–143. doi:10.1007/s10973-011-1448-2.
URL <http://dx.doi.org/10.1007/s10973-011-1448-2>
- [22] R. M. Bozorth, [Determination of ferromagnetic anisotropy in single crystals and in polycrystalline sheets](#), Phys. Rev. 50 (1936) 1076–1081. doi:10.1103/PhysRev.50.1076.
URL <http://link.aps.org/doi/10.1103/PhysRev.50.1076>
- [23] B. T. Shirk, W. Bussem, Temperature dependence of M_s and K_1 of $\text{BaFe}_{12}\text{O}_{19}$ and $\text{SrFe}_{12}\text{O}_{19}$ single crystals., J. Appl. Phys.
- [24] P. Blaha and K. Schwarz and G. Madsen and D. Kvasnicka and J. Luitz, WIEN2k, An Augmented Plane Wave + Local Orbitals Program for Calculating Crystal Properties(K. Schwarz, Tech. Univ. Wien, Austria, 2001).
- [25] Perdew, John P. and Burke, Kieron and Ernzerhof, Matthias, [Generalized Gradient Approximation Made Simple](#), Phys. Rev. Lett. 77 (1996) 3865–3868. doi:10.1103/PhysRevLett.77.3865.
URL <http://link.aps.org/doi/10.1103/PhysRevLett.77.3865>
- [26] B. C. Sales and B. Saporov and M. A. McGuire and D. J. Singh and D. S. Parker, Ferromagnetism of Fe_3Sn and alloy., Sci Rep 4 (2014) 7024.
- [27] G. H. O. Daalderop, P. J. Kelly, M. F. H. Schuurmans, [First-principles calculation of the magnetocrystalline anisotropy energy of iron, cobalt, and nickel](#), Phys. Rev. B 41 (1990) 11919–11937. doi:10.1103/PhysRevB.41.11919.
URL <http://link.aps.org/doi/10.1103/PhysRevB.41.11919>