Nuclear Magnetic Resonance Studies of the Solvation Structures of a High-Performance Nonaqueous Redox Flow Electrolyte

Xuchu Deng^{ab}, Mary Hu^b, Xiaoliang Wei^b, Wei Wang^b, Karl T. Mueller^{bc}, Zhong Chen^{a*}, Jian
Zhi Hu^{b*}

^a Department of Electronic Science, Xiamen University, Xiamen 361005, China

^b The Joint Center for Energy Storage Research (JCESR),

Pacific Northwest National Laboratory, Richland, WA 99352, USA

^c Department of Chemistry, Penn State University, University Park, PA 16802, USA

* To whom correspondence should be addressed:

Jian Zhi Hu; Email: Jianzhi.Hu@pnnl.gov; Phone: (509) 371-6544; Fax: (509) 371-6546

Zhong Chen; Email: chenz@xmu.edu.cn; Phone: (+86)0592-2181712

Abstract

Understanding the solvation structures of electrolytes is important for developing nonaqueous redox flow batteries that hold considerable potential for future large scale energy storage systems. The utilization of an emerging ionic-derivatived ferrocene compound, ferrocenylmethyl dimethyl ethyl ammonium bis(trifluoromethanesulfonyl)imide (Fc1N112-TFSI), has recently overcome the issue of solubility in the supporting electrolyte. In this work, ^{13}C , ^1H and ^{17}O NMR investigations were carried out using electrolyte solutions consisting of Fc1N112-TFSI as the solute and the mixed alkyl carbonate as the solvent. It was observed that the spectra of ^{13}C experience changes of chemical shifts while those of ^{17}O undergo linewidth broadening, indicating interactions between solute and solvent molecules. Quantum chemistry calculations of both molecular structures and chemical shifts (^{13}C , ^1H and ^{17}O) are performed for interpreting experimental results and for understanding the detailed solvation structures. The results indicate that Fc1N112-TFSI is dissociated at varying degrees in mixed solvent depending on concentrations. At dilute solute concentrations, most Fc1N112^+ and TFSI^- are fully disassociated with their own solvation shells formed by solvent molecules. At saturated concentration, $\text{Fc1N112}^+-\text{TFSI}^-$ contact ion pairs are formed and the solvent molecules are preferentially interacting with the Fc rings rather than interacting with the ionic pendant arm of Fc1N112-TFSI.

Key words: Electrolyte, Nuclear Magnetic Resonance, nonaqueous redox flow battery, solvation structures, molecular dynamics

1. Introduction

As a promising stationary energy storage technology, redox flow batteries (RFBs) have experienced a recent renaissance fueled by the rapidly evolving global energy profiles because of the growing deployment of renewable energy resources. The cell design of energy-bearing liquid electrolyte stored outside the electrodes offer significant advantages including the decoupling of energy and power, excellent scalability, modular manufacturing, active thermal management, intrinsic safety, etc.[1-4] Benefiting from wider electrochemically stable voltage windows, the emerging nonaqueous RFB (NRFB) holds great potential for overcoming the low energy density challenge present in current state-of-the-art aqueous RFB technologies.[3-6] Recent research on NRFBs focuses on the development of redox active materials including organometallic compounds,[7-9] redox organic materials,[10-12] redox active polymers,[13] and the synergy between flow battery and Li-ion or Li-metal battery chemistries.[14-20] However, the current performance of NRFBs has lagged far behind their inherent capability. To date, most of them have failed to demonstrate energy density and cycling durability even close to their aqueous counterparts.

One of the major technical hurdles for NRFBs is the low solubility of redox materials leading to limited energy density.[7, 8, 12] Often, low solubility originates from insufficient solvation interactions occurring between the redox materials and solvent molecules. A good understanding of the solvation phenomena is able to offer insights to questions such as preferred functionalities and chemical sites of interactions, solvation structure evolution upon concentration changes, effects of solvation structure on material properties, etc. According to such information obtained, one can rationally design the redox molecules, improve the supporting electrolyte systems, and

tune the flow cell conditions as redox material concentration increases. Especially, deliberate molecular engineering strategies to increase material solubility can advance the development of high energy density NRFB systems. In solvation studies, nuclear magnetic resonance (NMR) and computational modeling have proven to be powerful tools.

Recently, Wei et al. studied a new active redox species with high solubility in nonaqueous electrolytes by functionalizing pristine ferrocene (Fc) to embody an ionically charged tetraalkylammonium (TAA) pendant arm with a bis(trifluoromethanesulfonyl)imide (TFSI) counter anion (hence denoted as Fc1N112-TFSI).[6] This compound was electrochemically tested in a Li/organic redox flow battery configuration with a cell potential of ~3.5 V. Previous work verified that the ionic pendant intensifies interactions between Fc1N112-TFSI and the mixed solvents composed of ethylene carbonate (EC), propylene carbonate (PC) and ethyl methyl carbonate (EMC), demonstrated by proton NMR experiments and density function theory (DFT) calculations.[6] Chart 1 shows a representation of the structures of all major components in this system. The major hypothesis is that the solute-solvent interactions take place predominantly at the ionic pendant arm of Fc1N112-TFSI with fully dissociated TAA^+ and TFSI^- at Fc1N112-TFSI concentrations ranging from 0.1 M to 1.7 M in the solvent. However, with ^1H NMR alone, the complicated details of the solvation structures have not been sufficiently decoded. Additional studies utilizing Pulsed Field Gradient (PFG) NMR measurements of diffusion[21] coupled with molecular dynamics simulations argue that the PC solvent interacts with Fc1N112^+ strongly relative to the other solvent molecule, while ^1H T_1 relaxation time measurements[22] probe the evolution of solvent-solvent, ion-solvent and ion-ion interactions

1
2
3
4 during this preferential solvation. More theoretical and experimental evidence is still needed to
5
6 gain comprehensive understandings of the solvation mechanism.
7
8
9

10
11 Here, we continue this study through using natural abundance ^{13}C and ^{17}O solution-state NMR to
12
13 acquire a more accurate molecular view of the solvation structures as reported by the chemical
14
15 shift values or linewidths of these two nuclides. Both, ^{13}C and ^{17}O NMR have played important
16
17 roles in the development of liquid electrolytes as these methods reveal more in-depth structural
18
19 details when combined with ^1H NMR.[23-25] Quantum chemical calculations of ^1H , ^{13}C , and ^{17}O
20
21 NMR chemical shifts using a variety of solvation models are carried out to complementarily
22
23 interpret the experimental results and observations related to the detailed molecular interactions.
24
25
26
27
28
29
30

31 **2. Experimental**

32 **2.1 Materials and Sample Preparations**

33
34 The preparation of Fc1N112-TFSI is reported in detail elsewhere.[6, 26] Briefly, Fc1N112-TFSI
35
36 was synthesized in two steps: (dimethylaminomethyl)ferrocene (96%, Sigma-Aldrich) reacted
37
38 with bromoethane (98%, Sigma-Aldrich) in anhydrous acetonitrile (99.8%, Sigma-Aldrich) to
39
40 produce the intermediate of ferrocenylmethyl ethyl dimethylammonium bromide, followed by
41
42 anion exchange with lithium bis(trifluoromethanesulfonyl)imide (LiTFSI, BASF) in deionized
43
44 water to afford the Fc1N112-TFSI in an overall yield of 91%. The NMR sample solutions were
45
46 prepared simply by mixing the Fc1N112-TFSI and the solvents at specified concentrations in an
47
48 argon-filled glove box (Mbraun, Stratham, NH) with moisture and oxygen levels less than 1
49
50 ppm. Battery grade PC, EC and EMC were purchased from BASF. Since EC is in solid form at
51
52 room temperature, NMR spectra for neat EC were acquired by dissolving EC in deuterated
53
54
55
56
57
58
59
60
61
62
63
64
65

chloroform (CDCl_3).

2.2 NMR Measurements

All ^{13}C NMR experiments were carried out on a Varian 600 MHz NMR spectrometer equipped with a Z axis gradient 5 mm triple resonance probe. The corresponding Larmor frequency was 150.933 MHz. A single 90° hard pulse with gated decoupling during data acquisition period was used. About 512 to 2048 scans were acquired for each spectrum with an acquisition time of about 0.9 s and a recycle delay time of 5 s. ^{13}C NMR spectra were externally referenced to TMS (assigned a value of 0.0 ppm). The peak assignments for the ^{13}C NMR spectra of EC, PC, EMC and TFSI were according to those in computer databases, i.e., ACD/NMR Databases from ACDLabs (<http://www.acdlabs.com>). Natural abundance ^{17}O NMR experiments were performed on a Varian-Agilent 900MHz NMR spectrometer equipped with a home-built large-sample-volume probe (15mm outer diameter). Details of the probe design and performance will be published in a separate paper.[25] The corresponding Larmor frequency was 122.041 MHz. A 25 μs long pulse was used for spectral excitation. The spectra were collected in 1000 - 30000 scans depending on the linewidth of the peaks, with an acquisition time of 25 ms and a recycle delay time of 0.5 s. ^{17}O NMR spectra were referenced to the oxygen resonance from deuterium oxide (D_2O , assigned a value of 0.0 ppm). Chemical shifts and linewidths of NMR signals were obtained by fitting Lorentzian functions to the experimental spectra using the NUTs program (v.2012, Acorn NMR Inc., Las Positas, CA, USA). All NMR measurements were carried out at room temperature (20°C).

2.3 DFT Calculations

Quantum chemical calculations were carried out using the Gaussian09 software suite.[27] The structures of all the molecules were built using GaussView 5.[28] Geometry optimization was computed using DFT and B3LPY methods with 6-31G(d,p) basis set.[29] NMR calculations were performed based on the geometry optimized structures at the same level of the theory and with the basis set of 6-311+G(2d,p) to calculate the chemical shielding for each atom except Fe, where the basis set of Fe atom is still 6-31G(d,p). The solvation mode is employed with the key word “SCRF” in the Gaussian input script, which requests that a calculation be performed in the presence of a solvent by placing the solute in a cavity within the solvent reaction field. The radius of molecules are obtained by using optimized single molecules with the key word “volume” into input script.

3. Results and discussions

3.1 NMR Experiments

3.1.1. ^{13}C NMR Studies

Carbon atoms are abundant in both solute and solvent molecules, especially in the Fc1N112^+ cation that contains 15 carbon atoms (see Chart 1), leading to high complexity in the ^{13}C NMR spectra of these samples. To help assign the peaks in mixed systems, ^{13}C NMR experiments were conducted separately on each of the solvents and their mixture, showing well distinguishable peaks (Figure S1). It is noted that the ^{13}C NMR peak positions of individual neat solvents remain unchanged in the mixtures, indicating no noticeable interactions taking place among or between these solvent molecules that are different from the interactions experienced in neat solvents. The PFG NMR results [21] on a mixture of the solvents demonstrate that the three components of the ternary solvent mixture (without solute) are equal, probably due to the common interactions

through the carbonyl groups found in each solvent molecule, and that they lie between the measured diffusion coefficients of neat PC and neat EMC.

An expanded view of the ^{13}C NMR spectra of both pristine ferrocene and Fc1N112-TFSI dissolved in a solvent mixture of EC/PC/EMC (4/1/5 by weight) at different concentrations is shown in Figure 1 (the full spectra are plotted in Figure S2). All of the peaks are well separated and identified, shown by the numbering in the molecular structures and the spectra. Chemically equivalent carbon atoms are labeled with the same numbering, for example C3, C6, C7, and C8. The integrated peak intensity increases in accordance with the number of carbon atoms, i.e., C1 : C2 : C3 : C4 : C5 : C6 : C7 : C8 being 1 : 1 : 2 : 1 : 1 : 2 : 2 : 5, further validating our peak assignments.

Comparing the ^{13}C NMR of the solvent mixture (Figure 1a) and the solutions (Figure 1b-e), the changing of the peak positions for all solvents, if there is any, is no more than 0.22 ppm (See Table 1 for details). Such shifts are typically negligible for ^{13}C NMR, indicating no chemical bonds formed on the solvent molecules with any solute molecules in good agreement with ^1H NMR studies performed previously.[6] This is further supported by the observation that the peak positions of the Fc1N112⁺ change slightly (by no more than 0.28 ppm) at the Fc1N112-TFSI concentrations from 0.1 M to saturation (Table S1). However, non-chemical interactions between the solvent and the Fc1N112-TFSI molecules are indeed occurring especially at higher Fc1N112-TFSI concentrations, evidenced by the small downfield displacements (to higher ppm, dotted lines in Figure 1), for example, C1, C2, C7, and C8 for Fc1N112⁺; C3 and C4 for both PC and EMC. Meanwhile, chemical shifts of C3, C4 and C5 also change considerably, but they change

1
2
3
4 first upfield and then downfield with the concentrations changing from 0.1M to <1.7M and then
5
6 saturation. These changes may be related to the solvation structures changes demonstrated in ^1H
7
8 T_1 relaxation studies.[22] Fast molecular exchanges arise between bulk solvent molecules and
9
10 those in solvation shells, where the exchange frequency is beyond the NMR detection time scale,
11
12 leading to an averaged peak position for each carbon atoms in NMR.[25] As the Fc1N112-TFSI
13
14 concentration increases, more solvent molecules will stay out of the bulk and remain for more
15
16 time in the solvation shell, causing a departure of chemical shifts from their original positions for
17
18 both solvents and Fc1N112^+ .
19
20
21
22
23
24
25

26 **3.1.2. ^{17}O NMR Studies**

27
28 For natural abundance ^{17}O NMR, the line-width matters more significantly than changes in
29
30 chemical shift values. Figure 2 shows the ^{17}O NMR spectra of the Fc1N112-TFSI solutions in
31
32 the same solvent mixture of EC/PC/EMC at concentrations of 0M, 0.25 M, 0.85 M and 1.70 M,
33
34 respectively. The chemical shifts of all peaks remain unchanged (Table S2), which again
35
36 indicates that no chemical bonds formed between the Fc1N112-TFSI and the solvent molecules.
37
38 The line-width of all peaks of both solvents and TFSI^- anions increase substantially with the
39
40 Fc1N112-TFSI concentration, reflecting more restricted molecular motions caused by stronger
41
42 solute-solvent interactions at higher concentrations.
43
44
45
46
47
48
49

50
51 Similar to the solvent molecules, fast exchange of the TFSI^- anions also takes place between the
52
53 bulk solvent and the solvation shell. When the concentration of Fc1N112-TFSI is low, i.e. 0.25
54
55 M, only a small proportion of the solvent molecules occupy the solvation shell around Fc1N112^+
56
57 and TFSI^- , along with rapid exchanges of both solvent molecules and TFSI^- anions between
58
59
60
61
62
63
64
65

positions in the solvation shell and in the bulk. Thus most of solvent molecules are in the bulk solvent while TFSI anions have less opportunity to stay into solvation shells of Fc1N112⁺ ions, leading to almost unchanged peak line-width. At higher Fc1N112-TFSI concentrations, the solvent molecules are depleted from the bulk and take part in the solvation shells. Both solvents and TFSI in the solvation shells are less isotropic than those in bulk solvent due to interactions with the Fc1N112⁺ cations. The exchanges slow substantially, increasing the line-widths of the ¹⁷O NMR peaks. A combination of ¹H T₁ measurements and molecular dynamics simulations provide additional molecular level details.[22]

3.2. DFT Calculation

The main goal of the computational studies of the NMR chemical shifts is to gain further insight into solvation phenomenon of electrolytes based on NMR experimental results. Since we employ TMS as the experimental reference standard, NMR parameters for the TMS molecule are calculated first to reference calculated results of ¹H and ¹³C NMR. The absolute ¹³C chemical shift of TMS molecule is obtained as -182.74 ppm by averaging shifts of four equivalent carbon atoms. Then all the other calculated results are referenced by adding 182.74 ppm to absolute values. Similarly, calculated results of ¹H NMR are referenced by adding 31.86 ppm to absolute values.

Chemical shifts of ¹³C associated with neat EC, PC, and EMC are calculated in the gas phase, i.e., using a single molecule. Figure 3a-c shows optimized structures of EC, PC, and EMC molecules. Comparison chemical shifts between calculated and experimental results are summarized in

Table 1 using TMS as the reference as discussed above. Results of calculations are observed to be reasonable in agreement with experimental data.

For Fc1N112-TFSI molecule, models of Fc1N112⁺ ion and TFSI⁻ anion are developed separately. Optimized structures in the gas phase are shown in Figure 3d-e. The structure of Fc1N112⁺ ion agrees with previous results carried out using the ADF program.[6] Calculated chemical shifts are summarized in Table S3, where values of C3, C6, C7, and C8 represent average shifts of those atoms denoted with the same labels in Chart 1.

In order to simulate the interaction between solute and solvent, we employ the solvation mode. Both Fc1N112⁺ ions and Fc1N112-TFSI molecules are optimized in this mode by setting relative dielectric constants (ϵ) and molecular radius of solvent molecules, where ϵ of the mixed solvent is estimated by linear combination according to the molar ratio of EC/PC/EMC. Chemical shifts of ¹³C are calculated based on the optimized structures and are summarized in Table S3. With the addition of TFSI⁻ anion, chemical shifts of all carbon atoms of Fc1N112 undergo varying degrees of changes. In all systems, C1 experience downfield displacements (towards higher ppm) through the effect of TFSI. C7 and C8 shift to downfield only in environments of alkyl carbonyl solvent, i.e. in PC or the mixture of EC/PC/EMC. Detailed comparisons between experiments and calculations are organized in Table 2. In experiments, chemical shifts of saturated electrolyte are higher than those of electrolyte at concentrations of 0.1M. In calculations, chemical shifts of TFSI-coordinated Fc1N112 are larger than those of isolated Fc1N112. The data in “shifts” row represents differences between that in row two and row one, indicating that the shift direction of calculation agrees satisfactorily with experiments where concentrations of the solute increase.

Therefore, isolated Fc1N112^+ ions represent the majority form in electrolytes at low concentrations, i.e. 0.1M. Conversely, TFSI-coordinated Fc1N112^+ ions (i.e. contacted ion-pairs) are accounted as the greater part in electrolytes at high concentrations (i.e. saturation). The combination of experiments and calculations demonstrates that Fc1N112^+ and TFSI^- experience more opportunities to associate with each other at high concentrations. In other words, most Fc1N112-TFSI is dissociated in the alkyl carbonyl solvent at low concentrations.

In terms of ion-pair structure, Fc1N112-TFSI molecule shows slight changes with different environmental parameters. Figure 4a shows the optimized structure of Fc1N112-TFSI in the gas phase. The positive charge is distributed near the nitrogen atom of Fc1N112^+ ,^[6] while the negative charge is concentrated on the nitrogen atom of TFSI^- . Consequently, the attractive force emerges between these two nitrogen atoms. The distance (D) between these two atoms is one simple measure of the extent of interaction between Fc1N112^+ and TFSI^- . The structure of Fc1N112-TFSI remains unchanged by visual observation when it is placed in the solvation environment. It is worth noting that D is altered with variations of environmental parameters. Figure 4b shows the relationship between D and dielectric constant(ϵ) of solvent, where ϵ of the gas phase is equivalent to 1. The data can be fit with a curve described by an inverted exponential form. The change of D indicates that TFSI^- moves away from Fc1N112^+ with increased value of ϵ . In other words, it is more probable for the solvent with high ϵ to dissociate the Fc1N112-TFSI ion pair.

In addition, we have investigated the effect of solute molecules on solvent molecules. In the NMR experiments, ^{13}C chemical shifts of PC and EMC experience minor changes with

concentrations of Fc1N112⁺. For the calculations, we consider two cases of solute molecule, i.e. dissociation and contact. In the case of dissociated ion-pair, single solvent molecules (i.e. PC and EMC) are placed together with Fc1N112⁺ ion and TFSI⁻ anion respectively (Figure 5a-b). After optimization, carbonyl oxygen (O_C) atoms orient towards the nitrogen atom of Fc1N112, indicating that cations are coordinated by O_C atoms of solvent molecules. The O_C is attracted by the pendant arm due to the positive charge on the nitrogen atom and lone ion pair of O_C. Based on the optimization, calculated chemical shifts of ¹³C of PC and EMC are summarized in Table 3. Chemical shift values of majorities of carbon atoms increase (shift downfield) when solvent molecules are coordinated with either Fc1N112⁺ or TFSI⁻. Although the chemical shift of C4 of PC becomes slightly smaller due to the association with of Fc1N112⁺, the interaction of TFSI drives it towards the opposite direction more severely. Since the ratio of Fc1N112⁺ to TFSI⁻ in electrolytes is 1:1, the total effect of Fc1N112-TFSI on the chemical shifts can be estimated in accordance with the following equation.

$$\delta_E = (\delta_F - \delta_S) + (\delta_T - \delta_S) , \quad [1]$$

where δ_S , δ_F , and δ_T are chemical shifts of single, Fc1N112-coordinated, and TFSI-coordinated molecules, respectively. For C4 of PC, $\delta_S = 19.47$ ppm, $\delta_F = 19.30$ ppm, $\delta_T = 20.50$ ppm, thus the estimated total displacement, δ_E , is calculated to be 0.86 ppm. Similarly, C3 and C4 of EMC receive combined effects of interactions with solute molecules, and then shifts of 0.6 ppm and 0.52 ppm are predicted based on Eq. [1]. In general, carbon atoms of both PC and EMC become less shielding (shift towards higher ppm), when PC and EMC interact with solute molecules, or when solvent molecules form solvation shells. In the case of contact ion-pair, we develop a system of solvent molecule coordinated by contacted Fc1N112-TFSI pair. Optimized structures show that solvent molecules are located near the Cp ring of solute molecule (Figure

5c). It can be observed from Table 3 that ^{13}C chemical shifts of solvent molecules in this system move downfield compared with those of single solvent molecules (except C4 of EMC).

In experiments, relatively small values for perturbations of chemical shifts arise at low concentrations, i.e. 0.1M, while large values of shifts are measured at high concentrations, i.e. saturation (Table 1). Therefore, we concluded that most of solvent molecules are found as bulk solvent in electrolytes at low concentrations, resulting in small changes of chemical shifts. Conversely, majorities of solvent molecules are coordinated with Fc1N112^+ or TFSI^- , or Fc1N112-TFSI contact ion-pairs, thus behaving as direct solvation shells in electrolytes at high concentrations, leading to larger shifts. Based on simple chemical exchange theory, spectra show average chemical shifts of in the fast exchange regime, and therefore the bulk solvent constitutes the majority species at low concentrations, and the observed average shifts approach those of mixed solvent (Figure 1a). Similarly, the bulk solvent gradually forms solvation shells with the increase of concentrations, causing the dominance of solvent molecules in solvent shells, and resulting in peak-center displacements towards those of coordinated solvent molecules.

Taking advantage of optimized structures in ^{13}C NMR calculations, we perform ^1H chemical shifts calculations of solvent molecules, and results are summarized in Table S4. Notably, calculated values of free solvent molecules are in disagreement with chemical shifts of mixed solvent in experiments. To account for more complex intermolecular interaction, we perform solvent molecules ^1H NMR calculations by using multiple copies of solvent molecules surrounding a central solvent molecule and consider only the values obtained from the central one (Figure 5d). With increases in the number of solvent molecules, ^1H chemical shifts move

1
2
3
4 towards downfield. When the numbers of solvent molecules are five, i.e. one is surrounded by
5
6 four, for EC, or six for PC and EMC, calculated chemical shifts of central ones are satisfactorily
7
8 in agreement with those of mixed solvent in experiments (See Table 4 for comparisons).
9
10

11
12
13 Similar to ^{13}C calculations, ^1H shifts of solvent molecules in the present of Fc1N112-TFSI can be
14
15 estimated by taking averages of values of Fc1N112-coordinated and TFSI-coordinated systems
16
17 (Table S4). It can be observed from the table that estimated results disagree with experimental
18
19 results at either low or saturated concentration. In the case of 0.1M concentration, number of
20
21 bulk solvent molecules is far greater than that within solvation shells, thus the effect of
22
23 coordinated solvent molecules on the observed ^1H chemical shifts is negligible under rapid
24
25 molecular exchange. On the other hand, because most solvent molecules are in solvation shell in
26
27 saturated electrolyte, coordinated species dominate observed chemical shifts. Disagreements of
28
29 chemical shifts of solvent molecules between the ion-coordinated in calculations and saturated
30
31 electrolyte in experiments indicate that Fc1N112^+ and TFSI^- are contacted ion-pair rather than
32
33 dissociated at saturated concentration. We use structure of Fc1N112-TFSI-coordinated solvent
34
35 molecules to verify the conclusion (Figure 5c). Based on optimized structures, calculated ^1H
36
37 chemical shifts agree satisfactorily with those of saturated electrolyte in experiments (Table 4).
38
39 Additionally, shifts of solvent molecules move upfield (towards small ppm values) under the
40
41 effect of solute molecule, and differences between these two systems in calculations (Table 4)
42
43 are in agreement with displacements from low to high concentrations in experiments (Table S5).
44
45 These results confirm that major type of ion-pair in saturated electrolyte is contact rather than
46
47 dissociation. This argument is further supported by electrochemical performance of the solute at
48
49 different concentrations. In the cyclic voltammograms (CVs) of Fc1N112-TFSI shown in Figure
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

S3, the oxidation and reduction peak separations at 5.0 mM are significantly smaller than those at 0.1 M. The smaller peak separation reflects higher electrochemical reversibility under lower solute concentration. The Fc1N112⁺ and TFSI⁻ ions are more dissociated, have better mobility and thus respond more rapidly to the sweeping voltage. This is in good agreement with the NMR study.

Previous work has verified that dimethyl sulfoxide (DMSO) is more suitable as a reference for ¹⁷O NMR calculations than H₂O.[25] Additionally, the ¹⁷O chemical shift of DMSO is ~20 ppm larger than that of H₂O.[25, 30, 31] Hence, calculated absolute shifts are converted to results of calculations by adding 269.51 ppm where the absolute shift of DMSO is calculated to be 249.51 ppm.

Since intermolecular interactions in liquid phase would affect ¹⁷O chemical shifts,[25] calculations on both single and double solvent molecules are carried out. Results using double molecules are in much better agreement with the values obtained from experiments (see Table S6 for detail). Using optimized structures of solvent molecules coordinated by Fc1N112⁺ or TFSI⁻ (as discussed above), we compute ¹⁷O chemical shifts of solvent molecules (Table S6). Attentive comparisons of results between calculations and experiments are organized in Table 5. Similar to ¹H calculations, ¹⁷O shifts of solvent molecules that are influenced by Fc1N112⁺ or TFSI⁻ are fairly different, and those shifts under total effect of Fc1N112-TFSI contact ion-pairs can be estimated by taking averages of values of Fc1N112-coordinated and TFSI-coordinated systems (Table 5). Because of the insignificant changes of experimental ¹⁷O shifts in electrolytes at different concentrations (Figure 2), we calculate average values from systems of 0.25M,

0.85M and 1.7M in order to facilitate comparisons. It is observed in Table 5 that estimated results agree excellently with results of experiments. The consistency acts as a strong evidence of fast exchanges of solvent molecules. Specifically, solvent molecules in solvation shells of both Fc1N112^+ and TFSI^- exchange with those in the bulk solvent, resulting in averaged ^{17}O chemical shifts.

4. Conclusion

We have performed ^{13}C and ^{17}O NMR to understand the dissolution mechanism of Fc1N112-TFSI in mixed solvent composed of EC, PC, and EMC. The DFT calculations on ^1H , ^{13}C , and ^{17}O NMR reveal molecular-level details of chemical shifts and linewidth change with concentrations of solute. Interactions between solute and solvent molecules, ion association, and molecular motions are strongly proved by both experimental and theoretic studies. At dilute solute concentrations, the cation and the anion associated with Fc1N112-TFSI are dissociated, forming their own solvation shells. Molecules of EC, PC and EMC surround Fc1N112^+ ions as solvation shells, leading to the high solubility of Fc1N112-TFSI . In this case, TFSI^- anions have rare opportunities to influence chemical shifts of Fc1N112^+ . Rapid exchanges of both TFSI^- anions and solvent molecules take place between solvation shells and bulk, resulting in average observed chemical shifts in NMR experiments. Molecules in the bulk solvent outnumber those in solvation shells, and dominate chemical shifts of the solvent. With increasing concentrations of solute, Fc1N112-TFSI gradually turns into solvent-shared state. At saturated concentration, contact ion pairs are formed and the solvent molecules are interacting with the Fc rings rather than interacting with the ionic pendant arm of Fc1N112-TFSI . In this case, molecular motion is

1
2
3
4 restricted, leading to broad ^{17}O NMR peaks. However, molecular exchanges are still fast and
5
6 random enough to result in sufficiently narrow NMR peaks of ^1H and ^{13}C .
7
8

9 The study offers a mechanistic understanding at the molecular scale of solubility increase for the
10
11 Fc1N112-TFSI as compared to pristine ferrocene. Since the quaternary ammonium is the
12
13 preferred solvation site, incorporation of one or more such moieties into redox molecules can be
14
15 a universal molecular engineering method to improve material solubility. This finding will
16
17 greatly advance the development of high energy density NRFBs. The results also suggest that
18
19 organic solvents with high ϵ are more capable of dissociating the ion-pair in Fc1N112-TFSI and
20
21 yield flexible mobility of the charged ions. Therefore, at battery relevant conditions, i.e. high
22
23 Fc1N112-TFSI concentrations, high- ϵ organic solvents such as acetonitrile or dimethyl sulfoxide
24
25 may be better options provided they are compatible with the redox species.
26
27
28
29
30
31
32

33 **Acknowledgment**

34
35
36
37

38 This work was led intellectually as part of the Joint Center for Energy Storage Research (JCESR),
39
40 an Energy Innovation Hub funded by the U.S. Department of Energy, Office of Science, Basic
41
42 Energy Sciences (BES). The NMR sample preparations were supported by the funding from the
43
44 U.S. Department of Energy's (DOE's) Office of Electricity Delivery and Energy Reliability (OE)
45
46 (under Contract No. 57558). The NMR, and computational studies were conducted in the
47
48 William R. Wiley Environmental Molecular Sciences Laboratory (EMSL), a national scientific
49
50 user facility sponsored by DOE's Office of Biological and Environmental Research (BER) and
51
52 located at PNNL. Xuchu Deng was partially supported by the National Natural Science Fund of
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 China under Grant 21327001. PNNL is operated by Battelle for the Department of Energy under
5
6
7 Contract DE-AC05- 76RLO1830.
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Reference

- [1] A.Z. Weber, M.M. Mench, J.P. Meyers, P.N. Ross, J.T. Gostick, Q.H. Liu, *J Appl Electrochem*, 41 (2011) 1137-1164.
- [2] M. Skyllas-Kazacos, M.H. Chakrabarti, S.A. Hajimolana, F.S. Mjalli, M. Saleem, *J Electrochem Soc*, 158 (2011) R55-R79.
- [3] P. Leung, X.H. Li, C.P. de Leon, L. Berlouis, C.T.J. Low, F.C. Walsh, *RSC Adv.*, 2 (2012) 10125-10156.
- [4] W. Wang, Q.T. Luo, B. Li, X.L. Wei, L.Y. Li, Z.G. Yang, *Adv Funct Mater*, 23 (2013) 970-986.
- [5] S.H. Shin, S.H. Yun, S.H. Moon, *RSC Adv.*, 3 (2013) 9095-9116.
- [6] X.L. Wei, L. Cosimbescu, W. Xu, J.Z. Hu, M. Vijayakumar, J. Feng, M.Y. Hu, X.C. Deng, J. Xiao, J. Liu, V. Sprenkle, W. Wang, *Adv. Energy Mater.*, 5 (2015).
- [7] P.J. Cappillino, H.D. Pratt, N.S. Hudak, N.C. Tomson, T.M. Anderson, M.R. Anstey, *Adv. Energy Mater.*, 4 (2014).
- [8] A.E.S. Sleightholme, A.A. Shinkle, Q.H. Liu, Y.D. Li, C.W. Monroe, L.T. Thompson, *J Power Sources*, 196 (2011) 5742-5745.
- [9] H.D. Pratt, A.J. Rose, C.L. Staiger, D. Ingersoll, T.M. Anderson, *Dalton transactions*, 40 (2011) 11396-11401.
- [10] X.L. Wei, W. Xu, J.H. Huang, L. Zhang, E. Walter, C. Lawrence, M. Vijayakumar, W.A. Henderson, T.B. Liu, L. Cosimbescu, B. Li, V. Sprenkle, W. Wang, *Angew Chem Int Edit*, 54 (2015) 8684-8687.
- [11] F.R. Brushett, J.T. Vaughey, A.N. Jansen, *Adv. Energy Mater.*, 2 (2012) 1390-1396.
- [12] Z. Li, S. Li, S.Q. Liu, K.L. Huang, D. Fang, F.C. Wang, S. Peng, *Electrochem Solid St*, 14 (2011) A171-A173.
- [13] G. Nagarjuna, J.S. Hui, K.J. Cheng, T. Lichtenstein, M. Shen, J.S. Moore, J. Rodriguez-Lopez, *J Am Chem Soc*, 136 (2014) 16309-16316.

- [14] F.Y. Fan, W.H. Woodford, Z. Li, N. Baram, K.C. Smith, A. Helal, G.H. McKinley, W.C. Carter, Y.M. Chiang, *Nano Lett*, 14 (2014) 2210-2218.
- [15] Y. Yang, G.Y. Zheng, Y. Cui, *Energy Environ. Sci.*, 6 (2013) 1552-1558.
- [16] S. Hamelet, D. Larcher, L. Dupont, J.M. Tarascon, *J Electrochem Soc*, 160 (2013) A516-A520.
- [17] Y.R. Wang, P. He, H.S. Zhou, *Adv. Energy Mater.*, 2 (2012) 770-779.
- [18] W. Wang, W. Xu, L. Cosimbescu, D.W. Choi, L.Y. Li, Z.G. Yang, *Chem Commun*, 48 (2012) 6669-6671.
- [19] M. Duduta, B. Ho, V.C. Wood, P. Limthongkul, V.E. Brunini, W.C. Carter, Y.M. Chiang, *Adv. Energy Mater.*, 1 (2011) 511-516.
- [20] X. Wei, W. Xu, M. Vijayakumar, L. Cosimbescu, L. Tianbiao, V. Sprenkle, W. Wang, *Adv Mater*, 26 (2014) 7649-7653.
- [21] K.S. Han, N.N. Rajput, X.L. Wei, W. Wang, J.Z. Hu, K.A. Persson, K.T. Mueller, *J Chem Phys*, 141 (2014).
- [22] K.S. Han, N.N. Rajput, M. Vijayakumar, X.L. Wei, W. Wang, J.Z. Hu, K.A. Persson, K.T. Mueller, Preferential Solvation of an Asymmetric Redox Molecule. Submitted, (2015).
- [23] X. Bogle, R. Vazquez, S. Greenbaum, A.V. Cresce, K. Xu, *J. Phys. Chem. Lett.*, 4 (2013) 1664-1668.
- [24] L. Yang, A. Xiao, B.L. Lucht, *J Mol Liq*, 154 (2010) 131-133.
- [25] X. Deng, M.Y. Hu, X. Wei, W. Wang, Z. Chen, J. Liu, J.Z. Hu, *J Power Sources*, 285 (2015) 146-155.
- [26] L. Cosimbescu, X. Wei, M. Vijayakumar, W. Xu, M.L. Helm, S.D. Burton, C.M. Sorensen, J. Liu, V. Sprenkle, W. Wang, *Sci Rep-Uk*, Accepted (2015).
- [27] M.J.T. Frisch, G. W.; Schlegel, H. B.; Scuseria, G. E.; Robb, M. A.; Cheeseman, J. R.; Scalmani, G.; Barone, V.; Mennucci, B.; Petersson, G. A.; Nakatsuji, H.; Caricato, M.; Li, X.; Hratchian, H. P.; Izmaylov, A. F.; Bloino, J.; Zheng, G.; Sonnenberg, J. L.; Hada, M.; Ehara, M.; Toyota, K.; Fukuda, R.;

1
2
3
4 Hasegawa, J.; Ishida, M.; Nakajima, T.; Honda, Y.; Kitao, O.; Nakai, H.; Vreven, T.; Montgomery, J. A.,
5
6 Jr.; Peralta, J. E.; Ogliaro, F.; Bearpark, M.; Heyd, J. J.; Brothers, E.; Kudin, K. N.; Staroverov, V. N.;
7
8 Kobayashi, R.; Normand, J.; Raghavachari, K.; Rendell, A.; Burant, J. C.; Iyengar, S. S.; Tomasi, J.;
9
10 Cossi, M.; Rega, N.; Millam, J. M.; Klene, M.; Knox, J. E.; Cross, J. B.; Bakken, V.; Adamo, C.;
11
12 Jaramillo, J.; Gomperts, R.; Stratmann, R. E.; Yazyev, O.; Austin, A. J.; Cammi, R.; Pomelli, C.;
13
14 Ochterski, J. W.; Martin, R. L.; Morokuma, K.; Zakrzewski, V. G.; Voth, G. A.; Salvador, P.;
15
16 Dannenberg, J. J.; Dapprich, S.; Daniels, A. D.; Farkas, Ö.; Foresman, J. B.; Ortiz, J. V.; Cioslowski, J.;
17
18 Fox, D. J. Gaussian, Inc., Wallingford CT, (2009).
19
20
21
22 [28] R.K. Dennington, Todd; Millam, John. Semichem Inc., Shawnee Mission, KS, (2009).
23
24 [29] A.D. Becke, *Phys Rev A*, 38 (1988) 3098-3100.
25
26 [30] J.C. Dyer, D.L. Harris, S.A. Evans, *J Org Chem*, 47 (1982) 3660-3664.
27
28 [31] E. Block, A.A. Bazzi, J.B. Lambert, S.M. Wharry, K.K. Andersen, D.C. Dittmer, B.H. Patwardhan,
29
30 D.J.H. Smith, *J Org Chem*, 45 (1980) 4807-4810.
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Table 1. ^{13}C chemical shifts of solvent molecules in both experiments and calculations (ppm).

Systems	EC		PC				EMC			
	C1	C2, C3	C1	C2	C3	C4	C1	C2	C3	C4
EC/PC/EMC	155.92	65.08	155.29	74.00	70.75	18.30	155.68	63.68	54.00	13.50
0.2 M pristine Fc	155.91	65.09	155.29	74.00	70.76	18.35	155.69	63.71	54.04	13.56
0.1 M Fc1N112-TFSI	155.92	65.05	155.29	73.99	70.73	18.30	155.66	63.66	53.97	13.49
<1.7 M Fc1N112-TFSI	155.92	64.99	155.30	73.96	70.67	18.38	155.52	63.70	54.07	13.61
Saturated Fc1N112-TFSI	156.03	65.05	155.41	74.07	70.78	18.48	155.63	63.79	54.18	13.71
DFT Calculations	161.19	66.15	161.08	77.47	73.93	19.47	165.04	67.87	55.99	15.33

Table 2. Comparisons of ^{13}C chemical shifts on Fc1N112 between experiments and calculations (ppm).^a

Systems	C1		C7		C8	
	Exp.	Cal.	Exp.	Cal.	Exp.	Cal.
Low concentration	7.40	9.73	70.30	75.64	69.14	74.14
High concentration	7.49	9.77	70.46	76.11	69.30	74.44
Shifts	0.09	0.04	0.16	0.47	0.16	0.30

^a For experimental data, low and high concentrations are corresponding to 0.1M and saturation respectively; for calculated data, low concentration indicates isolated Fc1N112⁺ ion in solvation mode, while high concentration indicates Fc1N112-TFSI pair in solvation mode.

Table 3. Calculated ^{13}C chemical shifts of solvent in different systems (ppm).

Systems	PC				EMC			
	C1	C2	C3	C4	C1	C2	C3	C4
Single molecule	161.08	77.47	73.93	19.47	165.04	67.87	55.99	15.33
Fc1N112-coordinated	166.12	82.14	76.27	19.30	167.97	70.02	56.82	15.05
TFSI-coordinated	164.87	79.73	75.54	20.50	164.97	68.33	55.76	16.13
Fc1N112-TFSI-coordinated	162.50	78.87	74.48	19.52	165.83	69.08	56.37	15.07

Table 4. Comparisons of ^1H chemical shifts on solvent molecules between calculations ^a and experiments ^b (ppm).

Systems	EC		PC			EMC		
	H2, H3	H2	H3	H4	H2	H3	H4	
Surrounded solvent molecules (Cal.)	4.89	5.33	4.76	4.25	1.57	4.61	3.80	1.33
EC/PC/EMC (Exp.)	4.91	5.28	4.97	4.44	1.81	4.51	4.09	1.62
Fc1N112-TFSI-coordinated solvent molecules (Cal.)	4.45	4.84	4.44	3.88	1.41	4.24	3.80	1.29
Saturated Fc1N112-TFSI (Exp.)	4.48	4.86	4.55	4.01	1.39	4.10	3.68	1.22
Displacements ^c	-0.44	-0.49	-0.32	-0.37	-0.16	-0.37	0	-0.04

^a Surrounded solvent molecules are corresponding to clusters of Five EC, six PC, and six EMC.

^b Experimental results of Wei et al's works.

^c Differences of values between Fc1N112-TFSI-coordinated and surrounded solvent molecules.

Table 5. Comparisons of ^{17}O chemical shifts on solvent molecules between experiments and calculations (ppm).

Systems	EC	PC		EMC	
	O2, O3	O2	O3	O2	O3
Fc1N112-Coordinated	112.62	141.17	120.45	127.39	98.58
TFSI-Coordinated	107.78	135.85	107.78	120.09	89.30
Calculated Average ^a	110.20	138.51	114.12	123.74	93.94
Experimental Average	111.08	138.57	114.80	122.66	94.06

^a Averages of values of Fc1N112-Coordinated and TFSI-Coordinated.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure captions

Chart 1. The labeling of the carbon sites and the formula of EC, PC, EMC Fc1N112^+ and TFSI^- .

Figure 1. The ^{13}C NMR spectra of (a) the solvent mixture of EC/PC/EMC (4/1/5 by weight); (b) 0.2 M Fc; (c) 0.1 M Fc1N112-TFSI; (d) <1.7 M Fc1N112-TFSI; (e) Saturated Fc1N112-TFSI.

Figure 2. ^{17}O NMR spectra of Fc1N112-TFSI dissolved in the solvent mixture of EC/PC/EMC at concentrations of (a) 0 M, (b) 0.25 M, (c) 0.85 M and (d) 1.7 M.

Figure 3. Optimized structures of molecules and ions in the gas phase: (a) EC; (b) PC; (c) EMC; (d) Fc1N112^+ ; (e) TFSI^- .

Figure 4. The effect of ϵ on structures of solute molecule. (a) The optimized structure of Fc1N112-TFSI in gas phase; (b) The relationship between D and ϵ .

Figure 5. Optimized structures of: (a) coordination of Fc1N112 and PC; (b) coordination of TFSI and PC; (c) coordination of Fc1N112-TFSI and PC; (d) six PC molecules, where one surrounded by five. Taking PC for example, EC and EMC are also calculated in these systems, and results are not shown in this figure.

Low Concentrations

High Concentrations