Elevated Temperature Performance of High Voltage $\text{Li}_{1+y}\text{Mn}_{1.5}\text{Ni}_{0.5}\text{O}_{4-x}\text{F}_x$ Spinel in Window-Shifted Li-ion Cells

Nathalie Pereira, Michael C. Ruotolo, Matthew Y. Lu, Fadwa Badway, and Glenn G.*

Amatucci

Energy Storage Research Group, Department of Materials Science and Engineering,

Rutgers the State University of New Jersey, North Brunswick, NJ 08902, USA

* corresponding author: (email) npereira@rutgers.edu, (tel.) 848-932-0930, (fax) 732-932-6855

ABSTRACT

Although the $\text{LiMn}_{1.5}\text{Ni}_{0.5}\text{O}_4$ spinel operating at 4.7 V presents some beneficial characteristics over more traditional positive electrode materials, instability issues at elevated temperature have limited its practical use so far. While we previously proposed $\text{Li}_{1+y}\text{Mn}_{1.5}\text{Ni}_{0.5}\text{O}_{4-x}\text{F}_x$ (LMNOF) spinel that is intrinsically stable at elevated temperatures in Li-excess half-cell configuration, we investigate herein fixed, non-excess Li-content window-shifted Li-ion systems. By utilizing $\text{Li}_4\text{Ti}_5\text{O}_{12}$ (LTO) or TiS_2 negative electrodes stable in broad electrolyte compositions instead of carbonaceous electrodes, we aim at limiting the Li-consuming side reactions such as the formation of solid-electrolyte interphase and enable a focus on the exploration of electrolyte compositions including additives. Utilizing such an approach, excellent fundamental stability of LMNOF in a fixed Li-content Li-ion environment is demonstrated at 55°C with the use of relatively common electrolyte components.

KEYWORDS

High voltage cathode spinel, Li-ion, window-shifted systems, high-temperature cycling stability, lithium titanate, titanium disulfide

INTRODUCTION

Much effort has been devoted to the 4.7 V $\text{LiMn}_{1.5}\text{Ni}_{0.5}\text{O}_4$ (LMNO) spinel since higher potentials and therefore hopes for energy density gains were reported upon substitution of Ni for Mn in the LiMn_2O_4 (LMO) spinel framework [1-4]. The high voltage spinel present many sought-after qualities for application in Li-ion batteries including $>130 \text{ mAh g}^{-1}$ specific capacity, high operating voltage, low initial capacity loss, good rate performance, good cycling stability after optimization (at room temperature) and low cost (compared to the Co-rich materials). While the LMNO spinel's room temperature performance is quite satisfying, instability issues develop upon storage and cycling at elevated temperature currently limiting practical use. Sluggish kinetics associated to surface-related phenomena rather than active material degradation was reported as the root-cause for poor cycling performance at 60 °C. Surface chemistry of the material, transition metal dissolution, and the cathode electrolyte interface (CEI) have all been connected to the impedance rise at elevated temperature [5-8]. Back in 2008, Patoux et al. reported half-cells showing retaining 77 % capacity after 400 cycles at 55 °C through optimization of material and electrode formulation, slowing down the electrolyte instability [9].

It is clear that there is a degree of intrinsic passivation induced by surface transformation at the 4.7 V high voltage spinel surface. Ten years ago, Talyosef et al. [6] and Aurbach et al. [7]

indicated that the surface becomes Ni-poor resulting in a fine degree of MnO_2 like decomposition product. Our results on the elevated temperature properties of LMNO seems to support this argument as it was found that after an initial loss in capacity the capacity loss as a function of cycle number decreased markedly. We have also shown that the modification of the surface chemistry through ex-situ acid etching of the surface to induce such a MnO_2 surface layer has a very significant effect on the stabilization of the material at elevated temperature [8]. Other teams have focused on the use of thin coatings at the surface of the positive electrode material in order to minimize deleterious interactions with the electrolyte [10-16]. These surface treatments have all brought some degree of relief in terms of elevated temperature instability but progress remains marginal. We more recently achieved further advances through intrinsic stabilization of the spinel itself rather than just focusing at the surface where reactions with electrolyte occur [17]. The development of a fluorinated $\text{Li}_{1+y}\text{Mn}_{1.5}\text{Ni}_{0.5}\text{O}_{4-x}\text{F}_x$ ($0 \leq x \leq 0.5$, $0 \leq y \leq 0.3$) (LMNOF) material fabricated by a novel two-step solid-state fabrication procedure [17, 18] enabled exceptionally stable cycling in lithium half-cell with a capacity retention of 80% after 600 cycles at 60 °C. Interestingly, no drastic failure was observed and instead the capacity faded continuously to a 50% loss after 1400 cycles.

Despite such promising performance one cannot rely solely on half-cell data as a sufficient mark of the expected performance in a balanced Li-ion cell. Indeed numerous phenomena are present in such systems that work against perceived notions of stability and have haunted researchers for decades. The Li-ion system is a closed Li-content system where any parasitic reactions consuming Li has a devastating effect to the resulting stability of the cycling. This can be represented by the formation of cathode electrolyte interphase (CEI), solid electrolyte interphase

(SEI) layers form intrinsic reactions with the electrolyte at the anode, or contaminants in the electrolyte such as water or other species. Furthermore, fade as a function of cycle number can be induced by very complex interactions of deleterious species forming at the opposing electrode. A classic example of this is found in the LiMn_2O_4 -based system versus graphite [19, 20]. However, in contrast to the commonly accepted disproportionation reaction of Mn^{3+} as source of free Mn^{2+} subsequently reduced at the graphite negative electrode [21] recent investigations have proposed the formation of Mn^{2+} during charge and integration of a variety of $\text{Mn}^{2+/3+}$ and Ni^{2+} complexes/compounds into the graphite SEI. The latter could potentially partially dissolve in the electrolyte leading to continual capacity fading [22-25]. Finally, presence of HF either initially present in the system as an impurity or generated upon electrolyte decomposition is known to exacerbate the transition metal dissolution process thereby accelerating the failure process [15, 26-28].

Parallel efforts have been dedicated to understand the electrolyte decomposition processes [29] and the interaction reactions with LMNO [30, 31] to resolve the capacity fading issue from the electrolyte perspective by developing more suitable electrolytes with enhanced anodic stability compared to the commercialized carbonate-based electrolyte. The impact of salt, (co)solvent and additives have been previously investigated as a function of temperature, storage and cycling [32-35]. Many have searched for alternatives to the commonly used LiPF_6 salt that inherently generates deleterious HF within the cell. Fluorinated carbonates [36, 37], ionic liquids [38-40], and sulfones [41], to site just a few examples have been evaluated as solvent and (co)-solvent in search for improved anodic stability compared to the alkyl carbonates typically used in the industry. Finally, many electrolyte additives have also been assessed. Additives initially existing

as a salt/solid form include tris(hexafluoro-iso-propyl)phosphate (HFiP) [42], lithium bis(oxalate)borate (LiBOB) [43-55], while liquid additives consists of solvents such as vinylidene carbonate (VC) [28, 46-54], fluoroethylene carbonate (FEC) [52, 54-56], and dimethyl methylphosphate (DMMP) [57]. While these studies have advanced the comprehension of the intricate reactions occurring during cycling and realized some enhancements in capacity retention, some of the new systems suffer from high viscosity and low conductivity and may not provide a stable SEI on the carbonaceous negative electrodes thereby preventing from achieving cyclability levels required for practical use.

In 2003, Ariyoshi et al. first reported on the 3V window-shifted system based on LMNO positive electrode and LTO negative electrode to demonstrate high rate capability and long cycle life with 83% capacity retained after 1100 cycles at room temperature [9, 58, 59]. Li-ion batteries based on negative electrodes of higher potentials than the state of the art carbonaceous-based graphite have been referred to as voltage “window-shifted” systems, on the basis of the shift in voltage of the cells. In more correct terms, both the negative and positive electrode potentials should be increased to result in a true “window-shifted” cell vs. a “window-closing” cell. Other studies have determined LTO-limited systems exhibit better tolerance to high voltage and overcharge [60, 61]. As opposed to the general acceptance of LTO as a passivation-free material due its 1.55V potential above the carbonate-based electrolytes reduction potential, passivation was evidenced at the surface of LTO [62, 63]. However, significant gassing observed in LTO-based cells with the release of H₂, CO and CO₂ may prevent its use in commercial applications [63-66]. The release of H₂ has been correlated to the presence of water contamination in the cells, which implies control of the cell assembly may provide some relief.

Herein we investigate Li-ion window-shifted systems based on the stabilized LMNOF positive electrodes we previously developed to confirm no parasitic processes consuming lithium occurred. We have chosen to work with window shifted systems initially for the fact it gives us the most freedom to explore electrolytes and additives without being influenced by the affect of such on the SEI of graphite while still enabling a fixed content, non excess Li environment. Although we established that LMNOF offers exceptional elevated temperature and voltage stability (versus lithium metal), even cycling in relatively stable negative electrodes such as LTO still presents challenges to proper electrolyte selection for such improved performance to be realized at the Li-ion cell level. We thereby discuss optimization of such system under stress by visiting critical factors such as LTO material source, cell balancing, electrolyte salts, solvents and additives at 55 °C. The use of TiS_2 as an alternate window-shifted negative electrode is also proposed.

EXPERIMENTAL

Materials and Synthesis: Low surface area ($2\text{-}4\text{ m}^2\text{ g}^{-1}$) lithium-excess lithium nickel manganese oxyfluoride $\text{Li}_{1.1}\text{Mn}_{1.5}\text{Ni}_{0.5}\text{O}_{4-y}\text{F}_{0.2}$ (LMNOF) material was fabricated via a two-step solid-state synthesis process [18]. The first step consisted in the synthesis of a core spinel NiMn_2O_4 that was lithiated and fluorinated in a second step. Initially, the oxide precursors NiO (Aldrich) and MnO_2 (Broken Hill Proprietary's [BHP] Australian EMD) were mixed in acetone for enhanced homogeneity. After drying overnight at 110°C to remove the solvent completely, the mixture was heat-treated at 900°C for 10 hours to generate the NiMn_2O_4 core. Lithium fluoride (Aldrich) and lithium carbonate (Aldrich) was mixed to NiMn_2O_4 and heat-treated at

800 °C for 12 hours.

$\text{Li}_4\text{Ti}_5\text{O}_{12}$ lithium titanium oxide (LTO) was also fabricated but in a single step process with a heat-treatment at 780 °C for 24 hours after wet mixing of the titanium oxide (Rutile, Aldrich) and lithium carbonate precursors (Aldrich) in ethanol (Aldrich). The LTO material synthesized herein of low surface area ($2 \text{ m}^2 \text{ g}^{-1}$) was compared to a higher surface area ($59.5 \text{ m}^2 \text{ g}^{-1}$) material obtained from a commercial source (Altair). Structural analysis of both materials reveals LTO spinel with broader diffraction peaks associated to the smaller particle size commercial sample. As a result, hereunder each material is referenced as “macro”-LTO and “nano”-LTO, respectively. Finally, titanium disulfide (TiS_2) was purchased from a commercial source (Aldrich) and utilized as received.

All materials evaluated as electrolyte additives were also utilized as received and herein quantified as weight percent of the electrolyte weight: lithium bis(oxalato)borate (LiBOB, BASF), succinic anhydride (SA, 40000 average molecular weight polyvinylpyrrolidinone (PVP, Aldrich), 5000 average molecular weight poly(2-vinylpyridine) (P2VP, Aldrich) and vinylidene carbonate (VC, BASF).

Battery grade solvents such as linear carbonates, dimethyl carbonate (DMC) (BASF, 3 ppm H_2O) and ethyl methyl carbonate (EMC) (BASF, 3 ppm H_2O), gamma-butyrolactone (γ -GBL), and tetramethylene sulfone (TMS) as well as electrolyte salts and pre-mixtures were purchased from BASF and utilized as received. Adiponitrile (ADN) was however dried on molecular sieves

(Sigma) in order to achieve < 5 ppm H_2O content. Water content was measured using a KF coulometer (831, Metrohm).

Electrochemical testing: All active powder materials were dried at $350\text{ }^\circ\text{C}$ prior to tape casting following the Bellcore process [67]. The $\text{Li}_4\text{Ti}_5\text{O}_{12}$ - and TiS_2 - (Aldrich or Strem Chemicals) based electrodes were fabricated from 70 wt.% active, 10 wt.% carbon additive (SP, MMM) and 20 wt.% binder (2801, Alf Atochem) mixtures added to dibutyl phthalate (Aldrich) plasticizer in acetone (Aldrich). The LMNOF-based electrodes comprised 80 wt.% active, 10 wt.% carbon additive and 10 wt.% binder, or otherwise as stated in the text. All electrode tapes were dipped in diethyl ether (Aldrich) to extract the plasticizer prior to drying under vacuum and assembly. In Li-ion cell configuration, the negative electrode loadings of 8 mg cm^{-2} were matched as needed to positive electrode active loadings. All electrochemical cells were assembled in an argon atmosphere glovebox using Al-clad CR-2032 coin cells (Hohsen). Both half and Li-ion cells utilized glass-fiber separators embedded in the electrolyte specified in the text and tested in galvanostatic mode (Series 4000 Maccor Battery Test System) at both 24 and $55\text{ }^\circ\text{C}$.

All materials were first tested in half-cell configuration based on lithium metal (FMC) counter electrodes using 1M LiPF_6 in ethylene carbonate (EC): dimethyl carbonate (DMC) in 50:50 vol. %. LMNOF/Li cells were tested between 3.5 and 5 V at 30 mA g^{-1} , while the LTO/Li cells were cycled between 1.2 and 2 V at 44 mA g^{-1} for the first three cycles and 132 mA g^{-1} thereafter and finally TiS_2/Li cells were cycled between 1.2 and 3 V at 39 mA g^{-1} .

Li-ion cells were fabricated utilizing active positive to negative electrode weight matching ratios of 1.4 for LMNOF/LTO and 1.3 for LMNOF/TiS₂, or as stated in the text. Cells were cycled between 2.2 and 3.4 V for LMNOF/LTO and between 1.8 and 3.0V for LMNOF/TiS₂ at 30 mA g⁻¹ of active cathode. Three-electrode electrochemical testing using a lithium metal reference was performed with the LMNOF (72 wt.% active)/LTO (70 wt.% active) system, with weight matching ratios of 1.2 and 1.4. Cells were fabricated with 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte and were cycled at 24 °C in galvanostatic mode between 2.2 and 3.4 V using a MacPile potentiostat (Biologic, France).

RESULTS

LMNOF vs. Li Half Cells (Excess Li Cells): The scaled LMNOF chemistry and fabrication process was optimized to result in good cycle life up to 5 V both at room temperature and at more stressing elevated temperature as per our previous publications [17, 18]. Figure 1.a reveals the discharge capacity plotted as a function of cycle number at 24 °C and at 60 °C for the first 200 cycles followed by 55 °C. In cells with excess Li, the scaled material exhibited high discharge capacity with 135 mAh g⁻¹ at C/5 corresponding to 91 % utilization of theoretical. LMNOF also showed good capacity retention upon cycling maintaining respectively 90 % and 82 % of the initial capacity after 500 cycles at 24 °C and 55 °C, respectively. Based on the promising performance, LMNOF was utilized for adjusted window Li-ion systems comprising LTO and TiS₂ negative electrodes.

LTO and TiS₂ vs. Li Half Cells (Excess Li Cells): The two sources of LTO as well as TiS₂ were also tested in half-cell configuration versus lithium. As shown in figure 1.b, they all

realized theoretical capacity at elevated temperature while they achieved 90-95 % at room temperature. All samples also exhibited good cycling stability at both 24 °C and 55 °C demonstrating the validity of each of the components of the adjusted window systems considered herein.

Figure 1. Discharge capacity as a function of cycling number using 1M LiPF₆ in EC:DMC 50:50 vol. % of (a) LMNOF vs. Li at 30 mA g⁻¹ between 3.5 and 5 V at 24 and 60 °C (switched to 55 °C after 200 cycles), (b) “macro” and “nano” LTO vs. Li at 24 and 60 °C and 132 mA g⁻¹

between 1.2 and 2.0 V at 132 mA g^{-1} (first 3 cycles of the “nano” occurred at 44 mA g^{-1}), and TiS_2 vs. Li at 39 mA g^{-1} between 1.2 and 3.0 V, and (c) LMNOF (80 wt.% active loading) vs. LTO (70 wt.% active loading) from both sources with $\text{MR}=1.4$ at 55°C and 30 mA g^{-1} of LMNOF between 2.2 and 3.4 V.

LMNOF vs. $\text{Li}_4\text{Ti}_5\text{O}_{12}$ Li-ion Cells (Non-Excess Li Cells): Li-ion cells have been fabricated as described above by pairing LMNOF positive electrodes with LTO negative electrodes.

1. Macro LTO vs. Nano LTO: Both “macro” and “nano” sources of LTO have been evaluated with LMNOF cathodes. Cells were assembled using a LMNOF/LTO active weight matching ratio (MR) of 1.4 and a 1 M LiPF_6 in EC:DMC 50:50 in vol. % electrolyte. Cells utilizing both types of LTO delivered similar discharge capacities of 100 mAh g^{-1} of LMNOF. But while both type of cells retained good capacity retention upon cycling at 24°C (not shown here), differences were revealed between the two LTO sources at elevated temperature. Figure 1.c showed improved cycling stability with the “macro” LTO negative electrode compared to the “nano” LTO at 55°C . However, poorer cycle life is obtained in the absence of excess Li as shown in the previous half-cells results. This behavior, suggesting the source of failure was the LTO, is consistent with the known deleterious catalytic behavior carbonate electrolytes have with LTO. As mentioned above, all parasitic reactions consuming Li have a strong negative impact on cyclability once the Li-content is fixed. Thereby further evaluation and optimization of the Li-ion adjusted window system based on LTO negative electrodes was conducting utilizing the “macro” source.

2. Impact of matching ratio and cutoff voltage with LiPF₆-based electrolytes:

Based on the theoretical capacities of 145 mAh g⁻¹ for LMNOF and 175 mAh g⁻¹ for LTO, the theoretical active weight matching ratio of LMNOF to LTO that corresponds to capacity matching ratio of 1 amounts to a value of 1.2. The three-electrode measurements enabled the tracking of the actual voltage of the working electrodes with respect to a lithium reference. Figure 2.a reveals the full cells fabricated with the “theoretical” matching ratio of 1.2 exhibit voltage profiles and capacities of active electrodes consistent to those obtained in 2-electrode half-cells configurations versus lithium as the counter electrode. Cells with active weight matching ratios above 1.2 correspond to systems containing excess LMNOF positive electrode material while the negative electrode is limiting. For a high voltage cell operating at elevated temperature, one would expect that a negative electrode limited balancing scenario is preferred so to limit the anodic stress on the positive electrode. Figure 2.b confirms that a matching ratio of 1.4 achieved this goal with the end of charge induced by the completion of Li⁺ intercalation into the LTO negative electrode as opposed to the complete extraction of Li⁺ from the LMNOF positive electrode, consistent with previous reports with LMNO [60]. As expected in a LTO-limited system, LTO (the limited material) showed almost full utilization while the material in excess (LMNOF) only achieved 85 % of its theoretical capacity for MR=1.4.

Since deterioration of the electrolyte can significantly impact cycle life especially with high-voltage positive electrodes, special attention needs to be brought to the upper cut-off voltage in order to maximize operating performance (i.e. achieve long life without significantly sacrificing capacity and energy). A high cut-off voltage of 3.4 V was tested in the 3-electrode configuration with matching ratios of 1.2 (balanced cell, Fig.2.a) and 1.4 (LTO-limited, Fig.2.b). The balanced

cell of MR=1.2 revealed a distinct voltage increase before the high 3.4 V cut-off indicating end of charge with the full utilization of the LMNOF positive electrode material at 4.88 V vs. the lithium reference electrode (in the first cycle). In contrast, the LTO-limited system (LMNOF-excess) of MR=1.4 did not present such rise: the charge cut-off is induced by the completion of Li^+ intercalation into the LTO negative electrode while the excess LMNOF has not fully reacted and the electrode stopped mid-intercalation with a lower versus lithium (3.78 V in the first cycle) than in the balanced cell. Lowering the high cut-off below 3.4 V would have a significant negative impact on capacity since a small ΔV would result in a large Δx on the intercalation plateau. As a result, the 3.4 V cut-off voltage was retained for the rest of the study.

Figure 2. (a, b) 3-electrode voltage profiles of LMNOF (72 wt.% active)/LTO (70 wt.% active) cells using a lithium reference electrode cycled using 1M LiPF_6 in EC:DMC 50:50 in vol. % electrolyte at 24 °C and 30 mA g^{-1} of LMNOF between 2.2 and 3.4 V with MR= 1.4 (a) and 1.2 (b). (c) Discharge capacity retention percentage plotted as a function of cycling number of LMNOF vs. LTO cells cycling 30mA/g of LMNOF between 2.2 and 3.4 V using 1M LiPF_6 in

EC:DMC 50:50 in vol. % electrolyte with MR= 1.0, 1.2, 1.3, 1.4 and 1.5 at 60 °C. (d) Discharge specific capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number for cells with MR= 1.4 and 1.6 at 24 and 55 °C.

To further evaluate the impact of matching ratio on overall electrochemical performance, various electrochemical scenarios were evaluated with LTO-limited, LMNOF-limited and matched systems. As impact of matching is more clearly evident at elevated temperature than at room temperature, cells with MRs varying between 1.0 and 1.6 were fabricated and tested at 60 °C where the electrochemical stress is much more significant. Figure 2.c, which presents the capacity retention percentage based on the first discharge, reveals capacity retention at 60 °C improves with increasing MR and that the group of cells with the LMNOF-limited or with theoretical matching configurations perform better in terms of cyclability than the LTO-limited systems with MR<1.2. This would be consistent with the limitation of anodic stress on the positive electrode through the use of higher matching ratios. As a result, our attention focused on LMNOF-limited systems with ratios of 1.4 and 1.6 at both 24 and 55 °C (Figure 2.d). While all systems have good cycle life at room temperature, figure 2.d confirms that cycling stability improves with excess LMNOF however at the expense of discharge capacity. Indeed, a distinct decrease in capacity was observed with the higher MR of 1.6 leading to an exceptionally negative electrode limited scenario. Although all cells failed dramatically past 90 cycles at 55 °C, it seemed that the matching ratio of 1.4 provided the best compromise between capacity and cycling stability as little further improvement is noted above this value. Therefore, the matching ratio of 1.4 was maintained throughout the rest of the study reported herein.

3. Impact of electrolyte additives with LiPF₆-based electrolyte: Electrolyte additives have been evaluated aiming at improving the elevated temperature cycle life of the LMNOF/LTO system fabricated with the 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte. Traditional additives such as VC [28, 46-54] and FEC [52, 54-56] have yielded improvements in coulombic efficiency and cyclability of Li-ion batteries by changing the electrode/electrolyte interfaces. Herein we have therefore examined both additives at 1, 2 and 5 vol.% addition levels. As opposed to previous benefits observed in stand Li-ion cells, Figure 3.a shows that both additives were detrimental to both capacity and cycle life, although FEC performed better than VC. Performance loss scaled with the additive amount.

Other additives were assessed at different content level. Figure 3.b compares the impact of 2wt.% gamma-butyrolactone (GBL) [68, 69], 0.25 and 1 wt.% LiBOB [43-45], 2 wt.% succinic anhydride (SA) [70], 5wt.% poly(vinylpyrrolidone) (PVP) [53], and 1 to 2 wt.% poly(2-vinylpyridine) (P2VP) [53, 71, 72] to the initial additive-free electrolyte. While 2 wt.% GBL, 2 wt.% SA and 5 wt.% PVP were clearly detrimental, both P2VP and LiBOB could improve capacity retention markedly during cycling at elevated temperature. While the 1 wt.% P2VP caused a significant drop of the initial capacity of the system, LiBOB retained the initial capacity thereby enhancing the overall performance at elevated temperature compared to the initial bare electrolyte. However, although some progress was achieved through the utilization of electrolyte additives, cycle life remains limited with 23% capacity loss after 160 cycles.

Figure 3. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF (80 wt.% active)/LTO (70 wt.% active) cells with MR=1.4. Various additives were added to the 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte: (a) VC and FEC at 1, 2 and 5 vol.%, and (b) γ -GBL (2 wt.%), SA (2 wt.%), PVP (5 wt.%), P2VP (1 and 2 wt.%), LiBOB (0.25 and 1 wt.%). All cycling was performed at 30 mA g⁻¹ of LMNOF at 55 °C between 2.2 and 3.4 V.

4. Impact of electrolyte salt with carbonate-based electrolyte: In order to improve the LMNOF/LTO system performance further, attention turned to the consideration of the electrolyte salt itself. Cycling at 55 °C with LiBF_4 , LiAsF_6 and LiClO_4 salts was compared to LiPF_6 in figure 4.a. While LiAsF_6 and LiClO_4 resulted in catastrophic failure within 40 cycles, shifting to tetrafluoroborate salt resulted in a very significant enhancement in capacity retention at elevated temperature with less than 5 % loss after 150 cycles. This results come in contrast to Duncan et al. study that revealed better electrochemical performance at 60 °C with LiPF_6 than LiBF_4 -salt in EC:DEC 30:70 vol. % [73]. In spite of its relative lower conductivity compared to the ubiquitous LiPF_6 , LiBF_4 has previously demonstrated improved elevated temperature performance and improved water sensitivity in standard Li-ion systems as well as interfaces of lower charge transfer resistance [74-76]. As a result, LiBF_4 is utilized as a standard salt moving forward in this study as it brings forth such a significant enhancement in the elevated temperature stability of the LMNOF/LTO system.

Figure 4. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells cycling at 30 mA g⁻¹ of LMNOF and 55 °C between 2.2 and 3.4 V (a) with

MR=1.4 using 1M LiPF₆, LiBF₄, LiAsF₆ and LiClO₄ salts in EC:DMC 50:50 in vol. %, (b) with MR= 1.0, 1.2 and 1.4 using LiBF₄ salt. (c) Voltage profiles for MR= 1.4 using LiBF₄ salt.

5. Impact of matching ratio with LiBF₄-based electrolyte: The impact of the active weight matching ratio was reevaluated using LiBF₄ salt. Negative electrode limited system with a 1.4 ratio and positive electrode limited system with a 1.0 ratio were compared to theoretical matching associated to a 1.2 ratio utilizing 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte. Figure 4.b shows capacity plotted as a function of cycle number upon cycling at 55 °C. As expected, the initial specific capacity of LMNOF decreased proportionally to the excess of LMNOF/LTO deficiency. In contrast, 55 °C cycling stability improved with excess LMNOF (increasing MR). Since the best performance compromise was obtained with a matching ratio of 1.4, similar to what was identified for the LiPF₆ based electrolytes, the active weight matching ratio was maintained at 1.4 in further system optimization.

6. Impact of molarity and electrolyte solvent with LiBF₄ salt: Increasing the LiBF₄ molarity from 1 to 1.5M in the carbonate-based solvent EC:DMC 50:50 in vol. % did not have any significant impact on the system's performance at 55 °C (not shown). As a result, our focus shifted to the impact of solvent composition switching to linear ethyl methyl carbonate (EMC). Both EC:EMC 50:50 and 30:70 in vol. % compositions were evaluated without any significant change of cycling stability: after 150 cycle the EC:DMC 50:50 capacity retention amounted to 95.6% barely better than 93.2% of the EC:EMC 30:70 mixture (Figure 5.a). GBL was also considered as pure solvent and co-solvent to EMC but GBL clearly appeared detrimental to cycle life (Figure 5.a).

Adiponitrile (ADN), having excellent intrinsic stability at high voltages [52, 77, 78] was also tested for its high voltage stability as a pure and co-solvent with carbonates and GBL. Figure 5.b revealed that, unfortunately, the use of ADN in its pure form and as a co-solvent is detrimental to cycle life with LiBF_4 molarities of 0.75 to 2. A mixture of LiTFSI with LiBF_4 salt in pure ADN did not provide any relief and cycle life remained poor. This reinforces the fact that having an intrinsically stable high voltage electrolyte is not a prerequisite for enabling high voltage stability and that the formation of proper CEI exceeds the importance of the electrolyte stability. Finally, the utilization of TMS as a solvent and co-solvent to EMC did not enhance the performance upon the obtained with all carbonate-based solvents (Figure 5.c).

Figure 5. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells at 55 °C. Cells were fabricated with a LMNOF/LTO active weight matching of 1.4 using with various EMC (a), ADN (b) an TMS (c) based electrolytes compared to 1M

LiBF₄ in EC:DMC 50:50 in vol. % electrolyte. Cycling was performed at 30 mA g⁻¹ of LMNOF between 2.2 and 3.4 V.

7. Impact of electrolyte additives with LiBF₄-based electrolyte: As previously reported with LiPF₆-based electrolytes above, the impact of additives was evaluated at 55 °C utilizing LiBF₄ as the salt. Figure 6.a reveals that the addition of 1 wt.% VC, 0.25 wt.% PVP and 0.25 wt.% LiBOB lowers the specific capacity. Only the 0.25 wt.% P2VP additive maintained similar capacity compared to the additive free system and with the benefit of markedly improved cyclability. Based on the results of Figure 6.a, various combinations of additives were tested in hope of further improving cycle life. However, the addition of 0.25 wt.% LiBOB + 0.5 wt.% P2VP, 0.25 wt.% LiBOB + 1 wt.% VC and 1 wt.% VC + 0.5 wt.% P2VP to the 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte did not exhibit any further improvement in performance with respect to the 0.25 wt.% P2VP alone (Figure 6.b).

The improvement utilizing P2VP in LiBF₄-based electrolytes was quite dramatic and in contrast to the minimal improvement shown when this additive was evaluated in the LiPF₆ electrolyte (Fig.3.b). In order to further optimize and better understand the origin of the beneficial impact of the P2VP addition to the LMNOF/LTO system, the P2VP was added to the electrode themselves rather than integrating it in the electrolyte. Although not shown herein, the addition to the LMNOF cathode did not influence performance, while the addition of the P2VP additive to the LTO negative electrode did present improved cyclability though not as good as the addition to the electrolyte. This result alluded to the fact that although LMNOF is cycling at extreme

voltages, the origin of the failure in a lithium-limited cell may be rooted in the LTO negative electrode. Such failure may not be represented in lithium-excess half-cell studies.

Figure 6. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells at 55 °C. Cells were fabricated with a LMNOF/LTO active weight matching of 1.4 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte: (a) without and with the

respective 0.25 wt.% P2VP, 0.25 wt.% LiBOB, 0.25 wt.% PVP and 1 wt.% VC, and (b) with the combination of the following additives 0.25 wt.% P2VP, 0.25 wt.% LiBOB + 0.5 wt.% P2VP, 0.25 wt.% LiBOB + 1 wt.% VC and 1 wt.% VC + 0.5 wt.% P2VP. Cycling was performed at 30 mA g⁻¹ of LMNOF between 2.2 and 3.4 V.

8. Failure mechanism: A negative electrode limited LMNOF/LTO system with a matching weight ratio of 1.4 cycled at 55 °C show a 5.2 % capacity loss over 150 cycles (Figure 4.a). The evolution of the voltage profile upon cycling reveals a distinct increase in polarization upon charge (Figure 4.c). In order to understand the limiting factors of the LMNOF/LTO system in terms of performance, the full cell was disassembled after 156 cycles to retrieve each electrodes to be tested in half-cell configuration versus lithium at 55 °C using fresh 1M LiBF₄ in EC:DMC electrolyte. Both electrodes maintained good capacity after 156 cycles as expected. Interestingly, while the LMNOF half-cell cycling remained stable the LTO half-cell failed within 50 cycles. Such results seem to indicate that the LTO may demonstrate a strong impact on the elevated temperature performance of the LMNOF/LTO system reported herein.

Full Cells vs. TiS₂ (Non-Excess Li Cells): Since some experimental evidence pointed to the direction that the LTO electrode was inducing failure, we turned our attention to evaluating an alternative stable negative electrode to be sure the effect was isolated to the negative electrode. TiS₂ with its outstanding transport characteristics, and competitive balanced energy densities versus LMNOF relative to LTO, presents itself as an intriguing alternative negative electrode material. As a result, TiS₂ negative electrodes were investigated hereafter to further understand

the impact of the type of anode and optimize window-shifted systems utilizing high voltage LMNOF cathodes.

Figure 7. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/TiS₂ cells cycled at 30 mA g⁻¹ of LMNOF between 1.8 and 3.0 V: (a) with MR= 1.3, 1.5 and 1.7 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte at 55 °C, and (b) with MR=

1.3 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte with and without 0.25 wt% P2VP additive at 24 and 55 °C.

1. Impact of matching ratio with LiBF₄-based electrolyte: LMNOF/TiS₂ cells were fabricated utilizing LMNOF/TiS₂ active weight matching ratios of 1.3, 1.5 and 1.7 and tested at elevated temperature (Figure 7.a). Based on a TiS₂ theoretical capacity of 240 mAh g⁻¹, the theoretical matching ratio is 1.66 and the Li-ion cells contain excess TiS₂ (positive electrode limited) at MRs of 1.5 and 1.3. As expected, the specific capacity of the system based on the amount of LMNOF decreases consistently although slightly with larger amounts of LMNOF or increasing matching weight ratio. However, interestingly and as opposed to the LTO-based system, the cycling stability improves with excess TiS₂ even through this drives the positive electrode to the highest potentials. Indeed, capacity loss after 200 cycles at 55 °C decreases from 20.8-23 % for theoretical matching of MR=1.7 to 16 % at MR= 1.5 and finally down to 10-13 % at MR=1.3. As a result, we focused on improving the cycle life of the higher capacity system with a matching ratio of 1.3.

2. Impact of P2VP additive with LiBF₄-based electrolyte: Our attention focused on the use of P2VP as an electrolyte additive based on the significant beneficial impact observed with LMNOF/LTO in LiBF₄ based electrolytes. Although some improvement in cycle life was obtained at elevated temperature (Figure 7.b), the effect of P2VP was not as significant as with the LTO-based system. This result supports our theory that the P2VP improvement was directly linked to the additive induced stabilization of the LTO as opposed to the LMNOF. Direct comparison of the optimized TiS₂-based systems to the LTO-based systems in figure 8.a reveals

that both type of cells had similar cycle life with about 10% capacity loss at 1000 cycles at 24 °C. However, TiS_2 provided higher capacity with 115mAh/g LMNOF compared to 100mAh/g with LTO, such variance is consistent with the system build where the former is positive electrode-limited (i.e. TiS_2 excess) while the latter is negative electrode limited (i.e. excess LMNOF). At elevated temperature, difference in initial discharge capacity was not as significant but the TiS_2 clearly provided improved cycling stability with 20 % loss after 500 cycles instead of 27.2 % loss for the LTO (figure 8.b). In addition, the capacity loss remained fairly stable upon cycling with TiS_2 while it accelerates with cycle number for the LTO-based cells. As a result, the LMNOF/ TiS_2 system demonstrated 25 % loss after 650 cycles at elevated temperature.

Figure 8. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of optimized LMNOF/LTO and LMNOF/TiS₂ cells at 24 °C (a) and 55 °C (b). Cycling was performed at 30 mA g⁻¹ of LMNOF over 2.2-3.4 V and 1.8-3.0 V range, respectively.

DISCUSSION

Optimization of the negative electrode-limited LMNOF/LTO system through control of the electrolyte composition revealed the most significant improvements were obtained with LiBF_4 -salt in carbonate-based solvents and with P2VP additive. The drastic enhancement observed with LiBF_4 over LiPF_6 was not anticipated as it came in contrast to a previous study⁷⁴, but has become an enabling aspect. The decreased propensity for the formation of native and electrochemically derived HF relative to LiPF_6 and subsequent lower charge transfer resistance may be the root for the observed enhancement of LiBF_4 . Regarding the benefits of the P2VP additive, we can speculate that the lone pair of the nitrogen may act as a chelating agent trapping dissolved metal ions and preventing poisoning of the negative electrode.

Some of our experimental evidence pointed to the LTO electrode as potential source of failure, which would be in line with previous reports suggesting deleterious interactions between the positive and negative electrodes of LMNO/LTO systems [62, 63]. The effect of the LTO negative electrode on the Li-ion cell performance is likely due to minute amounts of dissolution product that do not affect the cycling capacity of the positive but poisons the negative. This is in agreement to previous reports providing evidence for a LTO-passivation, in spite of initial reasoning that LTO's potential might be too high for direct reduction of the solvent at its surface [62, 63]. The authors had also suggested that the passivation layer which is composed of organic species may result from the slight re-dissolution of oxygen species from the positive electrode occurring during charge followed by migration/diffusion to the LTO. Interestingly, we previously observed the reduction of EC solvent at voltages as high as 2V enabled by the catalysis of nano-sized Bismuth metal resulting from the conversion of bismuth fluoride (BiF_3) during lithiation [79].

As a result, we turned to TiS_2 as an alternative stable negative electrode to be sure the effect was isolated to the negative electrode. TiS_2 is an excellent candidate, as it is well known for its excellent electrochemical performance at higher potentials than LTO. Additional gains are obtained utilizing TiS_2 -based negative electrodes compared to the LTO-based system. At elevated temperature and similar capacity, TiS_2 -based system clearly provides improved cycling stability with 20 % loss after 500 cycles instead of 27.2 % loss for the LTO-system.

The important takeaway from the study is that within a lithium-limited Li-ion configuration, properly optimized 4.7V (Li/Li^+) spinel positive electrodes can exhibit exemplary fundamental elevated temperature stability in relatively common carbonate solvents

CONCLUSION

Dramatic statements about the instability of 4.7 V spinel have been reported for years, however our study reveals that the optimization of this material for high elevated temperature stability in Li-ion configuration, although nowhere near perfect yet, shows a viable pathway for performance can be extracted from this controversial system even at the extreme demands of elevated temperature. We report herein on the optimization of window-shifted Li-ion systems utilizing either LTO or TiS_2 negative electrode to mitigate poor stability at elevated temperature. The electrolyte study in LTO-based systems reveals a significant improvement with LiBF_4 salt compared to LiPF_6 . In turn, the evaluation of various additives shows P2VP further enhances upon the performance of the LiBF_4 -based electrolyte. However, the degree the electrolyte influences and becomes involved within this process needs to be investigated to a greater degree.

The work presented here was for window-shifted systems and we did not extend our work to negative electrodes of graphite and lithium alloys at this time. Indeed, further work needs to be completed to encompass these systems adequately. There are applications where window shifted systems based on LMNO/LMNOF positive electrodes have unique advantages, but to extract the full energy density and rate capability advantages of LMNOF, one needs to extend the studies to the lower voltage negative electrodes. The final impression of this work is that there is high degree of confidence that very stable high voltage systems utilizing LMNOF or LMNO positive electrodes can be realized with the use of liquid electrolytes without depending on the effective realization of solid electrolytes in the future.

Acknowledgement: This material is based upon work supported by the Department of Energy under Award Number DE-SC0001088.

REFERENCES

- [1] Y. Gao, K. Mystle, M. Zhang, J. N. Reimers, and J. R. Dahn, *Phys. Rev. B*, **54** (1996), 16670-16675
- [2] Q. Zhong, A. Bonakdarpour, M. Zhang, Y. Gao, and J. R. Dahn, *J. Electrochem. Soc.*, **144** (1997), 205-213
- [3] T. Ohzuku, S. Takeda, and M. Iwanaga, *J. Power Sources*, **81-82** (1999), 90-94
- [4] K. Amine, H. Tukamoto, H. Yasuda, and Y. Fujita, *J. Power Sources*, **68** (1997), 604-608
- [5] B. Markovsky, Y. Talyossef, G. Salitra, D. Aurbach, H.-J. Kim, and S. Choi, *Electrochem. Comm.*, **6** (2004), 821-826
- [6] Y. Talyossef, B. Markovsky, G. Salitra, D. Aurbach, H.-J. Kim, and S. Choi, *J. Power Sources*, **146** (2006), 664-669
- [7] D. Aurbach, B. Markovsky, Y. Talyossef, G. Salitra, H.-J. Kim, and S. Choi, *J. Power Sources*, **162** (2006), 780-789
- [8] N. Marandian Hagh, F. Cosandey, S. Rangan, R. Bartynski, and G. G. Amatucci, *J. Electrochem. Soc.*, **157** (2010), A305-A319
- [9] S. Patoux, L. Sannier, H. Lignier, Y. Reynier, C. Bourbon, S. Jouanneau, F. Le Cras, and S. Martinet, *Electrochim. Acta*, **53** (2008), 4137-4145
- [10] Y.-K. Sun, Y.-S. Lee, M. Yoshio, and K. Amine, *Electrochem. Solid-State Lett.*, **5** (2002), A99-A102
- [11] Y. Fan, J. Wang, Z. Tang, W. He, and J. Zhang, *Electrochim. Acta*, **52** (2007), 3870-3875
- [12] A. M. Kannan, and A. Manthiram, *Electrochem. Solid-State Lett.*, **5** (2002), A167-A169
- [13] J. Arrebola, A. Caballero, L. Hernan, J. Morales, E. Rodriguez Castellon, J.R. Ramos Barrado, *J. Electrochem. Soc.*, **154** (2007), A178-A184

- [14] J. Arrebola, A. Caballero, L. Hernan, and J. Morales, *J. Power Sources*, **195** (2010), 4278-4284
- [15] S. Brutti, G. Greco, P. Reale, and S. Panero, *Electrochim. Acta*, **106** (2013), 483-493
- [16] J. Liu, and A. Manthiram, *Chem. Mater.*, **21** (2009), 1695-1707
- [17] N. Marandian Hagh, and G. G. Amatucci, *J. Power Sources*, **256** (2014), 457-469
- [18] N. M. Hagh, and G.G. Amatucci, *J. Power Sources*, **195** (2010), 5005-5012
- [19] G. G. Amatucci, C.N. Schmutz, A. Blyr, C. Sigala, A.S. Gozdz, D. Larcher, and J.M. Tarascon, *J. Power Sources*, **69** (1997), 11–25
- [20] G. G. Amatucci, and J.-M. Tarascon, *J. Electrochem. Soc.*, **149** (2002), K31–K46
- [21] M. M. Thackeray, P. J. Johnson, L. A. de Picciotto, P. G. Bruce, and J. B. Goodenough, *Mater. Res. Bull.*, **19** (1984), 179–187
- [22] N. P. W. Pieczonka, Z. Liu, P. Lu, K. L. Olson, J. Moote, B. R. Powell, and J.-H. Kim, *J. Phys. Chem. C*, **117** (2013), 15947–15957
- [23] A. Jarry, S. Gottis, Y.-S. Yu, J. Roque-Rosell, C. Kim, J. Cabana, J. Kerr, and R. Kostecki, *J. Am. Chem. Soc.*, **137** (2016), 3533-3539
- [24] M. Park, X. Zhang, M. Chung, G. B. Less, and A. M. Sastry, *Chem. Mater.*, **26** (2014), 3128–3134
- [25] R. Qiao, Y. Wang, P.O. Velasco, H. Li, Y.S. Hu, and W. Yang, *J. Power Sources*, **273** (2015), 1120-1126
- [26] C. L. Campion, W. Li, and B.L. Lucht, *J. Electrochem. Soc.*, **152** (2005), A2327-A2334
- [27] A. Blyr, C. Sigala, G. Amatucci, D. Guyomard, Y. Chabre, and J.M. Tarascon, *J. Electrochem. Soc.*, **145** (1998), 194-209

- [28] R. Bernhard, M. Metzger, and H. A. Gasteiger, *J. Electrochem. Soc.*, **162** (2015), A1984-A1989
- [29] L. Yang, B. Ravdel, and B. L. Lucht, *Electrochem. Solid-State Lett.*, **13** (2010), A95-A97
- [30] D. Aurbach, B. Markovsky, G. Salitra, E. Markevich, Y. Talyossef, M. Koltypin, L. Nazar, B. Ellis, and D. Kovacheva, *J. Power Sources*, **165** (2007), 491-499
- [31] H. Duncan, D. Duguay, Y. Abu-Lebdeh, and I. J. Davidson, *J. Electrochem. Soc.*, **158** (2011), A537–A545
- [32] M. He, L. Coulet-Roblin, P. Borel, C. Tessier, P. Novák, C. Villevieille, and E. J. Berg, *J. Electrochem. Soc.*, **163** (2016), A83–A89
- [33] L. Hu, Z. Zhang, and K. Amine, *J. Power Sources*, **236** (2013), 175-180
- [34] M. Börner, , S. Klamor, B. Hoffmann, M. Schroeder, S. Novak, A. Würsig, M. Winter, and F. M. Schappacher, *J. Electrochem. Soc.*, **163** (2016), A831–A837
- [35] S. S. Zhang, *J. Power Sources*, **162** (2006), 1379-1394
- [36] Z. Shang, L. Hu, H. Wu, W. Weng, M. Koh, P. C. Redfern, L. A. Curtiss, and K. Amine, *Energy Environ. Sci.*, **6** (2013), 1806-1810
- [37] K. Fridman, R. Sharabi, R. Elazari, G. Gershinsky, E. Markevich, G. Silatra, D. Aurbach, A. Garsuch , and J. Lampert, *Electrochem. Comm.*, **33** (2013), 31-34
- [38] V. Borgel, E. Markevich, D. Aurbach, G. Semrau , and M. Schmidt, *J. Power Sources*, **189** (2009), 331-336
- [39] A. Lewandowski, and A. Świdarska-Moczek, *J. Power Sources*, **194** (2009), 601-609
- [40] J. Mun, T. Yim, K. Park, J. Heon Ryu, Y. Gyu Kim, and S. M. Oh, *J. Electrochem. Soc.*, **158** (2011), A453–A457
- [41] A. Abouimrane, I. Belharouak, and K. Amine, *Electrochem. Comm.*, **11** (2009), 1073-1076

- [42] A. von Cresce, and K. Xu, *J. Electrochem. Soc.*, **158** (2011), A337–A342
- [43] M. Xu, N. Tsiouvaras, A. Garsuch, H. A. Gasteiger, and B. L. Lucht, *J. Phys. Chem. C.*, **118** (2014), 7363-7368
- [44] N. P. W. Pieczonka, L. Yang, M. P. Balogh, B. R. Powell, K. Chemelewski, A. Manthiram, S. A. Krachkowskiy, G. R. Goward, M. Liu, and J.- H. Kim, *J. Phys. Chem. C.*, **117** (2013), 22603-22612
- [45] S. Dalavi, M. Xu, B. Knight, and B. L. Lucht, *Electrochem. Solid-State Lett.*, **15** (2012), A28-A31
- [46] L. El Ouatani, R. Dedryvère, C. Siret, P. Biensan, and D. Gonbeau, *J. Electrochem. Soc.*, **156** (2009), A468–A477
- [47] L. El Ouatani, R. Dedryvère, C. Siret, P. Biensan, and D. Gonbeau, *J. Electrochem. Soc.*, **156** (2009), A103–A113
- [48] J. C. Burns, N. N. Sinha, D. J. Coyle, G. Jain, C. M. VanElzen, W. M. Lamana, A. Xiao, E. Scott, J. P. Garner, and J. R. Dahn, *J. Electrochem. Soc.*, **159** (2012), A85–A90
- [49] R. Petibon, E. C. Henry, J. C. Burns, N. N. Sinha, and J. R. Dahn, *J. Electrochem. Soc.*, **161** (2014), A66–A74
- [50] A. Wuersig, W. Scheifele, and P. Novák, *J. Electrochem. Soc.*, **154** (2007), A449–A454
- [51] D. Aurbach, K. Gamolsky, B. Marovski, Y. Gofer, M. Schmidt, and U. Heider, *J. Electrochim. Acta*, **47** (2002), 1423-1439
- [52] A. J. Gmitter, I. Plitz, and G. G. Amatucci, *J. Electrochem. Soc.*, **159** (2012), A370-A379
- [53] H. Buqa, and M. Holzapfel, US 2015/0372348 A1, Published Dec. 24 (2015)
- [54] A. J. Gmitter, J. Gural, and G. G. Amatucci, *J. Power Sources*, **217** (2012), 21-28
- [55] R. McMillan, H. Slegr, Z. X. Shu, and W. Wang, *J. Power Sources*, **81-82** (1999), 20-26

- [56] I. A. Profatilova, S.-S. Kim, and N.-S. Choi, *J. Electrochim. Acta*, **54** (2009), 4445-4450
- [57] M. Xu, D. Lu, A. Garsuch, and B. L. Lucht, *J. Electrochem. Soc.*, **159** (2012), A2130–A2134
- [58] K. Ariyoshi, S. Yamamoto, and T. Ozhuku, *J. Power Sources*, **119-121** (2003), 959-963
- [59] S. Patoux, L. Daniel, C. Bourbon, H. Lignier, C. Pagano, F. Le Cras, S. Jouanneau, and S. Martinet, *J. Power Sources*, **189** (2009), 344-352
- [60] H. F. Xiang, Z. Zhang, Q. Y. Jin, C. P. Zhang, C. H. Chen, and X. W. Ge, *J. Power Sources*, **183** (2008), 355-360
- [61] H. M. Wu, I. Belharouak, H. Deng, A. Abouimrane, Y.-K. Sun, and K. Amine, *J. Electrochem. Soc.*, **156** (2009), A1047–A1050
- [62] R. Dedryvère, D. Foix, S. Franger, S. Patoux, L. Daniel, and D. Gonbeau, *J. Phys. Chem. C.*, **114** (2010), 10999-11008
- [63] I. Belharouak, G. M. Koenig Jr., T. Tan, H. Yumoto, N. Ota, and K. Amine, *J. Electrochem. Soc.*, **159** (2012), A1165–A1170
- [64] Y.-B. He, B. Li, M. Liu, C. Zhang, W. Lv, C. Yang, J. Li, H. Du, B. Zhang, Q.-H. Yang, J.-K. Kim, and F. Kang, *Sci. Rep.*, **2** (2012), 913
- [65] R. Bernhard, S. Meini, and H. A. Gasteiger, *J. Electrochem. Soc.*, **161** (2014), A497-A505
- [66] C. R. Fell, L. Sun, P. B. Hallac, B. Metz, and B. Sisk, *J. Electrochem. Soc.*, **162** (2015), A1916-A1920
- [67] A. S. Gozdz, C. Schmutz, J.M. Tarascon, and P. Warren, US 5,418,091 (1995)
- [68] D. Belov, and D.-T. Shieh, *J. Solid State Electrochem.*, **16** (2011), 603-615
- [69] L. Yang, and B. L. Lucht, *Electrochem. Solid State Lett.*, **12** (2009), A229-A231

- [70] H. Lee, S. Choi, S. Choi, H.-J. Kim, Y. Choi, S. Yoon, and J.-J. Cho, *Electrochem. Comm.*, **9** (2007), 801-806
- [71] C.-K. Park, US 8,940,443 (2015)
- [72] S. Komba, T. Itabashi, T. Ohtsuka, H. Groult, N. Kumagai, B. Kaplan, and H. Yashiro, *J. Electrochem. Soc.*, **152** (2005), A937-A946
- [73] H. Duncan, D. Duguay, Y. Abu-Lebdeh, and I. J. Davidson, *J. Electrochem. Soc.*, **158** (2011), A537-A545
- [74] S. S. Zhang, K. Xu, and T. R. Jow, *J. Electrochem. Soc.*, **149** (2012), A586-A590
- [75] S. S. Zhang, K. Xu, and T. R. Jow, *J. Solid State Electrochem.*, **7** (2003), 147-151
- [76] S. S. Zhang, K. Xu, and T. R. Jow, *Electrochem. Comm.*, **4** (2002), 928-932
- [77] Y. Abu-Lebdeh, and I. Davidson, *J. Electrochem. Soc.*, **156** (2009), A60–A65
- [78] P. Isken, C. Dippel, R. Schmitz, R. W. Schmitz, M. Kunze, S. Passerini, M. Winter, and A. Lex-Balducci, *J. Electrochim. Acta*, **56** (2011), 7530-7535
- [79] A. J. Gmitter, F. Badway, S. Rangan, R. A. Bartynski, A. Halajko, N. Pereira, and G. G. Amatucci, *J. Mater. Chem.*, **20** (2010), 4149-4161

FIGURE CAPTIONS

Figure 1. Discharge capacity as a function of cycling number using 1M LiPF₆ in EC:DMC 50:50 vol. % of (a) LMNOF vs. Li at 30 mA g⁻¹ between 3.5 and 5 V at 24 and 60 °C (switched to 55 °C after 200 cycles), (b) “macro” and “nano” LTO vs. Li at 24 and 60 °C and 132 mA g⁻¹ between 1.2 and 2.0 V at 132 mA g⁻¹ (first 3 cycles of the “nano” occurred at 44 mA g⁻¹), and TiS₂ vs. Li at 39 mA g⁻¹ between 1.2 and 3.0 V, and (c) LMNOF (80 wt.% active loading) vs. LTO (70 wt.% active loading) from both sources with MR=1.4 at 55 °C and 30mA g⁻¹ of LMNOF between 2.2 and 3.4 V.

Figure 2. (a, b) 3-electrode voltage profiles of LMNOF (72 wt.% active)/LTO (70 wt.% active) cells using a lithium reference electrode cycled using 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte at 24 °C and 30 mA g⁻¹ of LMNOF between 2.2 and 3.4 V with MR= 1.4 (a) and 1.2 (b). (c) Discharge capacity retention percentage plotted as a function of cycling number of LMNOF vs. LTO cells cycling 30mA/g of LMNOF between 2.2 and 3.4 V using 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte with MR= 1.0, 1.2, 1.3, 1.4 and 1.5 at 60 °C. (d) Discharge specific capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number for cells with MR= 1.4 and 1.6 at 24 and 55 °C.

Figure 3. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF (80 wt.% active)/LTO (70 wt.% active) cells with MR=1.4. Various additives were added to the 1M LiPF₆ in EC:DMC 50:50 in vol. % electrolyte: (a) VC and FEC at 1, 2 and 5 vol.%, and (b) γ -GBL (2 wt.%), SA (2 wt.%), PVP (5 wt.%), P2VP (1 and 2 wt.%), LiBOB (0.25

and 1 wt.%). All cycling was performed at 30 mA g⁻¹ of LMNOF at 55 °C between 2.2 and 3.4 V.

Figure 4. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells cycling at 30 mA g⁻¹ of LMNOF and 55 °C between 2.2 and 3.4 V (a) with MR=1.4 using 1M LiPF₆, LiBF₄, LiAsF₆ and LiClO₄ salts in EC:DMC 50:50 in vol. %, (b) with MR= 1.0, 1.2 and 1.4 using LiBF₄ salt. (c) Voltage profiles for MR= 1.4 using LiBF₄ salt.

Figure 5. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells at 55 °C. Cells were fabricated with a LMNOF/LTO active weight matching of 1.4 using with various EMC (a), ADN (b) and TMS (c) based electrolytes compared to 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte. Cycling was performed at 30 mA g⁻¹ of LMNOF between 2.2 and 3.4 V.

Figure 6. Discharge capacity (mAh g⁻¹ LMNOF) plotted as a function of cycling number of LMNOF/LTO cells at 55 °C. Cells were fabricated with a LMNOF/LTO active weight matching of 1.4 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte: (a) without and with the respective 0.25 wt.% P2VP, 0.25 wt.% LiBOB, 0.25 wt.% PVP and 1 wt.% VC, and (b) with the combination of the following additives 0.25 wt.% P2VP, 0.25 wt.% LiBOB + 0.5 wt.% P2VP, 0.25 wt.% LiBOB + 1 wt.% VC and 1 wt.% VC + 0.5 wt.% P2VP. Cycling was performed at 30 mA g⁻¹ of LMNOF between 2.2 and 3.4 V.

Figure 7. Discharge capacity (mAh g^{-1} LMNOF) plotted as a function of cycling number of LMNOF/TiS₂ cells cycled at 30 mA g^{-1} of LMNOF between 1.8 and 3.0 V: (a) with MR= 1.3, 1.5 and 1.7 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte at 55 °C, and (b) with MR= 1.3 using 1M LiBF₄ in EC:DMC 50:50 in vol. % electrolyte with and without 0.25 wt% P2VP additive at 24 and 55 °C.

Figure 8. Discharge capacity (mAh g^{-1} LMNOF) plotted as a function of cycling number of optimized LMNOF/LTO and LMNOF/TiS₂ cells at 24 °C (a) and 55 °C (b). Cycling was performed at 30 mA g^{-1} of LMNOF over 2.2-3.4 V and 1.8-3.0 V range, respectively.