A facile one-step synthesis of prussian blue/polyaniline/graphene oxide nanocomposites for electrochemical sensing of hydrogen peroxide

Ziyin Yang, Xiaohui Zheng and Jianbin Zheng *

Institute of Analytical Science, Shaanxi Provincial Key Laboratory of Electroanalytical Chemistry, Northwest University, Xi'an, Shaanxi 710069, China. E-mail address: zhengjb@nwu.edu.cn

Abstract

Prussian blue/polyaniline/graphene oxide (PB/PANI/GO) nanocomposites were synthesized and used for electrochemical sensing of hydrogen peroxide (H_2O_2). PB/PANI/GO nanocomposites were synthesized through a facile one-step approach, where aniline acted as both the precursor of PANI and the reductant for $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$, therefore making polymerization of aniline and anchoring of PB nanoparticles on PANI/GO occur simultaneously. Then, the nanocomposites were characterized by transmission electron microscopy (TEM), X-ray diffraction spectroscopy (XRD), fourier transform infrared spectroscopy (FTIR) and electrochemical techniques. The results indicated that PB nanoparticles with the size of about 4.0 nm were homogeneously distributed on the surface of PANI/GO, which made the sensor based on PB/PANI/GO exhibit an excellent performance toward H_2O_2 detection with a wide linear range of 5.0 μM to 1.275 mM, a sensitivity of 60.16 $\mu\text{A mM}^{-1}\text{cm}^{-2}$ and a low detection limit of 1.9 μM ($\text{S/N} = 3$).

Keywords: Prussian blue; Polyaniline; Graphene oxide; Hydrogen peroxide; Nonenzymatic sensor

1. Introduction

The accurate determination of hydrogen peroxide (H_2O_2) is important for its wide applications [1, 2]. Up to now, many methods were developed to detect H_2O_2 [3-6]. In particular, electrochemistry sensors which based on the simple and low cost electrode were extensively studied [7]. Moreover, in order to improve the catalytic activity of sensors for H_2O_2 oxidation/reduction, various nanomaterials were employed to modify electrodes due to their large specific surface areas as well as

unique electronic and catalytic properties [8-11]. Among nanomaterials, prussian blue (PB) aroused growing interest because of its excellent electrocatalytic activity toward H_2O_2 electroreduction [12, 13]. In addition, H_2O_2 sensors based on PB usually required a low working potential [14], which was beneficial to prevent the interference of other substances. However, the poor stability and low conductivity of PB limited its extensive applications [15]. Recently, it has been reported that hybrid nanomaterial might endow the integrity with enhanced activity compared with single component [16]. Therefore, in order to improve stability, conductivity and catalytic activity of PB, it was desirable to disperse PB on supporting materials with excellent electrical conductivity, large surface area and high stability.

Graphene oxide (GO) was two-dimensional and one-atom-thick sheet material, which exhibited interesting features of large surface area and good stability. PB/GO nanocomposites were investigated [17,18]. Zhang [17] synthesized GO/PB hybrid film by electropolymerizing PB onto the GO modified glassy carbon electrode and then used for electrochemical sensing applications. Li [18] prepared PB/graphene composite film and employed the composite for electrochemical sensing of H_2O_2 . Compared with PB films and graphene sheets, PB/graphene composite film showed the largest current response to the reduction of H_2O_2 due to the synergistic effects between graphene sheets and PB nanoparticles. In addition, polyaniline (PANI) was conductive polymer with excellent electronic properties [19]. Meanwhile, both GO and PANI were functionalized by many groups and these groups can be employed as the anchor sites for nanoparticles, which prevented nanoparticles from aggregating [20, 21]. Therefore, the combination of GO with PANI made GO/PANI an advanced support material with excellent electrical conductivity, large surface area and high stability. Up to now, a few examples of synthesis of GO/PANI-based nanocomposites were demonstrated [22, 23], where GO/PANI were synthesized first by electrochemical or chemical oxidative polymerization method, then nanoparticles are anchored on the surface of GO/PANI. However, the synthesis of GO/PANI-based nanocomposites was complicated. Meanwhile, as far as we know, few studies have managed to support PB on GO/PANI. Therefore, it is still highly necessary to develop

a facile one-step approach to synthesize PB/PANI/GO for the determination of H_2O_2 .

In this paper, PB/PANI/GO nanocomposites were synthesized through spontaneous polymerization of aniline and formation of PB nanoparticles on PANI/GO, where aniline was employed as both the precursor of PANI and the reductant for $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$. Then, the non-enzymatic H_2O_2 sensor based on PB/PANI/GO was fabricated and electrochemical performance of the sensor toward H_2O_2 was investigated.

2. Experimental

2.1. Reagents and materials

Aniline ($\text{C}_6\text{H}_7\text{N}$, 99.9%) and ferric chloride crystal ($\text{FeCl}_3\cdot 6\text{H}_2\text{O}$, 99.0%) were purchased from Xi'an Chemical Reagent (Xi'an, China). Graphite powder (99.998%, 325 mesh, Alfa Aesar) and H_2O_2 (30% v/v solution) were obtained from Shanghai Yuanju Biotechnology Co., Ltd (Shanghai, China).

2.2. Apparatus

Transmission electron microscopic (TEM) images were carried out by Tecnai G² F20 S-TWIN (FEI, USA). X ray diffraction (XRD) patterns of the samples were taken by D/MAX 3C (Rigaku, Japan). Fourier transform infrared spectroscopy (FTIR) was recorded with TENSIR 27 (Bruker, German). Electrochemical measurements were carried out in a conventional three-electrode electroanalysis system controlled by CHI 660 electrochemical workstation (Shanghai CH Instrument Co. Ltd., China). A conventional three-electrode cell was used, including a glassy carbon electrode (GCE, geometric area = 0.07 cm^2) as the working electrode, a saturated calomel electrode as the reference electrode and platinum foil as the counter electrode. All potentials given in this work were referred to the saturated calomel electrode.

2.3. Synthesis of PB/PANI/GO

GO was synthesized from graphite powder [24]. 100 μL of aniline was added in aqueous solution of GO (50 mL, 0.5 mg/mL) under vigorous stirring for 30 min. Then, 1 mL of 12 M HCl (containing 0.012 g $\text{FeCl}_3\cdot 6\text{H}_2\text{O}$ and 0.014 g $\text{K}_3[\text{Fe}(\text{CN})_6]$) was slowly added into above solution and the solution was stirred for 24 h. After that, the product was separated from solution by centrifugation and was washed for three times

by doubly distilled water.

2.4. Electrode modification

GCE was prepared by the casting method. 2.0 mg of PB/PANI/GO were dispersed into 1 mL of water and the solution was sonicated for 8 minutes. After that, 6 μ L of PB/PANI/GO solution and 3 μ L of Nafion (0.05 wt%) was dropped on the surface of GCE and then dried at room temperature in air.

3. Results and Discussion

3.1 Characterizations of PB/PANI/GO

Figure 1 showed the schematic illustration for the preparation of PB/PANI/GO. PB/PANI/GO were synthesized through spontaneous polymerization of aniline and formation of PB nanoparticles using aniline as both the precursor of PANI and the reductant for $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$. When adding aniline into GO solution, aniline was adsorbed on the surface of GO through hydrogen bond force [25], which was beneficial for the subsequent polymerization of aniline on the surface of GO. In addition, it was reported that $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$ was strong oxidant in acidic solution. Therefore, after adding acidic $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$ into above solution, aniline was polymerized on the surface of GO, meanwhile, Fe^{3+} was reduced to Fe^{2+} by aniline and then PB nanoparticles was obtained through the reaction of Fe^{2+} with $[\text{Fe}(\text{CN})_6]^{3-}$. Therefore, PB/PANI/GO were synthesized through a facile one-step approach using aniline as both the precursor of PANI and the reductant for $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$.

The morphologies of GO and PB/PANI/GO were characterized by TEM. As shown in Figure 2 (A), GO revealed nanosheet structures with wrinkles and folds. In the case of PB/PANI/GO, from Figure 2 (B) and (C), it can be seen that a large number of nanoparticles with the size of about 4.0 nm were homogeneously distributed on the surface of PANI/GO, which benefited from the nucleation sites provided by the functional groups on the surface of PANI/GO. These functional groups prevented PB nanoparticles from aggregating and facilitated the homogeneous distribution. Furthermore, the chemical structural characterization of PB/PANI/GO was investigated by XRD. As shown in Figure 1 (D), PB/PANI/GO revealed some peaks at 24.8° , 35.4° , 43.6° , 54.2° and 57.3° , which were indexed to (220), (400),

(422), (600) and (620) planes of PB [26], therefore confirming that the nanoparticles decorated on PANI/GO were PB.

FTIR spectra (Figure 3) was employed to study the chemical structural characterizations of GO and PB/PANI/GO. It can be seen that GO (curve a) showed absorption peaks at 3417 cm^{-1} , 1734 cm^{-1} , 1627 cm^{-1} and 1065 cm^{-1} which can be assigned to -OH , C=O , C=C , C-O stretching, respectively [27]. In the case of PB/PANI/GO (curve b), the new peaks at 1137 , and 1340 cm^{-1} were ascribed to C=N stretching vibration and C-N vibrations of PANI [28]. Moreover, comparing with the spectra of GO, PB/PANI/GO also showed two new peak at 2084 cm^{-1} and 498 cm^{-1} due to the stretching modes of $\text{C}\equiv\text{N}$ group and the formation of $\text{Fe}^{\text{II}}\text{-CN-Fe}^{\text{III}}$ [15], which confirmed the presence of PB. Therefore, on the basis of the results of TEM, XRD and FTIR characterizations, GO and PB/PANI/GO nanocomposites were successfully prepared.

3.2 Electrochemical properties of PB/PANI/GO nanocomposites

Cyclic voltammograms (CVs) were recorded to investigate the electrocatalytic behavior of PB/PANI/GO/GCE. Figure 4 (A) showed CVs obtained at PB/PANI/GO/GCE in 0.5 M KCl solution (HCl , $\text{pH } 3.0$) at a scan rate of 100 mV/s . From Figure 4 (A), it can be seen that PB/PANI/GO/GCE exhibited a pair of well-defined redox peaks with a formal redox potential of 184 mV , which were due to the transitions between PB and Prussian white ($\text{K}_2\text{Fe}^{\text{II}}[\text{Fe}^{\text{II}}(\text{CN})_6]$) [29]. Moreover, the potential separation of the redox peaks was 19 mV and the potential separation was very close to the theoretical value, indicating that fast charge transfer occurred in PB/PANI/GO composite [18]. The electrochemical stability of PB/PANI/GO/GCE was studied. As shown in Figure 4 (B), no significant current decreased after thirty cycles, indicating the good stability. Furthermore, in order to examined the possible kinetic mechanism of PB/PANI/GO/GCE, the effect of scan rates on the current response was investigated (Figure 4 (C and D)). It can be seen that the current increased in a linear relationship with the square root of scan rates, implying a diffusion controlled process [30]. The diffusion-controlled process was due to that the redox transition of PB was companied with the transfer of K^+ and therefore the

diffusion of K^+ might control the electrochemical process and result in the linear dependence of the peak current on the square root of scan rate [31, 32].

CVs were also employed to study the electrocatalytic behavior of modified electrodes toward H_2O_2 . Figure 5 showed CVs obtained at bare GCE (a, b), GO/GCE (c, d) and PB/PANI/GO/GCE (e, f) in 0.5 M 0.5 M KCl solution (HCl, pH 3.0) in the absence (a, c, e) and presence (b, d, f) of 1.0 mM H_2O_2 at the scan rate of 60 mV/s. As shown in Figure 5 (A), in the absence (a, c) or presence (b, d) of 1.0 mM H_2O_2 , both bare GCE and GO/GCE exhibit almost no electrochemical response. However, it can be seen from Figure 5 (B) that PB/PANI/GO/GCE showed a pair of well-defined redox peaks (curve e) in the absence of H_2O_2 . Moreover, the cathodic peak current increased and the anodic peak current decreased (curve f) after adding H_2O_2 , indicating the electrocatalytic reduction of H_2O_2 . During electrocatalytic reduction of H_2O_2 , PB acted as an electron transfer mediator as follows [33]:

In order to study the sensing property of PB/PANI/GO/GCE, the amperometric current-time curve was recorded. Figure 6 (A) displayed the amperometric current-time curve obtained by PB/PANI/GO/GCE with successive addition of varying H_2O_2 concentrations in 0.5 M KCl solution (HCl, pH 3.0) at 0 V. It was clear that the reduction current increased after adding H_2O_2 into 0.5 M KCl solution (HCl, pH 3.0). The calibration curve of PB/PANI/GO/GCE was shown in Figure 6 (B). The linear regression equation was expressed as $I_p (\mu A) = 0.2351 + 4.211 \cdot C (mM)$. The linear range was estimated to be from 5.0 μM to 1.275 mM ($R = 0.998$). The sensitivity was calculated using the equation $S = b/A$, where b was the slope of the analytical curve and A was the geometric area of glassy carbon electrode. Therefore, the sensitivity was estimated to be 60.16 $\mu A mM^{-1} cm^{-2}$. The detection limit was 1.9 μM at a signal-to-noise ratio of 3. As shown in Table1, PB/PANI/GO exhibited an excellent performance for hydrogen peroxide analysis. Therefore, PANI/GO with excellent electrical conductivity, large surface area, high stability and a large number of functional groups can act as the support for nucleation and growth of highly

dispersed PB. PB combined with PANI/GO improved the stability and conductivity of PB, therefore increasing the catalytic activity for H_2O_2 reduction.

Furthermore, in order to study the selectivity of PB/PANI/GO/GCE, the amperometric current-time curve was recorded. Figure 7 showed the amperometric current-time curve obtained at PB/PANI/GO/GCE with successive addition of H_2O_2 , glucose (Glu), ascorbic acid (AA) and L-cysteine (L-cys). As shown in Figure 7, Glu, AA and L-cys produced almost no current response, indicating a good selectivity. Moreover, PB/PANI/GO/GCE retained almost 88% of its initial current response after fifteen days and the relative standard deviation was about 7.1% for six PB/PANI/GO/GCE, confirming the favorable long-term stability and good reproducibility.

4. Conclusion

Prussian blue/polyaniline/graphene oxide (PB/PANI/GO) nanocomposites were successfully synthesized through a facile one-step approach. The experimental results revealed that the spontaneous redox reactions between aniline and $\text{FeCl}_3\text{--K}_3[\text{Fe}(\text{CN})_6]$ made the preparation method simple without employing additional reducing agents, surface modifier or complicated steps. Meanwhile, large numbers of PB with a narrow size distribution were well distributed on the surface of PANI/GO, which not only enhanced the electron transfer and improved catalytic activity but also also provided more catalytic surface for H_2O_2 reaction, therefore making PB/PANI/GO exhibit an excellent performance for hydrogen peroxide analysis. Considering the facile preparation route and excellent experimental results, this synthetic concept may paved the way for the facial synthesis of other GO/conductive polymer-based nanocomposites for applications.

Acknowledgments

The authors gratefully acknowledge the financial support of this project by the National Science Foundation of China (21575113, 21275116 and 21105080), Specialized Research Fund for the Doctoral Program of Higher Education (No. 20126101120023), the Natural Science Foundation of Shaanxi Province in China (2013KJXX-25), and the Scientific Research Foundation of Shaanxi Provincial Key

Laboratory (13JS097, 13JS098, 14JS094, 15JS100).

References:

- [1] Tsiafoulis CG, Trikalitis PN, Prodromidis MI (2005) *Electrochemistry communications* 7:1398–1404.
- [2] Nossol E, Zarbin AJG (2009) *Advanced Functional Materials* 19:3980–3986.
- [3] Matos RC, Coelho EO (2006) *Talanta* 69:1208–1214.
- [4] King DW, Cooper WJ, Rusak SA (2007) *Analytical chemistry* 79:4169–4176.
- [5] Srikun D, Albers AE, Nam CI (2010) *Journal of the American Chemical Society* 132:4455–4465.
- [6] Zhang C, Li L, Ju J (2016) *Electrochimica Acta* 210:181–189.
- [7] Uzunoglu A, Song S, Stanciu LA (2016) *Journal of The Electrochemical Society* 163:379–384.
- [8] Wang T, Zhu H, Zhuo J (2013) *Analytical chemistry* 85:10289–10295.
- [10] Ren S, Wang H, Zhang Y (2016) *Analyst* 141:2741–2747.
- [11] Lou X, Zhu C, Pan H (2016) *Electrochimica Acta* 205:70–76.
- [12] Su L, Xiong Y, Yang H (2016) *Journal of Materials Chemistry B* 4:128–134.
- [13] Prabhu P, Babu RS, Narayanan SS (2014) *Journal of Solid State Electrochemistry* 18:883–891.
- [14] Michopoulos A, Kouloumpis A, Gournis D (2014) *Electrochimica Acta* 146:477–484.
- [15] Tuo X, Li B, Chen C (2016) *Synthetic Metals* 213:73–77.
- [16] Liu Z, Zhao B, Shi Y (2010) *Talanta* 81:1650–1654.
- [17] Zhang Y, Sun X, Zhu L (2011) *Electrochimica Acta* 56:1239–1245.
- [18] Li SJ, Du JM, Shi YF (2012) *Journal of Solid State Electrochemistry* 16:2235–2241.
- [19] Liang B, Qin Z, Zhao J (2014) *Journal of Materials Chemistry A* 2:2129–2135.
- [20] Qin Y, Li J, Kong Y (2014) *Nanoscale* 6:1281–1285.
- [21] Feng X, Zhang Y, Yan Z (2014) *Journal of Solid State Electrochemistry* 18:1717–1723.
- [22] Han G, Liu Y, Zhang L (2014) *Scientific reports* 4:4824–4831.
- [23] Hu XW, Mao CJ, Song JM (2013) *Biosensors and Bioelectronics* 41:372–378.

- [24] Perera SD, Mariano RG, Vu K (2012) *Acs Catalysis* 2:949–956.
- [25] Tong Z, Yang Y, Wang J (2014) *Journal of Materials Chemistry A* 2:4642–4651.
- [26] Gong H, Sun M, Fan R (2013) *Microchimica Acta* 180:295–301.
- [27] Kim NH, Kuila T, Lee JH (2013) *Journal of Materials Chemistry A* 1:1349–1358.
- [28] Ma R, Wang M, Dam DT (2015) *ChemElectroChem* 2:503–507.
- [29] Zeng J, Wei W, Liu X (2008) *Microchimica Acta* 160:261–267.
- [30] Wang L, Ye Y, Lu X (2013) *Electrochimica Acta* 114:223–232.
- [31] Michopoulos A, Kouloumpis A, Gournis D (2014) *Electrochimica Acta* 146:477–484.
- [32] Zhu N, Han S, Gan S (2013) *Advanced Functional Materials* 23:5297–5306.
- [33] Yang JH, Myoung N, Hong HG (2012) *Electrochimica Acta* 81:37–43.
- [34] Wang L, Zhu H, Hou H (2012) *Journal of Solid State Electrochemistry* 16:1693–1700.
- [35] Li SJ, Du JM, Shi YF (2012) *Journal of Solid State Electrochemistry* 16:2235–2241.
- [36] Meng F, Yan X, Liu J (2011) *Electrochimica Acta* 56:4657–4662.
- [37] Li Y, Liu X, Zeng X (2009) *Microchimica Acta* 165:393–398.
- [38] Jiang Y, Zhang X, Shan C (2011) *Talanta* 85:76–81.

Figure Caption

Figure 1. Experimental procedure of synthesis of PB/PANI/GO.

Figure 2. TEM images of nanocomposites: (A) GO, (B, C) PB/PANI/GO and XRD of (D) PB/PANI/GO.

Figure 3. FTIR spectra of (a) GO and (b) PB/PANI/GO nanocomposites.

Figure 4. (A) Cyclic voltammograms obtained by PB/PANI/GO/GCE in 0.5 M KCl solution (HCl, pH 3.0) at a scan rate of 100 mV/s. (B) Cyclic voltammograms obtained by PB/PANI/GO/GCE in 0.5 M KCl solution (HCl, pH 3.0) after thirty cycles at a scan rate of 100 mV/s. (C) Cyclic voltammograms obtained by PB/PANI/GO/GCE in 0.5 M KCl solution (HCl, pH 3.0) at different scan rates (from a to g: 20, 40, 60, 80, 100, 120 and 140 mV/s). (D) Linear fitting program of current versus the square root of scan rate.

Figure 5. Cyclic voltammograms obtained by bare GCE (a, b) GO/GCE (c, d) and PB/PANI/GO/GCE (e, f) in 0.5 M KCl solution (HCl, pH 3.0) in the absence (a, c, e) and presence (b, d, f) of 1.0 mM H_2O_2 at a scan rate of 60 mV/s.

Figure 6. (A) Amperometric curve obtained by PB/PANI/GO/GCE for successive additions of H_2O_2 in 0.5 M KCl solution (HCl, pH 3.0) at the work potential of 0 V under constant stirring. (B) Calibration curve of H_2O_2 versus its concentration.

Figure 7. Amperometric response of 0.05 mM H_2O_2 , glucose, ascorbic acid and L-cysteine on PB/PANI/GO/GCE in 0.5 M KCl solution (HCl, pH 3.0) at the work potential of 0 V under constant stirring.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Table 1. Comparison of non-enzymatic H₂O₂ sensors.

Sensors	Applied Potential (V)	Linear range (mM)	Detection limit (μM)	References
GO/PB	0.1	0.005 – 1.2	0.122	17
PB-graphene	- 0.2	0.05 – 5	0.02	18
AgNPs/GO-CHIT/cysteamine/Au	- 0.4	0.006 – 18	0.7	34
AuNPs/graphite	- 0.2	0.005 – 5	0.02	35
Nanoporous gold	- 0.4	0.01 – 8	3.26	36
PB/CILE	- 0.1	0.05 – 6	1	37
PB-graphene	0.35	0.01 – 3	7	38
PB/PANI/GO	0	0.005 – 1.275	1.9	This work