1
2
3
4
5 **ON THE EFFECT OF RELATIVE DENSITY ON THE CRUSHING AND ENERGY**
6 **ABSORPTION OF OPEN-CELL FOAMS UNDER IMPACT**

7
8 by

9
10 Stavros Gaitanaros, Stelios Kyriakides¹
11
12

13
14
15
16 1 Corresponding author
17 E-mail: skk@mail.utexas.edu
18 Tel. (512) 471-4167, Fax (512) 471-5500
19
20
21
22
23
24
25
26
27
28
29

30 Revised December 2014
31
32
33
34
35
36
37

38 Research Center for Mechanics of Solids, Structures & Materials
39 The University of Texas at Austin
40 Austin, TX 78712

Abstract

Micromechanically accurate random foams are used to examine the effect of relative density on the crushing response and energy absorption of aluminum open-cell foams for a range of loading rates. Random soap froth microstructures generated with the Surface Evolver software are dressed with shear deformable beam elements with material distribution that mimics measured values. Foam models of relative densities between 3.67% and 10.0% are crushed first quasi-statically and then dynamically in a direct impact setting covering impact speeds that ranged from sub- to super-critical. Under quasi-static crushing, the limit and plateau stresses and the energy absorbed were found to increase linearly with relative density while the densification strains exhibit a modest linear decrease. In the shock regime, for all densities the proximal stresses rise significantly with relative density whereas the distal ones follow the more modest linear increase of the quasi-static limit stress. The Hugoniot strain depends strongly on impact speed approaching asymptotically values corresponding to the densification of the material at the high end. The energy induced to the material as it crosses the shock also increases also parabolically with impact speed. It was further confirmed that given the shock front velocity-impact speed Hugoniot the rest of the dynamic variables for each foam density can be estimated from the fundamental jump conditions for shocks in solids. For all densities examined it was illustrated that the transition from quasi-static to shock behavior is a process that spans several impact speed. The transitional range moves to moderately higher velocities as the foam density increases.

1. INTRODUCTION

Cellular materials in general and foams in particular have unique mechanical, thermal, acoustical and other properties derived from their cellular microstructures (e.g., see [Gibson and Ashby, 1997](#)). Mechanically they have compressive responses with a relatively low initial maximum stress followed by a stress plateau that extends to high strains. This behavior, in addition to their low density, is responsible for their wide use as cores in sandwich structures and in impact mitigation and blast protection applications (e.g., [Ashby et al., 2000](#)). It is now well established that the stress plateau, common to all but brittle cellular materials, is caused by localized crushing of cells that gradually spreads until the whole domain is crushed. In other words, the deformation is inhomogeneous and as a result does not represent a stress-strain response of the material ([Klintworth and Stronge, 1988](#); [Papka and Kyriakides, 1994, 1998](#); [Gong et al., 2005](#), [Jang and Kyriakides, 2009a](#)). The stress plateau is followed by a progressively stiffening response (densification) during which additional crushing takes place but now in a more homogeneous manner.

Impact mitigation and blast protection naturally require that attention be also paid to the effect of inertia on the material response and its energy absorption characteristics. In the shock physics community it has long been established that material systems with adiabatic compression modulus that increases with further compression, such as that of cellular materials in the densification regime, can be expected to develop stable shocks (e.g., see [Bethe, 1942](#); [Herrmann, 1969](#); [Knowles, 2002](#)). Furthermore, the shock behavior can be fully represented by the *Hugoniot* of the material. Shock formation, accompanied by significant increase in the dynamic energy absorption capacity in cellular materials was first reported in the mechanics community by [Reid and Peng \[1997\]](#) from Taylor impact experiments on wood. Dynamic crushing on polymeric foams (e.g., [Skews et al. 1991](#); [Zaretsky and Ben-Dor, 1995](#); [Zaretsky et al., 2012](#)) and more recent impact experiments on open and closed cell metal foams (e.g., [Tan et al., 2005a,b](#); [Elnasriet al., 2007](#); [Tan et al., 2012](#)) reported shock formation above a certain critical impact speed (for a more complete review of the experimental literature see [Barnes et al., 2014](#)).

Until recently the modeling of the dynamic/shock behavior of cellular materials was based on a homogenized material behavior, following the quasi-static crushing response, in which the deformation in the densification regime is precluded (*r-p-p-l: rigid-perfectly-plastic-locking model*, see [Tan et al., 2005b](#)) or, in more representative models, varies in a nonlinear

manner with impact velocity (e.g., [Pattofatto et al., 2007](#); [Karagiozova et al., 2012](#); [Karagiozova and Alves, 2014](#)). The adoption of the foam's quasi-static response as a stable material response is clearly refuted by results from crushing experiments on metal foams from many sources including [Jang and Kyriakides \[2009a\]](#) and [Barnes et al. \[2014\]](#) (see also earlier work on honeycombs such as: [Klintworth and Stronge, 1988](#); [Papka and Kyriakides, 1994, 1998a, 1998b](#)). [Barnes et al. \[2014\]](#) used high-speed photography to monitor the evolution of deformation and propagation of shocks in direct and stationary impact experiments on Al-alloy open-cell foams with a relative density of about 8%. Shocks developed at impact speeds higher than about 50 m/s. Direct measurements of shock velocity and strain behind the shock at different impact speeds enabled the establishment of the Hugoniot, which in turn allows calculation of all problem variables without resorting to a constitutive model. The Hugoniot strain was shown to increase significantly with impact speed and the stress behind the shock to increase quadratically. At impact speeds below the critical threshold localized crushing initiates progressively at multiple sites, similar to quasi-static crushing, while the stress traces the usual plateau. In summary, use of the quasi-static material response in modeling the shock behavior is inappropriate.

The modeling of the quasi-static compressive response and crushing of random foams, has evolved from models based on idealized microstructures such as variations of the periodic Kelvin cell ([Gong and Kyriakides, 2005](#); [Jang et al. 2008](#); [Jang and Kyriakides, 2009b](#)) to more representative random ones generated using the Surface Evolver software. These references showed that suitably calibrated Kelvin cell models can capture essentially all properties from the initial elastic behavior, the stress at the onset of localization, the stress plateau that follows and its extent, to densification. However, the crushing patterns are influenced by the periodicity of the microstructure and differ from ones observed in experiments on random foams. [Gaitanaros et al. \[2012\]](#) showed that micromechanically accurate random foam models reproduce all aspects of the quasi-static crushing behavior of such materials including the correct crushing behavior.

This type of random foam model was subsequently used in [Gaitanaros and Kyriakides \[2014\]](#) to study the crushing behavior of the foam used in the experiments of [Barnes et al. \[2014\]](#) under impact. The behavior observed in the experiments in the subcritical and supercritical regimes was reproduced. This included the generation of the Hugoniot, the parabolic increase of

the stress behind the shocks with impact speed, and the corresponding increase of the Hugoniot strain. The model was subsequently used to conduct a wider parametric study that included a detailed probing of the transition from quasi-static to shock type crushing. It is worth mentioning that the work of the authors and co-workers on the crushing of space filling foams by impact was preceded by micromechanical modeling of in-plane dynamic crushing of honeycomb where subcritical and shock behavior was observed. Specifically the works of [Hönig and Stronge, \[2002a,b\]](#), [Ruan et al. \[2003\]](#) and [Zou et al. \[2009\]](#) connect well with the present studies.

It is widely understood that most mechanical and other properties of cellular materials scale with their relative density ([Gibson and Ashby, 1997](#)). Thus the present study examines the effect of the foam relative density on crushing and energy absorption at different loading rates ranging from quasi-static to sub- and super-critical impact velocities. This is a natural extension of our preceding work [\[2014\]](#) and uses the same type of discrete random foam model to develop results in a range of densities of practical interest. The base material remains the same, Al-6101-T6, and the open cell foam models are again generated via the Surface Evolver ([Brakke, 1992](#)). The material distribution in the ligaments is assumed to follow the trends of the measurements performed in [Jang et al. \[2008\]](#) with the basic dimensions being varied to design models with relative densities ranging from 3.67% to 10.0% (range that is commercially available, see [ERG website](#)).

2. MODELING OF RANDOM FOAMS

The open cell foams used in our studies are Al-6101-T6 ERG Duocel® (see [ERG website](#)). This product is cast using molds generated from nearly monodisperse polymeric foams. Consequently, they have the same distribution of random polyhedra and polygonal sides as polymeric and more generally liquid foams. This characteristic enabled us to generate models with similar random microstructures from soap froths generated by the Surface Evolver (e.g., see [Kraynik et al., 2003, 2004](#)). The skeletal version of the froth (e.g., see Fig. [1a](#)) is “dressed” with appropriate distributions of solid to match those of ligaments in foams analyzed. In particular we start with a random soap froth with 12^3 cells. The vertices of the cells are joined with straight lines and anisotropy of $\lambda = 1.1$ is introduced by applying an affine deformation to the model in the x_1 -direction (see previous works of the group). The periodicity of the models is removed and

the ligaments in the top and bottom surfaces are cropped so that their ends become co-planar ending up with a domain size of $12 \times 10 \times 10$ cells (see [Gaitanaros et al., 2012](#) for more details).

2.1 Material Distribution in Ligaments and Discretization

The straight ligaments are “dressed” with shear-deformable beams with circular cross sections and variable area along their length that follows the expression developed from measurements on a nearly 8% relative density foam reported in [Jang et al. \[2008\]](#), repeated here for completeness,

$$A(\xi) = A_o f(\xi) = A_o (36\xi^4 + \xi^2 + 1), \quad \xi = x / \ell, \quad (1)$$

where A_o depends on the ligament length ℓ as follows:

$$A_o = \bar{A}_o g(\eta) = \bar{A}_o (0.6633 + 0.264\eta^{-2.5963}), \quad \eta = \ell / \bar{\ell} \quad (2)$$

and $\bar{A}_o$ and $\bar{\ell}$ are the average values measured.

Modeling ligaments as beams leads to an overlap of material at the nodes. This is accounted for using the following expression for the relative density ([Jang et al., 2008](#)):

$$\frac{\rho^*}{\rho} = k \left(\frac{R_o}{\ell} \right)^n, \quad (3)$$

where R_o is the mid-span radius of the ligament. The parameters k and n depend on the anisotropy and for $\lambda = 1.1$ take the values of 1.9543 and 1.7131 respectively. As mentioned above, the empirical expressions (1) and (2) came from measurements of ligament geometries in ERG Duocel® foams of relative density of about 8%. We generate models with relative densities of 3.67%, 5.56%, 7.75% and 10.0% by assuming that this distribution of material remains the same. As in our previous works, the ligaments are placed in two length groups: shorter and longer than $\bar{\ell}$. The average lengths of each group are designated as $\bar{\ell}_1$ and $\bar{\ell}_2$ and the corresponding values of A_o in (2) as $A_o|_{\bar{\ell}_\alpha}$, $\alpha = 1, 2$.

The ligaments are discretized with the [Hughes-Liu \[1981\]](#) linear beam element that is derived from the isoparametric 8-node solid element. Ligaments with $\ell < \bar{\ell}$ are discretized using 7 elements and those with $\ell > \bar{\ell}$ with 9 elements as in [Gaitanaros et al. \[2012\]](#). All elements have a uniform circular cross sectional area based on the following:

$$A(\xi) = A_o|_{\bar{\ell}_\alpha} f(\xi)|_{\bar{\ell}_\alpha}, \quad \alpha = 1, 2 \quad (4)$$

with $f(\xi)|_{\bar{\ell}_\alpha}$, $\alpha = 1, 2$ taking the same values listed in Table 1 of the reference given above (e.g., see model foam slice in Fig. 1b).

Proper modeling of contact between crushing ligaments is essential in order to reproduce correctly the shock front, its propagation and the compaction of the material behind it. This is achieved through the beam-to-beam contact algorithm of LS-DYNA adopted along with a penalty formulation with an interface stiffness chosen for numerical stability to be one order of magnitude less than the stiffness of the contacting elements. Coulomb friction with a coefficient of 0.4 was found to yield good numerical stability of the solutions and is used in all calculations.

As noted above, the use of beam elements leads to excess material at the nodes. This excess material was corrected for the calculation of the density of the model foam but the overlaps remain in the FE model. These overlaps at the nodes cause initial interpenetrations between beam elements and non-physical contacts that lead to numerical instabilities of the contact algorithm. This difficulty was bypassed by excluding the overlapping elements with the scaled assigned density from developing contact. Since for higher densities beams are thicker and the overlap is more significant, density is scaled in four elements per ligament for the 7.75% and 10.0% foams but in two elements for the 3.67% and 5.56% foams.

As in our previous works the Al-6061-T6 base material is modeled as a finitely deforming elastic-plastic solid calibrated to the true-stress-logarithmic strain version of the engineering stress-strain response with the following Ramberg-Osgood parameters: $E = 10^4$ ksi–69 GPa, $\sigma_y = 28$ ksi–193 MPa, $n = 48$ (properties measured in a tensile test on a specimen cast together with the foam in Jang and Kyriakides, 2009b).

3. RESULTS

3.1 Quasi-Static Crushing

The models for the four foam densities are first crushed quasi-statically between two rigid surfaces in the manner described in Gaitanaros and Kyriakides [2012]. The calculated nominal stress-shortening responses ($\sigma - \delta/h_o$; h_o is the undeformed height of the model) are plotted in Fig. 2. (σ is the net force acting on the rigid contacting plane divided by the initial cross sectional area of the model). The four responses are qualitatively similar, all displaying a

stiff and stable elastic branch, a local pressure maximum followed by relatively smooth stress plateau and a densification regime. As expected, the whole response moves to a higher stress level as the density increases and the average strain at densification decreases (marked with “■”). Figure 3 shows the undeformed and three deformed configurations for each of the four foam models. They are cross sections about two cells thick taken approximately from the center of each domain. It is readily noticed that as density increases ligaments become less slender. Images I correspond to $\delta/h_o = 10.0\%$ and are marked in Fig. 2 with “●”. Since the models originated from the same random soap froth, localized cell crushing initiated at the same location in each model. Subsequently, crushing propagates upwards while cell collapse has commenced in a second band above the first one that can be seen in images II at $\delta/h_o = 30\%$ (marked with “▲” in Fig. 2). In summary then the behavior observed thus far is very similar to that reported in Gaitanaros and Kyriakides [2012] for foams with densities of about 8%. Images III approximately correspond to the point when cell crushing has fully consumed each model. It coincides with the upswing in the stress of each response in Fig. 2 and we designate it as the onset of densification and the corresponding value of δ/h_o as ε_D (marked with “■” in Fig. 2). As the density increases, ε_D decreases which is also evident from the height of the densified configurations III in Fig. 3. The height of the model with relative density of 3.67% is $0.37 h_o$ while that of the one with 10.0% is $0.52 h_o$. Clearly, as the density increases, the ligaments become thicker and during crushing come into contact earlier which translates into a shorter stress plateau and thus a smaller densification strain.

Table 1 Quasi-static crushing characteristics of Al-alloy foams of several densities.

$\frac{\rho^*}{\rho}(\%)$	σ_I psi (MPa)	σ_P psi (MPa)	ε_D	U_o psi (MPa)
3.67	105 (0.72)	103 (0.71)	0.63	65.1 (0.45)
5.56	259 (1.76)	255 (1.76)	0.58	152.1 (1.05)
7.75	397 (2.74)	398 (2.74)	0.54	220.8 (1.52)
10.04	586 (4.04)	589 (4.06)	0.48	291.4 (2.01)

The initial stress maximum represents the onset of instability in compressed foams that we have designated as the *initiation stress*, σ_I . In dynamic crushing it represents the stress barrier that must be exceeded by an incoming stress wave for a shock to develop. The stress plateau, designated as σ_P , that follows and its extent, in other words ε_D , represent the energy absorption capacity of the foam. The energy absorption capacity per unit volume, designated as U_o , is established by integrating the response from 0 to ε_D . The calculated values of the four variables are listed in Table 1 while their trends can also be seen in Fig. 4a and 4b where they are plotted against relative density. Thus, σ_I and σ_P , each normalized by the base material yield parameter σ_y follow a linear trajectory that does not pass through the origin presumably because for very low densities the instability is governed by elastic material behavior. With the present definition of the densification strain their values are similar (Jang and Kyriakides, 2009a used an alternate definition of ε_D that accentuates the differences between the two stress variables). Their absolute values as well as the linear dependence on ρ^* / ρ are in general agreement with measured values reported in Jang and Kyriakides [2009a] and calculated values of σ_I in Jang *et al.* [2010]. Gibson and Ashby [1997] report two powerlaw expressions for σ_P / σ_y based on scaling arguments that are widely used in the design of foams and sandwich structures (e.g., Eq. (5.27a) $\sigma_P / \sigma_y \approx 0.3(\rho^* / \rho)^{3/2}$; no distinction is made between σ_I and σ_P). They were found to disagree with the present results as well as with the experimental results of Jang and Kyriakides [2009a] both qualitatively and quantitatively, underpredicting them by factors upwards of 2. The densification strain plotted in Fig. 4a is seen to decrease essentially linearly with relative density. Gibson and Ashby's expression for ε_D (Eq. (5.30): $\varepsilon_D = 1 - 1.4(\rho^* / \rho)$) also decreases linearly with relative density, however it over-predicts the present results by more than 30%. Driven primarily by the increase in the plateau stress, the energy absorption in Fig. 4b increases linearly with relative density. Thus for example, U_o for the 10.0% density foam is nearly 4.5 times larger than that of the 3.67% density foam.

3.2 Shock Formation Under Impact

The same four models are now crushed dynamically in a direct impact setting (see Fig. 1b). In each case the specimen is assigned a constant velocity towards a stationary rigid surface. The objective is to understand the effect of shocks on the induced stresses and deformations in foams of different densities as a function of impact speed. The tools that will be used to analyze the results are the classical jump conditions in Lagrangian form representing conservation of mass, momentum, and energy applied to plane longitudinal shocks summarized below (Davison, 2008):

$$\rho_o \dot{s} \left[\left[\frac{1}{\rho} \right] \right] + [[V]] = 0, \quad (5a)$$

$$\rho_o \dot{s} [[V]] + [[\sigma]] = 0, \quad (5b)$$

$$\rho_o \dot{s} \left[\left[U + \frac{1}{2} V^2 \right] \right] + [[\sigma V]] = 0, \quad (5c)$$

where $[[g]] = g^+ - g^-$ is the jump operator with g^+ and g^- representing the value of a variable ahead and behind a discontinuity; s is the position of the discontinuity in the undeformed configuration, and $\dot{s}$ its velocity. The variables $\{\rho, V, \sigma, U\}$ are respectively the mass density, particle velocity, nominal stress, and strain energy density.

Figure 5 shows an image of such a foam model that has been partially crushed by a shock. The rigid plane on the top is moving together with the uncrushed foam at a velocity V^+ while the one on the bottom is fixed in space. As the foam is crushed, cells located at the front experience a fast deceleration from V^+ to almost zero velocity. The horizontal dashed red line shows the best estimate of the position of the shock, in this particular location in the width of the model. Similar estimates of the position of the shock are conducted at different locations across the width and from the corresponding skeletal views. The average of these estimates is $h_c(t)$ and then $h_i(t) = h_b(t) - h_c(t)$. The position of the front in the undeformed configuration is then $s(t) = h_o - h_i(t)$, and its velocity is the time derivative $\dot{s}(t)$. As in Barnes *et al.* [2014], assuming that the transverse strain is negligibly small

$$\left(\frac{1}{\rho^+} - \frac{1}{\rho^-} \right) = \left(\frac{1}{\rho_o} - \frac{h_c}{s \rho_o} \right) = \frac{\varepsilon_H}{\rho_o} \quad (6)$$

where ρ_o is the initial density of the material assumed to remain unchanged ahead of the shock and ε_H is the strain behind the shock, named the *Hugoniot strain*. Using (6), each of Eqs. (5) can be respectively expressed as follows:

$$\dot{\varepsilon}_H = (V^+ - V^-), \quad (7a)$$

$$\sigma^+ = \sigma^- - \rho_o \dot{\varepsilon}_H (V^+ - V^-) = \sigma^- - \rho_o \frac{(V^+ - V^-)^2}{\varepsilon_H}, \quad (7b)$$

$$\rho_o (U^+ - U^-) = \frac{1}{2} (\sigma^+ + \sigma^-) \varepsilon_H. \quad (7c)$$

In the first set of simulations, an impact velocity of 90 m/s is chosen to ensure shock formation for all four densities. Figures 6a and 6b show the stress histories calculated at the proximal (σ^-) and distal (σ^+) ends respectively for the four foams. Qualitatively, the characteristics of the two pairs of responses are similar to those reported in Gaitanaros and Kyriakides [2014] in their simulations of specific experiments. Briefly, each of the stresses behind the shock exhibits an initial spike with a quick decent down to a stress plateau with several undulations. The events associated with the four responses are summarized in Fig. 7 that shows the undeformed and three deformed slices of each model that correspond to the bullets marked on the responses, labeled I, II and III (marked in Fig. 6a with ●, ▲, ■). Images I show the early formation of the shock; images II show the shock having crushed a significant part of the specimen; and set III shows the shock having just reached the end of the specimen when the σ^- stresses in Fig. 6a start rising. The σ^- stress plateaus increase with density going from approximately 200 psi (1.38 MPa) for the lowest density to approximately 950 psi (6.55 MPa) for the 10.0% relative density. Because the soap froth from which the four models originated is the same, the stress undulations occur at the same times (partly associated with the nearly planar shock crossing a relatively coarse microstructure). However, as is evident from the height of images III, the shock induced strain decreases as the density increases and consequently the corresponding plateaus terminate earlier.

The stress history recorded at the distal end, σ^+ , that represents the stress in the essentially undeformed (only elastic deformation) part of the specimen behind the shock is plotted in Fig. 6b. These stresses all experience a sharp rise at about the same time. The first rise is somewhat delayed from the time of first impact due to the time required for the stress wave to

traverse the length of the model. They trace relatively flat plateaus that again increase with density but the levels are significantly lower than those recorded at the proximal end in Fig. 6a. The difference can be explained using Eq. (7b) above. The plateaus again finish with a sharp rise in the stress close to the time that the shock has traversed the model. This termination of the plateaus occur somewhat earlier than the ones at the proximal end, possibly because as the shock approaches the rigid plane it interacts with it. Drawn with a dashed line in Fig. 6b is the initiation stress σ_I corresponding to each density (Table 1). Each plateau is seen to be bounded by σ_I , which is in agreement with the conclusion drawn in Gaitanaros and Kyriakides [2014] for a relative density of about 8% (similar observation made from modeling of impact of regular honeycomb in Zou *et al.*, 2009).

3.3 Effect of Relative Density on the Hugoniot

The random models are now used to generate first the $V^+ - \dot{s}$ Hugoniot for the four relative densities. This is achieved by performing a series of constant velocity direct impact simulations for each density in the velocity range of $30 < V^+ \leq 160$ m/s (the lower velocity varies with density in order to ensure that shocks develop). The numerical procedure used is the same as that outlined in Section 3.2. The values of $\dot{s}$ calculated for different impact speeds for the four foam densities are listed in Table 2. They are also plotted against each other in Fig. 8 for each density. All four sets of results form a nearly linear locus, a result that is in agreement with the trend of the experimental values from the nearly 8% relative density Al foam in Barnes *et al.* [2014]. Included with dashed lines are linear fits of the numerical results that can be represented by

$$\dot{s} = A + BV^+. \quad (8)$$

The fit parameters are listed in Table 3 along with the R^2 values of the fits. Again, the nearly perfect fits support the linearity of these Hugoniot curves. The four fits have nearly equal slopes but different intercepts. Thus, as the density increases the shock velocity for a given impact speed increases. For denser materials, the intercept is usually thought to be the wave speed of the solid (e.g., Davison, 2008). In foams with low densities like the ones impacted in this study, this limit is not recovered. Our best explanation at the present is that this is because the material deforms inhomogeneously at impact speeds lower than the critical value for shock formation

(Barnes *et al.*, 2014). Hugoniot curves(8) are characteristic of each foam and constitute the minimum amount of information required to evaluate the other shock propagation variables in such problems.

Table 3 Hugoniot linear fit parameters

$\frac{\rho^*}{\rho}(\%)$	A m/s	B	R^2
3.67	18.76	0.960	0.9994
5.56	26.03	0.974	0.9997
7.75	29.62	0.987	0.9996
10.04	36.61	0.9648	0.9998

The results of these simulations are also used to generate other representations of the Hugoniot. Thus Fig. 9 shows a plot of the strain behind the shock vs. the impact speed that we call the $V^+ - \varepsilon_H$ Hugoniot. The strains behind the shocks at different impact speeds can be obtained directly from the simulations of each foam density in the manner described in Section 3.2 and the associated Fig. 5. The measured values are plotted with solid bullets in the figure and are also listed in Table 2. They exhibit the same strong increase with impact speed observed in the experiments of Barnes *et al.* [2014] (see also similar trend in Fig. 7 of Zheng *et al.*, 2014 from dynamic crushing simulations of an idealized closed cell model). At higher speeds each set of results appears to asymptotically approach full densification of the material. However, we refrain from extending the numerical study to higher velocities because the lateral strain tends to increase while simultaneously our contact algorithm and strategy begin to lead to some self-penetration at the nodes.

Marked on the ordinate with empty symbols are the strains, ε_D , at the completion of the inhomogeneous crushing phase of each foam under quasi-static loading. It is interesting that the shock-induced strains tend to approach the corresponding value of ε_D from above, which can thus be viewed as a lower bound for ε_H .

In order to test once more the characteristic nature of the $V^+ - \varepsilon_H$ Hugoniot, the linear fit (8) along with the constants in Table 3 are used in Eq. (7a) to evaluate the Hugoniot strain from the following:

$$\varepsilon_H = \frac{V^+}{A + BV^+}. \quad (9)$$

The results are plotted in Fig. 9 with solid lines together with each set of the independently measured values. Expressions (9) are seen to track the trend of the data quite well for all four densities.

The stresses behind and ahead of the shock are important in the design of impact mitigation applications and are considered next. Accordingly Fig. 10 shows the $V^+ - \sigma^\pm$ Hugoniot, generated using the σ^- and σ^+ stresses measured directly from the numerical simulations (force acting on respective plane divided by the undeformed cross sectional area of the model foam). The σ^- stresses are represented by solid symbols and the σ^+ with the corresponding open ones. The stresses behind the shock exhibit a quadratic increase with velocity for all densities. These trends are in agreement with the experimental results of Barnes *et al.* [2014] and similar results in Tan *et al.* [2012] both for the same Duocel[®] Al-alloy foams that the microstructure of the present models is based on. The trajectories move to higher stress levels as the density increases and the increase with impact speed becomes stronger.

The stresses behind the shock remain nearly constant for all densities again in concert with experimental observations in Barnes *et al.* [2014]. Included in the figure on the ordinate are the initiation stresses from the quasi-static crushing calculation of each foam model (σ_I , in Table 1). Each is seen to correspond to the level of the corresponding σ^+ , which supports the premise that σ_I can be viewed as an upper bound for σ^+ .

It is also worth examining the veracity of the basic Hugoniot in (8) in estimating the $V^+ - \sigma^\pm$ Hugoniot. This can be achieved by substituting (8) in to (7b) leading to

$$\sigma^- = \sigma^+ + \rho_o V^+ (A + BV^+). \quad (10)$$

In Barnes *et al.* [2014] we recommended that in the absence of measured values of σ^+ they be replaced by σ_I in (10). This substitution produced trajectories that slightly overpredict the measured stresses in Fig. 10. This is explained by observing that the calculated σ^+ histories for 90 m/s impact speed in Fig. 6 match σ_I for the early part of the impact period but drop

somewhat in the latter part. The σ^+ values in Table 2 and in Fig. 10 represent the mean value of these plateaus and as a result they are somewhat lower than σ_I . Furthermore, the difference decreases as the impact speed increases. For these reasons in the present predictions of σ^- through (10) we adopt the average value of the four σ^+ values measured for each density. The calculated expressions are drawn in solid lines in Fig. 10. They are seen to track quite adequately the measured values, slightly overpredicting the ones corresponding to the highest density foam.

The energy expended across the shock can be evaluated using measured values of stresses and strains in (7c) as follows:

$$U_o = \rho_o U^- = \frac{1}{2}(\sigma^+ + \sigma^-)\varepsilon_H. \quad (11)$$

This expression is nicely illustrated by the Rayleigh line construction in Fig. 11 that shows stresses σ^+ and σ^- plotted against ε_H . The four Rayleigh lines are for 90 m/s impacts. The calculated values for the four foam densities are listed in Table 2 and are used in Fig. 12 to generate the energy per unit volume-velocity Hugoniot, $V^+ - U_o$. The energy density, U_o , is seen to increase significantly with impact speed for all foam densities analyzed. This is a trend that mimics that observed in the experimental results of Barnes *et al.* [2014]. Using (11) and the $V^+ - U_o$ Hugoniot one obtains:

$$U_o = \frac{\sigma^+ V^+}{A + B V^+} + \frac{1}{2} \rho_o V^{+2}. \quad (12)$$

Predictions based on this expression are included with solid lines in Fig. 12 using again the average of the calculated values of σ^+ for each density (does slightly better than adopting σ_I instead). The predictions are seen to reproduce the trend of the measured values, overestimating them slightly for the denser foam.

3.4 Transition from Subcritical Velocities to Shock Formation

In their study of an 8% relative density foam with similar microstructure to the present ones, Gaitanaros and Kyriakides [2014] demonstrated that at lower impact speeds the foam crushes in a manner that is very similar to that observed under quasi-static loading. Under impact, deformation localizes at the weakest site in the model. When ligaments come into contact in the collapsed cells, crushing spreads to neighboring cells or initiates at another

location. This continues until the whole domain is crushed while the stress traces a relatively flat plateau like the ones in Fig. 2. Subsequently, the now densified material starts deforming essentially homogenously at an increasing stress. As the impact speed increases, the first signs of shock formation is that crushing initiates first at the proximal end while the stress recorded there moves gradually to a higher level than the quasi-static crushing stress plateau. In this transitional velocity regime, localization at an alternate site is also possible. The formation of a shock that traverses the specimen consistently from one end to the other is delayed until a higher impact speed is reached. In other words, the transition to shock formation is a process that spans several impact speeds. These observations were confirmed by the experiments reported in Barnes *et al.* [2014].

In the present study the four density foam models were used to further scrutinize these observations and establish how foam density influences this transition. The results of this effort confirm that the transition to shock formation is a process. Furthermore, since change in density results in nearly parallel $V^+ - s$ Hugoniot lines with only a relatively modest increase in the intercept, the transitional velocity range was accordingly found not to be altered significantly. Thus, in order to highlight differences between foams of different densities, we will compare here results from the highest and lowest densities analyzed. To this end stress-normalized displacement responses for the 3.67% and 10.0% relative density foam impacted at different speeds in the transitional regime are plotted in Figs. 13a and 13b respectively. The lower density responses are for quasi-static (QS) crushing and at impact speeds of 15, 25 and 35m/s and the higher density foams for QS, 25, 35 and 50 m/s. Accompanying each response is a deformed configuration that appears in Fig. 14 corresponding to $\delta/h_o \approx 15\%$ and marked on the response with a solid bullet.

In the case of the 3.67% relative density foam, impact at 15 m/s causes an initial stress spike but the rest of the response traces a plateau that is at the same level as that for quasi-static crushing. Furthermore, the images in Fig. 14 show crushing to start localizing at the same location where collapse initiated quasi-statically. For impact at 25 m/s deformation localized at the same location as the QS case but concurrently some partial collapse of the cells adjacent to the impact plane takes place. This has the effect of lifting the response slightly. By the time that corresponds to the image shown in Fig. 14, deformation has spread to the lower fifth of the domain. In other words, inertial effects have started to influence the deformation patterns and to

increase the stress at the proximal end. When the impact speed is increased to 35 m/s, the proximal stress plateau recorded moves to a higher level (by about 10%) implying a larger influence of inertia. Indeed, the corresponding image in Fig. 14, shows collapse initiating at the impacted plane, and subsequently to propagate as a shock in the manner shown in Fig. 7. We can thus claim that for this density inertial effects start altering the behavior at 25 m/s leading to shock formation at 35 m/s.

The 10% relative density foam exhibits the same general behavior but the transition shifts to a higher impact speed. Thus, at 25 m/s the response is similar to the quasi-static one with crushing initiating at the same weak site in Fig. 14. At 35 m/s, the response moves to a slightly higher level and the same confused crushing patterns develop at the lower end of the domain as those seen for 25 m/s for the lower density foam. Impact at 50 m/s causes a clear shock to develop at the proximal end that propagates, crushing the whole domain. In other words, for the 10% relative density foam the transition from quasi-static to shock behavior has moved to between 35 m/s and 50 m/s.

4. SUMMARY AND CONCLUSIONS

Gaitanaros and Kyriakides [2012] demonstrated that micromechanically accurate models of random foams can reproduce all aspects of their quasi-static crushing behavior from the onset of localization to homogeneous compaction during densification. The same type model was also shown [2014] to be capable of reproducing the behavior in experiments on foam under impact in both the subcritical and supercritical regimes. Thus in the shock forming regime the generation of the Hugoniot, the parabolic increase of the stress behind the shocks with impact speed, and the corresponding increase of the Hugoniot strain were reproduced with accuracy for the 8% relative density foam considered. Since most mechanical properties of cellular materials scale with relative density, the present study used similar discrete models to examine its effect on the crushing at different loading rates ranging from quasi-static to sub- and super-critical impact speeds.

Random soap froth models generated using the Surface Evolver software were “dressed” with appropriate distribution of solid to produce foams of four relative densities, 3.67%, 5.56%, 7.75% and 10.0%. The main modeling parameters derived from the microstructural measurements of Jang *et al.* [2008] were adopted in this process. In addition, a geometric

anisotropy of $\lambda=1.1$ was assumed for all densities. Under quasi-static compression between rigid planes, the four models exhibited the same general behavior consisting of: an initial elastic regime that terminates into a local stress maximum that represents the onset of localized cell collapse, followed by an extended stress plateau during which collapse propagates throughout the domain. Once all cells have collapsed (densification) the stress rises once more and deformation is essentially uniform. For the density range considered the initiation, plateau stresses and energy absorption capacity increase linearly with density while the densification strain decreases linearly to some extent. The quantitative dependence of these variables to ρ^*/ρ was found to differ significantly from scaling estimates in [Gibson and Ashby \[1997\]](#).

The same models were crushed dynamically in a direct impact setting where each model impacts a stationary rigid plane at a contrast velocity. When the impact speed is high enough, a shock that consists of a narrow layer of crushed cells develops in the model foam. It initiates at the impacted surface and propagates at a constant velocity towards the distal end until the whole specimen is crushed. Calculations at impact speeds in the range of about 30-160 m/s were performed for each foam density. The shock velocity, the stress behind and ahead of the shock, the strain induced by the shock and the energy expended across it were established as a function of impact speed. This facilitated the generation of several representations of the Hugoniot for each foam density that can be summarized as follows:

- The shock velocity-impact speed Hugoniot is linear for all densities with essentially the same slope and an intercept that increases with density.
- The stress behind the shock grows in a quadratic manner with impact speed while the stress ahead of the shock remains essentially constant at a value bounded by the initiation stress at quasi-static crushing. The trend for the proximal stress increase significantly with density while that at the distal end follows the linear growth of σ_I .
- The Hugoniot strain depends strongly on impact speed approaching asymptotically values corresponding to the densification of the material. At the lower end the quasi-static densification strain appears to bound the dynamic strain values. The trend is the same for each density but moving to higher values as the density decreases.
- The crushing energy density also grows parabolically with impact speed. The trend applies to all densities considered with the net energy absorbed increasing significantly with density.

- The linear shock front velocity–impact speed Hugoniot were used in the fundamental jump conditions to estimate the rest of the dynamic variables for each foam density. The predictions follow the calculated results quite closely, as was the case in Barnes *et al.* [2014].

The transitional regimes of impact speeds between quasi-static and shock behavior were examined in some detail. It was confirmed that the transition to shock formation is a process that spans a range of impact speeds for all densities. At the lower end the crushing behavior and stress levels are like those in quasi-static crushing while at the higher end the proximal stress increases, crushing initiates at the impacted plane and propagates across the specimen as a shock. For the 3.67% relative density foam, this transition started at impact speeds of approximately 25 m/s and finished at 35 m/s. For the 10% relative density foam it was shifted to 35-50 m/s.

ACKNOWLEDGMENTS

The work reported was supported in part by the National Science Foundation through Grant CMMI-1029575 and by the University of Texas at Austin. This support is acknowledged with thanks. The authors would like to thank Andrew M. Kraynik for generating the soap froth models used in this study and for discussions and long term cooperation in mechanics of foams.

REFERENCES

- Ashby, M.F., Evans, A., Fleck, N.A., Gibson, L.J., Hutchinson, J.W. and Wadley, H.N.G. (2000). *Metal Foams: A Design Guide*. Butterworth-Heinemann.
- Brakke, K.A., 1992. The Surface Evolver. *Experimental Mathematics* **1**, 141-165. Available at <http://www.susqu.edu/facstaff/b/brakke/evolver/>
- Barnes, A.T., Ravi-Chandar, K., Kyriakides, S., Gaitanaros, S., 2014. Dynamic crushing of aluminum foams: Part I – Experiments. *Int'l J. Solids & Structures*, **51**:1631-1645.
- Bethe, H., 1942. On the theory of shock waves for an arbitrary equation of state. Report No. 545 for the Office of Scientific Research and Development, Serial No. NDRC-B-237; reproduced in *Classic Papers in Shock Compression Science*, J.N. Johnson and R. Cheret (Eds), Springer, 1998, 421-492).
- Davison, L. 2008. *Fundamentals of Shock Wave Propagation in Solids*. Springer.
- Elnasri, I., Patoatto, S., Zhao, H., Tsitsiris, H., Hild, F. and Girard, Y., 2007. Shock enhancement of cellular structures under impact loading: Part I experiments. *J. Mechanics Phys. Solids* **55**, 2652-2671.

ERG website: <http://www.ergaerospace.com/Aluminum-properties.htm>

Gaitanaros, S., Kyriakides, S., Kraynik, A.M. 2012. On the crushing response of random open-cell foams. *Int'l J. Solids Struct.***49**, 2733-2743.

Gaitanaros, S., Kyriakides, S., 2014. Dynamic crushing of aluminum foams: Part II – Analysis. *Int'l J. Solids & Struct.*, **51**, 1646-1661.

Gibson, L.J., Ashby, M.F., 1997. *Cellular Solids: Structure and Properties, 2nd Ed.* Cambridge University Press.

Gong, L., Jang, W.-Y., Kyriakides S., 2005. Compressive response of open-cell foams. Part I: Morphology and elastic properties. *Int'l J. Solids & Structures* **42**, 1355-1379.

Gong, L., Kyriakides S., 2005. Compressive response of open-cell foams. Part II: Initiation and evolution of crushing. *Int'l J. Solids & Structures* **42**, 1381-1399.

Herrmann, W., 1969. Constitutive equations for the dynamic compaction of ductile porous materials. *J. Appl. Physics* **40**, 2490-2499.

Hönig, A., Stronge, W.J. 2002a. In-plane dynamic crushing of honeycomb Part I: crush band initiation and wave trapping. *Int'l J. Mech. Sciences***44**, 1665-1696.

Hönig, A., Stronge, W.J. 2002b. In-plane dynamic crushing of honeycomb Part II: application to impact. *Int'l J. Mech. Sciences***44**, 1697-1714.

Hughes, T.J.R. and Liu, W.K., 1981. Nonlinear finite element analysis of shells-Part II. Two-dimensional shells. *Computer Meth. Applied Mech. Eng.***27**, 167-181.

Jang, W.-Y., Kraynik, A.M., Kyriakides, S., 2008. On the microstructure of open-cell foams and its effect on elastic properties. *Int'l J. Solids & Structures***45**, 1845-1875.

Jang, W.-Y., Kyriakides, S., 2009a. On the crushing of aluminum open-cell foams: Part I experiments. *Int'l J. Solids & Structures***46**, 617-634.

Jang, W.-Y., Kyriakides, S., 2009b. On the crushing of aluminum open-cell foams: Part II analysis. *Int'l J. Solids & Structures***46**, 635-650.

Jang, W.-Y., Kyriakides, S. and Kraynik, A.M. 2010. On the compressive strength of open-cell foams with Kelvin and random cell structures. *Int'l J. Solids & Structures***47**, 2872-2883.

Karagiozova, D., Langdon, G.S., Nurick, G.N. 2012. Propagation of compaction waves in metal foams exhibiting strain hardening. *Int'l J. Solids & Structures***49**, 2763-2777.

- Karagiozova, D., Alves, M., 2014. Compaction of a double-layered metal foam block impacting a rigid wall. *Int'l J. Solids & Structures***51**, 2424-2438.
- Klintworth, J.W. and Stronge, W.J., 1988. Elasto-plastic yield limits and deformation laws for transversely crushed honeycombs. *Int'l J. Mech. Sciences***30**, 273-292.
- Knowles, J.K., 2002. Impact induced tensile wave in a rubberlike material. *SIAM J. Appl. Math.***62**:4, 1153-1175.
- Kraynik, A.M., Reinelt, D.A., van Swol, F., 2003. Structure of random monodisperse foam. *Physical Review E***67**, 031403/1-11.
- Kraynik, A.M., Reinelt, D.A., van Swol, F., 2004. Structure of random foam. *Phys. Rev. Lett.***93**/20, 208301/1-4.
- Papka, S.D. and Kyriakides, S., 1994. In-plane compressive response and crushing of honeycomb. *J. Mechanics & Physics of Solids***42**:10, 1499-1532.
- Papka, S.D., Kyriakides, S., 1998a. In-plane crushing of a polycarbonate honeycomb. *Int'l J. Solids & Structures* **35**, 239-267.
- Papka, S.D. and Kyriakides, S., 1998b. Experiments and full-scale numerical simulations of in-plane crushing of a honeycomb. *Acta Materialia***46**:8, 2765-2776, 1998.
- Pattofatto, Elnasri, I., S., Zhao, H., Tsitsiris, H., Hild, F. and Girard, Y., 2007. Shock enhancement of cellular structures under impact loading: Part II analysis. *J. Mech. Physics Solids* **55**, 2672-2686.
- Reid, S.R. and Peng, C., 1997. Dynamic uniaxial crushing of wood. *Int'l J. Imp. Eng.***19**, 531-570.
- Ruan, D., Lu, G., Wang, B. and Yu, T.X. 2003. In-plane dynamic crushing of honeycombs – a finite element study. *Int'l J. Impact Engin.***28**, 161-182.
- Skews, B.W., Atkinks, M.D., and Seitz, M.W., 1991. Gas dynamic and physical behaviour of compressible porous foams struck by a weak shock. *Shock Waves, Proc. 18th Int'l Symp. on Shock Waves*, Sendai, Japan, Ed. K. Takayama, Vol. 1, pp. 511-516.
- Tan, P.J., Reid, S.R., Harrigan, J.J., Zou, Z. and Li, S., 2005a. Dynamic compressive strength properties of aluminium foams. Part I - experimental data and observations. *J. Mech. Phys. Solids***53**, 2174-2205.
- Tan, P.J., Reid, S.R., Harrigan, J.J., Zou, Z. and Li, S., 2005b. Dynamic compressive strength properties of aluminium foams. Part II - 'shock' theory and comparison with experimental data and numerical observations. *J. Mech. Phys. Solids* **53**, 2206-2230.

Zaretsky, E., Ben-Dor, G., 1995. Compressive stress-strain relations and shock Hugoniot curves for flexible foams. *AMSE J. Eng. Mater. Technol.***117**, 278-284.

Zaretsky, E., Asaf, Z., Ran, E., Aizik, F. 2012. Impact response of high density flexible polyurethane foam. *Int'l J. Impact Eng.***39**, 1-7.

Zheng, Z., Wang, C., Yu, J., Reid, S.R., Harrigan, J.J., 2014. Dynamic stress-strain states for metal foams using a 3D cellular model. *J. Mech. Phys. Solids***72**, 93-114.

Zou, Z., Reid, S.R., Tan, P.J., Li, S., Harrigan, J.J. 2009. Dynamic crushing of honeycombs and features of shock fronts. *Int'l J. Impact Eng.***36**, 165-176.

Figure Titles

Fig. 1 (a) A 3-D rendering of a random soap froth with $10 \times 10 \times 12$ cells. (b) Cross-sectional slice with ligaments dressed with beam elements.

Fig. 2 Quasi-static compressive response for foams of four different densities.

Fig. 3 Selected deformed configurations corresponding to points marked on the responses in Fig. 2.

Fig. 4 (a) Calculated initiation stresses, plateau stresses and densification strains and (b) crushing energy density both vs. relative density corresponding to the quasi-static crushing calculations.

Fig. 5 Slice of foam model crushed by shock; shows shock position and problem variables.

Fig. 6 (a) Proximal and (b) distal stress-time histories from direct impact simulation for foams of four densities (constant impact speed $V^+ = 90$ m/s).

Fig. 7 Selected deformed configurations corresponding to the marked points on the responses in Figs. 6a.

Fig. 8 Calculated shock speed-impact velocity Hugoniot for foams of four densities.

Fig. 9 Hugoniot strain vs. impact velocity for foams of four densities.

Fig. 10 Proximal (σ^-) and distal (σ^+) stresses vs. impact velocity for foams of four densities.

Fig. 11 Stresses vs. Hugoniot strain and the Rayleigh lines for $V^+ = 90$ m/s for foams of four densities.

Fig. 12 Energy density expended across shock vs. impact velocity for foams of four densities.

Fig. 13 Proximal stress-displacement responses for quasi-static to supercritical impact velocities for foam models with (a) 3.67% and (b) 10.0% relative densities.

Fig. 14 Deformed configurations of foam models impacted at different speeds. Images correspond to $\delta/h_o = 0.15$ (see responses in Fig. 13).