Decomposition of supercritical ammonia and modeling of supercritical ammonia-nitrogen-hydrogen solutions with applicability towards ammonothermal conditions

Siddha Pimputkar and Shuji Nakamura*

Materials Department, Solid State Lighting, Energy, and Electronics Center,
University of California, Santa Barbara, CA 93106, U.S.A.

*Corresponding Author: University of California, Materials Department, Santa
Barbara, CA 93106-5050; siddha@engr.ucsb.edu, +1 (312) 479 4859

Abstract

Ammonothermal growth of nitrides occurs at temperatures in excess of 800 K and pressures greater than 150 MPa. For this region, no experimentally verified equation of state (EOS) exists for ammonia, nor is there any accurate description available for the equilibrium constant of the ammonia decomposition reaction for

pressures in excess of 100 MPa. To fill this void, experimental P-v-T data was collected for pure ammonia at $T > 700$ K and compared to extrapolated data from the reference EOS for ammonia. For the extrapolated region, the reference EOS provided excellent agreement to within error of the collected experimental data. A simplified EOS based on the Beattie-Bridgeman (BB) EOS was derived and fit to calculated and, for ammonia, extrapolated reference EOS data for ammonia, hydrogen, and nitrogen ($T < 1000$ K, $P < 300$ MPa). By applying mixing rules with separated contributions for polar and non-polar interactions, an EOS was derived for $\text{NH}_3\text{-N}_2\text{-H}_2$ mixtures. With these expressions, an accurate description for the equilibrium constant for the ammonia decomposition reaction as a function of pressure and temperature was derived and verified against experimental data determined for total system pressures of 92, 151, and 210 MPa at $T \sim 810$ K. Coupling of the EOSs with the equilibrium constant permitted accurate modeling of a sealed autoclave filled with pure ammonia, after incorporating corrections for the expansion of the internal free volume due to thermal expansion and elastic strain response of the autoclave walls due to internal pressure buildup. Calculated total system pressure and equilibrium ammonia density at various temperatures and initial ammonia fill densities are in very good to excellent agreement with experimental data. This paper thus provides a simple EOS for ammonia, hydrogen, nitrogen and $\text{NH}_3\text{-N}_2\text{-H}_2$ mixtures accurate to within approximately 1—2 % in pressure for temperatures greater than 700 K. The equilibrium constant for the ammonia decomposition reaction includes non-ideal mixing contributions

from the second virial coefficient with a resulting accuracy in the equilibrium mole fraction of ammonia of approximately 2 % for $T < 850$ K.

Keywords: Supercritical Ammonia; Ammonia Decomposition; Ammonothermal; Ammonia-Nitrogen-Hydrogen Solutions; Beattie-Bridgeman; Equation of State (EOS)

Graphical Abstract

1. Introduction

Gallium Nitride (GaN) is a wide band gap semiconductor material with wide spread applications in electronics and opto-electronics. Advances in light emitting diodes (LEDs) and laser diodes (LDs) have led to longer wavelength devices operating at higher optical powers in the visible spectrum.^{1,2,3} The wide band gap material is increasingly used for power electronic devices due to its higher operating temperature regime compared to existing Si technology and due to the superior properties resulting from the two-dimensional electron gas (2DEG) that forms at the AlGaIn/GaN interface. Most industrial technology is based on the use of heteroepitaxial substrates, sapphire or SiC, with resulting GaN epitaxial films oriented along the polar $\langle 0001 \rangle$ axis. Wide spread availability of large area bulk GaN substrates with arbitrary orientations would enable novel devices and offer additional methods to improve performance and alloying capabilities with other Group III elements.⁴

Growth of bulk GaN is challenging as it cannot be easily grown from a molten solution given the high nitrogen over pressure needed to prevent decomposition. Promising growth techniques that overcome this challenge include hydride vapor phase epitaxy (HVPE)⁵, Na-flux based methods⁶, and the ammonothermal method^{7,8,9,10,11}.

The ammonothermal method is similar to the hydrothermal method and uses a supercritical ammonia and mineralizer (alkali metal or halogen) solution at elevated temperatures (> 700 K) and pressures (> 100 MPa) to dissolve GaN. Typical hot-walled autoclaves (< 300 MPa, < 925 K) require 20—25 mol/l of ammonia to achieve desired dissolved GaN concentrations and appreciable growth rates. To improve our understanding of the growth environment, an accurate description of the equilibrium concentrations of ammonia, hydrogen, and nitrogen during growth is needed, especially since experimental evidence suggests that the solubility of GaN is

inherently linked to the concentration of ammonia (NH_3) and resulting derived compounds such as amides (NH_2^-)¹² or ammonium (NH_4^+)¹³ present during growth.

While some information regarding chemical and physical properties of ammonothermal systems can be extracted from growth runs^{14,15,16}, *in-situ* investigations of the fluid properties^{17,18} and modeling of the heat and fluid flow within the system^{19,20,21}, currently the understanding is incomplete for the dependence of the equilibrium constant for ammonia decomposition on temperature and pressure at typical ammonothermal growth conditions. Furthermore, an experimentally verified equation of state (EOS) is not available for ammonia at temperatures greater than 700 K. The high temperature EOS is necessary to derive many thermodynamic properties.

This paper develops a practical EOS for ammonia, hydrogen, nitrogen, and ammonia-hydrogen-nitrogen mixtures applicable to typical ammonothermal conditions and derives an accurate thermodynamic expression for the equilibrium constant of the ammonia decomposition reaction. This will be done by extrapolating the existing reference EOS for ammonia beyond 700 K and comparing it to experimental data. The reference EOSs for ammonia, nitrogen and hydrogen will then be fit to a simpler, more practical EOS based on the Beattie-Bridgeman (BB) EOS. Using the existing thermodynamic framework for the BB EOS, an EOS for the $\text{H}_2\text{-N}_2\text{-NH}_3$ fluid mixture will be derived and compared to experiment. With these four EOSs, a thermodynamic expression for the equilibrium constant for the ammonia decomposition reaction, and hence equilibrium concentration of ammonia, will be derived and compared to experimental data. Lastly, by coupling the EOS for $\text{NH}_3\text{-H}_2\text{-N}_2$ mixtures and the equilibrium constant, the changes in total system pressure and corresponding dependence of the equilibrium mole fractions of NH_3 , H_2 , and N_2 , are determined for a sealed autoclave and compared to experimental data.

2. Theoretical Background

2.1. Equation of States

2.1.1. Pure Gases

An EOS provides a relationship between state variables of a system and can be used to determine various thermodynamic properties of a system. Various EOSs have been developed over the years, with the most accurate ones being empirical multiparameter equation of states (MEOS), which typically become the reference for the properties of that substance. MEOS typically represent the reduced Helmholtz free energy α of the substance as a sum of ideal and residual terms, both of which are explicit in reduced temperature $\tau = T_c/T$ and density $\delta = \rho/\rho_c$, where c denotes its critical value, T absolute temperature and ρ its density. A summary of the critical properties for ammonia, hydrogen and nitrogen is provided in Table 1.

$$\alpha(\tau, \delta) := \frac{a(T, \rho)}{RT} = \alpha^0(\tau, \delta) + \alpha^r(\tau, \delta) \quad (1)$$

Ideal and real contribution are parametrized and fit to experimental data for the specific fluid. Derived thermodynamic properties can be calculated from the Helmholtz free energy, including pressure:

$$P(\tau, \delta) = \rho RT \left[1 + \delta \left(\frac{\partial \alpha^r}{\partial \delta} \right)_\tau \right] \quad (2)$$

Table 1

Critical temperature (T_c), pressure (P_c) and density (ρ_c) for ammonia (NH₃), hydrogen (H₂) and nitrogen (N₂), respectively.

Fluid	T_c (K)	P_c (MPa)	ρ_c (mol/l)	Ref
NH₃	405.37	11.345	13.75	[22]
H₂	33.145	1.2964	15.508	[24]
N₂	126.192	3.3958	11.1839	[23]

The current reference properties for N₂, H₂, and NH₃ as provided by the National Institute of Standards and Technology (NIST) are derived from the MEOS for N₂ (applicable for temperatures between 63.151 to 1000 K and pressures up to 2200 MPa)²³, H₂ (applicable up to 1000 K and 2000 MPa)²⁴ and NH₃ (applicable up to 700 K and 1000 MPa)²⁵. Using the reference MEOS for NH₃, a P- ρ -T phase diagram was calculated and extrapolated beyond the experimentally verified 700 K temperature. Fig. 1 shows this P-T phase diagram for ammonia with overlaid contours of NH₃ density and applicable stable phase for the given P- ρ -T condition.

Fig. 1. P-T phase diagram of pure ammonia (NH_3) with contour lines of density ρ (mol/l) and superimposed phases present at equilibrium. Calculated and extrapolated beyond 700 K using the reference multiparameter equation of state (MEOS) as provided by the National Institute of Standards and Technology (NIST).^{25, 26, 27, 28, 29}

While highly accurate, MEOSs typically have a large number of terms (> 20) with varying exponential forms making it tedious and cumbersome to use in thermodynamic derivations and applying towards mixture of fluids, suggesting the use of a simpler, uniform EOS. For the purpose of this paper, it is of interest to determine the feasibility of using a modified Beattie-Bridgeman (BB) EOS given its ability to accurately determine the equilibrium constant of ammonia at elevated pressures (< 100 MPa) and temperatures (< 775 K).³⁰

$$P = \frac{RT(1 - \epsilon)}{v^2}(v + B) - \frac{A}{v^2} \quad (3)$$

Where R is the universal gas constant, P is pressure, T is absolute temperature, and v the molar volume calculated by dividing the volume V by n moles of gas: V/n .

The constant A in this equation originates from the observation that the potential energy between molecules is directly related to the density. Differentiating the potential energy with respect to volume provides the cohesive pressure. Corrections to the intermolecular forces for the dielectric constant of the gases leads to an expansion in higher orders of density. The traditional BB EOS only includes first order corrections, $A = A_0 \left(1 - \frac{a}{v}\right)$, it is proposed to expand them to second order

$$A = A_0 \left(1 - \frac{a}{v} - \frac{a_1}{v^2}\right). \quad (4)$$

The constant B is related to the attraction or repulsion of molecules due to intermolecular forces causing an increase in overall momentum transfer, and hence kinetic pressure, across any plane within the fluid. This term depends on the density of molecules and while the traditional BB EOS only expands this term to first order, $B = B_0 \left(1 - \frac{b}{v}\right)$, it is proposed to expand it to second order as well,

$$B = B_0 \left(1 - \frac{b}{v} - \frac{b_1}{v^2}\right). \quad (5)$$

The effects of temperature on the intermolecular force are included in the ϵ term. At lower temperature, molecules will form aggregates for extended periods of time modifying the time of encounter between molecules. This effect can also be thought of as an effective increase in average molecule weight in a system with fewer independent molecules, thereby effectively

reducing the pressure. The BB EOS incorporates and approximates the degree of aggregation to be linear with density and inversely proportional to the temperature raised to some power. Comparison with experimental data suggested an exponent of three to be very satisfactory. The corrective term, ϵ , therefore became

$$\epsilon = \frac{c}{vT^3} \quad (6)$$

Using these expressions, a total of seven fitting parameters ($A_0, B_0, a, a_1, b, b_1, c$) are needed to fully express the modified BB EOS.

The same EOS can be also be reformulated as a virial expansion:

$$P = \frac{RT}{v} + \frac{\beta}{v^2} + \frac{\gamma}{v^3} + \frac{\delta}{v^4} + \frac{\zeta}{v^5} \quad (7)$$

With

$$\begin{aligned} \beta &= RTB_0 - A_0 - \frac{Rc}{T^2} \\ \gamma &= -RTB_0b + A_0a - \frac{RcB_0}{T^2} \\ \delta &= -RTB_0b_1 + A_0a_1 + \frac{RcB_0b}{T^2} \\ \zeta &= \frac{RcB_0b_1}{T^2} \end{aligned}$$

The traditional BB EOS (omission of second order terms in density: $a_1 = 0, b_1 = 0$) accurately represented the behavior of NH_3 , H_2 and N_2 for moderate densities ($< 3 \text{ mol/l}$) and temperatures ($< 700 \text{ K}$). The accepted values for the traditional BB constants for these three gases are provided in Table 2, along with the highest experimental data point in temperature and

corresponding density used when creating the constants. Use of the traditional BB EOS with constants provided in Table 2 were found to be very inaccurate for higher densities of the gases.

Table 2

Standard values for the constants of the traditional Beattie-Bridgeman (BB) equation of state (EOS) for hydrogen (H_2), nitrogen (N_2) and ammonia (NH_3). Highest temperature and associated density data point used when fitting experimental data for determination of the constants is provided.

Gas	A_0 (Pa m ⁶ /mol ²)	B_0 (x10 ⁵) (m ³ /mol)	a (x10 ⁵) (m ³ /mol)	b (x10 ⁵) (m ³ /mol)	c (K ³ m ³ /mol)	Upper Bound		Ref
						T (K)	ρ (mol/l)	
NH_3	0.24247	3.4150	17.031	19.112	4768.7	598	2.9	[31]
H_2	0.02001	2.096	-0.5060	-4.359	0.5040	473	2.5	[30]
N_2	0.1362	5.046	2.617	-0.6910	42.00	673	1.5	[30]

2.1.2. Gas Mixtures

To arrive at an EOS for gas mixtures, it is convenient to assume that the form of the EOS remains unchanged to that of a pure gas. With this assumption, it is important to properly determine the new constants for the EOS as they depend on the gas composition. The simplest mixing rule would be to perform a linear sum of each variable independently, while weighting them by their molar fraction. This summation yields constants assuming an ideal mixture of real gases. To provide an EOS that behaves according to a real mixture, it is convenient to analyze

the second virial coefficient β and derive appropriate mixing rules for the various constants according to statistical thermodynamic and analysis of the intermolecular potential energy.

Using this approach, B_0 is related to the molecule diameter. With the assumption that the collision radii of two unlike molecules may be added to obtain the collision diameter of the pair, one arrives at a Lorentz combination for the individual B_0 values.

For the terms A_0 and c , the rules follow from theoretical predictions that the dispersion term in the potential energy between unlike pairs is not far from the geometric mean of that for two similar pairs, resulting in a square-root combination.

Given the polar nature of ammonia and non-polar nature of H_2 and N_2 , it was found that one needs to separate the mixing terms for A_0 and c into a non-polar ($A_{0,np}$, c_{np}) and polar ($A_{0,p}$, c_p) term as the dipole-dipole forces vanish when one of the two molecules in the pair is non-polar, yielding the following relationship:

$$\begin{aligned} A_0 &= A_{0,np} + A_{0,p} \\ c &= c_{np} + c_p \end{aligned}$$

The polar and non-polar contribution for a polar gas can be approximated by assuming a Stockmayer potential yielding the following relationships³²

$$\begin{aligned} A_{0,np} &= \frac{1}{2} \left(A_0 + (A_0^2 - 7.56 \times 10^{-3} \mu^4)^2 \right) \\ A_{0,p} &= \frac{1}{2} \left(A_0 - (A_0^2 - 7.56 \times 10^{-3} \mu^4)^2 \right) \\ c_{np} &= c - c_p \\ c_p &= 1.64 \times 10^{-6} \frac{\mu^4 A_{0,p}}{B_0^2} \end{aligned}$$

Where μ is the dipole moment of the gas in Debye units (1.471 for ammonia). The units for A_0 are $\text{Pa m}^6/\text{mol}^2$, B_0 m^3/mol and c $\text{K}^3 \text{m}^3/\text{mol}$. The mixing of the polar and non-polar terms can be performed individually by use of the square-root combination.³³

Without analyzing the third virial coefficient, the mixing for the remaining terms (a, a_1, b, b_1) was performed by linear combination as they make smaller contributions to the final mixing term.

The following equations summarize the applied mixing rules for which i denotes a gas species and x_i its mole fraction in the gas mixture:

$$\begin{aligned}
A_{0,m} &= \left(\sum_i x_i \sqrt{|A_{0,np,i}|} \right)^2 + \left(\sum_i x_i \sqrt{|A_{0,p,i}|} \right)^2 \\
a_m &= \sum_i x_i a_i \\
a_{1,m} &= \sum_i x_i a_{1,i} \\
B_{0,m} &= \frac{1}{8} \sum_i \sum_j x_i x_j (\sqrt[3]{B_{0,i}} + \sqrt[3]{B_{0,j}})^3 \\
&= \frac{1}{4} \sum_i x_i B_{0,i} + \frac{3}{4} \left(\sum_i x_i B_{0,i}^{1/3} \right) \left(\sum_i x_i B_{0,i}^{2/3} \right) \\
b_m &= \sum_i x_i b_i \\
b_{1,m} &= \sum_i x_i b_{1,i} \\
c_{np,m} &= \left(\sum_i x_i \sqrt{c_{np,i}} \right)^2 + \left(\sum_i x_i \sqrt{c_{p,i}} \right)^2
\end{aligned} \tag{8}$$

As will be presented later in this paper, the newly determined A_0 value for H_2 is negative. To circumvent mathematical challenges in taking the square root of a negative number, the following rule was applied for the evaluation of $A_{0,m}$:

$$\left(\sum_i x_i \sqrt{M}\right)^2 = \text{Sign}\left[\sum_i x_i \text{Sign}[M] \sqrt{|M|}\right] \left(\sum_i x_i \text{Sign}[M] \sqrt{|M|}\right)^2 \quad (9)$$

2.2. Decomposition of Ammonia

The equilibrium reaction for NH_3 , H_2 , and N_2 is as follows

It is of interest to derive a rigorous thermodynamic expression for the dependence of the equilibrium constant of this reaction on changes in composition of the gas mixtures, total system pressure, and temperature for real gases in real mixtures.

A definition for the equilibrium constant can be found by setting the sum of the products of the chemical potentials μ_i for the species i with their stoichiometrical coefficients, ν_i , equal to zero: $\sum_i \nu_i \mu_i = 0$. The coefficient ν_i is negative for reactants. By invoking the definition of activity:

$$\mu_i = \mu_i^0 + RT \ln a_i, \quad (11)$$

whereby, μ_i^0 is the standard chemical potential of species i at its standard state, R the gas constant, T the absolute temperature and performing the summation over all species, one arrives at

$$\sum_i \nu_i \mu_i^0 = \Delta G_{rxn}^0 = -RT \sum_i \nu_i \ln a_i, \quad (12)$$

where ΔG_{rxn}^0 is the standard Gibbs free energy for the reaction. The right hand side of the equation can be further manipulated

$$-RT \sum_i \nu_i \ln a_i = -RT \ln \prod_i a_i^{\nu_i} = -RT \ln K_a \quad (13)$$

yielding an expression for the equilibrium constant K_a as the ratio of activities raised to the power ν_i for all species i , with reactants in the denominator and products in the numerator. It is important to highlight that K_a is only a function of temperature as ΔG_{rxn}^0 is constant.

As the chemical reaction of interest involves gaseous species, it is convenient to define the fugacity f_i of species i in a mixture by means of the chemical potential

$$d\mu_i = RT d \ln f_i. \quad (14)$$

Upon integration, while using the standard state for the lower integration limit, one can immediately see that the activity, a_i , is equal to the fugacity normalized to its reference value f_i/f_i^0 . At very low pressures ($P \rightarrow 0$), the fugacity tends to the pressure, P^* , for pure gases and to $x_i P^*$ for mixtures, where x_i is the mole fraction of gas i in the mixture. This is a consequence of Lewis-Randall's Law which states that the fugacity of a gas in a mixture (f_i^e) is equal to its mole fraction (x_i) in the mixture multiplied by its fugacity at the temperature and total mixture pressure, f_i^P .

Replacing activities with fugacities and neglecting the minor correction term resulting from slight differences in f_i^0 at the standard state of, typically, 1 bar, one can equate $K_a = K_f$.

Differentiation of the definition of the fugacity (14) with respect to pressure and utilizing a Maxwell relationship one finds

$$RT \left(\frac{\partial \ln f_i}{\partial P} \right)_{T, x_i} = \left(\frac{\partial \mu_i}{\partial P} \right)_{T, x_i} = \left(\frac{\partial V}{\partial n_i} \right)_{T, x_j}. \quad (15)$$

Integrating the expression from a very low pressure, $x_i P^*$, to the total mixture pressure P results in

$$\ln f_i - \ln x_i P^* = \frac{1}{RT} \int_{x_i P^*}^P \frac{\partial V}{\partial n_i} dP. \quad (16)$$

A similar expression can be derived for fugacities for pure gases.

To determine the functional dependence of the fugacity of a gas in a mixture to changes in temperature, composition and pressure, a simple thought experiment can be used.³⁴ A semi-permeable membrane separates two gaseous volumes and allows gas 1 to freely diffuse between the two volumes. One side is a gaseous mixture at very low pressure, P^* , containing a mole fraction x_1 of gas 1. The other side is pure gas 1 at the same temperature, in equilibrium with the gas mixture at pressure P_e . The pressure is then increased on both sides (dP_e on the pure side, dP on the mixtures side) at constant temperature and composition in the mixture such that equilibrium is preserved at all times, leading to $\partial \mu_{1, \text{pure}} = \partial \mu_{1, \text{mix}}$. Invoking the same Maxwell relationship as equation (15) one finds that

$$\frac{\partial V}{\partial n_1} dP_e = \frac{V}{n_1} dP_e = \frac{\partial V}{\partial n_1} dP, \quad (17)$$

where the partial molar volume of the pure substance is equal to its molar volume V/n_1 .

Integration of this expression after adding and subtracting additional terms leads to the following expression:

$$\begin{aligned}
& \int_{x_1 P^*}^{P_e} \frac{V}{n_1} dP_e + RT \ln x_1 P^* \\
& = \int_{P^*}^P \left(\frac{\partial V}{\partial n_1} - \frac{V}{n_1} \right) dP + \int_{P^*}^P \frac{V}{n_1} dP + RT \ln P^* + RT \ln x_1
\end{aligned} \tag{18}$$

which can be simplified by utilization of equation (16)

$$RT \ln(f_1^e) = \int_{P^*}^P \left(\frac{\partial V}{\partial n_1} - \frac{V}{n_1} \right) dP + RT \ln(f_1^P) + RT \ln(x_1). \tag{19}$$

In this expression, f_1^e is the fugacity of the pure gas 1 at its equilibrium pressure, P_e , with respect to the mixture, which is at its mixture pressure P . f_1^P is the fugacity of the pure gas at the mixture pressure. Further simplification can be achieved by adding and subtracting $\int_{P^*}^P \frac{RT}{P} dP$ to equation (16) modified for pure gases, leading to

$$RT \ln(f_1^P) = \int_{P^*}^P \left(\frac{V}{n_1} - \frac{RT}{P} \right) dP + RT \ln P. \tag{20}$$

Inserting into equation (19) provides a relationship between the fugacity of a gas in a mixture as a function of temperature, mixture pressure and composition.

$$\ln(f_1^e) = \frac{1}{RT} \int_0^P \left(\frac{\partial V}{\partial n_1} - \frac{RT}{P} \right) dP + \ln(x_1 P) \tag{21}$$

Having found the fugacity, and therefore also chemical potential, of a gaseous species in the mixture, f_1^e , the equilibrium constant can be determined by summing each relationship for each species i weighted by their stoichiometrical coefficient ν_i . In doing so $\sum_i \nu_i \ln(f_i^e) = \ln(K_f)$ and $\sum_i \nu_i \ln(x_i P) = \ln(K_p)$ based on equation (13).

$$\ln \left(\frac{K_p}{K_f} \right) = -\frac{1}{RT} \sum_i \left\{ \nu_i \int_0^P \left(\frac{\partial V}{\partial n_i} - \frac{RT}{P} \right) dP \right\} \tag{22}$$

This equation provides a general thermodynamic relationship for the equilibrium constants without any approximations beyond those applied at the low pressure side, for which certain thermodynamic properties of real gases and mixtures approach those of ideal gases and mixtures in a definite manner. (Detailed discussion of the approximations made can be found in Ref [35])

Two terms now need be evaluated before the desired equilibrium constant K_P can be evaluated.

The functional dependence of K_f on temperature and the value of the integrand $\left(\frac{\partial V}{\partial n_i} - \frac{RT}{P}\right)$.

Determination of K_f can be achieved by realizing it is only a function of temperature and can be evaluated at any P . It is convenient to use the low pressure limit, as ideal gas approximations hold true, and therefore it is preferred to simplify the nomenclature by setting $K_f = K_P^*$. Evaluation of the temperature dependence of $\ln(K_P^*)$ can be performed by assuming ideal gas and therefore using Van't Hoff's equation:

$$\frac{d \ln(K_P^*)}{dT} = \frac{\Delta H^*}{RT^2} \quad (23)$$

ΔH^* is the heat absorbed by the reaction at zero pressure. Its dependence on temperature can be determined using Kirchoff's law:

$$\frac{d\Delta H^*}{dT} = \Delta C_P^* = \sum_i (v_i C_{P,i}^*) \quad (24)$$

The limiting value of the specific heat at constant pressure at zero pressure may be calculated by a series expansion in temperature:

$$C_{P,i}^* = R + A_i + B_i T + C_i T^2 \quad (25)$$

for which the constants are given in Table 3³⁸:

Table 3

Values for the specific heat capacity constants of equation (25) from Ref [38]

Gas	A (J / mol K)	B (x10³) (J / mol K ²)	C (x10⁶) (J / mol K ³)
NH₃	25.3	2.97	21.3
H₂	19.5	2.93	0.00
N₂	20.2	1.38	0.210

Integrating Kirchoff's law using this assumption yields

$$\Delta H^* = \left[\sum_i (v_i A_i) + \sum_i (v_i) R \right] T + \frac{1}{2} \sum_i (v_i B_i) T^2 + \frac{1}{3} \sum_i (v_i C_i) T^3 + I \quad (26)$$

While inserting this relationship into Van't Hoff's equation and further integration yields

$$\ln(K_p^*) = \frac{\sum(v_i A_i) + \sum(v_i) R}{R} \ln(T) + \frac{\sum(v_i B_i)}{2R} T + \frac{\sum(v_i C_i)}{6R} T^2 - \frac{I}{RT} + J \quad (27)$$

The integration constants I and J are related to the specific heats, molar energy, $u_{0,i}$, and molar entropy, $s_{0,i}$, constants of the reacting gases at T_0 and infinitely low pressure.³⁶

$$I = \sum (v_i A_i) T_0 + \frac{1}{2} \sum (v_i B_i) T_0^2 + \frac{1}{3} \sum (v_i C_i) T_0^3 - \sum (v_i u_{0,i}) \quad (28)$$

$$J = \frac{1}{R} \left(- \left(\sum (v_i A_i) + \sum (v_i) R \right) (1 + \ln(T_0)) - \sum (v_i B_i) T_0 \right. \\ \left. + \frac{1}{2} \sum (v_i C_i) T_0^2 + \sum (v_i s_{0,i}) \right) \quad (29)$$

The energy and entropy constants can be determined from the traditional BB EOS using following relationships³⁷

$$u_0 = u + \frac{nA_0}{V} \left(1 - \frac{na}{2V} \right) + \frac{3nRc}{VT_0^2} \left(1 + \frac{nB_0}{2V} - \frac{n^2 B_0 b}{3V^2} \right) \quad (30)$$

$$s_0 = s - R \ln \left(\frac{V}{nRT_0} \right) + \frac{nRB_0}{V} \left(1 - \frac{nb}{2V} \right) + \frac{2nRc}{VT_0^3} \left(1 + \frac{nB_0}{2V} - \frac{n^2 B_0 b}{3V^2} \right) \quad (31)$$

The values for the reference molar energy, u , and molar entropy, s , of the gas at T_0 and the molar volume V/n are set to 0 for $T_0 = 273.13^\circ\text{C}$ and using the applicable molar volume. For the purpose of this study, the integration constants I and J were based on experimentally determined values as they were deemed more accurate³⁸ and set equal to $I = -38319 \text{ J/mol}$ and $J = -5.33239$.

In order to evaluate the integrand $\left(\frac{\partial V}{\partial n_i} - \frac{RT}{P} \right)$ it is convenient to separate it into contributions from mixing and from real gas behavior:

$$\frac{\partial V}{\partial n_i} - \frac{RT}{P} = \left(\frac{\partial V}{\partial n_i} - \frac{V}{n_i} \right) + \left(\frac{V}{n_i} - \frac{RT}{P} \right) \quad (32)$$

The first difference expresses the excess partial molar volume of a gas in a mixture relative to its molar volume when pure at the temperature and pressure of the mixture, P . For an ideal mixture this term would be zero, though given the BB EOS (3) and using the mixing rules (8), one can calculate the deviation term D_i to be

$$\begin{aligned}
\left(\frac{\partial V}{\partial n_i} - \frac{V}{n_i}\right) &= \frac{D_i}{RT} \\
&= -\frac{3}{4} \left(B_{0,i}^{1/3} - \sum_j x_j B_{0,j}^{1/3} \right) \left(B_{0,j}^{2/3} - \sum_j x_j B_{0,j}^{2/3} \right) \\
&\quad + \frac{(\sqrt{A_{0,np,i}} - \sum_j x_j \sqrt{A_{0,np,j}})^2}{RT} + \frac{(\sqrt{A_{0,p,i}} - \sum_j x_j \sqrt{A_{0,p,j}})^2}{RT} \\
&\quad + \frac{(\sqrt{c_{np,i}} - \sum_j x_j \sqrt{c_{np,j}})^2}{T^3} + \frac{(\sqrt{c_{p,i}} - \sum_j x_j \sqrt{c_{p,j}})^2}{T^3}
\end{aligned} \tag{33}$$

The integration hence becomes

$$\int_0^P \left(\frac{\partial V}{\partial n_i} - \frac{RT}{P} \right) dP = \int_0^P \frac{D_i}{RT} dP + \int_0^P \left(\frac{V}{n_i} - \frac{RT}{P} \right) dP$$

The second integral can be most easily evaluated by using the BB EOS in its virial form (7) and applying the following for the lower limit of integration $(\ln P)_{P=0} + (\ln v)_{v=\infty} = \ln RT$:

$$\int_0^P \left(\frac{V}{n_i} - \frac{RT}{P} \right) dP = -RT \ln \frac{PV}{n_i RT} + \frac{2\beta}{v_i^2} + \frac{3\gamma}{v_i^3} + \frac{4\delta}{v_i^4} + \frac{5\zeta}{v_i^5} \tag{34}$$

Yielding the following final expression for the equilibrium constant

$$\ln\left(\frac{K_P}{K_P^*}\right) = -\frac{1}{RT}\left\{\sum_i v_i \frac{PD_i}{RT} + \sum_i v_i \left(-RT \ln \frac{PV}{n_i RT} + \frac{2\beta_i n_i}{V} + \frac{3\gamma_i n_i^2}{V^2} + \frac{4\delta_i n_i^3}{V^3} + \frac{5\zeta_i n_i^4}{V^4}\right)\right\} \quad (35)$$

Having fully determined all the necessary relationships, the equilibrium constant K_P can be calculated through an iterative approach. A provisional K_P can be determined by calculating K_P^* using equation (27) and using a simplified version of (35) which is independent of composition:

$$\ln\left(\frac{K_P}{K_P^*}\right) = -\frac{P}{RT} \sum_i \left[v_i \left(B_{0,i} - \frac{A_{0,i}}{RT} - \frac{c_i}{T^3} \right) \right] \quad (36)$$

With knowledge of an approximate value for the equilibrium constant K_P , along with the total system pressure P , the mole fraction of ammonia, α , can be determined. This is done by starting with a system that only contains pure H_2 and N_2 , expressed in their respective mole fractions as q and r , and allowing it to equilibrate according to the value K_P . For stoichiometric mixtures $q = 3/4$ and $r = 1/4$, though will differ for non-stoichiometric mixtures.

$$K_P = \frac{\alpha/(1+\alpha)^2}{\sqrt[2]{q - 3\alpha/2(1+\alpha)} \cdot \sqrt[3]{r - \alpha/2(1+\alpha)}} \cdot \frac{1}{P} \quad (37)$$

A more accurate value for K_P can then be determined using equation (35), from which a new equilibrium mole fraction of ammonia can be calculated. This process can be repeated until the

desired accuracy is reached, providing the desired equilibrium concentration of ammonia in the mixture.

2.3. Correction Terms for Volumetric Expansion of Autoclave

As ammonothermal growth occurs in sealed autoclaves, corrections need to be made to the internal free volume of the autoclave and hence density of gas species in the system. Two types of corrections were performed for this investigation, the first related to the thermal expansion of the autoclave and the second to the elastic response of the autoclave due to stresses in the autoclave wall to contain the high pressure fluid.

The correction for thermal expansion was performed by assuming the autoclave behaved isotropically in temperature permitting the use of an average value for the linear thermal expansion coefficient, α_L . The change in temperature, ΔT , was taken relative to room temperature – the temperature at which the free volume was experimentally determined.

$$V_{hot} = V_{cold}(1 + 3\alpha_L\Delta T) \quad (38)$$

Correction for the elastic expansion of the autoclave due to internal pressure, P , thick walled pressure vessel equations were used for the simplifying case of a closed end cylindrical vessel with inner radius, r_i , and outer radius, r_o , and assuming no external pressure. The solutions for radial and hoop stresses and displacements are also known as the Lamé's equations. The radial, σ_r , hoop, σ_θ , and longitudinal, σ_z , stresses are

$$\begin{aligned}\sigma_r &= -P \\ \sigma_\theta &= P \frac{r_o^2 + r_i^2}{r_o^2 - r_i^2} \\ \sigma_z &= P \frac{r_i^2}{r_o^2 - r_i^2}\end{aligned}$$

The resulting expansion in inner length, l , of the autoclave can be calculated from Hooke's Law ($\varepsilon_z = (\sigma_z - \nu\sigma_r - \nu\sigma_\theta)/E$, where ε_z is the resulting strain along the axis, E the elastic modulus, and ν Poisson's ratio) yielding the following displacements for the radius, u_r , and axis, u_z :

$$\begin{aligned}u_r &= \frac{P}{E} \left(\frac{r_o^2 + r_i^2}{r_o^2 - r_i^2} + \nu \right) r_i \\ u_z &= \frac{P}{E} \frac{r_i^2}{r_o^2 - r_i^2} (1 - 2\nu) l\end{aligned}$$

A resulting correction term to the free volume can be approximated by only including first order correction terms in displacement and assuming the free volume can be described by a cylindrical volume ($V_{P=0} = \pi r^2 l$) for which r is set to the measured inner autoclave diameter and l is adjusted to equal the experimentally measured free volume, $V_{P=0}$. The corrected free volume at pressure, $V_{P=P}$, then becomes

$$V_{P=P} = V_{P=0} \left(1 + \frac{u_z r_i^2 + 2u_r r_i l}{r_i^2 l} \right) \quad (39)$$

Combining and simplifying equations (38) and (39), a correction term for the initial fill density of ammonia, ρ_{fill} , to determine the effective density of ammonia at any T and P of the system was found to be

$$\rho_{hot,P=P} = \rho_{fill} (1 + 3\alpha_L \Delta T)^{-1} \left(1 + \frac{P (2 + 2\nu)r_o^2 + (3 - 4\nu)r_i^2}{E (r_o^2 - r_i^2)} \right)^{-1} \quad (40)$$

For the highest pressure and temperature runs performed in the autoclaves part of this study, the correction can be as high as ~ 3 % for the expansion of the free volume (reduction in fill density) over its cold, unpressurized state.

3. Experiments and Methods

3.1. Equation of State

3.1.1. Experimental Determination of P-v-T Relationship for Ammonia

In order to verify the applicability of the MEOS for ammonia at temperatures greater than 700 K, a René 41 autoclave system was built which contained an internal thermocouple to accurately measure the fluid temperature. A type K thermocouple with special limits of error (± 1.1 °C or ± 0.4 %) contained in a nitrided Inconel sheath was inserted such that the junction extended approximately two inches into the free volume of the body of the autoclave (8 inches above the bottom of the inside of the autoclave).

The inner dimensions of the autoclave included an inner diameter of 1 inch, an inner bore length of approximately 10 inches, and, when sealed, an internal free volume of approximately 160 ml. The inner surfaces of the autoclaves were heavily nitrided from previous ammonothermal growth runs minimizing the formation of new nitrides at the expense of ammonia fill.

The procedure to collect P-T data points at specific fill densities of ammonia was as follows. The autoclave and its parts were initially cleaned using acetone, isopropanol alcohol, and deionized water, and then dried in a vacuum oven to minimize contamination from oxygen and water. After sealing the autoclave with a head assembly, defined by a high pressure cross, a needle valve, a thermocouple feedthrough, and an external amplified pressure transducer (Honeywell, HP, Accuracy ± 2 MPa, Hysteresis: < 5 MPa), the internal free volume of the system was measured.

The internal free volume was experimentally determined by expanding ultra-high purity (UHP) nitrogen from a pressurized calibration volume into the empty autoclave. Ideal gas laws were then used to determine the increase in total system volume based on the drop in gas pressure. Details on this procedure will now be outlined.

The calibration volume (150.73 ml), was determined to an accuracy of ± 0.03 ml, contained an internal thermocouple (Type T) and had a high linearity pressure transducer attached to it (Omega Dyne, PX429-150A, Accuracy: ± 0.05 psia, Serial: 423728). The free volume (V_{free}^{Total}) was measured by initially connecting the calibration volume (V_{CV}) to the opened needle valve attached to the head assembly of the autoclave. The combined system was evacuated to a pressure below 10^{-1} torr (P_{CV}^{Vac}) and the valve to the autoclave was then sealed. Purified nitrogen was filled into the calibration volume. Once the internal nitrogen gas temperature stabilized, the temperature (T_{CV}^*) and pressure ($P_{CV}^{N_2}$) were recorded. The valve to the autoclave was opened and once the system had equilibrated, the temperatures of the gas in the autoclave (T_A) and in the calibration volume (T_{CV}) were recorded, along with the new final pressure ($P_{CV+A}^{N_2}$). Using ideal gas assumptions, the internal free volume of the autoclave was then calculated using equation (41). This process was repeated at least 3 times for each run, yielding internal free volume errors

for the autoclave system of ± 0.3 ml. The determined value was taken as the accessible free volume for the ammonia in the system.

$$V_{free}^{Total} = V_{CV} \left(\frac{P_{CV}^{N_2} - P_{CV}^{Vac}}{P_{CV+A}^{N_2} - P_{CV}^{Vac}} \frac{T_{CV}}{T_{CV}^*} - 1 \right) \left(\frac{T_A}{T_{CV}} \right) \quad (41)$$

After measuring the internal free volume, the pressure transducer attached to the autoclave was zeroed at room temperature and ambient pressure. The autoclave was cooled with liquid nitrogen and filled with pure ammonia (Showa Denko K.J. with 99.99995 % purity) purified using a Japan Pionics (JAP-5E-S) and a SAES MicoTorr (MC500-702FV) point-of-use purifier. The amount of ammonia was determined by means of integrating the signal from a mass flow controller calibrated for ammonia (Horiba STEC, SEC-E440J) and by comparing the weight before and after filling with ammonia (A&D, GX-10k, Precision: ± 10 mg). Both measurements consistently provided comparable values.

The autoclave was allowed to warm up for an hour and was then placed in a heater setup dedicated for ammonothermal growth. Further details on the experimental setup can be found in reference [39]. The autoclave was heated uniformly at a constant rate of $2^\circ\text{C}/\text{min}$ to an external wall temperature of 600°C . The autoclave was held at that temperature for one hour to verify the system was leak tight and was then allowed to cool to a temperature below 30°C at which point the total system pressure was recorded. After weighing the reactor, venting the gas, and weighing it again, the weights were compared to those at the beginning of the run to determine if any ammonia leaked out of the system. The zero drift of the pressure transducer was determined by measuring the voltage output at room temperature and ambient temperature. The drifts were between 0.1 and 0.5 MPa, within the error of the transducers.

This process was repeated eight times for ammonia fills of 2.24, 2.56, 2.88, 3.19, 3.52, 3.80, 3.80, and 3.99 mol_{NH3}.

3.1.2. Determination of BB EOS constants for pure Gases

The determination of new BB EOS constants applicable to the region of interest was performed by fitting the following equation to isochoric data calculated using the MEOS for the applicable gas:

$$P + \Gamma = \psi T - \phi \quad (42)$$

Where

$$\begin{aligned} T^2 \Gamma &= \frac{\psi c}{v} \\ \psi &= \frac{R(v + B)}{v^2} \\ \phi &= \frac{A}{v^2} \end{aligned}$$

with the molar volume v and the constants A , B , and c being those defined in BB EOS (3). The Γ term may be thought of as a correction term to the experimentally determined pressure to straighten the isochore lines. The resulting slope, ψ , and intercept, ϕ , of a line fit through the corrected pressure data results in determination of the BB constants A and B .

The fitting procedure was performed by means of the non-linear least squares method, seeding the algorithm with an approximate value determined from the traditional BB EOS constants provided in Table 2, and allowing ψ , ϕ , and c to freely vary until the sum of the squared errors was minimized. After performing this fitting procedure independently on multiple isochores for a

given gas, the final value for c was found by averaging all the determined values over a specified density range (see Fig. 4 (c)).

A second round of fitting was then performed, using the same procedure detailed above, but fixing the value of c to the determined value and only allowing variations in ψ and ϕ . The resulting values for A and B , calculated from the fitted values for ψ and ϕ , were then plotted against their corresponding density $1/v$ (see Fig. 4 (a) and (b)). A second order polynomial was then fit to the data by means of a linear least square method and minimizing the sum of the squared errors, yielding values for A_0, B_0, a, a_1, b , and b_1 .

This procedure was performed on calculated isochores from the reference MEOS provided by NIST. Within their defined region of applicability, the MEOS are considered accurate to less than at least 0.5 % error. Isochoric data was calculated in steps of 0.5 mol/l from 0.5 mol/l to 30 mol/l for NH_3 and N_2 and from 0.5 mol/l to 35 mol/l for H_2 . Temperatures ranged from 450 K to 1000 K in steps of 5 K. For the c value, computed values were averaged between 10—30 mol/l for ammonia and N_2 , and 20—35 mol/l for H_2 . Higher densities were selected as the effect of c is more prominent (higher curvature of the isochore) and hence provides a better means of fitting for this value. For ammonia, the density range was selected as it reduced the relative errors from the BB EOS with respect to the calculated values from the MEOS in the region of interest.

For determination of the value A and B , the second order polynomial was fit to densities ranging from 5—30 mol/l for ammonia, 1—30 mol/l for N_2 , and 1—35 mol/l for H_2 . For ammonia, it was found that overall a lower relative error to the MEOS in the higher temperature (> 600 K) and pressure region of interest occurred when a lower density of 5 mol/l instead of 1 mol/l was chosen when fitting A and B . As the motivation of this investigation is to find an EOS that is

accurate in the higher temperature and density region and not a universal EOS ranging the entire density and temperature spectrum this modification was deemed acceptable.

3.2. Decomposition of Ammonia

3.2.1. Total System Pressure for $\text{NH}_3\text{-N}_2\text{-H}_2$ Mixture in Equilibrium

In order to determine the accuracy of the BB EOS for gas mixtures using the stipulated mixing rules (8) and newly determined constants for the BB EOS (Table 4), four runs with different ammonia fill densities were performed during which the autoclave was held at various temperatures until equilibrium was reached. Due to enhanced permeability of hydrogen through the autoclave wall at elevated temperatures, diffusional mass loss of hydrogen from the system occurred at elevated temperatures and attempts were made to account for this loss.

The runs associated with this study were performed in the identical experimental setup and subject to the same loading procedure as detailed in Section 3.1.1 for the determination of the P-T data for pure ammonia. The run temperature profile differed in that the autoclave was heated at 2 °C/min until the external wall temperature of the autoclave uniformly reached 350 °C. The autoclave was then held at this temperature plateau until the total system pressure no longer increased by 0.2 MPa over the course of a day. Once this criteria was met, the total system pressure and internal fluid temperature were recorded. The autoclave was then uniformly ramped at 2 °C/min to the next temperature plateau. A total of six plateaus were established, ranging from 350 °C to 600 °C in steps of 50 °C based on external wall temperatures. A total of four

different runs were performed with ammonia fills of 1.650, 2.737, 3.475, and 3.960 mol_{NH3} with target total system pressures of 100, 150, 200, and 250 MPa. Once the run was complete, the autoclave was cooled to room temperature.

3.2.2. Mole Fraction of Ammonia at End of Run

Upon completion of the runs described in the previous section, the equilibrium mole fraction of ammonia ($\alpha_{NH3}^{Mol\,Frac}$) in the autoclave was calculated, providing experimental data for the mole fraction of ammonia present in equilibrium at the final peak internal fluid temperature (T_{Peak}). Assuming that only insignificant amounts of ammonia decompose or form during cooling of the autoclave (~ 3 hrs from 600 °C to 300 °C) and that the only species in the autoclave are hydrogen, nitrogen and ammonia, it is possible to estimate the amount of hydrogen (n_{H2}^{Equil}) and nitrogen (n_{N2}^{Equil}) in the autoclave based on the corrected total system pressure measured at a temperature after the ammonia has started to liquefy (T_{cold}).

This was done by calculating the applicable free volume for the gases (V_{free}^{Gas}) after subtracting the volume occupied by the liquid ammonia solution ($V_{NH3}^{Liquid} + \Delta V_{N2+H2}^{sat}$) from the measured free volume of the autoclave (V_{free}^{Total} , see equation (41)) at the beginning of the run prior to filling. The volumetric expansion of the liquid ammonia due to dissolved hydrogen and nitrogen species (ΔV_{N2+H2}^{sat})⁴⁰ was taken into account. Furthermore, the amount of dissolved hydrogen ($n_{H2}^{Dissolved}$) and nitrogen ($n_{N2}^{Dissolved}$) in the liquid ammonia (n_{NH3}^{Liquid}), which was assumed to be saturated in both gases,⁴¹ was determined.

To improve accuracy in pressure, the drift in zero point ($P_{zero\,drift}$) was subtracted from the measured pressure (P_{cold}) yielding the corrected total system pressure ($P_{corrected}$). By

comparing the sealed autoclave weights before (m_{full}^{Before}) and after (m_{full}^{After}) the run, it was possible to estimate the weight loss (Δm_{Total}) associated with hydrogen diffusion out of the autoclave during the run (Δn_{H2}), resulting in a non-stoichiometric mixture. To improve this estimate, the weights of the empty autoclave before (m_{empty}^{Before}) and after (m_{empty}^{After}) were measured to determine the weight change associated with just the system (Δm_{System}).

The applicable vapor pressure of ammonia (n_{NH3}^{Vapor}) was determined using experimental data for hydrogen, nitrogen, and ammonia gas mixtures over liquid ammonia and approximating the mixture to be stoichiometric⁴². Finally, the moles of ammonia in the liquid phase were determined using the MEOS for ammonia (ρ_{NH3}^{Liquid}).

The procedure that was followed to determine the equilibrium mole fraction of ammonia was to first determine the corrected pressure, ammonia fill and amount of hydrogen mass loss using the following relationships.

$$P_{corrected} = P_{cold} - P_{zero\ drift}$$

$$n_{NH3}^{Fill} = \frac{m_{full}^{Before} - m_{empty}^{Before}}{MW_{NH3}}$$

$$\begin{aligned}\Delta m_{Total} &= m_{full}^{After} - m_{full}^{Before} \\ \Delta m_{System} &= m_{empty}^{After} - m_{empty}^{Before} \\ \Delta n_{H2} &= \frac{\Delta m_{Total} - \Delta m_{System}}{MW_{H2}}\end{aligned}$$

Conservation of mass for hydrogen and nitrogen atoms was then invoked, allowing for the determination of the equilibrium amounts of hydrogen, nitrogen, and ammonia by solving the following system of equations.

$$\left. \begin{aligned} P_{corrected} \cdot V_{free}^{Gas} &= (n_{N_2}^{Gas} + n_{H_2}^{Gas} + n_{NH_3}^{Vapor})RT \\ V_{free}^{Gas} &= V_{free}^{Total} - (V_{NH_3}^{Liquid} + \Delta V_{N_2+H_2}^{sat}) \\ n_{NH_3}^{Equil} &= n_{NH_3}^{Vapor} + \rho_{NH_3}^{Liquid} \cdot V_{NH_3}^{Liquid} \\ n_{N_2}^{Equil} &= n_{N_2}^{Gas} + n_{N_2}^{Dissolved} \\ n_{H_2}^{Equil} &= n_{H_2}^{Gas} + n_{H_2}^{Dissolved} \\ 3 n_{NH_3}^{Fill} &= 3 n_{NH_3}^{Equil} + 2 n_{H_2}^{Equil} - 2 \Delta n_{H_2} \\ n_{NH_3}^{Fill} &= n_{NH_3}^{Equil} + 2 n_{N_2}^{Equil} \end{aligned} \right\} \quad (43)$$

Finally, with knowledge of the equilibrium quantities of ammonia, hydrogen and nitrogen, the equilibrium mole fraction of ammonia was calculated using the following relationship.

$$\alpha_{NH_3}^{Mol\,Frac} = \frac{n_{NH_3}^{Equil}}{n_{NH_3}^{Equil} + n_{N_2}^{Equil} + n_{H_2}^{Equil}} \quad (44)$$

The results from this calculation can be found in Table 5.

4. Results and Discussion

4.1. Equation of States

4.1.1. Experimental Determination of P-v-T Relationship for Ammonia

Experimental results pertaining to the determination if the MEOS for ammonia is accurate beyond 700 K are depicted in Fig. 2. Only data pertaining to the ramping of the run and not the holding portion at constant temperature are shown. All experimental runs were leak tight and no mass loss due to outward diffusion of hydrogen was determined within experimental errors based on weight measurements ($0.01 \text{ mol}_{\text{H}_2}$).

Fig. 2. Pressure vs. temperature behavior for pure ammonia at different fill densities of ammonia compared with extrapolated multiparameter equation of state (MEOS) for ammonia as provided by the National Institute of Standards and Technology (NIST) with close up of the data in the vicinity of the critical point. Temperature values corresponds to internal fluid temperatures

Despite the external wall temperature of the autoclave reaching and holding a value of 600 °C at the end of the run, the internal temperature only reached a value approximately 60—70 °C below that. This can be attributed to heat loss from the upper portion of the autoclave that was exposed and unheated, thereby acts as a heat sink. Due to this cooling effect, the internal fluid temperature fluctuated slightly due to convective fluid motion caused by preferential heating of the lower portion of the autoclave (lower density fluid) and passive cooling of the upper portion of the autoclave (higher density fluid). The measured temperature fluctuations were

approximately 10°C and are shown without any smoothening in the pressure versus temperature plot from the experimental runs (Fig. 2).

For comparison, the theoretically predicted values for the given initial fill density of ammonia are calculated using the MEOS for ammonia and overlaid. The deviation of the experimentally determined values from the predicted values can be explained by the expansion of the internal free volume due to thermal expansion of the autoclave (equation (38)) and elastic response of the metal wall due to buildup of internal pressure and resulting stresses in the autoclave walls (equation (39)). Both of these effects work in unison and result in a lowering of the density of ammonia at any given temperature and pressure.

Taking the expansion of free volume into account, it is possible to calculate the deviation in total system pressure for the experimental data from the MEOS, resulting in Fig. 3. The P-T data for this plot was smoothened by taking a running average of the data, which was collected at 2 second intervals, over the course of 1 min.

Fig. 3. Deviation in pressure from the corresponding calculated pressure using the reference multiparameter equation of state (MEOS) for ammonia as depicted in Fig. 2 at different fill densities of ammonia and adjusting for expansion in free volume due to temperature and internal pressure induced strain effects

As can be seen, the experimental data fits the extrapolated MEOS very well for runs 16.2, 20.2, 24.1, and 25.3 mol/l up to the measured 800 K within the temperature fluctuations of the system. The four runs that exhibit appreciable positive deviations (14.5, 18.6, 22.6, and 24.3 mol/l) were all performed in the same autoclave with the same thermocouple. It is currently thought that the immersed thermocouple for this particular system preferentially acted as a catalyst for ammonia decomposition causing increased production of hydrogen and nitrogen, leading to an overall increase in pressure. This hypothesis was substantiated by the observation of an elevated total system pressure of the autoclave after cool down when compared to the expected vapor pressure of ammonia.

Despite early onset of decomposition of ammonia for four of the runs, the other four runs exhibited good agreement without any concernable deviation in trends over the measured density spectrum, from which it was deduced that the MEOS can be extrapolated with no significant loss to accuracy to at least 800 K, if not higher.

Furthermore, given the close agreement with the MEOS at temperatures below 700 K, close to the critical point and over a wide range of densities, the internal thermocouple containing autoclave system was deemed to be accurate to within 1 % error or less, suggesting its use for

future experiments pertaining to experimental investigations of the ammonothermal growth environment.

4.1.2. Determination of new equation of state constants

With experimental verification of the MEOS for ammonia for temperatures greater than 700 K, the MEOS was used as the reference for ammonia for temperatures in excess of 700 K. Multiple isochores were calculated at various densities up to 1000 K for the three different gases using their respective MEOS, taking their calculated values to be reference values, and fitting them according to Section 3.1.2 to the modified BB EOS. The resulting values for the fit parameters c (calculated from Γ) for each isochore is depicted in Fig. 4 (c). Using the selected constant value for c (shown as a straight line in the plot), values for B (calculated from ψ), and A (calculated from ϕ) were calculated for each isochore and are summarized in Fig. 4 (a) and (b). The constants resulting with the second order polynomial fit to A and B are provided in Table 4 along with the constant value c , providing the complete set of constants required to describe each gas using the modified BB EOS.

Fig. 4. Parameter values (a) A , (b) B , and (c) c as a function of density with superimposed second order polynomial fit for A and B calculated for the selected constant value of c (equation (6),(5),

and (6)). Individual parameter values were calculated by fitting (equation (42)) the modified Beattie-Bridgeman equation of state (BB EOS) as defined in equation (3) to isochoric data calculated using the reference multiparameter equation of state (MEOS) data provided by the Institute of Standards and Technology (NIST) for three gases: • Ammonia, ■ Hydrogen, and ♦ Nitrogen

Table 4

Determined constants for the modified Beattie-Bridgeman equation of state (BB EOS) as defined by equations (3), (6), (5), and (6) and depicted in Fig. 4 for ammonia, hydrogen, and nitrogen.

Gas	A_0 (Pa m ⁶ /mol ²)	a (x10⁵) (m ³ /mol)	a_1 (x10¹⁰) (m ⁶ /mol ²)	B_0 (x10⁵) (m ³ /mol)	b (x10⁵) (m ³ /mol)	b_1 (x10¹⁰) (m ⁶ /mol ²)	c (K ³ m ³ /mol)
NH₃	0.429	2.07	-1.44	5.51	1.58	-8.00	575
H₂	-0.0143	-5.19	-13.8	1.48	-0.724	-0.0667	220
N₂	0.0544	-6.89	78.7	3.70	-3.14	-0.311	487

The BB EOS is considered to describe non-polar gases very well, though is not deemed as accurate for polar gases. A consequence of this formulation becomes apparent when looking at Fig. 4 (c) which shows a strong dependence of the value c on the density of the polar gas ammonia, whereas only a minimal dependence for the two non-polar gases nitrogen and hydrogen is observed. The use of exponential terms to describe the clustering of molecules and effects on the intermolecular potential would be preferred given the strong dipole-dipole

interaction, though would complicate the mathematical convenience of the BB EOS for future use in thermodynamic derivations. For the purpose of this study, the inaccuracies introduced by this deficiency were deemed acceptable as they did not impact the region of interest ($T > 600$ K, $P > 100$ MPa) significantly.

In order to determine the usefulness and accuracy of the determined modified BB EOS, the pressure calculated using the newly determined constants for the modified BB EOS was compared to the MEOS value for each respective gas as a function of temperature and density. For added convenience, isobar contour lines were calculated using the BB EOS and overlaid. The results from this comparison are provided in the form of relative deviations as a color map in Fig. 5 for ammonia, Fig. 6 for nitrogen, and Fig. 7 for hydrogen.

Fig. 5. Color map depicting relative deviation in pressure, as a function of density and temperature, for ammonia calculated using the modified Beattie-Bridgeman equation of state (BB EOS) and parameters provided in Table 4 to the reference multiparameter equation of state (MEOS) as provided by the National Institute of Standards and Technology (NIST). Isobars are

superimposed and were calculated using the BB EOS. Relative errors close to the critical temperature in the color saturated regions range from -2— -16 % for densities increasing from 12—30 mol/l, and 2 – 6 % for densities ranging between 1—10 mol/l

Fig. 6. Color map depicting relative deviation in pressure, as a function of density and temperature, for nitrogen calculated using the modified Beattie-Bridgeman equation of state (BB EOS) and parameters provided in Table 4 to the reference multiparameter equation of state (MEOS) as provided by the National Institute of Standards and Technology (NIST). Isobars are superimposed and were calculated using the BB EOS.

Fig. 7. Color map depicting relative deviation in pressure, as a function of density and temperature, for hydrogen calculated using the modified Beattie-Bridgeman equation of state (BB EOS) and parameters provided in Table 4 to the reference multiparameter equation of state (MEOS) as provided by the National Institute of Standards and Technology (NIST). Isobars are superimposed and were calculated using the BB EOS.

Based on this comparison, it can be seen that the BB EOS does not accurately describe ammonia near the critical point ($T = 405$ K, $P = 11.9$ MPa). The errors in the color saturated regions range from 2—6 % for densities ranging between 1—10 mol/l. Furthermore, significant deviations occurs when ammonia becomes a supercritical fluid from the liquid phase, exhibiting deviations ranging from -2 % for 12 mol/l density up to -16 % at 30 mol/l and 450 K.

Despite these inaccuracies, the deviations from the MEOS in the region of interest ($T > 600$ K, $P > 100$ MPa) are on the order of 1 % or less. Given that the MEOS has only been compared to experiment up to 800 K, it is unclear how accurately the BB EOS or MEOS describes ammonia

at temperatures in excess of 800 K. For the purpose of this paper, it is assumed to not differ significantly from the extrapolated values given observed experimental trends and the thermodynamic underpinning of the EOSs. Hence, the BB EOS adequately represents the pressure of ammonia as a function of temperature and density to within approximately 1 % error.

For nitrogen, it can be seen that the BB EOS does a good job representing the fluid at higher temperatures with relative errors less than approximately 0.5 % and can be used without hesitation.

Hydrogen is exceptionally well represented by the BB EOS with errors less than 0.25 % in the region of interest. It is interesting to note, that the value for A_0 is negative, in contrast to all other gases fitted to the standard BB EOS form. This possibility was already suggested by Beattie himself while fitting the available experimental data at the time for the lower density regime. While this complicates certain mathematical operations slightly, for example taking the square root for geometric mean calculations, a work around is proposed and described in equation (9), which separates the absolute value of the constant from its sign.

With the successful fitting of the mathematically simple, yet thermodynamically founded modified BB EOS to the highly accurate and sophisticated MEOSs to within accuracy errors of approximately 1 % or less, it should now be possible to perform accurate thermodynamic derivations with relative ease.

4.2. Decomposition of Ammonia

4.2.1. Equilibrium Constant

Determination of the equilibrium constant for ammonia at elevated temperatures and pressures was performed by Gillespie and Beattie in 1930 using the standard BB EOS.³⁸ While their derivation found excellent agreement with experimental data for pressures below 100 MPa, the authors have found it to be inadequate for pressures in excess of 100 MPa, primarily due to the divergence of their approximated BB EOS in virial form when explicitly solved for molar volume. Furthermore, their derivation only includes non-ideal mixing for the A_0 term, neglecting any contributions from B_0 and c . Also, no consideration was made for separate mixing of polar and non-polar contributions for A_0 and c .

To accurately represent the fugacities of the three different gases, the complete modified BB EOS was thus integrated without any approximations (equation (34)) yielding accurate values for pressures well in excess of 100 MPa. More sophisticated mixing rules (see equation (8)) were implemented providing better approximations for an accurate EOS describing $\text{NH}_3\text{-N}_2\text{-H}_2$ gas mixtures.

Using the improved and accurate EOS derived in the previous section for ammonia, hydrogen, and nitrogen, along with a better approximation for mixing rules and resulting EOS for a $\text{NH}_3\text{-N}_2\text{-H}_2$ gas mixtures, the equilibrium constant, K_p , for the ammonia decomposition as a function of pressure and temperature was calculated using equation (35). The resulting values are shown in Fig. 8 for temperatures up to 1000 K and pressures up to 300 MPa.

Fig. 8. Equilibrium constant, K_p , for the ammonia decomposition reaction defined by equation (10) as a function of inverse temperature calculated for various total system pressures ranging from 1 to 300 MPa.

As was already found by Gillespie and Beattie, the ammonia decomposition is greatly suppressed by elevating total system pressure. The more accurate derivation of the equilibrium constant, as compared to Gillespie and Beattie, suggests an even greater suppression at elevated pressures and temperatures as would be anticipated based on an extrapolation of their equation. It is also important to highlight the stark deviation from ideality that exists for this reaction for pressures in excess of a few MPas.

4.2.2. Equilibrium Mole Fraction of Ammonia

With knowledge of the equilibrium constant, it is possible to determine the equilibrium mole fraction of ammonia present in the system as a function of temperatures and pressure. To determine the accuracy of the derived equation used in conjunction with the MEOS derived BB

EOS, a comparison to experimental data is performed. Experimental data from literature was found for pressures below 100 MPa and temperatures below 500 °C.^{43,44}

As these data points could already be represented by the equilibrium constants determined by Gillespie and Beattie, new data points were experimentally determined for pressures in excess of 100 MP and temperatures up to 814 K. Their experimental determination and derivation is detailed in Section 3.2 with resulting values summarized in Table 5. Fig. 9 summarizes experimentally determined mole fractions of ammonia present in equilibrium along with the theoretically predicted values calculated using the modified BB EOS and improved mixing rules (Equation (35)). For this work's experimental data, it was found that the mixture was non-stoichiometric, due to hydrogen mass loss. In addition to the stoichiometric mixture equilibrium value (assuming no hydrogen mass loss) shown as a solid line, the non-stoichiometric behavior was included as a dashed lined.

Table 5

Experimental data and resulting calculated values for hydrogen mass loss (Δn_{H_2}), equilibrium concentrations of ammonia ($n_{NH_3}^{Equil}$), nitrogen ($n_{N_2}^{Equil}$), and hydrogen ($n_{H_2}^{Equil}$), and equilibrium mole fraction of ammonia ($\alpha_{NH_3}^{MolFrac}$) present at equilibrium at the specified peak run temperature (T_{Peak}) for three different runs with varying fill densities of ammonia.

		Run			Absolute	Unit	
		10.4 mol/l	16.9 mol/l	22.0 mol/l	Error		
3	me	T_{Peak}	796	811	814	± 10	K

	V_{free}^{Total}	158.2	162.4	158.2	± 0.1	ml
	n_{NH3}^{Fill}	1.650	2.737	3.475	± 0.003	mol
	$P_{corrected}$	17.5	17.5	12.6	± 0.2	MPa
	T_{cold}	308	304	303	± 2	K
	Δm_{Total}	-0.34	-0.43	-1.49	± 0.02	g
	Δm_{System}	0.30	0.35	-0.69	± 0.02	g
Calculated	Δn_{H2}	-0.32	-0.39	-0.40	± 0.02	mol
	n_{NH3}^{Equil}	1.06	2.17	3.06	± 0.03	mol
	n_{N2}^{Equil}	0.30	0.28	0.21	± 0.02	mol
	n_{H2}^{Equil}	0.57	0.45	0.22	± 0.01	mol
	$\alpha_{NH3}^{Mol\,Frac}$	0.55	0.75	0.88	± 0.02	mol/mol

Source	Larson <i>et al.</i>		Larson	This Work	
Pressure (MPa)	1	5	30	92	210
	3	10	61	101	151
Mixture	— Stoichiometric		- - Non-Stoichiometric		

Fig. 9. Comparison of experimentally determined equilibrium mole fraction of ammonia from • A.T. Larson and R.L. Dodge Ref. [43], ♦ A.T. Larson, Ref. [44], and ■ this work with calculated equilibrium mole fraction of ammonia in stoichiometric mixtures (solid lines). Dashed lines correspond to calculated mole fractions of ammonia in equilibrium for non-stoichiometric mixtures taking into account the experimentally determined mass loss of hydrogen from the system for this work (see Table 5). Experimental errors in pressure for data resulting from this work are ± 10 , ± 8 , ± 6 MPa for 92, 151, 210 MPa, respectively. For all other data points, the error is claimed to be less than 0.1 MPa.

Overall, the experimental data agrees well with the theoretically predicted values, except for the highest pressure values determined by Larson, and the lowest pressure value determined in this work. The deviation for the lowest pressure data point from this study can be explained by the large error in the pressure transducer read out. It was found that the error in pressure transducer readout increases with increasing hydrogen pressure, as hydrogen diffuses into the strain gauge effecting the readout value. Therefore, considering an error bar of 10 MPa on the pressure transducer readout, the experimental value may still be in agreement with the model assuming the upper end of the error, 102 MPa, corresponds to the actual pressure value.

An explanation for the deviation in Larson's data is harder to provide given the tighter tolerances in error on both pressure and temperature. Larson and Dodge's method for determination of the equilibrium constant included flowing a hydrogen, nitrogen and ammonia gas mixture over a catalyst which was placed in a temperature stabilized bath of molten salts. The ammonia concentration was varied at the inlet until no variation was observed as a function of flow rate at

the output, at which point equilibrium was considered to be reached. They approached the equilibrium value from both the ammonia rich and ammonia poor side, converging to the same value for the lower pressure runs. Given the excellent agreement for the lower pressure run, when Larson performed the high pressure runs, he only approached the value from the ammonia poor side. It is therefore possible, that for the highest pressures, there was insufficient catalyst present and true equilibrium was not reached, though this went unnoticed as it was not attempted to obtain the same value from the ammonia rich side. It is further possible, that the experimental data points are valid, and the derived equation in this paper requires a more accurate description for the mixing rules, most notably the inclusion of the third virial coefficient.

4.3. System Modeling

Having verified the BB EOS against reference MEOSs and the equilibrium constant equation against experimental data, it is of interest to determine the ability to couple both set of equations and accurately model the experimentally measurable total system pressure and mole fraction of ammonia present in equilibrium for a sealed autoclave, providing only the cold free volume, initial fill of ammonia, and temperature. Experimental data was collected for this purpose according to the details provided in Section 3.2 and the results are shown in Fig. 10 for the total system pressure and the corresponding mole fraction of ammonia Fig. 11.

Fig. 10. Comparison of measured total system pressure at specified fluid temperatures for four different fill densities of ammonia after allowing the system to reach equilibrium to theoretically predicted values using the modified Beattie-Bridgeman equation of state (BB EOS) with specified mixing rules assuming: (1) no decomposition of ammonia ($P_{Pure\ NH_3}$), (2) decomposition of ammonia and no hydrogen mass loss from the system ($P_{stoichiometric\ Equil.\ NH_3-N_2-H_2}^{stoichiometric}$), and (3) decomposition of ammonia with experimentally determined hydrogen mass loss at the end of the run, where available ($P_{Equil.\ NH_3-N_2-H_2}^{with\ H_2\ Loss}$).

Fig. 11. Calculated equilibrium mole fraction of ammonia as a function of temperature and initial fill density corresponding to the four runs depicted in Fig. 10. Three experimentally determined mole fractions of ammonia corresponding to the highest temperature state for the three lower density runs in Fig. 10 are overlaid.

Three different scenarios were calculated and are shown in Fig. 10. The first scenario ($P_{Pure\ NH_3}$) assumes no ammonia decomposition and is represented by the solid lines. The second scenario ($P_{Equil.\ NH_3-N_2-H_2}^{stoichiometric}$), depicted by dashed lines, couples the total system pressure to the equilibrium constant equation, while assuming a strictly stoichiometric mixture. As hydrogen mass loss was confirmed at the end of the runs for 10.4, 16.9, and 22.0 mol/l, a third scenario was included and is only applicable to the highest temperature value for those three runs. The third scenario ($P_{Equil.\ NH_3-N_2-H_2}^{with\ H_2\ Loss}$) permits ammonia decomposition while assuming an initially non-stoichiometric mixture consisting of ammonia and pure nitrogen and is depicted by a dash-dot line. The experimentally determined amount of hydrogen loss is provided in Table 5 and the

initial amount of ammonia and nitrogen was calculated by requiring the same number of nitrogen atoms being present in the system while maximizing the concentration of ammonia. No data could be collected for the highest density run, as the autoclave leaked immediately before completion of the run.

Within experimental error, the pressure values are in good agreement with the predicted values for stoichiometric mixtures. Taking hydrogen mass loss into account, slight improvements to the predicted value for the highest temperature value were found, especially for the lowest density run.

It is interesting to note that for temperatures below 650 K, little to no deviation from the pure ammonia curve is measured. This is in agreement with experimental evidence that even in the presence of an optimized catalyst, ammonia requires temperatures in excess of approximately 600 K prior to decomposition, suggesting, little to no decomposition occurred at the lower temperatures due to kinetic limitations.

The predicted trend for the equilibrium mole fraction of ammonia as a function of temperature for the four different runs is summarized in Fig. 11. The experimentally determined mole fraction values (identical to those provided in Fig. 9) are overlaid. It is found that when using the theoretically predicted total system pressure, as opposed to the experimentally determined total system pressure, for determination of the equilibrium constant, a much better agreement to experiment is found.

Given that the theoretical predictions are based exclusively on the BB EOS, which was fit to reference MEOS data, and that the experimental mole fraction data accurately aligns with the model, it is deemed possible that the pressure measurement was indeed inaccurate and a

correction needs to be taken into account for future measurements if higher accuracy measurements is desired.

Furthermore, given the good agreement between the modeled system and equilibrium mole fraction, along with the agreement within experimental error for the total system pressure trace, it is suggested that the accuracy error for the equilibrium constant shouldn't be significantly greater than the experimental error of 2 % for temperatures below 850 K.

5. Summary

The extrapolation of the reference MEOS provided by NIST to temperatures beyond 700 K was found to be accurate to within error of the experiment, up to 800K. Without any evidence for a significant deviation in trend for higher temperatures for the investigated densities, it was deemed acceptable to further extrapolate the MEOS to temperature up to 1000 K with minimal loss in accuracy.

To simplify thermodynamic investigations of this system at elevated temperatures and pressure, a simpler EOS (modified BB EOS) was successfully fit to data calculated from the MEOS for each of the three gases of interest: ammonia, hydrogen, and nitrogen. The deviation in pressure for the BB EOS from the MEOS in the region of interest ($T > 600$ K, $P > 100$ MPa) was on the order of 1 %, from which it was deduced that the BB EOS can accurately represent the fluid at hand to within approximately 1 % error, though possibly larger accuracy errors may exist for ammonia given unknown errors for the extrapolated MEOS beyond 800 K.

Using the uniform form of EOS for all three gases, an EOS was derived for $\text{NH}_3\text{-N}_2\text{-H}_2$ mixtures, based on mixing rules for the included constants investigating the second virial coefficient for

mixtures. Further improvements to accuracy could be made by more accurately representing mixing of the third virial coefficient, though the current model seems to adequately represent the experimental data to within error of the current experimental data.

Applying the BB EOS for the gases and their mixture to the derived thermodynamic relationship for the functional dependence of the equilibrium constant on pressure, temperature and composition, an expression was found that agreed with experimentally determined values at both high (> 150 MPa) and low pressures (< 90 MPa). Some disagreements occurred for data collected around 100 MPa, though may be explained by increased experimental error.

By combining the BB EOS and the validated equilibrium constant equation, while including corrections for expansion of internal free volumes of autoclaves due to temperature and internal pressure, the total system pressure and mole fraction of ammonia present in equilibrium was calculated as a function of temperature. Comparison with experimental data suggests the derived equations provide an accurate representation of the physical system to within experimental error, suggesting approximate errors in equilibrium constant on the order of 2 % for temperatures below 850 K.

Acknowledgements

The authors wish to thank James S. Speck for critical reading of the manuscript and Paul Von Dollen for fruitful discussions. The first author wishes to acknowledge the generous support by the National Science Foundation Graduate Research Fellowship (NSF-GRFP) under Grant No. DGE-0707460 and by the U.S. Department of Homeland Security (DHS) Graduate Student Fellowship Program under DOE contract number DE-AC05-06OR2310. The authors

acknowledge the support from the Solid State Lighting and Energy Center at University of California, Santa Barbara. All opinions expressed in this paper are the author's and do not necessarily reflect the policies and views of NSF, DHS, DOE, or ORAU/ORISE.

References

¹ S. Saito, R. Hashimoto, J. Hwang, S. Nunoue, InGaN Light-Emitting Diodes on c-Face Sapphire Substrates in Green Gap Spectral Range, *Applied Physics Express*. 6 (2013) 111004. doi:10.7567/APEX.6.111004.

² C.-C. Pan, S. Tanaka, F. Wu, Y. Zhao, J.S. Speck, S. Nakamura, et al., High-Power, Low-Efficiency-Droop Semipolar (20-21) Single-Quantum-Well Blue Light-Emitting Diodes, *Applied Physics Express*. 5 (2012) 062103. doi:10.1143/APEX.5.062103.

³ S. Takagi, Y. Enya, T. Kyono, M. Adachi, Y. Yoshizumi, T. Sumitomo, et al., High-Power (over 100 mW) Green Laser Diodes on Semipolar (20-21) GaN Substrates Operating at Wavelengths beyond 530 nm, *Applied Physics Express*. 5 (2012) 082102. doi:10.1143/APEX.5.082102.

⁴ Y. Zhao, S.H. Oh, F. Wu, Y. Kawaguchi, S. Tanaka, K. Fujito, et al., Green Semipolar (20-21) InGaN Light-Emitting Diodes with Small Wavelength Shift and Narrow Spectral Linewidth, *Applied Physics Express*. 6 (2013) 062102. doi:10.7567/APEX.6.062102.

⁵ K. Fujito, S. Kubo, H. Nagaoka, T. Mochizuki, H. Namita, S. Nagao, Bulk GaN crystals grown by HVPE, *Journal of Crystal Growth*. 311 (2009) 3011–3014. doi:10.1016/j.jcrysgro.2009.01.046.

⁶ Y. Mori, M. Imade, M. Maruyama, M. Yoshimura, Growth of GaN Crystals by Na Flux Method, *ECS Journal of Solid State Science and Technology*. 2 (2013) N3068–N3071. doi:10.1149/2.015308jss.

-
- ⁷ Q. Bao, M. Saito, K. Hazu, K. Furusawa, Y. Kagamitani, R. Kayano, et al., Ammonothermal Crystal Growth of GaN Using an NH₄F Mineralizer, *Crystal Growth & Design*. 13 (2013) 4158–4161. doi:10.1021/cg4007907.
- ⁸ E.R. Letts, T. Hashimoto, S. Hoff, D. Key, K. Male, M. Michaels, Development of GaN wafers via the ammonothermal method, *Journal of Crystal Growth*. 403 (2014) 3–6. doi:10.1016/j.jcrysgro.2014.06.004.
- ⁹ K. Yoshida, K. Aoki, T. Fukuda, High-temperature acidic ammonothermal method for GaN crystal growth, *Journal of Crystal Growth*. 393 (2014) 93–97. doi:10.1016/j.jcrysgro.2013.09.010.
- ¹⁰ W. Jiang, D. Ehrentraut, B.C. Downey, D.S. Kamber, R.T. Pakalapati, H.D. Yoo, et al., Highly transparent ammonothermal bulk GaN substrates, *Journal of Crystal Growth*. 403 (2014) 18–21. doi:10.1016/j.jcrysgro.2014.06.002.
- ¹¹ R. Kucharski, M. Zając, R.M. Doradziński, M. Rudziński, R. Kudrawiec, R.T. Dwiliński, Non-polar and semi-polar ammonothermal GaN substrates, *Semiconductor Science Technology*. 27 (2012) 024007. doi:10.1088/0268-1242/27/2/024007.
- ¹² S. Zhang, N.S.A. Alt, E. Schlücker, R. Niewa, Novel alkali metal amidogallates as intermediates in ammonothermal GaN crystal growth, *Journal of Crystal Growth*. 403 (2014) 22–28. doi:10.1016/j.jcrysgro.2014.06.015.
- ¹³ S. Zhang, F. Hintze, W. Schnick, R. Niewa, Intermediates in Ammonothermal GaN Crystal Growth under Ammonoacidic Conditions, *European Journal of Inorganic Chemistry*. 2013 (2013) 5387–5399. doi:10.1002/ejic.201300958.
- ¹⁴ M.P. D'Evelyn, H.C. Hong, D.-S. Park, H. LU, E. KAMINSKY, R.R. Melkote, et al., Bulk GaN crystal growth by the high-pressure ammonothermal method, *Journal of Crystal Growth*. 300 (2007) 11–16. doi:10.1016/j.jcrysgro.2006.10.232.

-
- ¹⁵ M.J. Callahan, B. Wang, K. RAKES, D.F. Bliss, L.O. Bouthiette, M. Suscavage, et al., GaN single crystals grown on HVPE seeds in alkaline supercritical ammonia, *Journal of Materials Science*. 41 (2006) 1399–1407. doi:10.1007/s10853-006-7428-4.
- ¹⁶ B. Wang, M.J. Callahan, Ammonothermal Synthesis of III-Nitride Crystals, *Crystal Growth & Design*. 6 (2006) 1227–1246. doi:10.1021/cg050271r.
- ¹⁷ T.G. Steigerwald, N.S.A. Alt, B. Hertweck, E. Schluecker, Feasibility of density and viscosity measurements under ammonothermal conditions, *Journal of Crystal Growth*. 403 (2014) 59–65. doi:10.1016/j.jcrysgro.2014.06.013.
- ¹⁸ N. Alt, E. Meissner, E. Schlücker, L. Frey, In situ monitoring technologies for ammonothermal reactors, *physica status solidi (c)*. 9 (2012) 436–439. doi:10.1002/pssc.201100361.
- ¹⁹ Q.-S. Chen, J.-Y. Yan, Y.-N. Jiang, W. Li, Modeling on ammonothermal growth of GaN semiconductor crystals, *Progress in Crystal Growth and Characterization of Materials*. 58 (2012) 61–73. doi:10.1016/j.pcrysgrow.2012.02.005.
- ²⁰ Y. Masuda, A. Suzuki, T. Ishiguro, C. Yokoyama, Numerical Simulation of Heat and Fluid Flow in Ammonothermal GaN Bulk Crystal Growth Process, *Japanese Journal of Applied Physics*. 52 (2013) 08JA05. doi:10.7567/JJAP.52.08JA05.
- ²¹ I.M. Kakhki, M. Charmchi, H. Sun, Computational Investigation of Gallium Nitride Ammonothermal Crystal Growth, ASME 2013 Heat Transfer Summer Conference Collocated with the ASME 2013 7th International Conference on Energy Sustainability and the ASME 2013 11th International Conference on Fuel Cell Science, Engineering and Technology. (2013) V003T09A001–V003T09A001. doi:10.1115/HT2013-17506.
- ²² H.W. Xiang, Vapor Pressures, Critical Parameters, Boiling Points, and Triple Points of Ammonia and Trideuteroammonia, *Journal of Physical and Chemical Reference Data*. 33 (2004) 1005–1011. doi:10.1063/1.1691451.

-
- ²³ R. Span, E.W. Lemmon, R.T. Jacobsen, W. Wagner, A. Yokozeki, A Reference Equation of State for the Thermodynamic Properties of Nitrogen for Temperatures from 63.151 to 1000 K and Pressures to 2200 MPa, *Journal of Physical and Chemical Reference Data*. 29 (2000) 1361–1433. doi:10.1063/1.1349047.
- ²⁴ J.W. Leachman, R.T. Jacobsen, S.G. Penoncello, E.W. Lemmon, Fundamental Equations of State for Parahydrogen, Normal Hydrogen, and Orthohydrogen, *Journal of Physical and Chemical Reference Data*. 38 (2009) 721–748. doi:10.1063/1.3160306.
- ²⁵ R. Tillner-Roth, F. Harms-Watzenberg, H. Baehr, Eine neue Fundamentalgleichung fuer Ammoniak, *DKV Tagungsbericht*. 20 (1993) 167–181.
- ²⁶ L. Haar, J.S. Gallagher, Thermodynamic properties of ammonia, *Journal of Physical and Chemical Reference Data*. 7 (1978) 635–792. doi:10.1063/1.555579.
- ²⁷ L. Glasser, Equations of State and Phase Diagrams of Ammonia, *Journal of Chemical Education*. 86 (2009) 1457–1458. doi:10.1021/ed086p1457.
- ²⁸ F.L. Vereschagin, F.F. Voronov, Change temperature melting solid ammonia at high pressures, *Russian Journal of Physical Chemistry. A*. 30 (1956) 329–333.
- ²⁹ S. Ninet, F. Datchi, High pressure–high temperature phase diagram of ammonia, *Journal of Chemical Physics*. 128 (2008) 154508. doi:10.1063/1.2903491.
- ³⁰ J.A. Beattie, O.C. Bridgeman, A New Equation of State for Fluids, *Proceedings of the American Academy of Arts and Sciences*. 63 (1928) 229–308. doi:10.2307/20026205.
- ³¹ J.A. Beattie, C.K. Lawrence, Some of the Thermodynamic Properties of Ammonia. I. the Compressibility of and an Equation of State for Gaseous Ammonia. the Vapor Pressure of Liquid Ammonia, *Journal of the American Chemical Society*. 52 (1930) 6–14. doi:10.1021/ja01364a002.
- ³² W.H. Stockmayer, Second Virial Coefficients of Polar Gases, *The Journal of Chemical Physics*. 9 (1941) 398–402. doi:10.1063/1.1750922.

³³ W.H. Stockmayer, Second Virial Coefficients of Polar Gas Mixtures, *The Journal of Chemical Physics*. 9 (1941) 863. doi:10.1063/1.1750858.

³⁴ L.J. Gillespie, Equilibrium Pressures of Individual Gases in Mixtures and the Mass-Action Law for Gases, *Journal of the American Chemical Society*. 47 (1925) 305–312. doi:10.1021/ja01679a003.

³⁵ J.A. Beattie, The Computation of the Thermodynamic Properties of Real Gases and Mixtures of Real Gases, *Chemical Reviews*. 44 (1949) 141–192. doi:10.1021/cr60137a010.

³⁶ L. Gillespie, J.A. Beattie, The Thermodynamic Treatment of Chemical Equilibria in Systems Composed of Real Gases. II. A Relation for the Heat of Reaction Applied to the Ammonia Synthesis Reaction. The Energy and Entropy Constants for Ammonia, *Physical Review*. 36 (1930) 1008–1013. doi:10.1103/PhysRev.36.1008.

³⁷ J.A. Beattie, The Entropy and Thermodynamic Potentials of Real Gases and Mixtures of Real Gases and a Mass Action Law for Chemical Reaction Between Real Gases: III. Relations for Pure Gases, and the Equilibrium Pressure of a Gas in a Mixture, *Physical Review*. 32 (1928) 699–705. doi:10.1103/PhysRev.32.699.

³⁸ L. Gillespie, J.A. Beattie, The Thermodynamic Treatment of Chemical Equilibria in Systems Composed of Real Gases. I. An Approximate Equation for the Mass Action Function Applied to the Existing Data on the Haber Equilibrium, *Physical Review*. 36 (1930) 743–753. doi:10.1103/PhysRev.36.743.

³⁹ S. Pimputkar, S. Kawabata, J.S. Speck, S. Nakamura, Improved growth rates and purity of basic ammonothermal GaN, *Journal of Crystal Growth*. 403 (2014) 7–17. doi:10.1016/j.jcrysgro.2014.06.017.

⁴⁰ R. Wiebe, T.H. Tremearne, The Partial Molal Volumes of Ammonia and Hydrogen in Liquid Ammonia—Hydrogen Mixtures under Pressure at 100°, *Journal of the American Chemical Society*. 57 (1935) 2601–2603. doi:10.1021/ja01315a083.

⁴¹ R. Wiebe, V.L. Gaddy, The solubility in liquid ammonia of hydrogen at 0 and of Nitrogen at

0, 50, 75, 90 and 100 at Pressures to 1000 atmospheres. Critical Phenomena of Ammonia-Nitrogen Mixtures, *Journal of the American Chemical Society*. 59 (1937) 1984–1987. doi:10.1021/ja01289a055.

⁴² A.T. Larson, C.A. Black, The Concentration of Ammonia in a Compressed Mixture of Hydrogen and Nitrogen Over Liquid Ammonia, *Journal of the American Chemical Society*. 47 (1925) 1015–1020. doi:10.1021/ja01681a014.

⁴³ A.T. Larson, R.L. Dodge, The Ammonia Equilibrium, *Journal of the American Chemical Society*. 45 (1923) 2918–2930. doi:10.1021/ja01665a017.

⁴⁴ A.T. Larson, The Ammonia Equilibrium at High Pressures, *Journal of the American Chemical Society*. 46 (1924) 367–372. doi:10.1021/ja01667a011.

$P > 100 \text{ MPa}, T > 700 \text{ K}$

Equil. Mol Frac NH_3
(Calc. & Exp. Data)

Total P for NH_3 - N_2 - H_2
Mixture in Equilibrium
(Calc. & Exp. Data)