High-pressure synchrotron Mössbauer and X-ray diffraction studies: exploring the structure-related valence fluctuation in EuNi_2P_2

Chunyu Li^{a,b}, Zhenhai Yu^{a,b,*}, Wenli Bi^{c,d}, Jiyong Zhao^c, Michael Y. Hu^c, Jinggeng Zhao^b, Wei Wu^c, Jianlin Luo^{e,f}, Hao Yan^{a,*}, Esen E. Alp^c, and Haozhe Liu^{a,b,*}

^aCenter for High Pressure Science and Technology Advanced Research, Shanghai 201203, China

^bNatural Science Research Center, Academy of Fundamental and Interdisciplinary Sciences, Harbin Institute of Technology, Harbin 150080, China

^cAdvanced Photon Source, Argonne National Laboratory, Argonne, IL 60439, USA

^dDepartment of Geology, University of Illinois at Urbana-Champaign, Urbana, IL 61801, USA

^eBeijing National Lab for Condensed Matter Physics, Institute of Physics, Chinese Academy of Sciences, Beijing 100190, China

^fCollaborative Innovation Center of Quantum Matter, Beijing 100190, China

* Corresponding author, Tel./fax: 86-21-80177069

E-mail address: yuzh@hpstar.ac.cn (Zhenhai Yu), yanhao@hpstar.ac.cn (Hao Yan),

haozhe.liu@hpstar.ac.cn (Haozhe Liu)

Keywords:

ThCr₂Si₂-type phosphides; Structural stability; Electronic phase transitions;
High-pressure.

Abstract

The high pressure effect on valence fluctuation of the ThCr₂Si₂-type intermetallic compound EuNi₂P₂ has been investigated using *in situ* synchrotron Mössbauer spectroscopy (SMS). The isomer shift of ¹⁵¹Eu in EuNi₂P₂ increases monotonically with increasing pressure up to 50 GPa, suggesting a valence transition of the Eu from mixed toward trivalent. The synchrotron angle-dispersive X-ray diffraction (AD-XRD) experiment shows that EuNi₂P₂ remains in the tetragonal structure up to 32.5 GPa at room temperature. We propose that the evolutions of bonding distance with pressure have an obvious effect on the valence fluctuation.

I. Introduction

The Eu-based intermetallic compounds RET_2X_2 (RE = rare earth, T = transition metal, X = *sp*-element) crystallizing in the ThCr_2Si_2 structure present many unusual properties such as the intermediate valences or the valence fluctuations [1]. The former corresponds to quantum mixing of two valence states due to overlapping of localized f-electrons and delocalized valence electrons. The latter can be considered as thermal fluctuations between two integer valence states. Among these compounds, EuNi_2P_2 is a homogeneously mixed-valency phosphide at ambient conditions. By Mössbauer and X-ray absorption spectroscopic studies, Nagarajan and co-workers have discovered an unusual valence-fluctuating phenomenon of EuNi_2P_2 that the average valency $\bar{v}$ of Eu in EuNi_2P_2 is nearly temperature-independent and the value maintains at about 2.5 even when $T \rightarrow 0$ [2,3]. Besides, the $\bar{v}$ of the Eu in EuNi_2P_2 just depends slightly on the magnetic field (2.64 at 0 T and 2.61 at 40 T) [4]. While the $\bar{v}$ of Eu in the homogeneously mixed valent compounds EuCu_2Si_2 and EuPd_2Si_2 has a strong temperature dependence, and the $\bar{v}$ of Eu can change from divalency to trivalency with the temperature increasing over a wide range (0 to 800 K for EuCu_2Si_2 and 100-200 K in EuPd_2Si_2) [5]. It should be noticed that the change of $\bar{v}$ of Eu in EuNi_2P_2 can be effectively enhanced with the combination of temperature and pressure (up to 9 GPa and down to 4.2 K) [5], which implies the important role of the pressure on the valence fluctuation. And it suggests that pushing the pressure further, a more abnormal and fascinating valence changing may be detected.

The valence fluctuation phenomenon was addressed from the viewpoint of strong

electron correlations [6]. Guritanu *et al.* investigated the optical conductivity of the valence fluctuating compound EuNi_2P_2 which shows a strong similarity with that of many Ce- or Yb intermediate valent systems, claiming that the hybridization between the 4f level and the conduction electrons plays an important role for the valence change [7]. In the case where the two configurations $4f^7(5d^06s^2)$ and $4f^6(5d^16s^2)$ are very close in energy, one 4f electron will fluctuate between its 4f localized orbital and the *ds* conduction band states at the Fermi level. Moreover, recent photoemission experiments suggest that there is also strong hybridization between the Eu 4f electrons and the Ni 3d electrons in EuNi_2P_2 [8]. Eu valence in EuNi_2P_2 is 2.5–2.6 due to the strong hybridization [5,9]. Very recently, Medvedev *et al.* investigated the electrical resistivity of mixed-valent EuNi_2P_2 at high pressure, and suggested that Eu is in the trivalent state at pressures above 24 GPa according to the resistivity data [10].

The ternary ThCr_2Si_2 -type intermetallics EuCo_2P_2 , EuFe_2P_2 and EuNi_2P_2 are the RET_2X_2 prototype with space group $I4/mmm$ (Pearson symbol TI10). The structural study on EuCo_2P_2 carried out by C. Huhnt *et al.* revealed that a pressure-induced isostructural phase transition occurred at 3 GPa [11]. The low-pressure (LP) and the high-pressure (HP) phases are within the same space group $I4/mmm$. It was suggested that this phase transition was accompanied by a valence change of the Eu in EuCo_2P_2 . The crystal structure of the ThCr_2Si_2 -type phosphide EuFe_2P_2 was investigated by the single crystal diffraction technique [12]. A pressure-induced similar structural phase transition also occurred in EuFe_2P_2 [13,14]. Furthermore, many RET_2X_2 -type intermetallics have been studied extensively to explore the correlation of

superconductivity or magnetism and the corresponding structures [15-20]

Although many studies have claimed that high pressure can tune the valence of the Eu in EuNi_2P_2 , the role of pressure playing in the valence fluctuation is still not clear.^{5,10} Detailed studies on the valence of the Eu in Eu-based systems are feasible by synchrotron Mössbauer spectroscopy (SMS) under high pressure [21,22]. In this work we have investigated the origin of the valency changing of the Eu in EuNi_2P_2 under high pressure through SMS combined with angle dispersive X-ray diffraction (AD-XRD). The mean of ^{151}Eu can be estimated from the Mössbauer isomer shift (IS) [23]. The high pressure structure of EuNi_2P_2 has been studied by AD-XRD) and compared with the isostructural compounds EuFe_2P_2 and EuCo_2P_2 . We discuss the relation between the valence fluctuation of Eu and the crystal structure and conclude that the pressure-induced valence change originates from the micro changes in crystal structure.

2. Materials and methods

The EuNi_2P_2 sample was synthesized using the tin-flux method. A full description can be found elsewhere [24]. The high pressure synchrotron SMS and AD-XRD experiments at room temperature with EuNi_2P_2 were carried out at the beamlines 3-ID-B and HPCAT 16-ID-B, the Advanced Photon Source (APS) of Argonne National Laboratory (ANL), respectively. EuNi_2P_2 samples in powder form were used in both The SMS and the AD-XRD experiments. A symmetric type diamond anvil cell (DAC) with a diamond culet size of 300 μm was used to achieve high pressure.

The SMS experiment of EuNi_2P_2 was carried out up to the pressure of 50 GPa at

beamline 3-ID-B at room temperature. Re gasket was preindented to 45 μm central thickness and a hole 110 μm in diameter EDM-drilled as a sample chamber. Ruby spheres were loaded together with the sample in the gasket hole. The pressure was determined in situ by the standard ruby fluorescence method [25]. The X-ray beam at the nuclear resonance energy of 21.541 KeV was focused to $\sim 15 \mu\text{m}$ at the sample position by the Kirkpatrick-Baez mirrors.

In AD-XRD experiments, a T301 stainless steel was used as gasket material. The gasket with initial thickness of 300 μm was pre-indented to 50 μm and 120 μm hole was drilled. Silicone oil was used as pressure transmitting medium. The AD-XRD experiments at room temperature were conducted with a monochromatic X-ray beam of 0.3679 Å, which was focused down using multilayer bimorph mirrors in a Kirkpatrick–Baez configuration [26,27] to $10 \mu\text{m} \times 10 \mu\text{m}$ at the sample location in both horizontal and vertical directions. A pinhole placed before the sample position was used as a cleanup aperture for filtering out the tail of the X-ray beam. The pressures were determined by the ruby fluorescence method off line. The pressure difference before and after the collection of diffraction patterns was taken as the pressure uncertainty. CeO_2 was used to calibrate the sample-detector distance and the orientation parameters of the detector. The two-dimensional XRD patterns were collected using a MAR345 image plate detector with an exposure time of 10 s. Then the XRD images were integrated using the FIT2D program [28]. The Rietveld refinement on XRD patterns of EuNi_2P_2 was performed using the General Structure Analysis System (GSAS) program package [29,30].

3. Results

The IS values for Eu^{2+} systems are in the range of -8 to -14 mm/s (with respect to EuF_3), whereas for Eu^{3+} systems, the IS is in the range of 0 to +4 mm/s [31]. The synchrotron Mössbauer spectra of ^{151}Eu for EuNi_2P_2 at various pressures are shown in Fig. 1. The time domain Mössbauer spectra of ^{151}Eu were collected with EuF_3 and EuS as reference samples under high pressure. The SMS spectra are fitted using the software CONUSS [32]. The conventional Mössbauer absorption spectra were simulated using the hyperfine parameters obtained from fitting the time domain spectra. It is noticed that the energy domain spectra of EuNi_2P_2 have a single resonance peak without quadrupole splitting, which indicates that the crystallographic order of EuNi_2P_2 is at very high degree. The IS of the Eu ion in EuNi_2P_2 shown in Fig. 1 is -5.96 mm/s at 0 GPa with EuF_3 as reference suggesting EuNi_2P_2 is a homogeneous mixed-valence system at ambient conditions. The value of IS is in good agreement with reported value of -6.3 mm/s in Ref. [3,5]. The IS of the divalent Eu ion in EuS is -12.03 mm/s (with respect to EuF_3). With increasing pressure the IS of the Eu ion in EuNi_2P_2 increases monotonically with increasing pressure, moving toward trivalent state of Eu. The high pressure values of IS in Eu are plotted in Fig. 2. It is shown that the IS of the Eu increases drastically with pressure in the range of 0 to 20 GPa. Above 20 GPa the increase of IS slows down and IS reaches zero at 50 GPa, indicating that the $\bar{\nu}$ of Eu in EuNi_2P_2 becomes fully trivalent at about 50 GPa. Perscheid *et al.* show that the valence of Eu remains mixed under pressure up to 10

GPa and at both 300 K and low temperatures [5]. For EuFe_2P_2 , a continuous valence change of Eu from Eu^{2+} to Eu^{3+} is accompanied by a second-order structural phase transition in the pressure range of 0 ~ 12 GPa. As for EuCo_2P_2 , a sharp valence transition of Eu from Eu^{2+} to Eu^{3+} is accompanied by a pressure-induced first-order structural phase transition at 3 GPa [33].

From the crystallographic point of view, the valence state can also be derived from the structural data alone via bond valence sum rules [34-36], which relates the interatomic distance and the coordination number to the corresponding element valence. However, Souza-Neto *et al.* studied Eu's valence in EuO under high pressure and found that the bond-valence sum rules fail to quantitatively describe the electronic valence behavior of EuO under high pressure [37]. For EuFe_2P_2 and EuCo_2P_2 , their structural instability was intimately connected to the electronic and magnetic instabilities [38]. For EuNi_2P_2 , it is unclear whether the same phenomenon exists. So it is necessary to investigate the detailed crystal structural change induced by pressure through XRD.

EuNi_2P_2 crystallizes in a body-centered tetragonal structure with two formulas per unit cell [39]. The schematic crystal structure and the Wyckoff positions of EuNi_2P_2 are shown in the inset of Fig. 2. The Wyckoff positions of Eu, Ni and P atoms are located at 2a (0, 0, 0), 4d (0, 0.5, 0.25) and 4e (0, 0, z), respectively. The Eu atoms are located at the center of a polyhedron composed of the Ni and P atoms. The crystal structure of EuNi_2P_2 can be schematically described as an alternative stacking sequence of the positively charged Eu sheets and the negatively charged Ni_2P_2 blocks,

which can be considered as consisting of the NiP_4 tetrahedra along c direction [40-44]. This interesting crystallography of the AB_2X_2 -type compounds was highlighted by R. Hoffmann and C. Zheng in 1985, who pointed out that the bonding between the A and the B_2X_2 layers is largely ionic. While in the B_2X_2 layers there are not only covalent B–X bonding but also the metallic bonding B–B, and the X–X bonding of two neighboring B_2X_2 layers varies from no bond to a fully formed X–X single bond according to the variety of the transition metal B [45].

In the isostructural phosphides EuT_2P_2 ($\text{T} = \text{Fe}, \text{Co}, \text{Ni}$), the different atomic sizes of the T element are responsible for the different lattice parameters. So they are the ideal series for exploring the relation of the element valences and the corresponding lattice parameters. AD-XRD experiment on EuNi_2P_2 was carried out under high pressure up to 32 GPa. The AD-XRD patterns are shown in Fig. 3. Up to 32 GPa no new diffraction peaks were observed, showing the crystal structure is stable in this pressure range. All the Bragg reflections can be indexed by the space group $I4/mmm$ from ambient pressure to about 32 GPa. The unit cell volumes of EuNi_2P_2 are calculated from the refined lattice parameters in GSAS and shown in Fig. 4. At ambient pressure, the unit cell volume of EuNi_2P_2 is $147.2 \text{ \AA}^3$, which is smaller than both EuFe_2P_2 and EuCo_2P_2 . Shown in the inset of Fig. 4, the crystalline lattices of EuNi_2P_2 shrink quite uniformly, similar to the behavior observed in the high pressure collapsed tetragonal phases of the other related compounds.

4. Discussion

The valence of the Eu ion can change from Eu^{2+} to Eu^{3+} in both EuFe_2P_2 and EuCo_2P_2 under high pressure, accompanied by the pressure-induced second-order and first-order structural phase transitions, respectively [33]. However, the valence of the Eu ion in EuNi_2P_2 changes monotonically from a mixed valency to nearly full trivalency with increasing pressure up to 50 GPa without any structural phase transition observed from the XRD patterns. The above phenomena can be addressed from the point of view of the atomic bonding. At ambient conditions, the P–P distance of two adjacent T_2P_2 ($\text{T} = \text{Fe}, \text{Co}, \text{Ni}$) layers in EuNi_2P_2 is very different from the ones in EuFe_2P_2 and EuCo_2P_2 , with the value being 2.371, 3.27 and 3.273 Å, respectively [24,46]. Only the P–P distance in EuNi_2P_2 is close to the ideal P–P single bonding distance of 2.21 Å [47]. It suggests the possible forming of the P–P covalent bonding in the direction normal to the layers in EuNi_2P_2 at ambient conditions. While the P atoms in two adjacent T_2P_2 layers in EuFe_2P_2 and EuCo_2P_2 are isolated from each other at ambient conditions, yielding divalent behavior in Eu. The chemical bonding in the ternary nickel phosphides LnNi_2P_2 was discussed on the basis of the Zintl-Klemm concept [48,49], analogously to which, the valences of all the elements can be described as ionic formulations $\text{Eu}^{2+}\text{Fe}^{2+}\text{Fe}^{2+}\text{P}^{3-}\text{P}^{3-}$ in EuFe_2P_2 and $\text{Eu}^{2+}\text{Co}^{2+}\text{Co}^{2+}\text{P}^{3-}\text{P}^{3-}$ in EuCo_2P_2 (where bonding electrons are counted as belong to the more electronegative partner). It suggests that the formulation of the mixed valence in EuNi_2P_2 is in between two types: part is $\text{Eu}^{2+}\text{Ni}^{2+}\text{Ni}^{2+}\text{P}^{3-}\text{P}^{3-}$ and part is $\text{Eu}^{3+}\text{Ni}^{1+}\text{Ni}^{1+}[\text{P}_2]^{5-}$ at ambient conditions. The P–P distance in EuNi_2P_2 becomes closer under high pressure. Finally, high pressure will turn the formulation of EuNi_2P_2 to the

$\text{Eu}^{3+}\text{Ni}^{1+}\text{Ni}^{1+}[\text{P}_2]^{5-}$ type which means there still exists the unbonding status for the P-P interaction. For the P element which is the form $[\text{P}_2]^{5-}$, the length of the P-P bonding is roughly in between that for a single covalent bonding form $[\text{P}_2]^{4-}$ and a non-bonding form 2P^{3-} . The valency of the Eu changes from Eu^{2+} to Eu^{3+} and the valency of the Ni element changes from Ni^{2+} to Ni^{1+} . It means that the Ni atoms finally possess nine unshared valence electrons in 3d orbital to form a “ d^9 ” system, if the partial covalency of the Ni-P interactions is not considered [47].

Using the third-order Birch–Murnaghan equation [50], the ambient pressure isothermal bulk modulus and its derivative of EuNi_2P_2 were obtained by the volume-pressure data fitting in Fig. 4, which are $B_0 = 154.9(6)$ GPa and $B_0' = 4.8(3)$, and the solid line in Fig. 4 is the fitting data. The present result of bulk modulus for EuNi_2P_2 was consistent with the reported literature data [10]. By using the high pressure energy dispersive XRD data in Ref. [11,13], the ambient pressure isothermal bulk moduli of the low pressure phases for EuFe_2P_2 and EuCo_2P_2 were estimated as 45 GPa and 73 GPa, respectively. By contrast, EuNi_2P_2 exhibits much larger bulk modulus, which may origin from the much harder covalent P-P bonding existing in EuNi_2P_2 .

The valence change in EuNi_2P_2 can be addressed from the aspect of the electronic structure. In the f-electron system, the mixed valency is mostly explained as the hybridization between the localized f orbital of the rare earth or the actinide element and the itinerant delocalized s , p , d valence electrons throughout the crystal lattice, which could result in many astonishing correlated phenomena [51]. In the

homogeneous mixed-valence Eu-based compounds, the $4f$ electrons of the Eu element have a dynamical fluctuation between localization and delocalization. For the Eu element in EuNi_2P_2 , the $4f$ orbital fluctuates between $4f^6$ and $4f^7$. The valence of Eu in EuNi_2P_2 is changed under high pressure and reaches almost full trivalency from the mixed valent state. It means that the external pressure is a main driving force for immensely enhancing the electrons hybridization which is responsible for the atom bonding status in EuNi_2P_2 . Furthermore, it is also indirectly claimed that even down to $T \rightarrow 0$ K is still not enough for the Eu element to reach trivalency because of the more moderate effect of temperature than pressure on the volume of EuNi_2P_2 . Besides, it should be noticed that the temperature and the composition dependences of the valence differ strongly between Eu based and Ce/Yb based systems, while the pressure dependence of the valence in EuNi_2P_2 definitely display a similar characteristic with many Ce/Yb based heavy fermion metals which are mainly dominated by the Kondo lattice/intermediate valence (KL/IV) scenario [52-54].

5. Conclusions

In summary, the valence change in EuNi_2P_2 has been discussed from the aspects of the crystal structure and electronic structure using the synchrotron Mössbauer and AD-XRD measurements. The synchrotron Mössbauer results suggest that in EuNi_2P_2 Eu's valence increases toward trivalent with increasing pressure and becomes fully trivalent around 50 GPa. AD-XRD experiments show no structural phase transition up to 32 GPa. It is claimed that the valence change of Eu is strongly correlated with P-P

bonding and the electrons hybridization.

Acknowledgements

We thank Stanislav V. Sinogeikin (16-ID-B, APS, ANL) for experimental help. The High Pressure Collaborative Access Team (HPCAT) facility is supported by CIW, CDAC, UNLV and LLNL through funding from DOE-NNSA, DOE-BES and NSF. APS is supported by DOE-BES, under Contract No. DE-AC02-06CH11357. Support by Consortium for Materials Properties Research in Earth Sciences (COMPRES), the National Science Foundation (NSF) through Grant No. DMR-1104742 is gratefully acknowledged. This work was partially supported by National Natural Science Foundation of China (Grant No. 10904022), the National Basic Research Program of China (Grant Nos. 2011CB921700, No. 2015CB921300) and the Strategic Priority Research Program of the Chinese Academy of Sciences (XDB07020000).

Reference

- [1] N.B. Brandt, V.V. Moshchalkov, *Adv. Phys.* 33 (1984) 373.
- [2] R. Nagarajan, E.V. Sampathkumaran, L.C. Gupta, R. Vijayaraghavan, V. Prabhawalkar, Bhaktadarshan, B.D. Padalia, *Phys. Lett. A* 84 (1981) 275.
- [3] R. Nagarajan, G. K. Shenoy, L.C. Gupta, and E.V. Sampathkumaran, *Phys. Rev. B* 32 (1985) 2846.
- [4] Y.H. Matsuda, Z.W. Ouyang, H. Nojiri, T. Inami, K. Ohwada, M. Suzuki, N. Kawamura, A. Mitsuda, and H. Wada, *Phys. Rev. Lett.* 103 (2009) 046402.
- [5] B. Perscheid, E.V. Sampathkumaran, G. Kaindl, *J. Magn. Magn. Mater.* 47-48 (1985) 410.
- [6] I. Serdons, S. Nasu, R. Callens, R. Coussement, T. Kawakami, J. Ladrère, S. Morimoto, T. Ono, K. Vyvey, T. Yamada, Y. Yoda, and J. Odeurs, *Phys. Rev. B* 70 (2004) 014109.
- [7] V. Guritanu, S. Seiro, J. Sichelschmidt, N. Caroca-Canales, T. Iizuka, S. Kimura, C. Geibel, and F. Steglich, *Phys. Rev. Lett.* 109 (2012) 247207.
- [8] S. Danzenbächer, D.V. Vyalikh, Yu. Kucherenko, A. Kade, C. Laubschat, N. Caroca-Canales, C. Krellner, C. Geibel, A.V. Fedorov, D.S. Dessau, R. Follath, W. Eberhardt, and S.L. Molodtsov, *Phys. Rev. Lett.* 102 (2009) 026403.
- [9] R. Nagarajan, G.K. Shenoy, L.C. Gupta, E.V. Sampathkumaran, *J. Magn. Magn. Mat.* 47-48 (1985) 413.
- [10] S.A. Medvedev, P. Naumov, O. Barkalov, C. Shekhar, T. Palasyuk, V. Ksenofontov, G. Wortmann and C. Felser, *J. Phys.: Condens. Matter* 26 (2014) 335701.
- [11] C. Huhnt, W. Schlabit, A. Wurth, A. Mewis, and M. Reehuis, *Phys. Rev. B* 56 (1997) 13796.
- [12] M. Reehuis, W. Jeitschko, *J. Phys. Chem. Solids* 51 (1990) 961.
- [13] C. Huhnt, W. Schlabit, A. Wurth, A. Mewis, M. Reehuis, *Physica B* 252 (1998) 44.
- [14] B. Ni, M.M. Abd-Elmeguid, H. Micklitz, J.P. Sanchez, P. Vulliet, and D. Johrendt, *Phys. Rev. B* 63 (2001) 100102(R).
- [15] F. Steglich, J. Aarts, C.D. Bredl, W. Lieke, D. Meschede, W. Franz, and H. Schäfer, *Phys. Rev. Lett.* 43 (1979) 1892.
- [16] G.W. Hull, J.H. Wernick, T.H. Geballe, J.V. Waszczak, and J.E. Bernardini, *Phys. Rev. B* 24 (1981) 6715.
- [17] Marianne Rotter, Marcus Tegel, and Dirk Johrendt, *Phys. Rev. Lett.* 101 (2008) 107006.
- [18] Y.Q. Chen, J. Luo, J.K. Liang, J.B. Li, G.H. Rao, J. Alloy. *Compd.* 489 (2010) 13.
- [19] Z. Hossain, C. Geibel, F. Weickert, T. Radu, Y. Tokiwa, H. Jeevan, P. Gegenwart, and F. Steglich, *Phys. Rev. B* 72 (2005) 094411.
- [20] H.S. Jeevan, C. Geibel, and Z. Hossain, *Phys. Rev. B* 73 (2006) 020407(R).
- [21] E.E. Alp, W. Sturhahn, T. Toellner, *Nucl. Instr. Meth. Phys. Res. B* 97 (1995) 526.
- [22] W. Bi, N.M. Souza-Neto, D. Haskel, G. Fabbris, E.E. Alp, J. Zhao, R.G. Hennig, M.M. Abd-Elmeguid, Y. Meng, R.W. McCallum, K. Dennis, and J.S. Schilling, *Phys. Rev. B* 85 (2012) 205134.
- [23] W. Sturhahn, E.E. Alp, T.S. Toellner, P. Hession, M. Hu, J. Sutter, *Hyperfine Interact.* 113 (1998) 47.
- [24] R. Marchand, W. Jeitschko, *J. Solid State Chem.* 24 (1978) 351.
- [25] H.K. Mao, J.A. Xu, P. Bell, *J. Geophys. Res.* 91 (1986) 4673.
- [26] S. Matsuyama, H. Mimura, H. Yumoto, K. Yamamura, Y. Sano, K. Endo, Y. Mori, Y. Nishino, K. Tamasaku, T. Ishikawa, M. Yabashi and K. Yamauchi, *Rev. Sci. Instrum.* 76 (2005) 083114.
- [27] S. Matsuyama, H. Mimura, H. Yumoto, H. Hara, K. Yamamura, Y. Sano, K. Endo, Y. Mori, M. Yabashi, Y. Nishino, K. Tamasaku, T. Ishikawa and K. Yamauchi, *Rev. Sci. Instrum.* 77 (2006) 093107.
- [28] A. Hammersley, S. Svensson, M. Hanfland, A. Fitch and D. Hausermann, *High Pressure Res.* 14 (1996) 235.
- [29] A.C. Larson, R.B. Von Dreele, *General Structure Analysis System (GSAS)*, Los Alamos National Laboratory Report LAUR (1994) 86-748.
- [30] B.H. Toby, *J. Appl. Crystallorg.* 34 (2001) 210.
- [31] J.G. Stevens, *Hyperfine Interact.* 13 (1983) 221.
- [32] W. Sturhahn, *Hyperfine Interactions* 125 (2000) 149.
- [33] M. Chefki, M.M. Abd-Elmeguid, H. Micklitz, C. Huhnt, W. Schlabit, M. Reehuis, and W. Jeitschko, *Phys. Rev. Lett.* 80 (1998) 802.
- [34] A. Jayaraman, A.K. Singh, A. Chatterjee, and S. Usha Devi, *Phys. Rev. B* 9 (1974) 2513.
- [35] N.E. Brese, M. O'keeffe, *Acta Crystallorg. B* 47 (1991) 192.

- [36] I.D. Brown, D. Altermatt, *Acta Crystallorg.* B 41 (1985) 244.
- [37] N.M. Souza-Neto, J. Zhao, E.E. Alp, G. Shen, S.V. Sinogeikin, G. Lapertot, and D. Haskel, *Phys. Rev. Lett.* 109 (2012) 026403.
- [38] P.H. Andersson, L. Nordström, P. Mohn, and O. Eriksson, *Phys. Rev. B* 65 (2002) 174109.
- [39] H.F. Braun, N. Engel, and E. Parthé, *Phys. Rev. B* 28 (1983) 1389.
- [40] J. Leciejewicz, S. Siek, A. Szytuła, *J. Less Common Met.* 144 (1988) L9.
- [41] I.R. Shein, A.L. Ivanovskii, *Solid State Commun.* 151 (2011) 1165.
- [42] R. Marazza, R. Ferro, G. Rambaldi, G. Zanocchi, *J. Less Common Met.* 53 (1977) 193.
- [43] A. Szytuła, B. Penc, M. Hofmann, J. Przewoźnik, *Solid State Commun.* 152 (2012) 1027.
- [44] Z. Ban, M. Sikirica, *Acta Crystallogr.* 18 (1965) 594.
- [45] R. Hoffmann, C. Zheng, *J. Phys. Chem.* 89 (1985) 4175.
- [46] W. Jeitschko, & B. Jaberger, *J. Solid State Chem.* 35 (1980) 312.
- [47] H.G. Von Schnering, & W. Hönl, *Chem. Rev.* 88 (1988) 243.
- [48] W. Jeitschko, & M. Reehuis, *J. Phys. Chem. Solids* 48 (1987) 667.
- [49] H. Schäfer, B. Eisenmann, & W. Müller, *Angew. Chem. Int. Ed.* 12 (1973) 694.
- [50] F. Birch, *Phys. Rev.* 71 (1947) 809.
- [51] C. Felser, S. Cramm, D. Johrendt, A. Mewis, O. Jepsen, G. Hohlneicher, W. Eberhardt and O.K. Andersen, *Europhys. Lett.* 40 (1997) 85.
- [52] Q.M. Si, F. Steglich, *Science* 329 (2010) 1161.
- [53] C.U. Segre, M. Croft, J.A. Hodges, V. Murgai, L.C. Gupta, and R.D. Parks, *Phys. Rev. Lett.* 49 (1982) 1947.
- [54] S. Seiro and C. Geibel, *J. Phys.: Condens. Matter* 23 (2011) 375601.

Figure captions

Fig. 1. Room temperature synchrotron Mössbauer spectra of ^{151}Eu for EuNi_2P_2 at various pressures.

Fig. 2. Isomer shift of ^{151}Eu ion in EuNi_2P_2 and EuFe_2P_2 versus pressure and temperature. The inset shows the schematic crystal structures of layered EuNi_2P_2 with the ThCr_2Si_2 -type structure.

Fig. 3. Selected Angle dispersive X-ray diffraction patterns of EuNi_2P_2 under various pressures.

Fig. 4. Pressure dependence of unit cell volume of EuNi_2P_2 on pressure fitted by Birch-Murnaghan equation of state. The inset shows the pressure dependence of lattice parameters of EuNi_2P_2 .