Superconductivity in compressed hydrogen-rich materials: pressing on hydrogen.

Viktor V. Struzhkin*

*Geophysical Laboratory, Carnegie Institution of Washington,
5251 Broad Branch Road NW, Washington DC 20015, USA*

Periodic table of elements starts with Hydrogen, a simplest element of all. The simplicity is lost when the element is compressed to high densities or participates in a chemical bonding in compounds, being subjected to “chemical pressure” of surrounding atoms or molecules. The chemical nature of hydrogen is dictated by its simplest electronic shell, which has only one electron. Hydrogen can donate this electron and behave like alkali metal, or accept an extra electron and form a hydride ion with closed shell resembling a group VII element. The complexity of hydrogen goes beyond these simplest configurations, when hydrogen is involved in a multicenter bonding or in hydrogen bonds. This complex behavior is tightly related to the ability of hydrogen to participate in the process of electronic transport in solids and potentially be able to contribute to the superconductivity in a material. Hydrogen by itself when compressed to immense pressures of 400-500 GPa may form a simple atomic phase with very high critical superconducting temperatures (T_c) well above room temperature. While this theoretical insight awaits confirmation at pressures at the limit of current experimental capabilities, a variety of other hydrogen-rich materials have been suggested recently to have record high T_c values. The very existence of many of these materials still lacks experimental confirmation. In this review article, we will present an extensive list of such predicted materials. We will also review superconductivity in classical hydrides (mostly metal hydrides) and current theoretical understanding of relatively low T_c 's in metal hydrides of transition and noble metals.

*Corresponding author:

Viktor Struzhkin

Tel.: +1 2024788952

Fax: +1 202 4788901

Email: vstruzhkin@carnegiescience.edu

Article outline

- 1. Introduction**
- 2. Phonon-driven superconductivity in hydrides**
 - A. Electron-phonon coupling and anharmonic effects**
 - B. Anharmonic reduction of T_c : PdH, PtH.**
- 3. Hydrogen “doping“ with other elements**
 - A. Silane and its siblings**
 - B. Polyhydrides of alkali and alkaline earth metals**
- 4. Prospects for room temperature superconductor based on hydrogen-rich materials: concluding remarks**
- 5. Appendix: Properties of the superconducting state of hydrides**

Introduction

As we may expect, chemical nature of hydrogen dictates its participation in transport phenomena in solids. “Dual” nature of hydrogen as an electron donor or acceptor, and its tendency to form multicenter bonds of various degree of complexity (1), provides for a variety of chemical environments for hydrogen (2). While “ionic” character of a hydride ion or a proton in most of these environments (3) is leading to insulating properties, a multicenter or metallic bonding (1) promotes materials with metallic conductivity. Within a BCS (Bardeen, Cooper and Schrieffer) scenario of superconductivity (4) high vibrational frequencies of hydrogen atoms raised hopes (5) for a high critical temperature in conducting hydrogen and hydrogen-rich materials (6). However, multiple attempts to find a material with high critical superconducting temperature in hydrides of transition and rare-earth metals did not produce a high- T_c material. The highest T_c ’s observed in hydrides of Pd and Pd-Au, Pd-Cu alloys did not exceed temperatures of the order of 15-17 K (7, 8). Moreover, substantial inverse isotope effect was observed in PdH and PdD, at first raising doubts in the validity of the electron-phonon coupling mechanism for superconductivity in these materials, and later leading to the understanding of the role played by anharmonicity of hydrogen vibrations in such “simple” hydrides (9). It should be noted that there are published claims of nearly room-temperature superconductivity in PdH_x materials (10), which have not been confirmed by other experimentalists and have no theoretical backing at the moment.

The ability to create hydrogen-based materials with desired properties has received tremendous boost recently from a variety of government funded programs aimed at a viable hydrogen storage material for automotive and energy-storage related applications

(11, 12). Chemical compounds (11), weakly interacting molecular materials (12, 13), surface interactions (14) have been attempted with limited success to conveniently store and retrieve hydrogen. However, no practical material for hydrogen storage did emerge from this massive effort so far. Despite the deceptive simplicity hydrogen turned out extremely complex chemical entity as a component of useful materials. The properties of hydrogen in high-pressure environment become even more complex. High energy density (15), high-temperature superconductivity and superfluidity (16) are expected in dense hydrogen and hydrides. Ambient pressure metastable metallic phase of hydrogen, consisting of weakly interacting chains of hydrogen atoms with interatomic distances about 1.06 Å was predicted in 1970's by Brovman and Kagan (17). Ashcroft (6) proposed a metallic state in hydrogen-rich alloys, where the electronic bands of hydrogen and the host element(s) overlap. In the work that followed, the superconductivity was found with T_c approaching 20 K in transport measurements performed by Eremets et al. (18). This claim was subjected to experimental (and theoretical) scrutiny as discussed in section 2 of this review. As a development of this idea, very unusual metallic polyhydrides of lithium have been proposed (19, 20) to exist at pressures about 100 GPa, well below the expected metallization pressure of pure hydrogen (21). Stable polyhydrides of alkali metals have been predicted recently by theoretical analysis of MH_n ($M = \text{Li, Na, K, Rb, Cs}$) compounds with variable hydrogen composition (19, 20, 22-25). These alkali and alkali earth polyhydrides will be reviewed in section 3.

Finally, we will discuss the prospects for high- T_c hydrogen-rich materials in a high-pressure environment. Both theoretical insights and experimental challenges will be discussed.

2. Phonon-driven superconductivity in hydrides

A. Electron-phonon coupling and anharmonic effects

We give below a quick summary of the results for electron-phonon coupling driven superconductivity relevant for the discussion of hydrogen-based superconductors. The critical superconducting temperature for a phonon-mediated superconductor can be conveniently represented by modified McMillan formula (26, 27) :

$$T_c = \frac{\omega_{\log}}{1.2} \exp \left[-\frac{1.04(1 + \lambda)}{\lambda - \mu^* (1 + 0.62\lambda)} \right] \quad (1)$$

where $\omega_{\log}$ is a logarithmic average of the phonon frequency, λ is electron-phonon coupling constant, and μ^* is the Coulomb pseudopotential of Morel and Anderson (28).

Another useful formula is defining electron phonon coupling parameter λ

$$\lambda \equiv \frac{N(\epsilon_F) \alpha^2}{M \omega_E^2} \quad (2)$$

in terms of the density of the electronic states $N(E_F)$ at the Fermi level, the phonon frequency ω_E and effective mass M , and the Holstein parameter α , a Fermi surface average of the electronic matrix element of the change in crystal potential as particular phonon mode-related atoms are moved (26). Partial contribution of phonon modes was analyzed in (29) for weakly coupled phonons; we show a figure with the results of this analysis (Fig.1)

$$1/E \delta T_c / \delta \alpha^2(\Omega) F(\Omega) \quad 101$$

$$\frac{\delta T_c}{\alpha^2(\Omega) F(\Omega)} \equiv \lim_{\epsilon \rightarrow 0} \frac{\delta T_c}{\epsilon} = \frac{1}{1 + \lambda} G(\bar{\Omega}) \quad (21)$$

here

Fig.1. Function $G(\bar{\Omega})$, $\bar{\Omega} = \Omega/T_c$ is the reduced frequency ($\hbar = 1$, $k_B = 1$). Reproduced from Solid State Commun. from Mitrović and Carbotte (29).

Fig.1 shows relative partial derivative of the T_c with respect to small change in the partial coupling strength $\alpha^2(\Omega)F(\Omega)$ at phonon frequency Ω , with broad maximum around $\Omega=10$. It means that the phonon frequencies contributing mostly to T_c , are about factor of 10 higher in frequency than the T_c (in equivalent units, $\hbar\omega/k_B T_c$). This result along with Eq.1, strongly favors high vibrational frequencies as a prerequisite of high T_c values. The highest vibrational frequencies are found in hydrogen in hydrides; for this reason hydrogen-rich materials have attracted significant amount of attention in the search for highest T_c values in materials. However, historically the quest for high- T_c hydrogen based materials did not produce any significant results. The early era before high- T_c cuprates, was reviewed in (30). Despite significant effort, only two families of relatively high T_c materials have been found with Th (31) and Pd (7, 32) hydrides. Both systems showed anomalous isotope effect when doped with deuterium; $\text{ThH}(\text{D})_{3.64}$ did not show any isotope effect, which initially raised doubts regarding the phonon-mediated mechanism, and $\text{PdH}(\text{D})$ showed inverse isotope effect (9). In the theoretical and

experimental papers that followed discovery of PdH superconductor, the anomalous isotope effect was understood as resulting from anomalously large anharmonicity of hydrogen (deuterium) vibrations (33, 34, 35-37). While earlier works used empirically scaled experimental phonon spectrum (34), the latest theoretical efforts have explained the observed anharmonicity from the first principles (37). Since the anharmonic effects are not treated explicitly in lately predicted high- T_c 's in transition and noble metal hydrides (38, 39), we will give a brief overview of current understanding of the anharmonicity effects on T_c in these materials.

1.B Anharmonic reduction of T_c : PdH, PtH.

In the early paper Klein et. al. (34) have used the measured phonon densities of states in PdH(D) (40) to introduce semiempirical correction to the electron-phonon coupling constant, and they concluded that observed (quartic) anharmonicity is sufficient to explain the anomalous isotope effect. Similar considerations were used in several other theoretical approaches; Klein and Cohen have calculated the phonon spectra and were able to reproduce the inverse isotope effect qualitatively (41). They also noticed strong dependence of the isotope effect on Coulomb pseudopotential (Eq. 1), which is theoretically justified (42). Anharmonic vibrations of hydrogen in AlH₃ were suggested (43) as the reason for disagreement between “harmonic” calculation and experimental findings (44). In Fig. 2 we show highly anharmonic character of hydrogen vibrations (quartic anharmonicity) as follows from the frozen-phonon calculations (43).

Fig.2. Frozen phonon total-energy calculations for the modes at X with frequencies ~ 20 meV (X1) and ~ 85 meV (X2), as a function of a displacement parameter η . Reproduced from Physical Review B (43).

Recently, Erea et al. (37) have performed ab-initio calculations of T_c in PdH using newly developed Stochastic Self-Consistent Harmonic approximation (SSCHA) – see also Ref. (45). This work was followed by two papers demonstrating the effect of anharmonicity on calculated T_c in PtH and PdH (45), and in other hydrides and chalcogenides (46). Their results show that the harmonic approximation describing the vibrations of atoms in solids can completely break down when the displacements of the atoms exceed the range in which the harmonic potential is valid. Such situations occur mostly for very light atoms like hydrogen, or in very soft effective potentials (47). In Fig.2 we reproduce the electron-phonon coupling calculation for PtH from Erea et al. (45).

Fig.3. $\alpha^2F(\omega)$ and $\lambda(\omega)$ of PtH at 100 GPa and 0 K in the harmonic approximation (top) and in the SSCHA (bottom). The contribution of Pt and H atoms to $\alpha^2F(\omega)$ is also shown. Reproduced from Phys. Rev. B., Erea et. al. (45).

As is clear from Fig. 2, the calculations in SSCHA formalism, taking account of anharmonic effects, reduce significantly theoretical estimation of electron-phonon coupling contribution due to vibrations of hydrogen atoms. The calculated anharmonic hydrogen vibrations are located much higher in frequency, than harmonic approximation would predict. According to Fig.1, the contribution to the T_c should dramatically decrease, since the phonon density of states is shifted by more than factor of 10 above the energy corresponding to T_c .

3. Hydrogen “doped“ with other elements

A. Silane and its siblings

The possibility that compressed hydrogen may convert to a metallic state under compression was first suggested in 1935 (48), but experimental realization of metallic hydrogen in its solid atomic form (49) remains a challenging goal. In 2004, Ashcroft suggested that dense hydrides of group IVa elements are promising candidates for realizing metallization of solid hydrogen at pressures considerably lower than may be necessary for solid hydrogen because hydrogen has already undergone a form of “chemical pre-compression” (6). The idea of diluting hydrogen with other elements is not new (50), but only recently experimental x-ray, Raman, transport, and infrared measurements as well as theoretical calculations have been performed on the group IVa hydrides (mostly silane SiH_4 and germane GeH_4) in order to explore their metallization and potential superconductivity suggested by Ashcroft(6). Experimental (51) and theoretical (52) results pointed to instability of germane at high pressures and even enabled measurements of high-quality x-ray diffraction data on high-pressure germanium phases (51), which were possible due to perfect powder x-ray diffraction of germanium in a soft pressure medium (H_2) formed by decomposition of GeH_4 .

Fig.4. The enthalpy versus pressure for competitive structures of SiH_4 . The enthalpy of the $I4_1/a$ phase is taken as the reference point. The “enthalpically” most favorable structures computed for SiH_4 polymorphs at high pressures are shown on the right (53). The Cmca structure having a layered network is the most likely candidate of the metallic phase of SiH_4 over a wide pressure range above 60 GPa. The superconducting transition temperature in this layered metallic phase is found to be in the range of 20–75 K (53).

The early theoretical work on silane (54-56) initiated significant experimental and theoretical efforts in search for superconductivity. Silane (SiH_4) has been the subject of several recent high-pressure studies. Chen et al. (57) used high-pressure spectroscopy to identify high-pressure behavior of silane. They found from Raman spectroscopy one fluid-solid transition at around 4.0 GPa and three solid-solid transitions near 6.5 GPa, 10 GPa, and 26.5 GPa at room temperature. Four high-pressure solid phases were detected, which we named phase III, IV, V, and VI. The infrared results show an increase of the reflectivity starting at 60 GPa (57), pointing at pressure-induced metallization, which confirms the prediction by Ashcroft (6). The results indicated that SiH_4 is a good candidate for the realization of the metallization of hydrogen under pressure. Theoretical

predictions by Chen et al. also favored high pressure superconductivity in silane (53) – see Fig.4. The predictions were made by other groups (58-60), also indicating high pressure superconductivity in silane. Indeed, the superconductivity was found with T_c approaching 20 K in transport measurements performed by Eremets et al. (18) – Fig.5. While silane remains stable below 50 GPa (61), it was claimed that it decomposes above 50 GPa (62) forming pure silicon (Si) and hydrogen (H_2), which in turn reacts with the metallic gasket (Re) or electrical leads (Pt) and may be responsible for a superconductivity and x-ray diffraction from platinum hydride observed in experiments by Eremets (18) and attributed to metallic silane. Further experiments by Hanfland et al. pointed to amorphisation of silane at 60 GPa and to formation of polymeric silane around 100 GPa (63). This study also found that silicon and hydrogen react above 100 GPa to form stable polymeric phases of silane (63). In the absence of decomposition, silane was found to remain partially transparent and nonmetallic to at least 150 GPa with a band gap constrained between 0.6 and 1.8 eV (64).

Fig.5. Electrical resistance and superconductivity in silane. (A) Photographs of silane at 125 GPa taken in transmitted (above) and reflected (below) light after annealing at $T = 400^\circ C$. Silane is transparent at this pressure; nevertheless, it noticeably reflects light. (B) A representative superconducting step on the

temperature dependence of resistance of silane at 192 GPa and 125 GPa (inset). Arrows indicate T_c . Electrical measurements were performed before the annealing, when an essential part of the sample remained in the metallic phase. (C) Pressure dependence of the critical transition temperature T_c of silane. Reproduced from Science (18).

Fig.6. SiH₄ - PtH controversy. Powder diffraction spectra of (a) the claimed “hcp phase of metallic silane” (18) and (b) hcp phase of PtH synthesized at high pressure. The tick marks in (b) show peak positions calculated from the reported lattice parameters for PtH in its hcp phase: $a = 2.773(1) \text{ \AA}$, and $c = 4.713(1) \text{ \AA}$. reproduced from Solid State Communications, Degtyareva et al. (62).

Experimentally, controversies regarding the decomposition of silane at high compression and its superconductivity are not resolved yet – Fig.6. We have performed both resistivity and magnetic susceptibility experiments (65) in platinum hydride formed in situ at high pressure to check the suggested effect (62) of electrical leads in previous experiments on silane (18). We were not able to confirm superconductivity of platinum hydride up to 100 GPa. Further magnetic susceptibility experiments may be required with silane loaded in a gold-lined and cBN gasket to exclude the effect of a metallic gasket and to contain possibly released hydrogen. In view of the theoretical results on anharmonic suppression of T_c in PtH, the high T_c observed in (18) may belong to superconducting phases of SiH_x compounds with different stoichiometry (66-69) or to polymeric phases of silane (63).

Stannane (SnH_4) (60) and plumbane (PbH_4) (70) were proposed as high-pressure (high-temperature) superconductor (SnH_4) and liquid metal (PbH_4), but experimental attempts to create these compounds at high pressure have not been reported so far.

B. Polyhydrides of alkali and alkaline earth metals

The content of this section will cover exclusively recent theoretical developments, which are very new and mostly did not find experimental confirmation at his moment. However, experiments are underway and experimentalists would benefit from a concise review of predicted polyhydrides, which have unusual compositions and defy our intuitive expectations.

As a very first development in that direction, metallic polyhydrides of lithium have been proposed (19, 20) to exist at pressures above 100 GPa, well below the expected metallization pressure of pure hydrogen (21). Stable polyhydrides of other alkali metals have been predicted recently by theoretical analysis of MH_n ($M = \text{Li, Na, K, Rb, Cs}$) compounds with variable hydrogen composition (19, 20, 22-25). The compounds with $n \geq 2$ are expected to become stable at pressures as low as few GPa in the case of Cs and above 100 GPa in the case of Li.

Fig. 7. The difference between the z and d distances in an $H \cdots H_2$ fragment (see inset) is plotted vs. their sum for an isolated H_3^- molecule in the gas phase. During the optimization, the total length of the molecule was constrained and the central atom was allowed to relax freely. These values are also illustrated for an $H \cdots H_2$ unit in $lp\text{-RbH}_9$ and $lp\text{-RbH}_5$. Reproduced from Chem. Eur. J., Hooper et al. (71).

New polyhydride phases are also anticipated for alkaline earth metals (24, 72, 73). The theoretically predicted polyhydrides are not only stabilized by compression, but are expected to metalize and exhibit superconducting properties at lower pressures than the constituent parts--the monohydride and hydrogen. Critical superconducting temperatures as high as 235 K have been predicted for polyhydrides of Ca (72).

These compounds provide new chemical means to pre-compress hydrogen molecules and to facilitate the creation of metallic superconducting hydrogen (5) with record high critical superconducting temperatures. Notably, linear H_3^- ions were predicted to form in polyhydrides of softer alkali metals, for example in RbH_5 (71) and CsH_3 (25). Such H_3^- ions (see for example Fig. 7) have a tendency to be stabilized in a linear configuration, contrary to triangular-shaped H_3^+ ions (74, 75). Symmetric H_3^- ions with interatomic distance 1.06 Å and with the lowest potential barrier (76) were discussed as transition states in hydrogen exchange processes of metal complexes (77). H_3^- and D_3^- ions were experimentally observed in discharge plasmas only recently (78). The chains of H_3^- ions that were found theoretically in RbH_5 (25) and CsH_3 (71), resemble one-dimensional hydrogen chains of ambient pressure metastable metallic hydrogen phases predicted in 1976 by Browman and Kagan (17). Such chains were also extensively discussed as a simplest model of strong correlations in a linear chain of hydrogen atoms (79, 80). In recent paper, Grabowski and Hoffman (81) have considered stabilization effect of the excited state of H_3^- anion with hydrogen separation 0.93 Å on a $(LiHHHLi)^+$ pentaatomic cation and also found (81) a linear coordinated arrangement. Other local stable clusters have been proposed. The pure hydrogen clusters (H_3^+ , H_3^- , etc...) and

clusters of hydrogen with other elements (81) may serve as building blocks of pressure-induced metallic phases. We are only starting to develop our intuitive understanding of emerging new strongly compressed materials with unexpected chemistry and physical properties.

LiH_2 LiH_6	BeH_2
NaH_3 NaH_7	MgH_4
NaH_9 NaH_{11}	MgH_{12}
KH_3 KH_5	MgH_{16}
$\text{KH}_8 \dots$	CaH_6
RbH_3 RbH_5	SrH_6
CsH_3 CsH_7	BaH_6 BaH_8
$\text{CsH}_9 \dots$	$\text{BaH}_{12} \dots$

H_2	
LiH	BeH_2
NaH	MgH_2
KH	CaH_2
RbH	SrH_2
CsH	BaH_2

	H_2	
B_2H_6	CH_4	NH_3
H_2O	HF	
AlH_3	SiH_4	PH_3
H_2S	HCl	
GaH_3	GeH_4	AsH_3
H_2Se	HBr	
SnH_4	SbH_3	H_2Te
HI		
PbH_4	BiH_3	H_2Po
HAt		

Fig.8. The modified Periodic Table shows hydrides of the elements belonging to main groups. A separate block on the left summarizes a variety of polyhydrides predicted recently and discussed in this section. NaH_3 and NaH_7 were synthesized recently in our group (submitted).

Alkali and alkaline earth polyhydrides predicted recently are summarized in Fig. 8. Apparently, polyhydrides of other main group elements may exist, as was reported

recently, for example, in Xe (82). Group VII polyhydrides, if they exist, would be “hole doped”, as compared to alkali and alkaline earth, which are “electron doped”. We may expect very different properties for hole doped polyhydrides, and also quite different local arrangements, possibly based on triangular H_3^+ cation (75). In this review we did not discuss polyhydrides of transition metals or rare earth metals at high pressure, which have only limited impact in current literature (83) and have limited connection to high-pressure experiments at this time, with only one candidate for “non-interstitial hydride”, IrH_3 (84). Existing classical “interstitial” metal hydrides were briefly discussed in section 1.

As a concluding remark, despite a wealth of theoretically predicted high pressure polyhydride structures, none of the predictions have been confirmed experimentally until now in the published literature. Also, the claims of metallic and superconducting phases should be considered with caution, and further in-depth theoretical analysis of superconducting properties may be required.

We have tried to create polyhydrides of Li (without success, see also Ref. (85)) and Na (NaH_3 and NaH_7 synthesized, work in progress) (86). We are optimistic and are looking forward to new polyhydrides coming to life very soon.

Notes added. When this paper was in review, the paper by Drozdov et. al. was published reporting nearly 190 K conventional superconductivity in H_2S hydride at 200 GPa (87). The experimental procedure and theoretical results by Duan et. al. (88) suggest that observed high T_c values may correspond to a polyhydride H_3S phase forming at high pressures when the sample is warmed up to room temperature (87). The experiments have reported superconductivity from resistivity measurements. If these results will be

confirmed by magnetic susceptibility measurements, there will remain no doubt that conventional phonon driven conductivity is possible close to room temperature. It is interesting to note that hydrogen in H_3S and its homologues would represent a test case to study a long sought “hole doped” metallic hydrogen, as discussed in this section.

4. Prospects for room temperature superconductor based on hydrogen-rich materials: concluding remarks.

Current candidate materials for high-temperature or even room-temperature superconductivity were discussed at length in previous sections. However, none of the predicted materials matches pure hydrogen as a candidate for room temperature superconductivity – Fig. 9. Pure hydrogen remains in the focus of current research, and quite remarkable progress in bringing hydrogen to nearly 400 GPa has been reported recently (89-94).

Fig.9. The highest T_c reached so far in a mercury based cuprate is 164 K at 30 GPa (95). T_c 's close to room temperature were predicted for CaF_6 at 150 GPa, and T_c 's well above room temperature are expected in metallic hydrogen (atomic form) (49). Recent claim of superconducting hydrogen sulfide (87) may change the record of the T_c to 190 K, if confirmed.

Conducting hydrogen has been claimed by Eremets and Troyan (96), however, this work has received a serious criticism (97). If this experiment will stand the test of time, it has reported semimetallic, poorly conducting molecular phase of hydrogen (97). It should be noted here that high T_c 's were also predicted in metallic molecular forms of hydrogen - see (98, 99) and references therein.

Apparently, room temperature superconducting atomic hydrogen (49) is still on the radar for experimentalists. Experimental challenges are significant, but the task of

reaching the immense pressures required to metalize hydrogen may be facilitated by recently developed double-stage diamond anvil technique (100). A combination of such technique with precise photolithography or Focused Ion Beam (FIB) techniques (101) may help to manufacture tiny electrical leads in a double-stage diamond anvil cell (DAC) and to probe metallization of hydrogen above 400 GPa.

New predicted polyhydrides (section 3) also hold a great promise to have high critical superconducting temperatures. However, predicted high T_c values should be carefully checked both by experiment and by more accurate calculations taking account of anharmonic effects. In view of recently reported superconductivity with $T_c \sim 190$ K in hydrogen sulfide (87), the “hole doped” hydrogen in combination with chalcogens or pnictides, or both, is a promising chemical route to new high- T_c superconducting materials.

5. Appendix: Properties of the superconducting state of hydrides

Table 1. The properties of hydride materials available in the literature, such as critical fields (H_{c1} and H_{c2}), pressure effect on the T_c , superconducting gap, isotope effects, and other available information, are listed along with the references to original publications. The information available for metal hydrides is limited due to difficulties in growing stoichiometric samples. This may also explain a large scatter in experimentally measured parameters. The information for PdH(D) and ThH(D) is dominant due to the large interest to the inverse isotope effect in these hydrides and their enhanced T_c values.

It should be also noted that hydrides of many transition and rare earth metals have been studied but no superconductivity has been found in them – see e. g. Refs. (30), (102)

for a list of such hydrides. Many examples are also given (30) showing that small amounts of hydrogen dissolved in a superconducting metal usually suppress its T_c .

Hydride	$T_c(K)$	Properties of the superconducting state	Reference
H ₂ S	30-150	P from 110 GPa to 200 GPa	(87), (103), (88)
D ₂ S	20-50	P from 100 GPa to 175 GPa	
H _x S	160-190	P from 150 to 200 GPa , possible x=3	
D _x S	90	P=170 GPa	
H ₂ S	60	$H_{c2}= 25$ T	
H _x S	185	$H_{c2}= 72$ T	
SiH ₄	17.5	at P~100 GPa	(18)
PdH _{0.97}	8.3	$H_{c2}= 1.7$ T	(104)
PdH _{0.97}	6.6	$H_{c2}= 0.18$ T	(105)
PdH _{0.996}	10.4	$H_{c2}= 0.09$ T	(106)
PdH _x	3.4 3.6 4.2 5.5 6.2 7.7	$H_{c2}(T)$ dH_{c2}/dT (T/K) $\rho_n(10^{-5} \Omega \text{ cm})$ 0.219 0.0645 1.23 0.238 0.0660 1.27 0.252 0.0600 1.04 0.250 0.0455 0.85 0.218 0.0350 0.61 0.243 0.0315 0.60 ρ_n - residual resistance	(107)
PdD _{0.9}	5.5	$2\Delta_0/k_B T_c = 3.6$	(108)
PdH _x	4.6	$2\Delta_0/k_B T_c = 3.8$	(109)
PdH _x	4.6	$2\Delta_0/k_B T_c = 2.6$	(110)
PdH	8.8	$d\ln T_c/dP = -6.8 \cdot 10^{-3} \text{ kbar}^{-1}$	(111)
PdD	11.05	$d\ln T_c/dP = -5.0 \cdot 10^{-3} \text{ kbar}^{-1}$	
Th ₄ H ₁₅	8.3	$H_{c2}= 2.5-3.0$ T	(31)
Th ₄ D ₁₅	8.3	$H_{c2}= 2.5-3.0$ T	
Th ₄ H ₁₅	7.62	$d\ln T_c/dP = 5.5 \cdot 10^{-3} \text{ kbar}^{-1}$	(112)
Th ₄ H ₁₅	7.9	$2\Delta_0/k_B T_c = 3.42$	(113)
Th ₄ D ₁₅	7.9	$2\Delta_0/k_B T_c = 3.47$	
Th ₄ H ₁₅	7.97	$\Theta_D = 211.5$ K, $\gamma = 8.07 \text{ mJ} \cdot \text{K}^{-2}/\text{mole Th}$	(113)
Th ₄ D ₁₅	8.00	$\Theta_D = 216.5$ K, $\gamma = 7.84 \text{ mJ} \cdot \text{K}^{-2}/\text{mole Th}$	
MoH _{1.27}	0.92	$H_c = 60$ mT	(114)
MoD _{1.26}	1.4	$H_c = 30$ mT	

Acknowledgements

This work was supported by Carnegie Institution for Science, and DOE BES under contracts DE-FG02-02ER45955 and DE-FG02-99ER45775. The author benefited from numerous discussions with W. Grochala, and D. Y. Kim, and M. Somayazulu.

References

1. A. Janotti, C. G. Van de Walle, Hydrogen multicentre bonds. *Nat Mater* **6**, 44-47 (2007); published online Epub01/print (http://www.nature.com/nmat/journal/v6/n1/supinfo/nmat1795_S1.html).
2. S. Hammes-Schiffer, Comparison of Hydride, Hydrogen Atom, and Proton-Coupled Electron Transfer Reactions. *ChemPhysChem* **3**, 33-42 (2002)10.1002/1439-7641(20020118)3:1<33::AID-CPHC33>3.0.CO;2-6).
3. R. G. Pearson, The transition-metal-hydrogen bond. *Chemical Reviews* **85**, 41-49 (1985); published online Epub1985/02/01 (10.1021/cr00065a002).
4. J. Bardeen, L. N. Cooper, J. R. Schrieffer, Theory of Superconductivity. *Phys. Rev.* **108**, 1175-1204 (1957).
5. N. W. Ashcroft, Metallic Hydrogen: A High-Temperature Superconductor? *Physical Review Letters* **21**, 1748-1749 (1968).
6. N. W. Ashcroft, Hydrogen Dominant Metallic Alloys: High Temperature Superconductors? *Phys. Rev. Lett.* **92**, 187002 (2004).
7. B. Stritzker, High superconducting transition temperatures in the palladium-noble metal-hydrogen system. *Z. Physik* **268**, 261-264 (1974); published online Epub1974/06/01 (10.1007/BF01669889).
8. A. Leiberich, W. Scholz, W. J. Standish, C. G. Homan, Superconductivity in H-charged Cu-implanted Pd. *Physics Letters A* **87**, 57-60 (1981); published online Epub12/21/ ([http://dx.doi.org/10.1016/0375-9601\(81\)90615-0](http://dx.doi.org/10.1016/0375-9601(81)90615-0)).
9. T. Skoskiewicz, A. W. Szafranski, W. Bujnowski, B. Baranowski, Isotope effect in the superconducting palladium-hydrogen-deuterium system. *Journal of Physics C: Solid State Physics* **7**, 2670 (1974).
10. P. Tripodi, D. Di Gioacchino, R. Borelli, J. D. Vinko, Possibility of high temperature superconducting phases in PdH. *Physica C: Superconductivity* **388–389**, 571-572 (2003); published online Epub5// ([http://dx.doi.org/10.1016/S0921-4534\(02\)02745-4](http://dx.doi.org/10.1016/S0921-4534(02)02745-4)).
11. W. Grochala, P. P. Edwards, Thermal Decomposition of the Non-Interstitial Hydrides for the Storage and Production of Hydrogen. *Chemical Reviews* **104**, 1283-1316 (2004); published online Epub2004/03/01 (10.1021/cr030691s).
12. V. V. Struzhkin, B. Militzer, W. L. Mao, H.-k. Mao, R. J. Hemley, Hydrogen Storage in Molecular Clathrates. *Chemical Reviews* **107**, 4133-4151 (2007); published online Epub2007/10/01 (10.1021/cr050183d).
13. J. Goldsmith, A. G. Wong-Foy, M. J. Cafarella, D. J. Siegel, Theoretical Limits of Hydrogen Storage in Metal–Organic Frameworks: Opportunities and Trade-Offs. *Chemistry of Materials* **25**, 3373-3382 (2013); published online Epub2013/08/27 (10.1021/cm401978e).
14. Z. Yang, Y. Xia, R. Mokaya, Enhanced Hydrogen Storage Capacity of High Surface Area Zeolite-like Carbon Materials. *Journal of the American Chemical Society* **129**, 1673-1679 (2007); published online Epub2007/02/01 (10.1021/ja067149g).

15. J. Yang, A. Sudik, C. Wolverton, D. J. Siegel, High capacity hydrogen storage materials: attributes for automotive applications and techniques for materials discovery. *Chemical Society Reviews* **39**, 656-675 (2010)10.1039/B802882F).
16. E. Babaev, A. Sudbø, N. W. Ashcroft, A superconductor to superfluid phase transition in liquid metallic hydrogen. *Nature* **431**, 666-668 (2004).
17. E. G. Brovman, Y. Kagan, A. Kholas, Structure of Metallic Hydrogen at Zero Pressure. *Sov. Phys. JETP* **34**, 1300-1315 (1972).
18. M. I. Eremets, I. A. Trojan, S. A. Medvedev, J. S. Tse, Y. Yao, Superconductivity in Hydrogen Dominant Materials: Silane. *Science* **319**, 1506-1509 (2008); published online EpubMarch 14, 2008 (10.1126/science.1153282).
19. E. Zurek, R. Hoffmann, N. W. Ashcroft, A. R. Oganov, A. O. Lyakhov, A little bit of lithium does a lot for hydrogen. *Proceedings of the National Academy of Sciences* **106**, 17640-17643 (2009); published online EpubOctober 20, 2009 (10.1073/pnas.0908262106).
20. J. P. Chris, R. J. Needs, Ab initio random structure searching. *Journal of Physics: Condensed Matter* **23**, 053201 (2011).
21. J. M. McMahon, D. M. Ceperley, Ground-State Structures of Atomic Metallic Hydrogen. *Physical Review Letters* **106**, 165302 (2011).
22. P. Baettig, E. Zurek, Pressure-Stabilized Sodium Polyhydrides: $\text{NaH}_{\{n\}}$ ($n \geq 1$). *Physical Review Letters* **106**, 237002 (2011).
23. J. Hooper, E. Zurek, High Pressure Potassium Polyhydrides: A Chemical Perspective. *The Journal of Physical Chemistry C* **116**, 13322-13328 (2012); published online Epub2012/06/21 (10.1021/jp303024h).
24. J. Hooper, B. Altintas, A. Shamp, E. Zurek, Polyhydrides of the Alkaline Earth Metals: A Look at the Extremes under Pressure. *The Journal of Physical Chemistry C* **117**, 2982-2992 (2013); published online Epub2013/02/14 (10.1021/jp311571n).
25. A. Shamp, J. Hooper, E. Zurek, Compressed Cesium Polyhydrides: Cs^+ Sublattices and H_3^- Three-Connected Nets. *Inorganic Chemistry* **51**, 9333-9342 (2012); published online Epub2012/09/03 (10.1021/ic301045v).
26. W. L. McMillan, Transition temperature of strong-coupled superconductors. *Phys. Rev.* **167**, 331-344 (1968).
27. P. B. Allen, R. C. Dynes, Transition temperature of strong-coupled superconductors reanalyzed. *Physical Review B* **12**, 905-922 (1975); published online Epub08/01/ (
28. P. Morel, P. W. Anderson, Calculation of the Superconducting State Parameters with Retarded Electron-Phonon Interaction. *Physical Review* **125**, 1263-1271 (1962); published online Epub02/15/ (
29. B. Mitrović, J. P. Carbotte, Functional derivative $\delta T_c / \delta \alpha^2(\Omega) F(\Omega)$ for weak coupling superconductors. *Solid State Communications* **37**, 1009-1013 (1981); published online Epub3// ([http://dx.doi.org/10.1016/0038-1098\(81\)91206-0](http://dx.doi.org/10.1016/0038-1098(81)91206-0)).
30. B. Stritzker, H. Wühl, in *Hydrogen in Metals II*, G. Alefeld, J. Völkl, Eds. (Springer Berlin Heidelberg, 1978), vol. 29, chap. 6, pp. 243-272.
31. C. B. Satterthwaite, I. L. Toepke, Superconductivity of Hydrides and Deuterides of Thorium. *Physical Review Letters* **25**, 741-743 (1970); published online Epub09/14/ (

32. T. Skoskiewicz, Superconductivity in the palladium-hydrogen and palladium-nickel-hydrogen systems. *physica status solidi (a)* **11**, K123-K126 (1972)10.1002/pssa.2210110253).
33. B. N. Ganguly, Anharmonicity and superconductivity in metal hydrides. I. Formulation. *Physical Review B* **14**, 3848-3852 (1976).
34. B. M. Klein, E. N. Economou, D. A. Papaconstantopoulos, Inverse Isotope Effect and the x Dependence of the Superconducting Transition Temperature in PdH_x and PdD_x. *Physical Review Letters* **39**, 574-577 (1977); published online Epub08/29/ (
35. J. P. Burger, Electron-phonon coupling and superconductivity in metal-hydrogen systems. *Journal of the Less Common Metals* **101**, 53-67 (1984); published online Epub8// ([http://dx.doi.org/10.1016/0022-5088\(84\)90087-0](http://dx.doi.org/10.1016/0022-5088(84)90087-0)).
36. P. M. Laufer, D. A. Papaconstantopoulos, Theory of superconductivity in palladium<i>—</i>noble-metal hydrides. *Physical Review B* **33**, 5134-5137 (1986); published online Epub04/01/ (
37. I. Errea, M. Calandra, F. Mauri, First-Principles Theory of Anharmonicity and the Inverse Isotope Effect in Superconducting Palladium-Hydride Compounds. *Physical Review Letters* **111**, 177002 (2013); published online Epub10/25/ (
38. D. Y. Kim, R. H. Scheicher, H.-k. Mao, T. W. Kang, R. Ahuja, General trend for pressurized superconducting hydrogen-dense materials. *Proceedings of the National Academy of Sciences* **107**, 2793-2796 (2010); published online EpubFebruary 16, 2010 (10.1073/pnas.0914462107).
39. D. Y. Kim, R. H. Scheicher, C. J. Pickard, R. J. Needs, R. Ahuja, Predicted Formation of Superconducting Platinum-Hydride Crystals under Pressure in the Presence of Molecular Hydrogen. *Physical Review Letters* **107**, 117002 (2011).
40. A. Rahman, K. Sköld, C. Pelizzari, S. K. Sinha, H. Flotow, Phonon spectra of nonstoichiometric palladium hydrides. *Physical Review B* **14**, 3630-3634 (1976); published online Epub10/15/ (
41. B. M. Klein, R. E. Cohen, Anharmonicity and the inverse isotope effect in the palladium-hydrogen system. *Physical Review B* **45**, 12405-12414 (1992); published online Epub06/01/ (
42. J. P. Carbotte, F. Marsiglio, in *The Physics of Superconductors*, K. H. Bennemann, J. B. Ketterson, Eds. (Springer Berlin Heidelberg, 2003), chap. 4, pp. 233-345.
43. B. Rousseau, A. Bergara, Giant anharmonicity suppresses superconductivity in AlH₃ under pressure. *Physical Review B* **82**, 104504 (2010); published online Epub09/07/ (
44. I. Goncharenko, M. I. Erements, M. Hanfland, J. S. Tse, M. Amboage, Y. Yao, I. A. Trojan, Pressure-Induced Hydrogen-Dominant Metallic State in Aluminum Hydride. *Physical Review Letters* **100**, 045504 (2008); published online Epub01/29/ (
45. I. Errea, M. Calandra, F. Mauri, Anharmonic free energies and phonon dispersions from the stochastic self-consistent harmonic approximation: Application to platinum and palladium hydrides. *Physical Review B* **89**, 064302 (2014); published online Epub02/10/ (

46. I. Errea, M. Calandra, F. Mauri, Huge anharmonic effects in superconducting hydrides and transition metal dichalcogenides. *physica status solidi (b)*, n/a-n/a (2014)10.1002/pssb.201451164).
47. I. Errea, B. Rousseau, A. Bergara, Enhanced Anharmonicity Under Pressure. *Journal of Physics: Conference Series* **377**, 012060 (2012).
48. E. Wigner, H. B. Huntington, On the Possibility of a Metallic Modification of Hydrogen. *J. Chem. Phys.* **3**, 764-770 (1935).
49. J. M. McMahon, D. M. Ceperley, High-temperature superconductivity in atomic metallic hydrogen. *Physical Review B* **84**, 144515 (2011); published online Epub10/17/ (
50. A. W. Overhauser, Crystal structure of lithium beryllium hydride. *Physical Review B* **35**, 411-414 (1987); published online Epub01/01/ (
51. X.-J. Chen, C. Zhang, Y. Meng, R.-Q. Zhang, H.-Q. Lin, V. V. Struzhkin, H.-k. Mao, β -tin $\rightarrow$ Imma $\rightarrow$ sh Phase Transitions of Germanium. *Physical Review Letters* **106**, 135502 (2011); published online Epub03/30/ (
52. G. Gao, A. R. Oganov, A. Bergara, M. Martinez-Canales, T. Cui, T. Iitaka, Y. Ma, G. Zou, Superconducting High Pressure Phase of Germane. *Physical Review Letters* **101**, 107002 (2008).
53. X.-J. Chen, J.-L. Wang, V. V. Struzhkin, H.-k. Mao, R. J. Hemley, H.-Q. Lin, Superconducting Behavior in Compressed Solid SiH₄ with a Layered Structure. *Physical Review Letters* **101**, 077002 (2008).
54. C. J. Pickard, R. J. Needs, High-Pressure Phases of Silane. *Physical Review Letters* **97**, 045504 (2006); published online Epub07/27/ (
55. J. Feng, W. Grochala, T. Jaroń, R. Hoffmann, A. Bergara, N. W. Ashcroft, Structures and Potential Superconductivity in SiH₄ at High Pressure: En Route to “Metallic Hydrogen”. *Physical Review Letters* **96**, 017006 (2006); published online Epub01/11/ (
56. Y. Yao, J. S. Tse, Y. Ma, K. Tanaka, Superconductivity in high-pressure SiH₄. *EPL (Europhysics Letters)* **78**, 37003 (2007).
57. X.-J. Chen, V. V. Struzhkin, Y. Song, A. F. Goncharov, M. Ahart, Z. Liu, H.-k. Mao, R. J. Hemley, Pressure-induced metallization of silane. *Proceedings of the National Academy of Sciences* **105**, 20-23 (2008).
58. D. Y. Kim, R. H. Scheicher, S. Lebègue, J. Prasongkit, B. Arnaud, M. Alouani, R. Ahuja, Crystal structure of the pressure-induced metallic phase of SiH₄ from ab initio theory. *Proceedings of the National Academy of Sciences* **105**, 16454-16459 (2008); published online EpubOctober 28, 2008 (10.1073/pnas.0804148105).
59. M. Martinez-Canales, A. R. Oganov, Y. Ma, Y. Yan, A. O. Lyakhov, A. Bergara, Novel Structures and Superconductivity of Silane under Pressure. *Physical Review Letters* **102**, 087005 (2009).
60. G. Gao, A. R. Oganov, P. Li, Z. Li, H. Wang, T. Cui, Y. Ma, A. Bergara, A. O. Lyakhov, T. Iitaka, G. Zou, High-pressure crystal structures and superconductivity of Stannane (SnH₄). *Proceedings of the National Academy of Sciences* **107**, 1317-1320 (2010); published online EpubJanuary 26, 2010 (10.1073/pnas.0908342107).

61. O. Degtyareva, M. M. Canales, A. Bergara, X.-J. Chen, Y. Song, V. V. Struzhkin, H.-k. Mao, R. J. Hemley, Crystal structure of SiH₄ at high pressure. *Physical Review B* **76**, 064123 (2007); published online Epub08/31/ (
62. O. Degtyareva, J. E. Proctor, C. L. Guillaume, E. Gregoryanz, M. Hanfland, Formation of transition metal hydrides at high pressures. *Solid State Communications* **149**, 1583-1586 (2009); published online Epub10// (<http://dx.doi.org/10.1016/j.ssc.2009.07.022>).
63. M. Hanfland, J. E. Proctor, C. L. Guillaume, O. Degtyareva, E. Gregoryanz, High-Pressure Synthesis, Amorphization, and Decomposition of Silane. *Physical Review Letters* **106**, 095503 (2011); published online Epub03/02/ (
64. T. A. Strobel, A. F. Goncharov, C. T. Seagle, Z. Liu, M. Somayazulu, V. V. Struzhkin, R. J. Hemley, High-pressure study of silane to 150 GPa. *Physical Review B* **83**, 144102 (2011).
65. T. Muramatsu, V. V. Struzhkin, *unpublished*.
66. Y. Yao, D. D. Klug, Silane plus molecular hydrogen as a possible pathway to metallic hydrogen. *Proceedings of the National Academy of Sciences* **107**, 20893-20898 (2010); published online EpubDecember 7, 2010 (10.1073/pnas.1006508107).
67. X. Jin, X. Meng, Z. He, Y. Ma, B. Liu, T. Cui, G. Zou, H.-k. Mao, Superconducting high-pressure phases of disilane. *Proceedings of the National Academy of Sciences* **107**, 9969-9973 (2010).
68. Y. Li, G. Gao, Y. Xie, Y. Ma, T. Cui, G. Zou, Superconductivity at ~100 K in dense SiH₄(H₂)₂ predicted by first principles. *Proceedings of the National Academy of Sciences* **107**, 15708-15711 (2010); published online EpubSeptember 7, 2010 (10.1073/pnas.1007354107).
69. J. A. Flores-Livas, M. Amsler, T. J. Lenosky, L. Lehtovaara, S. Botti, M. A. L. Marques, S. Goedecker, High-Pressure Structures of Disilane and Their Superconducting Properties. *Physical Review Letters* **108**, 117004 (2012).
70. P. Zaleski-Ejgierd, R. Hoffmann, N. W. Ashcroft, High Pressure Stabilization and Emergent Forms of PbH₄. *Physical Review Letters* **107**, 037002 (2011); published online Epub07/11/ (
71. J. Hooper, E. Zurek, Rubidium Polyhydrides Under Pressure: Emergence of the Linear H₃⁻ Species. *Chemistry – A European Journal* **18**, 5013-5021 (2012)10.1002/chem.201103205).
72. H. Wang, J. S. Tse, K. Tanaka, T. Iitaka, Y. Ma, Superconductive sodalite-like clathrate calcium hydride at high pressures. *Proceedings of the National Academy of Sciences* **109**, 6463-6466 (2012).
73. D. C. Lonie, J. Hooper, B. Altintas, E. Zurek, Metallization of magnesium polyhydrides under pressure. *Physical Review B* **87**, 054107 (2013).
74. C. A. Coulson, The electronic structure of H₃⁺ *Proc. Camb. Phil. Soc.* **31**, 244-259 (1935).
75. W. Grochala, R. Hoffmann, J. Feng, N. W. Ashcroft, The Chemical Imagination at Work in Very Tight Places. *Angewandte Chemie International Edition* **46**, 3620-3642 (2007)10.1002/anie.200602485).

76. M. Ayouz, O. Dulieu, R. Guérout, J. Robert, V. Kokoouline, Potential energy and dipole moment surfaces of H₃⁻ molecule. *The Journal of Chemical Physics* **132**, - (2010)doi:<http://dx.doi.org/10.1063/1.3424847>.
77. F. Maseras, A. Lledós, E. Clot, O. Eisenstein, Transition Metal Polyhydrides: From Qualitative Ideas to Reliable Computational Studies†. *Chemical Reviews* **100**, 601-636 (2000); published online Epub2000/02/01 (10.1021/cr980397d).
78. W. Wang, A. K. Belyaev, Y. Xu, A. Zhu, C. Xiao, X.-F. Yang, Observations of H₃⁻ and D₃⁻ from dielectric barrier discharge plasmas. *Chemical Physics Letters* **377**, 512-518 (2003); published online Epub8/22/ ([http://dx.doi.org/10.1016/S0009-2614\(03\)01210-7](http://dx.doi.org/10.1016/S0009-2614(03)01210-7)).
79. D. A. Mazziotti, Large-Scale Semidefinite Programming for Many-Electron Quantum Mechanics. *Physical Review Letters* **106**, 083001 (2011); published online Epub02/23/ (
80. L. Stella, C. Attaccalite, S. Sorella, A. Rubio, Strong electronic correlation in the hydrogen chain: A variational Monte Carlo study. *Physical Review B* **84**, 245117 (2011); published online Epub12/14/ (
81. S. J. Grabowski, R. Hoffmann, Stabilizing H₃⁻: Or Are We Stabilizing a Proton? *ChemPhysChem* **13**, 2286-2288 (2012)10.1002/cphc.201200182).
82. M. Somayazulu, P. Dera, A. F. Goncharov, S. A. Gramsch, P. Liermann, W. Yang, Z. Liu, H.-k. Mao, R. J. Hemley, Pressure-induced bonding and compound formation in xenon–hydrogen solids. *Nat Chem* **2**, 50-53 (2010)<http://www.nature.com/nchem/journal/v2/n1/abs/nchem.445.html - supplementary-information>).
83. Z. G. Bazhanova, O. A. R., G. O., Fe–C and Fe–H systems at pressures of the Earth's inner core. *Physics-Uspekhi* **55**, 489 (2012).
84. T. Scheler, M. Marqués, Z. Konôpková, C. L. Guillaume, R. T. Howie, E. Gregoryanz, High-Pressure Synthesis and Characterization of Iridium Trihydride. *Physical Review Letters* **111**, 215503 (2013); published online Epub11/19/ (
85. R. T. Howie, O. Narygina, C. L. Guillaume, S. Evans, E. Gregoryanz, High-pressure synthesis of lithium hydride. *Physical Review B* **86**, 064108 (2012); published online Epub08/16/ (
86. V. V. Struzhkin, D.-Y. Kim, E. Stavrou, T. Muramatsu, H.-k. Mao, C. J. Pickard, R. J. Needs, V. B. Prakapenka, A. F. Goncharov, Synthesis of Sodium Polyhydrides at High Pressures. *eprint arXiv:1412.1542*, (2014).
87. A. P. Drozdov, M. I. Erements, I. A. Troyan, Conventional superconductivity at 190 K at high pressures. *arXiv:1412.0460 [cond-mat.supr-con]*, (2014).
88. D. Duan, Y. Liu, F. Tian, D. Li, X. Huang, Z. Zhao, H. Yu, B. Liu, W. Tian, T. Cui, Pressure-induced metallization of dense (H₂S)₂H₂ with high-T_c superconductivity. *Sci. Rep.* **4**, (2014); published online Epub11/10/online (10.1038/srep06968 <http://www.nature.com/srep/2014/141110/srep06968/abs/srep06968.html - supplementary-information>).
89. R. T. Howie, C. L. Guillaume, T. Scheler, A. F. Goncharov, E. Gregoryanz, Mixed Molecular and Atomic Phase of Dense Hydrogen. *Physical Review Letters* **108**, 125501 (2012); published online Epub03/19/ (

90. A. F. Goncharov, J. S. Tse, H. Wang, J. Yang, V. V. Struzhkin, R. T. Howie, E. Gregoryanz, Bonding, structures, and band gap closure of hydrogen at high pressures. *Physical Review B* **87**, 024101 (2013); published online Epub01/02/ (
91. C.-s. Zha, Z. Liu, M. Ahart, R. Boehler, R. J. Hemley, High-Pressure Measurements of Hydrogen Phase IV Using Synchrotron Infrared Spectroscopy. *Physical Review Letters* **110**, 217402 (2013); published online Epub05/21/ (
92. R. T. Howie, T. Scheler, C. L. Guillaume, E. Gregoryanz, Proton tunneling in phase IV of hydrogen and deuterium. *Physical Review B* **86**, 214104 (2012); published online Epub12/10/ (
93. R. T. Howie, I. B. Magdu, A. F. Goncharov, G. J. Ackland, E. Gregoryanz, Phonon Localization by Mass Disorder in Dense Hydrogen-Deuterium Binary Alloy. *Physical Review Letters* **113**, 175501 (2014); published online Epub10/21/ (
94. C.-s. Zha, R. E. Cohen, H.-k. Mao, R. J. Hemley, Raman measurements of phase transitions in dense solid hydrogen and deuterium to 325 GPa. *Proceedings of the National Academy of Sciences* **111**, 4792-4797 (2014); published online EpubApril 1, 2014 (10.1073/pnas.1402737111).
95. L. Gao, Y. Y. Xue, F. Chen, Q. Xiong, R. L. Meng, D. Ramirez, C. W. Chu, J. H. Eggert, H. K. Mao, Superconductivity up to 164 K in $\text{HaBa}_2\text{Cam-1Cu}_m\text{O}_{2m+2+d}$ ($m=1,2$, and 3) under quasihydrostatic pressures. *Phys. Rev. B* **50**, 4260-4263 (1994).
96. M. I. Eremets, I. A. Troyan, Conductive dense hydrogen. *Nat Mater* **10**, 927-931 (2011); published online Epub12//print (<http://www.nature.com/nmat/journal/v10/n12/abs/nmat3175.html> - [supplementary-information](#)).
97. W. Nellis, I. Silvera, Has Metallic Hydrogen Been Made in a Diamond Anvil Cell? *arXiv.org > cond-mat > arXiv:1201.0407*, (2013).
98. P. Cudazzo, G. Profeta, A. Sanna, A. Floris, A. Continenza, S. Massidda, E. K. U. Gross, Electron-phonon interaction and superconductivity in metallic molecular hydrogen. I. Electronic and dynamical properties under pressure. *Physical Review B* **81**, 134505 (2010); published online Epub04/02/ (
99. P. Cudazzo, G. Profeta, A. Sanna, A. Floris, A. Continenza, S. Massidda, E. K. U. Gross, Electron-phonon interaction and superconductivity in metallic molecular hydrogen. II. Superconductivity under pressure. *Physical Review B* **81**, 134506 (2010); published online Epub04/02/ (
100. L. Dubrovinsky, N. Dubrovinskaia, V. B. Prakapenka, A. M. Abakumov, Implementation of micro-ball nanodiamond anvils for high-pressure studies above 6[thinsp]Mbar. *Nat Commun* **3**, 1163 (2012)http://www.nature.com/ncomms/journal/v3/n10/supinfo/ncomms2160_S1.html).
101. C. R. Rotundu, T. uk, R. L. Greene, Z.-X. Shen, R. J. Hemley, V. V. Struzhkin, High-pressure resistivity technique for quasi-hydrostatic compression experiments. *Review of Scientific Instruments* **84**, - (2013)doi:<http://dx.doi.org/10.1063/1.4809025>).
102. V. E. Antonov, T. E. Antonova, I. T. Belash, V. I. Rashupkin, Superconductivities of high-pressure phases in the metal-hydrogen systems. *High Pressure Research*

- 1, 315-320 (1989); published online Epub1989/11/01 (10.1080/08957958908202487).
103. Y. Li, J. Hao, H. Liu, Y. Li, Y. Ma, The metallization and superconductivity of dense hydrogen sulfide. *The Journal of Chemical Physics* **140**, - (2014)doi:<http://dx.doi.org/10.1063/1.4874158>.
104. D. R. Krahn, R. L. Henry, D. B. Tanner, P. E. Wigen, The critical fields of superconducting palladium hydride. *physica status solidi (a)* **46**, 209-212 (1978)10.1002/pssa.2210460125).
105. T. Skośkiewicz, Superconductivity in the palladium-hydrogen system. *physica status solidi (b)* **59**, 329-334 (1973)10.1002/pssb.2220590133).
106. D. S. McLachlan, T. B. Doyle, J. P. Burger, The superconducting properties of $\text{PdH}_{x \leq 1}$. *J Low Temp Phys* **26**, 589-601 (1977); published online Epub1977/02/01 (10.1007/BF00655432).
107. N. E. Alekseevskii, Y. A. Samarskii, H. Wolf, V. I. Tserbo, V. M. Zakosarenko, Critical magnetic fields of superconducting palladium hydride. *JETP Lett.* **19**, 676-679 (1974).
108. A. Eichler, H. Wühl, B. Stritzker, Tunneling experiments on superconducting palladium-deuterium alloys. *Solid State Communications* **17**, 213-216 (1975); published online Epub7/15/ ([http://dx.doi.org/10.1016/0038-1098\(75\)90045-9](http://dx.doi.org/10.1016/0038-1098(75)90045-9)).
109. P. J. Silverman, C. V. Briscoe, Superconducting tunneling in PdH. *Physics Letters A* **53**, 221-222 (1975); published online Epub6/16/ ([http://dx.doi.org/10.1016/0375-9601\(75\)90414-4](http://dx.doi.org/10.1016/0375-9601(75)90414-4)).
110. J. Igalson, L. Sniadower, A. J. Pindor, T. Skoskiewicz, K. Blüthner, F. Dettmann, Tunneling observation of the superconducting energy gap in the palladium hydride thin films. *Solid State Communications* **17**, 309-312 (1975); published online Epub8/1/ ([http://dx.doi.org/10.1016/0038-1098\(75\)90300-2](http://dx.doi.org/10.1016/0038-1098(75)90300-2)).
111. H. Hemmes, A. Driessen, R. Griessen, M. Gupta, Isotope effects and pressure dependence of the T_c of superconducting stoichiometric PdH and PdD synthesized and measured in a diamond anvil cell. *Physical Review B* **39**, 4110-4118 (1989); published online Epub03/01/ (
112. M. Dietrich, W. Gey, H. Rietschel, C. B. Satterthwaite, Pressure dependence of the superconducting transition temperature of Th_4H_{15} . *Solid State Communications* **15**, 941-943 (1974); published online Epub9/1/ ([http://dx.doi.org/10.1016/0038-1098\(74\)90699-1](http://dx.doi.org/10.1016/0038-1098(74)90699-1)).
113. J. F. Miller, R. H. Caton, C. B. Satterthwaite, Low-temperature heat capacity of normal and superconducting thorium hydride and thorium deuteride. *Physical Review B* **14**, 2795-2800 (1976); published online Epub10/01/ (
114. V. E. Antonov, I. T. Belash, O. V. Zharikov, A. I. Latynin, A. V. Pal'nichenko, Superconductivity of molybdenum hydride and deuteride. *Fizika Tverdogo Tela (in Russian)* **30**, 598-600 (1988).