Ultrasensitive non-enzymatic glucose sensors based on different copper oxide nanostructures by in-situ growth

Yan Zhong¹, Tielin Shi^{1,2}, Zhiyong Liu¹, Siyi Cheng¹, Yuanyuan Huang¹, Xiangxu Tao¹, Guanglan Liao^{1,2}, and Zirong Tang^{1,2}

¹ State Key Laboratory of Digital Manufacturing Equipment and Technology, Huazhong University of Science and Technology, Wuhan 430074, People's Republic of China

² Wuhan National Laboratory for Optoelectronics, Huazhong University of Science and Technology, Wuhan 430074, People's Republic of China

E-mail: zirong@hust.edu.cn

Abstract

Different nanostructures of copper oxide (CuO) by in-situ growth on carbon clothes (CC) are prepared to develop ultrasensitive non-enzymatic glucose sensors. The electrochemical performance of the CuO-based electrodes for detecting glucose has been investigated by cyclic voltammetry (CV) and chronoamperometry. The CuO nanosheets (CuO NSs)/CC electrode demonstrates a high sensitivity of $4902 \mu\text{A mM}^{-1} \text{cm}^{-2}$ at an applied potential of 0.55 V (vs. Ag/AgCl/ 3M KCl) in alkaline solution, and it shows $2973 \mu\text{A mM}^{-1} \text{cm}^{-2}$ and $1246 \mu\text{A mM}^{-1} \text{cm}^{-2}$ for the CuO nanowires (CuO NWs)/CC and CuO nanoparticles (CuO NPs)/CC, respectively. Ascribing to high conductivity of CC, high specific surface-area from CuO nanostructures, and facilitated charge transfer through in-situ grown structure, the electrodes demonstrate ultrasensitive, selective, stable and fast amperometric sensing ($<3 \text{ s}$) of glucose, which presents a new strategy to develop non-enzymatic glucose sensors.

Keywords: Copper oxide nanostructures; in-situ growth; glucose; non-enzymatic biosensor.

1. Introduction

The development of rapid and reliable methods of monitoring glucose is important in both medical area and food industry. For the past years, various enzymatic sensors that immobilize enzymes to perform selective recognition and quantitative analyses have been studied due to their good selectivity and high sensitivity [1, 2]. However, the use of enzymes may limit the application of enzymatic sensors due to their high cost, complicated immobilization procedure along with inherently instability. Recently, much attention has been concentrated on the development of non-enzymatic glucose sensors. One main strategy is based on electrochemical detection with utilization of transition metal oxides, such as CuO [3, 4], Co₃O₄ [5], NiO [6], Fe₂O₃ [7], MnO₂ [8]. Comparing with other methods, such as surface plasmon resonance (SPR) sensors based on optic fiber [9, 10], which involve complicated fabrication process, the electrochemical method attracts more attention due to its simple fabrication process, excellent stability and electro-catalytic performance [11-13].

Among various metal oxides, CuO is a promising material due to its high electrochemical activity, low cost, non-toxic, and it can be easily integrated with other materials. Recently, CuO has been widely studied in supercapacitors [14, 15], lithium ion batteries [16, 17], gas sensors [18, 19] and photo detectors [20]. Different CuO nanostructures for non-enzymatic glucose sensing have also been explored, such as CuO nanoparticles [21], CuO nanocubes [22], CuO nanoneedles [23], CuO nanowires [24], CuO nanoflowers [25], etc. Meanwhile, carbon-based materials (carbon nanotubes (CNTs), graphene) have been integrated to improve the sensitivity and conductivity through forming composite structures such as CuO/CNTs [26], CuO/carbon sphere [27] and CuO/graphene [28]. Nevertheless, the high-cost of graphene and CNTs along with the complicated procedures make it difficult for large-scale fabrication, and the introduction of polymer binders may degrade the device performance.

In-situ growth of CuO micro/nanostructures on conductive substrate can avoid the use of binder and improve the performance [29, 30]. For example, free-standing porous CuO nanowires grown on Cu foils are directly employed in detecting glucose,

which show a remarkably sensitivity of $1420.3 \mu\text{A cm}^{-2} \text{mM}^{-1}$ [31]. But Cu foil is easily poisoned by chloride ions, making it a necessity to find an alternative conductive substrate. Carbon clothes, consisting of bundles of carbon fiber with multiple channels, are emerged recently as a kind of three-dimensional flexible conductive substrate[32-34]. Compared to planar substrate, CC can provide more sites for active substance and enhance the electrochemical catalysis towards glucose[29].

In this work, we develop non-enzymatic sensor based on in-situ growth of CuO nanostructures (CuO NPs, CuO NWs and CuO NSs) on conductive carbon clothes. The effects of CuO nanostructure on the sensing performance such as sensitivity are investigated. As a result, the as-prepared CuO/CC electrodes exhibit high sensitivity and long-term stability, which are promising for practical applications.

2. Experiment

2.1. Chemical Reagent

Sodium hydroxide (NaOH), ammonium persulfate ($\text{NH}_4\text{S}_2\text{O}_8$), glucose, uric acid (UA), L-Ascorbic acid (AA), and Acetaminophen (AP) were obtained from Sigma-Aldrich Chemical Company. The CC (12.5 mg cm^{-2} , 0.32 cm in thickness) was purchased from WOS 1002 CeTech CO., Ltd., China. All other chemicals used in this investigation were of analytical grade. All the solutions were prepared with deionized water (DI) obtained from a Millipore system

2.2. Synthesis

CC were pre-treated in 1M HNO_3 solution for 12 h, and then cleaned under ultra-sonication in acetone, ethanol and DI water, respectively. Next, a layer of copper was sputtered on the CC substrate as a seed layer with a DC current of 5A for 10 minutes. CuO NPs were obtained through calcinations in air at 500°C for 4h. CuO

NWs and CuO NSs were prepared in an alkaline oxidative etchant solution (AOES) containing 30 mM $(\text{NH}_4)_2\text{S}_2\text{O}_8$ and 75 mM NaOH in different temperature[31]. In detail, the CC coated with copper seed layer were first immersed in AOES to grow $\text{Cu}(\text{OH})_2$ NWs at room temperature for about 15 min. The sample was then thermally treated at 200 °C for 2 h to dehydrate $\text{Cu}(\text{OH})_2$ into CuO NWs. While the black CuO NSs on CC was directly obtained by keeping CC with copper seed layer in the AOES at the 50°C water bath for 15 min without annealing.

2.3. Instrumentation

The morphology of the CC and CuO nanostructures was characterized by the field emission scanning electron microscopy (FESEM, JSM-7600F, JEOL). XRD analysis (PANalytical PW3040/60) with Cu $K\alpha$ radiation ($\lambda=1.5406 \text{ \AA}$) from 10° to 80° was carried out to illustrate the structural and crystalline phase of the as-obtained samples. The electrochemical experiments were performed with a CHI660C electrochemical workstation (Autolab PGSTAT302N, Metrohm Autolab, Utrecht, Netherlands). All electrochemical measurements were carried out by a three-electrode system with CC electrode as the working electrode, a Pt wire as the counter electrode, and a $\text{Ag}/\text{AgCl}/3\text{M KCl}$ as the reference electrode. Electrical Impedance Spectroscopy (EIS) measurements were also carried out with the electrochemical station in an electrolyte solution of 100 mM KCl containing 5 mM $[\text{Fe}(\text{CN})_6]^{4-/3-}$, in a frequency range from 0.1 Hz to 10^5 Hz with an ac probe amplitude of 10 mV.

3. Results and discussion

3.1. Structural characterization

Scheme. 1. Schematic illustration of synthesis of CuO nanostructures on CC

The preparation route of the samples was illustrated in Scheme.1. Briefly, CuO NPs were obtained through calcinations in the air at 500°C for 4h. For CuO NWs, CC with copper seed layer was first etched in AOES at room temperature to form Cu(OH)₂ NWs, and then annealed to give the final product of CuO NWs. CuO NSs were directly obtained in AOES at 50°C water bath for 15 minutes.

Fig. 1. SEM images of CC (A), CuO NPs/CC (B), CuO NWs/CC (C), CuO NS/CC (D), each inset was the high-magnification image; (E) XRD pattern of CC, Cu(OH)₂ NWs/ CC, CuO NWs/ CC, CuO NPs/ CC and CuO NSs/ CC

The SEM image and the enlarged view of CC, CuO NPs/CC, CuO NWs/CC and CuO NSs/CC were presented in Fig. 1A to D, respectively. Among the three

nanostuctures, CuO NSs displayed the largest surface area, indicating the most active sites for the adsorption of glucose molecules. As displayed in Fig. 1E, X-ray diffraction (XRD) was used to identify the component. For the CuO NPs and CuO NSs samples, strong diffraction peaks at 35.5° , 38.7° , 48.7° , 58.3° , 61.5° , 66.2° , 67.9° and 75.0° could be assigned to the (11-1), (111), (20-2), (202), (11-3), (31-1), (113), and (311) planes of monoclinic CuO, respectively. Note that the three strong diffraction peaks at 26.4° , 44.4° and 54.5° which were corresponding to the structure of carbon were from the CC substrate. And no diffraction peaks could be attributed to Cu_2O or $\text{Cu}(\text{OH})_2$ for both the samples. For the $\text{Cu}(\text{OH})_2$ NWs sample, diffraction peaks at 16.7° , 23.8° , 33.8° , 35.9° , 38.2° , 39.8° and 53.2° corresponded to the (020), (021), (040), (111), (041), (130) and (150) planes of orthorhombic structured $\text{Cu}(\text{OH})_2$, respectively. The CuO NWs sample gave two faintly recognizable peaks at 35.5° and 38.7° , corresponding to the (11-1) and (111) planes of the monoclinic CuO. And no diffraction peaks of Cu_2O or $\text{Cu}(\text{OH})_2$ for the CuO NWs samples were observed. In conclusion, the XRD results showed that the final samples were all with the purity of the CuO phase, and the samples could be used as non-enzymatic electrodes for glucose sensing.

EIS measurement was also performed to investigate the interfacial charge transfer performance of the electrodes, as shown in Fig. S1. Compared with the bare CC electrode, all the electrodes modified with CuO nanostructures showed smaller semicircle at high frequency, indicating improved charge transfer.

3.2. Electrocatalytic activity of CuO/CC toward glucose oxidation

3.2.1 Cyclic voltammetry measurements

Fig. 2. (A) and (B) CV curves of CC (curve a, e), CuO NPs/CC (curve b, f), CuO NWs/CC (curve c, g) and CuO NSs/CC (curve d, h) electrode in the absence and presence of 2.0 mM glucose in 100mM NaOH respectively. Scan rate: 10 mV s⁻¹. (C) CVs of CuO NS/CC electrode at different scan rates from 5 mV s⁻¹ to 100 mV s⁻¹ in 100mM NaOH with 0.5 mM glucose. (D) Calibration plots of anodic peak current vs. scan rate.

The CV of the pure CC electrode and electrodes modified with different CuO nanostructures was examined via cyclic voltammetry (CV) in 100 mM NaOH solution in the absence and presence of 2.0 mM glucose recorded at a scan rate of 10 mV s⁻¹. As shown in Fig. 2A, in the absence of glucose, there was no oxidation peaks for the pure CC electrode (curve a), CuO NPs/CC electrode (curve b) and the CuO NWs/CC electrode (curve c). The CuO NSs/CC electrode (curve d) showed a small and broad reduction which might correspond to a Cu(II)/Cu(III) redox couple, which was similar to the previous report [35]. The large oxide tail observed over +0.65 V was attributed to the onset of water breakdown. As shown in Fig. 2B, in the presence of 2.0 mM glucose, oxidation peaks was not observed either for the bare CC (curve e). On the other hand, for the CuO-based electrodes (curve f, g, h), a rapid increase in current starting at about +0.35 V was observed, corresponding to the oxidation of glucose, indicating the major role of CuO in the process of oxidation. The explicit mechanism for CuO-catalyzed electro-oxidation of glucose in alkaline had not been completely

clarified, and the generally accepted point suggested the formation of a high valence Cu^{III} intermediate that readily oxidized glucose into gluconic acid[36, 37], which could be described with the following reactions:

The reaction was completely irreversible as confirmed by the absence of a cathodic peak in the CV, which was quite similar to the reports of Yang et al [38, 39]. As shown in Fig. 2B, for the CuO NWs/CC electrode (curve g), an obvious shoulder oxidation peak at around +0.65V was observed, while the CuO NSs/CC electrode (curve h) showed substantially higher current. Furthermore, an obvious 150 mV negative shift in peak potential was observed, indicating a stronger electro-catalytic oxidation towards glucose. Based on the descriptions above, it was implied that CuO NSs/CC electrode had an enhanced electro-catalytic performance comparing with other CuO modified electrodes. It was suggested that surface area was responsible for the phenomena ($\text{CuO NSs} > \text{CuO NWs} > \text{CuO NPs}$).

The effects of different scan rates on the oxidation of glucose at the CuO NSs/CC electrode in 100 mM NaOH in the presence of 0.5 mM glucose were also investigated. As shown in Fig. 2C, the anodic peak current (I_p) increased with the rising of scan rates owing to the oxidation of glucose, and the anodic peak potential shifted to a more positive region (from 0.40 V to 0.70 V) at the same time. As shown in Fig. 2D, I_p vs. scan rate v (from 5 mV s^{-1} to 100 mV s^{-1}) plot was highly linear ($R = 0.995$): $I_p = 0.000618 + 0.10641 v$, indicating a typical surface-controlled process with a fast electron-transfer behavior [8, 40-42], which was ideal for quantitative analysis in practical applications.

3.2.2 Optimization of sensor

Fig. 3. Sensitivity of CuO NSs/CC electrode at different potentials in 100 mM NaOH with a drop addition of 0.1 mM glucose (detection potential: +0.30–0.60 V).

To improve the performance of the sensor, the applied potential influencing the response of the sensor was investigated. The optimal detection potential was determined by a drop addition of 0.1 mM glucose to 100 mM NaOH solution under different potentials for CuO NS/CC electrode. As shown in Fig. 3, the sensitivity was very small at potentials lower than 0.3 V. When the detection potential was increased from 0.4 to 0.6 V, the maximum response was observed at 0.55 V. Therefore, +0.55 V was selected as the optimal detection potential. The effect of NaOH concentration on the response of the sensor was also investigated and shown in Fig. S2. From the plot, 0.10 M NaOH was chosen as the optimal supporting electrolyte in the following measurements.

3.2.3. Amperometric measurements

Fig. 4. (A) I-t curves at +0.55 V with an increasing glucose concentration per 15 s for the CuO NPs/CC (curve a), CuO NWs/CC (curve b) and CuO NSs/CC (curve c) electrode. (B and C) the partly enlarged picture of (A). (D) The current response vs. glucose concentration at the CuO NPs/CC (curve d), CuO NWs/CC (curve e) and CuO NSs/CC (curve f) electrode. The lines indicated the calibration curve.

In order to determine the lower detection limit of the sensors, amperometric measurement was conducted. Fig. 4A displayed the steady-state I-t curves of the CuO NPs/CC (curve a), CuO NWs/CC (curve b) and CuO NSs/CC (curve c) electrode in 100 mM NaOH solution with the successive addition of glucose in the range of 0.005–2.515 mM at a bias of 0.55 V. From the curves, CuO NSs/CC electrode exhibited the highest amperometric response to glucose at different concentrations while CuO NPs/CC electrode displayed the weakest response current, consistent with the electrochemical testing results shown in Fig. 2A. It was suggested the enhanced performance was due to the larger surface area of CuO NSs/CC, which could provide more sites for glucose, ensuring the adsorption of more glucose molecular and producing a higher catalyzing current. For the CuO NSs/CC electrode, the response was linear up to 1 mM with the slope of $9803.92 \mu\text{A mM}^{-1}$ ($4901.96 \mu\text{A mM}^{-1} \text{cm}^{-2}$ in term of geometry area) and the correlation coefficient of 0.986 as shown in Fig. 4D (curve f). As shown in Fig. 4B, the electro-catalytic current increased sharply after the

addition of glucose and reached the steady-state within 3 s, illustrating a fast response. Besides, lower concentration of glucose was injected to explore the detection limit, and a limitation of 1 μM was determined (Fig. S3). As for CuO NWs/CC electrode, the amperometric response was linear up to 1.12 mM (curve b) with the slope of $5946.4 \mu\text{AmM}^{-1}$ ($2973.2 \mu\text{AmM}^{-1}\text{cm}^{-2}$ in term of geometry area) (curve e) while it was 1.22 mM (curve a) and $2491.8 \mu\text{AmM}^{-1}$ ($1245.9 \mu\text{AmM}^{-1}\text{cm}^{-2}$ in term of geometry area) (curve d) for CuO NPs/CC, respectively. Noting that, the curves would reach saturation at a higher glucose concentration. The small drift of baseline was observed after continuous injections of glucose, which may due to the faster consumption of glucose in comparison with its diffusion, the slight variation of local pH, or the adsorption of intermediates on the active sites[41, 43].

The performance of as-fabricated sensors was compared to that of some glucose sensors reported in the literature, as listed in Table1.

Table.1. Composite based non-enzymatic glucose sensors and their detection performances. Measurements were performed using amperometric technique

Electrode matrix	Sensitivity ($\mu\text{AmM}^{-1}\text{cm}^{-2}$)	LOD	Linear range	Applied potential	Reference
CuO NS/CC	4901.96	1 μM	Up to 1 mM	+0.55V	This work
CuO NW/CC	2973.2	1 μM	Up to 1.12 mM	+0.55V	This work
CuO NP/CC	1245.9	1 μM	Up to 1.22 mM	+0.55V	This work
CuO nanofibers/ITO	873	40nM	Up to 1.3 mM	+0.48V	[42]
CuO NWs/ Cu foil	1420.3	5.1 μM	Up to 2.05 mM	+0.35V	[30]
CuO NPs/CNTs on Ta foil	2596	0.2 μM	Up to 1.2 mM	+0.40V	[40]
CuO nanoneedle/ graphene/carbon nanofiber/GCE	912.7	0.1 μM	1–5.3 mM	+0.60V	[23]

CuOnanoleaf /MWCNTs	664.3	5.7 μ M	Up to 0.9 mM	+0.35V	[44]
Ni-Cu/TiO ₂ NTs	1590	5 μ M	Up to 3.2 mM	+0.60V	[45]
CuO/TiO ₂ /Ti	79.79	1 μ M	Up to 2.0 mM	+0.5V	[46]
MnO ₂ /MWNTs	33.19		up to 28 mM	−0.20 V	[8]
Co ₃ O ₄ microspheres	1440	0.15 μ M	0.005–12 mM	0.55 V	[47]

CNTs: carbon nanotubes, MWCNTs: multi-walled carbon nanotubes, ITO: Indium tin oxide coated glass, GCE: glassy carbon electrode, LOD: Limit of detection

From the table, the performance of the sensor developed in this work was impressive, especially in terms of the sensitivity. The improved performance could be attributed to that: (1) The 3D CC with porous channels had good electrical conductivity and provided more sites for active substance than planar substrate, which was beneficial to adsorb glucose molecules as much as possible. (2) CuO nanostructures could contribute higher specific surface area to providing more active sites and shortening ion diffusion distance. (3) The in-situ growth method avoided the use of polymer binders, facilitating charge transfer and ion transport from the electrolyte to the electrode surface.

3.3. Reproducibility, stability and anti-interference property

Fig. 5. (A) Stability of the sensors over 20 days using 100 mM NaOH with 0.2 mM glucose at +0.55 V for CuO NPs/CC electrode (curve a), CuO NWs/CC electrode (curve c) and CuO NSs/CC electrode (curve b). (B), (C) and (D) Interference tests of the sensors in 100 mM NaOH at +0.55 V with 0.2 mM glucose and 0.02 mM other interferents for CuO NPs/CC, CuO NWs/CC and CuO NSs/CC electrode, respectively.

Long-term stability and reproducibility of sensors were of critical importance for practical applications. The stability of glucose sensors based CuO nanostructures was evaluated by measuring its amperometric current response to glucose during a period of 20 days at a time interval of 24 hours, as shown in Fig. 5 A. After 20 days, the sensitivity of the CuO NPs/CC electrode maintained approximately 93.5% of its original current response. Meanwhile, it was just 86.5% and 76.2% for the CuO NSs/CC and CuO NWs/CC electrode, respectively. The reproducibility of the sensors was estimated by injecting 0.2mM of glucose with five different electrodes respectively. For the CuO NS/CC electrode, the relative standard deviation was obtained to be 2.76% while it was 4.78 % and 1.81% for CuO NWs/CC and CuO NPs/CC electrode, respectively. The outstanding stability of CuO NPs/CC electrode was ascribed to a much stronger binding of active substance on the substrate after high-temperature calcinations.

The blood glucose level of a normal human body was usually between 4 mM and 7 mM [48], while the concentration of endogenous AA and UA was about 0.125 mM and 0.33 mM in blood samples, respectively [49]. For practical applications, the interference experiments were carried out to discriminate the interfering species such as UA, AA and AP by successive addition of 0.2 mM glucose and 0.02 mM interfering species in 100mM NaOH at a bias of +0.55 V. As shown in Fig. 5 B, C and D, all the CuO-modified electrodes showed negligible rise in the sensor response to the interfering species and the caused current responses just ranged from 0.2 to 8% comparing with glucose, indicating an excellent selectivity toward common interfering species. To investigate the application of CuO electrodes in real blood samples, calf serum (CS) was chosen as blood samples (Fig. S4). CuO NSs/CC exhibited the similar response for both CS and pure glucose, indicating the electrodes fabricated here had the practical sensing capability for glucose.

4. Conclusion

In this paper, different CuO nanostructures on the conductive CC by in-situ growth have been applied as electrodes to develop ultrasensitive amperometric non-enzymatic glucose sensor. All the electrodes displayed high sensitivity and fast responses (< 3 s), and the sensitivity of the CuO NSs/CC reaches up to $4902 \mu\text{A mM}^{-1} \text{cm}^{-2}$. Due to high conductivity of carbon clothes, high specific surface-area from CuO nanostructures, fast charge transfer and ion transport from the electrolyte to the electrode surface, the developed electrodes demonstrate ultrasensitive, selective, stable and fast amperometric sensing of glucose, which are promising for developing non-enzymatic glucose sensors with high performance. Besides, the method presented here shows other advantages, such as ease of fabrication, low cost, and good reproducibility.

Acknowledgements

This work is supported by the National Science Foundation of China (No. 51275195), the National Basic Research Program of China (No. 2015CB057205), the Program for Changjiang Scholars and the Innovative Research Team in University (grant No. IRT13017).

References

- [1] D. Zhai, B. Liu, Y. Shi, L. Pan, Y. Wang, W. Li, et al., Highly sensitive glucose sensor based on Pt nanoparticle/polyaniline hydrogel heterostructures, *ACS nano*, 7(2013) 3540-6.
- [2] S. Xi, T. Shi, D. Liu, L. Xu, H. Long, W. Lai, et al., Integration of carbon nanotubes to three-dimensional C-MEMS for glucose sensors, *Sensors and Actuators A: Physical*, 198(2013) 15-20.
- [3] F. Cao, J. Gong, Nonenzymatic glucose sensor based on CuO microfibers composed of CuO nanoparticles, *Analytica chimica acta*, 723(2012) 39-44.
- [4] R. Ahmad, M. Vaseem, N. Tripathy, Y.-B. Hahn, Wide linear-range detecting nonenzymatic glucose biosensor based on CuO nanoparticles inkjet-printed on electrodes, *Analytical chemistry*, 85(2013) 10448-54.
- [5] J.S.C. Le Thuy Hoa, S.H. Hur, A highly sensitive enzyme-free glucose sensor based on Co₃O₄ nanoflowers and 3D graphene oxide hydrogel fabricated via hydrothermal synthesis, *Sensors and Actuators B: Chemical*, 223(2016) 76.
- [6] R. Prasad, B.R. Bhat, Multi-wall carbon nanotube–NiO nanoparticle composite as enzyme-free electrochemical glucose sensor, *Sensors and Actuators B: Chemical*, 220(2015) 81-90.
- [7] X. Cao, N. Wang, A novel non-enzymatic glucose sensor modified with Fe₂O₃ nanowire arrays, *Analyst*, 136(2011) 4241-6.
- [8] J. Chen, W.-D. Zhang, J.-S. Ye, Nonenzymatic electrochemical glucose sensor based on MnO₂/MWNTs nanocomposite, *Electrochemistry Communications*, 10(2008) 1268-71.
- [9] S. Singh, B.D. Gupta, Fabrication and characterization of a surface plasmon resonance based fiber optic sensor using gel entrapment technique for the detection of low glucose concentration, *Sensors and Actuators B: Chemical*, 177(2013) 589-95.
- [10] A.K. Mishra, S.K. Mishra, R.K. Verma, Graphene and Beyond Graphene MoS₂: A New Window in Surface-Plasmon-Resonance-Based Fiber Optic Sensing, *The Journal of Physical Chemistry C*, 120(2016) 2893-900.
- [11] A.S. Danial, M. Saleh, S. Salih, M. Awad, On the synthesis of nickel oxide nanoparticles by sol–gel technique and its electrocatalytic oxidation of glucose, *Journal of Power Sources*, 293(2015) 101-8.
- [12] Y. Zhao, L. Fan, Y. Zhang, H. Zhao, X. Li, Y. Li, et al., Hyper-Branched Cu@ Cu₂O Coaxial Nanowires Mesh Electrode for Ultra-Sensitive Glucose Detection, *ACS applied materials & interfaces*, 7(2015) 16802-12.
- [13] X. Niu, Y. Li, J. Tang, Y. Hu, H. Zhao, M. Lan, Electrochemical sensing interfaces with tunable porosity for nonenzymatic glucose detection: A Cu foam case, *Biosensors and Bioelectronics*, 51(2014) 22-8.
- [14] D.P. Dubal, G.S. Gund, R. Holze, C.D. Lokhande, Mild chemical strategy to grow micro-roses and micro-woolen like arranged CuO nanosheets for high performance supercapacitors, *Journal of Power Sources*, 242(2013) 687-98.
- [15] X. Zhang, W. Shi, J. Zhu, D.J. Kharistal, W. Zhao, B.S. Lalia, et al., High-power and high-energy-density flexible pseudocapacitor electrodes made from porous CuO nanobelts and single-walled carbon nanotubes, *ACS nano*, 5(2011) 2013-9.
- [16] S. Ko, J.I. Lee, H.S. Yang, S. Park, U. Jeong, Mesoporous CuO Particles Threaded with CNTs for High-Performance Lithium-Ion Battery Anodes, *Advanced Materials*, 24(2012) 4451-6.

- [17] L. Hu, Y. Huang, F. Zhang, Q. Chen, CuO/Cu₂O composite hollow polyhedrons fabricated from metal–organic framework templates for lithium-ion battery anodes with a long cycling life, *Nanoscale*, 5(2013) 4186-90.
- [18] M. Mazhar, G. Faglia, E. Comini, D. Zappa, C. Baratto, G. Sberveglieri, Kelvin probe as an effective tool to develop sensitive p-type CuO gas sensors, *Sensors and Actuators B: Chemical*, 222(2016) 1257-63.
- [19] Y. Qin, F. Zhang, Y. Chen, Y. Zhou, J. Li, A. Zhu, et al., Hierarchically porous CuO hollow spheres fabricated via a one-pot template-free method for high-performance gas sensors, *The Journal of Physical Chemistry C*, 116(2012) 11994-2000.
- [20] W. Tian, C. Zhi, T. Zhai, X. Wang, M. Liao, S. Li, et al., Ultrahigh quantum efficiency of CuO nanoparticle decorated In₂Ge₂O₇ nanobelt deep-ultraviolet photodetectors, *Nanoscale*, 4(2012) 6318-24.
- [21] K. Dhara, J. Stanley, T. Ramachandran, B.G. Nair, Pt-CuO nanoparticles decorated reduced graphene oxide for the fabrication of highly sensitive non-enzymatic disposable glucose sensor, *Sensors and Actuators B: Chemical*, 195(2014) 197-205.
- [22] L. Luo, L. Zhu, Z. Wang, Nonenzymatic amperometric determination of glucose by CuO nanocubes–graphene nanocomposite modified electrode, *Bioelectrochemistry*, 88(2012) 156-63.
- [23] D. Ye, G. Liang, H. Li, J. Luo, S. Zhang, H. Chen, et al., A novel nonenzymatic sensor based on CuO nanoneedle/graphene/carbon nanofiber modified electrode for probing glucose in saliva, *Talanta*, 116(2013) 223-30.
- [24] Y. Zhang, Y. Liu, L. Su, Z. Zhang, D. Huo, C. Hou, et al., CuO nanowires based sensitive and selective non-enzymatic glucose detection, *Sensors and Actuators B: Chemical*, 191(2014) 86-93.
- [25] S. Sun, X. Zhang, Y. Sun, S. Yang, X. Song, Z. Yang, Hierarchical CuO nanoflowers: water-required synthesis and their application in a nonenzymatic glucose biosensor, *Physical Chemistry Chemical Physics*, 15(2013) 10904-13.
- [26] N. Quoc Dung, D. Patil, H. Jung, D. Kim, A high-performance nonenzymatic glucose sensor made of CuO-SWCNT nanocomposites, *Biosensors & bioelectronics*, 42(2013) 280-6.
- [27] J. Zhang, J. Ma, S. Zhang, W. Wang, Z. Chen, A highly sensitive nonenzymatic glucose sensor based on CuO nanoparticles decorated carbon spheres, *Sensors and Actuators B: Chemical*, 211(2015) 385-91.
- [28] C.-L. Sun, W.-L. Cheng, T.-K. Hsu, C.-W. Chang, J.-L. Chang, J.-M. Zen, Ultrasensitive and highly stable nonenzymatic glucose sensor by a CuO/graphene-modified screen-printed carbon electrode integrated with flow-injection analysis, *Electrochemistry Communications*, 30(2013) 91-4.
- [29] W. Xu, S. Dai, X. Wang, X. He, M. Wang, Y. Xi, et al., Nanorod-aggregated flower-like CuO grown on a carbon fiber fabric for a super high sensitive non-enzymatic glucose sensor, *Journal of Materials Chemistry B*, 3(2015) 5777-85.
- [30] Y. Li, M. Zhao, J. Chen, S. Fan, J. Liang, L. Ding, et al., Flexible Chitosan/Carbon Nanotubes Aerogel, A Robust Matrix for In-situ Growth and Non-enzymatic Biosensing Applications, *Sensors and Actuators B: Chemical*, (2016).
- [31] J. Huang, Y. Zhu, X. Yang, W. Chen, Y. Zhou, C. Li, Flexible 3D porous CuO nanowire arrays for enzymeless glucose sensing: in situ engineered versus ex situ piled, *Nanoscale*, 7(2015) 559-69.
- [32] B. Hai, Y. Zou, Carbon cloth supported NiAl-layered double hydroxides for flexible application and highly sensitive electrochemical sensors, *Sensors and Actuators B: Chemical*, 208(2015) 143-50.
- [33] Y.-Y. Horng, Y.-K. Hsu, A. Ganguly, C.-C. Chen, L.-C. Chen, K.-H. Chen, Direct-growth of polyaniline nanowires for enzyme-immobilization and glucose detection, *Electrochemistry Communications*, 11(2009) 850-3.
- [34] T. Chen, X. Li, C. Qiu, W. Zhu, H. Ma, S. Chen, et al., Electrochemical sensing of glucose by carbon cloth-supported Co₃O₄/PbO₂ core-shell nanorod arrays, *Biosensors and Bioelectronics*, 53(2014) 200-6.
- [35] Q. Xu, Y. Zhao, J.Z. Xu, J.-J. Zhu, Preparation of functionalized copper nanoparticles and fabrication of a glucose sensor, *Sensors and Actuators B: Chemical*, 114(2006) 379-86.
- [36] S.K. Meher, G.R. Rao, Archetypal sandwich-structured CuO for high performance non-enzymatic sensing of glucose, *Nanoscale*, 5(2013) 2089-99.

- [37] G. Wang, X. He, L. Wang, A. Gu, Y. Huang, B. Fang, et al., Non-enzymatic electrochemical sensing of glucose, *Microchimica Acta*, 180(2013) 161-86.
- [38] J. Yang, W.-D. Zhang, S. Gunasekaran, An amperometric non-enzymatic glucose sensor by electrodepositing copper nanocubes onto vertically well-aligned multi-walled carbon nanotube arrays, *Biosensors and Bioelectronics*, 26(2010) 279-84.
- [39] J. Yang, L.-C. Jiang, W.-D. Zhang, S. Gunasekaran, A highly sensitive non-enzymatic glucose sensor based on a simple two-step electrodeposition of cupric oxide (CuO) nanoparticles onto multi-walled carbon nanotube arrays, *Talanta*, 82(2010) 25-33.
- [40] L.-C. Jiang, W.-D. Zhang, A highly sensitive nonenzymatic glucose sensor based on CuO nanoparticles-modified carbon nanotube electrode, *Biosensors and Bioelectronics*, 25(2010) 1402-7.
- [41] Y. Ding, Y. Wang, L. Su, M. Bellagamba, H. Zhang, Y. Lei, Electrospun Co₃O₄ nanofibers for sensitive and selective glucose detection, *Biosensors and Bioelectronics*, 26(2010) 542-8.
- [42] G. Liu, B. Zheng, Y. Jiang, Y. Cai, J. Du, H. Yuan, et al., Improvement of sensitive CuO NFs-ITO nonenzymatic glucose sensor based on in situ electrospun fiber, *Talanta*, 101(2012) 24-31.
- [43] L. Han, D.-P. Yang, A. Liu, Leaf-templated synthesis of 3D hierarchical porous cobalt oxide nanostructure as direct electrochemical biosensing interface with enhanced electrocatalysis, *Biosensors and Bioelectronics*, 63(2015) 145-52.
- [44] Z. Yang, J. Feng, J. Qiao, Y. Yan, Q. Yu, K. Sun, Copper oxide nanoleaves decorated multi-walled carbon nanotube as platform for glucose sensing, *Analytical Methods*, 4(2012) 1924-6.
- [45] X. Li, J. Yao, F. Liu, H. He, M. Zhou, N. Mao, et al., Nickel/Copper nanoparticles modified TiO₂ nanotubes for non-enzymatic glucose biosensors, *Sensors and Actuators B: Chemical*, 181(2013) 501-8.
- [46] S. Luo, F. Su, C. Liu, J. Li, R. Liu, Y. Xiao, et al., A new method for fabricating a CuO/TiO₂ nanotube arrays electrode and its application as a sensitive nonenzymatic glucose sensor, *Talanta*, 86(2011) 157-63.
- [47] C. Guo, X. Zhang, H. Huo, C. Xu, X. Han, Co₃O₄ microspheres with free-standing nanofibers for high performance non-enzymatic glucose sensor, *Analyst*, 138(2013) 6727-31.
- [48] S. Park, H. Boo, T.D. Chung, Electrochemical non-enzymatic glucose sensors, *Analytica Chimica Acta*, 556(2006) 46-57.
- [49] S. Hrapovic, J.H. Luong, Picoamperometric detection of glucose at ultrasmall platinum-based biosensors: preparation and characterization, *Analytical Chemistry*, 75(2003) 3308-15.

Biographies

Yan Zhong received the B.Sc. degree in mechanical engineering from North West Agriculture and Forestry University, China, in 2014. She is now working toward the Ph.D. degree in Mechanical Engineering in HUST. Her current research activities focus on fabrication of micro/nano-materials and their applications in supercapacitors and biosensors.

Tielin Shi is the director of the State Key Laboratory for Digital Manufacturing Equipment and Technology at HUST. He obtained his Ph.D. in Mechanical Engineering in 1999 from HUST. His interests are in micro/nanofabrication technologies and developing advanced fabrication systems for microelectronic industry.

Zhiyong Liu received the B.Sc. degree in mechanical engineering from Wuhan University of Technology, China, in 2013. He is now working toward the Ph.D. degree in Mechanical Engineering in HUST. His current research activities focus on fabrication of micro/nano-materials and their applications in Perovskite solar batteries.

Siyi Cheng received the master degree in control technology and instrument professional from Beijing University of Chemical Technology in 2014. He is now working toward the Ph.D. degree in Mechatronics Engineering at HUST. His research work includes synthesis of nano-materials, and the applications in lithium battery.

Yuanyuan Huang received the B.Sc. degree in mechanical engineering from Sichuan University in 2015. Currently she is working on her Ph.D. degree in Mechatronics Engineering at HUST. Her current research activities are in the area of synthesis of graphene and its application in

supercapacitors.

Xiangxu Tao received the B.Sc. degree in mechanical engineering from HeFei University of Technology in 2014. Currently he is working with Professor Z. R. Tang on his master degree in Mechatronics Engineering at HUST. His current research activities are the fabrication of thermocouple temperature sensor on tools.

Guanglan Liao is a professor of the State Key Laboratory for Digital Manufacturing Equipment and Technology at HUST. He obtained his Ph.D. in Mechanical Engineering in 2003 from HUST. His current interests are microelectronics manufacturing and packaging.

Zirong Tang is a professor in Wuhan National Laboratory for Optoelectronics at HUST, Wuhan, China. He obtained his Ph.D. in Material Science and Engineering in 2001 from the University of California, Irvine, USA. His current interests are in MEMS, electrochemical sensors, biosensors and micro/nanofabrication technologies.