Precipitation and dissolution of Ag in ageing hypoeutectic alloys

Xiaowei Zuo ¹⁾, Ke Han ^{2)*}, Congcong Zhao ¹⁾, Rongmei Niu ²⁾, Engang Wang ^{1)*}

1) Key Laboratory of Electromagnetic Processing of Materials (Ministry of Education),
Northeastern University, Shenyang, China, 110004

2) National High Magnetic Field Laboratory, Florida State University, 1800 East Paul
Dirac Drive, Tallahassee, Florida, USA, 32310

Corresponding authors: Tel. & fax: +86 24 83681739, egwang@mail.neu.edu.cn

(Engang Wang); Tel.: +1 850 6446746, fax: +1 850 6440867, han@magnet.fsu.edu (Ke Han).

Abstract

Understanding the precipitate kinetics of Ag in proeutectic Cu is valuable to optimize the precipitation and morphology of Ag for high strength high conductivity hypoeutectic Cu-Ag alloys. The precipitation behaviors of as-solution treated Cu28wt.%Ag alloys were analyzed by differential scanning calorimetric (DSC). The results indicated that the activation energies of Ag-rich phase formation and dissolution were 55.3 ± 22.4 kJ/mol and 129.1 ± 20.7 kJ/mol, respectively. The as-solution alloy was further aged at different temperatures for 2 hours. Their microhardness and electrical resistivity were measured. The results demonstrated that at the ageing temperature of 405°C, less scattering effects reflected more Ag precipitations from Cu matrix than the rest of temperatures. At 475°C, however, Ag precipitates produced more strengthening effects. Above results were related to the

competition between precipitation and dissolution of Ag in proeutectic Cu. This interpretation is supported by TEM observations on Ag precipitation.

Keywords: Cu-Ag alloy; precipitation; dissolution; DSC; microhardness; resistivity

1. Introduction.

Cu-Ag hypoeutectic materials with high strength and high conductivity are vital winding conductors for both DC resistive and AC pulsed high-field magnet coils [1-4]. Previous reports [4-7] have shown that microstructures of hypoeutectic CuAg alloys have two components: a) eutectic networks that surround b) Cu-rich proeutectic dendrites with nano sized Ag precipitates. Cu-rich proeutectic dendrites with a large proportion of volume fraction play crucial roles in properties of the Cu-Ag alloys. The morphology of nano sized Ag precipitations and Ag dissolution in proeutectic Cu dendrites are the most important influencing factors [5, 8]. Therefore, understanding the precipitate kinetics is necessary to optimize the precipitate and distribution of Ag in proeutectic Cu. Moreover, the investigation of precipitation and dissolution could be also applied to clarify the Ag diffusion theories along migrating or stationary grain boundaries [9, 10]. Two (discontinuous and continuous) precipitation reactions are strongly dependent on the silver content [11]. As the Ag composition was less than 8wt.%, the Cu-rich solid solutions were transformed into structures with rod-like Ag-rich precipitations embedded in Cu-rich matrix by discontinuous precipitation. Coarse precipitates from the high-angle grain boundaries were generated [9, 10, 12,

13]. The estimated activation energy of Ag precipitation [10, 12, 14], growth direction, morphology and habit planes [15] were reported. Whereas the silver content was more than 8wt%, a sufficient volume fraction of eutectics suppressed discontinuous precipitation by the absence of grain boundaries and fine precipitates were observed by continuous precipitation mode. By comparison, fine Ag precipitations by continuous reaction had greater strengthening contributions than coarsening precipitations by discontinuous one [11]. Consequently, in order to improve the strengthening effect, continuous mode should be promoted and discontinuous mode should be suppressed. [11] However, up to date, most of the precipitate kinetics of Cu-Ag alloy was paid attention to the low Ag content. Rare investigations were focused on the precipitation and dissolution of Ag in Cu-Ag alloys with higher silver content. Their activation energies and the properties have not been carried out so far. The investigation of precipitation and dissolution could be used to design heat treatment procedure that could provide Ag solid solution strengthening effects and precipitation effects. Additionally, the dissolution of Ag could increase the electrical resistivity of CuAg microcomposites if inappropriate thermomechanical process was employed [16]. In this paper, the activation energy, the precipitation behaviors, the properties and microstructure of Cu-28wt.%Ag alloys were analyzed by differential scanning calorimetric (DSC) analysis, microhardness, resistivity tests and transmission electron microscopy (TEM) .

2. Experimental methodologies

A Cu-28wt.%Ag (weight percent, expressed as Cu28%Ag in the context) alloy

was melt in a vacuum induction furnace and cast in a Cu mould under high-purity Ar atmosphere. The alloy was solution treated at 760 °C for 2h followed by quenching into water. The solid-solution specimen was machined into several sheets with about 0.4 mm in thickness and aged at temperatures between 300 °C and 580 °C for 2h. Microhardness tests were conducted on an Instron Wilson-Wolpert Tukon 2100 microhardness tester with a diamond square-based pyramid under a load of 50 g and the dwelling time of 10 s. The resistivity was measured by four-probe DC method in the deionized water. The differential scanning calorimetric (DSC) analysis was carried out under argon atmosphere with a Shimadzu DSC-60. The calibration procedures of DSC tests could be found in a separate paper [17]. As there is a eutectic reaction at about 540 °C between Al pans and Cu matrix in Cu28%Ag alloys, Al₂O₃ powders with 100 µm were used to separate the interfaces between Al and Cu. Thin foils for TEM were prepared by argon ion-milling with a voltage of 5 kV at an incidence angle of 3°. The foils were observed in a FEI-Tecnai G2 TEM operating at 200 kV.

3. Results and discussion

In our Cu28%Ag alloy, [18]the volume fraction of proeutectic Cu was larger than 80% [18]. Consequently, the heat flow of proeutectic Cu would be obviously over that of the eutectic component in DSC data obtained from Cu28%Ag alloys. The heat flow of proeutectic Cu is expected to dominate the total heat flow. At elevated temperature (>250°C), both exothermic Ag precipitation and endothermic Ag dissolution in proeutectic Cu will occur [14]. Those two reactions are shown in the DSC curves of as-solution treated Cu28%Ag alloys in Fig.1. At the exothermic peak

temperature between 250°C and 400°C, the solid arrow indicates the precipitation of Ag. The solid arrow marking lowest point between 400°C and 500°C indicates Ag dissolution. We observed another abnormal peak between 350°C and 450°C when the Al_2O_3 powers in Al pans were used in the DSC measurements. When Al_2O_3 crucibles were used instead, no abnormal peak was detected. We verified that this peak was the result of the Al_2O_3 powers. In our DSC measurements, we detected reactions of exothermic Ag precipitation and endothermic Ag dissolution.

Fig.1 Differential scanning calorimetric curves of Cu28%Ag alloys after solution treated at 760°C for 2h with different heating rates from 10°C/min to 40°C/min (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

The activation energy (E_a) could be calculated by the shift of the reaction temperatures in DSC measurements with different heating rates. E_a could be

determined by the Kissinger equation:

$$\ln\left(\frac{b}{T_p^2}\right) = -\frac{E_a}{RT_p} + C \quad (1)$$

where, b is the heating rate, E_a the activation energy (kJ/mol), T_p the reaction (or peak) temperature in the DSC curves, R the universal gas constant and C is a constant.

The linear fitting of data $\ln(b/T_p^2)$ against $1000/T_p$ is plotted in Fig. 2. The fitting gave 55.3 ± 22.4 kJ/mol as [20] the activation energy of Ag-rich precipitation (the first reaction of the DSC curves in Fig.1), which is lower than that in Cu-7wt.%Ag alloy (95 ± 4 kJ/mol) [14], Cu-3.8 at.% Ag bicrystals (144.1 kJ/mol) [10] and Cu-5.7wt%Ag single crystal (185 kJ/mol). The activation energy of Ag-rich dissolution (the high temperature reaction in the DSC curves in Fig.1) was 129.1 ± 20.7 kJ/mol. This value is lower than that measured by others (195 kJ/mol) [19]. These discrepancies could be related to the fact that the activation energies and diffusion rates were influenced by both Ag contents and heating rate. Since both precipitation and dissolution were diffusion-controlling reactions that require finite times and driving forces to complete. Different supersaturated Ag contents induced different driving forces. Variation in heating rates alters solvus concentrations. These caused in the changes of the activation energies. Therefore, higher Ag composition reduced the activation energy of the precipitation and dissolution of Ag in Cu matrix, which might be beneficial for the precipitation and dissolution of Ag in Cu matrix.

Fig. 2 The experimental data and fitting curve of Kissinger equation plotted between $\ln(b/T_p^2)$ and $1000/T_p$

With increasing ageing temperatures, the Ag precipitation competes with the Ag dissolution in proeutectic Cu if the Ag content remains constant. In Fig.3, samples experienced ageing at various temperatures at constant time before DSC measurements. In those samples, similar nucleation and growth process of Ag precipitates should occur. The similarities and differences could be identified from the measured reaction temperatures. At lower ageing temperatures, Ag precipitations required longer than 2 hours of precipitation times to complete. Therefore, the samples treated at higher temperatures have less supersaturated Ag in proeutectic Cu, and the driving force for further precipitation is reduced. This pushed the measured precipitation temperature higher in subsequent DSC measurements. The precipitation temperatures of DSC samples shown in Fig. 3a indicated that as the ageing temperature increased, the peak temperature increased until 405°C. The ageing temperature higher than 405 °C was likely to promote the

dissolution of Ag in Cu matrix. This reduced the measured precipitation temperature in DSC measurements. We concluded that the ageing temperature of 405°C produced more Ag precipitates than that at the rest of ageing temperatures.

Fig. 3 (a) The DSC peak temperatures relative to precipitation reactions of Cu28%Ag alloys after aged with different ageing temperatures as a function of the ageing temperature. (b) Both the resistivity and the microhardness of Cu28%Ag alloys with different ageing temperature after solid-solution treatment at 760°C. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

Both the electrical resistivity and microhardness of hypoeutectic CuAg alloys are dependent on the precipitation and dissolution of Ag in proeutectic Cu. The Ag dissolution and precipitation of Ag in proeutectic Cu could affect the changes in resistivity and microhardness. Fig.3b shows the effect of ageing temperatures on electrical resistivity and microhardness of Cu28%Ag alloys. The results indicated that as ageing temperatures increased, the electrical resistivity decreased until 405°C, and the microhardness increased until 475°C. These findings were thought from the

competitive growth between dissolution and precipitation of Ag in proeutectic Cu.

We could divide the growth into at least four different stages to describe the competition. In stage I (ageing temperature lower than 300°C), Ag precipitates started to nucleate and grow when the energies were larger than the activation energies of Ag phase formation. At this stage, the impact of Ag precipitation on hardness is marginal. The Ag precipitations reduce supersaturated Ag solid solution in Cu matrix, and consequently, decrease the impurity scattering and the resistivity. In stage II (ageing temperature ranging from 300°C to 405°C), Ag precipitation became dominant. Because Ag precipitation increased with increased ageing temperatures, as observed in Figs. 4(a)&(b), microhardness rapidly enhanced, and the resistivity decreased obviously. In stage III, obvious Ag dissolutions started with increasing ageing temperature, Ag solute increased, which made the resistivity increase rapidly. The total strengthening contributions from both solid solute hardening and precipitate hardening were likely to increase further and the peak hardness was reached at the ageing temperature of 475°C. We thought that it might attribute to the gradual growth of Ag precipitate at the ageing temperature of 475°C after entire nucleation at 405°C. In final stage, Ag dissolution was dominant. The larger portion of dissolution of Ag further increased resistivity. The dissolution of Ag consumed Ag precipitates. Meanwhile, TEM observations, shown in Figs. 4 (c) & (d), indicated that the Ag precipitations occurred the coarsening after the ageing temperature of 580°C. Consequently, the volume reduction and coarsening of Ag precipitates decreased the hardness and increased the resistivity. The variations of

resistivity with ageing temperature were consistent with the analysis in the peak temperature of Ag precipitations in the DSC measurement, as shown in Fig. 3a. This work made us believe that previous optimization ageing temperature for Cu24%Ag alloy between 330 °C and 430 °C was attributed to the precipitation and dissolution of Ag [3].

Fig. 4 TEM micrograph of ageing Cu28%Ag alloys, (a) and (b) showing Bright Field (BF) and Dark Field (DF) images at the temperature of 405 °C; (c) and (d) showing BF and DF images at temperature of 580 °C, respectively; The right-upper insets show the corresponding selected area diffraction patterns.

4. Conclusion

The precipitation behaviors of Cu28%Ag alloys were analyzed by differential scanning calorimetric (DSC), and the results indicated that the activation energies of Ag-rich phase formation and dissolution were 55.3 ± 22.4 kJ/mol and 129.1 ± 20.7

kJ/mol, respectively. The competitive growths between precipitation and dissolution of Ag could be reflected by both the microhardness and the resistivity and revealed that more Ag precipitation in Cu matrix was at about 405°C and more strengthening effect was at about 475°C. TEM observations on Ag precipitations showed fine Ag precipitations at 405 °C and the coarsening of Ag precipitations at 580 °C.

Acknowledgements

We thank Dr. Jun Lu at National High Magnetic Field Laboratory, Florida State University for assistance in the measurement of resistivity. This work was supported by the National Natural Science Foundation of China (Nos. 51474066 and 51004038), the Research Fund for the Doctoral Program of Higher Education (No. 2012004211008), the 111 Project of China (No. B07015) and NSF Cooperative Agreement (DMR- 0654118 and 1157490) by the State of Florida and the US Department of Energy.

References

- [1] C.A. Davy, K. Han, P.N. Kalu, S.T. Bole, Examinations of Cu-Ag composite conductors in sheet forms, IEEE Trans. Appl. Super., 18 (2008) 560-563.
- [2] K. Han, V. Toplosky, R. Goddard, J. Lu, R. Niu, J. Chen, Impacts of Heat Treatment on Properties and Microstructure of Cu16at%Ag Conductors, IEEE Trans. Appl. Super., 22 (2011) 6900204.
- [3] Y. Sakai, H.J. SchneiderMuntau, Ultra-high strength, high conductivity Cu-Ag alloy wires, Acta Mater., 45 (1997) 1017-1023.
- [4] Y. Sakai, K. Inoue, T. Asano, H. Wada, H. Maeda, Development of high-strength, high-conductivity Cu-Ag alloys for high-field pulsed magnet use, Appl. Phys. Lett., 59 (1991) 2965-2967.

-
- [5] K. Han, A.A. Vasquez, Y. Xin, P.N. Kalu, Microstructure and tensile properties of nanostructured Cu-25wt%Ag, *Acta Mater.*, 51 (2003) 767-780.
- [6] X.W. Zuo, C.C. Zhao, E.G. Wang, L. Zhang, K. Han, J.C. He, Microstructure Evolution of the Proeutectic Cu Dendrites in Diamagnetic Cu-Ag Alloys by Electromagnetic Suppressing Convection, *J Low Temp. Phys.*, 170 (2013) 409-417.
- [7] G. M. Li, E. G. Wang, L. Zhang, X.W. Zuo, J.C. He, Effect of High Magnetic Field on Solidified Structure, Drawn Structure and Electrical Conductivity of Cu-25Ag Alloys, *Rare Metal Mat. Eng.*, 41 (2012) 701-706.
- [8] W. Grunberger, M. Heilmaier, L. Schultz, Development of high-strength and high-conductivity conductor materials for pulsed high-field magnets at Dresden, *Physica B*, 294 (2001) 643-647.
- [9] S.P. Gupta, Kinetics of discontinuous precipitation and dissolution in Cu-Ag alloys, *Can. Metall. Q.*, 37 (1998) 141-159.
- [10] W. Gust, J. Beuers, J. Steffen, S. Stiltz, B. Predel, Diffusion Along Migrating and Stationary Grain-Boundaries in the Cu-Ag System, *Acta Metall.*, 34 (1986) 1671-1680.
- [11] A. Gaganov, J. Freudenberger, W. Grünberger, L. Schultz, Microstructural evolution and its effect on the mechanical properties of Cu–Ag microcomposites, *Z. Metallkd.*, 95 (2004) 425-432.
- [12] R. Monzen, K. Murase, H. Nagayoshi, C. Watanabe, Discontinuous precipitation in {100} planes in a Cu-5.7 wt% Ag alloy single crystal, *Philos. Mag. Lett.*, 84 (2004) 349-358.
- [13] D. Hamana, L. Boumaza, Precipitation mechanism in Ag-8 wt.% Cu alloy, *J. Alloys Compd.*, 477 (2009) 217-223.
- [14] D. Hamana, M. Hachouf, L. Boumaza, e. al., Precipitation kinetics and mechanism in Cu-7wt%Ag Alloy, *Mater. Sci. Appl.*, 2 (2011) 899-910.

-
- [15] C. Watanabe, R. Monzen, H. Nagayoshi, S. Onaka, Elastic state of rod-shaped Ag precipitates in a Cu-5.7 wt% Ag single crystal, *Philos. Mag. Lett.*, 86 (2006) 65-73.
- [16] Y. Sakai, Y. Hori, Cu-Ag alloy wire having high strength and high conductivity and method for manufacture thereof, WO2007046378, 2007.
- [17] R.M. Niu, K. Han, Y.F. Su, V.J. Salters, Atomic-scale studies on the effect of boundary coherency on stability in twinned Cu, *Appl. Phys. Lett.*, 104 (2014) 011913-1-4.
- [18] X.W. Zuo, K. Han, C.C. Zhao, R.M. Niu, E. G. Wang, Microstructure and Properties of Nanostructured Cu₂₈wt.%Ag Microcomposite Deformed after Solidifying under a High Magnetic Field, *Mater. Sci. Eng. A*, (2014) doi: 10.1016/j.msea.2014.09.070.
- [19] V. Burachynsky, J.R. Cahoon, A theory for solute impurity diffusion, which considers engel-brewer valences, balancing the fermi energy levels of solvent and solute, and differences in zero point energy, *Metall. Mat. Trans. A*, 28 (1997) 563-582.

Fig.1 Differential scanning calorimetric curves of Cu₂₈%Ag alloys after solution treated at 760°C for 2h with different heating rates from 10°C/min to 40°C/min (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

Fig. 2 The experimental data and fitting curve of Kissinger equation plotted between

$\ln(b/T_p^2)$ and $1000/T_p$

Fig. 3 (a) The DSC peak temperatures relative to precipitation reactions of Cu28%Ag alloys after aged with different ageing temperatures as a function of the ageing temperature. (b) Both the resistivity and the microhardness of Cu28%Ag alloys with different ageing temperature after solid-solution treatment at 760°C. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

Fig. 4 TEM micrograph of ageing Cu28%Ag alloys, (a) and (b) showing Bright Field (BF) and Dark Field (DF) images at the temperature of 405 °C; (c) and (d) showing BF and DF images at temperature of 580 °C, respectively; The right-upper insets show the corresponding selected area diffraction patterns.