Why the slip of $1/2\langle 331 \rangle$ dislocations on $\{013\}$ in $C11_b$ behaves differently at low and high temperatures?

V. Paidar^{a*}, H. Inui^b

^aInstitute of Physics ASCR, Na Slovance 2, 182 21 Praha 8, Czech Republic

^bDepartment of Materials Science and Engineering, Kyoto University, Sakyo-ku, Kyoto 606-8501, Japan

*Corresponding author. Tel.: +420 266052147; fax: +420 286890527.

E-mail addresses: paidar@fzu.cz (V. Paidar), inui.haruyuki.3z@kyoto-u.ac.jp (H. Inui).

Keywords

A. high-temperature alloys; A. intermetallics; C. atomic scale structure; C. dislocations; C. mechanical properties

Abstract

The $1/2\langle 331 \rangle$ dislocations in the tetragonal $C11_b$ structure of disilicides may possess a three-fold non-planar core structure inherited from the BCC lattice. Due to non-metallic bonding, the dislocation splitting is intrinsically asymmetrical what has large consequences for dislocation properties. The $1/2\langle 331 \rangle$ slip on the $\{013\}$ planes was observed at high temperatures above 900 °C when compressed along $[001]$, but surprisingly, also below 500 °C when compressed along $[0\ 15\ 1]$. Why different dislocation behaviour is observed at high and low temperatures is explained in this paper.

1. Introduction

Transition-metal disilicides have been studied for decades not only as functional materials but also as perspective structural materials for ultra-high temperature applications [1, 2]. However, complex dislocation behaviour in these materials has not yet been completely understood. One of fundamental questions is why the slip of dislocations with the large Burgers vectors of $1/2\langle 331 \rangle$ on the $\{013\}$ planes occurs in a completely different way at high and low temperatures.

The crystal structure of the most studied disilicide $MoSi_2$ is $C11_b$ that is a tetragonal structure composed essentially from three BCC type elementary cells – see Fig. 1. For the c/a ratio of $\sqrt{6}$, the atomic arrangement on the (110) plane is pseudo-hexagonal with six-fold symmetry. Many different slip systems were analysed in $MoSi_2$ [3] including the slip along the $\langle 100 \rangle$ short Burgers vector on several crystallographic planes as $\{010\}$, $\{011\}$ or $\{023\}$ and the $1/2\langle 111 \rangle$ slip on the $\{110\}$ plane. For the load direction along the $[001]$ tetragonal axis, the $1/2\langle 331 \rangle$ $\{013\}$ slip is observed only at high temperatures above 900°C while for the $[0\ 15\ 1]$ load direction, the same slip is active at low temperatures below 500°C. Relatively not too high values of CRSS for the $1/2\langle 331 \rangle$ $\{013\}$ slip were observed at low temperatures, contrary to a steeply increasing CRSS with decreasing temperature that was found at high-temperature zone – see Fig. 2.

Fig. 1. Tetragonal elementary cell of $C11_b$ lattice. Large circles are metallic atoms, small circles silicon atoms. The $1/2 [3-31]$ Burgers vector and the (013) slip plane are also depicted.

Fig. 2. Temperature dependence of the CRSS for the $1/2\langle 331 \rangle$ slip on the $\{013\}$ plane. According to [3].

The tetragonal $C11_b$ structure would become the BCC lattice if there were not two different species in the unit cell, metallic and silicon atoms. Consequently, there are certain aspects of dislocations in the $C11_b$ compounds that appear to emulate the dislocation properties in BCC metals, nevertheless, due to entirely different atomic bonding in disilicides, in comparison with metallic systems, there are huge differences in dislocation behaviour as discussed below.

2. $1/2\langle 331 \rangle$ dislocations

The $1/2\langle 331 \rangle$ dislocations are in fact inherited from the $1/2\langle 111 \rangle$ dislocations of the BCC crystals. In compression along the $[001]$ $C11_b$ tetragonal axis, the plastic deformation is exclusively controlled by the mobility of $1/2\langle 331 \rangle$ dislocations. This is the case in spite of the fact that for the ideal c/a ratio of $C11_b$, the magnitude of the $1/2\langle 331 \rangle$ Burgers vector is $\sqrt{6}$ larger than that of the $\langle 100 \rangle$ Burgers vector.

The structure of dislocation cores is related to the crystal symmetry of the direction of the dislocation line. An important material characteristic is whether metastable stacking-fault-like defects exist on planes containing the dislocation line. While no such stacking fault is known in BCC metals, metastable faults were found on the $\{013\}$ and $\{110\}$ planes in $MoSi_2$ with the $C11_b$ structure by *ab initio* calculations of γ -surface [4]. Using these results, the non-planar dissociations of screw $1/2\langle 331 \rangle$ dislocations in $MoSi_2$ can be analysed and their impact on dislocations glide can be discussed.

Due to a rather complex interatomic bonding in silicides, a quantum-mechanical density functional based *ab initio* method was employed in the calculations of γ -surfaces, i.e. the energies of generalized stacking faults as functions of displacement vectors [4]. Only one type of the metastable stacking fault can occur on the $\{110\}$ plane while three different metastable stacking faults were identified on the $\{013\}$ plane. The energies of these three stacking faults on $\{013\}$ are relatively high and very similar (1.22, 1.06 and 1.12 J/m²) while the stacking fault energy on the $\{110\}$ plane is appreciably lower (0.357 J/m²). A non-planar three-fold dissociation related to the well known dissociation of screw dislocations in BCC crystals can be anticipated – see Fig. 3.

Fig. 3. Non-planar three-fold splitting of $1/2[3-31]$ dislocations on $\{013\}$ and (110) planes. Circles denote the location of partial dislocations. $\mathbf{b}$ is the total Burgers vector, $\mathbf{b}_3$ and $\mathbf{b}_{3*}$ are equivalent Burgers vectors of partial dislocations on respective $\{013\}$ planes.

Planar dissociations of the $1/2\langle 331 \rangle$ dislocations on the $\{013\}$ planes had already been discussed in our previous paper [5]. In this paper, we concentrate on possible impacts of dissociations of the $1/2\langle 331 \rangle$ dislocations that relate crystallographically to the $1/2\langle 111 \rangle$

dislocations in BCC crystals. We focus on non-planar splitting of screw dislocations and discuss an analogy between splitting in $C11_b$ crystals and core spreading in BCC metals. $MoSi_2$ was studied extensively experimentally [2] and it is a system for which the stacking faults were identified in calculations employing a density functional theory (DFT) based method [4]. But our results can be generally valid for other $C11_b$ crystals as well.

3. Slip of $1/2\langle 331 \rangle$ dislocations on $\{013\}$ planes.

In BCC metals, the core of the $1/2\langle 111 \rangle$ screw dislocation spreads into three $\{101\}$ planes of the $\langle 111 \rangle$ zone. This non-planar core is responsible for a high Peierls stress of screw dislocations, which owing to their low mobility control then the plastic behaviour of BCC metals.

In the $C11_b$ lattice, two $\{013\}$ planes are equivalent but the third plane from the $\langle 331 \rangle$ zone, the $\{110\}$ plane, is geometrically different. The non-planar splitting of $1/2\langle 331 \rangle$ screw dislocations in the $C11_b$ lattice is intrinsically asymmetrical while the core spreading of the $1/2\langle 111 \rangle$ screw dislocations in BCC crystals takes place on the equivalent $\{110\}$ planes. As the stacking fault energy on $\{110\}$ in $MoSi_2$ is significantly lower than the energies of stacking faults on $\{013\}$, the dissociation widths are much larger on $\{110\}$ than on $\{013\}$. The most important point is that for the loading axis along the $[001]$ tetragonal direction, there is no shear stress acting on the $\{110\}$ planes that can drive the dislocation. Hence, the transition to a $\{013\}$ plane will require a large contribution of thermal activation and thus at low temperatures, such as room temperature, the deformation cannot take place and brittle fracture may ensue. This explanation is consistent with the earlier suggestion in [6].

Similarly, as in the case of $1/2\langle 111 \rangle$ screw dislocation in the BCC structure, the $1/2 [3 \bar{3} 1]$ screw dislocation may dissociate in a non-planar manner on three (103) , $(0 \bar{1} 3)$ and (110) planes with similar Burgers vectors on $\{013\}$, together with the $1/4\langle 331 \rangle$ Burgers vector on (110) . Due to high values of the stacking fault energies on $\{013\}$, the non-planar threefold dissociation is much wider along (110) . These dislocation splitting practically look as a dissociation into two partials with the Burgers vectors $1/4\langle 331 \rangle$ and with the core of the second partial at the intersection as spread into two planes of the $\{013\}$ type. From the separation of the $1/4\langle 111 \rangle$ partials on the $\{110\}$ planes, the energy of stacking fault on $\{110\}$ was estimated to be 365 mJ/m^2 [7, 3] in a very good agreement with the calculated value of 357 mJ/m^2 .

It was shown in [8, 9] that contrary to ordinary dislocations, the superdislocations with the asymmetric cores in TiAl can move more easily only in one direction and not in the opposite sense. A similar behaviour can be expected also in the $C11_b$ crystals when the dislocation cores are strongly asymmetric.

Since the dislocation mobility is of primary importance, the effect of applied stresses has to be considered. Due to the applied stress, the sessile dislocation core must be converted into a glissile configuration. Obviously, such a transition is less easy for wide spread core on a non-glide plane what is the case of the $1/2\langle 331 \rangle$ dislocation moving on the $\{013\}$ plane. Due to a large size of the dissociated dislocation core, it is not feasible to simulate such a dislocation core under the applied stress by *ab initio* methods. Let us just consider what stress components act on respective planes for different orientations of the loading axis.

Fig. 4. Active slip systems for the [001] loading. The crystallographic directions and planes are presented in the stereographic projection of the cubic lattice. The directions of the $1/2\langle 331 \rangle$ Burgers vectors are marked by $X = A, B, C, D$ and the respective glide planes of the $\{013\}$ type with the largest Schmid factor by X_p or X_q .

As illustrated in Fig. 4, the glide of all four possible Burgers vectors $1/2\langle 331 \rangle$ is equally possible for the [001] loading axis. Since there is zero-stress component acting on $\{110\}$, the dislocation glide along these planes does not take place. The other two equivalent glide planes of the $\{013\}$ type are denoted in Fig. 4 as p and q . Moreover, the acting stress can not directly help to transform the dislocation core into a configuration localized on the $\{013\}$ glide plane. Hence such a transformation is hard and requires large temperatures to provide sufficient energy for the dislocation core modification. This is why the CRSS increases with decreasing temperature is observed at much higher temperatures in $C11_b$ crystals than in BCC crystals. As depicted in Fig. 2, the CRSS steeply increases from the value of about 450 MPa with decreasing temperature below 1000 °C for the [001] loading, however, this CRSS can go down to about 200 MPa for the loading along the directions different from [001] [2].

A few simple configuration of transitional dislocation core have been evaluated in [10] but it is not feasible on the basis of such simplified consideration to determine quantitatively the stress necessary for dislocation motion.

Fig. 5. Active slip systems for the [010] loading. Similar presentation as in Fig. 4, only the respective glide planes of the $\{110\}$ or $\{013\}$ types with the largest Schmid factor are marked by X_b or X_d .

The situation is different for the [010] loading – see Fig. 5. Again all four Burgers vectors $1/2\langle 331 \rangle$ can be activated and the applied stress component is non-zero also on the $\{110\}$ planes. Nevertheless, for the reasons beyond the scope of this paper the $1/2\langle 331 \rangle$ dislocations are observed to glide only on the $\{013\}$ planes and not on $\{110\}$. Apparently, the applied stress can assist the dislocation core transition from the sessile non-planar configuration into a glissile one.

Let us speculate that the dislocation loops are nucleated on the (110) plane creating the stacking fault with low energy inside the loop and must then grow in the opposite direction than the internal dislocation partial is located. When the external partial has a more complex configuration penetrating into the $\{013\}$ planes, where the other metastable stacking faults can appear, it may prefer glide along one of the $\{013\}$ planes with higher Schmid factor for the load direction deviated from [010], instead of the glide on the (110) plane of the initial dissociation. For example, for the $[0\ 15\ 1]$ load, the glide plane Ad or Dd has a higher Schmid factor than the Ab or Db planes, respectively.

Notice, that an anomalous yield stress increase with growing temperature is observed for the [001] loading axis at high temperatures in $C11_b$ disilicides (see Fig. 2). In fact, the situation is similar to the $L1_2$ intermetallics where the antiphase boundary (APB) energy is lower on the $\{001\}$ cube plane than on the $\{111\}$ glide plane. The dislocations in $L1_2$ alloys are commonly mobile on the $\{111\}$ octahedral plane but can cross-slip into the cube plane immobilizing thus temporarily the dislocation motion. The relationship of stacking fault energies on the $\{013\}$ glide plane vs. the $\{110\}$ plane is similar in $C11_b$ as the relationship of APB energies on $\{111\}$ and

{001} in the $L1_2$ alloys. Hence it is likely that the model explaining the flow stress anomaly in $L1_2$ [11] could be applied to the $C11_b$ disilicides as well.

For information on the behaviour of non-planar dislocations in different crystal structure, the reader is referred to a chapter focused on this subject in the handbooks on dislocations [12].

4. Conclusions

It has been shown that the $1/2\langle 331 \rangle$ dislocation behaviour in $C11_b$ compounds is much more complex than that of BCC $1/2\langle 111 \rangle$ dislocations. Similarly, as the cores of $1/2\langle 111 \rangle$ screw dislocations in BCC metals spread into three planes of the $\langle 111 \rangle$ zone, the $1/2\langle 331 \rangle$ screw dislocations in the $C11_b$ lattice may dissociate in a non-planar way into planes of the $\langle 331 \rangle$ zone. Hence, the Peierls stress of these screw dislocations is very high and an anomalously high yield stress can be expected if there is no shear stress driving the dislocation motion on the {110} plane. This is the case of the compressive/tensile axis in the tetragonal [001] direction. While it can be anticipated that for other orientations of the loading axis, the glide of $1/2\langle 331 \rangle$ screw dislocations may take place even at relatively low temperatures, what is apparently the case of the [0 15 1] straining.

Acknowledgments

This research was supported by the Czech Science Foundation (Project No. GAP108/12/0144) and by the Academy of Sciences of the Czech Republic (Project No. M110411202). The support of JSPS KAKENHI through grants Nos. 24246113 and 25630304, the Elements Strategy Initiative for Structural Materials (ESISM) from the Ministry of Education, Culture, Sports, Science and Technology (MEXT) of Japan, and Advanced Low Carbon Technology Research and Development Program (ALCA) from the Japan Science and Technology Agency (JST) are greatly appreciated.

References

- [1] A.K. Vasudevan, J.J. Petrovic, A comparative overview of molybdenum disilicide composites, *Mater. Sci. Eng. A* 155 (1992) 1-17.
- [2] K. Ito, T. Yano, T. Nakamoto, M. Moriwaki, H. Inui, M. Yamaguchi, Microstructure and mechanical properties of $MoSi_2$ single crystals and directionally solidified $MoSi_2$ -based alloys, *Prog. Mater. Sci.* 42 (1997) 193-207.
- [3] K. Ito, H. Inui, Y. Shirai, M. Yamaguchi, Plastic deformation of $MoSi_2$ single crystals, *Phil. Mag. A* 72 (1995) 1075-1097.
- [4] M. Čák, M. Šob, V. Paidar, V. Vitek, Stacking faults and dislocation dissociation in $MoSi_2$, in: Palm, M., Bewlay, B.P., Takeyama, M., Wiezorek, J.M.K., He, Y.-H. (Eds.), *Advanced intermetallic-based alloys for extreme environment and energy applications*, *Mater. Res. Soc. Symp. Proc.*, vol. 1128, Warrendale, 2009, pp. U07-10.
- [5] V. Paidar, M. Čák, M. Šob, V. Vitek, Theoretical analysis of dislocation splittings in $MoSi_2$, *J. Phys. Conf. Series* 240 (2010) 012007.
- [6] T.E. Mitchell, M.I. Baskes, S.P. Chen, J.P. Hirth, R.G. Hoagland, Stacking-fault energy and yield stress asymmetry in molybdenum disilicide, *Phil. Mag. A* 81 (2001) 1079-1097.
- [7] D.J. Evans, S.A. Court, P.M. Hazzledine, H.L. Fraser, Dislocation dissociation in the intermetallic compound $MoSi_2$, *Phil. Mag. Lett.* 67 (1993) 331-341.

- [8] V. Paidar, H. Inui, K. Kishida, M. Yamaguchi, Dislocation dissociation in TiAl alloys, *Mater. Sci. Eng. A* 233 (1997) 111-115.
- [9] V. Paidar, K. Kishida, M. Yamaguchi, Polarization of plastic deformation modes in polysynthetically twinned TiAl crystals, *J. Mater. Res.* 18 (2003) 702-708.
- [10] V. Paidar, V. Vitek, Dislocations in $C11_b$ and bcc lattices, in: Groma, I. (Ed.), *Dislocations 2012*, Budapest, 2012, pp. 23-28.
- [11] V. Paidar, D.P. Pope, V. Vitek, A theory of the anomalous yield behaviour in $L1_2$ ordered alloys, *Acta Metall.* 32 (1984) 435-448.
- [12] V. Vitek, V. Paidar, Non-planar dislocation cores: A ubiquitous phenomenon affecting mechanical properties of crystalline materials, in: Hirth, J.P. (Ed.), *Dislocations in Solids*, vol. 14, North-Holland, Amsterdam 2008, pp. 439-514.

Fig. 1. Tetragonal elementary cell of $C11_b$ lattice. Large circles are metallic atoms, small circles silicon atoms. The $\frac{1}{2}[3-31]$ Burgers vector and the (013) slip plane are also depicted.

Fig. 2. Temperature dependence of the CRSS for the $1/2\langle 331 \rangle$ slip on the $\{013\}$ planes. According to [3].

Fig. 3. Non-planar three-fold splitting of $1/2[3-31]$ dislocations on $\{013\}$ and (110) planes. Circles denote the location of partial dislocations. $\mathbf{b}$ is the total Burgers vector, $\mathbf{b}_3$ and $\mathbf{b}_{3^*}$ are equivalent Burgers vectors of partial dislocations on respective $\{013\}$ planes.

Fig. 4. Active slip systems for the [001] loading. The crystallographic directions and planes are presented in the stereographic projection of the cubic lattice. The directions of the $1/2\langle 331 \rangle$ Burgers vectors are marked by X = A, B, C, D and the respective glide planes of the {013} type with the largest Schmid factor by Xp or Xq.

Fig. 5. Active slip systems for the [010] loading. Similar presentation as in Fig. 4, only the respective glide planes of the {110} or {013} types with the largest Schmid factor are marked by Xb or Xd.