Urchin-like hollow-structured cobalt oxides with excellent anode performance for lithium-ion batteries

Chunyu Zhu ^{a*}, Genki Saito ^a, Tomohiro Akiyama ^a

^aCenter for Advanced Research of Energy & Materials, Hokkaido University, Sapporo 060-8628,
Japan

*Corresponding author: Tel.: +81-11-706-6842; Fax: +81-11-726-0731.

E-mail address: chunyu6zhu@gmail.com or chunyu6zhu@eng.hokudai.ac.jp (Chunyu Zhu)

Abstract

Urchin-like CoO and Co₃O₄ hollow structures with potential use as anodes in lithium ion batteries were synthesized via the facile thermal decomposition of precipitated amorphous cobalt carbonate hydroxide under either Ar or air. The morphology and, consequently, electrochemical properties of the samples were highly dependent on the precipitation temperature. The cobalt oxides, as derived from precursors that were obtained at room temperature, exhibited superior activity to those obtained at 50 °C and 80 °C because of their unique nanosized architecture. Meanwhile, CoO samples demonstrated much better cyclability and rate capability than Co₃O₄ samples, as they exhibited much higher coulombic efficiency and lower hysteresis for lithium **insertion/extraction**. The curved, short, and closely entangled nanowires of CoO sample, which was derived from room temperature precursor, yielded excellent electrochemical performance. The sample displayed a high reversible capacity of about 850 mAh g⁻¹ at a current density of 500 mA g⁻¹, a good stability through 50 cycles with a high coulombic efficiency of about 98%, and a high rate capability of 610 mAh g⁻¹ even at a rate of 3000 mA g⁻¹.

Keywords: cobalt oxides, lithium ion battery, anode material, hollow structure

1. Introduction

Current research on negative electrodes for Li-ion batteries (LIBs) is mainly focused on both enhancing the electrochemical performance of commonly used carbonaceous materials through physical and chemical manipulation and finding alternative materials for this application. The first route has been limited by the theoretical capacity of carbonaceous anodes. However, the second approach has led to the discovery of new attractive materials, including Ti-based oxides such as TiO_2 and $\text{Li}_4\text{Ti}_5\text{O}_{12}$ [1-6], metals or alloys consisted of elements like Sn and Si [7-10], and conversion reaction anode materials such as oxides [11-19], nitrides [20-22], and hydrides [23, 24]. Cobalt oxides particularly have been widely studied given their high theoretical capacities. CoO and Co_3O_4 are the most promising candidates in this class, which theoretically undergo the following reversible reactions:

However, the low capacity retention and poor rate capability underlying the conversion reactions with huge volume changes have restricted their practical application. [25, 26] One of the most successful strategies for resolving these problems has been through the fabrication of nanosized structures. A great deal of research have focused on developing materials exhibiting novel morphologies, including nanowires [27, 28], nanorods [29], nanoparticles [30], nanosheets [31], and hollow structures [13, 26, 32]. Generally speaking, hollow microstructures with nanosized subunits and designed voids [13, 26, 33, 34], exhibit especially good electrochemical properties due to the increased mass-electrolyte contact area, shortened Li^+

diffusion distance, and alleviated structural strain that results from repeated lithium insertion-extraction process. Despite significant advancements, it continues to be a challenging issue to improve the rate capacity and cycling stability of cobalt oxide materials.

In this work, we report the simple preparation of urchin-like CoO and Co₃O₄ hollow structure. Cobalt oxides were synthesized via the thermal decomposition of precipitated amorphous cobalt carbonate hydroxide under Ar or air atmospheres. Unlike previous reports, which have synthesized precursors such as Co(OH)₂, CoCO₃, and cobalt carbonate hydroxide under sealed high-pressure conditions and temperatures ranging from 90 to 180 °C [15, 31, 35-37]. Our procedure employs a scalable precipitation method at/near room temperature. The synthesized cobalt oxide materials show high reversible capacity and superior rate performance.

2. Experimental

Preparation of cobalt carbonate hydroxide: Commercially available $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, NH_4HCO_3 , and $(\text{NH}_4)_2\text{SO}_4$ were used as reagents in the synthesis. First, 20 mmol of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and 200 mmol of $(\text{NH}_4)_2\text{SO}_4$ were dissolved in 700 mL of distilled water, yielding solution A. At the same time, 200 mmol of NH_4HCO_3 was dissolved in 700 mL of distilled water, forming solution B. Then, 100 mL of ethanol was added to solution A under vigorous stirring, after which solution B was introduced. The resulting mixture was stirred in a water bath for 24 h at room temperature for sample 1 (S1), 50 °C for sample 2 (S2), and 80 °C for sample 3 (S3). The pink precipitates were collected by centrifugation and washed several times with distilled water and ethanol. Finally, the samples were dried at 60 °C over night.

Preparation of cobalt oxides: The precipitates were heated to 500 °C over 2.5 h and kept at this temperature for 3 h under either air or Ar. Heat treatment under air produced Co_3O_4 , while treatment under Ar produced CoO. The obtained oxides were denoted as S1- Co_3O_4 , S1-CoO, S2- Co_3O_4 , S2-CoO, S3- Co_3O_4 , and S3-CoO, respectively.

Material characterization: Powder X-ray diffraction (XRD, Rigaku Miniflex), scanning electron microscopy (SEM, JEOL, JSM-7400F), and transmission electron microscopy (TEM, JEM-2010F, 200 kV) were used to characterize the phase composition and microscopic morphology. The BET specific surface area was determined by nitrogen sorption using a quantachrome surface area analyzer. Thermogravimetric analysis (TG, Mettler Toledo) and differential scanning calorimetry (DSC) were carried out at a heating rate of 5 °C min⁻¹ to elucidate decomposition behavior of the precipitates. A mass spectrometry (MS) was also used to characterize the gases that resulted from decomposition.

Electrochemical measurements: Electrochemical performance was studied using a two-electrode union-joint cell based on a modified Swagelok-type design. The design is shown

in Figure S1 (supporting information). A lithium disk was used as both the counter and reference electrode. The working electrode was composed of the cobalt oxides, conductive carbon (acetylene black), and a polyvinylidene fluoride binder, in a weight ratio of 70:20:10. N-methyl-2-pyrrolidone was used as a solvent to produce a slurry of the above materials, which was then coated on a Cu foil current collector. The coated electrodes were dried under vacuum at 100 °C over night and cut into 14 mm disks, each of which had a mass of about 3 mg. Cell assembly was carried out in an Ar-filled glove box. A 1 M solution of LiPF_6 in a 50:50 (v/v) mixture of ethylene carbonate and dimethyl carbonate was used as the electrolyte. Galvanostatic charge/discharge measurements were conducted using an Arbin battery tester with a voltage range of 0.01 to 3.0 V versus Li/Li^+ and at a constant temperature of 25 °C. Cyclic voltammetry (CV) was performed using a potentiostat/galvanostat apparatus (Autolab, PGSTAT128N) set to a potential scanning rate of 0.1 mV s^{-1} and a voltage range of 0.01 to 3.0 V versus Li/Li^+ .

3. Results and discussion

3.1 Structure and Morphology

The formation of cobalt carbonate hydroxide, $\text{CoCO}_3 \cdot \text{Co}(\text{OH})_x \cdot n\text{H}_2\text{O}$, is described in the following formula:

Figure 1 (a) shows the TG and DSC curves for the precipitates, which had been analyzed under an air flow of 40 mL min^{-1} . The profiles reveal two stages of weight loss overall. The first drop in weight, which occurred below 175°C , was likely the result of combined water removal, while the second steeper drop above 175°C was resulted from the release of water from hydroxide and CO_2 from carbonate. The released gas was also confirmed by MS. Figure 1 (b) shows the typical MS spectra of H_2O and CO_2 gases released during TG measurement.

Figure 2 shows the XRD patterns for both cobalt carbonate hydroxide precursors and the final cobalt oxides. The precipitated precursors are amorphous. The XRD peaks for the samples heated at air atmosphere can be indexed to a phase of Co_3O_4 (JCPDS no. 42-1467), while the peaks for the samples heated at Ar atmosphere indicate a phase of CoO (JCPDS no. 42-1300). The decomposition reactions can be described by the following formulas:

Sample morphology was assessed using SEM and TEM as shown in Figure 3 and Figure

S2. The samples presented urchin-like structures. These structures were assembled from individual nanowires with diameters of less than 10 nm. Interestingly, the nanowires extruded outward from a shared hollow shell. The S1 nanowires were curved, short, and closely entangled, while the S2 and S3 nanowires were straight and long. This indicates that the precipitate of cobalt carbonate hydroxide has higher growth rate at elevated solution temperatures. Furthermore, the wires exhibited a pod-like structure in which crystals aggregated after decomposition due to significant gas removal and high-temperature sintering. We measured the specific surface areas for the Co_3O_4 samples using a N_2 sorption method. The results revealed that the oxides had high BET specific surface areas, with values of $62 \text{ m}^2\text{g}^{-1}$ for S1, $82 \text{ m}^2\text{g}^{-1}$ for S2, and $91.11 \text{ m}^2\text{g}^{-1}$ for S3. Figure 4 shows the BET sorption isotherms.

3.2 Electrochemical properties

Figure 5 shows the cycling performance of the oxide samples at a current density of 500 mA g^{-1} , which were cycled in a voltage range of 0.01 to 3.0 V versus Li/Li^+ . Figure 6 presents the corresponding lithium insertion and extration curves at different cycles. The initial discharge capacities for S1-CoO, S2-CoO, S3-CoO, S1- Co_3O_4 , S2- Co_3O_4 , and S3- Co_3O_4 were 980, 999, 1133, 1110, 1235, and 1372 mAh g^{-1} , respectively, all of which were larger than their theoretical values. This is usually due to the irreversible reactions, such as the formation of a solid electrolyte interface layer and solvent decomposition in the electrolyte. [15, 38] During the initial few cycles, S3 showed the highest capacity while S1 showed the lowest, illustrating a positive correlation between the activity and specific surface area. Meanwhile, clear voltage plateaus at about 1.0 and 0.7 V for Co_3O_4 and CoO electrodes, respectively, were observed, corresponding to the reaction between Li and cobalt oxides to form metallic Co and Li_2O . Although the Co_3O_4 electrodes showed higher capacities of about 1000 mAh g^{-1} for the earlier

cycles, degradation occurred rapidly with retained capacities of only 520 mAh g⁻¹ for S1-Co₃O₄, 300 mAh g⁻¹ for S2-Co₃O₄, and 249 mAh g⁻¹ for S3-Co₃O₄, after 50 cycles. On the other hand, S1-CoO and S2-CoO consistently showed values of about 850 and 710 mAh g⁻¹, respectively, during the 50 cycles, while S3-CoO continuously lost its capacity after the eighth cycle. Investigation of the coulombic efficiency for lithium deintercalation/intercalation indicated a stable efficiency of around 98% for S1-CoO, and the values decreased in an order of S1-CoO, S2-CoO, S1-Co₃O₄, S2-Co₃O₄, S3-CoO, and S3-Co₃O₄. Table 1 summarizes the typical values of the electrochemical properties. **Totally, S1 samples showed better cycling performance than S2 and S3 samples, and CoO electrodes presented better capacity retention efficiency than Co₃O₄ electrodes. Overall, the large difference in cycling stability can mainly be attributed to their structural differences. The loose structure of the S2 and S3 electrodes likely allowed for only poor contact between each particle, since these samples had straight and long nanowires that extruded outward. After several cycles of discharge and charge, the outer wires were pulverized due to the severe volume change, which led to even worse contact between particles. However, the unique structure of S1 with closely entangled nanowires allowed for better contact, at the same time, its structure could maintain necessary voids between each nanosized subunit to alleviate the volume change. Note that the high surface areas of S2 and S3 likely harmed rather than helped the materials, which increased the potential of side reactions with the electrolyte.**

To further investigate the rate capabilities of these samples, current densities were programmed to increase stepwise from 400 to 3000 mA g⁻¹ and finally drop back to 400 mA g⁻¹, as shown in Figure 7. Although the Co₃O₄ samples exhibited higher capacities in the initial few cycles, CoO electrodes presented better rate capabilities. The S1-CoO electrode showed the best rate capability overall, illustrating a high capacity of 610 mAh g⁻¹ even at a high rate of 3000 mA g⁻¹. However, this increase in current rate adversely affected the capacities for S2-CoO,

S1-Co₃O₄, and S2-Co₃O₄, reducing them to 488, 427, and 224 mAh g⁻¹ respectively at a rate of 3000 mA g⁻¹. Since that S3 samples had presented even worse performance than both S1 and S2 in the tests at a constant current density, they were not analyzed here.

Cyclic voltammetry is also used to analyze the conversion reaction and redox potentials. Figure 8 shows the CV curves of the 1st to 4th cycles for the electrodes, which were obtained over a voltage range of 0.01 to 3.0 V and at a potential scan rate of 0.1 mV s⁻¹. The observed peaks in CVs closely resemble galvanostatic discharge-charge curves in Figure 6. The main cathodic peaks correspond to reduction of cobalt oxides to cobalt metal and lithium oxide, while the main anodic peaks represent the formation of cobalt oxide. It can be clearly seen that for all samples, the CV curves of the first cycle are considerably different from those of subsequent cycles. Furthermore, the first CV peaks, especially for the cathodic ones, are significantly different between the Co₃O₄ and CoO electrodes.

In the first cycle, cathodic peaks with maximum values at around 0.85 and 0.6 V were observed for the Co₃O₄ and CoO electrodes respectively. These two peak potentials also correspond to the dominant voltage plateaus that were observed in the first galvanostatic discharge curves (Figure 6) at about 1.0 and 0.7 V for Co₃O₄ and CoO electrodes, respectively. Here, the voltage differences observed between these two analyses are due to their difference in scanning speeds. Meanwhile, in the opposing delithiation process, similar anodic peaks at around 2.1 V were observed for both the Co₃O₄ and CoO electrodes, corresponding to the oxidation of metallic Co to CoO. These anodic peaks also resemble the galvanostatic charge profiles as shown in Figure 6, illustrating potential plateaus at around 2.1 V.

The reduction peaks shifted positively in the second cycle, moving from 0.85 V to about 1.15 V for the Co₃O₄ electrodes and from 0.6 V to about 1.30 V for the CoO electrodes. As compared to the first lithiation process, covered peak areas decreased and were kept almost

constant from the second to fourth cycles. While alleviation of the polarization effect has been used to explain the observed shift in potential, oxidation peaks for both Co_3O_4 and CoO only showed a small shift, moving from 2.1 V to about 2.11–2.13 V. Apparently, there was greater alleviation of the cathodic/anodic hysteresis of the CoO electrode than for the Co_3O_4 electrode after the second cycle; the shortened voltage difference in the discharge/charge measurements further reinforces this conclusion.

4. Conclusions

In summary, novel CoO and Co₃O₄ urchin-like hollow structures were prepared by the thermal decomposition of precipitated cobalt carbonate hydroxides under either Ar or air. The cobalt oxides as-derived from the precipitated precursor at room temperature exhibited better electrochemical properties than those precipitated at elevated temperatures due to their unique nanosized architecture. Overall, CoO samples showed much better cyclability and rate capability than Co₃O₄ samples because of their much higher coulombic efficiency and lower hysteresis for lithium insertion/extraction. The CoO sample as-derived from the room temperature precursor presented excellent electrochemical performance, showing a high reversible capacity of about 850 mAh g⁻¹ at a current density of 500 mA g⁻¹, a good stability through 50 cycles with a coulombic efficiency of about 98%, and a high rate capability indicating a capacity of 610 mAh g⁻¹ even at a rate of 3000 mA g⁻¹. These cobalt oxides could potentially be applied as high capacity anode materials for LIBs, with other potential applications in gas sensors, supercapacitors, and catalysts as well.

Acknowledgements

This work was financially supported partially by the Japan Society for Promotion of Science (JSPS) and Japan Science and Technology Agency (JST).

References

- [1] L. Yu, H.B. Wu, X.W. Lou, Mesoporous $\text{Li}_4\text{Ti}_5\text{O}_{12}$ Hollow Spheres with Enhanced Lithium Storage Capability, *Advanced Materials*, 25 (2013) 2296-2300.
- [2] K. Zhu, J. Tian, Y. Liu, N. Lin, Q. Tang, X. Yu, Y. Zhu, Z. Shan, Submicron-sized mesoporous anatase TiO_2 beads with a high specific surface synthesized by controlling reaction conditions for high-performance Li-batteries, *RSC Advances*, 3 (2013) 13149-13155.
- [3] Z. Zhu, F. Cheng, J. Chen, Investigation of effects of carbon coating on the electrochemical performance of $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{C}$ nanocomposites, *Journal of Materials Chemistry A*, 1 (2013) 9484-9490.
- [4] X. Li, H. Hu, S. Huang, G. Yu, L. Gao, H. Liu, Y. Yu, Nano-sized $\text{Li}_4\text{Ti}_5\text{O}_{12}$ anode material with excellent performance prepared by solid state reaction: The effect of precursor size and morphology, *Electrochimica Acta*, 112 (2013) 356-363.
- [5] Z. Yan, L. Liu, H. Guo, J. Tan, H. Shu, X. Yang, H. Hu, Q. Zhou, Z. Huang, X. Wang, One-pot synthesis of FCNTs-wired TiO_2 nanocomposites as anode materials for high-rate lithium ion batteries, *Electrochimica Acta*, 123 (2014) 551-559.
- [6] F. Li, P. Chen, H. Wu, Y. Zhang, Cooperative enhancement of electrochemical properties in double carbon-decorated $\text{Li}_4\text{Ti}_5\text{O}_{12}/\text{C}$ composite as anode for Li-ion batteries, *Journal of Alloys and Compounds*, 633 (2015) 443-447.
- [7] G. Saito, C. Zhu, T. Akiyama, Surfactant-assisted synthesis of Sn nanoparticles via solution plasma technique, *Advanced Powder Technology*, 25 (2014) 728-732.
- [8] Z. Tan, Z. Sun, H. Wang, Q. Guo, D. Su, Fabrication of porous Sn-C composites with high initial coulomb efficiency and good cyclic performance for lithium ion batteries, *Journal of Materials Chemistry A*, 1 (2013) 9462-9468.
- [9] Y. Zhao, X. Liu, H. Li, T. Zhai, H. Zhou, Hierarchical micro/nano porous silicon Li-ion battery anodes, *Chemical Communications*, 48 (2012) 5079-5081.
- [10] M. Zhang, X. Hou, J. Wang, M. Li, S. Hu, Z. Shao, X. Liu, Interweaved $\text{Si@C}/\text{CNTs}\&\text{CNFs}$ composites as anode materials for Li-ion batteries, *Journal of Alloys and Compounds*, 588 (2014) 206-211.
- [11] L. Wang, J. Liang, Y. Zhu, T. Mei, X. Zhang, Q. Yang, Y. Qian, Synthesis of $\text{Fe}_3\text{O}_4@\text{C}$ core-shell nanorings and their enhanced electrochemical performance for lithium-ion batteries, *Nanoscale*, 5 (2013) 3627-3631.
- [12] L. Wang, Y. Li, Z. Han, L. Chen, B. Qian, X. Jiang, J. Pinto, G. Yang, Composite structure and properties of $\text{Mn}_3\text{O}_4/\text{graphene oxide}$ and $\text{Mn}_3\text{O}_4/\text{graphene}$, *Journal of Materials Chemistry A*, 1 (2013) 8385-8397.
- [13] J. Wang, N. Yang, H. Tang, Z. Dong, Q. Jin, M. Yang, D. Kisailus, H. Zhao, Z. Tang, D.

Wang, Accurate Control of Multishelled Co₃O₄ Hollow Microspheres as High-Performance Anode Materials in Lithium-Ion Batteries, *Angewandte Chemie*, 125 (2013) 6545-6548.

[14] Q. Hao, M. Li, S. Jia, X. Zhao, C. Xu, Controllable preparation of Co₃O₄ nanosheets and their electrochemical performance for Li-ion batteries, *RSC Advances*, 3 (2013) 7850-7854.

[15] S.-W. Bian, L. Zhu, Template-free synthesis of mesoporous Co₃O₄ with controlled morphologies for lithium ion batteries, *RSC Advances*, 3 (2013) 4212-4215.

[16] Y. Yu, Y. Zhu, J. Liang, L. fan, Y. Qian, Synthesis of a novel carbon network-supported Fe₃O₄@C composite and its applications in high-power lithium-ion batteries, *Electrochimica Acta*, 111 (2013) 809-813.

[17] S.-K. Park, A. Jin, S.-H. Yu, J. Ha, B. Jang, S. Bong, S. Woo, Y.-E. Sung, Y. Piao, In Situ Hydrothermal Synthesis of Mn₃O₄ Nanoparticles on Nitrogen-doped Graphene as High-Performance Anode materials for Lithium Ion Batteries, *Electrochimica Acta*, 120 (2014) 452-459.

[18] C. Zhu, G. Saito, T. Akiyama, A facile solution combustion synthesis of nanosized amorphous iron oxide incorporated in a carbon matrix for use as a high-performance lithium ion battery anode material, *Journal of Alloys and Compounds*, 633 (2015) 424-429.

[19] N. Sivakumar, S.R.P. Gnanakan, K. Karthikeyan, S. Amaresh, W.S. Yoon, G.J. Park, Y.S. Lee, Nanostructured MgFe₂O₄ as anode materials for lithium-ion batteries, *Journal of Alloys and Compounds*, 509 (2011) 7038-7041.

[20] X. Li, M.M. Hasan, A.L. Hector, J.R. Owen, Performance of nanocrystalline Ni₃N as a negative electrode for sodium-ion batteries, *Journal of Materials Chemistry A*, 1 (2013) 6441-6445.

[21] B. Das, M.V. Reddy, G.V.S. Rao, B.V.R. Chowdari, Synthesis of porous-CoN nanoparticles and their application as a high capacity anode for lithium-ion batteries, *Journal of Materials Chemistry*, 22 (2012) 17505-17510.

[22] B. Das, M.V. Reddy, G.V. Subba Rao, B.V.R. Chowdari, Synthesis and Li-storage behavior of CrN nanoparticles, *RSC Advances*, 2 (2012) 9022-9028.

[23] Y. Oumellal, A. Rougier, J.M. Tarascon, L. Aymard, 2LiH + M (M = Mg, Ti): New concept of negative electrode for rechargeable lithium-ion batteries, *Journal of Power Sources*, 192 (2009) 698-702.

[24] Y. Oumellal, A. Rougier, G.A. Nazri, J.M. Tarascon, L. Aymard, Metal hydrides for lithium-ion batteries, *Nature Materials*, 7 (2008) 916-921.

[25] M.V. Reddy, G.V. Subba Rao, B.V.R. Chowdari, Metal Oxides and Oxysalts as Anode Materials for Li Ion Batteries, *Chemical Reviews*, 113 (2013) 5364-5457.

[26] Z. Wang, L. Zhou, X.W. Lou, Metal Oxide Hollow Nanostructures for Lithium-ion Batteries, *Advanced Materials*, 24 (2012) 1903-1911.

- [27] F. Zhang, C. Yuan, X. Lu, L. Zhang, Q. Che, X. Zhang, Facile growth of mesoporous Co₃O₄ nanowire arrays on Ni foam for high performance electrochemical capacitors, *Journal of Power Sources*, 203 (2012) 250-256.
- [28] J. Chen, X.-h. Xia, J.-p. Tu, Q.-q. Xiong, Y.-X. Yu, X.-l. Wang, C.-d. Gu, Co₃O₄-C core-shell nanowire array as an advanced anode material for lithium ion batteries, *Journal of Materials Chemistry*, 22 (2012) 15056-15061.
- [29] W. Mei, J. Huang, L. Zhu, Z. Ye, Y. Mai, J. Tu, Synthesis of porous rhombus-shaped Co₃O₄ nanorod arrays grown directly on a nickel substrate with high electrochemical performance, *Journal of Materials Chemistry*, 22 (2012) 9315-9321.
- [30] B.G. Choi, S.-J. Chang, Y.B. Lee, J.S. Bae, H.J. Kim, Y.S. Huh, 3D heterostructured architectures of Co₃O₄ nanoparticles deposited on porous graphene surfaces for high performance of lithium ion batteries, *Nanoscale*, 4 (2012) 5924-5930.
- [31] X. Wang, H. Guan, S. Chen, H. Li, T. Zhai, D. Tang, Y. Bando, D. Golberg, Self-stacked Co₃O₄ nanosheets for high-performance lithium ion batteries, *Chemical Communications*, 47 (2011) 12280-12282.
- [32] M.Y. Son, Y.J. Hong, Y.C. Kang, Superior electrochemical properties of Co₃O₄ yolk-shell powders with a filled core and multishells prepared by a one-pot spray pyrolysis, *Chemical Communications*, 49 (2013) 5678-5680.
- [33] C. Zhu, G. Saito, T. Akiyama, A new CaCO₃-template method to synthesize nanoporous manganese oxide hollow structures and their transformation to high-performance LiMn₂O₄ cathodes for lithium-ion batteries, *Journal of Materials Chemistry A*, 1 (2013) 7077-7082.
- [34] C. Zhu, T. Akiyama, Designed synthesis of LiNi_{0.5}Mn_{1.5}O₄ hollow microspheres with superior electrochemical properties as high-voltage cathode materials for lithium-ion batteries, *RSC Advances*, 4 (2014) 10151-10156.
- [35] Y. Fu, X. Li, X. Sun, X. Wang, D. Liu, D. He, Self-supporting Co₃O₄ with lemongrass-like morphology as a high-performance anode material for lithium ion batteries, *Journal of Materials Chemistry*, 22 (2012) 17429-17431.
- [36] Y. Wang, H.J. Zhang, L. Lu, L.P. Stubbs, C.C. Wong, J. Lin, Designed Functional Systems from Peapod-like Co@Carbon to Co₃O₄@Carbon Nanocomposites, *ACS Nano*, 4 (2010) 4753-4761.
- [37] S. Xiong, J.S. Chen, X.W. Lou, H.C. Zeng, Mesoporous Co₃O₄ and CoO@C Topotactically Transformed from Chrysanthemum-like Co(CO₃)_{0.5}(OH)·0.11H₂O and Their Lithium-Storage Properties, *Advanced Functional Materials*, 22 (2012) 861-871.
- [38] L. Jin, X. Li, H. Ming, H. Wang, Z. Jia, Y. Fu, J. Adkins, Q. Zhou, J. Zheng, Hydrothermal synthesis of Co₃O₄ with different morphologies towards efficient Li-ion storage, *RSC Advances*, 4 (2014) 6083-6089.

Table 1. Cycling performance for the samples at a current density of 500 mA g⁻¹.

Sample	Q _{1st} (mAh g ⁻¹), charge/discharge;	Q _{max, discharge} (mAh g ⁻¹), cycle	Q _{50th, discharge}	Capacity retention;
	Coulombic efficiency	No., and Coulombic efficiency	(mAh g ⁻¹)	Q _{50th} /Q _{max}
S1-Co ₃ O ₄	831.0/1110.2; 74.85%	1078.1; 24 th ; 96.80%	520.2	48.25%
S2-Co ₃ O ₄	891.3/1235.3; 72.15%	1048.5; 9 th ; 94.93%	300.3	28.64%
S3-Co ₃ O ₄	980.8/1371.8; 71.50%	1098.7; 4 th ; 90.18%	248.6	22.63%
S1-CoO	726.8/980.1; 78.44%	864.2; 24 th ; 97.9%	789.4	91.34%
S2-CoO	784.0/999.5; 74.16%	801.4; 4 th ; 96.30%	709.7	88.56%
S3-CoO	840.1/1132.7; 74.17%	900.4; 4 th ; 91.41%	346.2	38.45%
<i>Q_{max, discharge} is the peak discharge capacity after the first cycle. Coulombic efficiency is the efficiency for lithium deintercalation/intercalation.</i>				

Figure 1. (a) TG and DSC curves for precursor decomposition under air; (b) MS spectra of water and CO₂ produced as a result of sample decomposition.

Figure 2. XRD patterns for the precipitated precursors and cobalt oxide samples.

Figure 3. (a) SEM (b) TEM images of the precipitated samples. A TEM image at a high magnification of the resultant oxide (S2, after decomposition) is also shown as a comparison. Note that the morphology of the precipitated samples and the resultant cobalt oxides is almost the same as observed by SEM or TEM under a low magnification.

Figure 4. BET N_2 sorption isotherms for the cobalt oxide samples.

Figure 5. Electrochemical properties for the cobalt oxide electrodes. (a, c) Cycling performance at a current density of 500 mA g^{-1} , and (b, d) the corresponding coulombic efficiencies.

Figure 6. Discharge/charge curves at different cycles for the cobalt oxide electrodes tested at a current density of 500 mA g⁻¹.

Figure 7. Cycling performance of S1 and S2 cobalt oxide electrodes at different current densities.

Figure 8. CV curves for the oxide samples at a potential scan rate of 0.1 mV s^{-1} .