Porous magnesium-based scaffold tissue engineering

Mostafa Yazdimamaghani ¹, Mehdi Razavi², Daryoosh Vashae³, Keyvan Moharamzadeh^{4,5},

Aldo R. Boccaccini⁶, LobatTayebi^{5,7,*}

¹School of Chemical Engineering, Oklahoma State University, Stillwater, OK 74078, USA

²Department of Radiology, School of Medicine, Stanford University, Palo Alto, California
94304, USA

³Electrical and Computer Engineering Department, North Carolina State University, Raleigh, NC
27606, USA

⁴School of Clinical Dentistry, University of Sheffield, Claremont Crescent, Sheffield, UK

⁵Marquette University School of Dentistry, Milwaukee, WI 53233, USA

⁶Institute of Biomaterials, University of Erlangen-Nuremberg, Cauerstrasse 6, 91058 Erlangen,
Germany

⁷Department of Engineering Science, University of Oxford, Oxford OX1 3PJ, UK

***Corresponding author:** Tel.: +14142888383.

Email addresses: lobat.tayebi@marquette.edu, lobat.tayebi@eng.ox.ac.uk

Abstract

Significant amount of research efforts have been dedicated to the development of scaffolds for tissue engineering. Although, at present most of the studies are focused on non-load bearing scaffolds, many scaffolds have also been investigated for hard tissue repair. In particular, metallic scaffolds are being studied for hard tissue engineering due to their suitable mechanical properties. Several biocompatible metallic materials such as stainless steels, cobalt alloys, titanium alloys, tantalum, nitinol and magnesium alloys have been commonly employed as implants in orthopedic and dental treatments. They are often used to replace and regenerate the damaged bones or to provide structural support for healing bone defects. Among the metal implants, magnesium (Mg) and a number of its alloys are effective because of; their mechanical properties close to those of human bone, their natural ionic content that has important functional roles in physiological systems, and their *in vivo* biodegradation characteristics in body fluids. Due to such collective properties, Mg based alloys can be employed as biocompatible, bioactive, and biodegradable scaffolds for load-bearing applications. Recently, porous Mg and Mg alloys have been specially suggested as metallic scaffolds for bone tissue engineering. With further optimization of the fabrication techniques, porous Mg is expected to make a promising hard substitute scaffold. The present review covers research conducted on the fabrication techniques, surface modifications, properties and biological characteristics of Mg alloys. Furthermore, the potential applications, challenges and future trends of Mg scaffolds are discussed in detail.

Keywords: Magnesium; Porous Scaffolds, Biodegradation, Bone, Cartilage

1. Introduction

There are wide variety of biocompatible materials used for different orthopaedic applications. Among them, metallic biomaterials have been specifically utilized to produce an assortment of orthopaedic implants such as the head of the femoral component of a total hip joint replacement (THJR), the tibial tray in a total knee joint replacement (TKJR), the stem of the total shoulder joint replacement, and the spinal fusion cage [1, 2]. Biodegradable metals are a relatively new class of biodegradable materials that degrade slowly in the body with a suitable host reaction elicited by the released degradation products. The biodegradable metal should disappear entirely upon fulfilling the mission of supporting the tissue regeneration leaving no implant residues; hence, no further surgical operation is needed for the implant removal [3].

Appropriate biocompatibility, low *in vivo* corrosion rate and high strength are the main parameters for the selection of a metal for the mentioned applications [4]. The principal issue of metallic implants is their loosening due to bone resorption caused by stress shielding, weak interfacial bonding between the implant and the bone, and the lack of biological anchorage for the growing tissue [2]. To address these issues, there has been much effort on the development and characterization of metal implants with microstructures and properties close to those of trabecular bone. Accordingly, these materials are called open-cell porous metals, metallic foams, metallic scaffolds, or cellular metals with three-dimensional interconnected pores. The pore sizes are typically between 200 and 500 μm with total porosity of 50–75% [5].

The stability of an implant is mainly dependent on both its mechanical strength and its fixation ability to the host tissue. In the past, such stability was mostly achieved by means of pins, screws and bone cements [6]. However, in recent experiments, researchers are attempting to improve the fixation by tissue engineering techniques [7]. For this purpose, the metal is made porous to

provide a scaffold for the bone tissue to grow into and through the pores thus making a suitable bond to the metallic implant [8]. Present tissue engineering approaches are focused on the development of porous scaffolds made of different biomaterials with the aim of replacing and restoring the pathologically altered tissues by transplantation of the cells [9, 10]. Such scaffolds for engineering of hard tissues need suitable mechanical integrity [11]. A porous 3D material provides the required pathways for cells to grow, proliferate, and differentiate, while the architecture defines the final structure of the newly formed bone [12-15]. It is worth mentioning that the spontaneous renewal of the bone is restricted to only small defects. The treatment of large bone segments caused by tumors, trauma, implant failure, or osteitis is far more challenging to be addressed. An ideal bone tissue engineering scaffold must be biocompatible, osteoconductive, and biodegradable, with a high mechanical strength to fulfil the necessary load-bearing functions [8]. Also, it must have interconnected porous networks allowing cell migration, vascularization and nutrient delivery [16]. The challenge to achieve the abovementioned properties in existent scaffolds, has made bone tissue engineering a very popular research field in the last decade in regards to the material selections and production techniques [13, 17]. Although, porosity is necessary for scaffolds, it considerably reduces the scaffold's strength which is vital, in particular, for large bone defects [18, 19]. The trade-off between the mechanical strength and the porosity is one of the main challenges in designing tissue engineered bone scaffolds [6]. At present, various types of biomaterials have been employed for this aim, which are synthetic or naturally-derived.

2. Advantages and disadvantages of the porous magnesium-based scaffold compared to other scaffolds

Early 1970s was the starting date for investigations on porous biomaterials such as ceramic [20], polymeric [21], and metallic materials [22], which identified several promising selections for porous implants that would allow bone in-growth. Although ceramics have shown outstanding corrosion properties, their inherent brittleness makes them difficult to be used for load bearing applications [16]. Porous polymeric scaffolds cannot resist the high mechanical stresses present in bone replacement operations [16]. This has led researchers to study porous metals, based on orthopaedic metallic implants, due to their greater compressive strength, fracture toughness, and fatigue resistance, which are needed for load-bearing applications [6, 16]. Due to the excellent physical and mechanical properties of magnesium compared to other permanent (non-degradable) metals, porous magnesium and Mg alloys became a good candidate to serve as a biodegradable scaffold for bone treatments [23, 24].

Among the metal implants, Mg and a number of its alloys are effective because of 1) their mechanical properties which are close to those of human bone, 2) their natural ionic content that has important functional roles in physiological systems, and 3) their in vivo biodegradation characteristics in body fluids. Some physical properties of the Mg alloys, such as high specific strength and elastic modulus, are closer to those of the natural human bone compared to other traditional metal implants [27, 28]. For example, compared to titanium alloys with the elastic modulus of 110–117 GPa, Mg alloys have lower modulus (41–45 GPa) leading to a decreased stress-shielding effect [29, 30]. Moreover, Mg alloys are 3–16 times stronger than biopolymers and, at the same time, they are more ductile compared to bioceramics, which can reduce the chance of the device fracturing throughout the implantation process. Moreover, compared to polymers, Mg alloys can encourage bone growth, which can help the implant to be properly fixed with the host bone to potentially allow full healing of bone defects after degradation [31,

32]. Mg is an essential ion in metabolism and its deficiency in the body may cause some pathological conditions. Due to such collective properties, Mg based alloys can be employed as biocompatible, bioactive, and biodegradable scaffolds for load-bearing biomedical applications [25, 26]. Such characteristics encourage employing biodegradable Mg and Mg alloys as lightweight metals for load bearing orthopaedic implants, which would remain in the body and keep mechanical stability over a time scale of 3-4 months, while the natural bone tissue heals [33, 34].

The main challenge for employing Mg and its alloys as an implant is its high corrosion rate resulting in the rapid release of degradation products in the body [35, 36]. The low corrosion resistance in physiological environments can have an adverse effect on the mechanical stability of the implant prior to bone healing [37]. Mg's low corrosion resistance also leads to the rapid release of hydrogen gas and the formation of subcutaneous gas pockets close to the implant. These side products would collect around the implant and interrupt the tissue healing [38, 39]. In addition, due to the hydrogen release, a local alkalization occurs around the implant, which affects the pH-dependent physiological processes in the surrounding area of the implant [17]. The need for relatively low corrosion resistance property, makes it necessary to take relevant measures to control its high corrosion rate [40]. This review aims to bring together recent studies on Mg and Mg alloys scaffolds with regards to production techniques, surface modifications, general properties, potential applications and future trends. If Mg scaffolds with the proper mechanical and corrosion properties can be successfully applied in bone defect treatments, a second operation process for the implant removal will be avoided; which in turn will aid the bone healing, minimize the trauma to the patients, and decrease the medical costs [41].

2. Design and production methods

2.1. Titanium wire space holder

A novel technique for the production of magnesium scaffolds using titanium wires as space holder has been recently developed by Jiang et. al. [42]. This technique includes three steps: (a) An entangled three-dimensional shape is made of titanium wire [43], (b) the prepared titanium pattern is utilized as a space holder to generate a titanium/magnesium hybrid system by infiltrating the magnesium cast, and (c) the titanium space holder is dissolved from the hybrid system by hydrofluoric acid (HF) etching at room temperature [42]. With this approach, it is feasible to formulate porous magnesium scaffolds with adjustable pore size and structure [42]. Figure 1 schematically demonstrates the abovementioned stages[42]. Similar to the shape and dimension of titanium wires, the pores in the magnesium scaffold consist of channels with pipe-like structures with diameter of approximately 270 μm . The results of mechanical tests has shown that the produced magnesium scaffolds with porosities of 54.2%, 51% and 43.2% had elastic modulus of 0.5, 0.6 and 1.0 GPa, and compressive yield strengths of 4.3, 4.6 and 6.2 MPa, respectively. Such results are comparable to the mechanical properties of natural bone, and thus offer potential applications in the treatment of bone defects[42].

2.2. Negative salt pattern molding

Kirkland *et al.* [44] have developed a new multistep technique with the aim of production of an ordered open cell porous Mg scaffold with controllable porosity and microstructure by a rapid prototyping and casting method. For this purpose, as a supersaturated paste, salt particles were made with high purity (99.5%). Computer-aided design (CAD) models were then engineered as a positive pattern by 3D printing of an acrylic polymer infiltrated in a specific salt slurry. Entire elimination of the polymer by combustion in air using a burnout cycle led to formation of a negative salt pattern which was then infiltrated with melted Mg. Following Mg solidification, the salt was dissolved by washing in NaOH solution. Similar to the macroscopic shapes of the CAD models, a porous Mg scaffold with ordered pores was formed after removal of the salt template by solvent washing. A schematic picture of the entire process is illustrated in figure 2 [44]. This research indicates that successful manufacture of topologically ordered porous salt patterns facilitated the negative replication of the ordered three-dimensional configuration utilizing pure Mg [44].

An *in vivo* study was also carried out on open porous Mg scaffolds which had been produced by a negative salt pattern molding process on biodegradable AZ91D alloy [45]. In this study, a negative template was prepared by pouring the moistened NaCl particles into a core box. The salt template was then infiltrated by Mg melt in a die casting system and the salt particles were then washed out by the NaOH solution. This technique resulted in a scaffold with 72-76% porosity and a pore size distribution of 10–1000 μm [45]. The produced Mg scaffold was implanted into the right knee and an autologous bone graft from the left patellar groove was implanted into the left knee as a control group. Mg scaffolds were significantly corroded after 3 months, and most of the implanted Mg alloy was degraded. These findings confirm that even rapid corroding Mg scaffold has reliable biocompatibility with a desirable inflammatory host response *in vivo* [45].

2.3. Powder metallurgy

Porous Mg scaffolds can be prepared using a powder metallurgy process by mixing the Mg powder and space holder agents. Normally, a two-step heat treatment is required in order to burn out the space holder agents as well as a sintering process on the pressed powder. Seyedraoufi *et al.* [46] produced a Mg-Zn alloy scaffold by blending and pressing Mg, 4wt% Zn and 6wt% Zn powders with carbamide ($\text{CO}(\text{NH}_2)_2$, 15%, 25% and 35% volume contents) with the particle size of 200–400 μm . The blended powders were pressed at 100 MPa pressure followed by a two-step heat treatment. The first step was adjusted to remove the carbamide particles by heating up to 250 °C for 4 h. The second step involved the sintering process, by heating up to 500, 550, 565 and 580 °C for 2 h. This study found a relationship between the mechanical properties and the porosity content. The compressive strength and Young's modulus of the Mg-Zn scaffolds decreased with increment in porosities at all sintering temperatures. Moreover, the temperature of 550 °C was introduced as the optimum condition for the sintering process since the highest compressive strength and Young's modulus well obtained at this temperature. The results of this study confirmed that the produced Mg–Zn scaffolds with 21–36% porosity could have superior mechanical properties comparable with that of cancellous bone [46].

An example of an open porous magnesium scaffold with interconnected pore microstructure produced by powder metallurgy for orthopedic applications is shown in figure 3, reproduced from the work of Yazdimamaghani *et al.* [47].

The main disadvantage of Mg alloys is their low corrosion resistance. The presence of porosity adversely affects the corrosion resistance by enhancing the surface area exposed to the corrosive media [48]. In order to control the degradability of Mg scaffolds produced by powder metallurgy method, a multilayer polymeric matrix composed of polycaprolactone (PCL) and gelatin (Gel) reinforced with bioactive glass (BaG) particles has been coated on the surface of Mg scaffolds by freeze drying process [49]. In this study, Mg powder was mixed with carbonate hydrogen ammonium particles as the space holder agent with volume content of 35% and particle size of approximately 150–300 μm . The mixed powders were then pressed at a pressure of 400 MPa. Similar to other powder metallurgy techniques for production of Mg scaffolds, the burning out process was carried out at 175 °C followed by a 600 °C heat treatment for sintering. When the samples were immersed in a simulated body fluid for bioactivity tests, the Mg scaffold coated with PCL-BaG presented the best conditions for the deposition of biominerals. Both uncoated and Mg scaffold coated with the PCL-BaG entirely corroded after 3 and 7 days. However, approximately 87% of Mg scaffold coated with multilayer PCL-BaG/Gel-BaG coating remained intact after 14 days of immersion in A simulated body fluid (SBF)[49].

2.4. Hydrogen injection

In hydrogen injection method, Mg melt is poured in a crucible under vacuum, and high pressure hydrogen is introduced into the chamber [50]. As demonstrated in figure 4, the melt is superheated in anticipation that the dissolved hydrogen reaches its saturation, and then it is solidified into a water-cooled copper mould. Accordingly, the melt is solidified upwards unidirectionally and straight pores are formed by supersaturated hydrogen during solidification.

Changing the cooling part position would change the direction of pore growth [50]. Biological characterization on this type of Mg scaffolds by Guet *al.*[51] indicated an acceptable corrosion rate and biocompatibility. However, there are some concerns about the absence of interconnected pores in the scaffolds made by this method of production.

2.5. Laser perforation

Laser perforation technique has been used to produce designed porous Mg scaffolds [11] since Mg has been known as a machinable metal. Porous Mg scaffolds can be developed by laser perforation system by means of a programmable multifunctional laser processing machine on the casted Mg ingots. The advantage of this method is the simplicity to control the structure, size and shape of pores. Normally, interconnected and homogeneous pores with round and honeycomb-like structure can be formed by this technique [11]. Genget *al.*[11]produced a Mg scaffold with interconnected pores and honeycomb-like configuration. The optimum parameters in this study were the pulse frequency of 1-10 Hz, width of 0.3 ms, and the effective output of 100 W. Aligned long cylindrical pores with diameter of about 0.5 mm were manufactured within the Mg scaffold. The results confirmed a suitable behavior in mechanical properties due to the fewer flaws and voids resulting from the control of the fabrication technique [11]. Table 1 summarizes the techniques for producing porous Mg-based scaffolds.

3. Biomedical coatings on magnesium scaffolds

As aforementioned above, the main disadvantage of magnesium and magnesium alloy based scaffolds is their high corrosion rate, due to the high electrochemical activity of magnesium metal. Corrosion of magnesium alloy is rapid and inhomogeneous, as it can be localized

corrosion. The formation of hydrogen gas cavity due to the faster corrosion rate in comparison to the absorption rate is often observed in Mg scaffolds. In addition, an alkaline pH shift adjacent to the magnesium implant would result in damage to the host tissue. This has led to limiting the potential medical application of magnesium as implant, stents, and bone screws. Corrosion and degradation can drastically reduce the ultimate strength and fatigue life of implants. Increasing the surface area by introducing porosity generally increases the corrosion rates and accelerates the mechanical failure of the implant. To address the long-term safety of porous scaffolds, alloying and surface modification of magnesium scaffolds can be useful approaches. Altering the microstructure and composition by alloying, and surface modification of the scaffolds prior to the implantation, are conducted by a variety of materials and methods [16, 52, 53]. Surface modifying the scaffolds increases the corrosion resistance. The surface modification can be applied by two different processing techniques of conversion coatings or deposited coatings[27]. Conversion coatings are in situ chemical or electrochemical interactions of the magnesium scaffolds with the environment which leads to the formation of an inorganic ceramic-like coating on the surface. Deposited coatings are mostly organic coatings applied by different methods such as spraying, painting, spin coating, dip coating, or immersion. Materials used for coating should have specific characteristics such as good corrosion protection, biocompatibility, osseointegration, bioactivity, and controlled biodegradability. Hornberger *et al.* have comprehensively reviewed the different coating methods [27].

Calcium phosphates (CaPs) with similar composition of the bone mineral component possess several beneficial properties such as excellent bioactivity and osteoconductivity for bone-graft applications [54]. Promoting new bone formation and developing strong interfacial bonding

between CaPs biomaterials and the host bone tissue makes this material an appropriate choice for surface modification of magnesium scaffolds.

Hydroxyapatite [$\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$, HA], one of different phases of the calcium phosphates (CaPs), has been investigated extensively. Surface modification by hydroxyapatite coating is an effective method for enhancing the corrosion resistance of magnesium scaffolds. Although hydroxyapatite has exceptional biocompatibility, bioactivity properties, and similar chemical and structural nature as bone, it suffers from high brittleness and low strength which limits its application in load bearing conditions[55]. Therefore, utilizing biodegradable magnesium scaffolds with appropriate mechanics, coated with hydroxyapatite to enhance corrosion resistance, and to enhance bone forming ability can be a promising scaffold for bone tissue engineering in load bearing applications[56]. Different techniques such as sputtering process, electrophoretic deposition, sol-gel process, and biomimetic deposits can be used to coat metallic surfaces by hydroxyapatite. However, due to the poor heat resistance of magnesium, none of these techniques can be used efficiently for hydroxyapatite coating of magnesium scaffolds since a high temperature treatment will be required to densify the coating[56]. Therefore, one of the promising options to surface modify magnesium scaffolds is using electrochemical deposition which includes low deposition temperature and is capable of creating uniform coatings with controlled thickness and chemical composition [56-58].

Hydroxyapatite crystal structure size and morphology can also be manipulated by electrolyte concentration and electrochemical potential. Recently, researchers found that the morphology of hydroxyapatite coating can affect its osteoconductivity and biocompatibility. Healing process of bone defects can be accelerated by loose hydroxyapatite coating which allows easier infiltration and ingrowth of new bone tissue. [57-59].

One of the main concerns of using magnesium scaffolds is the amount of Mg ions and hydrogen gas released by its corrosion. Incorporating Zn element in contents of less than 3% can improve the corrosion resistance [60] and the mechanical properties of magnesium scaffolds [56, 61]. Seyedraoufi *et al.* [59] investigated and optimized different parameters of pulse electrodeposition such as peak current density, temperature, and duty cycle to surface modify porous Mg-2wt.% Zn scaffolds with nano hydroxyapatite ($\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$) coating upon post-treatment in alkali solutions. Porous Mg-2Zn (wt.%) scaffolds were prepared using a powder metallurgy process. Under optimized pulse electrodeposition of 1 hour, 40 mA cm^{-2} peak current density, 85°C temperature, and 0.1 duty cycle, followed by post-treatment in alkali solutions, uniform nano hydroxyapatite coatings were generated on the scaffolds. As shown in figure 5, perpendicularly needle-like hydroxyapatite crystals with 2-3 μm length with less than 100 nm in diameter were created on the surface of the scaffolds. Loose needle-like hydroxyapatite crystals highly resemble the inorganic apatite structure of natural bone [59].

Tricalcium phosphate [$\text{Ca}_3(\text{PO}_4)_2$, TCP] as coating material exhibits desirable biocompatibility and bioactivity. However, TCP shows poor mechanical strength and crack-growth propagation resistance. In contrary to HA which has poor rate of biodegradability, TCP is biodegradable. TCP has three polymorphs and among them, β -TCP with hexagonal crystal structure and R3CH space group has a slow-degrading rate [62]. In addition, β -TCP shows desired osteoimmunomodulatory properties which activates the immune response leading to accelerated bone healing process. Favorable osteoimmunomodulatory properties adjust the balance between osteogenesis and osteoclastogenesis which improve bone regeneration. Chen *et al.* prepared [63] magnesium scaffolds with the laser perforation technique and coated them with β -TCP, in an attempt to exploit the advantages of β -TCP coating such as osteoconductivity, biocompatibility,

high chemical stability, slower degradation rate compared to magnesium, and osteoimmunomodulatory[63]. In this study, the importance of β -TCP coating in immune cells and bone cells response was emphasized, and the role of immune cells in adjusting osteogenesis and osteoclastogenesis balance was investigated. Osteoimmunomodulatory property of β -TCP coating demonstrated the activated M2 phenotype of macrophage and release of bone morphogenetic protein 2 (BMP2). Subsequently, osteogenic differentiation of bone marrow stromal cells was observed due to the presence of BMP2 [63, 64]. Activated macrophages secrete BMP2 and transforming growth factor b (TGF-b). It has been shown that the discharging macrophages result in the inhibition of *in vivo* bone formation [65-68]. Thereby, magnesium scaffolds coated with β -TCP showed desired osteogenesis over osteoclastogenesis, due to the upregulation of osteoinductive molecules secreted by macrophages in contact with β -TCP coating [63].

In a similar study, Genget *al.* manufactured [69]interconnected porous magnesium scaffolds utilizing laser perforation technique and coated the samples with β -TCP [69]. *In vitro* biodegradation mechanism of surface modified scaffolds was evaluated and the osteosarcoma cell (UMR106) attachment and proliferation were studied. Figure 6a shows a macrograph of a fabricated porous magnesium scaffold with cylindrical aligned pores with 48% porosity before surface modification. Figure 6b is a SEM image of the β -TCP coated scaffolds obtained by chemical process of immersion in the mixture of $\text{Ca}(\text{NO}_3)_2$ and $\text{Na}_2\text{HPO}_4 \cdot 12\text{H}_2\text{O}$ after alkali-heat pretreatment.

Comparing the pH change of uncoated magnesium scaffold with coated scaffolds incubated in cell culture medium indicates that the pH of the β -TCP coated scaffolds was similar to the pH of the control group, while the uncoated scaffolds have significantly increased pH value. This result

confirms the barrier property of β -TCP which increases the corrosion resistance of the scaffold and decreases the magnesium ion release, and control the pH of the medium [69]. In addition, β -TCP coating acts as reservoir of calcium and phosphate ions around the scaffolds and triggers the bone growth. It has been reported that the local supersaturation of the body fluid with calcium and phosphate ions enhances the growth of bone [70, 71].

Degradation of β -TCP coating on the magnesium scaffold is coincident with the regrowth of new calcium and phosphate coating on the surface. This effect occurs by two simultaneous mechanisms namely increased nucleation and increase of pH values. First, degradation of β -TCP increase the magnesium ions release, which in turn leads to an elevated calcium concentration that is desired for nucleation and growth of the Ca-P compound on the magnesium scaffold [69, 72-74]. Concurrently, enhanced ionic activity of apatite at higher pH, due to the degradation of magnesium, can increase the apatite nucleation and formation of new Ca-P coating [75].

In an attempt to decrease the degradation rate and to increase the possible application potential of magnesium scaffolds in the field of tissue engineering, further biomedical coating studies have investigated various biodegradable materials such as polycaprolactone (PCL) [47, 76], polycaprolactone-bioactive glass (PCL-BaG) [40], and gelatin-bioactive glass/polycaprolactone-bioactive glass (Gel-BaG/PCL-BaG) coatings[49]. The results showed drastic enhanced corrosion resistance and compressive strength during the immersion in physiological saline solution (PSS). The open porous magnesium scaffolds were manufactured by a powder metallurgy technique. While the uncoated scaffolds degraded completely and lost 100% weight after 72 h, coated scaffolds with 3% w/v and 6% w/v PCL showed 36% and 23% weight loss, respectively. In addition, 41% and 83% improvement in compressive strength, and 24% and 100% enhancement in the elastic modulus have been observed, respectively, in 3% w/v and 6%

w/v PCL coated magnesium scaffolds [47, 76]. In addition, incorporating bioactive glass (BaG) into the coating layer led to improved bioactivity and mechanical integrity compared to the uncoated scaffold. Formation of an apatite layer on surface modified scaffolds was observed after immersion in SBF, which should stimulate biological bone ingrowth and prevent micro-cracks and pore channels propagation [40]. In the next step, utilizing a freeze drying process, gelatin (Gel)-bioactive glass (BaG) porous layer was added on top of the PCL-BaG layer of the porous magnesium scaffolds. As shown in the SEM images of figure 7, porous structure of magnesium scaffolds, PCL-BaG inner layer coating, and Gel-BaG outer layer are distinguishable from each other. While the Mg scaffold/PCL-BaG/Gel-BaGcoating almost remained intact after 14 days in SBF, the non-coated Mg scaffold was fully degraded after 3 days and Mg scaffold/PCL-BaG was fully degraded after 7 days. In conclusion, the Mg scaffold with PCL-BaG/Gel-BaGcoating showed better bioactivity, higher mechanical integrity and corrosion resistance compared to other scaffolds [49].

4. General properties and evaluations techniques

4.1. Mechanical properties

An appropriate mechanical strength and stability is required for scaffolds being used in musculoskeletal tissue engineering. Among all possible candidates, magnesium alloys attract considerable attention due to their desirable mechanical and biodegradation properties. During the last decades, researchers have shown increasing interest towards magnesium as a potential biodegradable material for bone and cartilage tissue engineering [29, 40]. In terms of mechanical properties, magnesium alloys show better characteristics than biodegradable polymers such as

polyglycolic acid (PGA) or polylactic acid (PLA). Furthermore, degradation and biomineralization of bioactive materials on the surface on the magnesium scaffolds promote osteoblastic activity and ingrowth of the new tissue [35, 45].

Cancellous bone is an interconnected porous structure with porosity varying within the range of 30% to 95%. It is well known that inclusion of porosity into the implants to make the scaffolds, can increase the similarity to the bone structure and enhance the ingrowth of new tissue, however, it can also compromise the mechanical properties. Scaffolds must have adequate strength and stiffness to tolerate the physiological loads. The main concern about the use of metallic implants, such as magnesium alloys, is the mismatch of Young's moduli of the implants and the adjacent bone tissue. This inconsistency between mechanical properties results in the inadequate loading of the bone that leads to bone stress shielding, can subsequently cause bone resorption, implant loosening, formation of cracks within the implant, and implant migration [77-80]. Thus, implants should have appropriate strength and stiffness matching those of bone tissue. By changing the material of the implant, one can achieve optimal elastic moduli close to the bone to prevent stress shielding. When stress shielding is reduced by changing the material, stiffness mismatch can still exist. In order to overcome the stiffness mismatch, researchers have made porous implants (scaffolds). Porous materials have reduced stiffness mismatches and increased the tissue scaffold interaction by bone ingrowth which helps in the fixation of implants in their place [16]. However, it is noteworthy to mention that the scaffold suffers from drastic decreases in fatigue strength.

It has been observed that the production method of porous magnesium can affect the mechanical behavior and the collapsing mechanism of the sample. A short elastic deformation in the initial stages of the stress-strain curves of compressive loading has been observed in specimens

produced by the mechanical perforation method [81] and by melt casting [42]. This behavior indicates the bulk deformation of scaffolds under the compression load, however, porous magnesium specimens produced by metal foaming method [82] and powder sintering method [48] show local collapse of pores with shortened elastic deformation. Following the linear elastic deformation ending at the yield strength, normally magnesium samples exhibit a long plateau of constant stress [82].

Changing the pore size, pore shape, porosity, and pore distribution can affect the mechanical properties [48, 83, 84]. Increasing porosity results in the decrease of compression strength, yield strength, and Young's modulus [48, 83, 84]. The mechanical properties of porous magnesium prepared by the green compacts method using carbamide particles as the space holder and under 100 MP uniaxial pressure were studied to demonstrate the dependence of mechanical properties on pore size and porosity [48]. Scaffolds with pore size of 70–400 μm and porosity of 35–55% were prepared. Compressive strength tests showed a decrease in compressive strength and Young's modulus with increase in porosity and pore size. Scaffolds with 35% porosity and pore size of 250 μm demonstrated 1.8 GPa of Young's modulus and 17 MPa peak stress, and scaffolds with pore size of 73 μm and porosity of 45% showed 1.3 GPa of Young's modulus and 16 MPa peak stress. Considering the mechanical properties of cancellous bone with compressive strength and Young's modulus of 0.2–80 MPa and 0.01–2 GPa [85], mechanical properties of porous magnesium fall in the range of cancellous bone which makes this material a suitable option for hard tissue regenerative scaffolds.

4.2. Bio-corrosion behavior

In contrast to inert materials such as PLA, the increase in bone formation and decrease in healing time observed with magnesium implants indicates the potential osteoconductivity and bioactivity of magnesium [29, 35]. The Osteoconductivity of magnesium is induced by the precipitation of calcium phosphate on the surface of the implants in an *in vitro* environment due to corrosion [86, 87]. Biomimetic calcium phosphate coatings enhance osteoblast response, impart osteoconductive capacity, and reduce the healing time for bone defects. Moreover, enhanced cell attachment and ingrowth due to calcium phosphate precipitation can lead to reduced corrosion rate [29].

Exposing pure magnesium to air will result in the formation of a gray oxide film of magnesium hydroxide on the surface. Recent studies [31, 34, 49, 88-95] proposed the formation of magnesium hydroxide and release of hydrogen bubbles in the electrolytic physiological environment upon degradation of magnesium, through the oxidation and reduction reactions which are summarize in the following reactions:

Oxidation reaction: $\text{Mg} \rightarrow \text{Mg}^{2+} + 2\text{e}^{-}$

Reduction reaction: $2\text{H}_2\text{O} + 2\text{e}^{-} \rightarrow \text{H}_2(\text{g}) + 2\text{OH}^{-}$

Combination reaction: $\text{Mg}^{2+} + 2\text{OH}^{-} \rightarrow \text{Mg}(\text{OH})_2$

Magnesium hydroxide is not highly soluble in water. The reaction between magnesium hydroxide and chlorine ions from the tissue fluid or any simulated biological fluids leads to production of highly water soluble magnesium chloride. The release of hydroxide ion from magnesium hydroxide upon reaction with chlorine ions results in the local enhancement of the pH value near the host tissue. The presence of calcium and phosphate ions in the tissue fluid triggers the production of $\text{Mg}_x\text{Ca}_y(\text{PO}_4)_z(\text{OH})_n$ compounds, such as calcium phosphate and/or calcium

magnesium phosphate by the interaction between Mg^{2+} , Ca^{2+} , and PO_4^{3-} . These complex bioactive mineral products form a deposition layer on the surface of magnesium scaffolds and inhibit further corrosion and increase of pH value. It has been shown that degradation, and consequently deposition of the bioactive passive layers containing calcium, promotes osteoblast growth [96, 97].

4.3. Cell/scaffold interactions

For newly designed materials, cytotoxicity tests including extract based assays, direct contact, and indirect contact for investigating the cell-scaffold interaction, are conducted by applying International Organization for Standardization (ISO) standards 10993-5 and 10993:12. Although direct contact cell cytotoxicity methods may introduce additional information, extract based assays are the most common ones [98]. These cytotoxicity testing standards are developed for non-degradable materials, thus applying them on the degradable magnesium scaffolds may not be suitable. Upon immersion of pure magnesium inside the extraction medium, visible gas evolution is detectable. Strong degradation locally increases the pH value which is evident by tuning normally red medium to colorless medium by the deprotonization of the phenol red. Rapid degradation of magnesium scaffolds in aqueous environment and cell culture media produces highly concentrated extracts with magnesium, strong hydrogen production, very high osmolalities and pH-values.

Osmotic shock by this harsh environment can be lethal to the cells *in vitro* and makes the *in vitro* cell culture evaluation nearly impossible for magnesium scaffolds with ISO standards. Active transport processes in *in vivo* environments regulate most of these fluctuations. Therefore, most research groups bypass the *in vitro* tests for magnesium scaffolds and directly perform *in vivo*

animal tests, which may be problematic from an ethical point of view. In order to address these issues one can use an *in vitro* bioreactor with dynamic flow system to simulate the human body situation. However, bioreactors are not always available and the need for *in vitro* experiments for magnesium scaffolds can be addressed by establishment of reliable test systems. Fischer *et al.* [99] proposed that *in vitro* cytotoxicity tests for magnesium materials must be done under physiological conditions corresponds to in cell culture medium containing 10% fetal bovine serum. A physiological condition is a CO₂ level of 5%, an O₂ level of 20%, temperature of 37 °C, and relative humidity of 95%. As proposed, 10 times more extraction medium should be used comparing to the recommended volume by the ISO standards (EN ISO standards 10993:5 and 10993:12 suggest specimen weight to extraction medium to be 0.2 g/mL) to have reliable results for cytotoxicity [99]. Dilution of the pure extracts decreases the osmolality and high magnesium concentration to avoid cell cycle arrest or apoptosis. It is noteworthy to remember that a high dilution may eliminate most toxic ionic content from the extracts and prevent real cytotoxicity evaluation. On the other hand, cytotoxicity studies on biodegradable magnesium scaffolds by the tetrazolium-salt-based assays such as MTT (3-(4,5-dimethyl-2-thiazolyl)-2,5-diphenyl-2H-tetrazolium bromide) and XTT (2,3-bis(2-methoxy-4-nitro-5-sulfophenyl)-5-((phenylamino)carbonyl)-2H-tetrazolium hydroxide) are prone to experimental errors. Corroded magnesium can interact with tetrazolium salts and convert it to formazan, causing misleading results in static *in vitro* assays. Therefore, using these assays should be conducted with high level of caution. It is suggested [100] to use luminescence-based (BrdU) cytotoxicity assays which do not have any interference with the corroding magnesium.

In vitro studies of biodegradable open porous magnesium scaffolds confirmed the different response of human osteoblast cells (HOB) and fibroblastic cell line (L929) to osmotic and ionic

changes. HOB showed better survival in higher osmotic solutions but exhibited lower proliferation rate comparing to L929 cells in high osmotic extracts [101]. This behavior may be explained by the cell-type-dependent proliferation to cell volume. Cell proliferation can be altered by osmotic swelling or shrinkage. Osmotic swollen cells exhibit more cell proliferation compared to osmotic shrunk cells. Osmotic shrunk cells demonstrate inhibited or delayed cell proliferation in hyperosmotic solutions [102].

Zhanget *al.* Showed extracellular magnesium ions have regulatory effects on intracellular free ionized calcium ($[Ca^{2+}]_i$) [103]. Magnesium ions can affect the $[Ca^{2+}]_i$ and K^+ channels. It was confirmed that $[Mg^{2+}]_o$ regulates the level of $[Ca^{2+}]_i$ and modulate cell shapes and metabolism of cultured vascular smooth muscle cells to control vascular contractile activities. It is known that $[Ca^{2+}]_i$ concentration can critically change the cell cycle, and K^+ and Cl^- channels can influence cell proliferation and cell cycle progression [101-104]. By having these facts in mind and considering the release of magnesium ions upon corrosion of the scaffold, one can correlate the effect of excess magnesium ion inside the extracts and the cell cycle arrest or apoptosis. Selective interaction of magnesium ions with each type of cell culture media extracts can change the behavior of the magnesium ions, resulting in distinct cytotoxicity responses for different cell types. For instance, corrosion of magnesium scaffolds in RPMI-1640 +10% FBS and DMEM +10% FBS showed similar degradation rate under the same cell culture conditions. However, significant differences in magnesium ion concentrations in two extracts were observed [101]. Both original cell culture media, namely RPMI-1640 +10% FBS and DMEM +10% FBS, have similar magnesium ion concentration and protein content. The difference in magnesium ion concentration between two media can be explained by the higher concentration of L-glutamine amino acids in DMEM, which can create complexes with magnesium [101].

4.4. In vivo assessments

The host tissue interaction with scaffolds, the fate of the biodegradable scaffolds, the ingrowth of newly formed tissue, in addition to neoangiogenesis, and inflammatory response, are important aspects of tissue engineering which should be considered for each scaffold designed for a specific application.

Three distinct phases have been recognized for the host tissue interaction with biodegradable scaffolds. The first phase occurs within the first two weeks of implanting the scaffolds and it is mainly characterized by the initiation and development of an inflammatory host response. This response is basically independent of the degradation rate of the scaffolds. This early phase response is indicated by the presence of plasma cells, lymphocytes, polymorphonuclear leukocytes, and monocytes. The second phase is detected by the predominance of monocytes and their differentiation to phenotype of macrophages, fibrous tissue encapsulation of the implants and neo-angiogenesis. The length of the second phase is determined by the rate of biodegradation of the implanted scaffolds. Increase in the degradation time would increase the length of the second phase. In addition, the presence of the foreign body giant cells at the surface of the scaffolds is evident in the second phase by fusion or joining the macrophages together. The third phase starts following the last steps of the degradation of the scaffold when the scaffold loses its integrity and mechanical properties. The formation of a fibrous capsule is accelerated in the third phase. In this step, the scaffolds totally lose their mechanical properties and the newly formed tissue replaces the scaffold. The scaffolds breakdown into particles, which undergo macrophage phagocytosis [105].

As mentioned above, magnesium is naturally found in bone and it is the fourth most abundant cation in the human body [106]. Witte *et al.* studied the behavior of host tissue response to open porous magnesium alloy AZ91D scaffolds during 3 and 6 months of implantation. Figure 8 shows the experimental design and porous scaffold prepared by casting in a negative salt pattern molding.

Although 2 weeks after the implantation gaseous bubbles were observed nearby the rabbit knees, all these bubbles disappeared within 1 week. No adverse events such as body weight loss, abnormal behavior, inflammation, damage to neighboring tissues, enhanced cell infiltrate into scaffold site, osteolysis, and sterile sinuses were detected. Chloroacetate esterase histochemistry was used for detecting neutrophil granulocytes, which represent the initial stage in inflammatory response, and no significant inflammatory processes were observed for magnesium scaffolds. Healing happens in 3 consequent stages of formation of fibrous capsule, angiogenesis, and bone formation. Fibrous capsule formation, which was accompanied with newly formed blood vessels, and later bone formation and ingrowth into the degraded scaffolds were detected in Mg and Mg alloy scaffolds. New bone formation at the interface of magnesium scaffolds due to osteoconductive properties advocates the fibrosis elimination and complete replacement with new bone tissue in later stages of the healing process [45]. Biomineralized bone volume detected by von Kossa stain in the vicinity of the degrading magnesium scaffolds revealed significantly higher density of bone growth comparing to the control side. This is suggested to be due to the increased osteoblastic and osteoclastic activities in the proximity of the degrading magnesium scaffold which resulted in formation of more mature bone structure. Compared to the control site, reduced trabecular separation and higher trabecular number were observed, indicating

formation of a more mature bone with a superior mechanical properties and osseointegration process [107, 108].

Liu *et al.* [89] studied the *in vivo* biodegradability and osteogenicity of porous magnesium scaffolds by implantation inside the femoral condyle of male New Zealand white rabbits [89]. Porous magnesium scaffolds were prepared by machining the extruded pure magnesium bars and surface modified by microarc oxidation technology. Histological examination on the heart, kidney, spleen, and liver exhibited normal morphology, confirming good biocompatibility of the both porous magnesium scaffold and control scaffolds. However, significant differences in degradation and new bone formation between magnesium scaffolds and control scaffolds were detected. This has been confirmed by micro-CT scans of 3 months post-operation scaffolds (figure 9).[89].

It is noteworthy to mention that in the X-ray images of the magnesium scaffold, bubbles appeared around the implanted scaffolds after 2 weeks due to the degradation of magnesium and formation of hydrogen gas. Although surface modifications was used to reduce the degradation rate and to decrease hydrogen generation, formation of mild swelling in rabbits knees starting from 2 weeks and persisting for 2 months, indicated inadequate thickness of magnesium oxide and surface treatment [89]. However, these findings show that even fast degrading magnesium scaffolds demonstrate good biocompatibility, suitable inflammatory response, and bone regeneration, which makes open porous magnesium scaffolds good candidates for bone and cartilage tissue engineering [45].

5. Applications

5.1. Bone

One of the most important advantages of the biodegradable magnesium scaffolds over conventional permanent metal scaffolds is total *in vivo* corrosion of the scaffolds and elimination of the additional surgery step of scaffolds removal. This will help to reduce the health risks, costs, and improve the patient compliance [47, 99, 101].

In long term applications such as bone implants, the magnesium scaffold must have slow rate of degradation to allow cell proliferation and ingrowth. Increased surface area in porous scaffolds leads to an increase in the corrosion rate. To control the degradation rate in such application, magnesium alloys are prepared. Incorporating yttrium to magnesium can increase the corrosion resistance. It is well known that yttrium element stimulates the grain refinement, increases cytocompatibility, and reduces the corrosion rate of magnesium [109-111]. Bobeet *al.* added 4 wt.% yttrium to magnesium and made open porous scaffolds by liquid phase sintering technique using magnesium short fibers [101]. As shown in the figure 10a, fibers with a diameter of 100-250 μm and a length of 4–8 mm under argon atmosphere were manufactured utilizing crucible melt extraction technique. Deposition of fibers on a tantalum substrate with an MgO sieve, with further liquid phase sintering, and subsequently additional heat treatment produced a bulk porous material which was finally cut into cylindrical porous scaffolds as shown in figure 10d. Light microscopy determined 58 to 63% porosity for the scaffolds. Mechanical analysis of the prepared scaffolds showed Young's modulus within the range of human cancellous bone, and compression strength exceeding that of human cancellous bone.

In vivo implantation of open porous scaffolds in femoral condyle of female rabbits demonstrated no severe clinical signs of gas cavities or inflammation. In general, rabbits showed normal foreign body giant reaction towards the implanted scaffolds with no pathological changes in the histology of the internal organs including lung, liver, pancreas, kidney, heart, spleen, and

intestine or any blood abnormalities. In addition, no signs of necrotic tissue or fibrous encapsulation were found at 6 weeks or at 12 weeks after implantation. Moreover, osteoblasts and osteoclast cells remodeling bone around and inside the scaffold were observed at 6 and 12 weeks respectively. However no signs of gas cavities were detected clinically. Postoperative microtomographs (figure 11) showed some entrapped gas cavities after 6 weeks around the implanted scaffolds. These gas cavities demolished within 12 weeks. Slow *in vivo* scaffold degradation and almost intact scaffolds after 6 weeks were detected by microtomography. Figure 11b shows evidence of new bone formation adjacent to the scaffolds. Slow *in vivo* scaffold degradation proceeds to 12 weeks and at this time only 7% volume of the scaffold remained.

5.2. Cartilage

Hyaline articular cartilage tissue lacks the sufficient regenerative potential due to absence of blood vessels in their structure. Therefore, all required nutrition agents and growth factors are being transferred by diffusion from the bone marrow and remote blood vessels. Cartilage nutrition is supported by the subchondral bone plate, thus any damages such as osteochondral defects can prevent regenerating cartilage. In such cases, using a biodegradable scaffold as the subchondral bone plate can enhance the cartilage healing process [112-114]. Ideal scaffolds in subchondral bone plate tissue engineering should provide adequate mechanical stability, appropriate pore size, sufficient porosity, and optimized programmed degradation. Gradual degradation provides more space for ingrowth of new tissue and blood vessels [47, 115-117].

The degradation profile of scaffolds for cartilage repair should warrant two months of suitable mechanical integrity, and afterwards rapid degradation to allow the infusion of nutrition and reparative cells towards the healing site. Magnesium scaffolds were studied as the subchondral

bone plate to induce cartilage repair [118]. Magnesium alloy (AZ91) with 75% porosity showed rapid degradation at twelve weeks postoperatively. Although no signs of negative influence were detected at the adjacent cartilage tissue, no adequate subchondral bone plate regeneration was observed. Furthermore, histological studies showed no significant cartilage regeneration above the degraded magnesium scaffold. Similar results have also been observed using autografted cancellous bone as the replacement of the subchondral bone plate [118]. This finding is surprising since the autograft is believed to be the best and first option for regenerative tissue engineering due to its immunocompatibility. Application of autografts is mainly limited by inadequate availability, and donor bone site morbidity [119, 120]. Comparison studies using autografted cancellous bone and magnesium scaffold for osteochondral defects confirm the necessity for the unconstrained access to nutrition and reparative cells from the bone marrow [118, 120]. Therefore, the designed scaffolds should satisfy the need for local blood circulation and bone marrow accessibility. On the other hand, in the untreated osteocartilaginous defect with the highest accessibility to bone marrow cavity, no reproduction of subchondral bone in the central part was observed [118]. Magnesium scaffolds with optimal porosity should provide appropriate mechanical support [47, 48], osteoinductive properties, excellent biocompatibility [121], biodegradability and bioresorbability [122]. Thus, such scaffolds can be designed to be suitable candidates for subchondral bone plate replacement.

6. Conclusion and future work

Porous scaffolds for biomedical applications such as orthopedic reconstructive surgery continue to attract research attention, which is confirmed by the ever-increasing number of publications on this subject. Metallic biomaterials have great potential as the basic materials to develop such

scaffolds, especially for load-bearing applications due to their high mechanical properties compared to biodegradable polymeric materials. Recently introduced Magnesium and its alloys appear to have the potential to be suitable biodegradable metallic materials with similar mechanical properties as those of bone. Mg and Mg alloys have shown encouraging results when used as tissue engineering scaffolds. This review summarized the common methods for fabricating porous Mg-based scaffolds. It also explored some of the surface modification methods, biological performance, and applications of Mg-based scaffolds. While a considerable number of studies encourages the use of magnesium alloys in bioactive and biodegradable implants for load bearing orthopedic applications, a great deal of research is still essential to fully assess the *in vivo* long-term capability of such scaffolds. The possibility of magnesium being employed as a reliable metallic scaffold calls for persistent research and study on *in vitro* osteoblast cell attachment, proliferation, differentiation to an osteoblast phenotype, formation of a bone matrix, studies of bone apposition, tissue regeneration, and finally *in vivo* bone healing including introduction of angiogenesis. In fact, the application of biodegradable metallic scaffolds for tissue engineering purposes is just at the beginning. Controlling the degradation rate of magnesium in body fluids can be the first step to advance the field, which may be achieved through the use of alloying elements, casting and forming techniques, composite fabrication and/or surface coatings. The possible cytotoxicity of the modified systems will also require further verification. A great deal of research is still needed to develop superior, straightforward, and more cost-effective modification methods to facilitate the full use of the biodegradability, mechanical strength, and improved bio-functional properties of Mg alloys. In addition, rapid prototype methods could be considered to produce porous scaffolds with properties purposely tailored for the cell regeneration and the tissue in-growth. Future research directions include

understanding the effect of porosity on the corrosion and mechanical properties, the cell regeneration and tissue healing in the porous structure, developing procedures for manufacturing suitable porous Mg scaffolds, and finally control over the degradation rate of the scaffolds. Furthermore, integrating Mg scaffolds with biopolymers, bioactive ceramics and drugs represents a new promising path to investigate.

Acknowledgements

The authors wish to appreciate the substantial financial support from Delta Dental. They are also thankful of the support from the National Science Foundation (NSF, Grant no.EEC-1160483, ECCS-1351533 and CMMI-1363485), AFOSR under contract number FA9550-12-1-0225, and Marquette University Strategic Innovation Fund.

References

- [1] K. Mishima, K. Satoh, T. Ogihara, The effects of pH and ions on myelin figure formation in phospholipid-water system, *Chemical physics letters*, 106 (1984) 513-516.
- [2] G. Lewis, Properties of open-cell porous metals and alloys for orthopaedic applications, *Journal of Materials Science: Materials in Medicine*, 24 (2013) 2293-2325.
- [3] E.D. McBRIDE, Absorbable metal in bone surgery a further report on the use of magnesium alloys, *Journal of the American Medical Association*, 111 (1938) 2464-2467.
- [4] M. Niinomi, M. Nakai, J. Hieda, Development of new metallic alloys for biomedical applications, *Acta Biomaterialia*, 8 (2012) 3888-3903.
- [5] B. Levine, A new era in porous metals: applications in orthopaedics, *Advanced Engineering Materials*, 10 (2008) 788-792.
- [6] K. Alvarez, H. Nakajima, Metallic scaffolds for bone regeneration, *Materials*, 2 (2009) 790-832.
- [7] R. Langer, D.A. Tirrell, Designing materials for biology and medicine, *Nature*, 428 (2004) 487-492.
- [8] A. Yusop, A. Bakir, N. Shaharom, M. Abdul Kadir, H. Hermawan, Porous biodegradable metals for hard tissue scaffolds: a review, *International journal of biomaterials*, 2012 (2012).
- [9] S.J. Hollister, Porous scaffold design for tissue engineering, *Nature materials*, 4 (2005) 518-524.

- [10] S. Yang, K.-F. Leong, Z. Du, C.-K. Chua, The design of scaffolds for use in tissue engineering. Part II. Rapid prototyping techniques, *Tissue engineering*, 8 (2002) 1-11.
- [11] F. Geng, L. Tan, B. Zhang, C. Wu, Y. He, J. Yang, K. Yang, Study on beta-TCP coated porous Mg as a bone tissue engineering scaffold material, *Journal of Materials Science and Technology*, 25 (2009) 123-129.
- [12] V. Karageorgiou, D. Kaplan, Porosity of 3D biomaterial scaffolds and osteogenesis, *Biomaterials*, 26 (2005) 5474-5491.
- [13] D.M. Yunos, O. Bretcanu, A.R. Boccaccini, Polymer-bioceramic composites for tissue engineering scaffolds, *Journal of Materials Science*, 43 (2008) 4433-4442.
- [14] W.L. Murphy, R.G. Dennis, J.L. Kileny, D.J. Mooney, Salt fusion: an approach to improve pore interconnectivity within tissue engineering scaffolds, *Tissue engineering*, 8 (2002) 43-52.
- [15] G. Bouet, D. Marchat, M. Cruel, L. Malaval, L. Vico, In Vitro Three-Dimensional Bone Tissue Models: From Cells to Controlled and Dynamic Environment, *Tissue Engineering Part B: Reviews*, 21 (2014) 133-156.
- [16] G. Ryan, A. Pandit, D.P. Apatsidis, Fabrication methods of porous metals for use in orthopaedic applications, *Biomaterials*, 27 (2006) 2651-2670.
- [17] K.F. Farraro, K.E. Kim, S.L. Woo, J.R. Flowers, M.B. McCullough, Revolutionizing Orthopaedic Biomaterials: The Potential of Biodegradable and Bioresorbable Magnesium-based Materials for Functional Tissue Engineering, *Journal of biomechanics*, 47 (2013) 1979–1986.
- [18] J.R. Jones, L.M. Ehrenfried, L.L. Hench, Optimising bioactive glass scaffolds for bone tissue engineering, *Biomaterials*, 27 (2006) 964-973.
- [19] L. Ghasemi-Mobarakeh, M.P. Prabhakaran, M. Morshed, M.-H. Nasr-Esfahani, S. Ramakrishna, Electrospun poly (ϵ -caprolactone)/gelatin nanofibrous scaffolds for nerve tissue engineering, *Biomaterials*, 29 (2008) 4532-4539.
- [20] H. Seitz, W. Rieder, S. Irsen, B. Leukers, C. Tille, Three-dimensional ceramic scaffolds for bone tissue engineering, *Journal of Biomedical Materials Research Part B: Applied Biomaterials*, 74 (2005) 782-788.
- [21] X. Liu, P.X. Ma, Polymeric scaffolds for bone tissue engineering, *Annals of biomedical engineering*, 32 (2004) 477-486.
- [22] H. Zhuang, Y. Han, A. Feng, Preparation, mechanical properties and *in vitro* biodegradation of porous magnesium scaffolds, *Materials Science and Engineering: C*, 28 (2008) 1462-1466.
- [23] X. Zhang, X.-W. Li, J.-G. Li, X.-D. Sun, Preparation and mechanical property of a novel 3D porous magnesium scaffold for bone tissue engineering, *Materials Science and Engineering: C*, 42 (2014) 362-367.
- [24] M. Yazdimamaghani, M. Razavi, D. Vashae, L. Tayebi, Development and degradation behavior of magnesium scaffolds coated with polycaprolactone for bone tissue engineering, *Materials Letters* 132 (2014) 106-110.
- [25] J. Degner, F. Singer, L. Cordero, A.R. Boccaccini, S. Virtanen, Electrochemical investigations of magnesium in DMEM with biodegradable polycaprolactone coating as corrosion barrier, *Applied Surface Science*, 282 (2013) 264-270.
- [26] M. Razavi, M. Fathi, O. Savabi, D. Vashae, L. Tayebi, In vitro study of nanostructured diopside coating on Mg alloy orthopedic implants, *Materials Science and Engineering: C*, 41 (2014) 168-177.
- [27] H. Hornberger, S. Virtanen, A. Boccaccini, Biomedical coatings on magnesium alloys—A review, *Acta biomaterialia*, 8 (2012) 2442-2455.

- [28] M. Razavi, M. Fathi, O. Savabi, D. Vashae, L. Tayebi, Biodegradation, bioactivity and in vivo biocompatibility analysis of plasma electrolytic oxidized (PEO) biodegradable Mg implants, *Physical Science International Journal*, 4 (2014) 708-722.
- [29] M.P. Staiger, A.M. Pietak, J. Huadmai, G. Dias, Magnesium and its alloys as orthopedic biomaterials: a review, *Biomaterials*, 27 (2006) 1728-1734.
- [30] M. Razavi, M. Fathi, O. Savabi, B.H. Beni, D. Vashae, L. Tayebi, Surface microstructure and in vitro analysis of nanostructured akermanite ($\text{Ca}_2\text{MgSi}_2\text{O}_7$) Coating on biodegradable magnesium alloy for biomedical applications, *Colloids and Surfaces B: Biointerfaces*, 117 (2014) 432-440.
- [31] N. Kirkland, N. Birbilis, M. Staiger, Assessing the corrosion of biodegradable magnesium implants: a critical review of current methodologies and their limitations, *Acta biomaterialia*, 8 (2012) 925-936.
- [32] M. Razavi, M. Fathi, O. Savabi, S.M. Razavi, F. Heidari, M. Manshaei, D. Vashae, L. Tayebi, In vivo study of nanostructured diopside ($\text{CaMgSi}_2\text{O}_6$) coating on magnesium alloy as biodegradable orthopedic implants, *Applied Surface Science*, DOI (2014).
- [33] F. Witte, J. Fischer, J. Nellesen, H.-A. Crostack, V. Kaese, A. Pisch, F. Beckmann, H. Windhagen, In vitro and in vivo corrosion measurements of magnesium alloys, *Biomaterials*, 27 (2006) 1013-1018.
- [34] G. Song, S. Song, A possible biodegradable magnesium implant material, *Advanced Engineering Materials*, 9 (2007) 298-302.
- [35] F. Witte, V. Kaese, H. Haferkamp, E. Switzer, A. Meyer-Lindenberg, C. Wirth, H. Windhagen, In vivo corrosion of four magnesium alloys and the associated bone response, *Biomaterials*, 26 (2005) 3557-3563.
- [36] M. Razavi, M. Fathi, O. Savabi, B. Hashemi Beni, D. Vashae, L. Tayebi, Nanostructured merwinite bioceramic coating on Mg alloy deposited by electrophoretic deposition, *Ceramics International*, 40 (2014) 9473-9484.
- [37] X. Zhang, X. Li, J. Li, X. Sun, Processing, microstructure and mechanical properties of biomedical magnesium with a specific two-layer structure, *Progress in Natural Science: Materials International*, 23 (2013) 183-189.
- [38] G. Song, Control of biodegradation of biocompatible magnesium alloys, *Corrosion Science*, 49 (2007) 1696-1701.
- [39] H.M. Wong, K.W. Yeung, K.O. Lam, V. Tam, P.K. Chu, K.D. Luk, K. Cheung, A biodegradable polymer-based coating to control the performance of magnesium alloy orthopaedic implants, *Biomaterials*, 31 (2010) 2084-2096.
- [40] M. Yazdimamaghani, M. Razavi, D. Vashae, L. Tayebi, Surface modification of biodegradable porous Mg bone scaffold using polycaprolactone/bioactive glass composite, *Materials Science and Engineering: C*, DOI (2015).
- [41] L. Xu, F. Pan, G. Yu, L. Yang, E. Zhang, K. Yang, *In vitro* and *in vivo* evaluation of the surface bioactivity of a calcium phosphate coated magnesium alloy, *Biomaterials*, 30 (2009) 1512-1523.
- [42] G. Jiang, G. He, A new approach to the fabrication of porous magnesium with well-controlled 3D pore structure for orthopedic applications, *Materials Science and Engineering: C*, 43 (2014) 317-320.
- [43] P. Liu, Q. Tan, L. Wu, G. He, Compressive and pseudo-elastic hysteresis behavior of entangled titanium wire materials, *Materials Science and Engineering: A*, 527 (2010) 3301-3309.

- [44] N. Kirkland, I. Kolbeinsson, T. Woodfield, G. Dias, M. Staiger, Synthesis and properties of topologically ordered porous magnesium, *Materials Science and Engineering: B*, 176 (2011) 1666-1672.
- [45] F. Witte, H. Ulrich, M. Rudert, E. Willbold, Biodegradable magnesium scaffolds: Part 1: appropriate inflammatory response, *Journal of Biomedical Materials Research Part A*, 81 (2007) 748-756.
- [46] Z. Seyedraoufi, S. Mirdamadi, Synthesis, microstructure and mechanical properties of porous Mg-Zn scaffolds, *Journal of the mechanical behavior of biomedical materials*, 21 (2013) 1-8.
- [47] M. Yazdimamaghani, M. Razavi, D. Vashaei, L. Tayebi, Microstructural and mechanical study of PCL coated Mg scaffolds, *Surface Engineering*, 30 (2014) 920-926.
- [48] C. Wen, Y. Yamada, K. Shimojima, Y. Chino, H. Hosokawa, M. Mabuchi, Compressibility of porous magnesium foam: dependency on porosity and pore size, *Materials letters*, 58 (2004) 357-360.
- [49] M. Yazdimamaghani, M. Razavi, D. Vashaei, V.R. Pothineni, J. Rajadas, L. Tayebi, Significant degradability enhancement in multilayer coating of polycaprolactone-bioactive glass/gelatin-bioactive glass on magnesium scaffold for tissue engineering applications, *Applied Surface Science*, 338 (2015) 137-145.
- [50] H. Nakajima, Fabrication, properties, and applications of porous metals with directional pores, *Proceedings of the Japan Academy. Series B, Physical and biological sciences*, 86 (2010) 884.
- [51] X. Gu, W. Zhou, Y. Zheng, Y. Liu, Y. Li, Degradation and cytotoxicity of lotus-type porous pure magnesium as potential tissue engineering scaffold material, *Materials Letters*, 64 (2010) 1871-1874.
- [52] P. Ducheyne, In vitro corrosion study of porous metal fibre coatings for bone ingrowth, *Biomaterials*, 4 (1983) 185-191.
- [53] G. Song, A. Atrens, X. Wu, B. Zhang, Corrosion behaviour of AZ21, AZ501 and AZ91 in sodium chloride, *Corrosion Science*, 40 (1998) 1769-1791.
- [54] L.L. Hench, Sol-gel materials for bioceramic applications, *Current Opinion in Solid State and Materials Science*, 2 (1997) 604-610.
- [55] S.M. Zakaria, S.H. Sharif Zein, M.R. Othman, F. Yang, J.A. Jansen, Nanophase hydroxyapatite as a biomaterial in advanced hard tissue engineering: a review, *Tissue Engineering Part B: Reviews*, 19 (2013) 431-441.
- [56] H. Wang, S. Guan, X. Wang, C. Ren, L. Wang, In vitro degradation and mechanical integrity of Mg-Zn-Ca alloy coated with Ca-deficient hydroxyapatite by the pulse electrodeposition process, *Acta Biomaterialia*, 6 (2010) 1743-1748.
- [57] C. Wen, S. Guan, L. Peng, C. Ren, X. Wang, Z. Hu, Characterization and degradation behavior of AZ31 alloy surface modified by bone-like hydroxyapatite for implant applications, *Applied Surface Science*, 255 (2009) 6433-6438.
- [58] Y. Song, D. Shan, E. Han, Electrodeposition of hydroxyapatite coating on AZ91D magnesium alloy for biomaterial application, *Materials Letters*, 62 (2008) 3276-3279.
- [59] Z. Seyedraoufi, S. Mirdamadi, Effects of pulse electrodeposition parameters and alkali treatment on the properties of nano hydroxyapatite coating on porous Mg-Zn scaffold for bone tissue engineering application, *Materials Chemistry and Physics*, 148 (2014) 519-527.

- [60] D.-S. Yin, E.-I. Zhang, S.-Y. Zeng, Effect of Zn on mechanical property and corrosion property of extruded Mg-Zn-Mn alloy, *Transactions of Nonferrous Metals Society of China*, 18 (2008) 763-768.
- [61] E. Zhang, D. Yin, L. Xu, L. Yang, K. Yang, Microstructure, mechanical and corrosion properties and biocompatibility of Mg-Zn-Mn alloys for biomedical application, *Materials Science and Engineering: C*, 29 (2009) 987-993.
- [62] S.J. Kalita, M. Ferguson, Fabrication of 3-D porous Mg/Zn doped tricalcium phosphate bone-scaffolds via the fused deposition modelling, *American Journal of Biochemistry and Biotechnology*, 2 (2006) 57.
- [63] Z. Chen, X. Mao, L. Tan, T. Friis, C. Wu, R. Crawford, Y. Xiao, Osteoimmunomodulatory properties of magnesium scaffolds coated with β -tricalcium phosphate, *Biomaterials*, 35 (2014) 8553-8565.
- [64] Z. Chen, C. Wu, W. Gu, T. Klein, R. Crawford, Y. Xiao, Osteogenic differentiation of bone marrow MSCs by β -tricalcium phosphate stimulating macrophages via BMP2 signalling pathway, *Biomaterials*, 35 (2014) 1507-1518.
- [65] M.K. Chang, L.-J. Raggatt, K.A. Alexander, J.S. Kuliwaba, N.L. Fazzalari, K. Schroder, E.R. Maylin, V.M. Ripoll, D.A. Hume, A.R. Pettit, Osteal tissue macrophages are intercalated throughout human and mouse bone lining tissues and regulate osteoblast function in vitro and in vivo, *The Journal of Immunology*, 181 (2008) 1232-1244.
- [66] A.R. Pettit, M.K. Chang, D.A. Hume, L.-J. Raggatt, Osteal macrophages: a new twist on coupling during bone dynamics, *Bone*, 43 (2008) 976-982.
- [67] Y. Honda, T. Anada, S. Kamakura, M. Nakamura, S. Sugawara, O. Suzuki, Elevated extracellular calcium stimulates secretion of bone morphogenetic protein 2 by a macrophage cell line, *Biochemical and biophysical research communications*, 345 (2006) 1155-1160.
- [68] S. Wahl, N. McCartney
Production of TGF- β by TGF- β Annals
Sciences, 593 (1990) 188-196.
- [69] F. Geng, L. Tan, B. Zhang, C. Wu, Y. He, J. Yang, K. Yang, Study on beta-TCP coated porous Mg as a bone tissue engineering scaffold material, DOI (2009).
- [70] L.L. Hench, Bioceramics, a clinical success, *American Ceramic Society Bulletin*, 77 (1998) 67-74.
- [71] F. Li, Q. Feng, F. Cui, H. Li, H. Schubert, A simple biomimetic method for calcium phosphate coating, *Surface and Coatings Technology*, 154 (2002) 88-93.
- [72] K.S. TenHuisen, P.W. Brown, Effects of magnesium on the formation of calcium hydroxyapatite from $\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$ and $\text{Ca}_4(\text{PO}_4)_2\text{O}$, *Journal of biomedical materials research*, 36 (1997) 306-314.
- [73] M. Pham, M. Maitz, W. Matz, H. Reuther, E. Richter, G. Steiner, Promoted hydroxyapatite nucleation on titanium ion-implanted with sodium, *Thin Solid Films*, 379 (2000) 50-56.
- [74] X. Lu, Y. Leng, Theoretical analysis of calcium phosphate precipitation in simulated body fluid, *Biomaterials*, 26 (2005) 1097-1108.
- [75] P. De Aza, F. Guitian, A. Merlos, E. Lora-Tamayo, S. De Aza, Bioceramics—simulated body fluid interfaces: pH and its influence of hydroxyapatite formation, *Journal of Materials Science: Materials in Medicine*, 7 (1996) 399-402.
- [76] M. Yazdimamaghani, D. Vashae, S. Assefa, K. Walker, S. Madhally, G. Köhler, L. Tayebi, Hybrid Macroporous Gelatin/Bioactive-Glass/Nanosilver Scaffolds with Controlled

Degradation Behavior and Antimicrobial Activity for Bone Tissue Engineering, *Journal of Biomedical Nanotechnology*, 10 (2014) 911-931.

[77] H. Cameron, I. Macnab, R. Pilliar, A porous metal system for joint replacement surgery, *The International journal of artificial organs*, 1 (1978) 104-109.

[78] D.M. Robertson, L. St Pierre, R. Chahal, Preliminary observations of bone ingrowth into porous materials, *Journal of biomedical materials research*, 10 (1976) 335-344.

[79] W.C. Head, D.J. Bauk, R.H. Emerson Jr, Titanium as the material of choice for cementless femoral components in total hip arthroplasty, *Clinical orthopaedics and related research*, 311 (1995) 85-90.

[80] H. Kröger, P. Venesmaa, J. Jurvelin, H. Miettinen, O. Suomalainen, E. Alhava, Bone density at the proximal femur after total hip arthroplasty, *Clinical orthopaedics and related research*, 352 (1998) 66-74.

[81] L. Tan, M. Gong, F. Zheng, B. Zhang, K. Yang, Study on compression behavior of porous magnesium used as bone tissue engineering scaffolds, *Biomedical Materials*, 4 (2009) 015016.

[82] L.J. Gibson, M.F. Ashby, *Cellular solids: structure and properties*, Cambridge university press 1997.

[83] C. Wen, M. Mabuchi, Y. Yamada, K. Shimojima, Y. Chino, T. Asahina, Processing of biocompatible porous Ti and Mg, *Scripta Materialia*, 45 (2001) 1147-1153.

[84] Y. Yamada, K. Shimojima, Y. Sakaguchi, M. Mabuchi, M. Nakamura, T. Asahina, T. Mukai, H. Kanahashi, K. Higashi, Processing of cellular magnesium materials, *Advanced Engineering Materials*, 2 (2000) 184-187.

[85] L.J. Gibson, The mechanical behaviour of cancellous bone, *Journal of biomechanics*, 18 (1985) 317-328.

[86] L. Li, J. Gao, Y. Wang, Evaluation of cyto-toxicity and corrosion behavior of alkali-heat-treated magnesium in simulated body fluid, *Surface and Coatings Technology*, 185 (2004) 92-98.

[87] H. Kuwahara, Y. Al-Abdullat, N. Mazaki, S. Tsutsumi, T. Aizawa, Precipitation of magnesium apatite on pure magnesium surface during immersing in Hank's solution, *Materials Transactions(Japan)*, 42 (2001) 1317-1321.

[88] S. Virtanen, Biodegradable Mg and Mg alloys: Corrosion and biocompatibility, *Materials Science and Engineering: B*, 176 (2011) 1600-1608.

[89] Y. Liu, Z. Yang, L. Tan, H. Li, Y. Zhang, An animal experimental study of porous magnesium scaffold degradation and osteogenesis, *Brazilian Journal of Medical and Biological Research*, 47 (2014) 715-720.

[90] T. Kraus, S.F. Fischerauer, A.C. Hänzi, P.J. Uggowitzer, J.F. Löffler, A.M. Weinberg, Magnesium alloys for temporary implants in osteosynthesis: in vivo studies of their degradation and interaction with bone, *Acta biomaterialia*, 8 (2012) 1230-1238.

[91] X. Gu, N. Li, W. Zhou, Y. Zheng, X. Zhao, Q. Cai, L. Ruan, Corrosion resistance and surface biocompatibility of a microarc oxidation coating on a Mg–Ca alloy, *Acta Biomaterialia*, 7 (2011) 1880-1889.

[92] H.M. Wong, K.W. Yeung, K.O. Lam, V. Tam, P.K. Chu, K.D. Luk, K.M. Cheung, A biodegradable polymer-based coating to control the performance of magnesium alloy orthopaedic implants, *Biomaterials*, 31 (2010) 2084-2096.

[93] X. Gu, Y. Zheng, L. Chen, Influence of artificial biological fluid composition on the biocorrosion of potential orthopedic Mg–Ca, AZ31, AZ91 alloys, *Biomedical Materials*, 4 (2009) 065011.

- [94] K.F. Farraro, K.E. Kim, S.L. Woo, J.R. Flowers, M.B. McCullough, Revolutionizing orthopaedic biomaterials: The potential of biodegradable and bioresorbable magnesium-based materials for functional tissue engineering, *Journal of biomechanics*, 47 (2014) 1979-1986.
- [95] N. Kirkland, J. Lespagnol, N. Birbilis, M. Staiger, A survey of bio-corrosion rates of magnesium alloys, *Corrosion Science*, 52 (2010) 287-291.
- [96] M. Salahshoor, Y. Guo, Surface integrity of biodegradable Magnesium–Calcium orthopedic implant by burnishing, *Journal of the mechanical behavior of biomedical materials*, 4 (2011) 1888-1904.
- [97] F. Witte, The history of biodegradable magnesium implants: a review, *Acta Biomaterialia*, 6 (2010) 1680-1692.
- [98] E.M. Sussman, B.J. Casey, D. Dutta, B.J. Dair, Different cytotoxicity responses to antimicrobial nanosilver coatings when comparing extract -based and direct contact, *Journal of Applied Toxicology*, DOI (2015).
- [99] J. Fischer, D. Pröfrock, N. Hort, R. Willumeit, F. Feyerabend, Reprint of: Improved cytotoxicity testing of magnesium materials, *Materials Science and Engineering: B*, 176 (2011) 1773-1777.
- [100] J. Fischer, M.H. Prosenc, M. Wolff, N. Hort, R. Willumeit, F. Feyerabend, Interference of magnesium corrosion with tetrazolium-based cytotoxicity assays, *Acta biomaterialia*, 6 (2010) 1813-1823.
- [101] K. Bobe, E. Willbold, I. Morgenthal, O. Andersen, T. Studnitzky, J. Nellesen, W. Tillmann, C. Vogt, K. Vano, F. Witte, In vitro and in vivo evaluation of biodegradable, open-porous scaffolds made of sintered magnesium W4 short fibres, *Acta biomaterialia*, 9 (2013) 8611-8623.
- [102] F. Lang, M. Föller, K. Lang, P. Lang, M. Ritter, A. Vereninov, I. Szabo, S.M. Huber, E. Gulbins, Chapter Eleven-Cell Volume Regulatory Ion Channels in Cell Proliferation and Cell Death, *Methods in enzymology*, 428 (2007) 209-225.
- [103] A. Zhang, T.P. Cheng, B.M. Altura, Magnesium regulates intracellular free ionized calcium concentration and cell geometry in vascular smooth muscle cells, *Biochimica et Biophysica Acta (BBA)-Molecular Cell Research*, 1134 (1992) 25-29.
- [104] C. Stout, A. Charles, Modulation of intercellular calcium signaling in astrocytes by extracellular calcium and magnesium, *Glia*, 43 (2003) 265-273.
- [105] J.M. Anderson, M.S. Shive, Biodegradation and biocompatibility of PLA and PLGA microspheres, *Advanced drug delivery reviews*, 64 (2012) 72-82.
- [106] J. Wei, J. Jia, F. Wu, S. Wei, H. Zhou, H. Zhang, J.-W. Shin, C. Liu, Hierarchically microporous/macroporous scaffold of magnesium–calcium phosphate for bone tissue regeneration, *Biomaterials*, 31 (2010) 1260-1269.
- [107] F. Witte, H. Ulrich, C. Palm, E. Willbold, Biodegradable magnesium scaffolds: Part II: Peri-implant bone formation, *Journal of Biomedical Materials Research Part A*, 81f (2007) 757-765.
- [108] M. Kleerekoper, A. Villanueva, J. Stanciu, D.S. Rao, A. Parfitt, The role of three-dimensional trabecular microstructure in the pathogenesis of vertebral compression fractures, *Calcified tissue international*, 37 (1985) 594-597.
- [109] K. Kubota, M. Mabuchi, K. Higashi, Review processing and mechanical properties of fine-grained magnesium alloys, *Journal of Materials Science*, 34 (1999) 2255-2262.

- [110] A.C. Hänzi, I. Gerber, M. Schinhammer, J.F. Löffler, P.J. Uggowitzer, On the in vitro and in vivo degradation performance and biological response of new biodegradable Mg–Y–Zn alloys, *Acta biomaterialia*, 6 (2010) 1824-1833.
- [111] P. Gunde, A. Furrer, A.C. Hänzi, P. Schmutz, P.J. Uggowitzer, The influence of heat treatment and plastic deformation on the bio -degradation
Biomedical Materials Research Part A, 92 (2010) 409-418.
- [112] S. Hoechel, D. Wirz, M. Müller-Gerbl, Density and strength distribution in the human subchondral bone plate of the patella, *International orthopaedics*, 36 (2012) 1827-1834.
- [113] T.J. Klein, J. Malda, R.L. Sah, D.W. Hutmacher, Tissue engineering of articular cartilage with biomimetic zones, *Tissue Engineering Part B: Reviews*, 15 (2009) 143-157.
- [114] K. Shimomura, Y. Moriguchi, C.D. Murawski, H. Yoshikawa, N. Nakamura, Osteochondral tissue engineering with biphasic scaffold: current strategies and techniques, *Tissue Engineering Part B: Reviews*, 20 (2014) 468-476.
- [115] E. Hunziker, Articular cartilage repair: basic science and clinical progress. A review of the current status and prospects, *Osteoarthritis and cartilage*, 10 (2002) 432-463.
- [116] A. Shahini, M. Yazdimamaghani, K.J. Walker, M.A. Eastman, H. Hatami-Marbini, B.J. Smith, J.L. Ricci, S.V. Madhally, D. Vashae, L. Tayebi, 3D conductive nanocomposite scaffold for bone tissue engineering, *International journal of nanomedicine*, 9 (2014) 167.
- [117] Y.-S. Qiu, B. Shahgaldi, W. Revell, F. Heatley, Observations of subchondral plate advancement during osteochondral repair: a histomorphometric and mechanical study in the rabbit femoral condyle, *Osteoarthritis and cartilage*, 11 (2003) 810-820.
- [118] F. Witte, J. Reifenrath, P. Müller, H.A. Crostack, J. Nellesen, F. Bach, D. Bormann, M. Rudert, Cartilage repair on magnesium scaffolds used as a subchondral bone replacement, *Materialwissenschaft und Werkstofftechnik*, 37 (2006) 504-508.
- [119] E. Hesse, G. Kluge, A. Atfi, D. Correa, C. Haasper, G. Berding, H.-o. Shin, J. Viering, F. Länger, P.M. Vogt, Repair of a segmental long bone defect in human by implantation of a novel multiple disc graft, *Bone*, 46 (2010) 1457-1463.
- [120] H. Shegarfi, O. Reikeras, Review article: Bone transplantation and immune response, *Journal of Orthopaedic Surgery*, 17 (2009).
- [121] C. Serre, M. Papillard, P. Chavassieux, J. Voegel, G. Boivin, Influence of magnesium substitution on a collagen–apatite biomaterial on the production of a calcifying matrix by human osteoblasts, *Journal of biomedical materials research*, 42 (1998) 626-633.
- [122] H.P. Wiesmann, T. Tkotz, U. Joos, K. Zierold, U. Stratmann, T. Szuwart, U. Plate, H.J. Höhling, Magnesium in newly formed dentin mineral of rat incisor, *Journal of Bone and Mineral Research*, 12 (1997) 380-383.

Figure Captions

Fig.1. Schematic design of the titanium wire space holder method for the production of porous magnesium scaffold (reproduced with permission of (42))

Fig. 2. Schematic picture of the negative salt pattern molding process: (a) polymeric template produced by rapid prototyping, (b) infiltration of produced porous polymer with salt paste, (c) Burning the polymer template and sintering of salt template, (d) casting of Mg melt into the produced salt template, and (e) final porous Mg scaffold following salt removal (reproduced with permission of (45))

Fig. 3. The cross section of Magnesium scaffold produced by powder metallurgy (reproduced with permission of (48))

Fig. 4. Schematic representation of the hydrogen injection technique through the Mg melt (reprinted with permission of (51))

Fig. 5. SEM micrographs in the different magnifications of perpendicularly needle-like hydroxyapatite (reprinted with permission of (60))

Fig.6. (a) Porous magnesium scaffold prepared by laser perforation technique before coating. (b) SEM micrograph of the β -TCP coated scaffolds (reproduced with permission of (71))

Fig.7. (a,b) low and high SEM magnification of magnesium scaffold. (c,d) top and cross-sectional view of magnesium scaffold coated by PCL-BaG layer. (e, f) cross-sectional view of magnesium scaffold coated with PCL-BaG inner layer and outer layer of Gel-BaG. (g) Inside and (h) top view of coated scaffold (reprinted with permission of (50))

Fig.8. (a) Magnesium alloy AZ91D cylindrical porous scaffold. Red rectangle in the middle picture shows the scaffold insertion place into right knees. (b) A special pestle used for boreholes insertion. Left knees were used as controls. Blue circle shows the autologous bone

grafted from the left patellar grooves. The empty patellar defect works as a control for natural defect remedial. (c,d) Longitudinal sections of safranin-O stained for magnesium scaffold site and the autologous patellar grooves bone site show the development of the wound healing six months postoperatively. Black arrows show the leftovers of the cartilaginous surface of the reverse implant. (e) Transversal section of safranin-O stained patellar defect. Scale bar $\frac{1}{4}$ 2000 μm (a), 500 μm (c, d, e) (reprinted with permission of(46))

Fig.9. Micro-CT image of (a) magnesium scaffold and (b) hydroxyapatite scaffold as control group. The new bone tissue in-growth is shown in green color (reprinted with permission of(91)).

Fig.10. (a) Melt extraction procedure to manufacture short fibers. (b) Deposition of Mg alloy fibers onto a moving substrate with an MgO barrier, then sintered and cut by laser jet method. (c) SEM cross sections of fibers demonstrates the sinter bonds (bar = 20 μm). (d) Cylindrical scaffolds before *in vitro* or *in vivo* tests (bar = 1000 μm). (e) SEM image of scaffold surface (bar = 200 μm) (reprinted with permission of(103))

Fig.11. (a) Tomograms of scaffolds before the implantation show open inter-connected porous structure with no residual materials. (b) At 6 weeks, newly formed bone marked by white dots, and gas cavities showed by white star. (c) 12 weeks no gas cavity is detectable. (White arrow heads indicates metallic implant and black arrow heads show corroded parts) (Scale bar = 1 mm) (reprinted with permission of(103))

Fig.1

Fig.2

Fig.3

Fig.4

Fig.4

Fig.5

Fig.6

Fig.7

Fig.8

Fig.9

Fig.10

Fig.11