CRACK PROPAGATION SPEED IN ULTRA HIGH PERFORMANCE CONCRETE (UHPC)

Sukhoon Pyo^{a*}, Mo Alkaysi^b and Sherif El-Tawil^b

^aNew Transportation Systems Research Center, Korea Railroad Research Institute, 176 Railroad Museum Road,
Uiwang-si, Gyeonggi-do, 16105, South Korea

^bDepartment of Civil & Environmental Engineering, University of Michigan, 2350 Hayward, G.G. Brown,
Ann Arbor, MI 48109-2125, USA

*Corresponding author, E-mail: shpyo@krii.re.kr, +82-31-460-5413

ABSTRACT

This paper investigates crack speed in ultra-high performance concrete (UHPC) using pre-notched three-point bending specimens. The experimental parameters are fiber volume fraction and rate of loading. A hydraulic servo-controlled testing machine is used to apply lower notch tip strain rates, in the range of 0.025 to 1.0 1/s, while a newly developed impact testing system is used to achieve higher notch tip strain rates, ranging from 6.8 to 41.1 1/s. A high-speed camera is used to record images of the UHPC specimens during testing. Notch tip strain and crack speed are computed from the images, which show that crack speed increases asymptotically as the crack initiation strain rate increases. Crack speeds of up to 514 m/s were achieved at the lower notch tip strain rates and up to 1454 m/s for the higher notch tip strain rates. The achieved relationships are incorporated into a recently proposed crack-velocity dependent dynamic fracture model. The model is validated using published experimental data and used to show that, like conventional concrete, the strain rate sensitivity of UHPC is strongly associated with the characteristics of dynamic crack growth.

Keywords: Crack Speed; Impact Loading; Strain-rate Effects; Ultra High Performance Concrete

1. INTRODUCTION

Crack propagation in brittle materials is a key mechanism leading to material failure and is a complex process to analyze, especially under dynamic loading. The main techniques used by researchers to characterize crack propagation are: experiments [1-5], analytical approaches [6-8], and numerical simulations [9-12]. Research on crack propagation was reviewed by Freund [13]. In spite of decades of research in this field, there is still controversy regarding fundamental aspects of the dynamic fracture process, such as the observed maximum crack velocity. For example, Xie and Sanderson [14] suggested that the measured crack velocity cannot reach the Rayleigh wave speed (i.e. the theoretically predicted maximum crack speed) because the dynamic stress intensity factor approaches zero when crack velocity is about half of the Rayleigh wave speed. In contrast, Sharon and Fineberg [3] insisted that measured peak crack velocities approach the theoretical predictions if the instantaneous velocity is used instead of the averaged value.

Understanding crack speed in a solid is important in dynamic fracture mechanics. This is because, with some assumptions, the stress field near the moving crack tip in linear elastic brittle solids under small-scale yielding can be expressed as a single parameter, the stress intensity factor [5]. This suggests that a relationship between crack velocity and the stress intensity factor can be established [5, 15, 16]. A number of analytical and numerical models have been proposed based on the assumption of constant crack velocity at a given strain rate. Landis et al. [8] used an elastic-viscoplastic constitutive law incorporating a rate dependent fracture process zone to explain Mode I steady-state crack growth in strain rate dependent materials. They computed the macroscopic work energy of fracture as a function of crack velocity. Pyo and El-Tawil [17] used experimental data in the literature supplemented by computational models to obtain a relationship between crack

1 velocity and strain rate in normal concrete. By implementing the developed relationships into
2 crack-speed dependent dynamic fracture models, they predicted the dynamic increase factor of
3 concrete under dynamic tensile loading. Based on the comparison, they suggested that strain rate
4 sensitivity is strongly associated with the characteristics of dynamic crack growth and inertial
5 effects at the boundaries of the crack.

6
7 Ultra high performance concrete (UHPC) is an advanced cement based composite, which has
8 extremely high compressive strength (over 150 MPa) and durability, including high resistance to
9 chemical attack, freeze-thaw cycles, abrasion, and chloride penetration [18-20]. Recent work
10 suggests that the mechanical and durability properties of UHPC make it an ideal candidate for use
11 in developing new solutions to pressing concerns about infrastructure deterioration, repair, and
12 replacement [21]. However, to the best knowledge of the authors, no studies have been reported
13 on the crack speed in UHPC under different loading speeds, which motivated this work.

14
15 In the present study, relationships between crack speed and crack initiation strain rate in UHPC
16 under various rates of loading are established. A hydraulic servo-controlled testing machine and a
17 newly developed impact testing system are used to apply 'low' and 'high' loading rates,
18 respectively, on pre-notched three-point bending specimens. The Digital Image Correlation (DIC)
19 technique and Canny edge detection algorithm are adopted to compute crack tip strain and crack
20 speed in UHPC specimens. The achieved relationship are incorporated into the crack-velocity
21 dependent dynamic fracture model proposed by Pyo and El-Tawil [17] to predict the DIF of UHPC
22 and compared with experimental data obtained from Pyo et al. [22] and Pyo [23].

2. EXPERIMENTAL PROGRAM

An experimental program was carried out to investigate crack propagation speed in UHPC as a function of notch tip crack initiation strain rate. The mix proportions of UHPC with three different volume fractions of fibers are given in Table 1. Further details about the mix constituents can be found in Wille et al. [24]. Mixes with no fibers were selected to focus attention on the matrix itself. Mixes with higher fiber volume fractions than those shown in Table 1 were not considered because of the concern that crack speed would be too slow to capture in a meaningful manner with a high speed camera. Table 2 lists the properties of the steel fibers used in this study.

A Hobart type laboratory mixer was used to prepare the UHPC mixture. The mixing procedure followed Wille et al. [24]. First, silica fume was mixed with all the sand for approximately 5 minutes. Then, cement and glass powder were added and mixed together for at least another 5 minutes before the water and superplasticizer were added. The cementitious mixture became fluid after approximately 5 minutes of adding the liquid ingredients. When the cementitious mixture started to show adequate flowability and viscosity, fibers were dispersed by hand into the mix. Once thoroughly mixed, the cementitious mixture was poured into pre-notched three point bending specimen molds without any vibration. After casting, the specimens were covered with plastic sheets and stored at room temperature for 24 hours prior to de-molding. After 27 days of water curing, but without any special curing such as heat or pressure treatment, the UHPC specimens were left to dry in the laboratory environment for at least 24 hours. Cube specimens with dimensions of 50 x 50 x 50 mm (2 x 2 x 2 in) were also made from each series and tested after curing. The compressive strengths were averaged from at least three cube specimens and are summarized in Table 3.

Table 1. Mixtures proportions by weight (based on Wille et al. [24])

Fiber Volume Fraction	0 %	0.5 %	1.0 %
Cement	1.00	1.00	1.00
Silica Fume	0.25	0.25	0.25
Glass Powder	0.25	0.25	0.25
Water	0.22	0.22	0.22
Superplasticizer	0.005	0.005	0.005
Sand A [†]	0.28	0.27	0.27
Sand B [§]	1.10	1.09	1.07

[†] Maximum grain size = 0.2 mm (1/128 in.).

[§]Maximum grain size = 0.8 mm (1/32 in.).

Table 2. Properties of steel fiber used in this study

Material	Brass coated high carbon steel wire
Shape	Cross section: round / length: straight
Diameter (mm)	0.2 ± 0.01
Length (mm)	19.5
Tensile Strength (MPa)	2450 ~ 2750

Table 3. Mechanical and fracture properties of UHPC

Test series	Compressive stress (MPa)	Critical stress intensity factor, K_{IC} , (MPa $\sqrt{m}$)	
		0.0076 mm/s	7.6 mm/s
CS-0%	151	5.00	5.46 [†]
CS-0.5%	171	N/A	7.19
CS-1.0%	191	N/A	14.3

[†] Calculated from one only experiment because of an error in the data acquisition system while testing.

Each test series is designated by its fiber volume fraction; e.g. CS-0.5% represents a crack speed (CS) mix with 0.5% fiber volume fraction. Four loading rates are considered in this study. The two lower loading speeds are achieved by using a hydraulic servo-controlled testing system running at

Fig. 2. Actual UHPC specimen

Fig. 3. Test setup for three-point bending testing using a hydraulic servo-controlled testing machine

the notch tip so that notch tip strain can be computed using the DIC technique. The DIC data is first used to measure displacement along the gage length shown in Fig. 1, then notch tip strain is computed from the displacement data by simply dividing displacement by gage length (10 mm). The assumption is that the initial crack is vertical and driven by the horizontal component of strain

1 at the notch tip. This follows, in spirit, the process used by John et al. [26], although they used a
 2 strain gage attached to the notch tip to measure strain. Fig. 3 shows the test setup within the
 3 hydraulic servo-controlled testing system (MTS-810).

Fig. 4. Impact testing system for crack propagation

4
 5
 6 An impact testing system developed by Pyo and El-Tawil [25] was modified to accommodate the
 7 new three-point bending test. Fig. 4a shows a FE model that was utilized by Pyo [23] to design the
 8 modifications and Fig. 4b shows the built prototype. The way by which the modified setup works
 9 is similar to the original system developed in Pyo and El-Tawil [25] for impact testing of tensile

specimens. When displacement is applied to the pull bar, the energy bar stores elastic energy. After failure of the coupler, which is notched, the stored elastic energy in the energy bar is suddenly released and transmitted to the specimen in the form of a load pulse. The coupler notch depth is selected so that fracture of the coupler occurs at a given load in order to control the level of the pulse and therefore impact speed. In this experiment, two different notch depths (designated Type 1 and Type 2) are considered in order to vary the impact demand on the specimen. Type 2 couplers are notched less than Type 1 resulting in greater stored energy and hence greater impact speed. Notch tip strain and crack speed are calculated by post-processing images of the specimen obtained using the high speed camera.

3. CRACK SPEED ANALYSIS

The images obtained from the high speed camera are post-processed to measure crack tip displacement, which enables calculation of the crack tip speed. In order to extract crack length data from the images, each frame is first queued into an image processing program that runs an edge detection algorithm. Edge detection is achieved using a mathematical method which identifies points in a digital image at which the image brightness changes sharply, signifying a crack edge. For this study, the Canny edge detection algorithm [27] was implemented because it has been shown that it performs better than other methods under almost all scenarios [28].

Applying the Canny algorithm results in a binary image which contains a matrix of pixels marked as either an edge pixel or a non-edge pixel. Processing the edge pixels results in characterization of the crack in terms of pixels. The actual length of the crack is computed by using a scale factor that correlates the pixels count to a known dimension. Since the frame rate at which the camera

records the images is known, the time in between increments in crack length is determined and used for computation of the crack tip speed.

4. EVALUATION OF EXPERIMENTAL RESULTS

4.1 Critical Stress Intensity Factor

Experimental results from the low rate tests are used to determine the critical stress intensity factor, K_{IC} , which is a key parameter that characterizes crack stability under service loads and provides a measure of the effectiveness of steel fiber reinforcement in UHPC. The critical stress intensity factor for a pre-notched three-point bending specimen is calculated using Eq. (1) [29, 30]:

$$K_{IC} = \sigma_{NC} \sqrt{\pi a_0} f_1(\alpha_0) \quad (1)$$

in which

$$f_1(\alpha) = \frac{1.99 - \alpha(1 - \alpha)(2.15 - 3.93\alpha + 2.7\alpha^2)}{\sqrt{\pi}(1 + 2\alpha)(1 - \alpha)^{3/2}} \quad (2)$$

and $\alpha = \frac{a_0}{H}$, $\sigma_{NC} = \frac{3P_{max}L}{2tH^2}$ and P_{max} is the maximum measured load plus the self-weight of the tested beam. All dimensions are given in Fig. 1.

The computed results of the critical stress intensity factor are given in Table 3. It should be noted that only one value for the load data was recorded in CS-0% for the 7.6 mm/s loading speed because of error in the data acquisition system while testing. It can be seen that the critical stress intensity factor increases substantially as fiber volume fraction increases, i.e. 31.8% and 162% increase for CS-0.5% and CS-1.0% series compared to CS-0%, respectively. In contrast, the compressive strength increases by 13.6% and 26.8% in CS-0.5% and CS-1.0% compared to CS-

0%. As many researchers have already stated [31, 32], these results confirm that fiber reinforcement has a greater effect on fracture toughness than on compressive strength.

Fig. 5 shows examples of load curves for the low loading rate cases. It can be seen from Fig. 5 that CS-0% shows brittle failure without a significant softening region, and thus shows fast crack speed even under low loading rates. In contrast, CS-0.5% and CS-1.0%, show somewhat more ductile failure patterns, allowing large energy dissipation and leading to slower crack speed under the low loading speed regime. Such different failure patterns with and without fiber reinforcements can also be found in the literature [31, 33, 34].

Fig. 5. Examples of load curves for the slow loading cases: (a) CS-0% tested at 0.0076 mm/s; (b) CS-0% tested at 7.6 mm/s; (c) CS-0.5% tested at 7.6 mm/s; (d) CS-1% tested at 7.6 mm/s

4.2 Crack Speed in UHPC

The high speed camera used to capture images of crack growth runs at 75,000 frames per second with a resolution of 256×256 pixels when low rate loading is applied (during testing with the hydraulic servo-controlled testing machine) and at 150,000 frames per second with a resolution of 256×144 pixels when fast loading is applied (during testing with the impact machine). Fig. 6 shows examples of the captured crack propagation images in CS-0%, CS-0.5% and CS-1.0% under various loading speeds. Crack initiation strain rate is computed as an average of the strain time history during which strain increases from zero to the point where the first crack initiates, typically at about 0.0165% strain. This condition corresponds to the point at which there is a sudden change in the slope of the strain versus time plots in Fig. 7. This also follows in spirit the process used by John et al. [26]. Fig. 7 shows examples of the strain rate calculations, while Table 5 summarizes the obtained rate results.

Crack speed is calculated by averaging the slope of the crack length curves (see Fig. 8). The edge detector was used to find the topology of the crack, including the crack tip. Fig. 9 shows an example of crack edge detection using the Canny edge detector. It can be seen in Fig. 9 that the crack edge detector algorithm is capable of accurately detecting the observed crack edges/tips. Fig. 8 illustrates examples of crack speed histories and averaged speeds. Table 5 summarizes all crack speed results from the experiments while Fig. 10 shows the calculated relationships between crack speed and crack initiation strain rate for UHPC.

For the purpose of reference, the theoretical crack speed (i.e. the Rayleigh wave speed) is also plotted in the figure. The Rayleigh wave speed for compressible isotropic elastic solids can be

Fig. 6. Examples of crack propagation under various loading speed: (a) CS-0% specimen with 0.0076 mm/s (using MTS machine); (b) CS-0.5% specimen with Type 1 coupler using the impact testing system

1 **Table 5.** Summary of crack speed results

Test series	Loading speed in MTS (mm/s)	Crack initiation strain rate (1/s)	Crack speed (m/s)	Test series	Coupler type in the impact testing system	Crack initiation strain rate (1/s)	Crack speed (m/s)	
CS-0%	0.0076	0.0255	135	CS-0%	Type 1	16.0	1117	
		0.0424	206			19.3	1420	
		0.0589	306			20.9	876	
	7.6	0.102	514			24.9	1058	
			Type 2		14.5	1201		
					18.3	963		
					32.5	1013		
		1.04			283			
CS-0.5%	7.6	0.0347	3.61	CS-0.5%	Type 1	6.79	954	
		0.0798	15.0			13.7	1079	
		0.203	3.98			20.1	1454	
					Type 2	21.3	1123	
						12.5	1442	
						20.9	1302	
CS-1.0%	7.6	0.0408	1.90	CS-1.0%	Type 1	41.1	827	
						12.0	1118	
						13.8	1380	
		0.108	1.32		Type 2	17.2	1126	
						20.5	1406	
						18.6	1009	
		0.200	4.12			23.1	1072	
						33.0	1127	

2

3 calculated by Eq. (3) [36, 37]:

$$4 \quad (2 - x)^2 = 4\sqrt{1 - x}\sqrt{1 - \gamma x} \quad (3)$$

5 where

$$6 \quad x = \frac{c^2}{c_2^2}, \quad c_2^2 = \frac{\mu}{\rho}, \quad 0 < x < 1, \quad 0 < \gamma \equiv \frac{\mu}{\lambda + 2\mu} < 1 \quad (4)$$

7 and ρ is the mass density of the material, c is the Rayleigh wave speed and μ and λ are the

8 classical Lamé moduli. For UHPC with $E = 50$ GPa, $\nu = 0.18$, $\rho = 2,550$ kg/m³ [18], the Rayleigh

9 wave speed is 2616 m/s, where E is Young's modulus and ν is Poisson's ratio. Experimental results

10 obtained by Zhang et al. [35] are also plotted in Fig. 10 for comparison. The results are comparable

with the experimental results obtained in this study despite the fact that Zhang et al. [35] tested a different concrete material and used a different testing configuration.

Fig. 7. Examples of strain rate calculations: (a) CS-0% tested at 0.0076 mm/s ($\dot{\epsilon} = 0.0589$ 1/s); (b) CS-0.5% tested at 7.6 mm/s ($\dot{\epsilon} = 0.203$ 1/s)

Several observations can be made from Fig. 10. The UHPC series with fiber reinforcement show much lower crack speed than UHPC without fibers at the lower loading speeds (achieved using the MTS hydraulic machine), which indicates that steel fiber reinforcement plays an important role in resisting crack opening at such speeds. In contrast, all UHPC series show similar crack speeds at higher loading rates, suggesting that cracking is independent of fiber reinforcement at these higher loading rates – although the CS-0% series fails right after crack propagation, while CS-0.5% and CS-1.0% series continues to resist load after matrix cracking, up to the point where fibers are pulled-out from the matrix. Fig. 10 also shows that crack speed increases asymptotically as crack initiation strain rate increases, which can be effectively described as a logarithmic function [17], and that the maximum asymptotic crack speed is below the theoretical maximum. The experimentally obtained data can be fitted as:

$$\begin{aligned}
 v &= 323 \log(\dot{\epsilon}) + 657, & R^2 &= 0.852 & \text{for CS} - 0\% \\
 v &= 470 \log(\dot{\epsilon}) + 567, & R^2 &= 0.829 & \text{for CS} - 0.5\% \\
 v &= 494 \log(\dot{\epsilon}) + 535, & R^2 &= 0.914 & \text{for CS} - 1.0\%
 \end{aligned}
 \tag{5}$$

Fig. 8. Examples of calculated crack speeds: (a) CS-0% tested at 0.0076 mm/s; (b) CS-1.0% tested at 7.6 mm/s; (c) CS-0% tested using Type 2 coupler using the impact testing system; (d) CS-0.5% tested using Type 1 coupler using the impact testing system

4.3 Discussion

It was found after visually examining the crack surfaces of all UHPC specimens that there were no noticeable changes in the features of the crack surfaces as a function of crack speed. This is

unlike brittle plastic materials, e.g. polymethylmethacrylate (PMMA) where the fracture surface is featureless up to a certain crack speed and appears jagged thereafter [38]. It was also found that single straight cracks developed predominantly in CS-0% specimens. In contrast, cracks that followed an irregular path occurred in CS-1.0% specimens, which is attributed to the effects of the fibers. Details of the failure surfaces can be found in Pyo [23]. It was noted from examining the specimens that fibers were generally oriented randomly, albeit aligned in the plane of the specimen. The preferential alignment is attributed to the relatively thin geometry of the specimen (25 mm).

Fig. 9. Examples of the final cracking stages in captured and processed images for CS-0% specimens under various loading speed: (a) 0.0076 mm/s (using the MTS machine); (b) 7.6 mm/s (using the MTS machine); (c) Type 1 coupler (using the impact testing system)

5. APPLICATION OF A DYNAMIC FRACTURE MECHANICS MODEL

The achieved relationships (Eq. 5) between crack speed and crack initiation strain rate of UHPC are incorporated into the DIF model proposed by Pyo and El-Tawil [17], which is based on a crack-velocity dependent dynamic fracture mechanics model [39]. The DIF model was originally developed by Pyo and El-Tawil [17] to explain the DIF of conventional concrete under direct tension as shown in Eq. (6).

$$DIF = \frac{\sigma_c^d}{\sigma_c^*} = \frac{K_{Ic}^d / \zeta(v) \sqrt{\pi l / 2}}{K_{Ic}^* / \sqrt{\pi l / 2}} = \frac{1}{\zeta(v)} \quad (6)$$

Fig. 10. Calculated crack speed as a function of crack initiation strain rate and compared with similar experimental data in the literature [35]: (a) including high strain rate results; (b) without high strain rate results

where, l is a crack length. σ_c^d and σ_c^* are the critical stresses in the dynamic and static cases, respectively. K_{Ic}^d and K_{Ic}^* are critical stress intensity factors in the dynamic and static cases, respectively. In this study, K_{Ic}^d and K_{Ic}^* are assumed to be the same following Pyo and El-Tawil [17]. And $\zeta(v) = K_I^d / K_I^*$ is a function correlating between dynamic stress intensity factor (K_I^d)

and static stress intensity factor (K_I^*), which is a function of crack speed, v . Pyo and El-Tawil [17] adopted Gao [6]'s approximation for $\zeta(v) = (1 - v/c_R)\sqrt{1 - v/c_d}$. Here, c_R and c_d are Rayleigh surface wave speed and the dilatational wave speed, respectively. The details of the theoretical model can be found in Pyo and El-Tawil [17].

Fig. 11. Comparison between experimental DIF data for UHPC obtained in Pyo et al. [22] and Pyo [23], and the dynamic fracture mechanics model proposed by Pyo and El-Tawil [17]

The results using the DIF model incorporated into the relationships between crack speed and crack initiation strain rate of UHPC obtained herein (Eq. 5) are plotted in Fig. 11 to contrast with the experimental results obtained in Pyo et al. [22] and Pyo [23]. In these studies, UHPC tensile specimens with various types of steel fibers and fiber volume fractions (V_f) ranging from one to three percent were tested at various strain rates and the experimentally obtained DIF data under tension were presented. Clearly, there is reasonable correlation between the prediction and the experimentally measured DIF data, which suggests that, like conventional concrete, the DIF of UHPC is also strongly associated with the characteristics of dynamic crack growth.

6. CONCLUSION

This experimental study investigated crack propagation in UHPC using three-point bending specimens subjected to a wide range of loading speeds. A hydraulic servo-controlled testing machine was used to generate ‘low’ loading speeds, while the impact testing system developed in Pyo and El-Tawil [25], was modified to achieve ‘fast’ loading speeds. The DIC technique and Canny edge detector technique were used to evaluate notch tip strain and crack speed, respectively. The relationships between crack speed and crack initiation strain rate for UHPC were presented based on the test data. Critical stress intensity factors for UHPC were computed to show the effectiveness of fiber reinforcement in UHPC under bending loading. The observations and findings of this study can be summarized as follows:

- The modified impact testing system was able to successfully perform three-point bending testing of UHPC under impact loading.
- Crack initiation strain rates ranging from 0.025 to 1.0 1/s and from 6.8 to 41.1 1/s were experimentally achieved using a hydraulic servo-controlled testing machine and the modified impact testing system, respectively. Crack speeds of up to 514 m/s were achieved in the former and up to 1454 m/s in the latter.
- Crack speed asymptotically increases as crack initiation strain rate increases. At low loading rates, the steel fiber reinforcement significantly slowed down crack propagation. This resulted in much slower crack speeds in the fiber reinforced cases than the case without fibers. However, at high loading rates, crack speeds were insensitive to the amount

of fibers in the specimens. In addition, the critical stress intensity factor increases substantially as fiber volume increases from 0.5% to 1.0%.

- The crack-velocity dependent dynamic fracture mechanics based DIF model incorporated into the relationships between crack speeds and crack initiation strain rate of UHPC reasonably predicts the experimentally obtained DIF of UHPC in Pyo et al. [22] and Pyo [23]. This suggests that, like conventional concrete, the DIF of UHPC is strongly associated with the characteristics of dynamic crack growth.

ACKNOWLEDGMENTS

The research described herein was sponsored by the National Science Foundation under Grant No. CMS 0928193 and the University of Michigan, Ann Arbor. The first author was partially supported by a grant from R&D Program of the Korea Railroad Research Institute, Republic of Korea. The opinions expressed in this paper are those of the authors and do not necessarily reflect the views of the sponsors.

REFERENCES

- [1] Shukla A, Nigam H. A note on the stress intensity factor and crack velocity relationship for Homalite 100. Eng Fract Mech 1986; 25: 91-102.
- [2] Dally JW, Agarwal RK, Sanford RJ. A study of hysteresis in the K_{ID} - $\dot{a}$ relation. Exp Mech 1990; 30: 177-183.
- [3] Sharon E, Fineberg J. Confirming the continuum theory of dynamic brittle fracture for fast cracks. Nat 1999; 397: 333-335.
- [4] Arakawa K, Mada T, Takahashi K. Correlations among dynamic stress intensity factor, crack velocity and acceleration in brittle fracture. Int J Fract 2000; 105: 311-320.

- 1 [5] Évora VMF, Jain N, Shukla A. Stress intensity factor and crack velocity relationship for
2 polyester/TiO₂ nanocomposites. *Exp Mech* 2005; 45: 153-159.
- 3 [6] Gao HJ. Surface roughening and branching instabilities in dynamic fracture. *J Mech Phys*
4 *Solids* 1993; 41: 457-486.
- 5 [7] Lee KH, Hawong JS, Choi SH. Dynamic stress intensity factors K_I , K_{II} and dynamic crack
6 propagation characteristics of orthotropic material. *Eng Fract Mech* 1996; 53: 119-140.
- 7 [8] Landis CM, Pardoen T, Hutchinson JW. Crack velocity dependent toughness in rate dependent
8 materials. *Mech Mater* 2000; 32: 663-678.
- 9 [9] Camacho M, Ortiz M. Computational modelling of impact damage in brittle materials. *Int J*
10 *Solids Struct* 1996; 33: 2899-2938.
- 11 [10] Belytschko T, Organ D, Gerlach C. Element-free Galerkin method for dynamic fracture in
12 concrete. *Comput Methods Appl Mech Eng* 2000; 187: 385-399.
- 13 [11] Duarte CA, Hamzeh ON, Lyszka TJ, Tworzydło WW. A generalized finite element method for
14 the simulation of three-dimensional dynamic crack. *Comput Methods Appl Mech Eng* 2001;
15 190: 2227-2262.
- 16 [12] Remmers JJC, de Borst R, Needleman A. The simulation of dynamic crack propagation using
17 the cohesive segments method. *J Mech Phys Solids* 2008; 56: 70-92.
- 18 [13] Freund LB. *Dynamic fracture mechanics*. New York: Cambridge University Press; 1990.
- 19 [14] Xie H, Sanderson DJ. Fractal effects of crack propagation on dynamic stress intensity factors
20 and crack velocities. *Int J Fract* 1995; 74: 29-42.
- 21 [15] Krafft JM, Irwin GR. Crack velocity considerations. *Fract Toughness Testing and Its*
22 *Applications*, ASTM STP 1965; 381: 114-129.
- 23 [16] Dally JW, Fourny WL, Irwin GR. On the uniqueness of stress intensity factor-crack velocity
24 relationship. *Int J Fract* 1985; 27: 159-168.
- 25 [17] Pyo S, El-Tawil S. Crack velocity-dependent dynamic tensile behavior of concrete. *Int J*
26 *Impact Eng* 2013; 55: 63-70.
- 27 [18] Graybeal BA. *Material Property Characterization of Ultra-High Performance Concrete*, Report
28 No. FHWA-HRT-06-103, Federal Highway Administration, Washington, DC, 2006.
- 29 [19] Pfeifer CG, Moeser B, Giebson C, Stark J. *Durability of ultra-high-performance concrete*.
30 *Tenth ACI International Conference on Recent Advances in Concrete Technology and*
31 *Sustainability Issues*. No. SP-261-1, 2009.

- 1 [20] Graybeal BA. Ultra-High Performance Concrete, Report No. FHWA-HRT-11-038, Federal
2 Highway Administration, Washington, DC, 2011.
- 3 [21] Graybeal BA. UHPC making strides, Public Roads, Federal Highway Administration,
4 McLean, VA, 2009; 72: 17-21.
- 5 [22] Pyo S, Wille K, El-Tawil S, Naaman AE. Strain rate dependent properties of ultra high
6 performance fiber reinforced concrete (UHP-FRC) under tension. *Cem Concr Compos* 2015;
7 56: 15-24.
- 8 [23] Pyo S. Characteristics of ultra high performance concrete subjected to dynamic loading. Ph.D.
9 Dissertation. University of Michigan, Ann Arbor, 2014.
- 10 [24] Wille K, Naaman AE, Parra-Montesinos GJ. Ultra-high performance concrete with
11 compressive strength exceeding 150 MPa (22 ksi): A simpler way. *ACI Mater J* 2011; 108:
12 46-54.
- 13 [25] Pyo S, El-Tawil S. Capturing the strain hardening and softening responses of cementitious
14 composites subjected to impact loading. *Constr Build Mater* 2015; 81: 276-283.
- 15 [26] John R, Shah SP, Jenq YS. A fracture mechanics model to predict the rate sensitivity of mode
16 I fracture of concrete. *Cem Concr Res* 1987; 17: 249-262.
- 17 [27] Canny J. A computational approach to edge detection. *IEEE Trans Pattern Anal Mach Intell*
18 1986; 8: 679-698.
- 19 [28] Maini R, Aggarwal H. Study and comparison of various image edge detection techniques. *Int*
20 *J Image Process* 2009; 3: 1-11.
- 21 [29] Shah SP. Determination of fracture parameters (K_{Ic}^S and $CTOD_c$) of plain concrete using three-
22 point bend tests. *Mater Struct* 1990; 23: 457-460.
- 23 [30] Wardeh G, Ghorbel E. Prediction of fracture parameters and strain-softening behavior of
24 concrete: effect of frost action. *Mater Struct* 2013; 1-16. DOI: 10.1617/s11527-013-0172-8.
- 25 [31] Trottier JF, Banthia N. Toughness characterization of steel-fiber reinforced concrete. *J Mat*
26 *Civ Eng* 1994; 6: 264-289.
- 27 [32] Banthia N, Sappakittipakorn M. Toughness enhancement in steel fiber reinforced concrete
28 through fiber hybridization. *Cem Concr Res* 2007; 37: 1366-1372.
- 29 [33] Kim DJ, Naaman AE, El-Tawil S. Comparative flexural behavior of four fiber reinforced
30 cementitious composites. *Cem Concr Compos* 2008; 30: 917-928.

- 1 [34] Kim DJ, Park SH, Ryu GS, Koh KT. Comparative flexural behavior of Hybrid Ultra High
2 Performance Fiber Reinforced Concrete with different macro fibers. *Constr Build Mater* 2011;
3 25: 4144-4155.
- 4 [35] Zhang X, Ruiz G, Elazim AMA. Loading rate effect on crack velocities in steel fiber-reinforced
5 concrete. *Int J Impact Eng* 2015; 76: 60-66.
- 6 [36] Rayleigh L. On waves propagated along the plane surface of an elastic solid. *Proc Royal Soc*
7 **A** 1885; 17: 4-11.
- 8 [37] Vinh PC, Ogden RW. On formulas for the Rayleigh wave speed. *Wave Motion* 2004; 39: 191-
9 197.
- 10 [38] Fineberg J, Gross SP, Marder M, Swinney HL. Instability in Dynamic Fracture. *Phys Rev Lett*
11 1991; 67: 457-460.
- 12 [39] Freund LB. Crack propagation in an elastic solid subjected to general loading—II. Non-
13 uniform rate of extension. *J Mech Phys Solids* 1972; 20: 141-152.