1
2
3
4 **Design and Fabrication of Ceramic Beads by the Vibration Method**
5

6 ¹Christian J. Espinoza Santos, ²Arif Z. Nelson, ³Elena Mendoza,
7

8
9 ²Randy H. Ewoldt, and ¹Waltraud M. Kriven
10

11 ¹Department of Materials Science and Engineering, the University of Illinois at
12
13
14 Urbana-Champaign
15

16 ²Department of Mechanical Science and Engineering, the University of Illinois at
17
18
19 Urbana-Champaign
20

21 ³Department of Chemical and Biomolecular Engineering, the University of Illinois at
22
23
24 Urbana-Champaign
25

26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48 **Keywords:** viscoelastic solid, alumina paste, vibration method, and alumina beads,
49

50 ***Corresponding author***
51

52 Waltraud M. Kriven
53

54
55 Email: kriven@illinois.edu
56

57
58 Tel.: +1 217 333 5258; fax: +1 217 333 2736.
59
60
61
62

Abstract

The purpose of this study was to investigate confined vibration method to produce alumina beads for the study of stress wave propagation in granular media. The method produces beads with desirable shape (i.e. Oblate, prolate, and tri-axial ellipsoid), microstructure (level of porosity), and size (5 mm to 3 cm in diameter). This environmentally friendly approach to process beads involves preparing a slurry with a small amount of PVA binder and dispersant. After drying, the pre-formed material is a shear-reversible soft-solid, which flows under applied stress with limited strain recovery. This rheological behavior is sufficient for the alumina paste to be processed into rounded shapes with a confined shaker table and to maintain the shape for sintering of the alumina beads.

1. INTRODUCTION

Early work by Hertz ¹ to understand the contact interaction between granular media motivated a series of publications ^{2; 3}; **Error! Hyperlink reference not valid.** focusing on theoretical and numerical predictions. The problem was extended to 1D granular chains to observe the formation of solitary waves and it was found that solitary waves occur when five or more beads are in contact ^{5; 6}. Although, some experimental work ^{7; 8} was conducted to understand stress wave propagation in granular media, a limitation ⁹ to further the research was due to the limited amount of choices in terms of bead size and bead composition.

In terms of bead size, forming methods such as single and multiple needle systems, ^{10; 11; 12} rotating atomizer for viscous liquids, ¹³ perforated plates, ¹⁴ nozzle mounted in a rotated cylinder, ^{15 16} rotating disc atomization ¹⁷ and electrostatic dripping ^{18; 19; 20} have been to make ceramic beads. However, these methods only produce beads with diameters below 5 mm ^{12; 21; 22; 23; 24; 25; 26; 27}.

This motivated our team to design a new processing technique to make ceramic beads using a modified version of the vibration molding method. The colloidal vibration molding method was previously introduced by Franks et al. ²⁸ where it was demonstrated that saturated ceramic paste, consolidated by either centrifugation or pressure filtration, could be fluidized by vibration and made to flow into a die to produce complex green body shapes ^{28; 29; 30; 31}. Though this approach was successful in producing complex shapes, information about producing spherical beads using this technique has not been reported in the current literature ^{28; 32; 33; 34}. A modified version of the colloidal vibration molding method was introduced in our

1
2
3
4 labs to produce ceramic beads ranging from 0.5 mm to 3 cm in diameter. During an
5
6 attempted slip casting using a plaster of Paris mold,^{35; 36} it was observed that small
7
8 drops of solution had dripped directly onto the vibrating table being used to vibrate
9
10 the alumina mixture into the mold. When this occurred, the small drops of alumina
11
12 solution formed themselves into small spheres.
13
14

15
16 The vibration kept the material sufficiently soft enough to deform and hard enough
17
18 to cause the spheres to bounce around randomly, helping to round them out. As the
19
20 beads slowly dried, they retained their spherical shape. In an effort to improve the
21
22 quality and reproducibility of alumina beads, processing parameters were optimized
23
24 for the original forming process. This work demonstrates how different parameters
25
26 such as the slurry formulation and processing variables of paste rheology affect the
27
28 formation of the alumina beads. More specifically, this work focuses on:
29
30
31

32
33 1.1 Optimizing the alumina slurry formulation by changing the amount of binder.
34

35
36 1.2 Evaluating the rheological behavior of the paste to understand the bead
37
38 shape evolution from non-spherical to spherical.
39

40
41 1.3 Standardizing the vibration process to make beads reproducibly.
42

43
44 1.4 Evaluating the performance of the alumina beads in terms of breaking force
45
46 and number of rotating cycles.
47

48 **2. EXPERIMENTAL PROCEDURES**

49

50
51 The experimental procedure to make alumina beads involves four main steps:
52
53 preparation of the slurry, drying of the slurry, formation of the paste, and
54
55 calcination/sintering of the beads as shown in Fig. 1.
56
57
58
59
60
61
62
63
64
65

2.1. Materials

The experimental procedure to make ceramic beads started with the procurement of alumina powder (A 152 SG Almatix Premium Alumina, Bauxite, AR) with particle size of 1.2 μm and surface area 4.3 m^2/g , polyvinyl alcohol (PVA) binder, 80% hydrolyzed with MW = 9,000-10,000, (PVA binder, Sigma-Aldrich, Saint Louis, MO), and D-3005 dispersant of MW ~ 2,400 (Rohm and Haas, Philadelphia, PA).

2.2. Preparation of Alumina Paste

An alumina slurry was prepared in two steps. Firstly, 55 vol% (82 wt%) of alumina powder was dispersed in 45 vol% (17.3 wt%) distilled water using a 0.8 wt% of ammonium salt dispersant (Duramax 3005) and was mixed for 15 minutes with a magnetic stirrer. All of the additives in the suspension, which included the dispersant and binder, were measured as a function of wt% alumina added. Secondly, 0.1, 0.3, and 0.5 wt% of PVA binder was added to the alumina suspension using a magnetic stir plate at room temperature for a period of 30 minutes, or until all of the binder was fully dissolved in the suspension. The prepared slurry was poured onto a slip-casting platform for partial dehydration before forming. The partial dehydration process of the alumina slurry created alumina paste with ~9 wt% water content. Table 1 shows an example of the slurry formulation before and after dehydration. It is important to clarify that after partial removal of the water, the alumina slurry becomes a paste. The moisture in the alumina slurry was measured by recording the weight before and after the slurries were poured onto the slip-casting platform.

2.3. Rheology of the Alumina Slurry

The rheological behavior of the suspensions was analyzed to gain an insight into the slurry characteristics, which eventually helped to obtain reproducible, consistent behavior. The rheological behavior of the suspensions was measured with a controlled stress (CS) rheometer (CS10, Bohlin Gemini, Worcestershire, UK), in which the apparent viscosity was measured as a function of shear rate. The controlled stress rheometer was fitted in a concentric cylindrical geometry (CS 25, Bohlin Gemini, Worcestershire, UK).

2.4. Rheology of the Alumina Paste

The rheological behavior of the alumina paste was analyzed to evaluate the material response and to gain a better understanding of the bead forming evolution. In order to probe the viscoelastic properties, alumina paste samples were subjected to simple shear deformation with an AR-G2 rotational rheometer (TA Instruments, New Castle, DE). A 40 mm diameter, parallel plate geometry was used for all testing. All stresses reported were apparent stress from direct mapping to the total torque. Temperature was controlled at 25 °C via a Peltier plate. Adhesive-backed 600 grit sandpaper was attached to the parallel plate and Peltier plate to minimize slip. With sandpaper attached, steady shear viscosity measurements at different gaps were in agreement (the difference between 1000 and 800 micron gaps were within the precision error of reproducibility tests at 1000 microns), thus indicating that slip was not significant.

The alumina paste was poured onto the bottom plate and the top plate was lowered to make contact with the sample. The top plate was then slowly lowered

1
2
3
4 while being slowly rotated by hand so that the sample would completely fill the gap.
5
6 The sample was trimmed with a spatula around the end of the plate for proper filling.
7
8 A solvent trap with distilled water was loaded over the top plate to prevent
9 evaporation from the sample. For consistent results, samples were subjected to a
10 prescribed deformation history after loading and before rheological characterization:
11
12 A shear stress of 100 Pa was applied for 120 seconds, then removed for 30 seconds
13 to reset the deformation history.
14
15
16
17
18
19
20

21 To identify the range of strains for which a linear viscoelastic response will be
22 observed, an oscillatory strain amplitude sweep was performed at the highest
23 frequency to be tested. The subsequent frequency sweeps were then performed at a
24 strain which fell within the linear viscoelastic regime of the initial strain sweep. Shear
25 creep and recovery experiments were also performed using the same experimental
26 setup to determine the steady state viscosity as well as the recovery response. After
27 the loading procedure, a particular shear stress was applied for 120 seconds after
28 which the strain recovery was recorded for 30 seconds.
29
30
31
32
33
34
35
36
37
38
39
40

41 **2.5. Fabrication of Spherical Green Bodies**

42
43 The alumina paste was placed on the vibrating table and a series of dividers were
44 used to contain individual pastes to keep them from sticking together and also to
45 make a large quantity of beads simultaneously (Fig. 2). The divider matrix was
46 moved in a circular motion throughout the process until the spheres were firm enough
47 to hold their shape. The beads were rolled around on the vibrating table for about 5
48 minutes, or until they achieved handling strength.
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

2.6. Calcination and Sintering

Calcination (thermal treatment process) was conducted on the green bodies (beads) to remove the unwanted organic materials that were introduced during the forming process of the beads. Thermogravimetric analysis (TGA) using a Netzsch STA 409 CD (Netzsch Instruments, Selb, Germany) was conducted to observe the water evolution and decomposition of the organic materials during the calcination stage. These studies were conducted at a temperature ranging from 25 °C to 800 °C at 10 °C/min for heating and cooling. As a result, calcination was conducted at 700 °C for 1 hr with heating of 0.5 °C/min and cooling down of 5 °C/min because lower heating and cooling rates helped with avoiding thermal shock during the thermal treatment process.

Sintering was conducted to fuse the particles and create a solid ceramic body³⁷. During the process, the atoms in the material diffused across the grain boundary of the particles³⁷. Sintering in the alumina beads was conducted at temperatures ranging from 1400 °C to 1650 °C for 4 hours. A constant time with increasing temperature during sintering was selected to optimize the sintering process of the beads and to observe the changes in density and microstructure evolution. Optimal sintering conditions such as the ones that will be discussed in this paper can enhance properties in the alumina beads resulting in higher density and strength³⁷.

2.7. Characterization of the Alumina Beads

The density, breaking force, and number of rotating cycles with microstructure analysis were used to analyze the mechanical properties and performance of the beads. First, the density of each sample was measured following the Archimedes

method ³⁸. In addition, the microstructure of the ceramic beads was observed to confirm the density measurements. Images were taken with a scanning electron microscope (JSM-6060LV, JEOL USA, Inc., Peabody, MA) using excitation energy of 20 kV. Prior to imaging, the samples were Au–Pd sputter-coated for 25 seconds to prevent charging of specimens. Moreover, the breaking force of the alumina beads was measured on a universal testing machine (Model 4502, Instron Corp., Canton, Mass.). A total of 5 beads per sample condition were analyzed under compression.

Comminution of the ceramic beads was performed in a tumbler to observe the loss of material and reduction of the bead diameter as the number of rotating cycles was increased. This test provides the mass and diameter wear rate of the sintered alumina beads prepared by the vibration method. Friction between the alumina beads during ball milling causes wear in the material when the beads are rolling and sliding over each other ^{39; 40}. The test was conducted for one month at 220 rpm and a total of 32 sintered beads were measured at different time intervals. The mass wear rate (Ω_t) was evaluated based on linear wear theory, where a gradual consumption process takes place by grinding beads inside a tumbler. The mass wear rate (Ω_t) in the ceramic beads was calculated using Equation 1

$$\Omega_t = \frac{d(m_b)}{d(t)} = -k_m A_b \quad (1)$$

where $\frac{d(m_b)}{d(t)}$ is the mass wear rate as a function of time, A_b is the exposed ball area, and K_m is the mass rate constant of the bead.

Similarly, the diameter wear rate $\frac{d(D)}{d(t)}$ in the ceramic beads was calculated using Equation 2.

$$\frac{d(D)}{d(t)} = -2 \frac{k_m}{\rho_b} = -K_d \quad (2)$$

where ρ_b is the ceramic bead density and K_d is the wear rate constant of the bead.

As a last characterization step, the eccentricity of the ceramic beads was measured. The eccentricity ⁴¹ is associated with how much something deviates from being circular. The eccentricity of the ceramic beads was measured in three mutually orthogonal planes xy, xz, and yz using Equation 3.

$$\sqrt{1 - \frac{b^2}{a^2}} \quad (3)$$

where a and b are the radii in any plane of the alumina bead. When the result of Equation 3 is 0, the plane is circular. However, when the result of Equation 3 is 1, the plane is an ellipse. The 3D construction of the three planes measured in the xy, xz, and yz give either a perfect sphere or an ellipsoid. Equation 4 provides the graphical representation of the ellipsoid.

$$\frac{x^2}{a^2} + \frac{y^2}{b^2} + \frac{z^2}{c^2} = 1 \quad (4)$$

Based on Equation 4, any of the bead geometry types can result: a sphere is when radius $a=b=c$, an oblate ellipsoid is when radius $a=b>c$, a prolate ellipsoid is when radius $a=b<c$, and a tri-axial or scalene ellipsoid is when $a>b>c$.

3. RESULTS AND DISCUSSION

3.1. Formation of Green Bodies

One of the advantages of the bead forming method is the ability to recycle the dry material, so this method is environmentally friendly because it requires only a small amount of binder and dispersant. The original formulation previously used for slip casting was modified by changing the amount of binder added to the suspension. To improve the formulation, three different amounts of PVA binder were used: 0.1, 0.2, and 0.5 wt% of PVA. To observe the variation in terms of rheology, viscosity measurements were performed in each suspension. It was observed that by increasing the amount of binder, the viscosity increased as shown in Fig. 3. All three suspensions showed shear thinning behavior for shear stresses above 1 Pa (Fig. 3 inset). The lower PVA concentrations (0.1 and 0.2 wt%) approached a high-rate plateau viscosity for shear stress above 10 Pa.

To test each formulation, all of the alumina slurries went through the same dehydration process (water removal) to form pastes. Through physical observations of the alumina paste when exposed to the vibrating table, the following were determined: (a) with 0.1 wt% PVA binder, the spherical green bodies did not hold their shape well enough; (b) with 0.5 wt% PVA binder, the alumina paste did not flow and the texture of the paste was too sticky; (c) with 0.2 wt% PVA binder, the spherical green bodies retained their shape and had good flowability when the intensity of the vibrating table was increased; (d) the paste that was dried was recycled for new batches. In addition, samples with 0.2 wt% PVA binder were good for making green bodies with a semi smooth surface. Having a smooth surface on the green bodies

helped to measure the green body density. The rest of the experiments in this paper were conducted using an alumina paste with 0.2 wt% PVA binder.

3.2. Rheology of the Alumina Paste

High quality ceramic green (body) beads were formed with the modified vibration molding method with the 0.2 wt% PVA formulation. An important aspect of the research was focused on understanding the type of rheology associated with the ability to form the paste into round shapes with the confined vibration processing method. The first observation while forming the beads was that the alumina paste required flowability under applied stress. Second, the alumina paste needed to be moldable, but with the ability to retain its shape. During rheological measurements of the paste, shear thickening at high stress was observed. Previous literature reported shear thickening in high loading slurries ⁴². However, it was unclear whether the formation of green body beads was purely dependent on a specific type of rheological behavior during the formation process. To understand the forming process of the green body beads using the alumina paste, several oscillatory, shear creep and recovery measurements were conducted.

3.3. Oscillatory Measurements

During oscillatory measurements, strain amplitude sweeps demonstrated that on time scales of ten seconds or less, alumina paste with 0.2 wt% PVA is a viscoelastic solid with non-linear softening upon the application of large strains or stresses. Figure 4 shows the results of strain sweeps performed at a frequency of 10 rad/s. Due to the material's sensitivity to water content, there was much difficulty in obtaining reproducible data. As such, it can be seen that across multiple samples, the

linear viscoelastic moduli may vary up to a half order of magnitude. Even with this variability, the qualitative trend clearly shows a linear viscoelastic plateau at low strain (and stress), followed by reversible yielding near an apparent stress amplitude of 2 Pa (Fig. 4 inset).

The results of linear viscoelastic frequency sweeps performed at a strain amplitude of 0.1% can be seen in Fig. 5. Due to the difficulty in obtaining reproducible data across multiple samples, the elastic storage modulus in this case would sometimes vary by over an order of magnitude. However, in the linear viscoelastic regime of small strains, the elastic storage modulus, G' , always dominated the viscous loss modulus, G'' , as seen by the loss ratio $\tan(\delta) = G''/G'$, the ratio of the viscous loss modulus to the elastic storage modulus, always being less than 1 and as low as 0.2. The sample shows a weak frequency dependence with slightly lower moduli at lower frequencies and slightly higher $\tan(\delta)$ at lower frequencies, but no crossover frequency was observed. During the bead formation process, the frequency of impact was found to be approximately 60 rad/s. This frequency fell within the tested range, indicating that during processing, the material was behaving as a shear-reversible visco-elasto-plastic solid. The application of large strain amplitudes was limited by instrumental inertia eventually dominating the torque response, but the initial nonlinear response at all tested frequencies universally showed both G' and G'' initially decreasing as a function of applied strain amplitude.

3.4. Shear Creep and Recovery

The creep and recovery responses of alumina paste containing 0.2 wt% PVA are shown in Figure 6 for shear stresses of 10 and 100 Pa. Here it can be seen that the

1
2
3
4 nonlinear response was predominantly plastic, as there was little recovery of the
5
6 accumulated strain. For stresses in the range of 10 to 1000 Pa on time scales of the
7
8 order of 10 s, the maximum recoverable compliance was always less than 1%.
9
10 Responses within the linear regime could not be verified with creep tests due to poor
11
12 reproducibility (water evaporation).
13
14

15
16 The steady state viscosity data for stresses in the range of 10 to 1000 Pa can be
17
18 seen in Fig. 7. Within this range, shear thickening was observed as the steady state
19
20 viscosity increased by a factor of 100. Although the material displayed shear
21
22 thickening, it was unclear how important this was to enabling bead processing.
23
24

25
26 We conjecture that the primary rheological requirement for vibration processing is
27
28 to behave as a solid at low stress on the relevant timescales to retain shape and
29
30 behave as a nonlinear plastic material exhibiting limited strain recovery at higher
31
32 stress to enable formation into rounded shapes. A yield stress would characterize
33
34 this transition, and the required/target yield stress would need to lie within a particular
35
36 range, depending on processing conditions and desired final shape of the bead. If
37
38 shear-thickening is relevant, it may serve the secondary role of limiting the
39
40 deformation of the paste during the largest impacts during processing. This may
41
42 reduce the statistical variability of strains induced by vibration impacts and result in
43
44 smoother beads. Here we have characterized what rheology is *sufficient* for
45
46 processing, for the 0.2 wt% PVA formulation. The minimum required rheological
47
48 requirements, such as range of yield stress and presence of shear thickening, are
49
50 beyond the scope of this work but could be tested by formulating a range of samples
51
52 with deliberately different rheology.
53
54
55
56
57
58
59
60
61
62
63
64
65

3.5. Calcination and Sintering of Beads

Thermal analysis for calcination and sintering of the beads were conducted: First, TGA results confirmed that there was an initial ~9 % weight loss decrease at 100 °C corresponding to the evolution of H₂O. This large amount of mass loss was due to the entrapped water within the outer dry shell of the green body. A ~2% at 425 °C mass loss was also observed, which corresponded to the burnout of the binder, dispersant, and any other organics (Fig 8). The calcination was carried out at 700 °C for 1 hour to complete decomposition of all volatile matter ⁴³. A slow calcination rate of 0.5 °C/min during calcination prevented thermal shock when the evaporation of the volatile matter occurred ⁴³.

During sintering, the ramp-up rate was increased to 5 °C/min and the samples were sintered at various temperatures from 1400 °C to 1650 °C with increments of 50 °C to induce densification. The samples sintered at 1400 °C/ 4 hours gave a density of 3.25 ± 0.14 g/cm³, but when the samples were sintered at 1650 °C/ 4 hours, the density was 3.78 ± 0.06 g/cm³. There was a 14 % increase in density when the temperature was incremented by 250 °C. To visually corroborate these results, the micrographs using SEM (Fig. 9(a)) reveal the porosity network of samples sintered at 1400 °C/ 4 hours. Moreover, when looking at the average grain size of the samples sintered 1400 °C/ 4 hours, two different features in the microstructure were observed: large agglomeration of grains (~20 µm in size) and small grains ranging between 1-3 µm in size with a dense network of porosity (Fig. 9(b)). In the opposite case, where the samples were sintered at 1650 °C for 4 hours, the microstructure revealed large grains ($x \geq 20$ µm in size) and few a large pores with ~15 µm in size.

3.6. Characterization of the Alumina Beads

The samples (five beads were measured and tested per condition) sintered at 1650 °C for 4 hours had a compressive load strength of 3954 ± 93 N, which was 71.6 % higher than the samples sintered at 1400 °C/4 hours. Table 2 summarizes breaking force, density, and bead diameters of tested samples.

The comminution results as a function of milling time provided more information (i.e. mass and diameter wear rate) on the performance of the alumina beads. Figure 10 shows the bead diameter reduction and bead weight loss due to the milling of the beads. The slopes in Fig. 10 are the diameter $\frac{d(m_b)}{d(t)}$ and mass $\frac{d(m_b)}{d(t)}$ wear rate from Equation 1 and 2.

In addition, Fig. 10 shows the three different stages of the alumina beads when they were exposed to longer milling time at a fixed 220 rpm. During the first stage, the rotating motion refined the surface of the beads; this step was considered as a refinement step to improve the finishing of the beads. The first stage occurred within the first 50 hours of milling time and the average bead diameter was reduced by 0.7%. During the second stage, the average bead diameter remained constant without wear/erosion. The second stage happened between 50-300 hours of milling time. The third stage occurred between 300 to 750 hours of milling time; beads at this point experienced excessive material loss that resulted in the misshaping or fracturing of the alumina beads, similar observation was obtained in the literature ⁴⁴. Knowing the slopes of each plot allowed calculation of the mass (K_m) and diameter wear (K_d) rate constants for the alumina beads. Fig 11(a) and Fig 11(b) shows the mass and diameter rate constants calculated using Equation 1 and Equation 2.

As the final characterization step, the eccentricity using Equation 3 was calculated in the xy, xz, and yz planes. The data was divided into four groups based on the bead diameter. It was found that in all the planes for the four diameter groups, the eccentricity was below 0.07. Having an eccentricity below 0.07 indicates the alumina beads could be produced by the vibration method, which are spherical (Fig. 12). In addition, Table 3 shows the distribution of the sphere-like type of beads measured.

4. CONCLUSION

The vibration method proved to be effective in producing alumina beads having tailorable size (Fig. 13) and shape (i.e. oblate, prolate, and tri-axial ellipsoid). The best slurry composition to make alumina beads was with 0.2 wt% with a PVA binder. After the removal of water during the dehydration step, the composition changed to a workable paste with ~9 wt% water content. In addition, characterization of the alumina paste rheology indicated a viscoelastic solid at low stress (<2 Pa) with nonlinear softening upon the application of larger stress or strain. In the linear viscoelastic regime of small strains, the elastic storage modulus, G' , always dominated the viscous loss modulus, G'' , and no crossover frequency was observed. Furthermore, it was found that the frequency of impact (60 rad/s) fell within the tested range of the alumina paste. Moreover for shear stresses of 10 to 100 Pa, the nonlinear response was predominantly plastic as there was little recovery of the accumulated strain. For stresses in the range of 10 to 1000 Pa, the maximum recovery compliance was always less than 1%. Based on the thermal treatment process, the optimum conditions were 700 °C/1 hour for calcination and 1650 °C/4hrs for sintering where the density was 97% of theoretical value and the load of the

1
2
3
4 alumina beads were $\sim 3954 \pm 93$ N. Furthermore, the refinement step provided more
5
6 insight into the mechanical performance of the alumina beads. The three stages
7
8 under longer milling times reveal that during the first 50 hours, the bead diameter was
9
10 reduced by 0.7%; during the second stage, the diameter remained constant; and
11
12 during the third stage the alumina bead either fractured or became misshapen. Thus
13
14 a processing method for making ceramic beads larger than 5 mm in diameter has
15
16 been developed.
17
18
19
20

21 **ACKNOWLEDGMENTS**

22
23 This work was funded by the Army Research Office (ARO), the DoD Multi University
24
25 Research Initiative (MURI) Program through Dr. David Stepp under grant No.
26
27 W911NF-09-1-0436. The authors acknowledge the National Science Foundation
28
29 Graduate Research Fellowship Program (NSF-GRFP) under grant No. NSF DGE 11-
30
31 44245 for their support during graduate school studies. Some of the experiments in
32
33 this paper were carried out in the Frederick Seitz Materials Research Laboratory
34
35 Central Facilities, University of Illinois at Urbana-Champaign, which are partially
36
37 supported by the U.S. Department of Energy under grants DE-FG02-07-ER46453
38
39 and DE-FG02-07-ER46471. Rheological studies were conducted at the Ewoldt
40
41 Research Labs at the University of Illinois. In addition, the authors acknowledge Mr.
42
43 Benjamin Walusiak and Mr. Samuel Hayes for helping to with the setup of some of
44
45 the experiments presented in this paper. Also, the authors acknowledge Dr.
46
47 Pathikumar Sellappan and Mr. Kevin Seymour for providing recommendations to
48
49 improve the quality of the paper.
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

REFERENCES

1. Hertz H. On the contact of elastic solids. Journal of Reine und Angewandte Mathematik 1881; **92**: 156-71.
2. Job M, Adam S, Surajit S. How hertzian solitary waves interact with boundary in a 1D granular medium. Physical Review Letters, 2005; **94**: 178002.
3. Daraio C, Nesterenko V, Herbold EB, Jin S. Tunability of solitary wave properties in one-dimensional strongly nonlinear phononic crystals. Physical Review E 2006; **73**: 026610.
4. Job M, Santibanez F, Tapia F. Nonlinear waves in hertzian granular chains: effects of inertial and stiffness heterogeneities. Proceedings of the International Congress on Ultrasonics: 1-5
5. Nesterenko, V. Solitary waves in discrete media with anomalous compressibility and similar to "sonic vacuum". J. Phys. IV France 1994; **04**: C8-729-C8-734.
6. Coste EF, Fauve S. Solitary waves in a chain of beads under hertz contact. Journal of Physical Review E, 1997; **56**: 5.
7. On T. Experimental study of the development of plastic waves in one-dimensional granular media. Department of Aerospace Engineering **Vol. Master in Science in Aerospace Engineering**. University of Illinois at Urbana-Champaign, 2011: pp. 1-63.
8. On T, LaVigne LA, Lambros J. Development of plastic nonlinear waves in one-dimensional ductile granular chains under impact loading. Mechanics of Materials 2014; **68**: 29-37.

9. Daraio C, Nesterenko V. Strongly nonlinear wave dynamics in a chain of polymer coated beads. *Physical Review E* 2006; **73**: 026612.
10. Hulst AC, Van't Riet TK, Westerbeek JM. A new technique for the production of immobilized biocatalyst in large quantities. *Biotechnology and Bioengineering* 1985; **27**: 870-876.
11. Walker HL, Connick WJ. Sodium alginate for production and formulation of mycoherbicides. *Weed Science* 1983; **31**: 333-338.
12. Espinoza Santos CJ, Wei TS, Cho B, Kriven WM. A forming technique to produce spherical ceramic beads using sodium alginate as a precursor binder phase. *Journal of the American Ceramic Society* 2013; **96**, 11: 3379-3388.
13. Fair JR, Steinmeyer DE, Penny WR, Brink JA. Liquid-gas systems. in: chemical engineer's handbook. McGraw-Hill: The Univeristy of California; 1973.
14. Klein JS, Vorlop J. Pore size and properties of spherical ca-alginate biocatalysts. *Applied Microbiology and Biotechnology* 1983; **18**: 86-91.
15. Matulovic U, Rasch D, Wagne F, New equipment for the scaled up production of small spherical biocatalysts. *Biotechnology Letters*, **8**[7] 485-90 (1986).
16. Vlach TJ, Yaroshenko V, Pujar VV. Method of forming ceramic beads. pp. 7. in, **Vol. US 6797203 B2**. CerCo LLC, United States, 2004.
17. Bégin A, Castaigne F, Goulet J. Production of alginate beads by a rotative atomizer. *Biotechnology Techniques* 1991; **5**: 459-464.
18. Bugarski B, Li Q, Goosen M, Poncelet D, Neufeld RJ, Vunjak G. Electrostatic droplet generation: mechanism of polymer droplet formation," *AIChE Journal* 1994; **40**: 1026-1031.

19. Romo S, Pérez-Martínez C. The use of immobilization in alginate beads for long-term storage of *pseudanabena galeata* (cyanobacteria) in the laboratory. *Journal of Phycology* 1997; **33**: 1073-1076.
20. Walsh PW, Isdell FV, Noone SM, O'Donovan MG, Malone DM. Growth patterns of *saccharomyces cerevisiae* microcolonies in alginate and carrageenan gel particles: effect of physical and chemical properties of gels," *Enzyme and Microbial Technology* 1996; **18**: 366-372.
21. Monakhova Y, Agulhon P, Quignard F, Tanchoux N, Tichit D. New mixed lanthanum- and alkaline-earth cation-containing basic catalysts obtained by an alginate route. *Catal. Today*, **189**[1] 28-34 (2012).
22. Nozaki T, Arima T, Idemitsu K, Inagaki J. Synthesis of zirconia sphere particles based on gelation of sodium alginate. *Journal of Nuclear Materials* 2011; **412**: 184-19.
23. Abramson S, Meiller C, Beaunier P, Dupuis V, Perrigaud L, Bee A, Cabuil V. Highly porous and monodisperse magnetic silica beads prepared by a green templating method. *Journal of Materials Chemistry* 2010; **20**: 4916-4924.
24. Teraoka K, Kato K. Production of alpha-tcp ceramic precision spheres for mosaic-like ceramics fabrication use. *Bioceramics Development and Application Journal* 2010;**1**: 1-3.
25. Yang J, Yu J, Huang Y. Recent developments in gelcasting of ceramics. *Journal of the European Ceramic Society* 2011; **31**: 2569-2591.
26. Garcia-Perez P, Pagnoux C, Pringuet A, Videcoq A, Baumard JF. Agglomeration of alumina submicronparticles by silica nanoparticles: application to processing

- spheres by colloidal route. Journal of Colloid and Interface Science 2007; **313**: 527-36.
27. Dilsiz N, Akovalı G. Study of sol-gel processing for fabrication of low density alumina microspheres, Materials Science and Engineering: A 2002; **332**: 91-96.
28. Franks GV, Velamakanni BV, and Lange FF. VibraForming and in situ flocculation of consolidated, coagulated, alumina Slurries. Journal of the American Ceramic Society 1995; **78**: 1324-1328.
29. Velamakanni BV, Lange FF. Method for preparation of dense ceramic products. in United States Patent, **Patent US005188780A**. Edited by The Regents of the University of California, United States, 1991.
30. Velamakanni BV, Chang JC, Lange FF, Pearson DS. New method for efficient colloidal particle packing via modulation of repulsive lubricating hydration forces Langmuir 1990; **6**: 1323-1325.
31. Luther PE, Kramer TM, Lange FF, Pearson DS. Development of short-range repulsive potentials in aqueous, silicon nitride slurries. Journal of the American Ceramic Society 1994 **77** :1047-1051.
32. Yu J, Yang J, Huang Y. The transformation mechanism from suspension to green body and the development of colloidal forming," Ceramics International 2011 **37**: 1435-1451.
33. Pivinskii YP. Refractory concretes of new generation. vibrorheology, vibration methods of compacting and forming. Refractories 1994; **35**: 211-220.
34. Evans JR. Seventy ways to make ceramics," Journal of the European Ceramic Society 2008; **28**: 1421-1432.

- 1
2
3
4 35. Requena J, Moreno R, J. Moya JS. Alumina and alumina/zirconia multilayer
5
6 composites obtained by slip casting. Journal of the American Ceramic Society
7
8 1989; **72**: 1511-13.
9
10
11 36. Buck GM and Vasquez P. Ceramic slip casting technique. in. Google Patents 1993.
12
13
14 37. Uhlmann KB. Introduction to ceramics. John Wiley & Sons: New York 1960.
15
16
17 38. Standard test method for water absorption, bulk density, apparent porosity, and
18
19 apparent specific gravity of fired whiteware products. ASTM International, West
20
21 Conshohocken, PA 1, 2006: 1-2
22
23
24 39. Schwedes M. Comminution of ceramics in stirred media mills and wear of grinding
25
26 beads. Journal of Powder Technology 1999:374-81.
27
28
29 40. Zhong WB, Lianmeng Z, Fang F, and Xiaoyi H. Prediction and experimental testing
30
31 of spherical milling media wear rate," Materials Transactions 2005; **46**: 2036-
32
33 2040.
34
35
36 41. Wadell H. Volume, shape, and roundness of quartz particles," The Journal of Geology
37
38 1935; **43**: 250-280.
39
40
41 42. Barners HA. ShearThickening ("dilatancy") in suspensions of nonaggregating solid
42
43 particles dispersed in newtonian liquids," journal of Rheology 1989; **329**: 329-
44
45 366
46
47
48 43. Lee SJ, Benson EA, and Kriven WM. Preparation of portland cement components by
49
50 poly(vinyl alcohol) solution polymerization. Journal of the American Ceramic
51
52 Society 1999; **82**: 2049-2055.
53
54
55 44. Becker M and Schwedes J. Comminution of Ceramics in Stirred Media Mills and Wear
56
57 of Grinding Beads. Powder Technology 1999: **105**[1-3] 374-381.
58
59
60
61
62
63
64
65

Table 1 An Example of the Alumina Formulation Before and After Dehydration

Component	Alumina Powder	Dispersant (Duramax 3005)	DI Water	Binder (PVA 80 % hydrolyzed)
Alumina slurry (before dehydration)*	55 vol % (82.7 wt %)	0.8 wt % (of alumina)	45 vol % 17.3 wt %	0.2 wt % (of alumina)
Alumina paste (after dehydration)**	91.5 wt %	0.8 wt % (of alumina)	8.5 wt %	0.2 wt % (of alumina)

(percentages of the alumina slurry* and paste** are not the same because water is removed from slurry using a porous medium)

Table 2 Properties of Alumina-Sintered Beads as a Function of Sintering
Temperature

Sintering Conditions	Bulk density (g/cm³)	Theoretical density (%)	Bead diameter (mm)	Compressive load (N)
1400°C/4 h	3.25 ± 0.14	83.4	8.50 ± 0.10	1122 ± 240
1450°C/4 h	3.31 ± 0.15	84.9	8.50 ± 0.08	1712 ± 300
1500°C/4 h	3.49 ± 0.14	89.4	8.50± 0.06	2161 ± 315
1550°C/4 h	3.60 ± 0.08	92.3	8.50 ± 0.08	2716 ± 79
1600°C/4 h	3.67 ± 0.07	94.1	8.50 ± 0.07	3948 ± 13
1650°C/4 h	3.78 ± 0.06	97.0	8.50 ± 0.08	3954 ± 93

Table 3 Selection of the Type of Ellipsoid for the Alumina Beads Based on Their
Radius in the xy, xz, and yz Planes

Tri-axial or scalene ellipsoid ($a>b>c$)	Oblate Ellipsoid ($a=b>c$)	Prolate ellipsoid ($a=b<c$)	Sphere ($a=b=c$)
53.6%	25.0%	25.4%	0

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9

Figure 10

Figure 11

Figure 12

Figure 13

Figure 1 Bead forming process showing the four main steps (mixing, drying, forming, and calcination/sintering) to make alumina beads

Figure 2 Experimental setup to make alumina beads

Figure 3 Viscosity as a function of shear rate of alumina slurries with 0.1, 0.2, and 0.5 wt% polyvinyl alcohol (PVA) binder

Figure 4 Strain amplitude sweep of the alumina paste with 0.2 wt% PVA binder at 10 rad/s

Figure 5 Linear Viscosity frequency sweep of the alumina paste with 0.2 wt% PVA binder at 0.1% strain amplitude

Figure 6 The nonlinear creep and recovery (after 120 s) of the alumina paste 0.2 wt% PVA binder at 100 Pa and 10 Pa

Figure 7 Shear thickening in steady shear of the alumina paste with 0.2 wt% PVA binder. Inconclusive measurements were obtained from 1-10 Pa and shear thickening behavior was observed from 10-1000 Pa

Figure 8 Thermogravimetric analysis of alumina slurry with 0.2 wt% PVA showing 10 % weight loss from 25-100 °C and 1.1 % weight loss from 100-300 °C

Figure 9 SEM micrographs of the microstructure of alumina beads sintered for 4 hours at (a) 1400 °C and (b) 1650 °C.

Figure 10 Diameter and weight profiles of the alumina beads as a function of milling time, with the first (0-50 hours), second (50-300 hours), and third (300-800 hours) stages of the bead evolution over milling time

Figure 11 The mass and diameter wear rate contact as a function of rotating cycles for alumina beads sintered at 1650 °C/4 hours

Figure 12 Eccentricity in the xy, xz, yz planes for alumina beads sintered at 1650 °C for hours

Figure 13 Alumina beads sintered at 1650 °C for 4 hours