Transmission electron microscopy characterization on the interfacial structure of a galvanized dual-phase steel

I. Aslam^{*a,b}, B. Li^{a,c}, R.L. Martens^d, J.R. Goodwin^d, H.J. Rhee^{a,b}, F. Goodwin^e.

^a Center for Advanced Vehicular Systems, Mississippi State University, MS 39759, United States.

^b Department of Mechanical Engineering, Mississippi State University, MS, 39762, United States.

^c Department of Chemical and Materials Engineering, University of Nevada, Reno, NV 89557, United States.

^d Central Analytical Facility, the University of Alabama, Tuscaloosa, AL 35487, United States.

^e International Zinc Association, Durham, NC 27713, United States.

Corresponding author: Imran Aslam, ia31@msstate.edu, 662-769-1185

Abstract

Site-specific studies were carried out to characterize the interface of a galvanized dual-phase (DP) steel. Focused ion beam (FIB) was used to prepare specimens the interface region (~100 nm thick) between the coating and the substrate. Transmission electron microscopy (TEM), scanning TEM (STEM) and high resolution TEM (HRTEM) were performed to resolve the phases and the structures at the interface between the zinc (Zn) coating and the steel substrate. The STEM and TEM results showed that a continuous manganese oxide (MnO) film with a thickness of ~20 nm was present on the surface of the substrate while no silicon (Si) oxides were resolved. Internal oxide particles were observed as well in the sub-surface region. Despite the presence of the continuous oxide film, a well-developed inhibition layer was observed right on top of the oxide film. The inhibition layer has a thickness of ~100 nm. Possible mechanisms for the growth of the inhibition layer were discussed.

Key Words: Electron Microscopy; Dual Phase Steel; Galvanizing; Inhibition layer; Oxides

1. Introduction

In continuous hot-dip galvanizing of automotive steels, a strip is submerged into a molten zinc (Zn) bath which contains a small amount of aluminum (Al) (<0.2% depending upon the nature of processing). Metallurgical reactions occur instantly at the solid-liquid interface. Because the affinity between iron (Fe) and Al is much higher than that between Zn and Fe, a thin layer of Fe-Al intermetallic (Fe_2Al_5 or $\text{Fe}_2\text{Al}_{5-x}\text{Zn}_x$) [1] is developed on the steel substrate surface. The thickness of this interface region falls in the range of ~100 nm [2]. The formation of the Fe-Al intermetallic delays or inhibits the formation of brittle Fe-Zn intermetallics and enables good adhesion between the Zn-coating and the steel [3].

The interest in improved fuel efficiency of vehicles has stimulated the development of the third generation (3G) of advanced high strength steels (AHSSs) which are vital for weight reduction. Mass reduction and the resultant better fuel efficiency can be achieved when the strength of steels is increased [4,5]. New generation AHSSs contain higher concentration of alloying elements, for example, silicon (Si) and manganese (Mn) that are key players for higher strength. However, the addition of these alloying elements with higher concentrations poses a challenge to the galvanizability that is crucial for enhanced corrosion resistance of the AHSSs [6]. One of the primary concerns for continuous galvanizing lines (CGLs) is selective oxidation of Si and Mn on steel surfaces during annealing. The Si and Mn oxides are difficult to be reduced by hydrogen [7,8,9,10] and these oxides remain on the surfaces before hot dipping. Oxidation may occur both externally and internally depending upon the oxidizing potential inside the annealing furnace [11,12,13,14]. Thus, understanding the structure of the interface of galvanized high strength steels is crucially important. How these oxides affect galvanizing of AHSSs has been the subject of extensive discussions [7,8,9,10,11,12,13,14] most recently.

Due to the complexity and the fine scale of the metallurgical reactions at the interface, characterizing the interfacial structure with clarity is rather challenging. The interface of galvanized steels has been studied extensively and primarily by scanning electron microscopy (SEM), glow discharge optical emission spectroscopy (GDEOS) which allows characterization across the Fe-Zn interface by sputtering through its thickness [15], energy dispersive spectroscopy (EDS) or x-ray photoelectron spectroscopy (XPS) [13, 16]. A number of transmission electron microscopy (TEM) studies have been conducted on the interface of galvanized steels only after focused ion beam (FIB) was available [2,17,18,19,20,21,22,23,24,25] since conventional TEM specimen preparation approaches are unable to locate the interface. These previous studies have shown very promising results in resolving the fine interface.

As part of the ongoing research on how processing parameters such as dew point affect oxidation and the subsequent coating processes of high strength steels, in this work, we employed TEM, high resolution TEM (HRTEM) and scanning TEM (STEM) and performed bright field (BF) and dark field (DF) imaging to characterize the interfacial structures of a galvanized dual phase (DP) steel. The results shed new insight on the galvanizing of high strength steels and the growth of the inhibition layer.

2. Experimental Method

The material used in this work is a galvanized dual phase (DP) steel supplied by POSCO. The chemical composition of such DP steel is shown in Table 1. The composition of Mn and Si are 1.75 wt% and 0.19 wt%, respectively. The steel strip was annealed at a well-controlled dew point. The peak annealing temperature before the Zn bath was 780 °C and the composition of the annealing gas was 95% N₂ and 5% H₂ with a dewpoint of -40 °C. The bath temperature of the

1 Zn bath was 460 °C. The 1.0 mm thick steel strip was hot-dipped with a galvanizing bath with a
2 dissolved Al concentration between 0.14 – 0.2% so that a full inhibition layer can be expected.

3 To prepare TEM specimens, first, the galvanized specimen was mechanically polished on the
4 cross-section through the thickness. The polishing was carefully performed to minimize the
5 mechanical damage to the interface region between the steel substrate and the coating. After
6 polishing, the Zn coating was well revealed. Afterwards, focus ion beam was used on a TESCAN
7 Lyra to fabricate specimens for TEM analysis. A thin slice approximately 1.0 µm thick was first
8 fabricated by digging trenches around the slice (Figure 1a). During milling, EDS mapping was
9 performed on the slice to ensure that the slice contains both the substrate and the coating. Before
10 the FIB fabrication, a 1.0 µm thin layer of platinum was deposited on the area of interest such
11 that the area of interest was protected from rapid sputtering and gallium implantation by the ion
12 beam. The regions adjacent to the area of interest were sputtered away (Figures 1a and 1b). Once
13 these trenches were created, the specimen was severed off from the bottom such that the
14 specimen was only connected with the bulk at one side, i.e., the specimen was a dangling
15 cantilever. A tungsten needle was then carefully inserted to make a gentle contact with the thin
16 specimen. Then platinum was deposited to weld the needle to the specimen. This was followed
17 by severing the last connection between the thin specimen and the steel substrate. The thin slice
18 was then transferred and welded onto the top of a TEM copper grid via platinum deposition on
19 the points of contact, as illustrated in Figure 1c. The tungsten needle was then cut off from the
20 specimen and retracted. A final thinning of the specimen was performed to reduce the thickness
21 to the level of electron transparency. A FEI TECNAI F-20 transmission electron microscope
22 (TEM), with an operating voltage of 200 keV, was used to examine the sample at higher
23 resolution. The final specimen was also characterized for elemental mapping using a JEOL 7000

FE scanning electron microscope (SEM) in STEM mode. The SEM-STEM scanning yields higher X-Ray intensities, enabling shorter scanning times and large scanned areas.

3. Results

The results from the SEM-STEM mapping are presented in Figure 2. A rectangular area that contains the Zn coating, interfacial layer, and the substrate was scanned (Figure 2a). In the mapped area, Zn is shown in blue and iron in red. In between, an Al-rich region can be observed, which is shown in green. The color codes of individual elements were superimposed in Figure 2a to show the structure of the interface at a relatively low magnification. The Al-rich layer, commonly referred to as the inhibition layer, has a stoichiometry of Fe_2Al_5 or $\text{Fe}_2\text{Al}_{5-x}\text{Zn}_x$ when some Al atoms are replaced by Zn. The inhibition layer appears to be continuous in nature over the interface. Another elemental mapping was performed in a thin section that encompasses the interface region to determine the distribution of alloying elements, e.g. Mn and Si. Figure 2b shows the distribution of Mn near the interface. A bright line along the interface can be resolved, indicating that the intensity of Mn is much higher at the interface than in other regions. Figure 2c shows the distribution of Si near the interface. In contrast to Mn, no observable intensity peak of Si can be seen.

The specimen was then examined under TEM at higher magnifications and resolution. High angle annular dark field (HAADF) imaging was performed at STEM mode to achieve better image contrast from the compositional difference of the phases (Figure 3a). In between the zinc coating and the steel substrate is the interface region which comprises the continuous inhibition layer (the dark region indicated by the arrows). Figure 3b shows the image of the inhibition layer at a higher magnification. The thickness of the inhibition layer was measured at ten different

1 locations by averaging the variation in the gray scale of the image. The average thickness of the
2 inhibition layer is about 93 ± 26 nm.

3 In the sub-surface region of the steel substrate adjacent to the inhibition layer, fine particles
4 with sizes about a few tens of nanometers can be observed (Figure 4a). These particles are
5 internal oxides. The internal oxide particles are distributed in a region about 150 nm below the
6 surface. The internal oxides were observed previously in high strength steels [7,11,12,13,14]. At
7 a higher magnification, right between the inhibition layer and the surface of the steel substrate is
8 another thin layer, which is evident by the different contrast, as shown in Figure 4b (indicated by
9 the pairs of arrows). This thin layer is the external oxide layer. In the HAADF imaging, the
10 external oxides layer appears to be continuous in nature. This is consistent with the EDS
11 mapping shown in Figure 2b.

12 The phases that are present at the interface region and the structure of the interface in the
13 galvanized DP steel are schematically summarized in Figure 5.

14 To determine the chemical composition of this thin layer, an EDS line scan was performed
15 starting from the zinc coating to the steel substrate. Figure 6 shows the result of the scan. The
16 intensity of Zn is high at the start but it begins to decrease as the scan progresses into the
17 inhibition layer, whereas the intensity of Al and Fe increases and levels out inside the inhibition
18 layer. A certain amount of Zn was detected in the inhibition layer as well. This could be an
19 indication of solid solution of Zn in Fe_2Al_5 , or the detection of Zn in the coating due to the large
20 excitation volume of the nano electron beam. Notably, following the sharp decrease of both Al
21 and Fe as the scanning approaches the substrate, an increase in Mn and O is registered between
22 the inhibition layer and the substrate. Clearly, the presence of the intensity peaks of Mn and O
23 indicates that Mn oxides was formed on the surface of the substrate during processing. Using the

similar measuring technique, the thickness of the Mn oxides layer was determined to be about 20 ± 6 nm.

To further resolve the structure of the interface, bright field imaging was also performed. Figure 7a shows both the internal oxide particles and the continuous external oxide film on the surface of the steel substrate. At a higher magnification (Figure 7b), grain boundaries can be observed inside the inhibition layer. These grains (or sub-grains) have an average grain size of approximately 5-10 nm. HRTEM was also performed and the lattice fringes observed are shown in figure 7c. Clearly, grain boundaries or sub-grain boundaries can be seen and the lattice fringes present different orientations.

Furthermore, the external manganese oxide is also crystalline as seen from the lattice fringes across the oxides. In order to determine the structure of the manganese oxide, diffraction patterns were obtained and indexed. A high resolution image is selected such that the lattice fringes across the manganese oxide layer are clearly visible, as illustrated in Figure 8a. A square box is drawn over our region of interest to create a diffraction pattern using Fast Fourier Transform (FFT) algorithm. The diffraction pattern obtained from FFT is shown in Figure 8b. The diffraction pattern was further processed in Digital Micrograph. The processed image, displayed in Figure 8c, is then indexed to reveal that the oxide is indeed manganese (II) oxide, which has a cubic structure. Similar observations were reported by Gong et al. [26,27]. In transformation induced plasticity (TRIP) steels, oxides at the surface of the substrate were reported to be rich in MnO and crystalline in nature.

4. Discussion

Our TEM work clearly revealed an almost continuous external MnO oxide film (~20 nm thick) on the surface of the DP steel, a layer of internal MnO oxide particles located about 100

1 nm below the surface, and a fully developed inhibition layer right on top of the external oxide
2 film. The transition from external to internal oxidation is dependent upon the dew point which is
3 a function of the partial pressure of water vapor in the H_2+N_2 mixture, i.e. the annealing
4 atmosphere. Increase in dew point results in an increased diffusion of oxygen into steel, causing
5 the formation of internal oxides [13,14]. On the other hand, lower hydrogen content in the
6 annealing atmosphere leads to a higher oxidation potential due to an increase in p_{H_2O}/p_{H_2} (i.e.
7 partial pressure of water vapor to partial pressure of hydrogen) ratio, thus yielding a transition of
8 oxidation from external to internal [7,8].

9 Although the presence of oxides on the steel surface could be detrimental to reactive wetting
10 [1,28,29], the TEM micrographs (Figures 3,4, and 6) indicate that a fully developed inhibition
11 layer can still grow on the oxide film. Prabhudev et al. [11] reported that nano-islands of oxides
12 present on the surface of the steel do not hinder the formation of the inhibition layer due to the
13 ability of Fe-Al interface layer to grow over the oxides. Parazanovic and Spiegel [10] suggested
14 that, oxides nucleate and grow as islands, instead of continuous layers, and do not deplete away
15 completely in the reducing annealing atmosphere. If the oxides nucleate as nano-islands on the
16 substrate grains that have different orientations, it is conceivable that the crystalline oxide grains
17 will have different orientations as well. Hence, when the oxide grains grow and meet, grain
18 boundaries or sub-grain boundaries will be produced. These grain boundaries act as short-circuit
19 paths for Fe to diffuse through the oxide film. Also, Mn oxides such as MnO and Mn_2SiO_4 have
20 been reported to be porous and have globular morphology [15,17] and this nature may not
21 significantly degrade the wettability of Zn. However, the phenomenon of overgrowth of the
22 inhibition layer over the oxide islands results in slowing down the reaction process. The study by
23 Frenznick et al. [30] reported that at same coverage of oxides over the substrate, the smaller

oxide islands had less detrimental effect to the reaction kinetics than the larger oxide islands. This is because the inhibition layer grows over the smaller islands faster than the larger ones.

Another possibility is that the seemingly continuous oxide film is actually discontinuous, as suggested by Sagl et al. [31]. As a result, surface areas free of oxides may be in direct contact with the liquid Zn, leading to the localized nucleation of the inhibition layer in these areas. The inhibition layer continue to grow over the oxide film. This seems against the TEM observations in this work. The growth of the inhibition layer appears to be rather uniform and local penetration of the inhibition layer through the oxide-free areas were hardly observed.

Aluminothermic reduction of Mn oxides by Al, proposed by Khondker et al. [7], is considered as the major reason for the formation of well-developed inhibition layer ($\text{Fe}_2\text{Al}_{5-x}\text{Zn}_x$) over MnO film [1,7,10,31]. Aluminothermic reduction helps the formation of inhibition layer. The Al in Zn bath attacks the oxides and dissolves some of the Mn into the zinc bath. The reduction of Mn oxides expose a larger surface area for Al to react with Fe [15, 31, 32]. Then the Fe in the substrate diffuses outwardly to come into reaction with the Al. A favorable location for the outwards diffusion of Fe could be the regions where the external oxide grains meet, i.e. grain boundaries of the oxide film.

5. Conclusions

FIB was used to prepare site-specific TEM specimens that contains the interface between the steel substrate and the Zn coating of a galvanized DP steel. TEM, STEM, and HRTEM were performed to characterize the interfacial structure. The morphology of the oxides and the inhibition layer were very well resolved. The following conclusions can be reached:

(1) External MnO oxide film was captured on the surface of the steel substrate. The oxide film appears to be continuous, and has a thickness about 20 nm. Internal oxide particles were

1 observed as well, and the particles are about few tens of nanometers and are located in a sub-
2 surface layer about 100 nm thick. However, no Si oxides were observed in this region. HRTEM
3 results shows that the oxide grains are crystalline.

4 (2) The Fe_2Al_5 or $\text{Fe}_2\text{Al}_{5-x}\text{Zn}_x$ inhibition layer was observed right on top of the external oxide
5 film. The inhibition layer appears to be continuous in nature. Sub-structures inside the inhibition
6 layer were resolved by HRTEM, which shows that grain boundaries or sub-grain boundaries
7 were present.

8 (3) The fully developed inhibition layer, despite the presence of a continuous Mn oxide film
9 on the surface of the steel substrate, may be attributed to diffusion of Fe through the porous MnO
10 film, the short-circuit diffusion paths between the oxide grains, or the aluminothermic reduction
11 of Mn oxides.

13 **Acknowledgements**

14 This work is supported by the International Zinc Association, under the contract ZCO-64.
15 Authors acknowledge the support from Center for Advanced Vehicular Systems, Mississippi
16 State University and Central Analytical Facility, University of Alabama. The authors also thank
17 POSCO for supplying steel specimens for this research.

19 **References:**

1 S. Alibeigi, R. Kavitha, R.J. Meguerian, J.R. McDermid, Reactive wetting of high Mn steels
during continuous hot-dip galvanizing, *Acta Mater.* 59 (2011) 3537–3549.

-
2. T. Kato, K. Nunome, K. Kaneko, H. Saka, Formation of the ζ phase at an interface between an Fe substrate and a molten 0.2 mass% Al–Zn during galvannealing, *Acta Mater.* 48 (2000) 2257–2262.
 - 3 A.R. Marder, The metallurgy of zinc-coated steel, *Prog. Mater. Sci.* 45 (2000) 191–271.
 - 4 B. Mintz, Hot dip galvanising of transformation induced plasticity and other intercritically annealed steels, *Int. Mater. Rev.* 46 (2001) 169–197.
 - 5 R. Bode, M. Meurer, T.W. Schaumann, W. Warnecke, Selection and use of coated advanced high-strength steels for automotive applications, *Rev. Métallurgie.* 101 (2004) 551–558.
 - 6 X.G. Zhang, *Corrosion and electrochemistry of zinc*, Plenum Press, New York, 1996.
 - 7 R. Khondker, A. Mertens, J.R. McDermid, Effect of annealing atmosphere on the galvanizing behavior of a dual-phase steel, *Mater. Sci. Eng. A.* 463 (2007) 157–165.
 - 8 I. Cvijović, I. Parezanović, M. Spiegel, Influence of H₂–N₂ atmosphere composition and annealing duration on the selective surface oxidation of low-carbon steels, *Corros. Sci.* 48 (2006) 980–993.
 - 9 G.M. Song, T. Vystavel, N. van der Pers, J.T.M. De Hosson, W.G. Sloof, Relation between microstructure and adhesion of hot dip galvanized zinc coatings on dual phase steel, *Acta Mater.* 60 (2012) 2973–2981.
 - 10 I. Parezanovic, M. Spiegel, *J. Corros. Sci. Engg.* 6 (2003) Conference Paper Number H032, Preprint 85.
 - 11 S. Prabhudev, S. Swaminathan, M. Rohwerder, Effect of oxides on the reaction kinetics during hot-dip galvanizing of high strength steels, *Corros. Sci.* 53 (2011) 2413–2418.
 - 12 H. Liu, F. Li, W. Shi, R. Liu, L. Li, Characterization of hot-dip galvanized coating on dual phase steels, *Surf. Coat. Technol.* 205 (2011) 3535–3539.

-
- 13 H. Liu, Y. He, S. Swaminathan, M. Rohwerder, L. Li, Effect of dew point on the surface selective oxidation and subsurface microstructure of TRIP-aided steel, *Surf. Coat. Technol.* 206 (2011) 1237–1243.
- 14 H. Liu, F. Li, W. Shi, S. Swaminathan, Y. He, M. Rohwerder, et al., Challenges in hot-dip galvanizing of high strength dual phase steel: Surface selective oxidation and mechanical property degradation, *Surf. Coat. Technol.* 206 (2012) 3428–3436.
- 15 M. Blumenau, M. Norden, F. Friedel, K. Peters, Reactive wetting during hot-dip galvanizing of high manganese alloyed steel, *Surf. Coat. Technol.* 205 (2011) 3319–3327.
- 16 K.-K. Wang, C.-W. Hsu, L. Chang, D. Gan, K.-C. Yang, Role of Al in Zn bath on the formation of the inhibition layer during hot-dip galvanizing for a 1.2Si–1.5Mn transformation-induced plasticity steel, *Appl. Surf. Sci.* 285 (2013) 458–468.
- 17 Y. Adachi, K. Kamei, Tem study of diffusional α -Fe/Zn interface (nano-scale-characterization of galvanized steel), *Acta Metall. Mater.* 43 (1995) 3189–3197.
- 18 K. Kuroda, M. Takahashi, T. Kato, H. Saka, S. Tsuji, Application of focused ion beam milling to cross-sectional TEM specimen preparation of industrial materials including heterointerfaces, *Thin Solid Films.* 319 (1998) 92–96.
- 19 T. Kato, M. Hong, K. Nunome, K. Sasaki, K. Kuroda, H. Saka, Cross-sectional TEM observation of multilayer structure of a galvanized steel, *Thin Solid Films.* 319 (1998) 132–139.
- 20 L.A. Giannuzzi, J.L. Drown, S.R. Brown, R.B. Irwin, F.A. Stevie, Applications of the FIB lift-out technique for TEM specimen preparation, *Microsc. Res. Tech.* 41 (1998) 285–290.
- 21 M.S. Kim, J.H. Kwak, J.S. Kim, Y.H. Liu, N. Gao, N.-Y. Tang, Galvanizability of Advanced High-Strength Steels 1180TRIP and 1180CP, *Metall. Mater. Trans. A.* 40 (2009) 1903–1910.

-
22. E.M. Bellhouse, J.R. McDermid, Analysis of the Fe–Zn interface of galvanized high Al–low Si TRIP steels, *Mater. Sci. Eng. A*. 491 (2008) 39–46.
23. R. Kavitha, J.R. McDermid, On the in-situ aluminothermic reduction of manganese oxides in continuous galvanizing baths, *Surf. Coat. Technol.* 212 (2012) 152–158.
24. K.-K. Wang, C.-W. Hsu, L. Chang, D. Gan, T.-R. Chen, K.-C. Yang, Study of Selective Oxidation Behavior of a 1.2Si-1.5Mn TRIP Steel during Intercritical Annealing, *J. Electrochem. Soc.* 159 (2012) C561–C570.
25. L. Cho, S.J. Lee, M.S. Kim, Y.H. Kim, B.C. De Cooman, Influence of Gas Atmosphere Dew Point on the Selective Oxidation and the Reactive Wetting During Hot Dip Galvanizing of CMnSi TRIP Steel, *Metall. Mater. Trans. A*. 44 (2013) 362–371.
26. Y.F. Gong, H.S. Kim, B.C. De Cooman, Formation of Surface and Subsurface Oxides during Ferritic, Intercritical and Austenitic Annealing of CMnSi TRIP Steel, *ISIJ Int.* 48 (2008) 1745–1751.
27. Y.F. Gong, H.S. Kim, B.C.D. Cooman, Internal Oxidation during Intercritical Annealing of CMnSi TRIP Steel, *ISIJ Int.* 49 (2009) 557–563.
- 28 I. Hertveldt, B.C.D. Cooman, S. Claessens, Influence of annealing conditions on the galvanizability and galvannealing properties of TiNb interstitial-free steels, strengthened with phosphorous and manganese, *Metall. Mater. Trans. A*. 31 (2000) 1225–1232.
- 29 G.M. Song, W.G. Sloof, T. Vystavel, J.T.M. de Hosson, Interface Microstructure and Adhesion of Zinc Coatings on TRIP Steels, *Mater. Sci. Forum.* 539-543 (2007) 1104–1109.
- 30 S. Frenznick, S. Swaminathan, M. Stratmann, M. Rohwerder, A novel approach to determine high temperature wettability and interfacial reactions in liquid metal/solid interface, *J. Mater. Sci.* 45 (2010) 2106–2111. doi:10.1007/s10853-009-4147-7.

31 R. Sagl, A. Jarosik, D. Stifter, G. Angeli, The role of surface oxides on annealed high-strength steels in hot-dip galvanizing, *Corros. Sci.* 70 (2013) 268–275.

32 E.M. Bellhouse, A.I.M. Mertens, J.R. McDermid, Development of the surface structure of TRIP steels prior to hot-dip galvanizing, *Mater. Sci. Eng. A.* 463 (2007) 147–156.

Figure 1. Fabrication of a galvanized dual-phase sample using focused ion beam (FIB). a) Digging trenches around the specimen. During sputtering EDS was performed to ensure that the interface region (indicated by the dashed line) was contained in the specimen. b) Lift-out of a 1 μm thin specimen by welding it to the tip of a tungsten needle. c) Cold welding the thin specimen to a copper grid by depositing platinum.

Figure 2. SEM EDS (Energy Dispersive Spectroscopy) elemental map across the interface of the Dual-Phase Galvanized steel. a) Red corresponds to iron, blue to zinc and green to aluminum. b) A segregation of manganese can be found at the surface of the steel substrate. c) No segregation of silicon was found at the steel surface.

Figure 3. The inhibition layer is captured in TEM using STEM mode with a High Angle Annular Dark Field (HAADF) detector. a) A low magnification image that encompasses the entire inhibition layer present in the fabricated specimen. b) A higher resolution image detailing the morphology of the inhibition layer, present in between the steel substrate and the zinc coating. The inhibition layer is approximately 93 nm in thickness.

Figure 4. TEM images in STEM mode. a) Internal oxides, indicated by the region in between the red dashed line and the external oxide layer, are present at the subsurface of the steel substrate. b) External oxides, pointed out by the red arrow markers, are present in between the steel substrate and the inhibition layer.

Figure 5 A schematic of the phases and the structure of the interfacial region of the galvanized DP steel.

Figure 6. EDS Line Scan result across the interface of Dual-Phase Galvanized Steel in STEM mode. Scan starts at the zinc coating and ends at the steel substrate region. The intensity for iron and aluminum stay constant across the inhibition layer. A spike in manganese and oxygen is observed as the inhibition layer ends, as evident by a drop in the intensity of aluminum.

Figure 7. a) A high resolution Bright Field (BF) TEM image of the interface illustrating the external and internal oxides. The external oxides are interconnected. b) A high resolution Bright Field (BF) TEM image of the inhibition layer and the external oxides. The inhibition layer comprises nanocrystalline grains.

Figure 7. c) A high resolution Bright Field (BF) TEM image illustrating the nanocrystalline inhibition layer, external oxides and the oxide/inhibition layer boundary. The inhibition layer contains multiple lattice fringes at different orientation that represents a nanocrystalline structure. The interface between the oxides and inhibition layer is pointed out by the arrows.

Figure 8. a) A high resolution TEM image which includes a manganese oxide particle present adjacent to the $\text{Fe}_2\text{Al}_5\text{Zn}_x$ inhibition layer. A square box is drawn on the oxide which contains lattice fringes to create a diffraction pattern using Fast Fourier Transform (FFT) algorithm.

Figure 8. b) A diffraction pattern obtained by using FFT of the manganese oxide region. Due to poor clarity of spots, further processing was performed. c) An indexed diffraction pattern providing evidence of manganese (II) oxides present at the surface of the steel substrate as external oxides.

Table 1. Chemical composition of the DP steel

C	Mn	Si	Al	Nb	Cr	Ca
0.0971	1.7500	0.1923	0.0408	0.0164	0.3304	0.0008