Synthesis and Structural Characterization of a Flexible Metal Organic Framework $\{[\text{Ni}(\text{dpbz})][\text{Ni}(\text{CN})_4]\}_n$, dpbz=1,4-bis(4-pyridyl)benzene) with an Unusual Ni-N Bond

Winnie Wong-Ng,^{*[1]} Jeffrey T. Culp^{[2][3]}, Yu-S. Chen,^[4] Jeffrey R. Deschamps,^[5] Anna Marti ^[2];

^[1] Materials Measurement Science Division, National Institute of Standards and Technology, Gaithersburg, MD 20899; ^[2] National Energy Technology Laboratory, Department of Energy, P.O. Box 10940, Pittsburgh, PA 15236; ^[3] AECOM, South Park, PA 15219; ^[4] ChemMatCARS, University of Chicago, Argonne, IL 60439; ^[5] Naval Research Laboratory, Washington DC 20375

Abstract

The chartreuse monoclinic Ni-dpbz ($\text{Ni}(\text{L})[\text{Ni}(\text{CN})_4]$, (L= 1,4-Bis(4-pyridyl)benzene, or dpbz) crystal assumes a pillared structure with layers defined by 2-D $\text{Ni}[\text{Ni}(\text{CN})_4]_n$ nets and dpbz ligands as pillars, linking between coordinated Ni sites. In addition to the hysteretic adsorption/desorption feature of Ni-dpbz, in half of the parallelepiped-shape space enclosed by the pillars and nets, an additional dpbz ligand was found to link between the open ends of two four-fold Ni sites. This arrangement results in an unusual 5-fold pseudo square-pyramid environment for Ni and a significantly long Ni-N distance of 2.369(4) Å. The presence of disordered dimethyl sulfoxide (DMSO) solvent molecules give rise to the formula of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4] \cdot \frac{1}{2}\text{dpbz} \cdot 0.44\text{DMSO}$. Sorption isotherms showed flexible behavior during the adsorption and desorption of CO_2 .

Keywords: Carbon dioxide capture; flexible porous MOF; soft porous crystals, Ni(1,4-Bis(4-pyridyl)benzene)[Ni(CN)₄]; synchrotron crystal structure; sorption isotherms, 5-coordinate nickel complex

*Contacting author: Winnie.wong-ng@nist.gov, Tel:301-975-5791; FAX: 301-975-5334

Introduction

Global warming resulting from greenhouse gas emissions continues to receive widespread attention. The CO₂ concentration in the atmosphere has increased substantially since the preindustrial revolution period, from about 300 ppm to nearly 400 ppm as of today [1,2]. Among the greenhouse gases, CO₂ contributes more than 60% to climate change [3]. To mitigate global warming as a major result of fossil fuel burning, CO₂ capture and storage (CCS) technology is critical [4]. Solid adsorption processes have been studied extensively in recent years as an effective and economical way for CCS. Various types of porous solid sorbent materials, including metal organic frameworks (MOF) and flexible MOF have been investigated worldwide [5-24]. Flexible MOF possess both highly ordered network and structural transformability [24]

One particular advantage of MOFs is their modular nature which allows the combination of organic and inorganic complex building blocks to be assembled into tailored porous materials with a wide range of pore size, surface area and pore functionality. One approach to modular MOF synthesis is the pillared layer structure where extended 2-D coordination networks are stacked through bridging pillar ligands to form 3D structures [25]. One example that utilizes this strategy is the Hofmann-type $[M_a(L)M_b(CN)_4]_n$ compounds [26], where M_a is an octahedrally coordinated transition metal ion, L is a bridging ligand, and M_b a square planar group 10 metal ion (i.e. Ni²⁺, Pd²⁺, Pt²⁺). Iwamoto applied this synthetic approach to form a number of clathrates using α,ω -diamines as pillaring ligands [27]. Several other derivatives with $M_a = Fe^{2+}$ have also been studied for their combination of host-guest chemistry and spin crossover behaviour [28-31]. This synthetic strategy was further expanded upon by Culp who included several bipyridyl derivatives as pillaring linkers forming a family of ≈ 40 different porous coordination compounds collectively called pillared cyanonickelates, or PICNICs [7].

A number of PICNICs show flexible behavior during the adsorption and desorption of guest molecules such as CO₂ [7, 8]. Flexible PICNICs and other soft porous crystals [32] change their structures in response to the adsorption and desorption of guests [33-39]. This transition between low porosity and high porosity structural phases (often referred to as a gating

behavior) is highly dependent on pressure, temperature and the nature of the guest. The nature of the gating behavior has led many to pursue flexible materials as selective sorbents [11, 40-43].

Experimental

1. Materials and Synthesis

Due to the challenge of growing suitable single crystals, few PICNIC crystal structures have been reported. Recently, an improved crystallization technique using NH_3 as a blocking ligand was developed for the PICNIC materials which led to the crystal structure of the flexible $[\text{Ni}(\text{bpene})\text{Ni}(\text{CN})_4]_n$ being determined [44, 45]. Herein, we report the structure of a second soft porous crystal from the PICNIC series synthesized using the same crystallization strategy with 1,4-di-(4-pyridyl)-benzene (dpbz) as the pillar ligand. In addition to its structural flexibility, what makes this material particularly interesting is the presence of a highly unusual coordination bond between the N atom of the guest dpbz ligands and the usually square-planar $\text{Ni}(\text{CN})_4$ complex to form a rarely observed 5-fold coordination square-pyramidal environment around Ni.

1.1. Synthesis of crystalline $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4] \cdot (\text{dpbz})_{0.44}(\text{DMSO})_{0.44}$ (dpbz = 1,4-bis(4-pyridyl)benzene and DMSO = dimethyl sulfoxide)

The synthesis is similar to that used to prepare $\text{Ni}(\text{bpene})[\text{Ni}(\text{CN})_4]$ which involves slow outgassing of NH_3 blocking ligands from the solution to initiate crystallization [44]. The ligand 1,4-bis(4-pyridyl)benzene (dpbz) was prepared from the Suzuki coupling of pyridine-4-boronic acid and 1,4-dibromobenzene as previously described [7]. The schematic of dpbz is given in Fig. 1.

At room temperature, a 25 mL 19/22 flask was charged with 0.25 mmol polymeric nickel cyanide hydrate $\text{Ni}[\text{Ni}(\text{CN})_4]_n(\text{H}_2\text{O})_3$ and made to dissolve through the sequential addition of 2.5 mL H_2O , 2.5 mL of reagent concentrated ammonium hydroxide solution, and 2.5 mL DMSO with stirring. (Caution: do not mix concentrated ammonium hydroxide and DMSO

directly as rapid outgassing of NH_3 can occur.) A solution of 0.68 mmol (0.158 g) dpbz in 12.5 mL warm DMSO was then added to the resulting solution. A six inch air-cooled condenser was added and the flask was transferred to an oil bath preheated to 70°C. The temperature of the oil bath was ramped to 90 °C over approximately 30 minutes after which time the stirring was stopped and the reaction left at 90°C undisturbed for three days. The dissolved NH_3 bubbled out of the solution rapidly during the initial hour, then slowed significantly while a crystalline product formed over the next two days. After completion, the reaction mixture was cooled to room temperature and the resulting crystals were isolated by first decanting off any suspended fine particles suspension of impurities while being careful to leave the crystals wetted within the reaction mixture. The impurities were removed by filtration and the filtrate returned to the flask. The pipetting and filtration cycle was repeated until the powdered impurities were removed. The chartreuse crystals were kept stored in the cleaned reaction mixture in a capped vial at room temperature until the X-ray diffraction measurements were taken.

After the above synthesis, the product was filtered and washed with 10 mL of methanol. The solid was air dried and ~ 75 mg then transferred to a Teflon lined PARR reactor and ~ 12 mL of toluene was added. The sealed reactor was heated at 150°C for > 48 hours. After cooling to room temperature, the solvent was removed by pipette and the solid air dried.

2. CO_2 adsorption-desorption isotherm measurements

Gravimetric CO_2 adsorption measurements were conducted on a Hiden IGA microbalance. The toluene extracted sample (~25 mg) was activated by heating under vacuum at 150°C until the sample weight stabilized. Isotherms were then measured under flowing CO_2 regulated by a mass flow controller. Equilibrium was determined at each pressure step using an internal fitting algorithm in the instrument control software. Buoyance corrections were then applied to the final equilibrium weights using known densities of all components in the sample and counter weight chambers from gas densities calculated using REFPROP [45-46].

Thermogravimetric Analysis (TGA) was conducted in platinum sample pans using a Mettler

TGA/DSC StarE system in air with a heating ramp of 15°C/min. Powder x-ray diffraction was measured using a PANalytical X'Pert Pro MPD powder diffractometer operating at 40 kV and 40 mA by using Cu-K α radiation. Fourier Transform-Infrared (FT-IR) spectra were recorded on KBr pellets.

3. Synchrotron X-ray Diffraction Experiment:

The structure of the Ni-dpbz crystals was determined using the ChemMatCARS microcrystallography facility at the Advanced Photon Source of Argonne National Laboratory. The small crystal that we used (0.015 x 0.015 x 0.005 mm³) has a thin-plate morphology. The crystal was mounted on the tip of a glass fiber with paratone oil and cooled down to 100 K with an Oxford Cryojet. A X-ray diffraction experiment was performed with a Bruker D8 diffractometer in the vertical mount with a APEX II CCD detector using double crystals technique with Si(111) monochromator at 30 keV ($\lambda = 0.4428 \text{ \AA}$) at sector15 (ChemMatCARS), Advanced Photon Sources (APS). For the structure determination data, 1440 frames (0.5° φ scans) were collected at ω values of -180° and -150°. Data were processed with APEX2 suite software [47] for cell refinement and reduction. The structure was solved by the direct method and refined on F^2 (SHELXTL[48]. Non-hydrogen atoms were refined with anisotropic displacement parameters, and hydrogen atoms on carbons were placed in idealized positions (C-H = 0.95 $\text{\AA}$).

RESULTS AND DISCUSSION

Structural characterization

The structure of Ni-dpbz was determined to be monoclinic, space group $P2_1/c$, $a=6.7883(3)\text{\AA}$, $b=14.4840(7)\text{\AA}$, $c=28.9167(13)\text{\AA}$, $\beta=93.2950(10)^\circ$, $V=2838.4(2) \text{ \AA}^3$, $Z=4$, $D_c=1.51 \text{ g cm}^{-3}$. Figure 2 shows the basic unit of the structure including the captured DMSO solvent molecule. Supplementary Fig. S1 gives the atom labeling scheme. Supplementary Table S1 gives the refinement results and crystallographic data for Ni-dpbz. Table 1 gives the atomic coordinates and displacement parameters for the non-hydrogen atoms, and Table 2 gives the selected bond distances. Table S2 gives the anisotropic displacement factors for the

non-hydrogen atoms.

The framework structure of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4]$ is related to the general $\text{Ni}(\text{L})[\text{Ni}(\text{CN})_4]$ 3-D Hofmann motif as both contain neutral 2-D polymeric layers formed from Ni^{2+} cations linked via N-coordination to $[\text{Ni}(\text{CN})_4]^{2-}$ anions. The Ni1-N and Ni2-C bond distances in the 2-D sheets of Ni-dpbz were found to be within the expected range. The mean Ni-C (1.866 Å) and C≡N (1.156 Å) bond lengths agree with the values reported for other tetracyanonickelate salts [49-51].

The 2-D polymeric sheets are connected through Ni-(dpbz)-Ni bridging interactions. In all previously known Hofmann structures, the pillar ligand L only coordinated to the octahedral M_a site with the $M_b(\text{CN})_4$ complex remaining square planar. The absence of pillar ligand coordination to the $M_b(\text{CN})_4$ site typically leads to the formation of empty voids of parallelepiped shapes which provide pockets that are effective for capturing guest molecules [7,8, 28, 30, 31, 44, 52]. Because of this well-known structural motif, it was interesting to discover that the structure of Ni-dpbz is different from the usual Hofmann compounds. The salient structural feature of the Ni-dpbz material is the presence of additional dpbz ligands that link between two typically 4-fold $\text{Ni}(\text{CN})_4$ sites. These “extra” pillar ligands occupy a fraction of the traditional Hofmann void space and in this sense behave like coordinated guest molecules. This arrangement is apparent in Fig. 3 which shows the structure viewing down the crystallographic axis *b*. This angle provides a clear view of how the two different dpbz ligands coordinate to the Ni ions in opposing 2-D layers. One arrangement is the expected pillaring interaction of parallel dpbz ligands connecting the Ni1 sites between the two $[\text{Ni}_2(\text{CN})_4]_n$ layers leading to the formation of the familiar 6-fold Ni1-N configuration. However, there is also an unexpected dpbz chain connecting the two Ni2 sites via the N atoms of the pyridyl rings, giving rise to an unusual long N...Ni2 distance of 2.369(4) Å. As a result, Ni2 has an unusual 5-fold square pyramid environment. In Fig. 4, an alternate view of the structure down the crystallographic axis ‘*a*’ with the 2-D layers united by the dpbz ligands is illustrated. The entrapped solvent DMSO molecules are also shown. Figure 5 gives the same view as that of Fig. 4 but also illustrates the 5- and 6-fold polyhedral coordination

around Ni2 and Ni1, respectively. Figure 6 depicts the 2-D Ni(CN)₄ square grid network. The Ni-N distances (range from 2.061(4) Å to 2.113 (4) Å) are substantially longer than the Ni-C distances (1.860(4) Å to 1.869(5) Å), which also conform to the literature values [49, 53, 54]. The 6-coordination Ni are of high spin configuration because nitrogen is acting as a weak-field ligand.

Additional features of the Ni-dpbz structure include the zig-zag manner of the chains that make up the 2-D Ni[Ni(CN)₄] layers (for example, deviations of bond angles from 180° are observed in the followings: Ni1-N-C angles range from 154.8(3)° to 162.0(3)°, and Ni2-C-N angles range from 172.2(4)° to 176.6(4)°). The configuration of the long dpbz ligand chain is also of interest, namely, the three rings (a benzene ring flanked by two pyridine rings) are not coplanar to avoid steric hindrance. The dihedral angles between the benzene and the pyridine rings are about the same, namely, 30.58(3)° and 30.36(4)°.

Though rare, compounds with weak Ni---H bonding and Ni- π intermolecular interactions involving the square planar Ni center of the [Ni(CN)₄]²⁻ complex have been recently reported by Büyükgüngör et al. [55-57]. To our knowledge, however, Ni-dpbz is the first example to show a Ni-N bonding interaction with the [Ni(CN)₄]²⁻ complex. The N---Ni(CN)₄ bond in Ni-dpbz is a weakly bonded ligand that may provide additional stabilization to the open framework structure. It is interesting to compare the host guest behavior of Ni-dpbz with a very similar Hofmann structure, Ni(1,2-bis(4-pyridyl)ethylene)[Ni(CN)₄] abbreviated as Ni-bpene, shown in Fig. 7 [44]. Both compounds crystallize with 0.44 equivalents of guest pillar ligand to give nominal formulas of Ni(L)[Ni(CN)₄](L)_{0.44} (solvents). However, in the Ni-bpene material, the long molecular axis of the guest bpene ligand is oriented parallel to the [Ni₂(CN)₄]_n sheet structure and does not participate in any bonding interaction with the Ni(CN)₄ complex. Since both the bpene and dpbz ligands are expected to have very similar Lewis basicity, the driving force for the interaction of the dpbz ligand with Ni(CN)₄ must be the result of a complex array of host-guest interactions and molecular recognition. For example, the orientation of the guest dpbz ligand could be due to a pi-stacking interaction with the dpbz pillar ligands (in Figs 3, 4 and 5, the pyridyl rings appear to stack upon each

other), the separation distance between these rings ($\approx 3.62 \text{ \AA}$) although precludes strong pi-orbital interactions, however, possible weak interactions may exist. A qualitative comparison of the strength of the guest ligand binding between the bpene and dpbz structures is evident in the effort needed to extract the guest ligand from the pore structure. The more loosely bound bpene guests in the $\text{Ni}(\text{bpene})[\text{Ni}(\text{CN})_4](\text{bpene})_{0.44}$ material can be removed in refluxing toluene (111°C) in less than 24 hours, whereas removal of the dpbz guests in the $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4](\text{dpbz})_{0.44}$ structure with toluene required solvothermal treatment in a Parr reactor at 150°C for 48 hours.

TGA and FTIR Studies

Figures 8 (a) and (b) give the TGA scans of Ni-dpbz as synthesized and Ni-dpbz after toluene extraction at 150°C in PARR reactor for 48 hours, respectively. The formula weight of the solvent-free framework can be calculated from the ratio of the residual mass of NiO to the mass of the framework where one mole of framework yields 2 moles of NiO. From this calculation, the bulk “as synthesized” material has a calculated FW of 602 g/mol which equates to a formula of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4](\text{dpbz})_{0.6}$, in reasonable agreement to the formula of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4](\text{dpbz})_{0.44}$ determined from crystallography. After extraction with toluene, the calculated formula weight of the empty framework is 444.6 g/mol, in agreement with a formula of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4]$ (FW = 453.7 g/mol) indicating effective removal of the excess dpbz guests.

FT-IR spectra of the $\nu(\text{CN})$ region taken as KBr pellets for a crystalline sample of Ni-dpbz during various stages of guest loading is shown in Fig. 9. The blue trace is the spectrum of the sample as initially synthesized with DMSO and dpbz guests. The red trace is for same sample after extraction with toluene in a PARR reactor at 150°C for 48 hours. The green trace is the spectrum after CO_2 isotherms were measured on the evacuated sample. Peak positions (cm^{-1}) (blue) 2167 shoulder, 2146; (red) 2167, 2150; (green) 2174, 2148. The $\nu(\text{CN})$ absorbance bands are shifted to higher wavenumber in relation to $\text{Na}_2[\text{Ni}(\text{CN})_4]$ (2132, 2128) as reported by McCullough [58]. The shift of $\nu(\text{CN})$ to high wavenumber is typical for bridging cyanides [59] and the values are in the range typically observed in Hofmann

compounds [60-66]. The higher wavenumber band is typically assigned to $\nu(\text{CN})$ E_u band and the additional lower energy peak assigned to hot band when observed [61-63, 65]. Removal of the guest dpbz ligand which is weakly coordinated to the $[\text{Ni}(\text{CN})_4]$ complex by extraction with toluene results in a significant change to the CN stretching region with a prominent split developing in the band. It is unclear at this point if the change is the result of an electronic or kinematic effect. The band changes little between the toluene loaded and evacuated sample.

Adsorption/Desorption Studies

A previous study involving a polycrystalline sample of Ni-dpbz prepared using a heterogeneous intercalation method showed adsorption and desorption behavior for CO_2 characteristic of a flexible MOF.⁶ The same material prepared by the crystallization technique described above followed by an activation procedure also showed flexible behavior during the adsorption and desorption of CO_2 . The CO_2 isotherms measured at 0°C and 10°C for the two materials are shown in Fig. 10. The threshold pressure (P_{th}) (or gating pressure) associated with the pore opening transition in the two materials are similar; however the slopes of the isotherms after the transition pressure and saturation loadings are different for the two materials. Similar variations in adsorption behavior have been observed in other flexible MOFs as the respective particle sizes of the materials was varied over the micro- to mesoscale regime [67, 68]. A reasonable hypothesis is that a similar mechanism is operating within the two Ni-dpbz samples where the more crystalline sample with a larger particle size shows a structure transition over a narrower pressure range due to a lower energy barrier for the structure change. A higher energy barrier for the structure transition in the powder sample is also evidenced by the persistence of a low angle peak in the x-ray diffraction pattern even after all guests have been removed as shown in Fig. 11. This peak is associated with the interlayer distance of the expanded structure (as shown by the toluene loaded pattern in Fig. 11) and is nearly absent in the evacuated crystalline sample. The presence of some open domains in the evacuated powder sample is also indicated by the higher initial uptake of CO_2 in the adsorption isotherm compared to the crystalline sample. The presence of a small fraction of these mesoscale “open pore” domains in the powder sample may be indicative of shape-memory nanopores similar to those recently described by Sakata [67] in mesoscale

particles of the flexible coordination network $[\text{Cu}_2(\text{bdc})_2(\text{bpy})]_n$. A similar contrast in isotherm shape was also observed between crystalline and powder samples of Ni-bpene [44]. More studies involving a more precise control of crystallize sizes will be needed to validate the proposed mechanism.

Conclusion

In conclusion, the dpbz ligand forms a weak bond to the four-fold coordinated Ni of the 2-D $\text{Ni}(\text{CN})_4$ layer, resulting in an unusual five-fold square-pyramidal coordination. It occurs as a ‘trapped ligand’, and the weak bond to the framework molecule may enhance the stability of the structure. We plan to continue to understand the bonding environment around the two Ni sites using electron density mapping technique in the future. Further time resolved, *in-situ* diffraction technique will be planned to study the sorption process of CO_2 .

Acknowledgements

This technical effort was performed in support of the National Energy Technology’s ongoing research in CO_2 capture under the RES contract DE-FE0004000. The authors gratefully acknowledge ChemMatCARS Sector 15 which is principally supported by the National Science Foundation/Department of Energy under grant number NSF/CHE-0822838. Use of

the Advanced Photon Source was supported by the U. S. Department of Energy, Office of Science, Office of Basic Energy Sciences, under Contract No. DE-AC02-06CH11357.

Figure Legends

Fig. 1. Structure of the pillar ligand 1,4-bis-(4-pyridyl)benzene, dpbz

Fig. 2. A basic motif of the $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4]$ molecules (including solvent DMSO), with partial labeling scheme provided (green – Ni, blue – N, grey – C, yellow-S, red-O). Full labeling scheme is included as Supporting Information Fig. S2.

Fig. 3. A projection view of the structure down the crystallographic *b*-axis showing the parallel dpbz pillared ligands as well as the cross-linking of the ligand molecule connecting the Ni2 sites via longer Ni-N distance (green – Ni, blue – N, grey – C).

Fig. 4. Alternative framework view of the structure of $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4]$ down the crystallographic axis '*a*' showing the 2D nets connected by the dpbz ligands. The solvent molecules DMSO are also shown (green – Ni, blue – N, grey – C, yellow-S, and red-O).

Fig. 5. Polyhedral view of the octahedral and square-pyramidal coordination environments of Ni1 (blue) and Ni2 (pink), respectively, in $\text{Ni}(\text{dpbz})[\text{Ni}(\text{CN})_4]$.

Fig. 6. 2-D square grid network formed by tetracyanonickelate molecules and the bridging dpbz ligands (green – Ni, blue – N, grey – C).

Fig. 7. Polyhedral view of the octahedral and square-planar coordination of the two different Ni sites in $\text{Ni}(\text{bpene})[\text{Ni}(\text{CN})_4]$ [44].

Fig. 8. TGA scans of (left) Ni-dpbz as synthesized and (right) Ni-dpbz after toluene extraction at 150°C in PARR reactor for 48 hours.

Fig. 9. FT-IR spectra of the $\nu(\text{CN})$ region taken as KBr pellets for a crystalline sample of Ni-dpbz during

various stages of guest loading. The blue trace is the spectrum of the sample as initially synthesized with DMSO and dpbz guests. The red trace is for same sample after extraction with toluene in a PARR reactor at 150°C for 48 hours. The green trace is the spectrum after CO₂ isotherms were measured on the evacuated sample.

Fig. 10. Comparing CO₂ adsorption (solid symbols) and desorption (open symbols) isotherms at 0°C (left) and 10°C (right) for those previously reported for a powder sample [7] of Ni-dpbz (black) and a crystalline sample of Ni-dpbz (red) prepared as described above.

Fig. 11. Comparing normalized x-ray powder diffraction patterns for the toluene extracted (black-bottom) and guest-free crystalline samples (red-middle) in the current report to one reported previously [7] for the guest-free powder sample of Ni-dpbz (blue-top) which was prepared using a heterogeneous intercalation reaction. The evacuated powder sample has a residual low angle peak indicating a fraction of the material remains in the open pore phase after evacuation. This peak is nearly absent in the evacuated crystalline sample.

References:

- [1] D.M. Etheridge, L.P. Steele, R.L. Langenfelds, R.J. Francey, J.M. Barnola, V.I. Morgan, *J. Geophys. Res. Atmos.*, 101 (1996) 4115.
- [2] R.H. Gammon, E.T. Sundquist, P.J. Fraser, *Atmospheric Carbon Dioxide and the Global Carbon Cycle*; Trabalka, J. R., Ed.; DOE/ER-239 U.S. Department of Energy: Washington, D.C., (1985) 25.
- [3] J. Albo, P. Luis, A. Irabien, *Ind. Eng. Chem. Res.* 49 (2010) 11045.
- [4] Espinal, L., Poster, D.L., Wong-Ng, W., Allen, A.J., Green, M., *Environmental Science and Technol.* 47, (2013) 11960-11975 .
- [5] R. Chen, J. Yao, Q. Gu, S. Smeets, C. Baerlocher, H. Gu, D. Zhu, W. Morris, O.M. Yaghi, H. Wang, *Chem. Commun.* 49 (2013) 9500
- [6] S.S.Y. Chui, S.M.F. Lo, J.P.H. Charmant, A.G. Orpen, I.D. Williams, *Science* 283 (1999) 1148.
- [7] J.T. Culp, C. Madden, K. Kauffman, F. Shi, C. Matranga, *Inorg. Chem.* 52 (2013) 4205-16.
- [8] J.T. Culp, M.R. Smith, E.; Bittner, B. Bockrath, *J. Am. Chem. Soc.* 130 (2008) 12427.
- [9] H. Furukawa, K.E. Cordova, M. O'Keeffe, O.M. Yaghi, *Science* 341 (2013) 974.
- [10] W.-Y. Gao, M. Chrzanowski, S. Ma, *Chem. Soc. Rev.* 43 (2014) 5841.
- [11] K.L. Kauffman, J.T. Culp, A.J. Allen, L. Espinal, W. Wong-Ng, T.D. Brown, A. Goodman, M.P. Bernardo, R.J. Panoost, D. Chirdon, C. Matranga, *Angew. Chem. Int. Ed.* 50 (2011) 10888.
- [12] V. Krungleviciute, K. Lask, L. Heroux, A.D. Migone, J.Y. Lee, J. Li, A. Skoulidas, *Langmuir* 23 (2007) 3106.
- [13] J. Lee, J. Li, J. Jagiello, *J. Solid State Chem.* 178 (2005) 2527.
- [14] A.I. Skoulidas, *J. Am. Chem. Soc.* 126 (2004) 1356.
- [15] Q.M. Wang, D.M. Shen, M. Bulow, M.L. Lau, S.G. Deng, F.R. Fitch, N.O. Lemcoff, *Microporous Mesoporous Mater.* 55 (2002) 217.

- [16] W. Wong-Ng, J.A. Kaduk, L. Espinal, M.R. Suchomel, A.J. Allen, H. Wu, *Powd. Diffr.* **26** (2011) 234.
- [17] W. Wong-Ng, J.A. Kaduk, Q. Huang, L. Espinal, L. Li, J.W. Burrell, *Microporous and Mesoporous Mater.* **172** (2013) 95.
- [18] W. Wong-Ng, J.A. Kaduk, H. Wu, M. Suchomel. *Powd. Diffr.* **27** (2012) 256.
- [19] Jun Zhao, Yenan Wang, Wenwen Dong, Yapan Wu, Dongsheng Li, Bin Liu and Qichun Zhang, *Chem. Commun.*, **51**(2015) 9479.
- [20] Hai-Hua Wang, Li-Na Jia, Lei Hou, Wen-juan Shi, Zhonghua Zhu and Yao-Yu Wang, *Inorg. Chem.* **54** (2015) 1841.
- [21] Li-Yun Du, Wen-Juan Shi, Lei Hou, Yao-Yu Wang, Qi-Zhen Shi, and Zhonghua Zhu, *Inorg. Chem.* **52** (2013) 8091.
- [22] Dong-Sheng Li, Jun Zhao, Ya-Pan Wu, Bin Liu, Liang Bai, Kun Zou, and Miao Du, *Inorg. Chem.* **52** (2013) 8091.
- [23] Dong-Sheng Li, Ya-Pan Wu, Jun Zhao, Jian Zhang, Jack Y. Lu, *Coord. Chem. Rev.* **261** (2014) 1.
- [24] A. Schneemann, V. Bon, I. Schwedler, I. Senkovska, S. Kaskel and R. A. Fischer, *Chem. Soc. Rev.* **43**, (2014), 6062-6096
- [25] S. Kitagawa, R. Kitaura, *Comments Inorg. Chem.* **23** (2002), 101.
- [26] K.A. Hofmann, F. Kuspert, *Z. Anorg. Allgem. Chem.* **15** (1897), 204.
- [27] T. Iwamoto, *J. Inclusion Phenom. Mol. Recognit. Chem.* **24** (1996) 61.
- [28] G. Agusti, S. Cobo, A.B. Gaspar, G. Molnar, N.O. Moussa, P.A. Szilagyi, V. Palfi, C. Vieu, M.C. Munoz, J.A. Real, A. Bousseksou, *Chem. Mater.* **20** (2008), 6721.
- [29] J.T. Culp, D.-L.; Chen, J. Liu, D. Chirdon, K. Kauffman, A. Goodman, J.K. Johnson, *Eur. J. Inorg. Chem.* (2013) 511.
- [30] V. Niel, J.M. Martinez-Agudo, M.C. Munoz, A.B. Gaspar, J.A. Real, *Inorg. Chem.* **40** (2001) 3838.

- [31] P.D. Southon, L. Liu, E.A. Fellows, D.J. Price, G.J. Halder, K.W. Chapman, B. Moubaraki, K.S. Murray, J.-F. Letard, C.J. Kepert, *J. Am. Chem. Soc.* **131** (2009) 10998-11009.
- [32] S. Horike, S. Shimomura, S. Kitagawa, *Nature Chem.* **1** (2009), 695.
- [33] S. Bureekaew, S. Shimomura, S. Kitagawa, *Sci. Technol. Adv. Mater.* (2008), 9.
- [34] X. Chen, H. Zhou, Y.-Y. Chen, A.-H. Yuan, *Crystengcomm* **13** (2011), 5666.
- [35] C. Gao, S. Liu, L. Xie, Y. Ren, J. Cao, C. Sun, *Crystengcomm* **9** (2007), 545-547.
- [36] R. Kitaura, K. Fujimoto, S. Noro, M. Kondo, S. Kitagawa, *Angew. Chem. Int. Ed.* **41** (2002), 133.
- [37] T.K. Maji, K. Uemura, H.C. Chang, R. Matsuda, S. Kitagawa, *Angew. Chem. Int. Ed.* **43** (2004), 3269.
- [38] P. Song, B. Liu, Y. Li, J. Yang, Z. Wang, X. Li, *Crystengcomm* **14** (2012), 2296-2301.
- [39] X.-F. Wang, Y. Wang, Y.-B. Zhang, W. Xue, J.-P. Zhang, X.-M. Chen, *Chem. Commun.* **48** (2012), 133-135.
- [40] F.-X. Coudert, M. Jeffroy, A.H. Fuchs, A. Boutin, C. Mellot-Draznieks, *J. Am. Chem. Soc.* **130** (2008), 14294.
- [41] V. Finsy, L. Ma, L. Alaerts, D.E. De Vos, G.V. Baron, J.F.M. Denayer, *Microporous Mesoporous Mater.* **120** (2009), 221.
- [42] L. Hamon, P.L. Llewellyn, T. Devic, A. Ghoufi, G. Clet, V. Guillerm, G.D. Pirngruber, G. Maurin, C. Serre, G. Driver, W. van Beek, E. Jolimaître, A. Vimont, M. Daturi, G. Ferey, *J. Am. Chem. Soc.* **131** (2009), 17490.
- [43] E. Stavitski, E.A. Pidko, S. Couck, T. Remy, E.J.M. Hensen, B.M. Weckhuysen, J. Denayer, J. Gascon, F. Kapteijn, *Langmuir* **27** (2011), 3970.
- [44] W. Wong-Ng, J.T. Culp, J. Y.S. Chen, P. Zavalij, L. Espinal, D.W. Siderius, A.J. Allen, S. Scheins, C. Matranga, *CrystEngComm* **15** (2013), 4684.
- [45] E.W. Lemmon, M.L. Huber, and M.O. McLinden, NIST Standard Reference Database 23: Reference Fluid Thermodynamic and Transport Properties-REFPROP, Version 9.1, National Institute of Standards and Technology, Standard Reference Data Program. 2013, Gaithersburg, MD.

- [46]R. Span, and W. Wagner, J. Phys. Chem. Ref. Data, **25** (1996) 1509.
- [47]APEX2 (2009.11-0). Program for Bruker CCD X-ray Diffractometer control 2009, Bruker AXS Inc: Madison, WI.
- [48]G.M. Sheldrick, *SHELXTL, version 6.14*. Program for solution and refinement of crystal structures 2000: Universität Göttingen, Germany.
- [49]J. Cernak, K.A. Abboud, Acta Crystallogr. **56** (2000), 783.
- [50] J. Cernak, J. Lipkowski, Monatsh. Chem. **130** (1999), 1195.
- [51] J. Cernak, M. Orendac, I. Potocnak, J. Chomic, A. Orendacova, J. Skorsepa, A. Feher, Coord. Chem. Rev. **224** (2002), 51-56.
- [52]J.T. Culp, S. Natesakhawat, M.R. Smith, E. Bittner, C. Matranga, B. Bockrath, J. Phys. Chem. C **112** (2008), 7079.
- [53]W.F. Yeung, H.K. Kwong, T.C. Lau, S. Gao, L. Szeto, W.T. Wong, Polyhedron **25** (2006), 1256.
- [54]H. Yuge, T. Iwamoto, J. Chem. Soc. Dalton Trans. (1994), 1237.
- [55]G.S. Kuerkcueoglu, O.Z. Yesilel, I. Kavlak, S. Kurtaran, O. Bueyuekguengoer, J. Inorg. Organomet. Polym. Mater. **19** (2009), 314.
- [56]G.S. Kurkcuglu, O.Z. Yesilel, I. Cayli, O. Buyukgungor, J. Mol. Struct. **994** (2011), 39.
- [57]G.S. Kurkcuglu, O.Z. Yesilel, I. Kavlak, O. Buyukgungor, Struct. Chem. **19** (2008), 879-888.
- [58]R.L. McCullough, L.H. Jones, and G.A. Crosby, Spectrochim. Acta, **16** (1960) 929.
- [59]S.Z. Zhan, D. Guo, X.Y. Zhang, C.X. Du, Y. Zhu, R.N. Yang, Inorg. Chim. Acta, **298** (2000) 57-62.
- [60]S. Akyüz, T. Akyuz, and J.E.D. Davies, J. Inclusion Phenom. Molecul. Recognit. Chem., **26** (1996) 111.
- [61]S. Akyüz, A.B. Dempster, and R.L. Morehous, Spectrochim. Acta, **A30** (1974) 1989.
- [62]Z. Kartal, J. Molecul. Struct., **938** (2009) 70.

- [63] Gábor Molnár, Virginie Niel, Ana B. Gaspar, José-A. Real, Antoine Zwick, Azzedine Bousseksou, and John J. McGarvey, *J. Phys. Chem. B*, **106** (2002) 9701.
- [64] C. Parlak, O. Alver, and M. Senyel, *J. Molecul. Struct.*, **919** (2009) 41.
- [65] M. Senyel, M.T. Aytekin, and Z. Kantarci, *J. Inclusion Phenom. Macrocyc. Chem.* **39** (2001) 169.
- [66] A. Sungur, S. Akyuz, S. and J.E.D. Davies, *J. Inclus. Phenom.*, **5** (1987) 491.
- [67] Y. Sakata, S. Furukawa, M. Kondo, K. Hirai, N. Horike, Y. Takashima, H. Uehara, N. Louvain, M. Meilikhov, T. Tsuruoka, S. Isoda, W. Kosaka, O. Sakata, S. Kitagawa, *Science* **339** (2013), 193.
- [68] C. Zhang, J.A. Gee, D.S. Sholl, R.P. Lively, *J. Phys. Chem. C* **118** (2014), 20727.

Table 1. Atomic coordinates and displacement parameters ($\text{\AA}^2 \times 10^3$) for Ni-dpbz. U(eq) is defined as one third of the trace of the orthogonal U_{ij} tensor.

	x	y	z	U(eq)
Ni(1)	-14(1)	7743(1)	2536(1)	6(1)
Ni(2)	5036(1)	5245(1)	2462(1)	7(1)
N(7)	8026(5)	3731(3)	2663(1)	9(1)
N(2)	8602(5)	7270(2)	6863(1)	8(1)
N(6)	7988(5)	6743(3)	2726(1)	10(1)
N(1)	1379(5)	7730(3)	3208(1)	9(1)
C(27)	6873(6)	4320(3)	2619(2)	9(1)
N(4)	1912(5)	6719(3)	2358(1)	9(1)
N(3)	6335(6)	5277(3)	1720(1)	13(1)
N(5)	1940(6)	3771(3)	2287(1)	10(1)
C(19)	8142(7)	5142(3)	873(2)	14(1)
C(5)	3345(7)	7745(3)	3282(2)	12(1)
C(12)	6637(7)	7245(3)	6787(2)	12(1)
C(7)	3172(7)	7903(3)	4967(2)	14(1)
C(6)	4095(7)	7560(3)	4584(2)	13(1)
C(10)	6827(7)	7075(4)	5104(2)	18(1)
C(9)	5920(7)	7419(3)	5484(2)	14(1)
C(23)	8219(7)	5457(3)	21(2)	16(1)
C(3)	3149(7)	7620(3)	4110(2)	12(1)
C(13)	5721(7)	7288(3)	6348(2)	16(1)
C(24)	9101(7)	5376(3)	-397(2)	16(1)
C(14)	6852(7)	7355(3)	5960(2)	12(1)
C(1)	310(7)	7666(3)	3579(2)	15(1)
C(4)	4270(7)	7698(4)	3719(2)	16(1)
C(21)	8286(7)	5294(4)	1700(2)	18(1)
C(16)	9681(7)	7330(4)	6492(2)	18(1)
C(17)	5279(7)	5192(4)	1316(2)	18(1)
C(20)	9230(8)	5230(4)	1288(2)	23(1)
C(8)	4054(7)	7839(3)	5407(2)	15(1)
C(22)	9102(7)	5077(3)	424(2)	14(1)
C(11)	5948(7)	7139(4)	4660(2)	17(1)
C(18)	6096(7)	5122(4)	892(2)	17(1)
C(15)	8891(7)	7368(4)	6043(2)	17(1)
C(2)	1110(7)	7609(4)	4027(2)	16(1)
C(25)	3104(6)	6150(3)	2382(2)	9(1)
C(26)	6839(6)	6159(3)	2658(2)	9(1)
C(28)	3117(6)	4341(3)	2340(1)	8(1)
S(1)	10479(10)	4935(4)	5895(2)	74(2)
C(29)	8950(20)	4799(8)	6373(5)	27(3)

C(31)	13080(30)	4954(12)	6196(5)	45(4)
O(5)	10550(20)	4256(13)	5579(5)	82(5)

Table 2. Selected bond distances (Å) for Ni-Dpbz)

Atom A-Atom B	Distance (Å)	Atom A-Atom B	Distance (Å)
Ni(1)-N(4)	2.061(4)	Ni(1)-N(5)#1	2.066(4)
Ni(1)-N(7)#2	2.071(4)	Ni(1)-N(6)#3	2.080(4)
Ni(1)-N(2)#4	2.111(4)	Ni(1)-N(1)	2.113(4)
Ni(2)-C(25)	1.860(4)	Ni(2)-C(28)	1.867(4)
Ni(2)-C(27)	1.868(4)	Ni(2)-C(26)	1.869(5)
Ni(2)-N(3)	2.369(4)		
N(1)-C(1)	1.333(6)	N(1)-C(5)	1.339(6)
N(2)-C(12)	1.340(6)	N(2)-C(16)	1.337(6)
N(3)-C(17)	1.338(6)	N(3)-C(21)	1.329(6)
N(4)-C(25)	1.155(6)	N(5)-C(28)	1.152(6)
N(6)-C(26)	1.159(6)	N(7)-C(27)	1.159(6)
C(1)-C(2)	1.377(7)	C(2)-C(3)	1.392(7)
C(3)-C(4)	1.403(6)	C(3)-C(6)	1.481(6)
C(4)-C(5)	1.382(6)	C(6)-C(7)	1.396(6)
C(6)-C(11)	1.403(7)	C(7)-C(8)	1.379(7)
C(8)-C(9)	1.411(7)	C(9)-C(10)	1.385(7)
C(9)-C(14)	1.482(6)	C(10)-C(11)	1.385(7)
C(12)-C(13)	1.381(6)	C(13)-C(14)	1.401(6)
C(14)-C(15)	1.392(7)	C(15)-C(16)	1.376(7)
C(17)-C(18)	1.379(7)	C(18)-C(19)	1.394(7)
C(19)-C(20)	1.381(7)	C(19)-C(22)	1.487(6)
C(20)-C(21)	1.386(7)	C(22)-C(23)	1.394(7)
C(22)-C(24)#9	1.392(7)	C(23)-C(24)	1.384(7)
S(1)-O(5)	1.346(16)	S(1)-C(29)	1.785(14)
S(1)-C(31)	1.922(19)		

Symmetry transformations used to generate equivalent atoms:

#1 -x,y+1/2,-z+1/2	#2 -x+1,y+1/2,-z+1/2	#3 x-1,y,z
#4 x-1,-y+3/2,z-1/2	#5 -x+1,y-1/2,-z+1/2	#6 x+1,-y+3/2,z+1/2
#7 x+1,y,z	#8 -x,y-1/2,-z+1/2	#9 -x+2,-y+1,-z

Graphical Abstract

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9

Figure 10

Figure 11