In situ studies on superior thermal stability of bulk FeZr nanocomposites

Z. Fan^a, J. Jian^b, Y. Liu^c, Y. Chen^c, M. Song^c, L. Jiao^b, H. Wang^b, X. Zhang^{a,c,*}

^a Department of Mechanical Engineering, Texas A&M University, College Station, TX 77843-3123, USA

^b Department of Electrical & Computer Engineering, Texas A&M University, College Station, TX 77843-3128, USA

^c Department of Materials Science & Engineering, Texas A&M University, College Station, TX 77843-3123, USA

*Corresponding author: X. Zhang, zhangx@tamu.edu, Tel: (979)845-2143

Abstract:

Nanostructured metals received significant attention due to their high mechanical strength. However, their poor thermal stability hinders their applications at high temperature. Here we show extraordinary thermal stability of FeZr nanocomposites with micron-sized Fe grains well distributed in the nanostructured Fe/Fe₂Zr eutectic laminates. The hardness of annealed FeZr nanocomposites remained unchanged up to 700°C. Grain growth at higher annealing temperatures leads to hardness drop. Moreover, *in situ* annealing inside a transmission electron microscope revealed an unexpected coarsening mechanism of α -Fe grain: thermal stress arising from thermal expansion mismatch between Fe and Fe₂Zr led to plastic yielding of large α -Fe grains. Debonding between α -Fe grain and Fe₂Zr along phase boundary introduced nanometer thick gaps, which were subsequently filled by Fe from eutectic laminates, manifested as grain coarsening of α -Fe grains.

Keywords: *in situ* annealing, eutectic laminates, plastic yielding, thermal stability

1. Introduction

The pursuit of strong and thermally stable metallic materials has been an active research subject as such materials may have applications at high temperatures. Nanostructured metals usually contain higher hardness, but relatively worse thermal stability than their coarse-grained counterparts. For instance, numerous nanocrystalline (nc) metals, such as Fe [1-3], Ni [4-7], and Cu [8-12], have high strength at room temperature, but upon annealing they typically soften because of rapid grain coarsening. Various strategies have been employed to enhance the thermal stability of nanostructured metals. Certain impurities segregated to grain boundaries can reduce grain boundary energy, and hence improve the thermal stability of nanograins [13, 14]. Inhomogenous solute distribution [15] can also enhance the thermal stability of nanograins. The influence of solutes on thermal stability of nc metals depends on parameters such as atomic radius difference and solid solubility [16, 17]. Additionally, in tri-phase immiscible nanocomposites (TPIN), the growth of nanograins can be efficiently suppressed because of the immiscibility among each phase, the number of immiscible phases, and abundant triple junctions [18]. Meanwhile, nanotwinned (nt) metals containing high density of coherent twin boundaries (CTBs) have shown outstanding thermal stability. Because the energy of CTBs is much lower than that of high angle grain boundaries, nt metals are thermodynamically more stable than nc counterparts [19-22]. Immiscible layer interfaces can also increase the thermal stability of nanolayered materials [23]. Yet bulk nanolayered metallic materials are rarely synthesized or studied [24, 25]. Our current study investigates the thermal stability of bulk Fe-Zr nanocomposites containing nanoscale eutectic laminates.

The FeZr alloy is an interesting system. FeZr amorphous alloys are soft magnetic materials [26, 27], and they can be fabricated by melt-spinning [28], co-sputtering techniques

[29], and mechanical alloying [30]. The incorporation of Zr into Fe by using the ball-milling technique leads to nc FeZr alloys with much higher hardness than pure nc Fe, and that grain growth of nc FeZr alloys can be inhibited up to a relatively high temperature [13]. Liu et al. [31] shows that FeZr alloy with eutectic composition exhibits outstanding compressive ductility, ~48% after annealing at 1190°C for 48 hours. Moreover, FeZr nanocomposites over a range of Zr composition showed impressive high compression strength and good ductility [32]. The laves phase in steel with Zr [33] was shown to be stable close to its eutectic point. Radiation damage in FeZr alloys has also been studied for nuclear reactor applications [34-36]. Yu et al. [37] shows that, via *in situ* Kr ion irradiation in a transmission electron microscope, bulk FeZr nanolaminates fabricated by rapid solidification have extraordinary radiation stability and tolerance. However, the thermal stability of these FeZr nanocomposites has not been well investigated.

To study the thermal stability of nanostructured FeZr alloys, we applied the suction casting technique to fabricate bulk FeZr nanocomposites, which contain two components with different morphology: nearly equiaxed α -Fe grains and eutectic laminates of Fe and FeZr intermetallic nanolayers. Ex *situ* annealing studies show that the FeZr nanocomposites have extraordinary thermal stability. In *situ* annealing studies in a transmission electron microscope revealed that the grain coarsening in α -Fe grains at high temperature originates from thermal stress induced plastic yielding of α -Fe grains, followed by decohesion between α -Fe and Fe₂Zr along phase boundaries.

2. Methods and experiments

The FeZr alloy with the nominal composition of Fe_{94.2}Zr_{5.8} was fabricated by arc-melting the mixture of high purity Fe (99.95%) and Zr (99.8%) under the Zr-gettered ultra high purity

(UHP) argon atmosphere using an Edmund Buhler Arc Melter. Cylindrical rods with the diameter of 3 mm and the length of 60 mm were prepared by suction casting via a water cooled copper mold. The alloy was melted at least 4 times before the suction-casting experiment to ensure the chemical homogeneity of the alloy. The chamber was evacuated to a [base](#) pressure better than 3×10^{-3} Pa and then inflated with UHP Argon to a pressure of 9×10^4 Pa. A plate mold with the dimension of $2 \times 25 \times 50$ mm was also used to fabricate the alloy. Thin slices of the alloy were cut from the cast alloys for transmission electron microscopy (TEM) studies.

The slices were mechanically polished to 50-100 μm and then electropolished by using [the solution](#) of 10% perchloric acid and 90% methanol. *In situ* heating experiment was performed on a JOEL 2010 transmission electron microscope operated at an accelerating voltage of 200 kV at a constant heating rate. A Gatan SC1000 Orius CCD camera (model 832) was used to record [the evolution of](#) microstructures during [the in situ](#) annealing experiments. An FEI Tecnai G2 F20 microscope operated at 200 kV was also employed to study the microstructure and chemistry of [the as-cast](#) alloys. Scanning transmission electron microscopy (STEM) and energy dispersive X-ray (EDX) analysis were conducted using [a](#) Fischione ultra-high resolution high angle annular dark field (HADDF) detector (0.23 nm [resolution](#) in the STEM image mode) and Oxford instruments detectors with a spatial resolution of ~ 1 nm attached to the Tecnai F20. Scanning electron microscopy (SEM) experiments were performed by using a Quanta 600 field emission scanning electron microscope. [The](#) hardness and elastic modulus of the specimens were determined by using the instrumented nanoindentation technique on a Fischerscope 2000XYp nano/micro indenter. A minimum of 25 indents were used to obtain an average hardness value at various indentation depths. The hardness of the specimens were determined as the hardness plateau in the plots of hardness vs. indentation depth [38, 39].

3. Results

The as-cast $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy (by using the plate mold) shown in Fig. 1a contained two phases: α -Fe grains and eutectic laminate matrix. The α -Fe grains are several microns in diameter. A high-magnification SEM image in Fig. 1b shows eutectic laminates consisting of alternating nanolayers of α -Fe and Fe_2Zr (laves phase). Besides large patches of straight nanolayers, cellular domains composed of α -Fe and Fe_2Zr were also observed. The α -Fe grains were typically separated from the eutectic phase by Fe_2Zr nanolayers.

A low-magnification TEM micrograph of the as-cast $\text{Fe}_{94.2}\text{Zr}_{5.8}$ nanocomposite (plate mold in Fig. 2a) shows the coexistence of α -Fe grains, cellular and laminar domains. Fig. 2b shows the typical laminates containing alternating dark Fe_2Zr and light α -Fe nanolayers with relatively long straight layer interfaces. The inserted selected area diffraction (SAD) pattern shows diffractions from both the α -Fe and Fe_2Zr with predominantly C15 structure, which is commonly accepted as the equilibrium phase at room temperature. Fig. 2c shows the STEM image of the laminates, wherein Fe_2Zr appears brighter due to its greater average atomic number than Fe. Fig. 2d shows a typical compositional line profile acquired across alternating layers over a distance of ~400nm as shown in Fig. 2c. The compositional profile of the laminates shows Fe layers, and FeZr layers with ~ 35 at.% Zr and 65 at.% Fe corresponding to the Fe_2Zr intermetallic phase. The $\text{Fe}_{23}\text{Zr}_6$ phase was also identified in the as-cast specimens.

For comparison, the TEM micrographs of the $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy synthesized by using the cylinder mold are presented in Fig. 3. Similarly this specimen consists of α -Fe grains, straight laminar and cellular domains as shown in Fig. 3a. Fig. 3b shows a typical example of abundant straight laminate patches separated by a grain boundary indicated by the dashed line. The Fe_2Zr layers appear to contain planar defects parallel to layer interfaces. The SAD pattern of the

eutectic phases in Fig. 3b is shown in Fig. 3c. Three phases were identified: α -Fe with zone axis of [011], and $\text{Fe}_{23}\text{Zr}_6$ and Fe_2Zr with respective zone axis of [011] and $[\bar{1}12]$. Hence, both specimens cast by the cylindrical and plate mold contained a certain amount of $\text{Fe}_{23}\text{Zr}_6$ phase. High density stacking faults in the Fe_2Zr phase are confirmed from the streaking lines in the SAD pattern. Although a majority of the α -Fe grains were separated from the α -Fe layers in nanolaminates by the Fe_2Zr intermetallic layers, in some cases, they were not entirely separated as indicated by the arrows in Fig. 3d. The direct contact of α -Fe grains with α -Fe in laminates has implications on the thermal stability of nanocomposites as will be discussed later from *in situ* annealing studies.

Annealing experiments at various temperatures (for 1h) were performed to examine the thermal stability of the as-cast FeZr nanocomposites. The indentation hardness (H_{IT}) of the annealed alloys tested at room temperature is shown in Fig. 4 (Please note that all the hardness data reported in this study were measured at room temperature, including the data from reference). The hardness of alloys cast in different molds remained stable up to 700°C, although the alloy fabricated in the cylinder mold had moderately higher hardness than that prepared by using the plate mold. After annealing at 900°C, the hardness of both alloys reduced moderately to ~ 3.5 GPa. In comparison, the hardness of ultrafine grained (UFG) Fe processed by equal channel angular pressing (ECAP) [40] decreased significantly after annealing above 250°C, to less than 1 GPa due to substantial grain coarsening.

Next we compare the microstructures of nanostructured eutectic laminates prepared by the cylinder and plate mold before annealing. The layer thicknesses of the α -Fe and Fe_2Zr layers are nearly the same in both as-cast alloys. The nanocomposite prepared in the cylinder mold has a smaller average layer thickness, ~35 nm, compared with that fabricated by the plate mold, ~75

nm (Fig. 5).

The SEM images of the FeZr alloy (plate mold) after annealing up to 900°C (800°C/1h and 900°C/0.5h) in Fig. 6 show the retention of all three components: α -Fe grains, nanolaminates, and cellular patches. The statistical analysis of more than 100 grains (from SEM images) in Fig. 7 shows that after annealing (800°C/1 h) the average grain size of α -Fe in the Fe_{94.2}Zr_{5.8} alloy (plate mold), increased from 3.3 (as-cast) to 3.5 μ m. Meanwhile the volume fraction of α -Fe grains increased from 43% to 47%, accompanied by the diminished volume fraction of laminar and cellular components.

In order to examine the microstructure evolution in detail, *in situ* heating experiments were performed at a constant heating rate inside a transmission electron microscope. Snapshots captured during *in situ* heating (up to 650°C) are shown in Fig. 8a-i (See **supplementary Video 1**). Several distinct events were captured in a typical region containing a large α -Fe grain encompassed by laminar/cellular patches.

First, no significant microstructure evolution was observed up to 540°C (Fig. 8a). By 575°C (Fig. 8b), several dislocations appeared in the α -Fe grain, manifesting the dislocation nucleation process. From 590 (Fig. 8c) to 595°C (Fig. 8d), numerous additional dislocations emerged in the α -Fe grain, and some of the dislocations started to migrate. By 600°C (Fig. 8e), the density of dislocations in the grain interior increased substantially. Meanwhile many of these dislocations appeared to propagate outwards and approached the phase boundary between the α -Fe grain and the eutectic phase, where the interaction occurred (at $\sim$ 625°C in Fig. 8f). Subsequently the dislocations arriving at the phase boundary were annihilated (Fig. 8g and Fig. 8h). The continuous absorption of dislocations by the phase boundary led to the formation of a narrow gap, $\sim$ several nanometers in width, surrounding the large α -Fe grain at 640°C or higher

temperature (Fig. 8i).

The microstructure evolution of nanoscale eutectic laminates was also investigated by *in situ* annealing. In general the nanolayer morphology remained thermally stable throughout the *in situ* heating study. In particular we observed an intriguing event involving the migration of defect clusters in the α -Fe layer. Figure 9a-f show that a defect cluster (outlined in red dashed circle) in the α -Fe layer adjacent to the boundary between the α -Fe grain and the eutectic phase propagated leftward. The migration of the defect cluster appeared to be confined in the α -Fe layer, and no sign of interaction between the defect cluster and the laminar interface was observed.

A comparison of the microstructural stability of various components in the FeZr nanocomposites is shown in Fig. 10 after *in situ* annealing up to 800°C/1 h. As shown in Fig. 10a, several defect clusters appeared in the α -Fe layer in the cellular domains and some gaps were observed surrounding the large α -Fe grains. In contrast, Fig. 10b shows that the nanostructured eutectic laminates retained the straight laminar interfaces after annealing under the same condition (Supplementary Video 2).

4. Discussion

4.1 Hardness evolution due to coarsening of microstructures

The microstructures of the as-cast FeZr nanocomposites contain several major components: straight laminates, cellular domains and large α -Fe grains. The nanolaminates, consisting of alternating Fe₂Zr and α -Fe layers, which are the products of eutectic phase transformations, have outstanding thermal stability and mechanical strength. Meanwhile α -Fe grains could sustain considerable ductility in the nanocomposite. Hence the interesting combination of these two structural motifs may render high strength and good ductility in the

nanocomposites [32].

The hardness of the nanocomposites with multiple components may be estimated from the rule-of-mixture method as follows:

$$H_{composite} = H_{eutectic} * f_{eutectic} + H_{\alpha Fe} * f_{\alpha Fe} \quad (1),$$

where $H_{composite}$, $H_{eutectic}$, and $H_{\alpha Fe}$ represent the hardness of the composite, eutectic phase and α -Fe grain, respectively. $f_{eutectic}$ and $f_{\alpha Fe}$ are the respective volume fraction of the eutectic phase (including nanolaminates and cellular domains) and α -Fe grains.

The weight percentage of α -Fe phase ($W_{\alpha Fe}$ %) in the composites estimated by lever rule is 40%. Considering that the density of pure Fe and Fe_2Zr phase [41] is similar, the volume fraction of α -Fe grains should be also ~ 40%, which agrees well with 43% volume fraction measured experimentally from the SEM analysis.

The hardness of the as-cast FeZr cylindrical specimen is greater than that cast by the plate mold. The volume fraction and average grain size of α -Fe grains in both specimens are close to each other. However the average laminar thickness for the cylindrical specimen is ~ 35 nm, much smaller than that cast by the plate mold, ~75nm. Such a difference arises from the disparity in cooling rate during rapid solidification process. The cylindrical specimen has smaller volume and greater surface area thus solidification time is shorter than that achieved in the plate mold according to the Chvorinov's rule [42] (assuming the mold constant is identical for both molds). A higher quenching rate leads to smaller average laminar thickness, which in turn induces greater hardness in metallic nanolaminates [43-48]. Consequently the hardness of the cylindrical specimen is greater than that of the plate specimen.

Prior studies show that the hardness of the ECAPed UFG Fe (measured at room

temperature after high temperature annealing) quickly decreases beyond the annealing temperature of 250°C primarily due to grain growth, and by 400°C, its hardness drops significantly to 1 GPa [40]. The addition of Zr to pure Fe by ball-milling can significantly enhance the thermal stability of nc Fe grains [13], but softening occurred in this alloy at an annealing temperature of ~ 550°C. Our study shows that the Fe_{94.2}Zr_{5.8} nanocomposites retain their hardness up to an annealing temperature of 700°C, and remain strong with a hardness of ~3.5 GPa upon further annealing to 900°C. The evolution of hardness of the annealed FeZr alloy with 4 at.% Fe with respect to annealing temperature (not reported here) follows the same trend.

In spite of their extraordinary thermal stability, the FeZr nanocomposites in both systems soften gradually after annealing above 700°C. Microscopy studies show that, after annealing at 800°C (for 1h), the average grain size of α -Fe grains increases from 3.3 to 3.5 μ m (Fig. 7), corresponding to ~ 10% of increase in the volume fraction of the α -Fe grains. As shown in equ. (1), the coarsening and increase in the volume fraction of the soft α -Fe grains ($f_{\alpha Fe}$) and the correlated decrease in the volume fraction of the strong eutectic laminates ($f_{eutectic}$) should account for the softening of nanocomposites after high temperature annealing.

Other factors that may contribute to softening could involve the chemistry and instability of cellular domains. In contrast to the long and straight interfaces in eutectic laminates, cellular domains have discontinuous and curved layer interfaces, and are more vulnerable to coarsening. Interestingly Fe₂₃Zr₆ is identified more frequently in the cellular domains than in straight laminates. Comparing with Fe₂Zr, the metastable Fe₂₃Zr₆ phase, enriched in Fe, could become less stable upon high temperature annealing.

It has been shown that lamellar structures in TiAl alloys could coarsen via direct cylinderization, edge spheroidization, boundary splitting, or termination migration [49].

However, these phenomena were not well observed in the annealed Fe/Fe₂Zr eutectic laminates, which are stable after annealing at 800°C/1h. We speculate that the eutectic FeZr nanocomposites with predominantly long straight nanolaminates and less cellular domains could have enhanced thermal stability comparing with the current hypoeutectic system.

4.2 Thermal stress induced plastic yielding of the large α -Fe grains due to nucleation of dislocations

The *in situ* heating studies (Fig. 8) show several distinctive events in α -Fe grains, including nucleation of dislocations, propagation of dislocations toward the phase boundary, annihilation of dislocations by the phase boundary followed by the generation of a ring of gap surrounding the α -Fe grains.

The nucleation of dislocations will be examined first. It is well known that under external stress, dislocations can nucleate in metallic materials, signaling the plastic yielding of grains. During the *in situ* heating studies of FeZr nanocomposites, however, there is no external applied stress. Hence it is necessary to evaluate the sources of stress that may lead to the observed nucleation of dislocations in the α -Fe grains. We hypothesize that one of such sources could be thermal stress.

The TEM studies show that the large α -Fe grains are typically surrounded by a thin layer of Fe₂Zr (Fig. 2, Fig. 3). As the thermal expansion coefficient (TEC) of Fe and Fe₂Zr is different, thermal stress would arise during *in situ* annealing experiments. If the magnitude of the thermal stress exceeds the yield strength of the α -Fe grains, then dislocations may nucleate. In order to validate such a hypothesis, we first estimate the magnitude of the thermal stress (σ_t) by using

$$\sigma_t = E\varepsilon_t = E(\alpha_{\alpha Fe} - \alpha_{Fe_2Zr}) * \Delta T \quad (2),$$

where ε_i is the thermal mismatch strain, E is the Young's modulus of Fe, $\alpha_{\alpha\text{Fe}}$ and $\alpha_{\text{Fe}_2\text{Zr}}$ are the respective TEC of the α -Fe and Fe_2Zr phase, and ΔT is the change in temperature.

The TEC of Fe (near room temperature) varies slightly: $10.4 \times 10^{-6} \text{ K}^{-1}$ for cast Fe, $11.8 \times 10^{-6} \text{ K}^{-1}$ for pure Fe, and $11 \times 10^{-6} \text{ K}^{-1}$ for forged Fe. According to [50], the TEC of Fe increases at higher temperatures. The TEC value of Fe_2Zr phase in $\text{Fe}_{67}\text{Zr}_{33}$, $\text{Fe}_{70}\text{Zr}_{30}$, and $\text{Fe}_{72}\text{Zr}_{28}$ can be estimated as 2.91, 3.91, and $4.73 \times 10^{-6} \text{ K}^{-1}$ [41]. In this study, we selected TEC of Fe as $10.4 \times 10^{-6} \text{ K}^{-1}$ and Fe_2Zr as $4.73 \times 10^{-6} \text{ K}^{-1}$, which may lead to a slightly underestimated thermal stress. At 575°C , when dislocations begin to nucleate as evidenced from *in situ* annealing studies, the thermal stress is estimated to be $\sim 670 \text{ MPa}$.

Next, we need to estimate the yield strength of the large α -Fe grains via Hall-Patch relation [51, 52]:

$$\sigma = \sigma_0 + k_y d^{-0.5} \quad (3),$$

where σ_0 is the friction stress, $\sim 25 \text{ MPa}$ for Fe, and k_y is the locking parameter, $\sim 0.6 \text{ MPa} \cdot \text{m}^{-1/2}$ for Fe [53, 54]. Thus the yield strength for the α -Fe grain (shown in the *in situ* video) with a grain size of $1.4 \mu\text{m}$ (as shown in Fig. 8) is $\sim 530 \text{ MPa}$. Clearly the TEC mismatch induced stress exceeds the yield strength, and hence dislocations can nucleate at 575°C , in good agreement with the *in situ* experimental observation.

4.3 The generation of gaps and coarsening of α -Fe grains

The growth of the α -Fe grains at high temperatures could be related to the intriguing formation of gaps surrounding the α -Fe grain induced during annealing. As revealed by the *in situ* heating studies, the nucleated dislocations traveled toward the grain/phase boundary where they were annihilated afterwards. Comparing with the specimens at room temperature, annealing

1
2
3
4 at 600°C or higher may increase the vacancy concentration and atomic mobility for diffusion.
5
6 The mobile dislocations that carry free volume and vacancies interact with the phase boundary
7
8 between α -Fe grain and the eutectic Fe₂Zr nanolayer. After their interactions, the dislocations are
9
10 annihilated and consequently may release the access free volume and vacancies along the phase
11
12 boundary. It is likely that the aggregation of the vacancies and excess free volume at the phase
13
14 boundaries could lead to the formation of the ring of gap observed in the *in situ* TEM studies. On
15
16 the other hand, continuous absorption of dislocations by the α -Fe/Fe₂Zr phase boundaries may
17
18 lead to large plastic deformation, distort the bonding between α -Fe and Fe₂Zr along their phase
19
20 boundary, and eventually lead to delamination, manifested by the formation of a ring of gaps.
21
22 The creation of gaps may encourage the diffusion of Fe atoms from the eutectic laminates to the
23
24 α -Fe grains, leading to grain coarsening as observed in this study. The discontinuous phase
25
26 boundaries between nanolaminates and large grains (Fig. 3d) may also become channels that
27
28 permit the diffusion of Fe atoms from eutectic (cellular/laminar) phase to α -Fe grains.
29
30
31
32
33
34
35
36

37 The growth of the Fe grains could also be a consequence of Ostwald coarsening process
38
39 [55, 56]. We examined the evolution of nanolaminate thicknesses from *ex situ* SEM studies of
40
41 the annealed (800°C/1h) specimens. Our *ex situ* studies show that indeed the average laminar
42
43 thickness in the cellular zone decreases substantially from 90 to 68 nm, implying that Fe from
44
45 the nanolaminates may have diffused into the neighboring large Fe grains.
46
47
48

49 Analysis of the *in situ* TEM studies (Fig. 8) also shows that the average thickness of FeZr
50
51 layers in the cellular zone (adjacent to the large Fe grains) decreases from 105 to 95 nm.
52
53 Furthermore the width of the laminates between two large α -Fe grains decreases, implying that
54
55 Fe may have diffused from the Fe and Fe₂Zr laminates into the large α -Fe grains. The reduction
56
57 in the thickness of FeZr alloy layers could be a result of the frequent existence of metastable
58
59
60

1
2
3
4 $\text{Fe}_{23}\text{Zr}_6$ phase in the FeZr layers in the cellular zones, as confirmed by the TEM studies.
5
6 According to the equilibrium Fe-Zr phase diagram, the $\text{Fe}_{23}\text{Zr}_6$ could transform into Fe and
7
8 Fe_2Zr . Consequently during annealing the thickness of FeZr alloy layer reduces, whereas the
9
10 extra Fe atoms may diffuse into the α -Fe layers or fill in the gaps surrounding the α -Fe grains,
11
12 leading to the reduction of FeZr layer thickness.
13
14

15
16 Although thermal stress leads to the formation of the gaps surrounding the large α -Fe
17
18 grains, it is insufficient to create interfacial delamination between the α -Fe and Fe_2Zr layers in
19
20 nanolaminates. The α -Fe layer in eutectic laminates has much greater yield strength than its
21
22 coarse grained counterpart. At the current length scale, ~ 35 -70 nm, the yield strength of α -Fe
23
24 layers in the laminate could exceed 1 GPa. Hence fewer dislocations can be generated in the α -
25
26 Fe layer in the nanolaminate. Correspondingly we observed sporadic migration of defect clusters
27
28 confined within the α -Fe layers in the eutectic laminates (Fig. 9). It is interesting to note that the
29
30 mobile defect clusters in the α -Fe nanolayer are often initiated from the large α -Fe grain
31
32 boundaries, where the α -Fe nanolayer is in direct contact to the α -Fe grains.
33
34
35
36
37
38

39
40 The nucleation of dislocations (from 575°C) and the subsequent gap formation (at 650°C)
41
42 observed from the *in situ* videos agree well with the *ex situ* hardness measurements which show
43
44 that the softening of FeZr nanocomposites gradually starts from 700°C (Fig. 4).
45
46

47
48 A schematic illustrating the microstructural evolution of the FeZr nanocomposite is
49
50 shown in Fig. 11. The FeZr nanocomposite contains α -Fe grains embedded in the nanostructured
51
52 straight and cellular eutectic laminates (Fig. 11a), and a nearly continuous Fe_2Zr phase boundary
53
54 separates the α -Fe grains from laminar/cellular components. Beyond a critical temperature T_1
55
56 (Fig. 11b), dislocations nucleate as thermal stress (due to TEC mismatch) exceeds the yield
57
58 strength of α -Fe grains. At even greater temperature T_2 (Fig. 11c), dislocations reach and interact
59
60

with the phase boundary. The debonding between Fe and Fe₂Zr at the phase boundary results in the formation of a ring of gaps. The gap can be backfilled by the diffusion of Fe atoms (at T₃) from cellular/lamellar domains, leading to the gradual growth of the α -Fe grains. Sporadic defect clusters may also be present in the α -Fe layer in nanolaminates. But their density is low in general, and insufficient to lead to debonding at the layer interfaces. And consequently the nanolaminates are very stable throughout the entire annealing studies.

5. Conclusions

FeZr nanocomposites containing the nanoscale eutectic laminates matrix exhibit extraordinary thermal stability up to $\sim 900^{\circ}\text{C}$. Softening beyond 700°C results from the coarsening of large α -Fe grains. *In situ* studies show that the mismatch in thermal expansion coefficient between Fe and Fe₂Zr induced significant thermal stress that could exceed the yield strength of the α -Fe grains, manifested by nucleation and migration of dislocations towards phase boundaries. The absorption of dislocations leads to debonding along phase boundaries manifested by the formation of a narrow gap, which permits the diffusion of Fe from nanolaminates to the large α -Fe grains, leading to their coarsening. The coarsening of α -Fe grains could also arise from the Ostwald coarsening process through which Fe in the laminates diffuse into the large α -Fe grains. In contrast, nanolaminates at a distance from α -Fe grains are much more stable up to a very high temperature.

Acknowledgements

We acknowledge the financial support by NSF-CMMI under grant No. 1161978. Y. Liu is partially supported by NSF-CMMI under grant No. 1129065. Accesses to the DOE-Center for Integrated Nanotechnologies (CINT) at Los Alamos and Sandia National Laboratories and Microscopy Imaging Center at Texas A&M University are also acknowledged.

References

- [1] Y.H. Zhao, H.W. Sheng, K. Lu. Microstructure evolution and thermal properties in nanocrystalline Fe during mechanical attrition, *Acta Mater.* 49 (2001) 365-375.
- [2] C.H. Moelle, H.J. Fecht. Thermal stability of nanocrystalline iron prepared by mechanical attrition, *Nanostruct. Mater.* 6 (1995) 421-424.
- [3] T.R. Malow, C.C. Koch. Grain growth in nanocrystalline iron prepared by mechanical attrition, *Acta Mater.* 45 (1997) 2177-2186.
- [4] H. Natter, M. Schmelzer, R. Hempelmann. Nanocrystalline nickel and nickel-copper alloys: Synthesis, characterization, and thermal stability, *J. Mater. Res.* 13 (1998) 1186-1197.
- [5] U. Klement, U. Erb, A.M. El-Sherik, K.T. Aust. Thermal stability of nanocrystalline Ni, *Mater. Sci. Eng., A* 203 (1995) 177-186.
- [6] R. Klemm, E. Thiele, C. Holste, J. Eckert, N. Schell. Thermal stability of grain structure and defects in submicrocrystalline and nanocrystalline nickel, *Scripta Mater.* 46 (2002) 685-690.
- [7] M. Thuvander, M. Abraham, A. Cerezo, G.D.W. Smith. Thermal stability of electrodeposited nanocrystalline nickel and iron–nickel alloys, *Mater. Sci. Technol.* 17 (2001) 961-970.
- [8] L. Lu, L.B. Wang, B.Z. Ding, K. Lu. High-tensile ductility in nanocrystalline copper, *J. Mater. Res.* 15 (2000) 270-273.
- [9] L. Lu, N.R. Tao, L.B. Wang, B.Z. Ding, K. Lu. Grain growth and strain release in nanocrystalline copper, *J. Appl. Phys.* 89 (2001) 6408-6414.
- [10] L.H. Qian, S.C. Wang, Y.H. Zhao, K. Lu. Microstrain effect on thermal properties of nanocrystalline Cu, *Acta Mater.* 50 (2002) 3425-3434.
- [11] H. Jiang, Y.T. Zhu, D.P. Butt, I.V. Alexandrov, T.C. Lowe. Microstructural evolution, microhardness and thermal stability of HPT-processed Cu, *Mater. Sci. Eng., A* 290 (2000) 128-138.
- [12] J. Schiøtz, K.W. Jacobsen. A Maximum in the Strength of Nanocrystalline Copper, *Science* 301 (2003) 1357-1359.
- [13] K.A. Darling, B.K. VanLeeuwen, C.C. Koch, R.O. Scattergood. Thermal stability of nanocrystalline Fe–Zr alloys, *Mater. Sci. Eng., A* 527 (2010) 3572-3580.
- [14] K.A. Darling, R.N. Chan, P.Z. Wong, J.E. Semones, R.O. Scattergood, C.C. Koch. Grain-size stabilization in nanocrystalline FeZr alloys, *Scripta Mater.* 59 (2008) 530-533.
- [15] T. Chookajorn, H.A. Murdoch, C.A. Schuh. Design of Stable Nanocrystalline Alloys, *Science* 337 (2012) 951-954.
- [16] P.C. Millett, R.P. Selvam, A. Saxena. Stabilizing nanocrystalline materials with dopants, *Acta Mater.* 55 (2007) 2329-2336.
- [17] P. Choi, M. da Silva, U. Klement, T. Al-Kassab, R. Kirchheim. Thermal stability of electrodeposited nanocrystalline Co-1.1at.%P, *Acta Mater.* 53 (2005) 4473-4481.
- [18] Y. Chen, Y. Liu, F. Khatkhatay, C. Sun, H. Wang, X. Zhang. Significant enhancement in the thermal stability of nanocrystalline metals via immiscible tri-phases, *Scripta Mater.* 67 (2012) 177-180.
- [19] X. Zhang, A. Misra. Superior thermal stability of coherent twin boundaries in nanotwinned metals, *Scripta Mater.* 66 (2012) 860-865.
- [20] D. Bufford, H. Wang, X. Zhang. Thermal stability of twins and strengthening mechanisms in differently oriented epitaxial nanotwinned Ag films, *J. Mater. Res.* 28 (2013) 1729-1739.
- [21] X. Zhang, R.K. Schulze, H. Wang, A. Misra. Thermal stability of sputtered Cu / 304 stainless steel multilayer films, *J. Appl. Phys.* 101 (2007) 124311.
- [22] O. Anderoglu, A. Misra, H. Wang, X. Zhang. Thermal stability of sputtered Cu films with nanoscale growth twins, *J. Appl. Phys.* 103 (2008) 094322.
- [23] A. Misra, R.G. Hoagland, H. Kung ‡. Thermal stability of self-supported nanolayered Cu/Nb films, *Philos. Mag.* 84 (2004) 1021-1028.

- [24] J.S. Carpenter, S.C. Vogel, J.E. LeDonne, D.L. Hammon, I.J. Beyerlein, N.A. Mara. Bulk texture evolution of Cu–Nb nanolamellar composites during accumulative roll bonding, *Acta Mater.* 60 (2012) 1576-1586.
- [25] J.S. Carpenter, S.J. Zheng, R.F. Zhang, S.C. Vogel, I.J. Beyerlein, N.A. Mara. Thermal stability of Cu–Nb nanolamellar composites fabricated via accumulative roll bonding, *Philos. Mag.* 93 (2012) 718-735.
- [26] D.H. Ryan, J.M.D. Coey, E. Batalla, Z. Altounian, J.O. Ström-Olsen. Magnetic properties of iron-rich Fe–Zr glasses, *Phys. Rev. B* 35 (1987) 8630-8638.
- [27] L.F. Kiss, G. Huhn, T. Kemény, J. Balogh, D. Kaptás. Magnetic properties of Fe–Zr metastable phases, *J. Magn. Mater.* 160 (1996) 229-232.
- [28] H. Hiroyoshi, K. Fukamichi. Ferromagnetic - spin glass transition in Fe - Zr amorphous alloy system, *J. Appl. Phys.* 53 (1982) 2226-2228.
- [29] K. Fukamichi, R.J. Gambino, T.R. McGuire. Electrical resistivity and Hall effect in Fe - Zr amorphous sputtered films, *J. Appl. Phys.* 53 (1982) 2310-2312.
- [30] E. Hellstern, L. Schultz. Progress of the amorphization reaction during mechanical alloying in Fe - Zr, *J. Appl. Phys.* 63 (1988) 1408-1413.
- [31] Y. Liu, J. Livingston, S. Allen. Room-temperature deformation and stress- induced phase, *Metall. Trans. A* 23 (1992) 3303-3308.
- [32] J.M. Park, S.W. Sohn, T.E. Kim, D.H. Kim, K.B. Kim, W.T. Kim. Nanostructure–dendrite composites in the Fe–Zr binary alloy system exhibiting high strength and plasticity, *Scripta Mater.* 57 (2007) 1153-1156.
- [33] D.P. Abraham, J.W. Richardson Jr, S.M. McDeavitt. Laves intermetallics in stainless steel–zirconium alloys, *Mater. Sci. Eng., A* 239–240 (1997) 658-664.
- [34] S. Chatain, C. Guéneau, C. Chatillon. High temperature mass spectrometry: Application to the thermodynamic study of the Fe–Zr system, *J. Nucl. Mater.* 344 (2005) 281-284.
- [35] S.M. McDeavitt, D.P. Abraham, J.Y. Park. Evaluation of stainless steel–zirconium alloys as high-level nuclear waste forms, *J. Nucl. Mater.* 257 (1998) 21-34.
- [36] C.-C. Wei, A. Aitkaliyeva, Z. Luo, A. Ewh, Y.H. Sohn, J.R. Kennedy, B.H. Sencer, M.T. Myers, M. Martin, J. Wallace, M.J. General, L. Shao. Understanding the phase equilibrium and irradiation effects in Fe–Zr diffusion couples, *J. Nucl. Mater.* 432 (2013) 205-211.
- [37] K.Y. Yu, Z. Fan, Y. Chen, M. Song, Y. Liu, H. Wang, M.A. Kirk, M. Li, X. Zhang. In situ Observation of Defect Annihilation in Kr Ion-Irradiated Bulk Fe/Amorphous-Fe₂Zr Nanocomposite Alloy, *Mater. Res. Lett.* 3 (2014) 35-42.
- [38] E.G. Fu, A. Misra, H. Wang, L. Shao, X. Zhang. Interface enabled defects reduction in helium ion irradiated Cu/V nanolayers, *J. Nucl. Mater.* 407 (2010) 178-188.
- [39] R. Saha, W.D. Nix. Effects of the substrate on the determination of thin film mechanical properties by nanoindentation, *Acta Mater.* 50 (2002) 23-38.
- [40] B. Han, F. Mohamed, E. Lavernia. Mechanical properties of iron processed by severe plastic deformation, *Metall. Mater. Trans. A* 34 (2003) 71-83.
- [41] N. Mattern, W.X. Zhang, S. Roth, H. Reuther, C. Baehtz, M. Richter. Structural and magnetic properties of non-stoichiometric Fe₂Zr, *J. Phys. Condens. Mat.* 19 (2007) 376202.
- [42] N. Chorinov. Theory of solidification of casting, *Giesserei* 27 (1940) 177-186.
- [43] E.G. Fu, N. Li, A. Misra, R.G. Hoagland, H. Wang, X. Zhang. Mechanical properties of sputtered Cu/V and Al/Nb multilayer films, *Mater. Sci. Eng., A* 493 (2008) 283-287.
- [44] Y. Liu, D. Bufford, H. Wang, C. Sun, X. Zhang. Mechanical properties of highly textured Cu/Ni multilayers, *Acta Mater.* 59 (2011) 1924-1933.
- [45] N. Li, K.Y. Yu, J. Lee, H. Wang, X. Zhang. Size dependent strengthening mechanisms in sputtered Fe/W multilayers, *J. Appl. Phys.* 107 (2010) 093503.

- [46] J.Y. Zhang, Y. Liu, J. Chen, Y. Chen, G. Liu, X. Zhang, J. Sun. Mechanical properties of crystalline Cu/Zr and crystal–amorphous Cu/Cu–Zr multilayers, *Mater. Sci. Eng., A* 552 (2012) 392-398.
- [47] X. Zhang, O. Anderoglu, R.G. Hoagland, A. Misra. Nanoscale growth twins in sputtered metal films, *JOM* 60 (2008) 75-78.
- [48] X. Zhang, A. Misra, H. Wang, T.D. Shen, M. Nastasi, T.E. Mitchell, J.P. Hirth, R.G. Hoagland, J.D. Embury. Enhanced hardening in Cu/330 stainless steel multilayers by nanoscale twinning, *Acta Mater.* 52 (2004) 995-1002.
- [49] G. Sharma, R.V. Ramanujan, G.P. Tiwari. Instability mechanisms in lamellar microstructures, *Acta Mater.* 48 (2000) 875-889.
- [50] F.C. Nix, D. MacNair. The Thermal Expansion of Pure Metals: Copper, Gold, Aluminum, Nickel, and Iron, *Phys. Rev.* 60 (1941) 597-605.
- [51] E. Hall. The deformation and ageing of mild steel: III discussion of results, *Proceedings of the Physical Society. Section B* 64 (1951) 747.
- [52] N. Petch. The cleavage strength of polycrystals, *J. Iron Steel Inst.* 174 (1953) 25-28.
- [53] Y. Bergström, H. Hallén. Hall–Petch relationships of iron and steel, *Met. Sci.* 17 (1983) 341-347.
- [54] J. Jang, C. Koch. The Hall-Petch relationship in nanocrystalline iron produced by ball milling, *Scripta Metall. Mater.* 24 (1990) 1599-1604.
- [55] L. Ratke, P.W. Voorhees. *Growth and coarsening: Ostwald ripening in material processing*, Springer Science & Business Media, 2013.
- [56] P.W. Voorhees. The theory of Ostwald ripening, *Journal of Statistical Physics* 38 (1985) 231-252.

Figure Captions:

Figure 1. The microstructure of the as-cast $\text{Fe}_{94.2}\text{Zr}_{5.8}$ nanocomposite prepared by the suction casting method using a plate mold. (a) A low-magnification SEM image of the cast $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy. The nanolaminate matrix contained relatively large α -Fe grains with several microns in diameter. (b) A higher magnification SEM micrograph of the alloy consisting of regions of different morphology, including large α -Fe grains, cellular and straight nanolaminates. The typical interface between laminated (cellular) regions and α -Fe grains is also marked.

Figure 2. TEM micrographs showing the microstructure of $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy prepared by the suction casting technique using a plate mold. (a) A low magnification TEM image shows that the as-cast alloy contains three components: α -Fe grains, straight laminates and cellular phases. (b) A higher magnification TEM micrograph showing straight laminates. The inserted selected area diffraction (SAD) pattern shows the single crystal-like Fe_2Zr (C15) eutectic phase. The zone axis of Fe_2Zr is $\langle 114 \rangle$. (c) A scanning transmission electron microscopy (STEM) micrograph shows the alternating laminates with an average layer thickness of ~ 100 nm. (d) The corresponding EDS composition profiles show alternating Fe and Fe_2Zr nanolaminates.

Figure 3. The TEM micrographs of different phases in the $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy prepared by using the cylinder mold. (a) An overview TEM micrograph shows the microstructure of the as-cast alloy containing α -Fe grains, straight laminates and cellular zones. (b) A TEM micrograph shows the straight nanolaminates. The dashed line distinguishes the grain boundary between two different domains in the laminar region. (c) SAD pattern shows the existence of α -Fe, Fe_2Zr and $\text{Fe}_{23}\text{Zr}_6$, as well as stacking faults as indicated by streaking lines. Zone axis for α -Fe and $\text{Fe}_{23}\text{Zr}_6$ is $\langle 011 \rangle$, and Fe_2Zr is $\langle 112 \rangle$. (d) A higher magnification TEM micrograph shows α -Fe grains and Fe in nanolaminates are sometimes interconnected.

Figure 4. The hardness evolution of the FeZr nanocomposites prepared by different molds after annealing at different temperatures (All the hardness data were measured at room temperature after the annealing experiments including the hardness data on Fe from the reference). For comparison, the hardness data of pure Fe (solid triangle) [42] fabricated by the equal channel angular pressing (ECAP) technique are also provided. The hardness of the ECAPed Fe reduced rapidly after annealing at 250°C or greater, whereas the hardness of the FeZr alloys decreased moderately after annealing at 800°C or higher.

Figure 5. Comparison of laminar thickness of the as-cast $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy prepared by using the (a) cylinder and (b) plate mold. The average Fe_2Zr layer thickness is $\sim 35\text{nm}$ for the specimen cast in the cylinder mold, comparing to 75nm for the alloy prepared by the plate mold.

Figure 6. The SEM images of the $\text{Fe}_{94.2}\text{Zr}_{5.8}$ alloy (plate mold) after *in situ* heating studies ($800^\circ\text{C}/1\text{h}$ and then $900^\circ\text{C}/0.5\text{h}$). (a) A low magnification SEM image of the annealed

Fe_{94.2}Zr_{5.8} alloy showing the retention of laminates and relatively large grains. (b) A higher magnification SEM micrograph of the alloy displaying large grains and nanolaminates.

Figure 7. The grain size distribution of the α -Fe grains in Fe_{94.2}Zr_{5.8} (plate mold) before and after annealing (800°C/1h) obtained from SEM images. The average grain size of α -Fe grains enlarged from 3.3 to 3.5 μ m. Meanwhile the volume fraction of α -Fe grains escalated from 43 to 47%.

Figure 8. *In situ* TEM studies showing the evolution of dislocation density in an α -Fe grain and the consequent formation of a gap along its peripheral observed during the *in situ* heating experiment (See **supplementary Video 1**). (a) At 540°C, few dislocations were observed in the α -Fe grain. (b) At 575°C, several dislocations nucleated inside the grain. (c) By 590°C, more dislocations nucleated in the grain. (d) At 595°C, dislocation density increased across the entire grain. (e) At 600°C, dislocations proliferated and propagated rapidly toward the grain boundary. (f) At 625°C, the dislocation density reached a maximum level and dislocations interacted prominently with the grain boundary. (g) A large number of dislocations were annihilated at the grain boundary. Meanwhile the density of dislocations in grain interior started to decrease. (h) The density of dislocations in grain interior decreased significantly while dislocations continued their interactions with the grain boundary. (i) The substantial absorption of the dislocations by the grain boundary led to creation of a gap surrounding the grain boundary.

Figure 9. Defect cluster migration in the nanolaminate captured during *in situ* heating study. (a) Defect clusters reside in the α -Fe layer adjacent to the boundary between nanolaminates and the α -Fe grain. (b-e) A defect cluster (highlighted in a red dashed circle) first propagated leftwards away from the boundary. Then the defect cluster migrated within the α -Fe layer and changed its geometry continuously. (f) The defect cluster stopped propagating and remained in the α -Fe layer.

Figure 10. TEM micrograph of Fe_{94.2}Zr_{5.8} alloy cast by plate mold after *in situ* annealing at 800°C for 1h. (a) In area containing large α -Fe grains and cellular domains, some defect clusters are observed in α -Fe layer of the cellular domains, and a gap appeared surrounding the annealed large α -Fe grains. (b) Area composed of long straight laminates remained very stable after high temperature annealing (**Supplementary Video 2**).

Figure 11. A schematic diagram illustrating the grain growth mechanism for α -Fe grains under high temperature annealing. (a) The as-cast nanocomposite contains α -Fe grains separated by patches of nanolaminates. (b) At elevated temperature, dislocations start to nucleate in the α -Fe grain interior when the thermal stress (induced by thermal expansion mismatch between the α -Fe grain and Fe₂Zr at phase boundary) exceeds the yield strength of the α -Fe grain. Meanwhile, some defect clusters are nucleated in the α -Fe nanolaminates. (c) The dislocation density in the α -Fe grain increases sharply and dislocations propagate towards and interact with the phase boundary. The phase boundary continuously absorbs these dislocations until it cannot accommodate the ever increasing

1
2
3
4 dislocations, then a gap is created along the phase boundary. (d) The diffusion of Fe
5 atoms from the α -Fe nanolaminates to the α -Fe grains fill in the gap, and leads to
6 subsequent grain growth and gradual shrinkage of the nanolaminates.
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure 1
[Click here to download high resolution image](#)

Figure 2
[Click here to download high resolution image](#)

Figure 3
[Click here to download high resolution image](#)

Figure 5
[Click here to download high resolution image](#)

Figure 8
[Click here to download high resolution image](#)

Figure 9
[Click here to download high resolution image](#)