A Facile Synthesis of $\text{SO}_4^{2-}/\text{SnO}_2$ Solid Superacid Nanoparticles as Anode Materials for Lithium-Ion Batteries

Wei Zhang^a, Xiaoli Du^b, Yueyue Tan^a, Jinbo Hu^c, Siyao He^c, Andreas Stein^c and Bohejin Tang^{ac#}

^aCollege of Chemistry and Chemical Engineering, Shanghai University of Engineering Science, Shanghai 201620, PR China

^bSchool of Materials Engineering, Shanghai University of Engineering Science, Shanghai 201620, PR China

^cDepartment of Chemistry, University of Minnesota, 207 Pleasant St. SE, Minneapolis, Minnesota 55455, United States

[#]Corresponding author: tangbohejin@sues.edu.cn

Abstract:

This paper presents a study of SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid nanoparticles, synthesized by a facile sol-gel route, as anode materials for lithium-ion batteries (LIBs). A possible reversible reaction mechanism is proposed for the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid nanoparticles used as an anode material. The $\text{SO}_4^{2-}/\text{SnO}_2$ exhibits a reversible lithium storage capacity of 925 mAh g⁻¹ at a low charge–discharge rate of 0.2 C (156 mA g⁻¹). Furthermore, it exhibits a stable cycling performance over 50 cycles at the rate of 0.2 C, maintaining the specific capacity of 310 mAh g⁻¹, whereas SO_4^{2-} -free SnO_2 only delivers the capacity retention of 126 mAh g⁻¹.

Keywords: Lithium-ion battery, solid super acid, $\text{SO}_4^{2-}/\text{SnO}_2$ nanoparticles

1. Introduction

Lithium ion batteries (LIBs) are among the prime candidates for electrical energy storage, because of their reasonably high energy densities and good cyclability [1, 2]. Many transition metal oxides have been investigated for use as anode materials for LIBs. Among them, SnO₂ has attracted particular attention due to its high theoretical specific capacity (782 mAh g⁻¹ based on 4.4 Li per formula unit) and low potential for lithium alloying [3]. However, a dramatic volume change (> 300%) commonly occurs in SnO₂-based anodes during lithium ion alloying/dealloying, leading to rapid capacity decay and poor cyclability [4]. To overcome this problem, we report a novel, simple and low cost synthetic route to prepare the SO₄²⁻/SnO₂ solid superacid, which improves the electrochemical activity of SnO₂ nanoparticles as anode materials for LIBs. To the best of our knowledge, this is the first report of the SO₄²⁻/SnO₂ solid superacid applied to LIBs.

2. Experimental

10 mL of a solution containing 0.4 mmol of SnCl₂·2H₂O in *N,N*-dimethylformamide (DMF) was sealed in a 25 mL Teflon-lined autoclave. The autoclave was heated at 110 °C for 16 h. The resulting sol was washed four times with ethanol and dried under vacuum at 80 °C. Finally, a yellow solid powder of SnO₂ was obtained. The obtained SnO₂ was immersed in sulfuric acid (3 M, 15 mL of acid solution per 1 g of solid) at room temperature for 1 h. Subsequently, the solid was filtered, dried, and calcined in air at 500 °C for 4 h to afford the SO₄²⁻/SnO₂ super acid.

A common method to confirm the presence and the type of acid sites in a solid acid is pyridine absorption-IR spectroscopy, which focuses on specific vibrational bands of pyridine that shift in position when the pyridine adsorbs to Lewis or Brønsted acid sites. FT-IR spectra were recorded on a Nicolet AVATAR 380 infrared spectrometer. The detailed procedure of

preparation of electrodes is similarly with the previous report [4]. The C rate was set so that 1 C = 782 mA per gram of active material in the electrode, which corresponds to the theoretical capacity of SnO₂.

3. Results and Discussion

XRD patterns of SnO₂ and SO₄²⁻/SnO₂ nanoparticles are shown in Fig. 1a. For both materials the pattern corresponds to the crystalline phase of SnO₂ (JCPDS: 41-1445). The diffraction peaks at $2\theta = 27^\circ$, 34° and 52° can be indexed to the (110), (101) and (221) reflections of tetragonal structure of SnO₂. In addition, the broadness of the peaks indicates that the crystalline SnO₂ and SO₄²⁻/SnO₂ particles are very small. According to the Scherrer equation, the average crystallite sizes of SnO₂ and SO₄²⁻/SnO₂ were calculated to be similar for the two materials, 2.5 and 3.4 nm, respectively. A magnified TEM image (Fig. 1b) reveals that the typical diameter of SnO₂ nanoparticles is 3~5 nm, consistent with the XRD data. Even though the SO₄²⁻/SnO₂ nanoparticles were synthesized at a high temperature of 500 °C at which agglomeration and sintering might be expected, the nanoparticles of SO₄²⁻/SnO₂ remained very fine with particle sizes between 3 and 5 nm, and they formed a looser network (Fig. 1c). The reason may be the negative surface charge introduced to the SO₄²⁻/SnO₂ particles by the SO₄²⁻ groups.

The IR spectra of SO₄²⁻/SnO₂ samples before and after pyridine adsorption are given in Fig. 1d. Four obvious adsorption peaks in the 900–1300 cm⁻¹ range can be observed, which are respectively located at ca. 990, 1037, 1157, and 1272 cm⁻¹. The IR peak at 990 cm⁻¹ can be attributed to the ν_1 vibrational mode of the sulfate group. In the free ion, this is not IR active, but here it becomes active due to the decrease in symmetry when the sulfate group complexes with Sn. The other three peaks are due to the splitting of the ν_3 peak of the sulfate group in the reduced

symmetry environment [5]. Therefore, the IR data confirm that the sulfate groups have been combined mainly with Sn on the $\text{SO}_4^{2-}/\text{SnO}_2$ surface. The type of acidity of these nanoparticles can be distinguished from infrared spectra of adsorbed molecules, especially pyridine. The infrared spectra of the pyridine-adsorbed $\text{SO}_4^{2-}/\text{SnO}_2$ (Fig. 1d) reveals two peaks at ca. 1450 and 1540 cm^{-1} due to pyridine adsorbed on Lewis and Brönsted acid sites [6], respectively. Evidently, sulfate modification not only increased the number of strong Lewis acid sites, but induced a significant amount of strong Brönsted acidic sites on the surface of SnO_2 . The IR spectra therefore demonstrate that the $\text{SO}_4^{2-}/\text{SnO}_2$ nanoparticles possess the characteristics of a solid superacid. In addition, the results obtained from SEM images (Fig. 1e and 1f) are consistent with previous report [7], the surfaces of $\text{SO}_4^{2-}/\text{SnO}_2$ particles show the greater pores structure, which is beneficial for the electrochemical reaction.

Fig. 2a shows the cyclic voltammograms of SnO_2 for the initial three cycles at a scan rate of 0.1 mV s^{-1} in the potential window of 0.01 to 3.0 V vs. Li/Li^+ . During the cathodic sweeps, two reduction peaks occur at 0.76 V and 0.07 V, respectively. The former peak could be assigned to the reduction reaction between SnO_2 and Li^+ to form Sn and Li_2O (eq 1) and the formation of a solid electrolyte interface (SEI) [8], while the latter is due to the alloying process of Sn with additional Li uptake (eq 2) [9]. Usually, the alloying reaction 2 is thought to be highly reversible, giving a theoretical lithium storage capacity of 782 mAh g^{-1} ($\text{Li}_{4.4}\text{Sn}$). In the anodic sweeps, the two peaks observed at 0.66 and 1.26 V indicated the corresponding reversible reaction of eq 2 [8].

In Fig. 2b, the behavior of the CVs represents electrochemical reactions caused from the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid, which are similar to those of unmodified SnO_2 nanoparticles during cycling. The two cathodic peaks around 0.76 V and 0.07 V that correspond to reactions (1) and (2). The broad peaks in the positive current range (charge) include all steps of dealloying. In addition, an XRD pattern of the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid after cycling also demonstrates the electrochemical reaction process in $\text{SO}_4^{2-}/\text{SnO}_2$. The diffraction peaks for the three materials match well with those of standard XRD patterns of Sn (JCPDF: 04-0673 and 05-0390) and cubic Li_2O (JCPDF: 01-077-2144) from reaction (1) and cubic Cu (JCPDF: 01-085-1326) from the Cu foil that was used as current collector (Fig. 2c,). The presence of Sn and Li_2O supports our hypothesis that SnO_2 and the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid behave similarly in the electrochemical reaction process. Therefore, the more important role for the sulfate anions is to prevent nanoparticle agglomeration through electrostatic repulsions and mitigate the effect of swelling of grains by forming a sulfate-rich buffer layer on the grain surfaces.

As shown in Figure 3a and 3b, both kinds of active materials possess similar charge-discharge plateaus during the first charge-discharge cycle. The first discharge plateau at about 0.7 V could be attributed to the formation of Sn from SnO_2 , and it becomes indiscernible in the following cycles. The second one at 0.1 V~0.3 V probably corresponds to the formation of the Li_xSn alloy. The events in the voltage regions at 0.5–1.0 V and above 1.2 V in the first charge curve could be due to the reverse reaction described in eq. 2 [10]. They are consistent with the CV curves in Fig. 2a and 2b. Fig. 3a and 3b show the 1st, 2nd, 3rd and 4th charge-discharge profiles of SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid nanoparticles, respectively. The corresponding specific discharge capacities of the SnO_2 nanoparticles are 1643, 571, 520 and 485 mAh g^{-1} , respectively,

where as those of the $\text{SO}_4^{2-}/\text{SnO}_2$ nanoparticles are up to 1667, 1000, 941 and 900 mAh g^{-1} , respectively. The initial capacity loss may result from the formation of a solid electrolyte interphase (SEI) layer [11]. In the formation process, a large volume change occurs in the Sn regions during the lithium insertion and extraction reactions. However, it is worth noting that the specific capacitance of $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid is still twice that of SnO_2 .

For the SnO_2 sample (Fig. 3c), the corresponding 5th cycle multi-rate average discharge capacities are 502, 221, 90 and 27 mAh g^{-1} at rates of 0.2 C, 0.5 C, 1 C and 2C, respectively. In comparison, the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid exhibits higher reversible capacities (Fig. 3c). It delivers specific discharge capacities of 925, 694, 476 and 176 mAh g^{-1} when the rates is 0.2 C, 0.5 C, 1 C and 2 C, respectively, and the specific discharge capacity recovers to 605 mAh g^{-1} when the rate is lowered again to 0.2 C. These data indicate that the specific capacity of the electrode is improved by incorporation of sulfate groups. Electrochemical impedance spectroscopy (EIS) was used to characterize the electrode materials, and the results are shown in Fig. 3d and 3e. The diameter of the semicircle is smaller for the $\text{SO}_4^{2-}/\text{SnO}_2$ electrode than for the SnO_2 electrode (Fig. 3e), indicative of lower charge-transfer resistance. These data suggest that in the structure formed by the $\text{SO}_4^{2-}/\text{SnO}_2$ nanoparticles, the sulfate anions provide a more continuous conductive path between SnO_2 nanoparticles, reducing the particle–particle interfacial resistance. Therefore, the improved electrochemical performance of $\text{SO}_4^{2-}/\text{SnO}_2$ can be ascribed to the following factors. On the one hand, the sulfate anions facilitate a nanoparticle structure that improves the electronic conductivity of active material. On the other hand, the sulfate anion around the active material may provide a buffer-layer to alleviate the volume change during the alloying and dealloying reactions between Sn and Li, and delay the

pulverization to improve the specific capacity.

In Fig. 3f, the initial discharge capacity of $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid is 537 mAh g^{-1} , but after 50 cycles the value decreases to 310 mAh g^{-1} . The Coulombic efficiency for the first cycle is about 91%, but it increases steadily to values exceeding 97%. In comparison, pure SnO_2 powder-based anodes have poor cycling performance with capacity retention of only 126 mAh g^{-1} at the same rate. Then, the incorporation of sulfate anions alleviates this problem. In other words, the sulfate anion also improved the cycle characteristics of Sn.

4. Conclusions

In summary, SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid nanoparticles were synthesized using a facile sol-gel process. When used in LIBs, the $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid material exhibits a high reversible capacity, good rate capability, and excellent cycling stability. The notably enhanced electrochemical performance of the $\text{SO}_4^{2-}/\text{SnO}_2$ can be attributed to the morphological features that provide improved electronic conductivity and reduce the possibility of Sn aggregation, thereby restricting their size increase in reversible reactions. Considering the simple synthetic process and remarkable electrochemical performance, the synthesis method could be extended for producing other metal oxides or solid super acid as anode electrode materials for LIBs.

Acknowledgements

This work was supported by the U.S. Department of Energy, Office of Basic Energy Sciences, under Award Number DE-SC0008662 and Shanghai Municipal Education Commission (High-energy Beam Intelligent Processing and Green Manufacturing).

References

[1] S.M. Hwang, S.Y. Kim, J.-G. Kim, K.J. Kim, J.-W. Lee, M.-S. Park, Y.-J. Kim, M.

Shahabuddin, Y. Yamauchi, J.H. Kim, Electrospun manganese–cobalt oxide hollow nanofibres synthesized via combustion reactions and their lithium storage performance, *Nanoscale*, 7 (2015) 8351-8355.

[2] M. Pramanik, Y. Tsujimoto, V. Malgras, S.X. Dou, J.H. Kim, Y. Yamauchi, Mesoporous Iron Phosphonate Electrodes with Crystalline Frameworks for Lithium-Ion Batteries, *Chem. Mater.*, 27 (2015) 1082-1089.

[3] S.M. Hwang, Y.-G. Lim, J.-G. Kim, Y.-U. Heo, J.H. Lim, Y. Yamauchi, M.-S. Park, Y.-J. Kim, S.X. Dou, J.H. Kim, A case study on fibrous porous SnO₂ anode for robust, high-capacity lithium-ion batteries, *Nano Energy*, 10 (2014) 53-62.

[4] J. Qin, C. He, N. Zhao, Z. Wang, C. Shi, E.-Z. Liu, J. Li, Graphene networks anchored with Sn@ Graphene as lithium ion battery anode, *ACS Nano*, 8 (2014) 1728-1738.

[5] H.-F. Guo, P. Yan, X.-Y. Hao, Z.-Z. Wang, Influences of introducing Al on the solid super acid SO₄²⁻/SnO₂, *Mater. Chem. Phys.*, 112 (2008) 1065-1068.

[6] Y. Wu, L. Qin, G. Zhang, L. Chen, X. Guo, M. Liu, Porous solid superacid SO₄²⁻/Fe²⁺-xZr_x O₃ Fenton catalyst for highly effective oxidation of X-3B under visible light, *Ind. Eng. Chem. Res.*, 52 (2013) 16698-16708.

[7] R. Gutierrez-Baez, J. Toledo-Antonio, M. Cortes-Jácome, P. Sebastian, A. Vázquez, Effects of the SO₄ groups on the textural properties and local order deformation of SnO₂ rutile structure, *Langmuir*, 20 (2004) 4265-4271.

[8] S. Jiang, W. Yue, Z. Gao, Y. Ren, H. Ma, X. Zhao, Y. Liu, X. Yang, Graphene-encapsulated mesoporous SnO₂ composites as high performance anodes for lithium-ion batteries, *J. Mater. Sci.*, 48 (2013) 3870-3876.

- [9] H.B. Wu, J.S. Chen, H.H. Hng, X.W.D. Lou, Nanostructured metal oxide-based materials as advanced anodes for lithium-ion batteries, *Nanoscale*, 4 (2012) 2526-2542.
- [10] Y. Zhao, J. Li, N. Wang, C. Wu, G. Dong, L. Guan, Fully reversible conversion between SnO_2 and Sn in SWNTs@ SnO_2 @ PPy coaxial nanocable as high performance anode material for lithium ion batteries, *The Journal of Physical Chemistry C*, 116 (2012) 18612-18617.
- [11] X.-Y. Xue, B. He, S. Yuan, L.-L. Xing, Z.-H. Chen, C.-h. Ma, SnO_2/WO_3 core-shell nanorods and their high reversible capacity as lithium-ion battery anodes, *Nanotechnology*, 22 (2011) 395702.

Fig. 1. (a) XRD patterns of SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$; TEM images of (b) SnO_2 and (c) $\text{SO}_4^{2-}/\text{SnO}_2$. (d) Infrared spectra of $\text{SO}_4^{2-}/\text{SnO}_2$ without and with adsorbed pyridine; SEM images of (e) SnO_2 and (f) $\text{SO}_4^{2-}/\text{SnO}_2$.

Fig. 2. (a and b) Cyclic voltammograms of the SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid electrodes from the first cycle to the third cycle at a scan rate of 0.1 mV s^{-1} between 0.01 and 3 V. (c) XRD pattern of $\text{SO}_4^{2-}/\text{SnO}_2$ after cycling.

Fig. 3. The discharge-charge profiles of (a) SnO_2 and (b) $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid electrodes at

a current rate of 0.2 C. (c) Multiple rate tests of SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid electrodes with 5 cycles for each step. (d) Impedance spectra of SnO_2 and $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid (e) The magnification of the Nyquist curves. (f) Charge-discharge specific capacity and Coulombic efficiency of $\text{SO}_4^{2-}/\text{SnO}_2$ solid superacid and SnO_2 electrodes cycled at 0.2 C, respectively.